



HAL
open science

In situ liquid transmission electron microscopy reveals self-assembly-driven nucleation in radiolytic synthesis of iron oxide nanoparticles in organic media

Nathaly Ortiz Peña, Dris Ihiawakrim, Sorina Crețu, Geoffrey Cotin, Céline Kiefer, Sylvie Begin-Colin, Clément Sanchez, David Portehault, Ovidiu Ersen

► **To cite this version:**

Nathaly Ortiz Peña, Dris Ihiawakrim, Sorina Crețu, Geoffrey Cotin, Céline Kiefer, et al.. In situ liquid transmission electron microscopy reveals self-assembly-driven nucleation in radiolytic synthesis of iron oxide nanoparticles in organic media. *Nanoscale*, 2022, 14 (30), pp.10950-10957. 10.1039/D2NR01511K . hal-03814318

HAL Id: hal-03814318

<https://hal.science/hal-03814318v1>

Submitted on 13 Oct 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

***In situ* liquid transmission electron microscopy reveals self-assembly-driven nucleation in radiolytic synthesis of iron oxide nanoparticles in organic media**

Nathaly Ortiz Peña,^{1,2} Dris Ihiawakrim,¹ Sorina Crețu,¹ Geoffrey Cotin,¹ Céline Kiefer,¹ Sylvie Begin-Colin,¹ Clément Sanchez,^{3,4} David Portehault,³ Ovidiu Ersen^{1*}

We have investigated the early stages of formation of iron oxide nanoparticles from iron stearate precursors in the presence of sodium stearate in an organic solvent by *in situ* liquid phase transmission electron microscopy (IL-TEM). Before nucleation, we have evidenced the spontaneous formation of vesicular assemblies made of iron polycation-based precursors sandwiched between stearate layers. Nucleation of iron oxide nanoparticles occurs within the walls of the vesicles, which subsequently collapse upon consumption of the iron precursors and growth of the nanoparticles. We then evidenced that fine control of the electron dose, and therefore of the local concentration of reactive iron species in the vicinity of the nuclei, enables controlling crystal growth and selecting the morphology of the resulting iron oxide nanoparticles. Such direct observation of the nucleation process templated by vesicular assemblies in a hydrophobic organic solvent sheds new light on the formation process of metal oxide nanoparticles and therefore opens ways for the synthesis of inorganic colloidal systems with tunable shape and size.

Introduction

Understanding crystallization pathways is crucial to control the size and shape of nanoparticles. This is particularly important the case of the thermal decomposition method developed by Heyon et al.¹ and Sun et al.² to design iron oxide nanoparticles with hand-picked sizes and morphologies. The synthesis consists in the thermal decomposition of a metal precursor (eg., iron stearate, iron oleate or iron pentacarbonyl) in the presence of a surfactant (often oleic acid) in a high boiling point organic solvent.³ The heating rates, reagents and surfactants molar ratio, water content, nature of surfactants and reagents are efficient experimental parameters to reach nano-objects with narrow size distribution and controlled morphology that are promising for the biomedical field,^{4–10} especially as magnetic resonance imaging contrast agents^{11–13} or for hyperthermia cancer treatment.^{14–17} Although there is a good understanding of how a high supersaturation regime drives monodispersity in the heating-up thermal decomposition method,³ the atom-scale and nanoscale mechanisms responsible for the particle size and shape control are mostly a black box. This is especially the case for events occurring before nucleation, the so-called pre-nucleation stage that impacts deeply the kinetics of precursor production, hence the nucleation and growth rates.

In situ liquid TEM complements other *in situ* techniques^{18–22} for probing nucleation and growth stages by providing direct visualization of solid formation in real space, with nanoscale or even atomic scale resolution, and has been already instrumental in deciphering processes of nucleation and growth of solids in liquids.^{23–35} Indeed, beyond the classical nucleation theory that relies on monomer-by-monomer aggregation in a supersaturated solution,^{36–38} a myriad of other mechanisms are now recognized to occur during the formation of various solids in liquids.^{29,39,40} These processes are

coined as non-classical crystallization pathways.^{41,42} They also encompass events occurring during the pre-nucleation stage.^{43,44}

The mechanisms of particle formation by the thermal decomposition method have been mostly inferred from *ex situ* analyses, which are not adapted to assess pre-nucleation processes.⁴⁵ More recently, *in situ* small angle X-ray scattering (SAXS) studies^{5,46} have demonstrated the importance of the pre-nucleation stage by unveiling the assembly of inorganic clusters preceding particle nucleation. The size and concentration of these clusters depend on the precursor-to-surfactant ratio and heating rate, which in turn leads to differences in the onset and rate of nucleation. However, the local structure of the pre-nucleation assemblies and their dynamics are yet to be determined. In an effort to get insights into these assemblies, we have adapted the conditions of synthesis to trigger radiolytic decomposition of an iron precursor in a transmission electron microscope. The present work focuses on unveiling by *in situ* liquid TEM the self-assembly processes that occur during pre-nucleation in radiolysis-induced colloidal synthesis, in conditions close to the thermal decomposition method. We probe the reaction *in situ* by using the electron beam as a trigger, thus allowing to observe processes before and after nucleation.

Results and discussion

We focus here on the decomposition of the iron (II) stearate FeSt_2 ^{47,48} in the presence of 80% of sodium oleate and 20% of oleic acid surfactants in octadecene, conditions that lead *ex situ* to spinel iron oxide nanoplates at ca. 315 °C.^{9,47,49,50} The mixture was first stirred and heated at 120 °C for 1 h without reflux condenser in order to homogenize the solution. Thereafter, one drop was added on the observation window of the *in situ* liquid TEM cell. In this set-up (supp figure), a thin layer of liquid is enclosed between two electron transparent observation windows. In our case, the enclosed liquid

was not heated up within the holder. Therefore, the reaction was triggered by the electron beam. The temperature rise of a liquid irradiated by an electron beam depends on the stopping power of the medium and the thickness of the liquid. We calculated the increase in temperature due to the electron beam to be negligible (see Suppl. info).⁵¹ Therefore, the *in situ* decomposition does not arise from a temperature increase, as in the usual thermal decomposition method,⁵² but relates to radiolytic processes. Although the nucleation and growth *in situ* is beam induced, computational studies^{49,53,54} have pointed out that the decomposition of the precursor into reactive intermediates starts at temperatures close to the homogenization conditions used in our protocol, before *in situ* observations. Thus, upon homogenization and beam irradiation, the reaction medium should contain complexed single iron cations, free iron cations and reduced iron species (Figure 1). Two processes may be at the origin of the decomposition of the precursors: electron beam-induced reduction and direct cleavage of the iron stearate precursor. This protocol yields crystalline spinel iron oxide and metallic iron nanoparticles by the end of the reaction, as demonstrated by high resolution TEM (HRTEM) and selected area electron diffraction (SAED) analyses of the sample recovered after drying (Figure S1).

Figure 2 shows an image sequence acquired at the beginning of the *in situ* reaction using liquid reaction mixture immediately after its homogenization by a heat treatment at 120 °C for 1 h. No nucleus could be detected just after starting the electron irradiation. Nucleation occurs after several minutes (Supporting movie S1). Before nucleation starts, we observe globule-like structures with diameters ranging from ca. 20 to 80 nm (Figure 2). The presence of iron in these globules was confirmed by energy-dispersive spectroscopy (Figure S2). These globules do not contain yet nanoparticles. They exhibit a very dynamic behavior (circles in Figure 2a-g) as they move around in the liquid reaction mixture, deform and undergo coalescence as well as Ostwald-like ripening. Their walls are darker than their cores, suggesting that the iron precursor molecules

are rather localized in the walls. Different from typical beam-induced bubbles,⁵⁵ these globules finally burst to form nuclei and then nanoparticles, observed as dark spots in Figure 2 and Figure 3. Furthermore, when the octadecene without precursors was observed under the same irradiation conditions, any bubbles formed in the media did not present darker more contrasted walls like in the case of the reaction mixture. (Supporting movie S2).

In order to probe the local structure of the globule-like structures and their evolution, we have focused on their dynamic behavior over several minutes before and after nanoparticles appear, hence in the time scale of nucleation (Supporting movie S3 and corresponding snapshots in Figure 3). As already observed in the previous image sequence, objects ranging from 10 to 20 nm in diameter coalesce or collapse and new ones are formed continuously. This behavior is typical of vesicle-like assemblies. The diameter of these globules increases up to several tens of nanometers until they collapse (Figure 2h). A close look to the walls of the vesicles highlights the presence of some more contrasted, darker areas of ca. 1-2 nm, which underlines that nucleation occurs in the walls of the vesicles. Therefore, these vesicles trap in their corona some iron oxo oligomers. Such self-assembled structures are related to lamellar iron soaps observed in aqueous media.⁵⁶ Thus, we hypothesize that such globules could be attributed to self-assembled iron precursors.⁵⁷ This hypothesis is supported by previous works on simulations,^{10,58} which showed that bilayers form by self-assembly of the iron precursors used herein. Iron cations are expected to be located in the center part of these bilayers.^{10,58} Because these hybrid self-assemblies form here in an organic medium, they yield closed spherical entities with vesicular shapes and with iron cations segregated into the walls.⁵⁹ The increase in the number of nuclei in the walls over time destabilizes the vesicles, which then dissociate, releasing nuclei in the continuous medium. These nuclei further aggregate and form nanoparticles. *Ex situ* and cryo-electron microscopy experiments have recently confirmed the presence of iron in similar structures.⁶⁰




Figure 1. Schematic representation of the reaction mixture upon the homogenization step and initial irradiation. The process is expected to go through the formation of complexed single iron ions, free iron ions and reduced species.⁴⁴⁻⁴⁶




Figure 2. (a-g) *In situ* liquid-phase TEM image sequence from a reaction mixture in octadecene. (h) Evolution of the globules diameter within the yellow circle over time. The electron dose used in this experiment was $90 \text{ e}/\text{Å}^2\cdot\text{s}$.

These observations point to a two-steps pre-nucleation/nucleation process⁶¹ taking place for the radiolytically induced formation of iron oxide in organic media. Mechanisms involving self-assembly prior to nucleation have been enlisted to explain the crystallization of proteins, of some organic molecules^{62,63} and of few minerals and metallic nanoparticles.⁶⁴ Although we could not solve the local structure of the inverse vesicle walls, it is instructive to note that the decomposition process involves iron complexes with long chain oleate ligands, which are prone to self-assemble into layered mesophases.^{65–67} Such species could then spontaneously evolve into a vesicular mesophase, thus locating iron cations within the vesicle walls. This hypothesis is in line with the observation that the iron oxide nuclei are forming only in the walls, and not in the core of the reverse vesicles. Our observations clearly indicate the presence of globule-like structures prior the nucleation burst. We provide thus direct evidence of the self-organization of the iron precursors in the pre-nucleation step. Furthermore, we reveal the formation and accumulation of nuclei within the restrained volume of globule's walls. Such inverse vesicles-like structures had been intuited from *in situ* x-ray absorption and mass spectrometry studies that have shown evidence of poly-oxo-iron bridges at the pre-nucleation stage in a heating-up synthesis.⁶⁰ The fact that we directly observe this

phenomenon from radiolytic synthesis shows that at least the pre-nucleation and nucleation stages are similar, whatever the stimulus used for the decomposition of iron precursors.

To further understand the subsequent course of the nanoparticles formation, we have evaluated the impact of the electron dose on the radiolytic decomposition synthesis. In fact, it has already been observed that the electron dose may provide a direct control on the formation kinetics and on the morphology of Au, Ag, Pt and mixed oxides from aqueous solutions.^{69–74} First, we have used the conventional TEM mode to provide a high electron dose, since the observation area is continuously irradiated. With a beam current of 150 pA, the electron dose is about $9400 \text{ e}^-/\text{nm}^2\cdot\text{s}$. In these conditions, the formation of the nanoparticles is very fast: nucleation takes place in less than 10 s as evidenced in **Figure 4 (Supporting movie S4)**. Rapidly, the nuclei grow until reaching a critical radius. The particle size stabilizes at this critical radius (**Figure 4b**), then growth continues before the particle reaches a second plateau corresponding to the final particle size. It should be noted that with this amount of electron dose and energy input, neither the morphology nor the size distribution can be controlled.




Figure 3. *In situ* TEM images sequence of the reaction mixture in octadecene. The ovals and arrows highlight the walls of the vesicles where the nuclei form. The electron dose used in this experiment was $90 \text{ e}/\text{Å}^2\cdot\text{s}$.

In a second set of conditions, the electron dose was decreased to a value of $6900 \text{ e}/\text{nm}^2\cdot\text{s}$ in TEM mode, almost a third less than in the previous conditions, in order to delay the nucleation step (Figure 5, Supporting movie S5). Contrary to the observations made with higher electron dose (Figure 4), the pre-nucleation vesicles are detected (Figure 5a-e). The nanoparticles released by collapsing vesicles tend to further aggregate in order to form large particles (Figure 5f-h), possibly by oriented attachment growth already evidenced for iron oxides.²⁹

In a third set of exposure conditions, the electron dose used was $2500 \text{ e}/\text{nm}^2\cdot\text{s}$ in TEM mode. We have then been able to monitor the

size evolution of two nanoparticles over time (Figure 6 and Supporting movie S6). Three regimes are observed (Figure 6g): i) in the first one, the size of the nanoparticles is increasing; ii) the second region shows a relative stability of the particle sizes; iii) in the last stage, the size of small nanoparticles decreases at the benefit of larger particles. This observation could account for the Ostwald ripening mechanism caused by the change in solubility of nanoparticles dependent on their size. Due to the high surface energy of smaller particles, they have a high solubility and re-dissolve within the solution, which allows in turn the larger particles to further grow.³⁹




Figure 4. (a-f) *In situ* image sequence of the evolution of iron oxide nanoparticles in octadecene recorded under an electron dose of $9400 \text{ e}/\text{nm}^2\cdot\text{s}$. (g) Evolution of the size of one nanoparticle (white arrow) upon time. It is possible to identify the different formation regimes, from the nucleation burst until the critical size around 25 nm after which growth continues until reaching the final size of around 60 nm.




Figure 5. a-h) *In situ* TEM sequence using an electron dose of $6900 \text{ e}^-/\text{nm}^2\cdot\text{s}$. i) Schematic representation of the nucleation within a vesicle. The nucleation takes place in the walls of the vesicle, then the particles release upon vesicle collapse aggregate and form larger nanoparticles.

In a last set of illumination conditions, we have used the scanning TEM (STEM) mode for which the beam irradiation conditions are very different, in terms of total electron dose and image acquisition protocol. In this case, even after two hours of electron beam irradiation, the reaction does not take place. This can be explained by the fact that the energy provided by the electron probe during the rastering of the area of interest is rapidly dissipated and therefore insufficient to exceed the threshold required for the decomposition reaction of iron stearate. Thusly, to trigger the reaction, we used the spot mode, in which the beam is focused and blocked for a while (generally few seconds) at a unique position. Hence, this mode allows

concentrating the energy input at a chosen location, in the center of the observation area. Thanks to this highly concentrated beam on a small area (tens of pm),⁷⁵ it was possible to trigger the reaction. In addition, this mode provides a fine control of the beam current and then of the energy input and of its impact on the formation of the nanoparticles and on their final morphologies. When the electron dose was $900 \text{ e}^-/\text{nm}^2\cdot\text{s}$ (Figure 7), the nanoparticle grew into an isotropic, faceted polyhedral morphology (Supporting movie S7). In contrast, at a lower dose of $230 \text{ e}^-/\text{nm}^2\cdot\text{s}$, anisotropic growth was observed (Supporting movie S8).




Figure 6. a-f) Images sequence from a video acquired by *in situ* liquid-phase TEM under an electron dose of $2500 \text{ e}^-/\text{nm}^2\cdot\text{s}$, for monitoring the size evolution of two neighbouring nanoparticles NP1 and NP2. g) Evolution of NP1 (in red in the first image) particle size upon time. Nuclei under the critical size re-dissolve in the solution, probably in favour of the growth of other surrounding particles.




Figure 7. *In situ* scanning TEM analysis of the radiolytic growth of iron oxide particles induced by electron irradiation using an electron dose of 900 e⁻/nm²-s (a-b) and of 230 e⁻/nm²-s (c-d). The influence of the amount of energy provided by the electron beam on the growth of nanoparticles is schematized in (e). With a higher electron dose, the nanoparticles tend to be polyhedral and spherical; using lower electron doses, a faceting effect is unambiguously observed.

Contrary to the observations in TEM mode, the STEM mode enables triggering the nanoparticle nucleation and growth only in the focused electron beam area, so that the observed nanoparticles evolution can be ascribed only to the objects within the observation area. Therefore, we can hypothesize that in the lowest dose conditions, the amount of reactive species produced is low, so that the nanoparticle growth rate is limited by the flux of reagents and the depletion of monomers near the growing nanoparticles.⁷⁶ In these conditions, the difference of reactivity of the various crystal facets is exacerbated and yields anisotropic nano-objects. On the other side, a large energy input (provided either by the electron beam or by the thermal energy) generates larger amounts of monomers, so that the growth rates of the different facets are levered, yielding isotropic particles. The fact that the nanoparticles morphology can be tailored as a function of the energy input, without varying the nature of the capping agents, opens exciting paths in the development of nanoparticles with very specific and well identified morphology, possibly by using radiolytic synthesis.^{73,74} Complementary insight has been achieved as well by correlating different characterization, both *in situ* and post-mortem in similar systems, in a recent publication.⁶⁰

Experimental

Materials

All chemicals were purchased from Sigma-Aldrich and used as received.

Iron oleate reaction mixture preparation

The reaction mixtures used in these experiments were the ones usually employed for thermal decomposition synthesis of iron oxide Fe_{3-x}O₄ nanoparticles in organic media. First, 2.32 mmol of iron stearate were mixed with 3 mmol of the ligands, oleic acid and sodium oleate, in 15 mL octadecene used as a solvent. The mixture was stirred and heated at 120 °C for 60 min without reflux condenser in order to dissolve the reactants and remove the water residues.

In situ liquid TEM and STEM observations and post-mortem analysis

For *in situ* liquid TEM analysis, a Protochips liquid cell holder (Poseidon Select 550) was used. It consists of disposable silicon chips onto which the sample is deposited. Experiments were performed in a corrected JEOL 2100F/Cs (S)TEM at 200 kV. Selected area electron diffraction (SAED) analysis were performed post *in situ* over the dry e-chips.

Conclusions

In situ liquid-phase transmission electron microscopy allowed triggering by radiolysis and tracking in real space and in real time with nanometre resolution, the formation of iron oxide nanoparticles from a thermal decomposition reaction mixture. We provide evidences that the reaction, especially the pre-nucleation step, follows a non-classical crystallization route, through the formation of elusive and dynamic inverse vesicular-like assemblies with the iron precursor confined within the walls. Nucleation occurs within the walls of the vesicles where the subsequent accumulation of the nuclei agrees with a soft-templating nucleation and growth process. After a significant increase of the size of the inorganic nuclei, the vesicles collapse and release nuclei into the continuous medium. By scrutinizing the effect of the energy input through the electron dose,

we have observed a strong impact of the electron dose on the morphology of the nanoparticles, which we attribute to different regimes of growth depending on the local concentration of reactive iron species near the growing particles and the stability of vesicles. This work contributes not only to the comprehension of formation mechanism of iron oxide nanoparticles by an electron beam but we hope it helps in the overall understanding of the nanometric process taking place probably in thermal decomposition synthesis as well.

Conflicts of interest

There are no conflicts to declare.

Acknowledgements

This work was supported by the French National Agency for Research (ANR) under the project InSiChem ANR-16-CE05- 0011 and by the USIAS chair of Prof. Clément Sanchez.

Notes and references

- 1 J. Park, K. An, Y. Hwang, J.-G. Park, H.-J. Noh, J.-Y. Kim, J.-H. Park, N.-M. Hwang and T. Hyeon, *Nat. Mater.*, 2004, **3**, 891–895.
- 2 S. Sun and H. Zeng, *J. Am. Chem. Soc.*, 2002, **124**, 8204–8205.
- 3 S. G. Kwon and T. Hyeon, *Small*, 2011, **7**, 2685–2702.
- 4 M. V. Kovalenko, M. I. Bodnarchuk, R. T. Lechner, G. Hesser, F. Schäffler and W. Heiss, *J. Am. Chem. Soc.*, 2007, **129**, 6352–6353.
- 5 A. Lassenberger, T. A. Grünwald, P. D. J. Van Oostrum, H. Rennhofer, H. Amenitsch, R. Zirbs, H. C. Lichtenegger and E. Reimhult, *Chem. Mater.*, 2017, **29**, 4511–4522.
- 6 J. Park, K. An, Y. Hwang, J. E. G. Park, H. J. Noh, J. Y. Kim, J. H. Park, N. M. Hwang and T. Hyeon, *Nat. Mater.*, 2004, **3**, 891–895.
- 7 R. Hufschmid, H. Arami, R. M. Ferguson, M. Gonzales, E. Teeman, L. N. Brush, N. D. Browning and K. M. Krishnan, *Nanoscale*, 2015, **7**, 11142–11154.
- 8 W. Baaziz, B. P. Pichon, S. Fleutot, Y. Liu, C. Lefevre, J. M. Greneche, M. Toumi, T. Mhiri and S. Begin-Colin, *J. Phys. Chem. C*, 2014, **118**, 3795–3810.
- 9 A. Walter, C. Billotey, A. Garofalo, C. Ulhaq-Bouillet, C. Lefèvre, J. Taleb, S. Laurent, L. Vander Elst, R. N. Muller, L. Lartigue, F. Gazeau, D. Felder-Flesch and S. Begin-Colin, *Chem. Mater.*, 2014, **26**, 5252–5264.
- 10 G. Cotin, C. Kiefer, F. Pertion, M. Boero, B. Özdamar, A. Bouzid, G. Ori, C. Massobrio, D. Begin, B. Pichon, D. Mertz and S. Begin-Colin, *ACS Appl. Nano Mater.*, 2018, **1**, 4306–4316.
- 11 L. Lartigue, P. Hugounenq, D. Alloyeau, S. P. Clarke, M. Lévy, J. C. Bacri, R. Bazzi, D. F. Brougham, C. Wilhelm and F. Gazeau, *ACS Nano*, 2012, **6**, 10935–10949.
- 12 A. Boni, A. M. Basini, L. Capolupo, C. Innocenti, M. Corti, M. Cobianchi, F. Orsini, A. Guerrini, C. Sangregorio and A. Lascialfari, *RSC Adv.*, 2017, **7**, 44104–44111.
- 13 L. Li, W. Jiang, K. Luo, H. Song, F. Lan, Y. Wu and Z. Gu, *Theranostics*, 2013, **3**, 595–615.
- 14 A. Espinosa, R. Di Corato, J. Kolosnjaj-Tabi, P. Flaud, T. Pellegrino and C. Wilhelm, *ACS Nano*, 2016, **10**, 2436–2446.
- 15 M. Bañobre-López, A. Teijeiro and J. Rivas, *Reports Pract. Oncol. Radiother.*, 2013, **18**, 397–400.
- 16 C. Martinez-Boubeta, K. Simeonidis, A. Makridis, M. Angelakeris, O. Iglesias, P. Guardia, A. Cabot, L. Yedra, S. Estradé, F. Peiró, Z. Saghi, P. A. Midgley, I. Conde-Leborán, D. Serantes and D. Baldomir, *Sci. Rep.*, 2013, **3**, 1–8.
- 17 C. Blanco-Andujar, A. Walter, G. Cotin, C. Bordeianu, D. Mertz, D. Felder-Flesch and S. Begin-Colin, *Nanomedicine (Lond)*, 2016, **11**, 1889–1910.
- 18 P. J. M. Smeets, A. R. Finney, W. J. E. M. Habraken, F. Nudelman, H. Friedrich, J. Laven, J. J. De Yoreo, P. M. Rodger and N. A. J. M. Sommerdijk, *Proc. Natl. Acad. Sci. U. S. A.*, 2017, **114**, E7882–E7890.
- 19 B. Fleury, M. A. Neouze, J. M. Guigner, N. Menguy, O. Spalla, T. Gacoin and D. Carriere, *ACS Nano*, 2014, **8**, 2602–2608.
- 20 S. L. P. Wolf, L. Caballero, F. Melo and H. Cölfen, *Langmuir*, 2017, **33**, 158–163.
- 21 J. Baumgartner, R. K. Ramamoorthy, A. P. Freitas, M.-A. Neouze, M. Bennet, D. Faivre and D. Carriere, *Nano Lett.*, 2020, **20**, 5001–5007.
- 22 J. Baumgartner, A. Dey, P. H. H. Bomans, C. Le Coadou, P. Fratzl, N. A. J. M. Sommerdijk and D. Faivre, *Nat. Mater.*, 2013, **12**, 310–314.
- 23 J. J. De Yoreo, *Prog. Cryst. Growth Charact. Mater.*, 2016, **62**, 69–88.
- 24 M. H. Nielsen, D. Li, H. Zhang, S. Aloni, T. Y.-J. Han, C. Frandsen, J. Seto, J. F. Banfield, H. Cölfen and J. J. De Yoreo, *Microsc. Microanal.*, 2014, **20**, 425–436.
- 25 M. M. Longuinho, V. Ramnarain, N. Ortiz Peña, D. Ihiawakrim, R. Soria-Martínez, M. Farina, O. Ersen and A. L. Rossi, *CrystEngComm*, 2022, **24**, 2602–2614.
- 26 W. Dachraoui, D. Keller, T. R. Henninen, O. J. Ashton and R. Erni, *Nano Lett.*, 2021, **21**, 2861–2869.
- 27 T. R. Henninen, D. Keller and R. Erni, *ChemNanoMat*, 2021, **7**, 110–116.
- 28 G. Zhu, H. Reiner, H. Cölfen and J. J. De Yoreo, *Micron*, 2019, **118**, 35–42.

- 29 J. J. De Yoreo, P. U. P. A. Gilbert, N. A. J. M. Sommerdijk, R. L. Penn, S. Whitelam, D. Joester, H. Zhang, J. D. Rimer, A. Navrotsky, J. F. Banfield, A. F. Wallace, F. M. Michel, F. C. Meldrum, H. Cölfen and P. M. Dove, *Science (80-.)*, 2015, **349**, aaa6760.
- 30 H. Zheng, R. K. Smith, Y. W. Jun, C. Kisielowski, U. Dahmen and A. Paul Alivisatos, *Science (80-.)*, 2009, **324**, 1309–1312.
- 31 M. R. Hauwiler, X. Zhang, W. I. Liang, C. H. Chiu, Q. Zhang, W. Zheng, C. Ophus, E. M. Chan, C. Czarnik, M. Pan, F. M. Ross, W. W. Wu, Y. H. Chu, M. Asta, P. W. Voorhees, A. P. Alivisatos and H. Zheng, *Nano Lett.*, 2018, **18**, 6427–6433.
- 32 H. G. Liao, L. Cui, S. Whitelam and H. Zheng, *Science (80-.)*, 2012, **336**, 1011–1014.
- 33 A. S. Kashin and V. P. Ananikov, *Nat. Rev. Chem.*, 2019, **3**, 624–637.
- 34 N. Bhattarai, D. L. Woodall, J. E. Boercker, J. G. Tischler and T. H. Brintlinger, *Nanoscale*, 2019, **11**, 14573–14580.
- 35 W. Dachraoui, T. R. Henninen, D. Keller and R. Erni, *Sci. Rep.*, 2021, **11**, 1–10.
- 36 D. B. K. Chu, J. S. Owen and B. Peters, *J. Phys. Chem. A*, 2017, **121**, 7511–7517.
- 37 V. K. LaMer and R. H. Dinegar, *J. Am. Chem. Soc.*, 1950, **72**, 4847.
- 38 H. Mehranpour, M. Askari and M. Sasani Ghamsari, in *I.R. Iran*, 2012, pp. 1710–1712.
- 39 N. T. K. Thanh, N. Maclean and S. Mahiddine, *Chem. Rev.*, 2014, **114**, 7610–7630.
- 40 J. Lee, J. Yang, S. G. Kwon and T. Hyeon, *Nat. Rev. Mater.*, 2016, **1**, 16034.
- 41 H. Cölfen and M. Antonietti, *Mesocrystals and Nonclassical Crystallization*, John Wiley & Sons, Ltd, Chichester, UK, 1st edn., 2008.
- 42 Z. Ou, Z. Wang, B. Luo, E. Luijten and Q. Chen, *Nat. Mater.*, 2020, **19**, 450–455.
- 43 D. Gebauer, M. Kellermeier, J. D. Gale, L. Bergström and H. Cölfen, *Chem. Soc. Rev.*, 2014, **43**, 2348–2371.
- 44 W. J. E. M. Habraken, J. Tao, L. J. Brylka, H. Friedrich, L. Bertinetti, A. S. Schenk, A. Verch, V. Dmitrovic, P. H. H. Bomans, P. M. Frederik, J. Laven, P. van der Schoot, B. Aichmayer, G. de With, J. J. DeYoreo and N. A. J. M. Sommerdijk, *Nat. Commun.*, 2013, **4**, 1507.
- 45 W. Wu, Z. Wu, T. Yu, C. Jiang and W.-S. Kim, *Sci. Technol. Adv. Mater.*, 2015, **16**, 023501.
- 46 Y. Tan, D. Sun, H. Yu, S. Jiao, Y. Gong, S. Yan, Z. Chen, X. Xing, G. Mo, Q. Cai and Z. Wu, *J. Phys. Chem. C*, 2018, **122**, 16397–16405.
- 47 G. Cotin, F. Pertont, C. Petit, S. Sall, C. Kiefer, V. Begin, B. Pichon, C. Lefevre, D. Mertz, J. M. Greneche and S. Begin-Colin, *Chem. Mater.*, 2020, **32**, 9245–9259.
- 48 F. Pertont, Université de Strasbourg, 2019.
- 49 G. Cotin, C. Kiefer, F. Pertont, M. Boero, B. Özdamar, A. Bouzid, G. Ori, C. Massobrio, D. Begin, B. Pichon, D. Mertz and S. Begin-Colin, *ACS Appl. Nano Mater.*, 2018, **1**, 4306–4316.
- 50 G. Cotin, C. Kiefer, F. Pertont, D. Ihiawakrim, C. Blanco-Andujar, S. Moldovan, C. Lefevre, O. Ersen, B. Pichon, D. Mertz and S. Bégin-Colin, *Nanomaterials*, 2018, **8**, 881.
- 51 N. M. Schneider, in *Liquid Cell Electron Microscopy*, Cambridge University Press, 2017, pp. 140–163.
- 52 G. K. Soon, Y. Piao, J. Park, S. Angappane, Y. Jo, N. M. Hwang, J. G. Park and T. Hyeon, *J. Am. Chem. Soc.*, 2007, **129**, 12571–12584.
- 53 S. Palchoudhury, W. An, Y. Xu, Y. Qin, Z. Zhang, N. Chopra, R. A. Holler, C. H. Turner and Y. Bao, *Nano Lett.*, 2011, **11**, 1141–1146.
- 54 A. López-Cruz and G. E. López, *Mol. Phys.*, 2009, **107**, 1799–1804.
- 55 J. M. Grogan, N. M. N. M. Schneider, F. M. Ross and H. H. Bau, *Nano Lett.*, 2014, **14**, 359–64.
- 56 R. Corkery, Australian National University, 1998.
- 57 H. Kunieda, K. Nakamura, M. R. Infante and C. Solans, *Adv. Mater.*, 1992, **4**, 291–293.
- 58 B. Özdamar, A. Bouzid, G. Ori, C. Massobrio and M. Boero, *J. Chem. Theory Comput.*, 2018, **14**, 225–235.
- 59 F. Evans and H. Wennerström, *The colloidal domain where physics, chemistry, biology and technology meet*, Wiley-VCH, USA, 2nd edn., 1999.
- 60 G. Cotin, B. Heinrich, F. Pertont, C. Kiefer, G. Francius, D. Mertz, B. Freis, B. Pichon, J. Strub, S. Cianféroni, N. Ortiz Peña, D. Ihiawakrim, D. Portehault, O. Ersen, A. Khammari, M. Picher, F. Banhart, C. Sanchez and S. Begin-Colin, *Small*, 2022, **2200414**, 2200414.
- 61 P. G. Vekilov, *Cryst. Growth Des.*, 2010, **10**, 5007–5019.
- 62 P. G. Vekilov, *Cryst. Growth Des.*, 2004, **4**, 671–685.
- 63 A. Sauter, F. Roosen-Runge, F. Zhang, G. Lotze, R. M. J. Jacobs and F. Schreiber, *J. Am. Chem. Soc.*, 2015, **137**, 1485–1491.
- 64 Y. Mikhlin, A. Karacharov, M. Likhatski, T. Podlipskaya, Y. Zubavichus, A. Veligzhanin and V. Zaikovski, *J Colloid Interface Sci*, 2011, **362**, 330–336.
- 65 C. V. Nikiforidis, E. P. Gilbert and E. Scholten, *RSC Adv.*, 2015, **5**, 47466–47475.

- 66 M. Delample, F. Jérôme, J. Barrault and J. P. Douliez, *Green Chem.*, 2011, **13**, 64–68.
- 67 C. Larquet, D. Carriere, A. M. Nguyen, T. K. C. Le, X. Frogneux-Plé, I. Géniois, P. Le Griel, A. Gauzzi, C. Sanchez and S. Carencio, *Chem. Mater.*, 2020, **32**, 1131–1139.
- 68 Y. Wu, X. Chen, C. Li, J. Fang and H. Liu, *New J. Chem.*, 2019, **43**, 12548–12554.
- 69 M. Ge, M. Lu, Y. Chu and H. Xin, *Sci. Rep.*, 2017, **7**, 16420.
- 70 D. Alloyeau, W. Dachraoui, Y. Javed, H. Belkahla, G. Wang, H. Lecoq, S. Ammar, O. Ersen, A. Wisnet, F. Gazeau and C. Ricolleau, *Nano Lett.*, 2015, **15**, 2574–2581.
- 71 V. Beermann, M. E. Holtz, E. Padgett, J. F. de Araujo, D. A. Muller and P. Strasser, *Energy Environ. Sci.*, 2019, **12**, 2476–2485.
- 72 T. J. Woehl, J. E. Evans, I. Arslan, W. D. Ristenpart and N. D. Browning, *ACS Nano*, 2012, **6**, 8599–8610.
- 73 M. Mirdamadi-Esfahani, M. Mostafavi, B. Keita, L. Nadjjo, P. Kooyman and H. Remita, *Gold Bull.*, 2010, **43**, 49–56.
- 74 W. Abidi, P. R. Selvakannan, Y. Guillet, I. Lampre, P. Beaunier, B. Pansu, B. Palpant and H. Remita, *J. Phys. Chem. C*, 2010, **114**, 14794–14803.
- 75 H. Sawada, N. Shimura, F. Hosokawa, N. Shibata and Y. Ikuhara, *Microscopy*, 2015, **64**, 213–217.
- 76 R. Kröger and A. Verch, *Minerals*, 2018, **8**, 21.

SUPPORTING INFORMATION

In situ liquid transmission electron microscopy reveals self-assembly-driven nucleation in radiolytic synthesis of iron oxide nanoparticles in organic media




Figure S1. HRTEM images (a-c and e) and corresponding SAED pattern of c and e (d and f respectively) of nanoparticles of iron oxide spinel and metallic iron nanoparticles obtained by *in situ* liquid-phase radiolytic decomposition within the transmission electron microscope. These particles are analyzed *post mortem*, after blanking the electron beam and drying the *in situ* cell out of the microscope. The Selected Area Electron Diffraction pattern is indexed along a typical iron oxide spinel and metallic iron nanoparticles structure. Fe may arise from reduction under the electron beam.




Figure S2. Energy dispersive spectrum obtained during the *in situ* experiment depicted in Figure 2. The signature K α of iron was detected at 6.40 keV.

MAXIMUM TEMPERATURE RISE CALCULATION DUE TO THE ELECTRON BEAM¹

$$\Delta T_{max} = \frac{S 10^2}{\pi \alpha_{th} C_p} I \left(1 + \frac{t}{\lambda} \right) \left(\frac{1}{4} + \frac{1}{2} \ln \left[\frac{L}{a} \right] \right)$$

I = beam current; a = beam radius; t = thickness; L = Window size; λ = Mean free path

Parameter	Water	Organic solvent
S = stopping power (MeV cm ² g ⁻¹) (200 kV)	2.79 ²	2.99 (paraffin wax) ²
C _p = specific heat at constant pressure (J mol ⁻¹ K ⁻¹) (300 K)	75.28	564.4 (octadecane) ³
α_{th} = thermal diffusivity (10 ⁻⁶ m ² s ⁻¹) (300 K)	0.148 ⁴	0.06 (octadecane) ⁵

Hence,

$$\Delta T_{max-Water} < 4 K$$

$$\Delta T_{max-Octadecane} < 10 K$$

Supporting movie S1. Decomposition of the iron (II) stearate FeSt_2 in 80% of sodium oleate and 20% of oleic acid surfactants in octadecene. No nuclei are initially observed. Apparition of vesicle-like structures.

Supporting movie S2. Octadecene under irradiation.

Supporting movie S3. Dynamic interaction of vesicles upon irradiation. Apparition of nuclei upon bursting of the vesicles.

Supporting movie S4. Nucleation and growth under TEM illumination at a high electron dose of $9400 \text{ e}^-/\text{nm}^2\cdot\text{s}$.

Supporting movie S5. Nucleation and growth under TEM illumination at a medium electron dose of $6900 \text{ e}^-/\text{nm}^2\cdot\text{s}$.

Supporting movie S6. Nucleation and growth under TEM illumination at a low electron dose of $2500 \text{ e}^-/\text{nm}^2\cdot\text{s}$.

Supporting movie S7. Nucleation and growth under STEM illumination at a low electron dose of $900 \text{ e}^-/\text{nm}^2\cdot\text{s}$.

Supporting movie S8. Nucleation and growth under STEM illumination at a low electron dose of $230 \text{ e}^-/\text{nm}^2\cdot\text{s}$.

REFERENCES

- (1) Schneider, N. M. Electron Beam Effects in Liquid Cell TEM and STEM. In *Liquid Cell Electron Microscopy*; Cambridge University Press, 2017; pp 140–163.
- (2) Berger, M. J.; Seltzer, S. M. *Stopping Powers and Ranges of Electrons and Positrons*; 1983.
- (3) U.S. Secretary of Commerce on behalf of the United States of America. Octadecane <https://webbook.nist.gov/cgi/cbook.cgi?ID=C593453&Units=SI&Mask=FFF> (accessed Oct 14, 2019).
- (4) Water - Thermal Diffusivity https://www.engineeringtoolbox.com/water-steam-thermal-diffusivity-d_2058.html (accessed Oct 14, 2019).
- (5) Vélez, C.; Khayet, M.; Ortiz De Zárate, J. M. Temperature-Dependent Thermal Properties of Solid/Liquid Phase Change Even-Numbered n-Alkanes: N-Hexadecane, n-Octadecane and n-Eicosane. *Appl. Energy* **2015**, *143*, 383–394.