



Polar Layered Intermetallic LaCo₂P₂ as a Water Oxidation Electrocatalyst

Dallas K Mann, Aida M Díez, Junyuan Xu, Oleg I Lebedev, Yury V Kolen'ko,
Michael Shatruk

► To cite this version:

Dallas K Mann, Aida M Díez, Junyuan Xu, Oleg I Lebedev, Yury V Kolen'ko, et al.. Polar Layered Intermetallic LaCo₂P₂ as a Water Oxidation Electrocatalyst. ACS Applied Materials & Interfaces, 2022, 14 (12), pp.14120 - 14128. <10.1021/acsami.1c19858>. <hal-03815263>

HAL Id: hal-03815263

<https://hal.science/hal-03815263v1>

Submitted on 14 Oct 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



HAL Authorization

Polar Layered Intermetallic LaCo_2P_2 as a Water Oxidation Electrocatalyst

Dallas K. Mann, Aida M. Díez, Junyuan Xu, Oleg I. Lebedev, Yury V. Kolen'ko,* and Michael Shatruk*



Cite This: *ACS Appl. Mater. Interfaces* 2022, 14, 14120–14128



Read Online

ACCESS |



Metrics & More




Article Recommendations



Supporting Information

ABSTRACT: We investigate LaCo_2P_2 as an electrocatalytic material for oxygen evolution reaction (OER) under alkaline and acidic conditions. This layered intermetallic material was prepared *via* Sn-flux high-temperature annealing. The electrocatalytic ink, prepared with the ball-milled LaCo_2P_2 catalyst at the mass loading of 0.25 mg/cm^2 , shows OER activity at $\text{pH} = 14$, reaching current densities of 10, 50, and 100 mA/cm^2 under the overpotential of 400, 440, and 460 mV, respectively. Remarkably, the electrocatalytic performance remains constant for at least 4 days. Transmission electron microscopy reveals the formation of a catalytically active CoO_x shell around the pre-catalyst LaCo_2P_2 core during the alkaline OER. The core serves as a robust support for the *in situ*-formed electrocatalytic system. Similar studies under $\text{pH} = 0$ reveal the rapid deterioration of LaCo_2P_2 , with the formation of LaPO_4 and amorphous cobalt oxide. This study shows the viability of layered intermetallics as stable OER electrocatalysts, although further developments are required to improve the electrocatalytic performance and increase the stability at lower pH values.

KEYWORDS: core–shell, electrocatalysis, intermetallic, oxygen evolution reaction, precatalyst, water oxidation



INTRODUCTION

The growing worldwide need for clean energy technologies, aiming to replace rapidly depleting and environmentally harmful fossil fuels, has been driving extensive research efforts into the viability of a hydrogen fuel economy. The centerpiece of these efforts is the decomposition of water into the constituent elements.¹ The overall water-splitting reaction can be divided into two half-reactions known as hydrogen evolution reaction (HER) and oxygen evolution reaction (OER). In practice, however, these electrochemical processes suffer from a large overpotential, defined as the difference between the experimental and thermodynamic values of the electrochemical potential required to drive the water electrolysis reaction. The overpotential is caused by substantial kinetic barriers associated with the two-electron HER and especially with the four-electron OER mechanisms.^{2,3} A broad range of electro- and photocatalysts has been investigated to address this problem.^{4,5} The state-of-the-art electrocatalysts, such as RuO_2 and IrO_2 , have afforded a substantial decrease in the OER overpotential,⁶ but their use is not sustainable, given the scarcity and high cost of the platinum group metals.^{7–9} In recent years, extensive research efforts have been devoted to the discovery of sustainable electrocatalysts based on 3d metal hydroxides, oxyhydroxides, and oxides,^{4,10–14} chalcogenides,^{15–17} phosphides,^{18–23} and borides.^{24,25}

The challenge in developing efficient electrocatalysts based on 3d metal compounds stems from the decomposition of such materials under conditions of electrocatalysis in acidic electrolytes. As a result, examples of such electrocatalysts

that can operate under acidic OER conditions even for a few hours, without the loss of performance, are extremely rare. Among the materials mentioned above, transition-metal phosphides (TMPs) and transition-metal borides (TMBs) are well known to show high stability toward acids, in the absence of applied voltage, while OER activity in alkaline solutions has been demonstrated for several binaries, such as CoP , Ni_2P , NiP_2 , FeB , Co_2B , and Ni_2B .^{26–31} Hence, TMPs and TMBs offer appealing alternatives to the more extensively studied OER electrocatalysts based on 3d metal hydroxides, oxyhydroxides, and oxides.³²

Recently, we have reported a promising performance by AlFe_2B_2 in alkaline OER electrocatalysis.²⁹ Our studies revealed that AlFe_2B_2 acts as a precatalyst by governing the formation of a thick and very stable shell of catalytically active Fe_3O_4 nanoparticles around the particles of AlFe_2B_2 . Remarkably, this material far outperformed stand-alone Fe_3O_4 nanoparticles by showing a substantially higher long-term stability, faster reaction kinetics, and a lower overpotential in the electrocatalytic OER in a 1 M KOH electrolyte. Interestingly, AlFe_2B_2 also showed much better catalytic properties as compared to the Al-free FeB counterpart. We

Received: October 14, 2021

Accepted: February 22, 2022

Published: March 15, 2022






Figure 1. Side-by-side comparison of the crystal structures of AlFe₂B₂ (a) and LaCo₂P₂ (b).

attributed this improved performance to the crystal structure of AlFe₂B₂, in which layers of Al atoms alternate with [Fe₂B₂] slabs (Figure 1a). The catalytically inactive Al layer provides additional structural stability and increased electrical conductivity within the structure, thus improving the electron-transfer kinetics and longevity of the catalytic system. At the onset of the OER, the surface layers of AlFe₂B₂ undergo reconstruction due to the partial etching of the Al layers by 1 M KOH and electro-oxidation of the [Fe₂B₂] slabs to the shell of Fe₃O₄ nanoparticles. Nevertheless, the remaining AlFe₂B₂ precatalyst core provides an excellent structural support and improved electron-transfer rate between the underlying electrode and the catalytically active oxide shell.

Despite its excellent performance in the alkaline electrocatalytic OER, AlFe₂B₂ is not stable under acidic conditions.^{33–35} In contrast, many ternary phosphides with related layered structures (Figure 1b) are known to exhibit high stability toward acids.³⁶ Building on this knowledge, we have decided to explore the use of such structures in both acidic and alkaline water oxidation. Herein, we report a study of OER electrocatalysis on LaCo₂P₂, which was previously investigated by us and a few other research groups as an interesting ferromagnetic material with the ordering temperature of 132 K.^{37–40} We demonstrate that, despite its high general stability in acidic environment, this material quickly deteriorates once the voltage is applied to drive the OER at pH = 0. On the other hand, it acts as a stable OER precatalyst at pH = 14, showing only a slightly higher overpotential but similar electrochemical kinetics as compared to the reported performance of binary CoP. We also discuss the possible reasons for our observations and strategies to improve the stability and electrocatalytic performance of layered-structure TMPs.

MATERIALS AND METHODS

Starting Materials. All manipulations during sample preparation were carried out in an Ar-filled dry box (content of O₂ < 0.5 ppm). A lanthanum rod (≥99.9%), cobalt powder (99.9%), phosphorus powder (99.9%), tin powder (99.85%), and concentrated hydrochloric acid (36.5–38.0%) were obtained from VWR. The lanthanum rod was filed to powder immediately before the reaction. Cobalt powder was additionally purified by heating in a flow of H₂ gas at 500 °C for 5 h. Nafion ionomer solution (5% in aliphatic alcohols and water) and platinum wire (99.9%) were acquired from Sigma-Aldrich, while the IrO₂ (99.99%, #43396) reference material was purchased from Alfa Aesar. Ultrapure water (18.2 MΩ cm⁻²) was produced using a Milli-Q Advantage A10 system (Millipore). For electrolyte preparation, purified NaOH (98.5%) from Acros Organics and H₂SO₄ (95–98%) from Sigma-Aldrich were used.

Synthesis. LaCo₂P₂ was synthesized according to the previously reported Sn-flux method.³⁷ The starting materials were mixed in the La/Co/P/Sn = 1.6:2:2:20 ratio (the total mass = 2 g) and sealed in a fused silica tube of 10 mm inner diameter under vacuum (≈10⁻⁴ mbar). The mixture was annealed at 880 °C for 7 days and cooled to 600 °C at 10 °C/min, at which point the tube was quenched into ice water. The Sn-rich matrix was dissolved in dilute HCl (1:1 v/v) until the gas evolution ceased. The product was recovered by filtration, washed successively with water and ethanol, and dried.

Powder X-ray diffraction (PXRD) was carried out on a SmartLab diffractometer (Rigaku) equipped with a D/teX Ultra 250 1D detector and a Cu K_α radiation source (λ = 1.54187 Å). Each pattern was recorded in the 2θ range from 10 to 80° with a step of 0.03° and the total collection time of 1 h. The analysis of PXRD patterns was carried out with the SmartLab Studio II (Rigaku).⁴¹

Electrocatalyst Preparation. The phase-pure sample of LaCo₂P₂ was ball-milled at 1725 rpm for 1 h in an 8000 M high-energy mixer/mill (SPEX), using a stainless steel ball-milling set. The milling process was performed under Ar atmosphere to minimize surface oxidation. The PXRD analysis of the ball-milled sample revealed no new impurity phases, although the diffraction peaks broadened, in accord with the decreased particle size and increased strain. The specific surface areas of the ball-milled LaCo₂P₂ and reference electrocatalyst were evaluated by measuring N₂ physisorption using an Autosorb iQ2 analyzer (Quantachrome). For that purpose, ≈100 mg of a sample was placed in the sample holder tube and degassed at 120 °C for 2 h. Subsequently, the sample holder tube was placed into a liquid N₂ bath for the analysis. The specific surface area of the materials was determined by the Brunauer–Emmett–Teller (BET) method.

The ball-milled sample of LaCo₂P₂ was converted to an electrocatalyst ink by dispersing 5 mg of the material in 50 μL of Nafion ionomer solution and 1.0 mL of anhydrous ethanol (Honeywell). The mixture was homogenized for 30 min in a bath sonicator USC-TH (VWR) and for 1 min with an ultrasonic probe Vibra-Cell 75185 (Thermo Fisher Scientific). Catalytic anodes were prepared by depositing the as-derived homogeneous ink on Ni foam (Heze Jiaotong, 110 pores per in., 0.3 mm thick) for alkaline OER or Ti felt (Bekaert Fibre Technologies, 20 μm fiber diameter, 1 mm thick) for acidic OER. Before the ink deposition, both the Ni foam and the Ti felt were cleaned by sequential 30 min ultrasonication in acetone, ethanol, and Milli-Q water. Prior to ultrasonic cleaning, the Ti felt was additionally purified by heating it under Ar atmosphere to 400 °C at 3 °C/min and maintaining it at this temperature for 2 h. In each case, 640 μL of the ink was loaded in 20 μL batches on the surface of the Ni foam or the Ti felt current collectors, letting ethanol evaporate between the batches. The exposed surface area of the anode was fixed to be 1 cm², and the total mass of the ball-milled LaCo₂P₂ catalyst or the reference IrO₂ catalyst loaded on the anode was varied from 0.25 to 3 mg/cm². Finally, the obtained anode was air-dried.

Electrocatalytic Measurements. Electrochemical studies were conducted at room temperature using an Autolab PGSTAT302N

potentiostat (Metrohm). The OER performance of the electrocatalysts was evaluated under moderate Ar bubbling (≈ 1 bubble/s) while stirring at 150 rpm in a three-electrode system filled with a purified 1.0 M NaOH (alkaline OER) or 0.5 M H_2SO_4 (acidic OER) electrolyte. The catalytic anode, a calibrated saturated calomel electrode (SCE), and a Pt wire served as the working, reference, and counter electrodes, respectively. Unless stated otherwise, all potentials reported in this work were converted to a reversible hydrogen electrode (RHE) reference scale according to the following equation: $E_{\text{RHE}} = E_{\text{SCE}} + 0.059\text{pH} + 0.241$. An iR correction of 85% was applied in the polarization experiments to compensate for the voltage drop between the reference and working electrodes, which was evaluated by a single-point high-frequency impedance measurement. OER anodic polarization curves were recorded using cyclic voltammetry (CV) with a scan rate of 5 mV/s. In the case of electrocatalyst activation, the scan rate was augmented to 50 mV/s. The catalytic stability of the anodes was evaluated as a function of time by means of chronopotentiometry at a constant current density of 10 mA/cm^2 .

Electrochemical impedance spectroscopy (EIS) was carried out on stable electrocatalytic systems at an overpotential of 0.42 V in the frequency range from 105 to 0.01 Hz with a 10 mV sinusoidal perturbation. The EIS measurements and the interpretation of results were conducted in accordance with an aqueous electrochemical assembly, the so-called supported system.⁴²

Chemical Analysis. Inductively coupled plasma-optical emission spectroscopy (ICP-OES) was carried out using an ICPE-9000 spectrometer (Shimadzu). Each sample was measured three times to ensure the reproducibility of results.

Transmission Electron Microscopy. Transmission electron microscopy (TEM), high-resolution TEM (HRTEM), high-angle annular dark-field scanning TEM (HAADF-STEM), selected area electron diffraction (SAED), and energy-dispersive X-ray spectroscopy in STEM mode (STEM-EDX) were performed using a JEM-ARM200F microscope (JEOL) equipped with a cold field-emission gun, a probe, an image aberration correction, a CENTURIO EDX detector, and a GIF Quantum filter. TEM samples were prepared by crushing a sample in an agate mortar in ethanol and depositing the obtained suspension on a copper carbon holey grid.

RESULTS AND DISCUSSION

Electrocatalyst Preparation. Bulk LaCo_2P_2 was prepared by annealing the constituent elements in Sn flux. After the Sn-rich matrix had been dissolved in dilute HCl, a phase-pure material was obtained, as evidenced by PXRD (Figure 2). The




Figure 2. PXRD patterns for the bulk (red) and ball-milled (blue) samples of LaCo_2P_2 . The calculated pattern (black) for LaCo_2P_2 is provided for comparison.

material was ball-milled for 1 h to increase the surface area for improved catalytic performance. According to the BET method, the surface area of the ball-milled sample was 9.9 cm^2/g . PXRD of the ball-milled material revealed that the sample remained phase-pure, but the diffraction peaks broadened due to the well-known combined effects of the decreased particle size and the strain introduced by ball-milling. The crystallite size was estimated as $D = K\lambda/[(w_s - w_i) \cdot \cos(\theta)]$,⁴³ where K is a shape factor (set to 0.9), λ is the X-ray wavelength, θ is the diffraction angle of the observed peak, and w_s and w_i are the full widths at half-maximum for the sample and an instrumental standard (highly crystalline Si powder), respectively. Using this equation, the lower bound for the crystallite size was estimated at ≈ 25 nm. This value does not represent the actual average crystallite size because the Scherrer equation does not account for the strain induced by the ball-milling process, which will necessarily increase the w_s value.

The TEM characterization prior to electrochemical testing revealed that the sample of ball-milled LaCo_2P_2 , in general, showed good crystallinity and contained a mixture of nanosized (≈ 10 nm) and submicron particles. The STEM-EDX elemental mappings (Figure 3a) indicate homogeneous chemical distribution of all constituent elements (La, Co, and P), as well as a negligible amount of oxygen that can be attributed to minor surface oxidation. High-resolution HAADF-STEM (Figure 3b) and TEM (Figure 3c) images, along with the corresponding Fourier transform (FT) patterns, confirm the tetragonal structure of LaCo_2P_2 (space group $I4/mmm$, $a = 3.8145$ Å, $c = 11.041$ Å, ICSD-624010).

Electrochemical Testing. The electrochemical OER testing in a purified 1 M NaOH electrolyte revealed that LaCo_2P_2 requires initial activation for *ca.* 100 CV cycles to achieve steady-state conditions, after which the material exhibits constant OER performance. Experimentally, it was found that LaCo_2P_2 with a loading of 0.25 mg/cm^2 was the most OER-active (Figure S1), reaching anodic current densities of 10, 50, and 100 mA/cm^2 at overpotentials of *ca.* 400 mV (η_{10}), 440 mV (η_{50}), and 460 mV (η_{100}), respectively (the blue curve in Figure 4a). A reference state-of-the-art IrO_2 catalyst (Figure S2) showed a higher performance at an industrially relevant loading of 1 mg/cm^2 (the red curve in Figure 4a), but at the same loading as that of LaCo_2P_2 , that is, at 0.25 mg/cm^2 , the overpotentials achieved with IrO_2 were quite similar (the yellow curve in Figure 4a). We would like to emphasize that at the same loading of 0.25 mg/cm^2 , the BET surface area of the IrO_2 catalyst (25.5 cm^2/g) was substantially larger than that of the LaCo_2P_2 material (9.92 cm^2/g), while the cost of the IrO_2 catalyst at such loading would be prohibitively high. Nevertheless, it might still be possible to achieve lower overpotentials with the LaCo_2P_2 -based catalyst, if the particle size can be further reduced to increase the electrocatalytically active surface area. Such an effect could be achieved, for example, by a solvent-assisted ball-milling process.

Given these promising results, the kinetic behavior of LaCo_2P_2 was investigated using a combination of Tafel and Nyquist plots. The Tafel plot relates the rate of the electrochemical reaction to the overpotential as $\eta = b \log(j/j_0)$, where j is the current density, j_0 is the exchange current density (*i.e.*, the current density at zero overpotential), and b is the Tafel slope, which represents the decade change in the reaction rate as a function of applied voltage.⁴⁴ Analysis of the




Figure 3. TEM analysis of LaCo_2P_2 particles after ball-milling: (a) low-magnification overview HAADF-STEM image and simultaneous STEM-EDX elemental mappings acquired at the L-line of La (red) and K-lines of P (purple), O (blue), and Co (green), and their mixture; (b) high-resolution HAADF-STEM image of a single LaCo_2P_2 particle viewed along the $[111]$ zone axis (the corresponding FT pattern is shown in the inset); (c) bright-field HRTEM image of the LaCo_2P_2 sample, together with the insets showing the FT patterns taken from $[100]$ (A) and $[110]$ (B) oriented particles.




Figure 4. (a) Alkaline OER anodic polarization curves for Ni foam (after 100 activation cycles), Ni foam-supported ball-milled LaCo_2P_2 at 0.25 mg/cm^2 loading (after 100 activation cycles) and Ni foam-supported reference IrO_2 catalyst at 0.25 and 1 mg/cm^2 loadings. (b) Respective Tafel plots. (c) Comparison of Nyquist plots for Ni foam-supported LaCo_2P_2 and Ni foam-supported reference IrO_2 at the applied overpotential $\eta = 420$ mV. The inset shows an equivalent electrical circuit model used to fit the Nyquist plots. (d) Chronopotentiometric stability tests under alkaline OER for Ni foam-supported LaCo_2P_2 and Ni foam-supported reference IrO_2 at the same loading of 0.25 mg/cm^2 .

electrocatalytic data according to this equation led to $b = 57$ mV dec⁻¹ for LaCo₂P₂ and $b = 69$ mV dec⁻¹ for IrO₂ at the same 0.25 mg/cm² loading (Figure 4b). Subsequently, EIS data were collected at low frequencies (Figure 4c), and the obtained semicircles were fit with an equivalent circuit model (Figure 4c, inset) consisting of a resistor (R_s) in series with two parallel combinations of a resistor (R_1 , R_{ct}) and a constant phase element (CPE1, CPE2).⁴⁵ R_s represents the Ohmic resistance from the electrolyte and all contacts. The time constant R_1 –CPE1 accounts for the interfacial resistance from the electron transport between the LaCo₂P₂ material and supporting Ni foam. R_{ct} –CPE2 is the charge-transfer resistance (R_{ct}) at the interface between the catalyst and the electrolyte, and smaller R_{ct} values typically reflect faster charge-transfer kinetics. The derived parameters, listed in Table 1, reveal that

Table 1. Impedance Parameters Calculated by Fitting the Nyquist Plots (Figure 4c)

circuit element	LaCo ₂ P ₂	IrO ₂
equivalent series resistance (R_s)	1.460 Ω	0.985 Ω
electron-/charge-transport resistance (R_1)	0.961 Ω	1.860 Ω
charge-transfer resistance (R_{ct})	1.470 Ω	2.820 Ω

the LaCo₂P₂ anode shows a significantly smaller R_{ct} value (1.470 Ω) as compared to that of IrO₂ (2.820 Ω), indicating that the LaCo₂P₂ catalyst offers favorable charge-transfer kinetics, competitive with that of IrO₂.

Lastly, we performed chronopotentiometry to study the stability of LaCo₂P₂ and reference IrO₂ with the same mass loading of 0.25 mg/cm² under the alkaline OER conditions (pH = 14). Over 100 h, LaCo₂P₂ compares favorably to IrO₂ and, more importantly, demonstrates an essentially constant performance for more than 4 days, driving the current density of 10 mA/cm² with $\eta \approx 400$ mV in the 1 M NaOH electrolyte solution (Figure 4d). Notably, the ICP-OES chemical analysis of the electrolyte after the stability testing showed the presence of only 0.077 ppm of Pt admixture, which, most likely, stems from leaching of the counter electrode.⁴⁶ Importantly, no traces of La, Co, or Ni were identified by the chemical analysis of the alkaline electrolyte, suggesting excellent stability of the LaCo₂P₂ catalyst, in particular, and the LaCo₂P₂/Ni foam anode assembly, in general.

After the studies of LaCo₂P₂ under alkaline OER, the material was tested under acidic OER (pH = 0) to determine its possible bifunctionality. The electrochemical station and the sample were prepared in a manner identical to that described for the alkaline OER, with the catalyst ink deposited on a Ti felt and 0.5 M H₂SO₄ used as the electrolyte. Under such conditions, the LaCo₂P₂ catalyst showed a much higher overpotential, $\eta = 1.01$ V, at 10 mA/cm² (Figure 5). Chronopotentiometric testing (Figure 5, inset) for driving current density of 10 mA/cm² showed that LaCo₂P₂ is not stable, causing a gradual increase in the overpotential with time. Thus, this material is impractical as an OER electrocatalyst under acidic conditions.

Post-electrochemical Testing. PXRD. To monitor changes to the LaCo₂P₂ phase under the OER conditions, the samples obtained after electrochemical testing in the alkaline and acidic electrolytes were harvested from the Ni foam and Ti felt, respectively, and subjected to PXRD analysis. The PXRD patterns obtained for the sample used in alkaline OER revealed that LaCo₂P₂ remains stable under the harsh




Figure 5. Acidic OER anodic polarization curves and the continuous chronopotentiometric profiles (shown as an inset) for the Ti felt, as well as Ti felt-supported ball-milled LaCo₂P₂, and Ti felt-supported reference IrO₂ materials, both at 3 mg/cm² loading.

alkaline conditions (Figure 6a). The large unresolved amorphous peaks that appear in the low-angle region are due to a Nafion ionomer admixture in the postcatalytic sample. The lower bound for the crystallite size, estimated from the Scherrer equation, decreased from 25 nm before the catalysis to 19 nm after the catalysis. This change is in agreement with the OER-induced *in situ* surface reconstruction that converts the outer layers of the LaCo₂P₂ particles to a shell of a catalytically active oxide–(oxy)hydroxide phase,^{29,32} as suggested by the observations made in the TEM studies discussed below.

In sharp contrast to the alkaline OER testing, the sample obtained after the acidic OER testing contained predominantly LaPO₄ and minor impurities that could not be assigned due to the large amorphous peak observed in the low-angle region due to the Nafion ionomer (Figure 6b). As seen later from the EDX mapping results, the other impurity is Co-based due to the high content of Co found in this sample.

Electron Microscopy. The samples obtained after the alkaline and acidic OER testing were subjected to TEM imaging and STEM–EDX elemental mapping. In comparison to the sample prior to testing (Figure 3), an extreme increase in the oxygen content was observed after 100 h of stability testing under alkaline conditions (Figure 7a). HAADF-STEM and SAED were employed to determine the nature of the oxygen-containing phase formed on the surface of the LaCo₂P₂ particles. These particles showed well-defined lattice planes (Figure 7b) with a number of defects, while the respective SAED (Figure 7b, inset) could be indexed with the lattice parameters corresponding to the tetragonal *I4/mmm* structure of LaCo₂P₂ ($a = 3.814$ Å, $c = 11.041$ Å, ICSD-624010). The HAADF-STEM image simulation based on this structure showed a good agreement with the experimental one (Figure 7b, inset). Interestingly, the edge of the LaCo₂P₂ particle is decorated by an amorphous layer of several nanometers thickness, and according to STEM–EDX elemental mapping, it can be attributed to the CoO_x phase. The high-resolution HAADF-STEM image (Figure 7b) clearly reveals a transition from the region of the CoO_x shell to the layered structure of




Figure 6. PXRD patterns of LaCo_2P_2 after 100 h of chronopotentiometric testing at $10 \text{ mA}/\text{cm}^2$ in 1 M NaOH (a) and $0.5 \text{ M H}_2\text{SO}_4$ (b). Broad amorphous peaks present in both samples are due to the Nafion ionomer. The calculated patterns for LaCo_2P_2 and LaPO_4 are shown as references.




Figure 7. HAADF-STEM images together with simultaneously collected STEM–EDX elemental mappings of La, P, O, Co, and their mixture for LaCo_2P_2 particles after OER electrocatalysis in alkaline (a) and acidic (c) electrolytes. (b) High-resolution $[201]$ HAADF-STEM image with the corresponding SAED (upper corner inset) and the magnified HAADF-STEM image with an overlaid simulated image (bottom corner inset) for LaCo_2P_2 particles after alkaline OER electrocatalysis. (d) Low-magnification TEM overview image for the LaPO_4 needle-like particles formed after acidic OER electrocatalysis over LaCo_2P_2 .

the LaCo_2P_2 core, indicating the *in situ* surface reconstruction caused by alkaline OER electrocatalysis.

Under acidic OER conditions, the LaCo_2P_2 catalyst underwent a complete change in its morphology, as compared to the material before electrocatalysis. The particle shape changed from plate-like (Figure 3a) to needle-like (Figure 7c). This observation is in agreement with the formation of LaPO_4 as the major phase observed by PXRD (Figure 6b). Indeed, LaPO_4 was shown to form rodlike particles^{47,48} that exhibit an increasing aspect ratio with decreasing pH.⁴⁹ The STEM–EDX elemental mapping of the postcatalytic sample showed an increase in the O content and a decrease in the La and P contents, while the content of Co remained relatively high (Figure 7c). These observations support the PXRD findings, which showed that LaCo_2P_2 decomposes during the acidic OER electrocatalysis to form LaPO_4 , and also suggest that the

crystalline phosphate particles are surrounded by an amorphous cobalt oxide phase. This phase was unstable under the electron beam during TEM measurements even at low voltage (80 kV), which impeded the high-resolution imaging to identify the exact nature of this oxidic Co phase.

CONCLUDING REMARKS

Based on the results presented above, we rationalize that LaCo_2P_2 acts as pre-catalyst in the alkaline water oxidation. Under the applied voltage at $\text{pH} = 14$, its surface undergoes *in situ* reconstruction, most likely, according to the following equation




Table 2. Overpotential and Performance Parameters Reported for Cobalt Oxides and Phosphides Used in Alkaline OER Electrocatalysis

catalyst	electrolyte	catalyst loading (mg/cm ²)	η_{10} (mV)	b (mV/dec)	references
LaCo ₂ P ₂	1 M NaOH	0.25	400	57	this work
IrO ₂	1 M NaOH	1.0	340	73	this work
IrO ₂	1 M NaOH	0.25	380	69	this work
co-polythiophene	1 M KOH	1.4	338	52	52
Ni–S–CoFe ₂ O ₄	1 M KOH	n/a	228	72	53
La _{0.9} CoO _{3–δ}	0.1 M KOH	0.24	380	83	54
Co ₃ O ₄ (nanoparticles)	0.1 M KOH	n/a	310	53	55
CoP (film)	1 M KOH	2.5	345	47	56
CoP (nanoframes)	1 M KOH	0.27	323	50	57
CoP (N-doped carbon)	1 M KOH	0.27	354	60	57
CoP (graphitic carbon)	1 M KOH	n/a	345	56	58

Although this equation is a much-simplified version of what actually occurs on the surface, it allows us to highlight two major points. First, during approximately the first 100 CV cycles of required activation, as established experimentally, the surface of the LaCo₂P₂ particles is converted to the oxidic CoO_x shell. The formation of the La(OH)₃ phase is postulated according to the Pourbaix diagram for La at the specific applied voltage and pH = 14.⁵⁰ Second, the surface is reconstructed to the catalytically active amorphous CoO_x shell (or perhaps the CoOOH shell⁵¹), as evidenced by the electron microscopy analysis and the experimentally observed decrease in the overpotential over the first 100 cycles of the electrocatalysis. While CoO_x serves as an active OER electrocatalyst, the underlying LaCo₂P₂ phase provides a robust support, allowing the catalyst to maintain stability for at least 4 days of electrocatalysis. In contrast, under acidic conditions, LaCo₂P₂ rapidly decomposes to LaPO₄ and amorphous cobalt oxide or (oxy)hydroxide, resulting in a rapid increase in the overpotential.

To determine the effectiveness of LaCo₂P₂ as an alkaline OER electrocatalyst, we compared its performance to that of other Co-based OER electrocatalysts studied under alkaline conditions (Table 2). The overpotential at 10 mA/cm² (η_{10} = 400 mV) observed for the CoO_x/LaCo₂P₂ electrocatalytic system in the present work is slightly higher than the values reported for other Co-based electrocatalysts, which typically show η_{10} above 300 mV. On the other hand, the Tafel slope of 57 mV, measured for CoO_x/LaCo₂P₂ in this work, is comparable to the values observed for the other Co-based systems at similar catalyst loading. Xing *et al.* added polythiophene to increase the electrical conductivity of the catalyst to achieve an overpotential of 338 mV at 10 mA/cm² and a low Tafel slope of 52 mV/dec.⁵² Nevertheless, the stability of such a system is substantially lower than that of LaCo₂P₂, as the performance decreased by 5% after 15 h, whereas our LaCo₂P₂ catalyst maintained constant performance for 100 h (Figure 4a, inset). Li *et al.* achieved good electrocatalytic results by applying an external magnetic field during the synthesis of the catalyst (Ni–S–CoFe₂O₄), which they attributed to the formation of a larger concentration of catalytically active sites and an effective electrochemical surface area on the active site surface.⁵³

Overall, the performance of LaCo₂P₂ in OER electrocatalysis is comparable to the previously reported performance by CoP, as well as to the performance of the IrO₂ benchmark. The presence of the additional La layer does not have a substantial effect on the electrochemical activity, which is in contrast to

our recent finding for AlFe₂B₂,²⁹ where the extra layer of Al appeared to improve the charge-transfer kinetics in comparison to the performance of binary iron borides. The lack of improved kinetics may be attributed to the higher polarity of the LaCo₂P₂ structure that contains alternating electropositive La layers and electronegative [Co₂P₂] layers. Another detrimental factor might be the presence of insoluble La(OH)₃ in the amorphous surface layer. Lowering the polarity of the intermetallic structure and using an electropositive element that forms a more soluble hydroxide might alleviate these problems. In this vein, ACo₂P₂ structures that contain alkaline-earth metals (A) can serve as promising targets for future studies. These efforts are currently underway in our laboratories, and the results of such studies will be reported in due course.

■ ASSOCIATED CONTENT

Supporting Information

The Supporting Information is available free of charge at <https://pubs.acs.org/doi/10.1021/acsami.1c19858>.

Alkaline OER activity of Ni foam-supported ball-milled LaCo₂P₂ and reference IrO₂ catalyst as a function of the material mass loading (PDF)

■ AUTHOR INFORMATION

Corresponding Authors

Yury V. Kolen'ko – International Iberian Nanotechnology Laboratory, Braga 4715-330, Portugal; orcid.org/0000-0001-7493-1762; Email: yury.kolenko@inl.int

Michael Shatruk – Department of Chemistry and Biochemistry, Florida State University, Tallahassee, Florida 32306, United States; orcid.org/0000-0002-2883-4694; Email: shatruk@chem.fsu.edu

Authors

Dallas K. Mann – Department of Chemistry and Biochemistry, Florida State University, Tallahassee, Florida 32306, United States

Aida M. Díez – International Iberian Nanotechnology Laboratory, Braga 4715-330, Portugal

Junyuan Xu – International Iberian Nanotechnology Laboratory, Braga 4715-330, Portugal

Oleg I. Lebedev – Laboratoire CRISMAT, UMR 6508, CNRS-Ensicaen, Caen 14050, France

Complete contact information is available at: <https://pubs.acs.org/doi/10.1021/acsami.1c19858>

Notes

The authors declare no competing financial interest.

■ ACKNOWLEDGMENTS

The work performed at Florida State University was supported by the Petroleum Research Fund of the American Chemical Society (award 59251-ND10) and in part by the U.S. National Science Foundation (award DMR-1905499) as well as the European Union's Horizon 2020 research and innovation program through the SpinCat project under grant agreement no. 964972. The electron microscopy studies were performed with the financial support from the Agence Nationale de la Recherche in the framework of the "Investissements d'avenir" program with the reference ANR-11-EQPX-0020. A.M.D. is grateful to Xunta de Galicia (ED481B 2019/091) for the financial support. Y.V.K. thanks the Portuguese Foundation for Science and Technology (FCT) for the support under the CritMag Project (PTDC/NAN-MAT/28745/2017).

■ REFERENCES

- (1) Buttlar, A.; Spliethoff, H. Current Status of Water Electrolysis for Energy Storage, Grid Balancing and Sector Coupling Via Power-to-Gas and Power-to-Liquids: A Review. *Renewable Sustainable Energy Rev.* **2018**, *82*, 2440–2454.
- (2) Seh, Z. W.; Kibsgaard, J.; Dickens, C. F.; Chorkendorff, I.; Nørskov, J. K.; Jaramillo, T. F. Combining Theory and Experiment in Electrocatalysis: Insights into Materials Design. *Science* **2017**, *355*, No. eaad4998.
- (3) Katsounaros, I.; Cherevko, S.; Zeradjanin, A. R.; Mayrhofer, K. J. Oxygen Electrochemistry as a Cornerstone for Sustainable Energy Conversion. *Angew. Chem., Int. Ed.* **2014**, *53*, 102–121.
- (4) McCrory, C. C. L.; Jung, S.; Ferrer, I. M.; Chatman, S. M.; Peters, J. C.; Jaramillo, T. F. Benchmarking Hydrogen Evolving Reaction and Oxygen Evolving Reaction Electrocatalysts for Solar Water Splitting Devices. *J. Am. Chem. Soc.* **2015**, *137*, 4347–4357.
- (5) Roger, I.; Shipman, M. A.; Symes, M. D. Earth-Abundant Catalysts for Electrochemical and Photoelectrochemical Water Splitting. *Nat. Rev. Chem.* **2017**, *1*, 0003.
- (6) Lee, Y.; Suntivich, J.; May, K. J.; Perry, E. E.; Shao-Horn, Y. Synthesis and Activities of Rutile IrO_2 and RuO_2 Nanoparticles for Oxygen Evolution in Acid and Alkaline Solutions. *J. Phys. Chem. Lett.* **2012**, *3*, 399–404.
- (7) Walter, M. G.; Warren, E. L.; McKone, J. R.; Boettcher, S. W.; Mi, Q.; Santori, E. A.; Lewis, N. S. Solar Water Splitting Cells. *Chem. Rev.* **2010**, *110*, 6446–6473.
- (8) McKone, J. R.; Lewis, N. S.; Gray, H. B. Will Solar-Driven Water-Splitting Devices See the Light of Day? *Chem. Mater.* **2014**, *26*, 407–414.
- (9) Salonen, L. M.; Petrovykh, D. Y.; Kolen'ko, Y. V. Sustainable Catalysts for Water Electrolysis: Selected Strategies for Reduction and Replacement of Platinum-Group Metals. *Mater. Today Sustain.* **2021**, *11–12*, 100060.
- (10) Mavrokefalos, C.; Patzke, G. Water Oxidation Catalysts: The Quest for New Oxide-Based Materials. *Inorganics* **2019**, *7*, 29.
- (11) Subbaraman, R.; Tripkovic, D.; Chang, K.-C.; Strmcnik, D.; Paulikas, A. P.; Hirunsit, P.; Chan, M.; Greeley, J.; Stamenkovic, V.; Markovic, N. M. Trends in Activity for the Water Electrolyser Reactions on $3d$ $M(\text{Ni}, \text{Co}, \text{Fe}, \text{Mn})$ Hydr(Oxy)Oxide Catalysts. *Nat. Mater.* **2012**, *11*, 550–557.
- (12) Suen, N.-T.; Hung, S.-F.; Quan, Q.; Zhang, N.; Xu, Y.-J.; Chen, H. M. Electrocatalysis for the Oxygen Evolution Reaction: Recent Development and Future Perspectives. *Chem. Soc. Rev.* **2017**, *46*, 337–365.
- (13) Song, F.; Bai, L.; Moysiadiou, A.; Lee, S.; Hu, C.; Liardet, L.; Hu, X. Transition Metal Oxides as Electrocatalysts for the Oxygen Evolution Reaction in Alkaline Solutions: An Application-Inspired Renaissance. *J. Am. Chem. Soc.* **2018**, *140*, 7748–7759.
- (14) Lu, F.; Zhou, M.; Zhou, Y.; Zeng, X. First-Row Transition Metal Based Catalysts for the Oxygen Evolution Reaction under Alkaline Conditions: Basic Principles and Recent Advances. *Small* **2017**, *13*, 1701931.
- (15) Liu, Y.; Xiao, C.; Lyu, M.; Lin, Y.; Cai, W.; Huang, P.; Tong, W.; Zou, Y.; Xie, Y. Ultrathin Co_3S_4 Nanosheets That Synergistically Engineer Spin States and Exposed Polyhedra That Promote Water Oxidation under Neutral Conditions. *Angew. Chem., Int. Ed.* **2015**, *54*, 11231–11235.
- (16) Kwak, I. H.; Im, H. S.; Jang, D. M.; Kim, Y. W.; Park, K.; Lim, Y. R.; Cha, E. H.; Park, J. CoSe_2 and NiSe_2 Nanocrystals as Superior Bifunctional Catalysts for Electrochemical and Photoelectrochemical Water Splitting. *ACS Appl. Mater. Interfaces* **2016**, *8*, 5327–5334.
- (17) Yang, Y.; Zhang, K.; Lin, H.; Li, X.; Chan, H. C.; Yang, L.; Gao, Q. MoS_2 – Ni_3S_2 Heteronanorods as Efficient and Stable Bifunctional Electrocatalysts for Overall Water Splitting. *ACS Catal.* **2017**, *7*, 2357–2366.
- (18) Liu, K.; Zhang, C.; Sun, Y.; Zhang, G.; Shen, X.; Zou, F.; Zhang, H.; Wu, Z.; Wegener, E. C.; Taubert, C. J.; Miller, J. T.; Peng, Z.; Zhu, Y. High-Performance Transition Metal Phosphide Alloy Catalyst for Oxygen Evolution Reaction. *ACS Nano* **2018**, *12*, 158–167.
- (19) Parra-Puerto, A.; Ng, K. L.; Fahy, K.; Goode, A. E.; Ryan, M. P.; Kucernak, A. Supported Transition Metal Phosphides: Activity Survey for Her, Orr, Oer, and Corrosion Resistance in Acid and Alkaline Electrolytes. *ACS Catal.* **2019**, *9*, 11515–11529.
- (20) Yu, X.-Y.; Feng, Y.; Guan, B.; Lou, X. W.; Paik, U. Carbon Coated Porous Nickel Phosphides Nanoplates for Highly Efficient Oxygen Evolution Reaction. *Energy Environ. Sci.* **2016**, *9*, 1246–1250.
- (21) Chang, J.; Xiao, Y.; Xiao, M.; Ge, J.; Liu, C.; Xing, W. Surface Oxidized Cobalt-Phosphide Nanorods as an Advanced Oxygen Evolution Catalyst in Alkaline Solution. *ACS Catal.* **2015**, *5*, 6874–6878.
- (22) Xu, J.; Sousa, J. P. S.; Mordvinova, N. E.; Costa, J. D.; Petrovykh, D. Y.; Kovnir, K.; Lebedev, O. I.; Kolen'ko, Y. V. Al-Induced in Situ Formation of Highly Active Nanostructured Water-Oxidation Electrocatalyst Based on Ni-Phosphide. *ACS Catal.* **2018**, *8*, 2595–2600.
- (23) Xu, J.; Wei, X.-K.; Costa, J. D.; Lado, J. L.; Owens-Baird, B.; Gonçalves, L. P. L.; Fernandes, S. P. S.; Heggen, M.; Petrovykh, D. Y.; Dunin-Borkowski, R. E.; Kovnir, K.; Kolen'ko, Y. V. Interface Engineering in Nanostructured Nickel Phosphide Catalyst for Efficient and Stable Water Oxidation. *ACS Catal.* **2017**, *7*, 5450–5455.
- (24) Gupta, S.; Patel, M. K.; Miotello, A.; Patel, N. Metal Boride-Based Catalysts for Electrochemical Water-Splitting: A Review. *Adv. Funct. Mater.* **2020**, *30*, 1906481.
- (25) Li, Y.; Huang, B.; Sun, Y.; Luo, M.; Yang, Y.; Qin, Y.; Wang, L.; Li, C.; Lv, F.; Zhang, W.; Guo, S. Multimetal Borides Nanochains as Efficient Electrocatalysts for Overall Water Splitting. *Small* **2019**, *15*, 1804212.
- (26) Jiao, L.; Zhou, Y.-X.; Jiang, H.-L. Metal–Organic Framework-Based CoP/Reduced Graphene Oxide: High-Performance Bifunctional Electrocatalyst for Overall Water Splitting. *Chem. Sci.* **2016**, *7*, 1690–1695.
- (27) Stern, L.-A.; Feng, L.; Song, F.; Hu, X. Ni_2P as a Janus Catalyst for Water Splitting: The Oxygen Evolution Activity of Ni_2P Nanoparticles. *Energy Environ. Sci.* **2015**, *8*, 2347–2351.
- (28) Owens-Baird, B.; Xu, J.; Petrovykh, D. Y.; Bondarchuk, O.; Ziouani, Y.; González-Ballesteros, N.; Yox, P.; Sapountzi, F. M.; Niemantsverdriet, H.; Kolen'ko, Y. V.; Kovnir, K. NiP_2 : A Story of Two Divergent Polymorphic Multifunctional Materials. *Chem. Mater.* **2019**, *31*, 3407–3418.
- (29) Mann, D. K.; Xu, J.; Mordvinova, N. E.; Yannello, V.; Ziouani, Y.; González-Ballesteros, N.; Sousa, J. P. S.; Lebedev, O. I.; Kolen'ko, Y. V.; Shatruk, M. Electrocatalytic Water Oxidation over AlFe_2B_2 . *Chem. Sci.* **2019**, *10*, 2796–2804.
- (30) Guo, F.; Wu, Y.; Chen, H.; Liu, Y.; Yang, L.; Ai, X.; Zou, X. High-Performance Oxygen Evolution Electrocatalysis by Boronized

Metal Sheets with Self-Functionalized Surfaces. *Energy Environ. Sci.* **2019**, *12*, 684–692.

(31) Jiang, J.; Wang, M.; Yan, W.; Liu, X.; Liu, J.; Yang, J.; Sun, L. Highly Active and Durable Electrocatalytic Water Oxidation by a $\text{NiB}_{0.45}/\text{NiO}_x$ Core-Shell Heterostructured Nanoparticulate Film. *Nano Energy* **2017**, *38*, 175–184.

(32) Serov, A.; Kovnir, K.; Shatruk, M.; Kolen'ko, Y. V. Critical Review of Platinum Group Metal-Free Materials for Water Electrolysis: Transition from the Laboratory to the Market: Earth-Abundant Borides and Phosphides as Catalysts for Sustainable Hydrogen Production. *Johnson Matthey Technol. Rev.* **2021**, *65*, 207–226.

(33) Tan, X.; Chai, P.; Thompson, C. M.; Shatruk, M. Magnetocaloric Effect in AlFe_2B_2 : Toward Magnetic Refrigerants from Earth-Abundant Elements. *J. Am. Chem. Soc.* **2013**, *135*, 9553–9557.

(34) Chai, P.; Stoian, S. A.; Tan, X.; Dube, P. A.; Shatruk, M. Investigation of Magnetic Properties and Electronic Structure of Layered-Structure Borides AlT_2B_2 ($\text{T} = \text{Fe}, \text{Mn}, \text{Cr}$) and $\text{AlFe}_{2-x}\text{Mn}_x\text{B}_2$. *J. Solid State Chem.* **2015**, *224*, 52–61.

(35) Mann, D. K.; Wang, Y.; Marks, J. D.; Strouse, G. F.; Shatruk, M. Microwave Synthesis and Magnetocaloric Effect in AlFe_2B_2 . *Inorg. Chem.* **2020**, *59*, 12625–12631.

(36) Pöttgen, R.; Hönle, W.; von Schnering, H. G. Phosphides: Solid-State Chemistry. In *Encyclopedia of Inorganic Chemistry*; King, R. B., Ed.; Wiley: Chichester, 2005; Vol. 8, pp 4255–4308.

(37) Kovnir, K.; Thompson, C. M.; Zhou, H. D.; Wiebe, C. R.; Shatruk, M. Tuning Ferro- and Metamagnetic Transitions in Rare-Earth Cobalt Phosphides $\text{La}_{1-x}\text{Pr}_x\text{Co}_2\text{P}_2$. *Chem. Mater.* **2010**, *22*, 1704–1713.

(38) Reehuis, M.; Ritter, C.; Ballou, R.; Jeitschko, W. Ferromagnetism in the ThCr_2Si_2 -Type Phosphide LaCo_2P_2 . *J. Magn. Magn. Mater.* **1994**, *138*, 85–93.

(39) Tian, Y.; Kong, Y.; Liu, K.; Zhang, A.; He, R.; Zhang, Q. Magnetic Evolution of Itinerant Ferromagnetism and Interlayer Antiferromagnetism in Cerium Doped LaCo_2P_2 Crystals. *Phys. B* **2017**, *512*, 75–80.

(40) Clark, J. K.; Tan, X.; Garlea, V. O.; Arico, A. A.; Ramirez, A. P.; Yannello, V.; Thompson, C. M.; Kovnir, K.; Shatruk, M. Reentrant Spin Glass State Induced by Structural Phase Transition in $\text{La}_{0.4}\text{Ce}_{0.6}\text{Co}_2\text{P}_2$. *Phys. Rev. Mater.* **2020**, *4*, 074412.

(41) Rigaku Corporation. Integrated X-Ray Diffraction Software Smartlab Studio II. *Rigaku J.* **2015**, *31*, 25–26.

(42) Macdonald, J. R.; Johnson, W. B. Fundamentals of Impedance Spectroscopy. In *Impedance Spectroscopy*; John Wiley & Sons, Inc., 2018; pp 1–20.

(43) Patterson, A. L. The Scherrer Formula for X-Ray Particle-Size Determination. *Phys. Rev.* **1939**, *56*, 978–982.

(44) Shinagawa, T.; Garcia-Esparza, A. T.; Takanabe, K. Insight on Tafel Slopes from a Microkinetic Analysis of Aqueous Electrocatalysis for Energy Conversion. *Sci. Rep.* **2015**, *5*, 13801.

(45) Bonanos, N.; Steele, B. C. H.; Butler, E. P.; Macdonald, J. R.; Johnson, W. B.; Worrell, W. L.; Niklasson, G. A.; Malmgren, S.; Strømme, M.; Sundaram, S. K.; McKubre, M. C. H.; Macdonald, D. D.; Engelhardt, G. R.; Barsoukov, E.; Conway, B. E.; Pell, W. G.; Wagner, N.; Roland, C. M.; Eisenberg, R. S. Applications of Impedance Spectroscopy. In *Impedance Spectroscopy*; John Wiley & Sons, Inc., 2018; pp 175–478.

(46) Roger, I.; Symes, M. D. Efficient Electrocatalytic Water Oxidation at Neutral and High pH by Adventitious Nickel at Nanomolar Concentrations. *J. Am. Chem. Soc.* **2015**, *137*, 13980–13988.

(47) Vats, B. G.; Shafeeq, M.; Singhal, P.; Neogy, S. Organic Soluble $\text{LaPO}_4:\text{Eu}^{3+}$ Nanorods: Sensitization of Surface Eu^{3+} Ions and Phase Transfer in Water. *ChemistrySelect* **2018**, *3*, 4930–4938.

(48) Ansari, A. A.; Khan, M. A. M. Structural and Spectroscopic Studies of $\text{LaPO}_4:\text{Ce}/\text{Tb}@ \text{LaPO}_4/\text{SiO}_2$ Nanorods: Synthesis and Role of Surface Coating. *Vib. Spectrosc.* **2018**, *94*, 43–48.

(49) Wang, X.; Zhang, L.; Zhang, Z.; Wang, X. Effects of Ph Value on Growth Morphology of LaPO_4 Nanocrystals: Investigated from

Experiment and Theoretical Calculations. *Appl. Phys. A* **2016**, *122*, 508.

(50) Pourbaix, M. *Atlas of Electrochemical Equilibria in Aqueous Solutions*, 2nd ed.; National Association of Corrosion: Houston, TX, 1974.

(51) Lopes, P. P.; Chung, D. Y.; Rui, X.; Zheng, H.; He, H.; Farinazzo Bergamo Dias Martins, P.; Strmcnik, D.; Stamenkovic, V. R.; Zapol, P.; Mitchell, J. F.; Klie, R. F.; Markovic, N. M. Dynamically Stable Active Sites from Surface Evolution of Perovskite Materials During the Oxygen Evolution Reaction. *J. Am. Chem. Soc.* **2021**, *143*, 2741–2750.

(52) Xing, D.; Zhou, P.; Liu, Y.; Wang, Z.; Wang, P.; Zheng, Z.; Dai, Y.; Whangbo, M.-H.; Huang, B. Atomically Dispersed Cobalt-Based Species Anchored on Polythiophene as an Efficient Electrocatalyst for Oxygen Evolution Reaction. *Appl. Surf. Sci.* **2021**, *545*, 148943.

(53) Li, Z.; Lv, Z.; Liu, X.; Wang, G.; Lin, Y.; Xie, G.; Jiang, L. Magnetic-Field Guided Synthesis of Highly Active $\text{Ni-S-CoFe}_2\text{O}_4$ Electrocatalysts for Oxygen Evolution Reaction. *Renewable Energy* **2021**, *165*, 612–618.

(54) Wang, H.; Chen, X.; Huang, D.; Zhou, M.; Ding, D.; Luo, H. Cation Deficiency Tuning of LaCoO_3 Perovskite as Bifunctional Oxygen Electrocatalyst. *ChemCatChem* **2020**, *12*, 2768–2775.

(55) Mehboob, A.; Gilani, S. R.; Anwar, A.; Sadiqa, A.; Akbar, S.; Patujo, J. Nanoscale Cobalt-Oxide Electrocatalyst for Efficient Oxygen Evolution Reactions in Alkaline Electrolyte. *J. Appl. Electrochem.* **2021**, *51*, 691–702.

(56) Jiang, N.; You, B.; Sheng, M.; Sun, Y. Electrodeposited Cobalt-Phosphorous-Derived Films as Competent Bifunctional Catalysts for Overall Water Splitting. *Angew. Chem., Int. Ed.* **2015**, *54*, 6251–6254.

(57) Ji, L.; Wang, J.; Teng, X.; Meyer, T. J.; Chen, Z. CoP Nanoframes as Bifunctional Electrocatalysts for Efficient Overall Water Splitting. *ACS Catal.* **2020**, *10*, 412–419.

(58) Wu, R.; Wang, D. P.; Zhou, K.; Srikanth, N.; Wei, J.; Chen, Z. Porous Cobalt Phosphide/Graphitic Carbon Polyhedral Hybrid Composites for Efficient Oxygen Evolution Reactions. *J. Mater. Chem. A* **2016**, *4*, 13742–13745.