



HAL
open science

Plasma-Enhanced Chemical Vapor Deposition in a Transmission Electron Microscope?

Jean-Luc Maurice, Pavel Bulkin, Éric Ngo, Weixi Wang, Pere Roca I
Cabarrocas, Martin Foldyna, Ileana Florea

► **To cite this version:**

Jean-Luc Maurice, Pavel Bulkin, Éric Ngo, Weixi Wang, Pere Roca I Cabarrocas, et al.. Plasma-Enhanced Chemical Vapor Deposition in a Transmission Electron Microscope?. *Microscopy and Microanalysis*, 2021, 27 (S2), pp.25-26. 10.1017/S143192762101312X . hal-03822374

HAL Id: hal-03822374

<https://hal.science/hal-03822374>

Submitted on 20 Oct 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Plasma-Enhanced Chemical Vapor Deposition in a Transmission Electron Microscope?

Jean-Luc Maurice^{1,*}, Pavel Bulkin¹, Éric Ngo¹, Weixi Wang¹, Pere Roca i Cabarrocas¹, Martin Foldyna¹ and Ileana Florea¹

¹ LPICM, École polytechnique, CNRS, Institut Polytechnique de Paris, Palaiseau, France.

In plasma-enhanced chemical vapor deposition (PECVD), reactive species generated by the plasma have the effect, among others, of changing the surface energies of the growing materials, which allows one to prepare objects that would not stabilize otherwise. Here, we use this property to stabilize Sn droplets used as catalysts in the growth of Si nanowires (SiNWs) with the vapor-liquid-solid (VLS) method [1]. However, the conditions necessary to ignite a plasma are not compatible with transmission electron microscopy (TEM), so that adapting the growth conditions of a PECVD reactor to *in-situ* TEM is hardly imaginable, hence the question mark in our title.

The TEM equipment we use is the environmental transmission electron microscope “NanoMAX”, a modified Thermo Fisher Titan ETEM. To circumvent the incompatibility between PECVD and TEM, we implemented, on the H₂ line of that ETEM, an electron-cyclotron-resonance plasma source (Aurawave from SAIREM), to remotely generate the H atoms necessary for the growth. Our *in situ* observations (Fig. 1) clearly show that, without the supply of hydrogen atoms (“plasma OFF”, in Fig. 1), the liquid Sn at the top of NWs is unstable (because Sn naturally wets Si surface) so that no growth is allowed, whereas in the presence of H atoms generated by the plasma, the Si surface energies are drastically lowered [2]; the Sn droplet stabilizes and can be used by the VLS mechanism of growth [3].

Moreover, we have recently found [4] that the addition of Cu to Sn, to make Cu-Sn bi-catalysts, allows one to reduce the size of the liquid nanoparticles below 10 nm, which appears to be a necessary condition for obtaining SiNWs with the hexagonal 2H polytype [2,4,5] (Fig. 2), a metastable structure that would have interesting optical properties [6]. Thanks to our unique setting, we have been able to obtain Sn-Cu-catalyzed SiNWs *in-situ*, with 2H regions [7]. The talk presents the effect on NW growth of switching the plasma on and off, and shows movies of the nucleation of the Si 2H metastable polytype recorded at atomic resolution [8].

References:

- [1] RS Wagner and WC Ellis, Appl. Phys. Lett., **4** (1964), p. 89.
- [2] R Béjaud and O Hardouin Duparc, Comput. Mater. Sci., **188** (2021), p. 110180.
- [3] S Misra *et al*, J. Phys. D: Appl. Phys., **47** (2014), p. 393001.
- [4] W Wang. PhD thesis, Institut Polytechnique de Paris, École polytechnique, 2021.
- [5] J Tang *et al*, Nanoscale, **9** (2017), p. 8113.
- [6] M Amato *et al*, Nano Lett., **16** (2016), p. 5694.
- [7] É Ngo. PhD thesis, Institut Polytechnique de Paris, École polytechnique, 2021.
- [8] This work was funded by the French National Research Agency - ANR: TEMPOS-NanoMAX (ANR-10-EQPX-50); HexaNW (ANR-17-CE09-0011). We kindly thank F. Glas, F. Panciera (C2N), for fruitful discussions, and F. Panciera doubly, for providing precious cantilever substrates. Thanks are also due to the CIMEX for the use of the electron microscopes at École polytechnique.




Figure 1. SiNW grown *in situ* in NanoMAX with Sn catalyst, at the moment of switching plasma off (0 s, left) and 31 s after plasma has been switched off (right).




Figure 2. 2H SiNW obtained in a PECVD reactor [4], with a short 3C (cubic) domain.