

Investigating the nucleation of Al2O3 on clean Si in ALD: plasma post and pre-processing

Pascal Dubreuil, Emmanuel Scheid

▶ To cite this version:

Pascal Dubreuil, Emmanuel Scheid. Investigating the nucleation of Al2O3 on clean Si in ALD : plasma post and pre-processing. School of Atomic Layer Deposition, Oct 2022, Autrans, France. , 2022. hal-03843720

HAL Id: hal-03843720 https://hal.science/hal-03843720

Submitted on 8 Nov 2022

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Investigating the nucleation of Al2O3 on clean Si in ALD : plasma post and pre-processing

<u>P. DUBREUIL</u>, E. SCHEID LAAS, Université de Toulouse, CNRS, Toulouse, France. Contact : dubreuil@laazs.fr

This study is dedicated to the investigation of the nucleation behavior of Al_2O_3 deposited by ALD via TetraMethylAlumina (TMA) and H_2O on clean Silicon. We already showed in previous studies^{1,2} that this nucleation may follow a island growth regime, with a seed density ranging approximatively at 0.5% of the Silicon surface density. This is supposed to lead to the growth of non-continuous layers, for thicknesses lower than 3nm. In this work, we first study the oxidation in plasma of layers (supposedly Al_2O_3) grown after a few number of cycles (13 to 50). The fact that there is a noticeable oxidation of layers thinner than 5m confirms the non-continuous character of these last.

We then try to optimize the in-situ plasma pre-processing, for which we already demonstrated^{1,2} that the creation of an intermediate layer by nitridation of the Si gave an instantaneous linear growth regime of Al_2O_3 i.e. a seed density at 100% on the initial surface. We tried to optimize this intermediate layer, using different source of gases instead of N₂-NH₃ used previously^{1,2}, which presented the drawback to give a relatively thick layer (1.5nm) with a low material density. We compare three different compounds for the plasma pre-processing : N₂, N₂+O₂ and O₂, by performing 30cyles of Al₂O₃ deposition. Observations by TEM and EDX show that the pre-treatments involving N₂ are effective and optimum, creating a thinner interface (0.5 nm), and a continuous layer of Al₂O₃ with a thickness of 3nm, as expected for a continuous growth. Using plasma O₂ only does not give so positive results, with a thicker interfacial layer and a thinner deposited Al₂O₃.

Finally, an attempt was made using in-situ plasma SF6 pre-treatments. The purpose was to avoid the creation of an intermediate layer, as obtained by nitridating/oxidizing plasmas. We hoped to improve the nucleation on Si by removing the Si-H bonds leaved on the Si surface by wet cleaning with diluted HF, because these Si-H bonds were supposed to be at the origin of the low density of seeds for ALD deposition. The first experiments exhibit unattended results : the deposition kinetic is strongly reduced, with a complex dependence with the parameters of the plasma (time , pressure and power). After further "optimization", we obtain a case were no deposition is observed till 120cycles, and an apparent deposited thickness of 12nm after 250cycles. For this last experiment, we observed, for the first time, by AFM nuclei of Al₂O₃, confirming that, for this case the initial seed density is around 0.002% of the Si surface density. Assumptions for the explanation of these results are made, involving cleanness of the surface, and leading for promising results in micro-electronic applications.

[1] : Gakis et al., J. Appl. Phys., 2019[

2] : Gakis et al. RAFALD 2019 Toulouse