



**HAL**  
open science

# EFFECT OF PROCESS PARAMETERS ON IMPACT ON COMPOSITES AND COMPRESSION AFTER IMPACT

Florentin Berthet, Alvine Njionhou, Bruno Castanié, Christophe Bouvet

► **To cite this version:**

Florentin Berthet, Alvine Njionhou, Bruno Castanié, Christophe Bouvet. EFFECT OF PROCESS PARAMETERS ON IMPACT ON COMPOSITES AND COMPRESSION AFTER IMPACT. ECCCS 2022 - 2nd European Conference on Crashworthiness of Composite Structures, Nov 2022, Toulouse, France. hal-03869022

**HAL Id: hal-03869022**

**<https://hal.science/hal-03869022>**

Submitted on 16 Mar 2023

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

## EFFECT OF PROCESS PARAMETERS ON IMPACT ON COMPOSITES AND COMPRESSION AFTER IMPACT

Florentin Berthet<sup>1</sup>, Alvine Njionhou<sup>1</sup>, Bruno Castanié<sup>1</sup>, Christophe Bouvet<sup>1</sup>,

<sup>1</sup>ICA Institut Clément Ader

IMT Mines Albi-Carmaux, 81013 Albi Cedex 09, Albi, France

Email: [florentin.berthet@mines-albi.fr](mailto:florentin.berthet@mines-albi.fr), web page: <https://www.imt-mines-albi.fr/>

**Keywords:** Composites, Liquid resin infusion, impact testing

### ABSTRACT

The purpose of this article is the question of the possible link between composite processing and impact and post-impact behaviour [1,2,3,4].

A Taguchi method of design of experiments was used to establish possible links between processing parameters and impact and compression after impact behaviour. The processing method studied is liquid resin infusion of stitched or unstitched preforms made of carbon quadri-axial Non-Crimp Fabric (NCF). Five process parameters were selected (stitching, cure temperature, preform position, number of high porous media and vacuum Level). The parameters used are shown in Table 1.

Table 1: parameters used in experimentation.

Plate N°	Plate side	Stitching	Curing temperature (°C)	Number of HPM	Vacuum level (mbars)
1	Vacuum	Without	180	1	1.3
2	Injection	Without	180	1	1.3
3	Vacuum	Without	160	2	1.4
4	Injection	Without	160	2	1.4
5	Vacuum	Yes	180	2	1.6
6	Injection	Yes	180	2	1.6
7	Vacuum	Yes	160	1	1.4
8	Injection	Yes	160	1	1.4
9	Vacuum	Yes	170	2	1.3
10	Injection	Yes	170	2	1.3

Table 1 gives an idea of parameters that have been varied and how, during experimentation (fabrication of plates).

The general equation of a linear model for a property Y takes the form of equation 1.

$$Y = C + a. CO + b. Tc + c. NHMP + d. Cp + e. VL \quad (1)$$

Where

- CO is stitching
- Tc is cure temperature
- NHMP is number of high porous media
- Cp is plate side of composite
- VL is vacuum level




Figure 1: Delaminated surface as function of number of high porous media.

The statistical analysis done showed a very high sensitivity to stitching of many properties what was of course expected.

Stitching was found influent on After impact compression strength, elastic energy, absorbed energy and residual dent depth. Damaged area was found sensitive to number of high porous media (Figure 1)

Residual dent depth was found sensitive to stitching, cure temperature and side of the plate.

## REFERENCES

- [1] A. Njionhou, F. Berthet, et B. Castanié. *Effects of process parameters on the mechanical properties and morphology of stitched and non-stitched carbon/epoxy liquid resin-infused NCF laminate, out of autoclave and out of oven*. The International Journal of Advanced Manufacturing Technology, 2013, vol. 65, no 9, p. 1289-1302.
- [2] F. Berthet, et al. "rtm carbon composites: influence of process parameters on compression strength after impact." *ICCM 11-11th International conference on composites materials*. 1997.
- [3] A. Njionhou, F. Berthet, et B. Castanié, and al. "Relationships between LRI process parameters and impact and post-impact behaviour of stitched and unstitched NCF laminates". *Applied Composite Materials*, 2012, vol. 19, no 6, p. 885-899.
- [4] A. R. Brindle, and X. Zhang. "Predicting the compression-after-impact performance of carbon fibre composites based on impact response." *Proc of 17th int conf in composite materials (ICCM17)*, Edinburgh, UK. 2009.