



**HAL**  
open science

## Impact of $\gamma$ -radiation on carbon steel anaerobic corrosion and H<sub>2</sub> production.

Stavroula Isidora Giannakandropoulou, Hortense Desjonqueres, Charles Wittebroodt, Gérard Baldacchino

### ► To cite this version:

Stavroula Isidora Giannakandropoulou, Hortense Desjonqueres, Charles Wittebroodt, Gérard Baldacchino. Impact of  $\gamma$ -radiation on carbon steel anaerobic corrosion and H<sub>2</sub> production.. Radiation Physics and Chemistry, 2023, 206, pp.110742. 10.1016/j.radphyschem.2022.110742 . hal-03909667v1

**HAL Id: hal-03909667**

**<https://hal.science/hal-03909667v1>**

Submitted on 21 Dec 2022 (v1), last revised 9 Jan 2024 (v2)

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial - NoDerivatives 4.0 International License

1 “Impact of  $\gamma$ -radiation on carbon steel anaerobic corrosion and H<sub>2</sub>  
2 production.”

3 **Authors list / affiliations**

4 Stavroula-Isidora Giannakandropoulou<sup>1,3</sup>, Hortense Desjonqueres<sup>1</sup>, Charles Wittebroodt<sup>2\*</sup>, Gérard  
5 Baldacchino<sup>3</sup>

6 <sup>1</sup>Institut de Radioprotection et de Sûreté Nucléaire (IRSN), PSN-RES/SCA/LECEV, 91191, Gif-sur-  
7 Yvette, France; <sup>2</sup>Institut de Radioprotection et de Sûreté Nucléaire (IRSN), PSE-ENV/SEDRE/LETIS,  
8 92260, Fontenay-aux-Roses, France; <sup>3</sup>Université Paris-Saclay, CEA, CNRS, LIDYL, 91191, Gif-sur-  
9 Yvette, France.

10

11 **Abstract**

12 This article reports investigations on the anoxic corrosion process impacting a carbon steel/ultrapure  
13 deaerated water system when it is exposed to gamma radiation (50 Gy h<sup>-1</sup>), and on the associated  
14 molecular hydrogen gas generation. On the one hand, a dynamic semi-open experimental setup allowing  
15 to distinguish between the H<sub>2</sub> production related to water radiolysis and the one related to anoxic  
16 corrosion has been adopted to estimate the corrosion rate associated to three successive temporal phases:  
17 pre-irradiation, irradiation and post-irradiation phases. On the other hand, *post mortem* analyses  
18 performed on both liquid and solid samples permitted to (i) quantify the chemical changes occurring in  
19 solution due to the formation of water radiolysis products and (ii) observe and characterize the thin  
20 corrosion layer composed of magnetite (Fe<sub>3</sub>O<sub>4</sub>) at the surface of the metallic coupons. We show that  
21 gamma radiation induces a slight diminution of the carbon steel corrosion rate. However, by comparing  
22 the mean corrosion rate values obtained for the three studied phases (i.e., before, during and after  
23 irradiation), the chemical changes caused by radiolytic species seem to inhibit the formation of a thick  
24 magnetite protective layer. Additionally, the corrosion rate observed in post-irradiation phase does not  
25 decrease over time, which suggests that irradiation could modify the properties of the corrosion product

---

\* Corresponding author. *Email address*: charles.wittebroodt@irsn.fr (C. Wittebroodt).

26 layer by making it less protective. A structural modification of this oxide film might be caused by the  
27 oxidizing water radiolysis products. Such mechanisms may favour continuous active corrosion  
28 processes rather than passivation of the metallic surface and thus lead to a reduced lifetime of the  
29 component.

### 30 **Keywords**


31 Anoxic corrosion; carbon steel; water radiolysis;  $\gamma$ -rays; hydrogen production

32


#### 33 1. Introduction

34 Deep geological disposal of high-level radioactive waste (HLW) is foreseen by several countries to  
35 protect living organisms from long-term radioactive contamination [1,2]. In France, according to the  
36 multi-barrier concept developed by Andra (French radioactive waste management agency), HLW would  
37 be embedded in a glass matrix cooled in a stainless steel container. This package would be then  
38 encapsulated into cylindrical carbon steel overpack and inserted in a carbon steel casing tube within  
39 horizontal micro-tunnel drilled in the highly impermeable Callovo-Oxfordian (COx) clay rock of the  
40 Paris Basin [3,4]. A bentonitic cement-based grout material would be injected between the steel casing  
41 and the host rock in order to (i) neutralize the acidity coming from pyrite oxidation in the COx while  
42 preserving glass from detrimental highly alkaline media, (ii) limit oxygen diffusion and microbial  
43 activity and (iii) passivate the steel casing. If carbon steel casing should ensure adequate mechanical  
44 function over a century to allow the nuclear waste to be retrieved from the deep geological disposal  
45 concept, carbon steel overpack must remain leakproof for a few thousand years to prevent natural clayey  
46 porewater seeping from the host rock from reaching the vitrified waste during the thermal phase [4].  
47 Throughout the duration of the operational phase of the project and long after the closure of the disposal  
48 facility, several corrosion processes are expected to occur in a series of distinct environments (i.e., in  
49 oxic or anoxic conditions, in contact with liquid or vapour phase solution, in contact with solution whose  
50 chemical composition evolves over time due to the continuous percolation of clayey porewater through  
51 the bentonitic cement grout material) which will gradually impair the carbon steel and finally induce  
52 mechanical failure of the metallic component [5]. Predominant over the long term, carbon steel anoxic

53 corrosion process will progressively attack the metallic elements, with a mean corrosion rate value  
54 between 0.1-10  $\mu\text{m year}^{-1}$  [3,6–8]. Under these conditions, iron will interact with water to produce  
55 ferrous hydroxide ( $\text{Fe}(\text{OH})_2$ ) and hydrogen gas ( $\text{H}_2$ ):



57 When the Schikorr reaction (reaction 2) occurs, ferrous hydroxide ( $\text{Fe}(\text{OH})_2$ ) can be then transformed  
58 to the more thermodynamically stable magnetite ( $\text{Fe}_3\text{O}_4$ ):



60 In natural or artificial porewater, or in presence of bentonite, iron can react with dissolved species to  
61 form other corrosion products such as siderite ( $\text{FeCO}_3$ ) through the overall reaction:



63 where M is a balancing univalent cation [9]. As shown in reactions (2) and (3), anoxic corrosion process  
64 will produce magnetite and/or siderite as main corrosion products and generate significant amounts of  
65 hydrogen. Thus, such anoxic corrosion processes induce corrosion products the formation of corrosion  
66 products leading to the progressive protection of the metallic surface. However, this beneficial  
67 phenomenon is always accompanied by the production of  $\text{H}_2$  gas whose accumulation may significantly  
68 affect mid- and long-term safety of the disposal facility. On the one hand, its high flammable and  
69 explosive properties represent a risk during the operational phase and on the other hand, the consequent  
70 overpressure is liable to lead to incomplete saturation of bentonite sealing plugs aiming at mitigating the  
71 migration of radionuclides through disposal installation [5-9]. In addition, it is noteworthy that all these  
72 corrosion processes will take place on carbon steel component exposed to ionizing radiations originating  
73 from nuclear waste. These radiations will lead to the radiolysis of percolated porewater which forms  
74 radiolytic species such as radicals ( $e_{\text{aq}}^-$ ,  $\text{H}^\cdot$ ,  $\cdot\text{OH}$ ), molecular products ( $\text{H}_2\text{O}_2$ ,  $\text{H}_2$ ) and ionic species  
75 ( $\text{H}_3\text{O}^+$ ), according to reaction (4) [10-11]:



77 These chemical species, whose concentrations are dependent on LET (Linear Energy Transfer, defined  
78 as the amount of energy deposited by the charged particle along its path in solution) are prone to modify  
79 the physico-chemical conditions at the metal-water interface, and thus to impact the corrosion processes  
80 and the associated corrosion rate. Furthermore, these formed radiolytic species include H<sub>2</sub> gas, meaning  
81 that porewater radiolysis will also lead to the additional production of this problematic gas [5,12-13].

82 Therefore, to contribute to the long-term safety assessment of such deep geological disposal, dedicated  
83 research programs have been committed to study steel corrosion under irradiation and the associated  
84 hydrogen gas production. The various experimental techniques that have been used to measure uniform  
85 corrosion rates can be grouped as follow: weight loss measurements [13], hydrogen gas production  
86 monitoring [14] and electrochemical measurements [15]. While a range of individual studies has been  
87 performed to understand the impact of several parameters such as the dose rate (or total dose), the  
88 temperature or the physico-chemical properties of the solution, the observed effects of ionizing radiation  
89 on steel corrosion are still conflicting. Even though, most studies demonstrate that carbon steel corrosion  
90 rate is enhanced by radiation exposure [13,16-17], some others tend to indicate the contrary [18–20]. In  
91 parallel, while a large majority of the works cited above agreed on the fact that magnetite (Fe<sub>3</sub>O<sub>4</sub>) is the  
92 predominant corrosion product which is formed under such experimental conditions, many key  
93 questions regarding the mid and long term evolution of this oxide film properties, induced by the  
94 physico-chemical modifications of the solution caused by irradiation, remain unanswered.

95 The primary motivation of the work presented in this article is to investigate the impact of gamma  
96 radiation on carbon steel anoxic corrosion processes in order to (i) quantify the H<sub>2</sub> production and (ii)  
97 estimate the associated corrosion rate allowing an optimisation of the metallic elements design. As an  
98 initial approach, ultrapure deaerated water has been used in order to study a simplified system allowing  
99 to capture the main radiolytic processes that could influence the corrosion processes. While almost all  
100 studies dealing with the impact of ionizing radiations on steel corrosion processes have been performed  
101 in closed systems, the present work is meant to get closer to the real disposal conditions by working in  
102 a semi-open system. This experimental setup allows to distinguish between the H<sub>2</sub> production related to  
103 water radiolysis and the one related to anoxic corrosion, making possible the estimation of associated


104 corrosion rate. Finally, *post mortem* analysis are performed on the metallic samples surface to identify  
105 neoformed corrosion products, and chemical characteristics of the solution are determined.

106

## 107 2. Materials and Methods

### 108 2.1. Experimental setup

109 A schematic overview of the innovative dynamic experimental set up used in this work to study the  
110 impact of gamma radiation on anoxic corrosion of steel processes is given in Figure 1. It allows to  
111 differentiate the hydrogen production attributed to anoxic corrosion and the one imputed to radiolytic  
112 process, by measuring continuously the H<sub>2</sub> gas generated by two parallel systems: one cell containing  
113 six carbon steel samples immersed in pure deaerated water, the other cell containing only pure deaerated  
114 water. These two stainless steel cells are placed into an irradiation chamber where they are exposed to  
115 gamma-radiation and their H<sub>2</sub> evolution is recorded using in-line gas chromatography. This paper reports  
116 the results associated with two successive series of experimental tests (Exp-A and Exp-B) where  
117 hydrogen production is monitored before, during and after irradiation under anoxic conditions and at  
118 ambient temperature.



119

120 **Fig. 1:** Schematic view of the experimental set-up and presentation of the adopted procedure, from the  
121 preparation and closure of the cells until their dismantlement.


122

## 123 2.2. Experimental procedure

124 Corrosion experiments are performed on coupons (50 x 10 x 1 mm) of commercially available S235  
125 carbon steel (max. 0.17 wt% of C, 1.40 wt% of Mn, 0.03 wt% of Sb, 0.02 wt% of P, 0.02 wt% of S). To  
126 minimize the amount of surface oxide present before the start of Exp-A, four metallic samples are  
127 roughly polished using #220 and #1200 SiC paper ("AR-coupons"), and two other samples are further  
128 polished using diamond paste, obtaining a smooth mirror surface ("AP-coupons"). For Exp-B, the six  
129 metallic samples are roughly polished ("BR-coupons") with the same procedure described above. After  
130 polishing, which takes place only few hours before the experiment, the samples are cleaned for 10  
131 minutes with ethanol in an ultrasonic bath and then they are let to dry. For experimental system involving  
132 metallic samples (A1-cell and B1-cell), the six coupons are inserted in a dedicated borosilicate glass  
133 sample holder which allow to maximize the carbon steel surface available for corrosion processes. The  
134 sample holder is then introduced in a borosilicate glass beaker containing a volume of 200 mL of  
135 ultrapure (Millipore Alpha-Q with an electrical resistivity of 18.2 M $\Omega$ ) deaerated water sufficient to  
136 ensure a total immersion of the coupons. The beaker is then emplaced in a stainless steel cell made up  
137 of a cylindrical body (10.4 cm, r=11cm) and a cover fitted with a tin seal allowing it to be hermetically  
138 closed. The cell cover is fitted with two stainless steel line allowing the circulation of a carrier gas. The  
139 input line has a sufficient length to get into the solution contained in the beaker whereas the output line  
140 internal extremity is located at the same level as the beaker upper part (Figure 2). Both lines are equipped  
141 with a valve on their external part to avoid any unintended oxygen contamination during cells  
142 transportation. In parallel, experimental system dedicated to ultrapure deaerated water radiolysis study  
143 (A2-cell and B2-cell) is prepared following the same procedural steps as in the case of experimental  
144 system involving metallic samples, except the introduction of the sample holder containing the coupons.  
145 To ensure that inert atmosphere prevail in our experimental cells and to avoid any further oxidation of  
146 the metallic coupons, all these preparation processes are performed in an anoxic glove box under

147 continual nitrogen ( $N_2$ ) flow. Once the cells are closed their tightness is checked via leak detector  
148 (Leybold Inficon, UL 200).

149



150

151 **Fig. 2:** Schematic view of a stainless steel cell containing carbon steel samples (cell A1 & B1). Metallic  
152 coupons, sample holder and pure deaerated water are placed into a glass beaker before entering the cell.

153

### 154 2.3. Irradiation experiments

155 Each experimental test involves two cells: a first one containing ultrapure deaerated water and metallic  
156 samples and a second one containing only ultrapure deaerated water. After their preparation under inert  
157 atmosphere, both cells are hermetically closed and carried from the glove box to the irradiation chamber  
158 of IRMA (IRradiation MAterials) facility, of the Institute for Radiological Protection and Nuclear Safety  
159 (IRSN), located at Saclay research center. The IRMA facility, by design, allows on-line measurements  
160 during the irradiation phases. Thanks to the input/output lines, the cells are then connected to the  
161 circulation system making possible to inject a carrier gas into the solution (input line) and to flow  
162 continuously the produced hydrogen gas towards a gas chromatograph (output line) *via* flow-controllers,  
163 set at  $5 \text{ ml min}^{-1}$ . In IRMA facility, materials are submitted to gamma radiation thanks to four cylindrical



164 sealed sources of  $^{60}\text{Co}$  ( $T_{1/2} = 5.27$  years). At the date of the experiments, the total activity of the sources  
165 was about 774 TBq and 684TBq for Exp-A and Exp-B, respectively. In order to achieve an estimation  
166 of the real conditions that would prevail in a repository environment, a rather low dose rate of 50 Gy h<sup>-1</sup>  
167 (corresponding to approximately five times to the predicted *in situ* dose rate) is applied. The  
168 calculations of the theoretical distances between the sources and the cells, required to obtain the desired  
169 dose rate, were carried out with a dedicated software (Microshield® 9.07). These distances are  
170 afterwards validated by measuring the dose rate using a calibrated ionization chamber, at the defined  
171 locations, in the presence of radioactive sources. Hence, the cells were placed about 1 m from the sources  
172 support, behind a 5 cm width steel shield for Exp-A and a 2 cm width lead shield for Exp-B. For Exp-  
173 A and Exp-B, the duration of the test under irradiation was 15 and 16 days respectively, corresponding  
174 to a total absorbed dose of 18 and 20 kGy (in comparison with the 87660 kGy that a metallic component  
175 should absorb over a period of 1000 years considering a reference dose rate of 10 Gy h<sup>-1</sup>.

176

#### 177 2.4. Hydrogen measurements

178 Hydrogen ( $\text{H}_2$ ) is measured with a gas chromatograph VARIAN 450-GC. High purity helium is used as  
179 the carrier gas with a pressure of 200 kPa. The analyzed gas sample volume is 1 mL. The column is a  
180 Molecular Sieve 5A (length = 3m and diameter = 3.17 mm). The detection is performed using a Pulsed  
181 Discharge Helium Ionization Detector (PDHID detector). The GALAXIE software (Galaxie  
182 chromatography Data System) is used to collect data. Calibration of the detector is performed by  
183 injection of a mixture of  $\text{H}_2/\text{O}_2/\text{N}_2/\text{He}$  gas (gas mixture X50A, AirProducts) and uncertainty associated  
184 to gas measurement is estimated to be less than 10%. Accordingly to a predetermined analytical  
185 sequences, hydrogen production relative to each cell is independently measured every 20 minutes  
186 before, during and after irradiation period. This measurement is performed on 1 mL of gas which is  
187 sampled from the system and analysed by the gas chromatograph. Such measurement allowed to know  
188 the exact amount of  $\text{H}_2$  (ppm) contained in this 1 mL gas sample and after a conversion, one can obtain  
189 the number of  $\text{H}_2$  nanomoles present in this 1 mL gas sample. Since carrier gas ( $\text{He}$ ) circulates at a flow  
190 rate fixed at 5 mL min<sup>-1</sup>, the number of  $\text{H}_2$  nanomoles is multiplied by a factor 5 to obtain the number

191 of H<sub>2</sub> nanomoles generated by the experimental system during a 1-minute period (nmol min<sup>-1</sup>). Once  
192 irradiation phase stopped, cell containing only ultrapure deaerated water is disconnected from the  
193 circulation system whereas cell containing metallic samples and ultrapure deaerated water remains  
194 connected for some days more. Corrosion rate is estimated due to the precise measurement of molecular  
195 hydrogen production in the cells. By subtracting the H<sub>2</sub> production associated to the cells containing  
196 only pure deaerated water (cells A2 and B2) from the one generated by the cells containing pure  
197 deaerated water and metallic samples (cells A1 and B1), it should permit to estimate the volume of  
198 hydrogen generated only by the process of anoxic corrosion under irradiation during a 1-minute period  
199 (nmol min<sup>-1</sup>). At this point, it should be mentioned that the potential impact on H<sub>2</sub> production induced  
200 by the additional water/glass surface interface arising from the sample holder, present only in the cells  
201 A1 and B1, is assumed to be quite limited and is not considered in our calculation. The corresponding  
202 number of H<sub>2</sub> nanomoles that are generated by our experimental system in a 1-year period (nmol year<sup>-1</sup>)  
203 is calculated and associated to the total surface area of our metallic samples to obtain the number of  
204 H<sub>2</sub> nanomoles produced by the anoxic corrosion of the metallic coupons during a 1-year period (nmol  
205 m<sup>-2</sup> year<sup>-1</sup>). These H<sub>2</sub> production values (nmol m<sup>-2</sup> year<sup>-1</sup>) are then converted in corrosion rate (μm year<sup>-1</sup>)  
206 values by using a conversion factor. This conversion factor is selected after the end of the experiment,  
207 accordingly to the main corrosion product that is identified after structural characterization of the  
208 sample's surface, as explained in previous study [21].

## 209 2.5. *Post mortem* analyses

210 At the end of the experimental tests, the cells are disconnected from the circulation system and moved  
211 into the glove box to be dismantled in order to collect the carbon steel coupons and the solutions under  
212 anoxic conditions.

### 213 2.5.1 Liquid samples

214 pH values of the solutions are measured immediately after the opening of the cells using a pH meter  
215 (Multi 3420, WTW) with a glass electrode (ADA S7/IDS, WTW). For the solution collected in the cell  
216 containing only ultrapure deaerated water, the concentration of hydrogen peroxide (H<sub>2</sub>O<sub>2</sub>) is determined

Commenté [LG1]: Lina's version

217 in less than 24 hours after the end of the irradiation phase with the Ghormley triiodide method [22]. Two  
218 reagents are used: the first one is a mixture of potassium iodide (KI, VWR), potassium hydroxide (KOH,  
219 Fluka) and ammonium heptamolybdate ((NH<sub>4</sub>)<sub>6</sub>Mo<sub>7</sub>O<sub>24</sub>, VWR), and the second one is a buffer mixture  
220 (pH = 6) of potassium phthalate (C<sub>8</sub>H<sub>4</sub>K<sub>2</sub>O<sub>4</sub>, Merck) and phthalic acid (C<sub>8</sub>H<sub>6</sub>O<sub>4</sub>, Merck). For a total  
221 volume of 3 mL, 750 μL of both reagents are mixed with 1.5 mL of the sampled solution. After ten  
222 minutes of reaction, the concentration of H<sub>2</sub>O<sub>2</sub> is indirectly determined by measurement of I<sub>3</sub><sup>-</sup> absorbance  
223 with the UV-VIS spectrophotometer UV-2600 (Shimadzu). For the studied solution, at ambient  
224 temperature, the molar extinction of I<sub>3</sub><sup>-</sup> at the 348 nm wavelength is estimated at 25800 L mol<sup>-1</sup> cm<sup>-1</sup>.  
225 For the solution collected in the cell containing both ultrapure deaerated water and metallic samples, the  
226 concentration of total dissolved iron (Fe<sub>tot</sub>) is measured after acidification (HNO<sub>3</sub>) by Inductively  
227 Coupled Plasma Atomic Emission Spectroscopy (ICP-AES), using a iCAP 7600 Duo (Thermo Electron)  
228 apparatus. The concentration of silicon (Si) is also determined by ICP-AES.

#### 229 2.5.2 Solid samples

230 During the dismantling of the experimental cell in the anoxic glove box, metallic coupons are collected,  
231 rinsed with ethanol and dried to prevent post-oxidation. They are then introduced into airtight boxes  
232 stocked inside the anoxic glove box. Out of the six coupons involved in each experimental test, two  
233 coupons are dedicated to microstructural characterization, two other coupons are used for weight loss  
234 measurement and corrosion rate estimation and the two last coupons are retained for additional analyses.  
235 One should note that all the analysed metallic samples have been submitted to irradiation and that no  
236 reference metallic sample (corroded without irradiation) has been studied in this work. Morphology and  
237 chemical composition of the corrosion products formed at the surface of the carbon steel samples are  
238 firstly investigated using a Scanning Electron Microscopy (SEM) coupled to Energy Dispersive  
239 Spectroscopy (EDS). Analysis is performed using a Field Emission Gun (FEG) JSM7000-F SEM  
240 apparatus (JEOL) under an accelerating voltage of 15 kV. Sample surface images are obtained using  
241 both Secondary Electron (SE) mode and BackScattered Electron (BSE) mode. EDS spectra are collected  
242 on point of interest using a silicon-drift detector (Bruker AXS). Samples are brought to the microscope  
243 in an airtight anoxic box and all subsequent transfers are done rapidly (less than one minute) to minimize

244 exposure to oxygen. For optical imaging and micro-Raman ( $\mu$ Raman) spectroscopy, metallic coupons  
245 are kept in airtight anoxic box equipped with a 1 mm thick glass window. Samples surfaces are imaged  
246 with an Olympus MX41 microscope equipped with a CCD camera.  $\mu$ Raman spectra are obtained using  
247 a LabRam HR800 spectrometer equipped with an Olympus MX41 microscope. YAG solid-state laser  
248 with wavelengths of 532 and 785 nm are used as excitation sources and power outputs are kept at  
249 reasonably low values ( $\approx 500 \mu\text{W}/\mu\text{m}^2$ ) to limit thermal degradation.

### 250 2.5.3 Weight loss measurement

251 In the anoxic glove box, gravimetric measurements are performed on the dedicated metallic coupons  
252 which have been initially weighted. At the end of the irradiation phase, these coupons are weighted  
253 before and after being soaked in ultrasonic baths, with intermediate rinsing in deionized water between  
254 each bath. This operation is repeated until the weight stabilization of the coupons. Such soaking stages  
255 aim to remove the corrosion products present at the surface of the metallic sample without dissolving  
256 carbon steel material. The solution contained in the bath is composed of 50% m distilled water + 50% m  
257 HCl (37%, VMR) containing  $5 \text{ g L}^{-1}$  of hexamethylenetetramine ( $(\text{CH}_2)_6\text{N}_4$ , VMR) as an inhibitor of  
258 iron dissolution under acidic conditions, and the duration of each bath is 5 minutes. The weight of the  
259 coupons is measured using a high accuracy mass balance (XP205DR, METTLER TOLEDO) to allow  
260 an estimate of the average general corrosion rate ( $r$ , in  $\mu\text{m}/\text{y}$ ). The thickness ( $e$ , in  $\mu\text{m}$ ) of metal damaged  
261 by corrosion is calculated according to (5):

$$262 \quad e = \Delta m / (S \times \rho(\text{Fe})) \quad (5)$$

263 where  $S$  is the surface area,  $\Delta m$  is the mass difference, and  $\rho(\text{Fe})$  is the iron density. The general  
264 corrosion rate  $r$  is given by (6):

$$265 \quad r = e / t \quad (6)$$


266 where  $t$  is time (in year).

267

## 268 3. Results

269 3.1. Hydrogen gas generation and corrosion rate measurements


270 The evolution of hydrogen gas ( $H_2$ ) production arising from the experimental cells tested during both  
271 Exp-A and Exp-B are shown in Figure 3. The evolutions of the temperature measured in the IRMA



272 irradiation chamber during these two experiments are also reported in Figure 3. A comparison of the  
273 hydrogen gas generation associated with the two cells containing carbon steel samples immersed in pure  
274 deaerated water (A1-cell and B1-cell) is proposed in Figure 4.

275


276 **Fig. 3:** Hydrogen productions evolution measured during the three studied phases (before, during and  
277 after irradiation) for experiments A and B with the associated temperature evolutions.



278  
 279 **Fig. 4:** Hydrogen productions evolution measured during the three studied phases (before, during and  
 280 after irradiation) for cell A1 & B1 (ultrapure deaerated water and metallic samples).

281  
 282 For both cells, we can observe the very first H<sub>2</sub> production measurements performed before the  
 283 irradiation phase that correspond to the hydrogen gas generated by carbon steel anoxic corrosion  
 284 process. Then, the H<sub>2</sub> production measurements recorded during the irradiation phase correspond to the  
 285 hydrogen gas generated by both water radiolysis and carbon steel anoxic corrosion processes. Finally,  
 286 the last H<sub>2</sub> production results recorded after the irradiation phase correspond to the hydrogen gas  
 287 generated by carbon steel anoxic corrosion process taking place post-irradiation. In parallel, Figure 5  
 288 presents the evolutions of the hydrogen gas produced by the two cells containing only pure deaerated  
 289 water (A2-cell and B2-cell), which is exclusively generated by water radiolysis.

290



291  
 292 **Fig. 5:** Hydrogen productions evolution measured during the three studied phases (before, during and  
 293 after irradiation) for cell A2 & B2 (ultrapure deaerated water only).

294  
 295 For all cells, the average and maximum values of hydrogen gas produced during the three tested phases  
 296 (i.e., before, during and after irradiation) are given in Table 1. Average and maximum corrosion rates  
 297 determined from these hydrogen gas generation are presented in Table 2. Table 3 presents the corrosion  
 298 rate values that have been calculated from weight loss measurements performed either on 2 metallic  
 299 samples for experiment A or on 1 metallic sample for experiment B.

300  
 301  
 302  
 303

cell	H <sub>2</sub> production before irradiation (nmol min <sup>-1</sup> )	H <sub>2</sub> production during irradiation (nmol min <sup>-1</sup> )	H <sub>2</sub> production post-irradiation (nmol min <sup>-1</sup> )
A1	2.5 ± 0.1	16.2 ± 0.7	2.8 ± 0.2
B1	2.8 ± 0.1	14.2 ± 0.4	3.0 ± 0.1
A2	0.0	15.4 ± 0.9	-
B2	0.0	13.8 ± 0.9	-

304  
305 **Table 1:** Average values of H<sub>2</sub> production obtained for the three studied phases (before, during and after  
306 irradiation) of experiments A and B.

307

corrosion rate via H <sub>2</sub> gas measurements (µm year <sup>-1</sup> )		before irradiation	during irradiation	post-irradiation
A1	Average	1.1 ± 0.1	0.3 ± 0.4	1.2 ± 0.1
	Maximum	1.1	1.1	1.4
B1	Average	1.2 ± 0.1	0.2 ± 0.4	1.2 ± 0.1
	Maximum	1.2	0.8	1.3

308  
309 **Table 2:** Mean corrosion rate values (obtained *via* H<sub>2</sub> production monitoring) for the three studied phases  
310 (before, during and after irradiation) of experiments A and B.

311

corrosion rate <i>via</i> weight loss measurements (µm year <sup>-1</sup> )	
A1 (2 metallic samples)	4.8 (± 0.3)
B1 (1 metallic sample)	1.9 (± 0.3)

312  
313 **Table 3:** Mean corrosion rate values (obtained *via* weight loss measurements) for experiments A and B.

314

### 315 3.2. *Post mortem* analyses

#### 316 3.2.1 Liquid samples



317 Once the irradiation stops, cells A2 and B2 were dismantled in the anoxic glove box. Hydrogen peroxide  
 318 ( $\text{H}_2\text{O}_2$ ) concentration measurement was performed within 24 hours after the end of irradiation for cell-  
 319 A2 only, and the associated result is  $0.52 \times 10^{-6} \text{ mol L}^{-1}$ . After the end of the experiment, A1 and B1  
 320 were also dismantled in the anoxic glove box. The collected solutions, showed a slightly grey coloration,  
 321 were analyzed to determine the quantity of the released dissolved iron. In cells A1 and B1 the dissolved  
 322 iron was measured in comparable concentrations at  $0.34 \text{ mmol L}^{-1}$  and  $0.25 \text{ mmol L}^{-1}$ , respectively.  
 323 Furthermore, the initial and final values of pH were recorded in the glove box for each cell just before  
 324 their closure and just after their dismantling. All the above mentioned measurements results are  
 325 summarized in Table 4.


cells	initial pH ( $\pm 0.2$ )	final pH ( $\pm 0.2$ )	[Fe <sub>total</sub> ] ( $\text{mmol L}^{-1}$ )	[H <sub>2</sub> O <sub>2</sub> ] ( $\mu\text{mol L}^{-1}$ )
A1	6.5	5.4	$0.34 \pm 0.01$	-
B1	6.6	6.0	$0.25 \pm 0.07$	-
A2	6.5	4.4	-	$0.52 \pm 0.09$
B2	6.6	4.3	-	-

326  
 327 **Table 4:** Overview of the solution chemical characteristics. Initial and final pH values, final total iron  
 328 concentrations ([Fe<sub>total</sub>]) and final hydrogen peroxide concentration ([H<sub>2</sub>O<sub>2</sub>]).

329

### 330 3.2.2 Solid samples

331 After the end of the experiment, carbon steel samples have been structurally characterized as it is  
 332 depicted on Figure 6. Metallic coupons collected in cells A1 and B1 exhibited a darker appearance  
 333 regarding their initial state. We observed that this coloration is even more intense at the samples' edges.  
 334 In comparison with the "roughly polished" samples (AR and BR coupons), the "mirror surface" samples  
 335 (AP coupons) present a blurrier surface. Unfortunately, the first observation shows that the short  
 336 duration of our experiments does not permit the formation of a thick and significant corrosion layer, as  
 337 illustrated by the slightly corroded surface observed by optical imaging on "AR-coupon" (Fig. 6a), "AP-  
 338 coupon" (Fig. 6b) and "BR-coupon" (Fig 6c).



340 **Fig. 6:** Microstructural characterization of the carbon steel samples. Optical image of the corroded  
 341 surface of AR-coupon (a), AP-coupon (b) and BR-coupon (c). SEM image in Backscattered Electron  
 342 (BSE) mode of a roughly polished coupon before experiment (d), corroded surface of AR-coupon (e),  
 343 corroded surface of BR-coupon (g) and corroded surface of AP-coupon (i). Composite BSE image –  
 344 EDS elements map highlighting the areas enriched in Si on corroded surface of AR-coupon (f), corroded  
 345 surface of BR-coupon (h) and corroded surface of AP-coupon (j).  $\mu$ Raman spectrum collected on the  
 346 corroded surface of AR-coupon (k) and on the corroded surface of AP-coupon (l).

347  
 348 Surface examination using SEM-FEG microscopy have been performed on the surface of the metallic  
 349 samples using Back Scattered Electron (BSE) as well as Secondary Electron (SE) mode. When  
 350 comparing the initial surface of a roughly polished sample (Fig. 6d) with the final one of “AR-coupon”  
 351 (Fig. 6e) and “BR-coupon” (fig 6g), we observe the formation of corrosion products mainly composed  
 352 of hexagonal-shaped magnetite nanoplates. Surprisingly, such crystals formation has not been identified  
 353 for “AP-coupon” (Fig 6i). Associated  $\mu$ Raman analyses indicated the presence of magnetite ( $\text{Fe}_3\text{O}_4$ ),  
 354 with a characteristic peak at  $675.68\text{ cm}^{-1}$  and at  $679.12\text{ cm}^{-1}$ , as the only identified corrosion product for  
 355 “AR-coupon” (Fig. 6k) and “AP-coupon” (Fig. 6l) respectively. On the other hand, it was not possible  
 356 to identify any corrosion product for “BR-coupon”, even though, fine hexagonal-shaped formations  
 357 observed in Fig. 6g. Moreover, it is worth mentioning that for both “AR-coupon” (Fig. 6f) and “BR-  
 358 coupon” (Fig. 6h), elemental mapping revealed the presence of a significant amount of silicon (Table  
 359 5).

Composition (at.%)						
	C	O	Na	Si	S	Fe
<b>AR-coupon (zone 1)</b>	6.6	51.2	0.2	11.9	0.1	29.9
<b>BR-coupon (zone 1)</b>	9.2	37.7	-	4.1	-	48.7
<b>BR-coupon (zone 2)</b>	12.4	13.3	-	0.1	2.2	72.0
<b>AP-coupon</b>	8.8	24.8	0.1	0.8	0.1	65.3

360  
 361 **Table 5:** EDX analyses of selected zones for AR-coupon, BR-coupon and AP-coupon. Selected zones  
 362 are illustrated in Fig. 6.

363

#### 364 4. Discussion

365 This study made possible to assess the quantities of H<sub>2</sub> produced by two parallel systems (cell-1  
366 containing six carbon steel samples immersed in pure deaerated water and cell-2 containing only pure  
367 deaerated water) before, during and after irradiation under anoxic conditions and at ambient temperature.  
368 Hydrogen productions associated to each system which have been measured during two successive  
369 series of experimental tests (Exp-A and Exp-B) indicate quite reproducible results for the three studied  
370 phases (before, during and after irradiation) (Fig.3), allowing us to validate our experimental setup.

371 Before irradiation, hydrogen production associated with the cells containing only pure deaerated water  
372 (A2 and B2) remains zero, as expected (Fig.5). During this short pre-irradiation phase, the average H<sub>2</sub>  
373 production measured for the cells containing carbon steel samples (A1 and B1) is in the range of 2.5 -  
374 2.8 x 10<sup>-9</sup> mol min<sup>-1</sup> (Fig.4). These fluxes of hydrogen, which are generated only through anoxic  
375 corrosion process, can be convert into corrosion rate values using a conversion factor [21] relevant for  
376 anoxic corrosion mechanism leading to the formation of magnetite (Fe<sub>3</sub>O<sub>4</sub>) as main corrosion product  
377 (*vide infra*). The corresponding calculated corrosion rate values range between 1.1 and 1.2 μm year<sup>-1</sup>.

378 Such values are in good agreement with literature data obtained in anoxic conditions and at near neutral  
379 pH, using ultrapure deaerated water [23], synthetic clay/granitic porewater [7-8], or numerical  
380 simulation with porewater [24], for greater time scales.

381 Once the irradiation phase starts, water radiolysis process takes place in cells A2 and B2, and we can  
382 immediately observe an intense production of H<sub>2</sub> (Fig.5). This is mainly due to recombination reactions  
383 occurring between hydrogen radicals and hydrated electrons [25]. According to Pastina et al. [26] the  
384 reactions (7), (8) and (9), which highlight the importance of hydrated electron (e<sub>aq</sub><sup>-</sup>) and H radical (H<sup>•</sup>)  
385 regarding molecular hydrogen formation, are responsible for the majority of H<sub>2</sub> formation:



Commenté [LG2]: Lina's version

389 Since we consider the case of gamma rays in this experiment, we assume these reactions occur in spurs  
390 following the ionization processes [27]. As a result, G-values represent the primary yields of water  
391 radiolysis species in the beginning of the homogeneous stage. The initial slope of the intense increase  
392 of H<sub>2</sub> should correspond to the H<sub>2</sub> G-value, under  $\gamma$ -rays,  $4.6 \times 10^{-8} \text{ mol J}^{-1}$  [28]. Using Figure 5 plots  
393 for pure deaerated water and the experimental parameters (dose rate of  $50 \text{ Gy h}^{-1}$ , measured volume of  
394 1 mL), we have determined the initial slope of H<sub>2</sub>-formation. We obtained  $5.03 \times 10^{-8} \text{ mol J}^{-1}$  and  $4.48$   
395  $\times 10^{-8} \text{ mol J}^{-1}$  for A2 and B2 respectively, which roughly agrees with the literature. In parallel, H<sub>2</sub> can  
396 be consumed by reacting towards  $\cdot\text{OH}$  according to reaction (10):




398 but not in a big extent as this reaction is relatively slow and due to the fact that the use of a semi-open  
399 system does not permit to H<sub>2</sub> gas to return to the liquid phase. A better explanation of the stabilization  
400 of H<sub>2</sub> production is the accumulation in the solution of a radiolytic species which can efficiently react  
401 with the precursors of H<sub>2</sub> i.e.  $e_{\text{aq}}^-$  and H atom as seen in reactions (7) to (9). This species in pure deaerated  
402 water, under gamma rays, is H<sub>2</sub>O<sub>2</sub>, since O<sub>2</sub> cannot accumulate due to a constant He-bubbling.

403 Moreover, H<sub>2</sub>O<sub>2</sub> can be formed as primary radiolytic species; but it can be also formed from HO<sub>2</sub> $\cdot$  [29].  
404 We can mention this eventuality in case of accidental inclusion of air in the system, since under gamma  
405 rays HO<sub>2</sub> $\cdot$  stems from the reaction of O<sub>2</sub> with  $e_{\text{aq}}^-$ . In deaerated water this mechanism is not relevant. The  
406 only pathway to form HO<sub>2</sub> $\cdot$  could be the reaction  $\text{OH} + \text{H}_2\text{O}_2$  that in fine produces H<sub>2</sub>O and O<sub>2</sub>, which is  
407 released into the atmosphere by bubbling. This might be relevant under high LET irradiation, e.g. alpha  
408 rays, [29] in the case of a real deep geological repository.

409 As shown in Fig.5, H<sub>2</sub> productions successively measured for cells A2 and B2 indicate quite similar  
410 evolution and correspond to average values of  $15.4 \times 10^{-9} \text{ mol min}^{-1}$  and  $13.8 \times 10^{-9} \text{ mol min}^{-1}$ ,  
411 respectively. For both cells, the initial H<sub>2</sub> production peak related to the beginning of the irradiation  
412 phase is followed by a sharp decrease taking place during the first 48h. After this, we observe a  
413 stabilization phase (between day 2 and day 4) which is followed by a progressive increase (between day  
414 4 and day 6) and then by a second stabilization period (between day 6 and day 10). The fact that the

Commenté [LG3]: GB version

415 similar bell-shaped trends that we notice in H<sub>2</sub> trends in the absence of metal are not in accordance with  
416 temperature evolution and there are not related to an accumulated pressure within the cell, makes us  
417 conclude that they should be more attributed to a kind of regulation, considering the presence of possible  
418 impurities. Impurities arising from anything in contact with the pure water solution could lead to  
419 interaction of very reactive radicals e.g., ·OH and this could impact hydrogen production, as the  
420 maintenance of a totally ultra-pure water system in practice is almost impossible. Finally, both cells  
421 display a progressive decrease of their H<sub>2</sub> production until the end of the irradiation phase. According  
422 to the literature, a possible explanation for this progressive H<sub>2</sub> decrease arises from the formation of  
423 other radiolytic products with compatible reaction rates. The major factor that could inhibit H<sub>2</sub> formation  
424 is the presence of hydrogen peroxide (H<sub>2</sub>O<sub>2</sub>). The latter, as its concentration rises, is able to scavenge  
425 the main precursor of hydrogen, i.e. the hydrated electron (e<sub>aq</sub><sup>-</sup>) [30], as shown by reaction (11):



427 and thus, to inhibit the formation of molecular hydrogen. H<sub>2</sub>O<sub>2</sub> was still identified in solution after a few  
428 hours necessary to collect sample in the cell A2 just after the end of irradiation. This low concentration  
429 (H<sub>2</sub>O<sub>2</sub> = 0.52 × 10<sup>-6</sup> mol L<sup>-1</sup>, see Table 4) is the H<sub>2</sub>O<sub>2</sub> concentration remaining in solution after  
430 irradiation. Then it suggests that reaction (11) occurred during irradiation.

431 Even if it seems that the H<sub>2</sub> production is influenced by the temperature fluctuations (Fig.3), it is  
432 somehow difficult to definitely state on the real impact of temperature on hydrogen production. On the  
433 one hand, the decrease of the temperature recorded between day 11 and day 13 for Exp-A seems to  
434 induce a diminution of the H<sub>2</sub> produced in cell A2. On the other hand, the increase of H<sub>2</sub> production  
435 observed between day 4 and day 6 takes place during a temperature decrease suggesting that temperature  
436 has no strong impact on radiolytic hydrogen production, as it has been previously mentioned [25]. The  
437 hypothetical coupled fluctuation of both H<sub>2</sub> production and temperature values observed on Fig.3 is indeed  
438 due to an experimental artefact induced by the great sensitivity of the gas chromatograph PDHID  
439 detector to temperature variation. If such perturbation could modify somehow the values of H<sub>2</sub>  
440 production, it impacts the two studied cells in parallel and should not have any effect on the derived  
441 corrosion rate values.

442 As shown in Fig.4, hydrogen productions associated to cells A1 and B1 are also strongly impacted by  
443 the irradiation. Indeed, the volume of H<sub>2</sub> generated by anoxic corrosion of the carbon steel samples is  
444 added to the one produced by water radiolysis process. Hydrogen productions successively measured  
445 for cells A1 and B1 indicate quite similar evolution and correspond to average values of  $16.2 \times 10^{-9}$  mol  
446 min<sup>-1</sup> and  $14.2 \times 10^{-9}$  mol min<sup>-1</sup>, respectively. This could be due to the fact that Fe-ions are known for  
447 reacting with radiolytical species with competitive reactions and thus they are able to impact H<sub>2</sub>  
448 evolution. Fe-ions can scavenge H<sub>2</sub> precursors (e<sub>aq</sub><sup>-</sup>) and thus lead to a H<sub>2</sub> decrease, but at the same time  
449 Fe-ions can also interact very fast with OH radical, inhibiting the probability of reaction (11) and  
450 promote an H<sub>2</sub> increase. Therefore, we could say that an overall outcome would be a more stable H<sub>2</sub>  
451 evolution over time in the presence of metallic surfaces. By subtracting H<sub>2</sub> production associated to the  
452 cells containing only pure deaerated water (cells A2 and B2) from the one generated by the cells  
453 containing pure deaerated water and metallic samples (cells A1 and B1), it should permit to estimate the  
454 volume of hydrogen generated only by anoxic corrosion process. Thus, the average corrosion rates  
455 calculated for A1 and B1 during the irradiation phase are 0.3 μm year<sup>-1</sup> and 0.2 μm year<sup>-1</sup>, respectively.  
456 These corrosion rate values obtained under irradiation and for anoxic conditions are consistent with the  
457 ones in previous studies performed in such experimental conditions [14,23]. Furthermore, we observe  
458 that cells A1 and B1 display constant behaviors all along the irradiation phase without any significant  
459 corrosion rate increase. This stabilization may be attributed to the gradual formation of a thin corrosion  
460 product layer, mainly composed of magnetite as observed during the structural characterization of our  
461 samples (Fig.6), which passivate and protect the carbon steel coupons surface. The identification of  
462 magnetite as predominant corrosion product has previously been observed in several carbon steel anoxic  
463 corrosion studies performed either under un-irradiated conditions [6,8,9,31–34] or under irradiation  
464 [14,23,35–37]. In previous studies dealing with long term anoxic corrosion under irradiation [14,38]  
465 such progressive magnetite formation has been associated to corrosion rate decrease. On the other hand,  
466 the comparison between corrosion rate values obtained during irradiation (0.3-0.2 μm year<sup>-1</sup>) and the  
467 ones gained during the short pre-irradiation phase (1.1-1.2 μm year<sup>-1</sup>) suggests that the presence of  
468 gamma radiation inhibits the anoxic corrosion rate of carbon steel. This is in contradiction with studies

Commenté [LG4]: Addition by linas version comment 33

469 comparing irradiated and un-irradiated samples [13,14,16,17,23] suggesting that ionizing radiation leads  
470 to a clear enhancement of the corrosion rate.

471 As soon as irradiation stops, hydrogen production associated to cells A1 and B1 falls until its  
472 stabilization at values around  $2.8 \times 10^{-9}$  mol min<sup>-1</sup> and  $3.0 \times 10^{-9}$  mol min<sup>-1</sup>, respectively (Fig.4). These  
473 volumes of hydrogen are generated only through anoxic corrosion process, and they allow to calculate  
474 corresponding anoxic corrosion rate, approximately at 1.2  $\mu\text{m year}^{-1}$  for both experiments. When  
475 comparing these results with the ones obtained during the pre-irradiation phase, we do not observe any  
476 diminution suggesting that, despite the primary and partial formation of a thin magnetite layer on the  
477 surface of the metallic samples, anoxic corrosion process continues to operate at the same rate that as  
478 before irradiation. This could be due to a progressive alteration of the primary formed magnetite layer  
479 which no longer protects the metal surface from further corrosion. The alteration could be caused by  
480 radiolytic-induced modifications of the solution. For example, the acidification of the solutions  
481 contained in cells A1 and B1 (see Table 4) could be due to the fact that under irradiation hydronium  
482 ions are produced in larger quantities than hydroxide ions. In the modelling work performed by Lapuerta  
483 [39], to explain the pH decrease that she observed experimentally (from 6.5 to 4.5), the author used  
484 primary radiolytical yields of  $\alpha$ -rays ( $g(\text{H}^+) = 0.37 \times 10^{-7}$  mol J<sup>-1</sup> and  $g(\text{OH}^-) = 0.06 \times 10^{-7}$  mol J<sup>-1</sup>)  
485 corresponding to a mean LET value associated to a 2 MeV proton. Similarly, Christensen & Bjergbakke  
486 [40], propose primary radiolytical yields for low LET associated to gamma radiation with values at  $2.85$   
487  $\times 10^{-7}$  mol J<sup>-1</sup> and  $0.10 \times 10^{-7}$  mol J<sup>-1</sup> for H<sup>+</sup> and OH<sup>-</sup>, respectively. However, simulation results show  
488 that the H<sup>+</sup> concentration increase is not sufficient and the author proposed the contribution of additional  
489 ferrous/ferric ions hydrolysis processes to explain the observed pH diminution [39]. Additionally, the  
490 pH decrease due to the radiolytic oxidation of ferrous ions under gamma irradiation is also confirmed  
491 by Sutherland et al. [41]. Moreover, focusing on the final pH value on cells A1, B1 we should have in  
492 mind that our pH measurements have been performed several days after the end of irradiation phase.  
493 Once irradiation stops, the concentration of radiolytic species is dramatically decreased, although, the  
494 most stable among them, is hydrogen peroxide (H<sub>2</sub>O<sub>2</sub>), able to oxidize ferrous ions available in bulk  
495 solution via Fenton reaction (12):





497 During post-irradiation phase, this reaction will generate hydroxide ions prone to contribute to the higher  
498 final pH values, compared with the pH values measured in the cells where there were no metallic  
499 samples. Hence, the measured acidification of the solution is lower in the presence of iron compared  
500 to the one's measured in the cells with pure water, however, it could be sufficient enough to impact  
501 corrosion processes.

Commenté [LG5]: Lina s version on comment 38

502 Such acidification of the solution can affect the magnetite solubility and thus inhibits the formation of a  
503 significant corrosion product layer which would lead to a corrosion rate decrease. This observation is to  
504 put in perspective with the work of Daub [42], showing that, contrary to the un-irradiated samples  
505 exhibiting a constant oxide film growth, the magnetite film thickness obtained on the gamma-irradiated  
506 sample displayed an initial fast development and then rapidly stabilized over time. On the other hand,  
507 impact of ionizing radiations on corrosion process can also be attributed to the oxidizing water radiolysis  
508 products such ( $\text{H}_2\text{O}_2$ ,  $\text{O}_2$  or  $\cdot\text{OH}$ ) which are produced simultaneously with reducing water radiolysis  
509 species ( $\text{H}_2$ ,  $e_{\text{aq}}^-$ ). Their interactions with carbon steel and stainless steel are known to induce a metal  
510 corrosion potential increase, as has been described by an electrochemical study [15]. Demonstrating that  
511 even after the end of the irradiation, the corrosion potential of the steel did not return to its initial lower  
512 pre-irradiated value, this work also pointed out the possible long-term changes in the corrosion product  
513 layer properties induced by structural modification of the oxide film (e.g., aggregation and coarsening  
514 of magnetite particles caused by the continuous dissolution-precipitation processes induced by  
515 irradiation as it is proposed by Sutherland et al. [41]). Such deterioration could impact the porosity of  
516 the neoformed corrosion product layer and may lead to a less active passivation of the metal.

517 In parallel, other parameters linked to our experimental setup can potentially impact the stability of the  
518 neoformed magnetite layer. If we refer to the work of Brusch & Pearl [31], highlighting the almost linear  
519 dependence of corrosion rate on the velocity of the tested flowing system, one can imagine that the 5  
520  $\text{mL min}^{-1}$  flow rate used into our gas circulation system may participate to the constant removal of the  
521 corrosion product located at the liquid/solid interface.

522 In addition, it was pointed out by Platts et al. [9], that any loss of ferrous ions from the system, e.g. from  
523 either adsorption and/or precipitation phenomena, can impair the formation of a thick protective  
524 corrosion product layer and lead to a renewed corrosion process.

525 Due to the progressive glass alteration process, the use of glass beaker and glass sample holder may  
526 induce ion-exchange mechanisms between silicon and iron ions [44–46]. We thus decided to perform  
527 additional post-mortem analysis on these glass elements. Acidic attack realized on glass beakers showed  
528 that total iron concentration value obtained for A1 beaker is two orders of magnitude higher than the  
529 one associated to the pristine beaker, meaning that ferrous iron ions have been entrapped in the glass  
530 alteration layer as observed in previous studies [47,48]. This ion exchange between iron and silicon is  
531 further confirmed by both the presence of silicon on the surface of the metallic coupons (Fig. 6 and  
532 Table 5), and the presence of silicon in solutions collected in A1 and B1 cells (results not shown).

533 From a radiolytical point of view, the densification of the borosilicate glass under gamma irradiation  
534 has been described in previous studies [49–52] to be a dose rate and boron content dependent process.  
535 In parallel, one can note that previous studies [53–55] showed that radiolytic yield of H<sub>2</sub> can be impacted  
536 in the case of oxide/water interfaces. Moreover, Schatz et al. [56], pointed out the fact that, during  
537 experiments dealing with silica suspensions under irradiation, the absorbed energy by silica  
538 nanoparticles crosses the solid/liquid interface and generates hydrated electrons in the aqueous phase as  
539 a result of an interfacial charge transfer process. This observation is in good agreement with the work  
540 of Nakashima & Tachikawa [57], where is mentioned the possible mechanism for hydrogen production  
541 by energy transfer from silica to the aqueous solution. The authors mention that a part of the initial  
542 hole/electron formation from irradiated silica can migrate in solids and reach the surface where they  
543 excite physisorbed water, leading to hydrogen formation. Therefore, we should note these parallel  
544 mechanisms potentially able to moderately affect hydrogen production arising from our experimental  
545 set-up involving irradiated glass. However, considering the low silica concentrations measured in our  
546 solutions, we consider that such processes involving silica nanoparticles should not significantly impact  
547 H<sub>2</sub> production.

548 Regarding the corrosion rates values estimated by weight loss measurements ( $4.8 \mu\text{m year}^{-1}$  for A test  
549 and  $1.9 \mu\text{m year}^{-1}$  for B test, see table 3), we observe that they are in the same order of magnitude as the  
550 ones obtained during previous studies using the same technique [13,23]. Nevertheless, as mentioned in  
551 previous studies [58–60] corrosion rates exported from weight loss measurements are higher than the  
552 ones derived from the hydrogen gas generation measurements. Even though it is difficult to compare  
553 instantaneous corrosion rate values obtained by  $\text{H}_2$  gas generation monitoring with average corrosion  
554 rate by weight loss measurements, such discrepancy would highlight that these two methods do not  
555 monitor the same process. Moreover, one should mention that despite the anoxic conditions prevailing  
556 in our experimental set-up, water radiolysis induced the production of reducing ( $\text{H}_2$ ,  $\text{e}_{\text{aq}}^-$ ) as well as  
557 oxidizing ( $\text{H}_2\text{O}_2$ ,  $\cdot\text{OH}$ ,  $\text{O}_2$ ) species prone to modify locally physico-chemical conditions and to promote  
558 in some extent oxidic corrosion processes that are not associated to any  $\text{H}_2$  gas production and for this  
559 reason, they are not considered by our experimental approach which is based on  $\text{H}_2$  monitoring.  
560 Consideration of such information should support the concept of anoxic corrosion experiments based  
561 on a twofold approach combining  $\text{H}_2$  monitoring and weight loss measurements methods.

## 562 5. Conclusion

563 This work provides new insights on the impact of gamma radiation on carbon steel anoxic corrosion  
564 process and on the associated  $\text{H}_2$  gas generation. We adopted an experimental set-up based on the  
565 hydrogen gas production monitoring which allows to distinguish between the  $\text{H}_2$  production related to  
566 water radiolysis and the one related to anoxic corrosion, making possible the estimation of associated  
567 corrosion rate. Contrary to numerous previous results found in the literature, the first observation is that  
568 gamma radiation does not induce a clear increase of the carbon steel corrosion rate but rather to slightly  
569 inhibit it. This is probably due to the gradual formation of a thin magnetite layer which partially  
570 passivates and protects the metallic surface. The second observation concerns the properties of  
571 associated with such the magnetite layer and their evolution, during and after irradiation. Even though  
572 corrosion rate under irradiation appears to be lower, the redox modifications of the solution induced by  
573 radiolytic species production can induce the progressive alteration of the magnetite layer. This passive  
574 film deterioration may maintain the metal surface in an active corrosion mode for longer period of time.  
575 In parallel, the fact that the corrosion rate observed post-irradiation does not differ from the one

576 measured before irradiation also suggests the possible progressive degradation of the passivating  
577 corrosion product layer. This degradation could be due to oxidizing water radiolysis products which can  
578 induce structural modifications of the oxide film, either directly or through local modification of the  
579 physico-chemical conditions of the solution. If such sustained corrosion processes are verified, it could  
580 impact the degradation kinetic and the durability of metallic components used for HLW disposal gallery.  
581 Nevertheless, these assumptions need to be confirmed by further investigations performed with longer  
582 irradiation period and with more representative solutions (clayey pore water, alkaline pore water) in  
583 order to acquire an accurate understanding of gamma radiation impact on corrosion product growth and  
584 also on the evolution of oxide film properties. In parallel, numerical simulations should help to predict  
585 the concentration evolution associated to key radiolytic species prone to impact anoxic corrosion under  
586 irradiation processes and to better understand the effect of ionizing radiation in presence of metal/water  
587 interface or metal/oxide/water interface.

#### 588 **Acknowledgements**

589 This work was supported by the French Institute of Radiation protection and Nuclear Safety (IRSN).

590

#### 591 **References**

- 592 [1] D. G. Bennett and R. Gens, "Overview of European concepts for high-level waste and spent fuel disposal  
593 with special reference waste container corrosion," *J. Nucl. Mater.*, vol. 379, no. 1–3, pp. 1–8, 2008.
- 594 [2] C. Padovani et al., "The corrosion behaviour of candidate container materials for the disposal of high-level  
595 waste and spent fuel—a summary of the state of the art and opportunities for synergies in future R&D,"  
596 *Corros. Eng. Sci. Technol.*, vol. 52, pp. 227–231, 2017.
- 597 [3] D. Crusset et al., "Corrosion of carbon steel components in the French high-level waste programme :  
598 evolution of disposal concept and selection of materials," *Corros. Eng. Sci. Technol.*, vol. 2782, pp. 17–  
599 24, 2017.
- 600 [4] Andra, "Referentiel du site Meuse/Haute-Marne, Présentation Générale," Rap. C.RP.ADS.04.0022,  
601 Andra, Chatenay-Malabry, France, 2005.
- 602 [5] Andra, "Corrosion des matériaux métalliques," Tome 3, Rap. C.RP.ASCM.04.0015, Andra, Chatenay-  
603 Malabry, France., 2005.
- 604 [6] S. Necib, Y. Linard, D. Crusset, M. Schlegel, S. Daumas, and N. Michau, "Corrosion processes of C-steel  
605 in long-term repository conditions," *Corros. Eng. Sci. Technol.*, vol. 52, pp. 127–130, 2017.

- 606 [7] M. L. Schlegel, F. Martin, M. Fenart, C. Blanc, J. Varlet, and E. Foy, "Corrosion of carbon steel in clay  
607 compact environments at 90 °C: Effect of confined conditions," *Corros. Sci.*, vol. 184, no. March, 2021.
- 608 [8] N. Smart, D. Blackwood, and L. Werme, "The anaerobic corrosion of carbon steel and cast iron in artificial  
609 groundwaters," SKB Tech. Rep., 2001.
- 610 [9] N. Platts, D. J. Blackwood, C. C. Naish, S. N. Fuel, and W. M. Co, "Anaerobic oxidation of carbon steel  
611 in granitic groundwaters: A review of the relevant literature," SKB Tech. Rep. 94-01, no. February, 1994.
- 612 [10] A. O. Allen, "The radiation chemistry of water and aqueous solutions," D. Van Nostrand Company, Inc.,  
613 1961.
- 614 [11] G. V. Buxton, C. . Greenstock, W. P. Helman, and A. B. Ross, "Critical Review of Rate Constants for  
615 Reactions of Hydrated Electrons, Hydrogen Atoms and Hydroxyl Radicals (.OH/O-) in Aqueous  
616 Solution," *J. Phys. Chem. Ref. Data*, 1988.
- 617 [12] V. Cuba, V. Mucka, and M. Pospisil, "Radiation Induced Corrosion of Nuclear Fuel and Materials," *Adv.*  
618 *Nucl. Fuel*, 2012.
- 619 [13] G. P. Marsh and K. J. Taylor, "An assessment of carbon steel containers for radioactive waste disposal,"  
620 *Corros. Sci.*, vol. 28, no. 3, pp. 289–320, 1988.
- 621 [14] N. R. Smart, A. P. Rance, and L. O. Werme, "The effect of radiation on the anaerobic corrosion of steel,"  
622 *J. Nucl. Mater.*, vol. 379, no. 1–3, pp. 97–104, 2008.
- 623 [15] K. Daub, X. Zhang, J. J. Noël, and J. C. Wren, "Effects of  $\gamma$ -radiation versus H<sub>2</sub>O<sub>2</sub> on carbon steel  
624 corrosion," *Electrochim. Acta*, vol. 55, no. 8, pp. 2767–2776, 2010.
- 625 [16] N. Fujita, C. Matsuura, and K. Saigo, "Irradiation-enhanced corrosion of carbon steel in high temperature  
626 water - In view of a cell formation induced by  $\gamma$ -rays," *Radiat. Phys. Chem.*, vol. 58, no. 2, pp. 139–147,  
627 2000.
- 628 [17] N. Fujita, C. Matsuura, and K. Saigo, "Radiation-induced preferential dissolution of specific planes of  
629 carbon steel in high-temperature water," *Radiat. Phys. Chem.*, vol. 60, no. 1–2, pp. 53–60, 2001, doi:  
630 10.1016/S0969-806X(00)00326-1.
- 631 [18] E. Smailos, W. Schwarzkopf, R. Koster, B. Fiehn, and B. Halm, "Corrosion Testing of Selected Packaging  
632 Materials for Disposal of High-Level Waste Glass in Rock Salt Formations," Kernforschungszentrum  
633 Karlsruhe, KFK 4723, Karlsruhe, Ger., 1990.
- 634 [19] T. M. Ahn and P. Soo, "Corrosion of low carbon steel in concentrated synthetic groundwater at 80 to  
635 150°C," *Waste Manag.*, vol. 15, no. 7, pp. 471–476, 1995.
- 636 [20] B. Kursten et al., "Review of corrosion studies of metallic barrier in geological disposal conditions with  
637 respect to Belgian Supercontainer concept," *Corros. Eng. Sci. Technol.*, vol. 46, no. 2, pp. 91–97, 2011.
- 638 [21] N. Smart and A. Rance, "Effect of radiation on anaerobic corrosion of iron," SKB Tech. Rep. 05-05, 2005.

- 639 [22] A. O. Allen, C. J. Hochanadel, J. A. Ghormley, and T. W. Davis, "Decomposition of water and aqueous  
640 solutions under mixed fast neutron and gamma radiation," *J. Phys. Chem.*, vol. 56, no. 5, pp. 575–586,  
641 1952.
- 642 [23] H. Badet, "Effet de la radiolyse sur les systèmes de corrosion anoxiques à très long terme des alliages  
643 ferreux," Thesis, Univ. Pierre Marie Curie, 2014.
- 644 [24] M. Mohamed-Said, B. Vuillemin, R. Oltra, A. Marion, L. Trenty, and D. Crusset, "Predictive modelling  
645 of the corrosion rate of carbon steel focusing on the effect of the precipitation of corrosion products,"  
646 *Corros. Eng. Sci. Technol.*, vol. 52, pp. 178–185, 2017.
- 647 [25] Y. Tabata, Y. Ito, and S. Tagawa, *CRC handbook of radiation chemistry*. Boca Raton: CRC Press, 1991.
- 648 [26] B. Pastina, J. Laverne, and S. M. Pimblott, "Dependence of Molecular Hydrogen Formation in Water on  
649 Scavengers of the Precursor to the Hydrated Electron," *J. Phys. Chem. A*, vol. 103, no. 29, 1999.
- 650 [27] Y. Hatano, Y. Katsumura, and A. Mozumder, "Charged Particle and Photon Interactions with Matter,"  
651 CRC Press, 2010, doi: 10.1201/b10389.
- 652 [28] J. W. T. Spinks, R. J. Woods, "An Introduction to Radiation Chemistry," Third Edition, John-Wiley and  
653 Sons, Inc., New York, Toronto 1990.
- 654 [29] G. Baldacchino, E. Brun, I. Denden, S. Bouhadoun, R. Roux, H. Khodja, C. Sicard-Roselli, "Importance  
655 of radiolytic reactions during high-LET irradiation modalities: LET effect, role of O<sub>2</sub> and  
656 radiosensitization by nanoparticles," *Cancer Nano* 10, 2019.
- 657 [30] B. Pastina and J. A. LaVerne, "Effect of molecular hydrogen on hydrogen peroxide in water radiolysis,"  
658 *J. Phys. Chem. A*, vol. 105, no. 40, pp. 9316–9322, 2001.
- 659 [31] E. Bruschi and W. Pearl, "Corrosion and Corrosion Product Release Behavior of Carbon Steel," *Proc. Am.*  
660 *Power Conf.*, vol. 31, pp. 699–705, 1969.
- 661 [32] J. Jelinek and P. Neufeld, "Kinetics of Hydrogen Formation From Mild Steel in Water Under Anaerobic  
662 Conditions," *Corrosion*, vol. 38, no. 2, pp. 98–104, 1982.
- 663 [33] N. Senior, T. Martino, and N. Diomidis, "The anoxic corrosion behaviour of carbon steel in a noxic alkaline  
664 environments simulating a Swiss L/ILW repository environment," *Mater. Corros.*, vol. 72, no. 1–2, pp.  
665 131–140, 2020.
- 666 [34] N. Smart, A. Rance, and L. Werme, "Anaerobic Corrosion of Steel in Bentonite," *Mat. Res. Soc. Symp.*  
667 *Proc. Vol. 807* ©, pp. 1–5, 2004.
- 668 [35] V. Cuba et al., "Radiolytic formation of ferrous and ferric ions in carbon steel - deaerated water system,"  
669 *Radiat. Phys. Chem.*, vol. 80, no. 3, pp. 440–445, 2011.
- 670 [36] N. R. Smart, A. P. Rance, D. J. Nixon, P. A. H. Fennell, B. Reddy, and B. Kursten, "Summary of studies  
671 on the anaerobic corrosion of carbon steel in alkaline media in support of the Belgian supercontainer  
672 concept," *Corros. Eng. Sci. Technol.*, vol. 52, pp. 217–226, 2017.

- 673 [37] J. Vandendorre, F. Crumière, G. Blain, R. Essehli, B. Humbert, and M. Fattahi, "Alpha localized radiolysis  
674 and corrosion mechanisms at the iron/water interface: Role of molecular species," *J. Nucl. Mater.*, vol.  
675 433, no. 1–3, pp. 124–131, 2013.
- 676 [38] N. R. Smart, B. Reddy, A. P. Rance, D. J. Nixon, and N. Diomidis, "The anaerobic corrosion of carbon  
677 steel in saturated compacted bentonite in the Swiss repository concept," *Corros. Eng. Sci. Technol.*, vol.  
678 52, pp. 113–126, 2017.
- 679 [39] S. Lapuerta, "Étude de la corrosion du fer à l' interface de différents milieux (eau , air) soumis à l'   
680 irradiation de protons," Thesis, Univ. Claude Bernard - Lyon I, 2006.
- 681 [40] H. Christensen and E. Bjergbakke, "Application of chemsimul for groundwater radiolysis," *Nucl. Chem.  
682 Waste Manag.*, vol. 6, no. 3–4, pp. 265–270, 1986.
- 683 [41] T. I. Sutherland, C. J. Sparks, J. M. Joseph, Z. Wang, G. Whitaker, T. K. Sham, & J. C. Wren, "Effect of  
684 ferrous ion concentration on the kinetics of radiation-induced iron-oxide nanoparticle formation and  
685 growth," *Phys. Chem.*, 19, 695-708, 2017.
- 686 [42] K. Daub, "A Study of Gamma Radiation Induced Carbon Steel Corrosion," Thesis, Univ. West. Ontario,  
687 no. January, 2013.
- 688 [43] R. S. Glass, G. E. Overturf, R. A. Van Konynenburg, and R. D. McCright, "Gamma radiation effects on  
689 corrosion-I. Electrochemical mechanisms for the aqueous corrosion processes of austenitic stainless steels  
690 relevant to nuclear waste disposal in Tuff," *Corros. Sci.*, vol. 26, no. 8, pp. 577–590, 1986.
- 691 [44] C. Carriere et al., "AVM nuclear glass / steel / claystone system altered by Callovo – Oxfordian poral  
692 water with and without cement – bentonite grout at 70 ° C," *Mater. Corros.*, 2020.
- 693 [45] T. Ducasse, "Apport des verres basaltiques à la validation du modèle GRAAL sur le très long terme,"  
694 Thesis, Univerité de Montpellier, 2017.
- 695 [46] M. Fournier, S. Gin, and P. Frugier, "Resumption of nuclear glass alteration: State of the art," *J. Nucl.  
696 Mater.*, vol. 448, no. 1–3, pp. 348–363, 2014.
- 697 [47] H. Aréna et al., "Impact of iron and magnesium on glass alteration: Characterization of the secondary  
698 phases and determination of their solubility constants," *Appl. Geochemistry*, vol. 82, pp. 119–133, 2017.
- 699 [48] P. Dillmann, S. Gin, D. Neff, L. Gentaz, and D. Rebiscoul, "Effect of natural and synthetic iron corrosion  
700 products on silicate glass alteration processes," *Geochim. Cosmochim. Acta*, vol. 172, pp. 287–305, 2016.
- 701 [49] C. Allred, "Effect of radiation on silicon and borosilicate glass," Thesis, MIT, 2003.
- 702 [50] E. Birtch and J. Shelby, "Annealing of hydrogen-impregnated and irradiated vitreous silica," *J. Non. Cryst.  
703 Solids*, vol. 349, no. 1–3, pp. 156–161, 2004.
- 704 [51] H. Manaktala, "An assessment of borosilicate glass as a High-Level waste form," *Cent. Nucl. Waste Regul.  
705 Anal.* San Antonio, Texas, 1992.

- 706 [52] W. Primak, "Effects of ionization on silicate glasses," Nucl. Waste Manag. Mater. (UC-25), Argonne,  
707 Illinois, 1982.
- 708 [53] N. G. Petrik, A. B. Alexandrov, and A. I. Vall, "Interfacial Energy Transfer during Gamma Radiolysis of  
709 Water on the Surface of ZrO<sub>2</sub> and Some Other Oxides," J. Phys. Chem. B, 105, 25, 5935–5944, 2001.
- 710 [54] P. Rotureau, J. P. Renault, B. Lebeau, J. Patarin, J. C. Mialocq, "Radiolysis of confined water: molecular  
711 hydrogen formation," Chemphyschem, 1316-1323, 2005.
- 712 [55] S. Le Caer, "Water radiolysis: Influence of oxide surfaces on H<sub>2</sub> production under ionizing radiation,"  
713 Water, 3(1), 235-25, 2011.
- 714 [56] T. Schatz, A. Cook, and D. Meisel, "Charge carrier transfer across the silica nanoparticle/water interface,"  
715 J. Phys. Chem. B, vol. 102, no. 37, pp. 7225–7230, 1998.
- 716 [57] M. Nakashima and E. Tachikawa, "Self-radiolysis of Tritiated Water Adsorbed on Silica Gel," Appl.  
717 Radiat. Isot., vol. 37, no. 6, pp. 527–530, 1986.
- 718 [58] N. Diomidis, "Scientific basis for the production of gas due to corrosion in a deep geological repository,"  
719 nagra, 2014.
- 720 [59] F. King, "Corrosion of carbon steel under anaerobic conditions in a repository for SF and HLW in Opalinus  
721 Clay," nagra, 2008.
- 722 [60] M. Kaneko, N. Miura, A. Fujiwara, and M. Yamamoto, "Evaluation of Gas Generation Rate by Metal  
723 Corrosion in the Reducing Environment," Eng. Report-Radioactive Waste Manag. Funding Res.  
724 Center(RWMC), no. RWMC-TRE-03003, p. 145, 2004.
- 725