



HAL
open science

Dipolar Modification in Heterogeneous Catalysts under Electron Beam Irradiation for the Conversion of Biomass-Derived Platform Molecules

Zhiyan Chen, Haozhe Li, Keyan Sheng, Xiaohan Dong, Jushigang Yuan, Shuai Hao, Minghao Li, Rongxian Bai, Yves Queneau, Alexander Sidorenko, et al.

► **To cite this version:**

Zhiyan Chen, Haozhe Li, Keyan Sheng, Xiaohan Dong, Jushigang Yuan, et al.. Dipolar Modification in Heterogeneous Catalysts under Electron Beam Irradiation for the Conversion of Biomass-Derived Platform Molecules. *ACS Catalysis*, 2022, 12 (24), pp.15618-15625. 10.1021/acscatal.2c04519 . hal-03922887

HAL Id: hal-03922887

<https://hal.science/hal-03922887>

Submitted on 4 Jan 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Dipolar Modification in Heterogeneous Catalysts under Electron Beam Irradiation for the Conversion of Biomass-derived Platform Molecules

Zhiyan Chen,^{a,c} Haozhe Li,^{a,c} Keyan Sheng,^a Xiaohan Dong,^{a,c} Jushigang Yuan,^a Shuai Hao,^{a,c} Minghao Li,^{a,c} Rongxian Bai,^{a,c} Yves Queneau,^d Alexander Sidorenko,^e Jiang Huang,^{a,b*} Yanlong Gu^{a,b*}

^a Huazhong University of Science and Technology, 1037 Luoyu road, Hongshan District, Wuhan 430074, China

^b State Key Laboratory of Advanced Electromagnetic Engineering and Technology, Huazhong University of Science and Technology, Wuhan 430074, China

^c Key laboratory of Material Chemistry for Energy Conversion and Storage, Ministry of Education, Hubei Key Laboratory of Material Chemistry and Service Failure, Huazhong University of Science and Technology, Wuhan 430074, China

^d Institut de Chimie et Biochimie Moléculaires et Supramoléculaires (ICBMS), Université de Lyon, CNRS, Université Lyon 1, INSA Lyon, CPE Lyon, UMR 5246, Université Claude Bernard, Bâtiment Lederer, 1 Rue Victor Grignard, 69622 Villeurbanne, France

^e Institute of Chemistry of New Materials of National Academy of Sciences of Belarus, Skaryna str, 36, 220084 Minsk, Belarus

KEYWORDS: biomass-derived platform molecules, electron beam irradiation, irradiation, dipolar catalyst, biomass

ABSTRACT: Herein, an efficient and practical approach for dipolar modification of commercially available solid catalysts is reported. The solid catalysts HMS (hexagonal mesoporous silica)-DMSO decorated with organic dipolar layers are designed and synthesized by radiation technology under simple and accessible conditions. The dipolar catalysts can serve as platforms to introduce various active sites, benefiting from the flexibility and diversity of the dipolar layer, which in turn allow them to achieve catalytic performance in relatively friendly systems. Specifically, the upgraded dipolar catalyst HMS-DMSO-SO₃H exhibits good performance in converting the oxidized lignin model compound of α -hydroxyacetophenone to 1,3-dioxolane derivatives and dehydrating isomaltulose to glycosyloxymethyl-furfural (GMF).

With the world energy crisis and total global energy consumption increasing dramatically, it is essential to develop methods for the efficient use of renewable resources.¹⁻³ Biomass, as an attractive carbon-based source, has been widely used to produce value-added fine chemicals and fuels.⁴⁻⁸ The catalytic activation/cleavage of ubiquitous C-C/C-O bonds in biomass is crucial through various methods, including oxygen removal processes and increasing the molecular weight *via* C-C coupling reactions.⁹⁻¹¹ Efficient regulation of the state of reaction intermediates derived from C-C/C-O bond activation/cleavage to maximize the selectivity and yield of bio-based products is a key challenge. In this context, a valid strategy for this goal in heterogeneous catalysis is to enrich the dipolarity of the solid catalyst surface, allowing the reactants to participate in specific non-covalent interactions to stabilize or destabilize the reaction intermediates, thereby enabling the transformations to proceed smoothly.¹²⁻¹⁸ However, there is still a lack of universal methods to prepare dipolar catalysts.


Despite these encountered challenges, with great efforts and contributions from many pioneers, various dipolar

catalysts have been designed and synthesized successfully for the conversion of biomass.^{12,19} For example, the organic-inorganic nanocomposite catalysts with dipolar microenvironments were prepared, which exhibited excellent catalytic performance for the selective conversion of fructose to HMF in a mixed solvent of water and tetrahydrofuran.²⁰ Xiao and co-workers developed the heterogeneous catalyst with strong dipolar moieties through constructing microenvironment to tune the performance of active sites.²¹ The catalysts exhibit high yields of fructose to 5-hydroxymethylfurfural in THF. Parallely, a dipolar and flexible linear polymer polyvinylpyrrolidone (PVP) was incorporated into the pores of the acidic COF material to facilitate the fructose dehydration reaction.²² Recently, the HCP materials with a dipolar moiety have been developed as alternatives to DMF in the conversion of NaN₃ to benzylic azides and triazoles.²³ Although these strategies have been developed, complex designs, long synthesis periods and lack of clean processes lead to high costs of catalyst synthesis, which are the important factors that limiting their application in industry.²⁴ From a catalyst

design perspective, it is generally recommended to optimize the already existing catalyst for a specific process, which mainly depends on the needs of the user, rather than to develop an entirely new catalyst material.²⁵ Obviously, the development of general and eco-efficient methods for dipolar modification of readily available catalysts or supports is one of the important issues that chemists need to address urgently at present.

Currently, electron beam irradiation (EBI) technology has been used as a green replacement method for traditional chemical processing, especially surface modification processes.²⁶⁻³⁰ The EBI process is a flow of energetic electrons generated by an accelerator that directly injects energy to the materials, and then initiates a series of chemical reactions through free radicals to improve product quality by changing its chemical and physical properties. Compared with other conventional methods, the EBI technology is an efficient method of chemical modification because no catalysts or additives are required to initiate the reaction, and the chemical reaction can be easily adjusted by varying the radiation conditions under simple operation,

Scheme 1. Schematic illustration of the preparation process of dipolar silica-based catalysts by electron beam



irradiation^a

^aReaction conditions: Step 1: HMS-SH (0.20 g, 0.43 mmol), 10.0 mmol of G1, 5.0 mL of CH₃CN, N₂ atmosphere, 2100 kGy, 5 s. Step 2: HMS-DMSO (0.50 g, 1.55 mmol), 4-vinylbenzenesulfonic acid sodium salt (1.03 g, 5.0 mmol), 2.0 mL of H₂O, N₂ atmosphere, 1800 kGy, 5 s, treat with HCl (1 mol/L, 40 mL).

In order to confirm the structures of the grafted moieties, the prepared catalysts including HMS-DMSO and HMS-DMSO-SO₃H were characterized by various spectroscopic methods. The FTIR spectroscopy showed that the profiles of fresh and irradiated silica-based catalysts were quite similar, as shown in **Figure 1a**, indicating that the chemical structure of catalysts was not significantly changed through electron beam irradiation. The silica-based HMS-SH catalysts showed weak characteristic peak appearing at about 2527 cm⁻¹, which was assigned to the vibration of the HS group.³¹⁻³² Meanwhile, the bands at 2985 cm⁻¹ and 2934 cm⁻¹ corresponded to the symmetric stretching vibrations and asymmetric stretching vibrations of the -CH₂ group.³³ The disappearance of the S-H stretching band, while the peaks of catalysts with DMSO moieties, including HMS-DMSO and HMS-DMSO-SO₃H, were significantly enhanced at these locations, indicating that the grafting of sulfolane onto the surface of silica-base was successful. Despite the fact that the broad area at 1250-1000 cm⁻¹ may

thus enabling large-scale production. The EBI technology thus offers a great opportunity for the production of dipolar catalysts that are not easily accessible by chemical methods.


Out of all these considerations, in this work, without changing the specific preparation process of the original catalysts, an efficient and versatile method is reported for dipolar modification of commercially available solid catalysts by EBI technology. The high-density dipolar moieties were anchored on the surface of catalyst *via* rapid thiol-ene reaction, which endows the catalyst with polar properties. Notably, the upgrade catalyst exhibits outstanding performance in the conversion of lignin model compound to valuable 1,3-dioxolane derivatives and the dehydration of isomaltulose to glycosyloxymethyl-furfural (GMF). The successful implementation of this protocol not only brings innovation to the catalysts synthesis industry, but also significantly relieves the dependence on unfriendly polar aprotic solvents in the conversion process of biomass-derived platform molecules.

include many characteristic peaks, the emerging peaks at 1188 cm⁻¹ and 1132 cm⁻¹ in HMS-DMSO-SO₃H were related to stretching vibration of the S=O bonds of aromatic sulfonic acid.³⁴⁻³⁵ These results implied that the grafting of double bond-containing species onto the silica-based surface *via* electron beam irradiation was successful. Besides, the characterization with ¹³C MAS NMR spectra also suggested dipolar moieties and acid sites were successfully introduced, as demonstrated in **Figure 1b**. It was clearly observed that the chemical shifts of three catalysts varied with the grafted species. Compared with the starting material of HMS-SH, the carbon peaks in HMS-DMSO around 55.8, 51.9, 39.8 and 33.9 ppm were ascribed to sulfolane species. After treatment of acidification, the emerging peaks at 149.0, 147.1, 140.4, 126.7 ppm in HMS-DMSO-SO₃H were related to the aromatic sulfonic acid.³⁶⁻³⁷ In addition, with the increase of the strong electron-withdraw groups, the resonance-absorption peaks move to lower

field, resulting in larger chemical shifts of HMS-DMSO-SO₃H.

As representative samples, X-ray photoelectron spectroscopy (XPS) of HMS-DMSO-SO₃H was shown in **Figure 1**, while the detailed characterization results of other samples are provided in the **ESI (Figures S6-S7)**. As expected, all the essential elements were observed (**Figure S8**), and the conspicuous signal of C 1s appeared at 284.79 eV was assigned to the C-C bond (**Figure 1d**).³⁸ The two peaks were located at 285.80 and 286.45 eV, which were assigned to the C-S and C-O bands, respectively.³⁹ The O 1s clearly evidenced the presence of three chemical environments for the oxygen atoms (**Figure 1e**). The predominant

Notably, in the O 1s XPS spectra of HMS-DMSO-SO₃H, the existence of S-O band was evidenced by the peak appearing at 531.80 eV. Indeed, the S-O bands were also found in the O 1s XPS spectrum of HMS-DMSO, and the content of surface elements increased significantly after sulfonation. Correspondingly, it was clearly showed that in the S 2p region (**Figure 1f**), the characteristic peaks at 168.12 eV and the peaks area ratio were about 2:1, which can be attributed to the S-O bond.⁴¹⁻⁴² The pattern of the S 2p region showed peaks located at around 163.47 eV, which is attributed to the presence of C-S groups on the surface of HMS-DMSO-SO₃H (**Tables S2-S3**). These results indicated that the grafting of dipolar moieties and -SO₃H groups onto



peak at 532.71 eV was characteristic of the HMS backbone, while the peak at 533.68 corresponds to the C-O groups.⁴⁰

Figure 1. a) The FT-IR spectra of HMS-SH, HMS-DMSO, and HMS-DMSO-HSO₃H; b) solid-state ¹³C NMR spectra of different dipolar catalysts; c) fluorescence emission spectra of Nile red adsorbed in three catalysts; XPS spectra of HMS-DMSO-SO₃H, including magnifications of the C 1s (d), O 1s (e), S 2p region (f), the data of HMS-SH and HMS-DMSO are shown in figure S6-S7.


The morphologies of the obtained catalysts were investigated by emission scanning electron microscopy (FE-SEM), and the changes of the three catalysts were shown in **Figure 2**. With the increase of monomer **G1**, a large number of particles are generated on the surface of the smooth massive solid (**Figure 2a**), forming unique spatial structures (**Figure 2b**). After treatment of sulfonic modification, the structures were more compact (**Figure 2c**), which was consistent with the above description. The energy-dispersive spectroscopy (EDX) analysis indicated that all the expected elements were present and uniformly distributed in the HMS-DMSO-SO₃H (**Figure 2d-2f**) catalyst as well as HMS-DMSO (**Figure S9**). Furthermore, the effect of

the surface was successful.

electron beam energy on the catalyst preparation process is evaluated by means of the Monte Carlo code FLUKA. Electron beam energy is one of the most vital parameters in the process of electron irradiation, which affects the absorbed dose distribution in catalysts and determines the quality of the product.⁴³⁻⁴⁴ The results show that the EBI technology is amenable for the role of surface modification due to its strong penetrating ability and uniform distribution (**Figures S12-S15**). In addition, the prepared materials including HMS-SH, HMS-DMSO and HMS-DMSO-SO₃H were also submitted to elemental analysis to confirm the amount of grafted DMSO or -SO₃H fragment on silica-based composite. Compared with the raw material of HMS-SH,

the sulfur content of HMS-DMSO increased significantly after treating HMS-SH with 3-sulfolene, indicating the occurrence of grafting. By attributing the increase in sulfur content to the anchoring of monomer **G1** onto HMS-SH, the amount of grafted DMSO moieties was approximately 1.1. The concentration of the grafted -SO₃H fragment on the HMS-DMSO is approximately 0.88 mmol/g (**Table S1**).

The N₂ sorption isotherms were collected and the N₂ isotherms corresponded to type-IV isotherm, which was typical for mesoporous materials (**Figures S10**). Analysis of pore-size distribution evaluated shows that pore-sizes were predominantly distributed at 4.0 nm. The Brunauer-Emmett-Teller (BET) surface areas of all the obtained materials were also calculated. The S_{BET} of the dipolar catalysts decreased from 1351 m² g⁻¹ of HMS-SH to 979 m² g⁻¹ of HMS-DMSO, mainly contributed by the increase of **G1** content. After treatment of sulfonation, the catalysts still exhibited high surface areas (768 m² g⁻¹) and no significant change in surface area was observed. The thermal stability of the obtained catalysts was inspected by thermogravimetric analysis (TGA) (**Figure S11**). Although the organic components in HMS-DMSO or HMS-DMSO-SO₃H were significantly higher than that in HMS-SH, it was observed from the TGA curves that all the catalysts were quite stable below 240 °C. When the temperature was elevated to around 270 °C, the weight loss was clearly observed in HMS-DMSO-SO₃H. The TGA results implied that the obtained catalysts have an excellent thermostability, it



is feasible to use them in harsh conditions.

Figure 2. FSEM image characterizations of different dipolar catalysts, a) HMS-SH; b) HMS-DMSO; c) HMS-DMSO-SO₃H; d-f) elemental mapping of HMS-DMSO-SO₃H for C (d), O (e) and S (f), the data of HMS-SH and HMS-DMSO are shown in figure S8.

The fluorescence emission spectra were also analyzed, as shown in **Figure 1c**. To the best of our knowledge, Nile red was a sensitive probe, which was considered the best choice to determine the local polarity of some media in a variety of heterogeneous systems because the photophysical properties of Nile red vary with the polarity of the solvent.⁴⁶⁻⁴⁸ Upon photo-excitation at 400 nm, the fluorescence intensity of Nile red adsorbed in HMS-DMSO and HMS-DMSO-SO₃H almost disappeared with the increase content of sulfone group, while the obvious peak at 649 nm was maintained after treatment with HMS-SH (see **ESI** for details). Significant decrease or even disappearance

mmol/g. Indeed, HMS-SH exhibits a better ability to graft monomer **G1** due to its high loading of thiol groups (2.21 mmol/g).⁴⁵ To facilitate the subsequent introduction of active sites to maximize the catalytic ability, an excess amount of aromatic sulfonic acid was used. In intensity has been attributed to a formation of the twisted intramolecular charge transfer (TICT) state.⁴⁹ The results demonstrated that the polarity of HMS-DMSO and HMS-DMSO-SO₃H significantly enhanced by decoration of polar moieties.

To verify the applicability of dipolar catalysts as reaction medium, lignin model compound⁵⁰ (**1a**) and formaldehyde (**2a**) were employed as reaction substrates to synthesize 1,3-dioxolane derivative **3a**, which is useful intermediates in the synthesis of pharmaceuticals and fine chemicals.⁵¹⁻⁵³ In the presence of HMS-DMSO-SO₃H, various solvents were screened (**Table 1**, entries 1-4). EtOH and 2-methyltetrahydrofuran (2-Me-THF) were not suitable for this reaction (entries 1 and 2). Although **1a** didn't completely converted (entry 3), the result indicated that the dipolar catalyst is promising for achieving a good result. A moderate yield of **3a** was obtained in cyclopentyl methyl ether (CPME, entry 3). When the reaction was performed in isopropyl acetate (iPrOAc), **3a** was obtained in 95% of yield (entry 4). Under the identical conditions, the reactions over *p*-toluenesulfonic, Amberlyst-15 and HMS-SO₃H gave only moderate yields (entries 5-7). HMS-DMSO has no acidic site, but contains **G1** fragment in the solid surface, has no catalytic activity for the synthesis of **3a** (entry 8). When HMS-DMSO was used along with TsOH, **3a** can be isolated with 56% yield (entry 9). To evaluate the effect of acid content, the catalysts with different ratios were prepared and the results were described in **Table S4**. Furthermore, the reference catalyst PSS-DMSO-SO₃H²¹ with dipolar moieties also exhibits good catalytic performance, affording the desired product in 62% yield (entry 10). These results demonstrate that the presence of dipolar components is indeed effective in enhancing the activity of the catalyst. The reactions over the analogous dipolar catalysts that were prepared through the conventional chemical grafting with free radical initiators proceeded sluggishly (entries 11 and 12). These results implied that the use of EBI is a key for ensuring the dipolar catalyst to have a good catalytic performance. It should be noted that the catalyst is also recyclable (**Figure S23**) and still maintains good catalytic activity after 5 cycles. Finally, a possible mechanism is illustrated, as depicted in **Figure S16- S21**.

Table 1. Condition optimization of the reaction lignin model compound and 2a.

Entry ^a	Catalyst	Solvent	Conv. (%) ^b	Select. (%) ^c	Yield (%) ^e
1	HMS-DMSO-SO ₃ H	EtOH	43	63	27
2	HMS-DMSO-SO ₃ H	2-Me-THF	28	36	10
3	HMS-DMSO-SO ₃ H	CPME	67	82	55
4	HMS-DMSO-SO ₃ H	ⁱ PrOAc	>99	95	95
5	TsOH	ⁱ PrOAc	66	50	33
6	Amberlyst-15	ⁱ PrOAc	60	82	49
7	HMS-SO ₃ H	ⁱ PrOAc	65	74	48
8	HMS-DMSO	ⁱ PrOAc	24	0	0
9 ^b	HMS-DMSO	ⁱ PrOAc	72	78	56
10	PSS-DMSO-SO ₃ H	ⁱ PrOAc	85	73	62
11 ^c	HMS-DMSO-SO ₃ H	ⁱ PrOAc	45	51	23
12 ^d	HMS-DMSO-SO ₃ H	ⁱ PrOAc	49	55	27

^aReaction conditions: **1a** (0.3 mmol), **2a** (30% solution 0.9 mmol), catalyst (15 mg), solvent (1.0 mL), 80 °C, 6 h; ^b: addition of TsOH (20 mol%); ^c: AIBN (azodiisobutyronitrile); ^d: TBHP (butyl hydroperoxide); ^e: the selectivity and yield of product were determined by the combination of liquid chromatography and gas chromatography.


Various substituents patterns and diverse functional groups in the aryl ring were used as viable substrates to react with **2a** (Scheme 2). A series of compounds bearing electron-donating groups (**3b**, **3g**, **3h**) can also be successfully converted to the desired products with excellent yields. Di-substituted electron-rich α -hydroxyacetophenones (**3c**, **3i**) can react smoothly with **2a**, affording the desired products in good yields. Various electron-withdraw groups, varying from halogen to cyano group (**3k-3n**), were also able to efficiently offer the corresponding products with the yields ranging from 83% to 59%. Lignin model compounds contained large steric hindrance groups (**3d-3e**, **3j**) was also well-tolerated in this reaction. Notably, the substituent bearing phenyl group reacted smoothly in the presence of HMS-DMSO-SO₃H, and the desired product **3f** was obtained in 74%, which has been reported by using HCl as a catalyst in HOAc at 110 °C for 24 h.⁵⁴ Interestingly, the heteroaromatic substrates could also be easily delivered uneventfully into the target product in moderate to good yields (**3o-3q**). These results indicated that the dipolar solid acids prepared with the aid of EBI were indeed efficient catalysts for the transformations of lignin model compounds to 1,3-dioxolane derivatives.

Scheme 2. The substrate scope of lignin model compounds to 1,3-dioxolane derivatives.

1a-q	2a	3a-3q
R = H, 3a , 95%		
R = 4-Me, 3b , 93%		
R = 2,5-Me, 3c , 76%		
R = 4- ⁱ Pr, 3d , 84%		
R = 4- ⁱ Bu, 3e , 78%		
R = 4-Ph, 3f , 74%		
R = 4-OH, 3g , 89%		
R = 4-OMe, 3h , 94%		
R = 3,4-OMe, 3i , 81%		
R = 4-OBn, 3j , 90%		
	R = 4-F, 3k , 83%	
	R = 4-Cl, 3l , 79%	
	R = 4-Br, 3m , 64%	
	R = 4-CN, 3n , 59%	
		3o , 82%
		3p , 84%
		3q , 90%

The conversion of isomaltulose to glucosyloxymethylfurfural (GMF) was also evaluated. GMF is an interesting analog of 5-hydroxymethylfurfural (HMF) with a glucosyl moiety that has several applications and is highly sensitive to the dipolar environment.⁵⁵⁻⁵⁷ As shown in Table 2, the reaction proceeded smoothly in γ -valerolactone (GVL), but hardly proceeded in THF and CPME (entries 1-3). Gratifyingly, when HMS-DMSO-SO₃H was used as the catalyst, the conversion of isomaltulose proceed smoothly in ⁱPrOAc, providing the desired product **5a** in 63% yield (entry 4). Given that **5a** can be effectively separated in a low boiling solvent, the results are acceptable (see the NMR spectra of the product in ESI), despite the fact that the yields obtained are not as good as those already reported for the method performed in DMSO. When TsOH and Amberlyst-15 were used as catalysts, the yield obtained is inferior to the former catalysts of HMS-DMSO-SO₃H (entries 5 and 6). In addition, HMS-DMSO and HMS-SO₃H proved to be unsuitable for this reaction (entries 7 and 8). When TsOH was introduced into the reaction system of HMS-DMSO, only 17% of the desired product was obtained (entry 9). Besides, when the grafting rate of sulfolene was decreased, the yield of the product also decreased significantly (entry 12). Furthermore, the desired product can be obtained in 25%, when the reference catalyst PSS-DMSO-SO₃H was used (entry 10). These observations imply the cooperative effect between the dipolar moieties and the acid groups are important factors in promoting chemical reactions (the mechanism see Figure S22 for details). The catalyst of HMS-DMSO-SO₃H prepared by free radical initiators did not display the expected catalytic performance (entry 11). These results further demonstrate that the dipolar catalysts modified by EBI techniques are indeed necessary to enhance the catalytic capacity in the process of transformation, especially the transformation of biomass-derived platform molecules.

Table 2. Catalytic reaction in the dehydration of isomaltulose to GMF.



Entry ^a	Catalyst	Solvent	Conv. (%) ^e	Select. (%) ^e	Yield (%) ^e
1	HMS-DMSO-SO ₃ H	THF	31	48	15
2	HMS-DMSO-SO ₃ H	CPME	10	0	0
3	HMS-DMSO-SO ₃ H	GVL	80	68	54
4	HMS-DMSO-SO ₃ H	iPrOAc	89	71	63
5	TsOH	iPrOAc	81	22	18
6	Amberlyst-15	iPrOAc	68	32	22
7	HMS-SO ₃ H	iPrOAc	62	11	7
8	HMS-DMSO	iPrOAc	0	0	0
9 ^b	HMS-DMSO	iPrOAc	32	53	17
10	PSS-DMSO-SO ₃ H	iPrOAc	58	43	25
11 ^c	HMS-DMSO-SO ₃ H	iPrOAc	8	0	0
12 ^d	HMS-DMSO-SO ₃ H	iPrOAc	25	48	12

^aReaction conditions: **4a** (50.0 mg, 0.15 mmol), catalyst (based on the amount of sulfonic acid 2.0 mol%), solvent (3.0 mL), 100 °C, 2 h; ^b: addition of TsOH (20 mol%) ^c: AIBN (azodisobutyronitrile); ^d: the amount of grafted DMSO moieties was approximately 0.6 mmol/g; ^e: the selectivity and yield of GMF were determined by the combination of liquid chromatography and gas chromatography.

In summary, the EBI technology provides an efficient and general method for dipolarization based on existing catalysts. Compared with traditional chemical methods, it has the advantages of simple steps, high efficiency, no initiator and easy engineering production. The use of the dipolar catalysts, not only enables successfully conversion of the biomass platform molecules, but also facilitated the separation of products in low boiling point solvent. Considering the economy and high efficiency of this method, this work opens up an avenue for the design, synthesis, and application of catalysts.

AUTHOR INFORMATION

Corresponding Author

Yanlong Gu – State Key Laboratory of Advanced Electromagnetic Engineering and Technology, School of Chemistry and Chemical Engineering, Huazhong University of Science and Technology, Wuhan 430074, China; Email: klgyl@hust.edu.cn

Jiang Huang – State Key Laboratory of Advanced Electromagnetic Engineering and Technology, School of Electrical and Electronic Engineering, Huazhong University of Science and Technology, Wuhan 430074, China; Email: jhuang@hust.edu.cn

Authors

Zhiyan Chen – Key laboratory of Material Chemistry for Energy Conversion and Storage, School of Chemistry and Chemical Engineering, Huazhong University of Science and Technology, Wuhan 430074, China

Haozhe Li – Key laboratory of Material Chemistry for Energy Conversion and Storage, School of Chemistry and Chemical Engineering, Huazhong University of Science and Technology, Wuhan 430074, China

Keyan Sheng – State Key Laboratory of Advanced Electromagnetic Engineering and Technology, School of Electrical and Electronic Engineering, Huazhong University of Science and Technology, Wuhan 430074, China

Xiaohan Dong – Key laboratory of Material Chemistry for Energy Conversion and Storage, School of Chemistry and Chemical Engineering, Huazhong University of Science and Technology, Wuhan 430074, China

Jushigang Yuan – State Key Laboratory of Advanced Electromagnetic Engineering and Technology, School of Electrical and Electronic Engineering, Huazhong University of Science and Technology, Wuhan 430074, China

Shuai Hao – Key laboratory of Material Chemistry for Energy Conversion and Storage, School of Chemistry and Chemical Engineering, Huazhong University of Science and Technology, Wuhan 430074, China

Minghao Li – Key laboratory of Material Chemistry for Energy Conversion and Storage, School of Chemistry and Chemical Engineering, Huazhong University of Science and Technology, Wuhan 430074, China

Rongxian Bai – Key laboratory of Material Chemistry for Energy Conversion and Storage, School of Chemistry and Chemical Engineering, Huazhong University of Science and Technology, Wuhan 430074, China

Yves Queneau – Institut de Chimie et Biochimie Moléculaires et Supramoléculaires (ICBMS), Université de Lyon, CNRS, Université Lyon 1, INSA Lyon, CPE Lyon, UMR 5246, Université Claude Bernard, Bâtiment Lederer, 1 Rue Victor Grignard, 69622 Villeurbanne, France

Alexander Sidorenko – Institute of Chemistry of New Materials of National Academy of Sciences of Belarus, Skaryna str, 36, 220084 Minsk, Belarus

Funding Sources

National Key Research and Development Project (2022YFE0124100), Ordos Key Research and Development Project (2022EEDSKJZDZX003), the National Natural Science Foundation of China (22072049, 21902054 and 21872060) and the HUST Academic Frontier Youth Team (2019QYTD06) are the key funding sources for the financial support. Financial support is also partially from CNRS and MESRI for financial support and to the China Scholarship Council for a scholarship to Lianjie Wang who prepared GMF samples in the Lyon team.

Notes

The authors declare no competing financial interest.

ASSOCIATED CONTENT

The Supporting Information is available free of charge via the Internet at <http://pubs.acs.org>.

The synthetic procedures, optimization data, chemical computations, experimental procedures, and characterization data (PDF)

ACKNOWLEDGMENT

We gratefully acknowledge the financial support from National Key Research and Development Project (2022YFE0124100), Ordos Key Research and Development Project (2022EEDSKJZDZX003), the National Natural Science Foundation of China (22072049, 21902054 and 21872060) and the HUST Academic Frontier Youth Team (2019QYTD06) for the financial support. Financial support from CNRS and MESRI and the China Scholarship Council for a scholarship to Lianjie Wang who prepared GMF samples in the Lyon team is also acknowledged.

REFERENCES

- (1) Shen, X.; Zhang, C.; Han, B.; Wang, F., Catalytic self-transfer hydrogenolysis of lignin with endogenous hydrogen: road to the carbon-neutral future. *Chem. Soc. Rev.* **2022**, *51*, 1608–1628.
- (2) Ates, B.; Koytepe, S.; Ulu, A.; Gurses, C.; Thakur, V. K., Chemistry, Structures, and Advanced Applications of Nanocomposites from Biorenewable Resources. *Chem. Rev.* **2020**, *120*, 9304–9362.
- (3) De, S.; Saha, B.; Luque, R., Hydrodeoxygenation processes: Advances on catalytic transformations of biomass-derived platform chemicals into hydrocarbon fuels. *Bioresour. Technol.* **2015**, *178*, 108–118.
- (4) Xu, C.; Paone, E.; Rodríguez-Padrón, D.; Luque, R.; Mauriello, F., Recent catalytic routes for the preparation and the upgrading of biomass derived furfural and 5-hydroxymethylfurfural. *Chem. Soc. Rev.* **2020**, *49*, 4273–4306.
- (5) Gu, Y.; Jérôme, F., Bio-based solvents: an emerging generation of fluids for the design of eco-efficient processes in catalysis and organic chemistry. *Chem. Soc. Rev.* **2013**, *42*, 9550–9570.
- (6) Shuai, L.; Amiri, M. T.; Questell-Santiago, Y. M.; Héroguel, F.; Li, Y.; Kim, H.; Meilan, R.; Chapple, C.; Ralph, J.; Luterbacher, J. S., Formaldehyde stabilization facilitates lignin monomer production during biomass depolymerization. *Science* **2016**, *354*, 329–333.
- (7) Xia, Q.; Chen, Z.; Shao, Y.; Gong, X.; Wang, H.; Liu, X.; Parker, S. F.; Han, X.; Yang, S.; Wang, Y., Direct hydrodeoxygenation of raw woody biomass into liquid alkanes. *Nat. Commun.* **2016**, *7*, 11162.
- (8) Zhao, H.; Holladay, J. E.; Brown, H.; Zhang, Z. C., Metal chlorides in ionic liquid solvents convert sugars to 5-hydroxymethylfurfural. *Science* **2007**, *316*, 1597–600.
- (9) Espro, C.; Paone, E.; Mauriello, F.; Gotti, R.; Uliassi, E.; Bolognesi, M. L.; Rodríguez-Padrón, D.; Luque, R., Sustainable production of pharmaceutical, nutraceutical and bioactive compounds from biomass and waste. *Chem. Soc. Rev.* **2021**, *50*, 11191–11207.
- (10) Corma, A.; Iborra, S.; Velty, A., Chemical Routes for the Transformation of Biomass into Chemicals. *Chem. Rev.* **2007**, *107*, 2411–2502.
- (11) Thiyagarajan, S.; Genuino, H. C.; van der Waal, J. C.; de Jong, E.; Weckhuysen, B. M.; van Haveren, J.; Bruijninx, P. C. A.; van Es, D. S., A Facile Solid-Phase Route to Renewable Aromatic Chemicals from Biobased Furanics. *Angew. Chem. Int. Ed.* **2016**, *55*, 1368–1371.
- (12) Gao, F.; Bai, R.; Ferlin, F.; Vaccaro, L.; Li, M.; Gu, Y., Replacement strategies for non-green dipolar aprotic solvents. *Green Chem.* **2020**, *22*, 6240–6257.
- (13) Zhang, X.; Wilson, K.; Lee, A. F., Heterogeneously Catalyzed Hydrothermal Processing of C5–C6 Sugars. *Chem. Rev.* **2016**, *116*, 12328–12368.
- (14) Mellmer, M. A.; Sener, C.; Gallo, J. M. R.; Luterbacher, J. S.; Alonso, D. M.; Dumesic, J. A., Solvent Effects in Acid-Catalyzed Biomass Conversion Reactions. *Angew. Chem. Int. Ed.* **2014**, *53*, 11872–11875.
- (15) Nikolakis, V.; Mushrif, S. H.; Herbert, B.; Booksh, K. S.; Vlachos, D. G., Fructose–Water–Dimethylsulfoxide Interactions by Vibrational Spectroscopy and Molecular Dynamics Simulations. *J. Phys. Chem. B* **2012**, *116*, 11274–11283.
- (16) Mellmer, M. A.; Sanpitakseree, C.; Demir, B.; Ma, K.; Elliott, W. A.; Bai, P.; Johnson, R. L.; Walker, T. W.; Shanks, B. H.; Rioux, R. M.; Neurock, M.; Dumesic, J. A., Effects of chloride ions in acid-catalyzed biomass dehydration reactions in polar aprotic solvents. *Nat. Commun.* **2019**, *10*, 1132.
- (17) Bui, L.; Luo, H.; Gunther, W. R.; Román-Leshkov, Y., Domino Reaction Catalyzed by Zeolites with Brønsted and Lewis Acid Sites for the Production of γ -Valerolactone from Furfural. *Angew. Chem. Int. Ed.* **2013**, *52*, 8022–8025.
- (18) Marković, D.; Vogel, P., Polysulfones: Catalysts for Alkene Isomerization. *Angew. Chem. Int. Ed.* **2004**, *43*, 2928–2930.
- (19) Schwartz, T. J.; Johnson, R. L.; Cardenas, J.; Okerlund, A.; Da Silva, N. A.; Schmidt-Rohr, K.; Dumesic, J. A., Engineering Catalyst Microenvironments for Metal-Catalyzed Hydrogenation of Biologically Derived Platform Chemicals. *Angew. Chem. Int. Ed.* **2014**, *53*, 12718–12722.
- (20) Alamillo, R.; Crisci, A. J.; Gallo, J. M. R.; Scott, S. L.; Dumesic, J. A., A Tailored Microenvironment for Catalytic Biomass Conversion in Inorganic–Organic Nanoreactors. *Angew. Chem. Int. Ed.* **2013**, *52*, 10349–10351.
- (21) Sun, Q.; Wang, S.; Aguila, B.; Meng, X.; Ma, S.; Xiao, F.-S., Creating solvation environments in heterogeneous catalysts for efficient biomass conversion. *Nat. Commun.* **2018**, *9*, 3236.
- (22) Sun, Q.; Tang, Y.; Aguila, B.; Wang, S.; Xiao, F.-S.; Thallapally, P. K.; Al-Enizi, A. M.; Nafady, A.; Ma, S., Reaction Environment Modification in Covalent Organic Frameworks for Catalytic Performance Enhancement. *Angew. Chem. Int. Ed.* **2019**, *58*, 8670–8675.
- (23) Gao, F.; Bai, R.; Li, M.; Gu, Y., Dipolar HCP materials as alternatives to DMF solvent for azide-based synthesis. *Green Chem.* **2021**, *23*, 7499–7505.
- (24) Hübner, S.; de Vries, J. G.; Farina, V., Why Does Industry Not Use Immobilized Transition Metal Complexes as Catalysts? *Adv. Synth. Catal.* **2016**, *358*, 3–25.
- (25) Arun, N.; Sharma, R. V.; Dalai, A. K., Green diesel synthesis by hydrodeoxygenation of bio-based feedstocks: Strategies for catalyst design and development. *Renew. Sust. Energ. Rev.* **2015**, *48*, 240–255.
- (26) Kim, J.; Lee, W. J.; Park, H. W., The state of the art in the electron beam manufacturing processes. *Int. J. Precis. Eng. Manuf.* **2016**, *17*, 1575–1585.
- (27) Zhang, M.; Chen, J.; Zhang, S.; Zhou, X.; He, L.; Sheridan, M. V.; Yuan, M.; Zhang, M.; Chen, L.; Dai, X.; Ma, F.; Wang, J.; Hu, J.; Wu, G.; Kong, X.; Zhou, R.; Albrecht-Schmitt, T. E.; Chai, Z.; Wang, S., Electron Beam Irradiation as a General Approach for the Rapid Synthesis of Covalent Organic Frameworks under Ambient Conditions. *J. Am. Chem. Soc.* **2020**, *142*, 9169–9174.
- (28) Chen, J.; Zhang, M.; Shu, J.; Yuan, M.; Yan, W.; Bai, P.; He, L.; Shen, N.; Gong, S.; Zhang, D.; Li, J.; Hu, J.; Li, R.; Wu, G.; Chai, Z.; Yu, J.; Wang, S., Electron Beam Irradiation-Induced Formation of Defect-Rich Zeolites under Ambient Condition within Minutes. *Angew. Chem. Int. Ed.* **2021**, *60*, 14858–14863.
- (29) Xie, K.; Dong, Z.; Zhai, M.; Shi, W.; Zhao, L., Radiation-induced surface modification of silanized silica with n-alkylimidazolium ionic liquids and their applications for the removal of ReO_4^- as an analogue for TcO_4^- . *Appl. Surf. Sci.* **2021**, *551*, 149406.
- (30) Sheng, K.; Dong, X.; Chen, Z.; Zhou, Z.; Gu, Y.; Huang, J., Increasing the surface hydrophobicity of silicone rubber by electron beam irradiation in the presence of a glycerol layer. *Appl. Surf. Sci.* **2022**, *591*, 153097.
- (31) Sun, Q.; Aguila, B.; Perman, J.; Earl, L. D.; Abney, C. W.; Cheng, Y.; Wei, H.; Nguyen, N.; Wojtas, L.; Ma, S., Postsynthetically Modified Covalent Organic Frameworks for Efficient and Effective Mercury Removal. *J. Am. Chem. Soc.* **2017**, *139*, 2786–2793.
- (32) Rostamizadeh, S.; Estiri, H.; Azad, M., Au anchored to (α - Fe_2O_3)-MCM-41-HS as a novel magnetic nanocatalyst for water-medium and solvent-free alkyne hydration. *Catal. Commun.* **2014**, *57*, 29–35.
- (33) Li, B.; Zhang, Y.; Ma, D.; Shi, Z.; Ma, S., Mercury nano-trap for effective and efficient removal of mercury(II) from aqueous solution. *Nat. Commun.* **2014**, *5*, 5537.
- (34) Chen, J.; Li, K.; Chen, L.; Liu, R.; Huang, X.; Ye, D., Conversion of fructose into 5-hydroxymethylfurfural catalyzed by recyclable sulfonic acid-functionalized metal–organic frameworks. *Green Chem.* **2014**, *16*, 2490–2499.
- (35) Phang, W. J.; Jo, H.; Lee, W. R.; Song, J. H.; Yoo, K.; Kim, B.; Hong, C. S., Superprotonic Conductivity of a UiO-66 Framework Functionalized with Sulfonic Acid Groups by Facile Postsynthetic Oxidation. *Angew. Chem. Int. Ed.* **2015**, *54*, 5142–5146.
- (36) Zhan, S.; Tao, X.; Cai, L.; Liu, X.; Liu, T., The carbon material functionalized with NH_2^+ and SO_3H groups catalyzed esterification with high activity and selectivity. *Green Chem.* **2014**, *16*, 4649–4653.

- (37) Yang, Q.; Kapoor, M. P.; Inagaki, S., Sulfuric Acid-Functionalized Mesoporous Benzene-Silica with a Molecular-Scale Periodicity in the Walls. *J. Am. Chem. Soc.* **2002**, *124*, 9694–9695.
- (38) Lang, X.; Jia, W.; Wang, Y.; Zhu, Z., Novel fluorination of polystyrene sulfonic acid resin by $\text{CF}_3\text{SO}_3\text{H}$ for high stability and strong acidity. *Catal. Commun.* **2015**, *70*, 58–61.
- (39) Kang, D. W.; Lim, K. S.; Lee, K. J.; Lee, J. H.; Lee, W. R.; Song, J. H.; Yeom, K. H.; Kim, J. Y.; Hong, C. S., Cost-Effective, High-Performance Porous-Organic-Polymer Conductors Functionalized with Sulfonic Acid Groups by Direct Postsynthetic Substitution. *Angew. Chem. Int. Ed.* **2016**, *55*, 16123–16126.
- (40) González, M. D.; Salagre, P.; Taboada, E.; Llorca, J.; Cesteros, Y., Microwave-assisted synthesis of sulfonic acid-functionalized microporous materials for the catalytic etherification of glycerol with isobutene. *Green Chem.* **2013**, *15*, 2230–2239.
- (41) Liu, F.; Kong, W.; Qi, C.; Zhu, L.; Xiao, F.-S., Design and Synthesis of Mesoporous Polymer-Based Solid Acid Catalysts with Excellent Hydrophobicity and Extraordinary Catalytic Activity. *ACS Catal.* **2012**, *2*, 565–572.
- (42) Fu, J.; Ji, X.; Chen, J.; Chen, L.; Fan, X.; Mu, D.; Wang, C., Lithium Nitrate Regulated Sulfone Electrolytes for Lithium Metal Batteries. *Angew. Chem. Int. Ed.* **2020**, *59*, 22194–22201.
- (43) Apiwattanakul, P.; Rimjaem, S., Electron beam dynamic study and Monte Carlo simulation of accelerator-based irradiation system for natural rubber vulcanization. *Nucl. Instrum. Methods B* **2020**, *466*, 69–75.
- (44) Chen, J.; Zhang, M.; Zhang, S.; Cao, K.; Mao, X.; Zhang, M.; He, L.; Dong, X.; Shu, J.; Dong, H.; Zhai, F.; Shen, R.; Yuan, M.; Zhao, X.; Wu, G.; Chai, Z.; Wang, S., Metal-Organic Framework@Metal Oxide Heterostructures Induced by Electron-Beam Radiation. *Angew. Chem. Int. Ed.* **2022**, e202212532.
- (45) Lai, B.; Huang, Z.; Jia, Z.; Bai, R.; Gu, Y., Silica-supported metal acetylacetonate catalysts with a robust and flexible linker constructed by using 2-butoxy-3,4-dihydropyrans as dual anchoring reagents and ligand donors. *Catal. Sci. Technol.* **2016**, *6*, 1810–1820.
- (46) Yang, Z.; Cao, J.; He, Y.; Yang, J. H.; Kim, T.; Peng, X.; Kim, J. S., Macro-/micro-environment-sensitive chemosensing and biological imaging. *Chem. Soc. Rev.* **2014**, *43*, 4563–4601.
- (47) Yang, Z.; He, Y.; Lee, J. H.; Chae, W.-S.; Ren, W. X.; Lee, J. H.; Kang, C.; Kim, J. S., A Nile Red/BODIPY-based bimodal probe sensitive to changes in the micropolarity and microviscosity of the endoplasmic reticulum. *Chem. Commun.* **2014**, *50*, 11672–11675.
- (48) Swain, J.; Mishra, A. K., Nile red fluorescence for quantitative monitoring of micropolarity and microviscosity of pluronic F127 in aqueous media. *Photochem. Photobiol. Sci.* **2016**, *15*, 1400–1407.
- (49) Jee, A.-Y.; Park, S.; Kwon, H.; Lee, M., Excited state dynamics of Nile Red in polymers. *Chem. Phys. Lett.* **2009**, *477*, 112–115.
- (50) Chen, Z.; Huang, W.; Yi, L.; Dong, X.; Sheng, K.; Li, M.; Bai, R.; Sidorenko, A. Y.; Huang, J.; Gu, Y., Synthesis of indoles and carbazoles from a lignin model compound α -hydroxyacetophenone. *Green Chem.* **2022**, *24*, 2919–2926.
- (51) Tarr, J. C.; Johnson, J. S., Lanthanum Tricyanide-Catalyzed Acyl Silane-Ketone Benzoin Additions and Kinetic Resolution of Resultant α -Silyloxyketones. *J. Org. Chem.* **2010**, *75*, 3317–3325.
- (52) Lei, W.-L.; Yang, B.; Zhang, Q.-B.; Yuan, P.-F.; Wu, L.-Z.; Liu, Q., Visible-light-enabled aerobic synthesis of benzoin bis-ethers from alkynes and alcohols. *Green Chem.* **2018**, *20*, 5479–5483.
- (53) Yoshikawa, N.; Kumagai, N.; Matsunaga, S.; Moll, G.; Ohshima, T.; Suzuki, T.; Shibasaki, M., Direct Catalytic Asymmetric Aldol Reaction: Synthesis of Either syn- or anti- α,β -Dihydroxy Ketones. *J. Am. Chem. Soc.* **2001**, *123*, 2466–2467.
- (54) Vainer, A. Y.; Askerov, D. B.; Isaev, Y. V.; Popkova, V. Y.; Lakhonina, T. I.; Tishchenko, A. I., ChemInform Abstract: Study of Products of the Condensation of Benzoin with Formaldehyde in an Acetic Acid Medium. *Chemischer Informationsdienst* **1979**, *10* (14). DOI: 10.1002/chin.197914204.
- (55) Tan, J.-N.; Ahmar, M.; Queneau, Y., Glucosyloxymethylfurfural (GMF): a creative renewable scaffold towards bioinspired architectures. *Pure Appl. Chem.* **2015**, *87*, 827–839.
- (56) Lichtenthaler, F. W.; Brust, A.; Cuny, E., Sugar-derived building blocks. Part 26. Hydrophilic pyrroles, pyridazines and diazepinones from -fructose and isomaltulose. *Green Chem.* **2001**, *3*, 201–209.
- (57) Ontiveros, J. F.; Wang, L.; Chatel, K.; Yue, X.; Tan, J.-N.; Ali-Rachedi, F.; Ahmar, M.; Verrier, C.; Fusina, A.; Nardello-Rataj, V.; Queneau, Y., Design and Properties of a Novel Family of Nonionic Biobased Furanic Hydroxyester and Amide Surfactants. *ACS Sustainable Chem. Eng.* **2021**, *9*, 16977–16988.




Table of Contents