

Characterization of a multilayer x-ray waveguide by x-ray diffuse scattering and grazing incidence x-ray fluorescence

Philippe Jonnard, Jean-Michel André, Karine Le Guen, Yves Ménesguen, Anastasia Novikova, Marie-Christine Lépy, Mohammed H. Modi, Mitali Sinha, Amol Singh

► To cite this version:

Philippe Jonnard, Jean-Michel André, Karine Le Guen, Yves Ménesguen, Anastasia Novikova, et al.. Characterization of a multilayer x-ray waveguide by x-ray diffuse scattering and grazing incidence x-ray fluorescence. PXRNMS2018, Physics of X-ray and Neutron Multilayer Structures, Nov 2018, Palaiseau, France. hal-03932488

HAL Id: hal-03932488 https://hal.science/hal-03932488

Submitted on 10 Jan2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Characterization of a multilayer x-ray waveguide by x-ray diffuse scattering and grazing incidence x-ray fluorescence

P. Jonnard¹, J.-M. André¹, K. Le Guen¹, Y. Ménesguen², A. Novikova², M.-C. Lépy², M. H. Modi³, M. Sinha³, A. Singh^{3,4}

¹ Sorbonne Université, Département des Sciences et Ingénierie, UMR CNRS, Laboratoire de Chimie Physique - Matière et Rayonnement, 4 place Jussieu, F-75252 Paris cedex 05, France

² CEA, LIST, Laboratoire National Henri Becquerel (LNE-LNHB), bât 602 PC 111, CEA-Saclay, F-91191 Gif-sur-Yvette, France ³ Soft X-ray Applications Lab, Raja Ramanna Centre for Advanced Technology, Indore 452013, India

⁴ National Synchrotron Radiation Research Center, Hsinchu, Taiwan 30076



Geometry of the **diffuse scattering** experiment and scattering curves measured at 10.25 keV. The detector is at 2° from the incident direction. (a): whole scanned range. (b): angular range where the guided mode feature is present. (c): comparison between experiment (solid line) and simulation (dashed line).



X-ray emission spectrum of the sample measured by a SDD (left). Comparison of the experimental (solid-dotted line) and simulated (dashed line) **GIXRF** curves of W La (a) and Zr La (b); (d) W La and W Mb curves plotted on a common intensity scale. Measurements are performed at 10.25 keV.

Conclusion

	Thickness from	Thickness from	Diffuseness from	In-plane correlation
	design (nm)	GIXR - XDS (nm)	GIXR - XDS (nm)	length (nm)
Al	5	7 ± 1	2.8 ± 0.2	20 ± 10
ZrC	7	8.0 ± 0.5	2.8 ± 0.2	30 ± 5
Al	15	20 ± 1	2.8 ± 0.2	20 ± 10
W	50	50	-	-

The combination of diffuse scattering and GIXRF results puts constraints on the fit process and makes us expecting a precise description of this AI/ZrC/AI/W planar waveguide.