

Glycosaminoglycan mimetics obtained by microwave-assisted sulfation of marine bacterium sourced infernan exopolysaccharide

Sylvia Colliec-Jouault, Fabiana Esposito, Hélène Ledru, Corinne Sinquin, Arnaud Fillaudeau, Sylvain Routier, Frédéric Buron, Chrystel Lopin-Bon, Stéphane Cuenot, Emiliano Bedini, et al.

▶ To cite this version:

Sylvia Colliec-Jouault, Fabiana Esposito, Hélène Ledru, Corinne Sinquin, Arnaud Fillaudeau, et al.. Glycosaminoglycan mimetics obtained by microwave-assisted sulfation of marine bacterium sourced infernan exopolysaccharide. Biomacromolecules, 2023, 24, pp.462-470. 10.1021/acs.biomac.2c01277 . hal-03948691

HAL Id: hal-03948691 https://hal.science/hal-03948691v1

Submitted on 20 Jan 2023 $\,$

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

1 Glycosaminoglycan-Mimetics Obtained by Microwave-Assisted Sulfation of

2 Marine Bacterium Sourced Infernan Exopolysaccharide

- 3 Sylvia Colliec-Jouault^{a*}, Fabiana Esposito,^b Hélène Ledru,^c Corinne Sinquin,^a Laetitia
- 4 Marchand,^a Arnaud Fillaudeau,^a Sylvain Routier,^c Frédéric Buron,^c Chrystel Lopin-Bon,^c
- 5 Stéphane Cuenot,^d Emiliano Bedini^b and Agata Zykwinska^a
- ⁶ ^a Ifremer, Centre Atlantique, MASAE, Nantes, France
- ⁷ ^b Department of Chemical Sciences, University of Naples Federico II, Complesso Universitario
- 8 Monte S.Angelo, via Cintia 4, I-80126 Napoli, Italy
- ^o Institut de Chimie Organique et Analytique, UMR 7311, Université d'Orléans et CNRS, Rue
- 10 de Chartres, BP 6759, 45067 Orléans Cedex 2, France
- ¹¹ ^d Nantes Université, CNRS, Institut des Matériaux Jean Rouxel, IMN, Nantes, France

12

- 13 **Corresponding Author**
- * E-mail address: <u>Sylvia.Colliec.Jouault@ifremer.fr.</u> Tel: + 33 2 40 37 40 93.

15

16

18 ABSTRACT

Sulfated glycosaminoglycans (GAGs) are fundamental constituents of both cell surface and 19 extracellular matrix. By playing a key role in cell-cell and cell-matrix interactions, GAGs are 20 involved in many physiological and pathological processes. To design GAG-mimetics with 21 similar therapeutic potential than the natural ones, the specific structural features, amongst 22 sulfate content, sulfation pattern and chain length should be considered. In the present study, 23 we describe a sulfation method based on microwave radiation to obtain highly-sulfated 24 derivatives as GAG-mimetics. The starting low-molecular weight (LMW) derivative was 25 prepared from infernan exopolysaccharide, a highly branched naturally slightly-sulfated 26 heteropolysaccharide synthesized by the deep-sea hydrothermal vent bacterium Alteromonas 27 infernus. LMW highly-sulfated infernan derivatives obtained by a conventional heating 28 sulfation have already been shown to display GAG-mimetic properties. Here, the potential of 29 microwave-assisted sulfation versus conventional method to obtain GAG-mimetics was 30 explored. Structural analysis by NMR revealed that both highly-sulfated derivatives shared 31 similar structural features, emphasizing that microwave-assisted sulfation with twelve-fold 32 shorter reaction time is as efficient as the classical one. 33

34

35 KEYWORDS: exopolysaccharide, microwave-assisted sulfation, semi-synthesis,
36 glycosaminoglycan-mimetics

38 INTRODUCTION

Sulfated glycosaminoglycans (GAGs), such as heparin, heparan sulfate and chondroitin 39 sulfate are highly evolutionary conserved complex anionic linear polysaccharides found in a 40 broad range of both vertebrates and invertebrates. They are fundamental constituents of both 41 cell surface and extracellular matrix, and through their localization they participate in many 42 biological processes by playing a key role in cell-cell and cell-matrix interactions.¹ Biological 43 effects of GAGs are mainly due to their interaction with various proteins present in their 44 microenvironment, including chemokines, cytokines, growth factors, morphogens, enzymes 45 and their natural inhibitors and adhesion molecules. The binding between GAGs and proteins 46 requires specific structural features, such as sulfation pattern, conformational flexibility, chain 47 length and counter-ions, which determine the level of affinity.² These structural requirements 48 are essential to design compounds that mimic the bioactive function of GAGs and to fine-tune 49 their benefit/risk ratio.³ With the demand of both animal-free molecules and environmentally 50 friendly processes, the production of GAG-mimetics from other sources than mammalian 51 tissues is flourishing, especially to avoid a risk of contamination by harmful substances and/or 52 unconventional pathogens.⁴ The production of GAG-mimetics with specific biological targets 53 can be performed by organic synthesis or chemo-enzymatic approaches.^{5,6} Synthetic routes 54 55 have however some limits because oligosaccharides longer than dodecasaccharides are not easily achieved and their specific sulfation is still a challenge⁷. GAG-mimetics have also been 56 developed from natural polymers, especially polysaccharides obtained from different sources, 57 such as plant, algae and bacteria. The use of exopolysaccharide (EPS) producing bacteria is 58 highly advantageous over traditional polysaccharide sources. Indeed, EPS production by 59 fermentation represents a renewable and sustainable process devoid of risks related to raw 60 material supply. In addition, their production in bioreactors can be controlled and optimized to 61 obtain high yields, while keeping the EPS composition and structure. Some bacteria are able to 62

synthesize polysaccharides with structures close or even apparently identical to mammalian 63 GAGs. Escherichia coli serotype K5 can produce a precursor of heparin, unsulfated heparosan, 64 whereas E. coli K4 produces unsulfated chondroitin.^{8,9} However, bacterial EPSs are often 65 unsulfated or only weakly sulfated, and their chemical oversulfation is therefore required to 66 obtain GAG-mimetics. The use of sulfur trioxide complexes as sulfating agent in organic 67 solvents such as formamide, N,N-dimethylformamide (DMF), dimethylsulfoxide or pyridine is 68 recommended to avoid uncontrolled depolymerization usually observed with sulfuryl chloride, 69 sulfuric acid or chlorosulfuric acid.¹⁰ In comparison to the conventional heating, sulfation using 70 microwave radiation has recently been recognized as a powerful method allowing to improve 71 the heating regulation, reagent mixing and reaction kinetics. The time of reaction can 72 considerably be reduced, which minimizes product degradation.^{11,12} Therefore, microwave-73 assisted synthesis leads to homogeneously sulfated polysaccharides with both excellent yield 74 75 and reproducibility.

The bacterial EPSs from terrestrial origin present a great structural diversity but this diversity 76 is tremendously increased in the marine environment due to the enormity of the marine 77 biosphere.¹³ Several EPS-producing marine strains have been studied, which led to the 78 discovery and isolation of novel macromolecules exhibiting valuable biological activities, in 79 particular GAG-mimetic properties.¹⁴⁻¹⁶ Alteromonas infernus, a deep-sea hydrothermal vent 80 bacterium isolated in Guaymas basin in Gulf of California, produces a high-molecular weight 81 (HMW), slightly sulfated (3% of sulfur) EPS, named infernan.^{17,18} In our previous studies, 82 GAG-mimetic properties of infernan resulting not only from the presence of sulfate groups but 83 also from uronic acid residues were shown both in vitro and in vivo.¹⁹⁻²⁴ The addition of the 84 native EPS into cellulose-based hydrogel supported the 3D culture of functionally competent 85 chondrocytes able to produce type II collagen and sulfated GAGs.¹⁹ In order to further enhance 86 its GAG-mimetic properties, native infernan was depolymerized and chemically oversulfated 87

to obtain low-molecular weight (LMW) and highly sulfated derivatives, with molecular weight 88 ranging from 8,000 to 30,000 g/mol and a sulfur content from 12 to 14 %S (w/w).²⁰ Through 89 their physical interactions with growth factors, e.g. TGF-B1 and BMP-2, these highly sulfated 90 derivatives were able to induce cellular processes essential for tissue regeneration.²¹⁻²³ 91 Moreover, their presence allowed to effectively inhibit both migration and invasiveness of 92 osteosarcoma cells in vitro, as well as the establishment of lung metastases in vivo.²⁴ LMW 93 highly sulfated derivatives displayed also some anticoagulant properties, remaining however 94 lower compared to LMW heparin and unfractionated heparin (2.5 and 6.5 times, respectively).²⁵ 95 96 These bioactive derivatives are classically prepared in the presence of sulfur trioxide pyridine complex (SO₃·py) in dry DMF and the reaction is followed for 2h at 45°C.²⁰ In this context, the 97 objective of the present study was to prepare highly sulfated infernan derivatives as GAG 98 mimetics using microwave radiation with similar features to those usually prepared by 99 100 conventional method. By tuning the sulfation conditions, derivatives with different sulfate contents were obtained and fully characterized. The structure of the EPS derivatives with the 101 highest sulfate content obtained by both conventional and microwave radiation sulfation 102 methods was analyzed by NMR and compared with the LMW-infernan precursors. The 103 obtained results clearly emphasized that microwave-assisted sulfation is a fast and efficient 104 method to get suitable GAG-mimetic derivatives. 105

106

107 EXPERIMENTAL SECTION

LMW EPS Derivative Production and Modification. Infernan EPS was produced by fermentation of the marine bacterium *A. infernus* as described previously.²⁵ LMW EPS derivatives (EPS DR), with an average molecular weight of 7,800 g/mol (EPS DR_{7,8k}) and 19,000 g/mol (EPS DR_{19k}) were obtained by the depolymerization of the native EPS using a free-radical process as previously described.²⁰ After depolymerization, polysaccharide chains were reduced with sodium borohydride, purified on Chelex® resin, ultrafiltered on a 1 kD (EPS DR_{7,8k}) or 10 kDa (EPS DR_{19k}) cut-off membrane and finally freeze-dried. In order to obtain a homogeneous fraction with a low polydispersity, a gel filtration chromatography on a Superdex® 30 (GE Healthcare Life Sciences), using an AKTA FPLC system coupled with a refractometric detector (Gilson®), was performed in water. EPS DR fractions were pooled and freeze-dried prior to sulfation step.

Sulfation by Conventional Heating. Oversulfated EPS derivatives (EPS DRS) were obtained by a chemical sulfation of EPS DR_{7,8k}, as described previously.²⁰ Sulfation was performed in duplicate at three different EPS/SO₃·py w/w ratios: 1/5, 1/2.5 or 1/1.25. Briefly, EPS DR_{7,8k} (20 mg) in its pyridinium salt form was firstly solubilized in extra dry DMF over molecular sieve (4 mL) for 2h at 45°C under continuous stirring and then sulfated for the next 2h at 45°C in the presence of SO₃·py (100, 50, or 25 mg). The final aqueous solution (pH 7) was dialyzed against water for three days before freeze-drying.

Sulfation by Microwave Radiation. Oversulfated EPS derivatives (EPS DRS-MW) were 126 obtained in duplicate by a microwave-assisted sulfation of EPS DR7.8k using three different 127 EPS/SO₃·py w/w ratios: 1/5, 1/2.5 or 1/1.25 using a Biotage Initiator Microwave Synthesizer 128 (Sweden). Briefly, EPS DR_{7.8k} (25 mg) in its pyridinium salt form was firstly solubilized in 129 extra dry DMF over molecular sieve (12.5 mL) under stirring for 2 h at 45 °C. Then, SO₃·py 130 (125, 62.5, or 31.2 mg) was added and the mixture was placed in the microwave oven turn table 131 and exposed to 300 Watts maximum power (temperature was measured and controlled 132 externally by an IR probe) for 10 min at 45°C. The obtained solution (pH 7) was then dialyzed 133 against water for three days before freeze-drying. In order to determine the potential effect of 134 microwave radiation on polysaccharides, EPS DR7,8k was also exposed to microwaves without 135 any SO₃·py addition. 136

Physico-chemical Analyses. Monosaccharide Composition. Monosaccharide composition 137 was determined in triplicate according to the Kamerling *et al* method as modified by Montreuil 138 et al.^{26,27} Briefly, infernan and its LMW derivatives (EPS DR) were hydrolyzed for 4h at 100°C 139 by 3 M MeOH/HCl with myo-inositol used as internal standard. After re-N-acetylation with 140 acetic anhydride overnight at room temperature, the methyl glycosides were converted to their 141 corresponding trimethylsilyl derivatives. Separation and quantification of the per-O-142 trimethylsilyl methyl glycosides were performed by gas chromatography (GC-FID, Agilent 143 Technologies 6890N). 144

Molecular Weight and Polydispersity Index. The weight-average molecular weight (Mw) 145 was determined by high-performance size-exclusion chromatography (HPSEC) coupled with 146 multi-angle light scattering (MALS, Dawn Heleos-II, Wyatt Technology) and differential 147 refractive index (RI) (Optilab Wyatt technology) detectors. HPSEC system was composed of a 148 Prominence Shimadzu HPLC system, a PL aquagel-OH mixed, 8 µm (Varian) guard column 149 $(U 7.5 \text{mm} \times L 50 \text{ mm})$, and a PL aquagel-OH mixed (Varian) separation column. Samples (in 150 duplicate) were eluted with 0.1 M ammonium acetate at 1 mL/min flow rate. The mean 151 molecular weight was calculated using a refractive index increment dn/dc of 0.145 mL/g. To 152 estimate the heterogeneity of measured sizes of the native EPS and its derivatives, the 153 polydispersity index (Ip) was calculated by the Mw/Mn ratio, where Mn is the number average 154 molar mass. 155

Elemental Analysis and degree of sulfation. Elemental analysis was performed in duplicate using a FlashSmart V CHNS instrument (ThermoFischer) to determine the mean carbon (%C) and sulfur (%S) contents of the samples. The degree of sulfation (DS) was calculated using mean %C and %S values following the equation (1):

$$DS = \frac{\%S}{\%C} \times \frac{awC}{awS} \times nC$$
(1)

where awC and awS are the atomic weights of carbon (C) and sulfur (S), respectively, and nCis the number of carbon atoms per nonasaccharide (54 C) or octasaccharide (48 C) repeating units.

ATR-FTIR Spectroscopy. Infrared spectra of native EPS and its derivatives were recorded
 with a FTIR VERTEX 70 spectrometer (Bruker) in ATR mode in the range 4000-500 cm⁻¹.


NMR Analysis. NMR spectra were recorded on a Bruker (Billerica, MA, USA) Avance-III 165 HD (¹H: 400 MHz, ¹³C: 100 MHz) or on a Bruker Avance-III (¹H: 600 MHz, ¹³C: 150 MHz) 166 instrument – the latter equipped with a cryo-probe – in D_2O (acetone as internal standard, ¹H: 167 $(CH_3)_2CO$ at δ 2.22 ppm; ¹³C: $(CH_3)_2CO$ at δ 31.5 ppm). Data were processed using the data 168 analysis packages integrated with Bruker TopSpin[®] 4.0.5 software. ¹H,¹³C-HSQC and ¹H,¹³C-169 HMBC experiments were measured in the ¹H-detected mode via single quantum coherence with 170 proton decoupling in the ¹³C domain, using data sets of 2048×256 points and typically 80 171 increments (160 for HMBC). 172

173

174 **RESULTS AND DISCUSSION**

Native infernan and its LMW derivatives (EPS DR). Native infernan produced by A. 175 *infernus* is a highly branched anionic heteropolysaccharide with a monosulfated nonasaccharide 176 repeating unit firstly described in 2004 by Roger et al. (Figure 1).¹⁸ Infernan main chain is 177 composed of only three residues, glucose (Glc), galacturonic acid (GalA) and galactose (Gal), 178 which are covalently linked in the sequence: \rightarrow 4)- β -D-Glcp-(1 \rightarrow 4)- α -D-GalpA-(1 \rightarrow 4)- α -D-179 Galp-(1 \rightarrow . GalA residue of the main chain is substituted at O-2 by one sulfate group and at O-180 3 by a short side chain composed of two glucuronic acids (GlcA), Gal and Glc units linked 181 through the sequence: β -D-Glc*p*-(1 \rightarrow 6)- α -D-Gal*p*-(1 \rightarrow 4)- β -D-Glc*p*A-(1 \rightarrow 4)- β -D-Glc*p*A-(1 \rightarrow . 182 In addition, each GlcA residue is substituted by a terminal Glc. Recently, a novel disulfated 183 octasaccharide repeating unit was described after mass spectrometry analysis performed on 184

LMW infernan derivatives obtained after enzymatic depolymerization.²⁸ In this new repeating unit, the terminal Glc of the side chain initially linked to Gal residue at C-6 was replaced by a



sulfate group (Figure 1). It appeared therefore that during EPS biosynthesis two types ofrepeating unit could be assembled.

189

Figure 1. The two types of infernan repeating unit: a monosulfated nonasaccharide repeating unit $(R = \beta - Glc)^{18}$ and a disulfated octasaccharide repeating unit $(R = SO_3 - Na^+)^{28}$

192

In order to prepare GAG-mimetics, native infernan of high-molecular weight (2,000,000 g/mol) 193 was firstly depolymerized using a free-radical process to prepare LMW derivatives (EPS DR). 194 Two derivatives of two different molecular weights were obtained, EPS DR7,8k of 7,800 g/mol 195 and EPS DR_{19k} of 19,000 g/mol. As shown in Table 1, both derivatives presented similar 196 monosaccharide composition as starting EPS, suggesting that the depolymerization process had 197 no major impact on the polysaccharide structure. Elemental analysis performed on the native 198 EPS and its LMW derivatives revealed the DS close to 2 assuming both a nonasaccharide and 199 an octasaccharide repeating units (Table 1). 200

carbon (%C) and sulfur (%S) contents and degree of sulfation (DS) of the native HMW EPS

204	and its LMW	derivatives, E	EPS DR _{19k} a	ind EPS DR _{7,8k} .
-----	-------------	----------------	-------------------------	------------------------------

	Monosaccharide composition (w/w%)				%C	%S	DS*	DS**	Mw (g/mol)	<i>Ip</i> Mw/Mn
	Gal	Glc	GalA	GlcA	-					
Infernan EPS	10.4	18.5	7.6	12.7	29.6	2.9	2.0	1.8	$2,000,000 \pm 100,000$	1.1
EPS DR _{19k}	9.7	18.9	10.4	14.7	30.3	3.0	2.0	1.8	$19,\!000\pm0,\!400$	1.9
EPS DR _{7,8k}	9.8	18.7	10.3	14.8	30.4	2.7	1.8	1.6	$7,800 \pm 1,200$	1.5

Gal, galactose; Glc, glucose; GalA, galacturonic acid; GlcA, glucuronic acid; %C, mean carbon content and

206 %S, mean sulfur content measured by elemental analysis; DS*, degree of sulfation assuming a

207 nonasaccharide repeating unit; DS^{**} , degree of sulfation assuming an octasaccharide repeating unit. Mw,

208 weight average molecular weight; *Ip* (Mw/Mn), polydispersity index.

These two derivatives were then analyzed by NMR to reveal their fine structures, and in 209 particular to establish the presence of the monosulfated nonasaccharide and/or the disulfated 210 octasaccharide repeating units. ¹H-NMR and a set of 2D-NMR ¹H, ¹H-homonuclear (COSY, 211 TOCSY, NOESY) and ¹H,¹³C-heteronuclear spectra (DEPT-HSQC, HSQC-TOCSY, HMBC) 212 were measured for the EPS DR samples in D₂O. Their comparison revealed no significant 213 differences between the two samples (Figure 2 and Figure S1). Chemical shift data were in 214 agreement with those previously reported in 2004 by Roger et al.,¹⁸ apart for the Gal F unit 215 (Figure 1). Indeed, in the ¹H, ¹³C-DEPT-HSQC spectra the presence of CH₂ signals in two 216 different regions could be detected. The most crowded one at $\delta_{H/C}$ 3.50-4.00/60-65 ppm hosts 217 the methylene signals of Glc and Gal residues carrying a free hydroxyl at C-6, in agreement 218 with Roger *et al.* (2004).¹⁸ The signal at $\delta_{H/C}$ 4.13/67.5 ppm could be assigned to the CH₂O-219 moiety of 6-O-sulfated Gal F unit, in agreement with NMR data previously reported for the 220 synthetic α -D-Gal6Sp-(1 \rightarrow 4)- β -D-GlcpA disaccharide (F-E fragment).²⁹ This assignment was 221 in disagreement with Roger et al. (2004), that attributed such signal to a O-glycosylated (with 222

a β -Glc residue) rather than 6-O-sulfated Gal F unit, in spite of the absence of any n.O.e. 223 between β -Glc and Gal F residues¹⁸ as well as of any correlation between the signal at $\delta_{H/C}$ 224 4.13/67.5 ppm and anomeric signals in the ¹H,¹³C-HMBC spectrum (Figure S2). NMR data 225 together with the DS values determined for both derivatives, indicating the presence of 2 sulfate 226 groups per repeating unit (Table 1), suggested that a revision of the structure of the repeating 227 unit of infernan should be done. Indeed, a disulfated octasaccharide, in agreement with our 228 recent mass spectrometry data on LMW infernan derivatives,²⁸ rather than a monosulfated 229 nonasaccharide¹⁸ should only be considered. 230




Figure 2. ¹H- and ¹H, ¹³C-DEPT-HSQC NMR spectra (400 MHz, D₂O, 298K, zoom) of EPS DR_{19k} (top) and EPS DR_{7,8k} (bottom).

233

Conventional *versus* microwave-assisted sulfation of EPS DR. In the next step, the LMW derivative of the lowest molecular weight, namely EPS DR_{7,8k}, was selected to explore the potential of microwave-assisted sulfation to obtain a highly sulfated compound similar to GAGs, such as LMW heparin. Firstly, the effect of microwave radiation on the polysaccharide structural integrity was assessed by exposing the derivative to the radiation without the SO₃·py addition. Weight average molecular weight was similar before and after microwave exposure suggesting that radiation had no destructive effect on the polysaccharide structure (Table 2).

Sulfation was then performed in the presence of SO₃·py complex using microwave radiation, 241 in parallel to the conventional heating method.²⁰ By tuning EPS/SO₃·py ratio, the sulfur content, 242 corresponding to the amount of added sulfate groups, could be modulated (Table 2). Highly 243 sulfated derivatives were obtained with the highest EPS/SO₃·py ratio (1/5) using both 244 conventional heating (EPS DRS_{HS}) and microwave radiation (EPS DRS-MW_{HS}). The amount 245 of sulfur was above 10%, which corresponds to a ~32% of sulfate groups, similarly to the 246 amount typically found in sulfated GAGs. A two-fold decrease in the sulfur content was 247 measured for the derivatives sulfated using the EPS/SO₃·py ratio of 1/2.5. The lowest 248 EPS/SO₃·py ratio (1/1.25) applied was not sufficient to sulfate the derivative, as the sulfur 249 content was comparable to the derivative before sulfation. In addition, a molecular weight 250 increase was observed with the increase of added sulfate groups, suggesting that the backbone 251 252 of the EPS derivatives was not degraded during the reaction (Table 2), in contrast to other widely used sulfation reagents such as chlorosulfonic acid or sulfuric acid.¹² The polydispersity 253 index (Mw/Mn ratio) only slightly increased with the sulfur content. 254

EPS derivative	Т (°С)	t (min)	EPS/SO ₃ ·py	%S	Mw (g/mol)	<i>Ip</i> Mw/Mn
EPS DR-MW	45	120	-	2.5	$6{,}900\pm0{,}600$	1.3
EPS DRS _{HS}	45	120	1/5	12.2	$17,200 \pm 3,400$	1.6
EPS DRS _{MS}	45	120	1/2.5	6.1	$8,\!000\pm0,\!200$	1.7
EPS DRS _{LS}	45	120	1/1.25	2.6	$6{,}800\pm0{,}200$	1.5
EPS DRS-MW _{HS}	45	10	1/5	13.7	$12,600 \pm 0,800$	1.5
EPS DRS-MW _{MS}	45	10	1/2.5	7.1	$11,\!700\pm0,\!500$	1.4
EPS DRS-MW $_{LS}$	45	10	1/1.25	3.1	$\textbf{7,700} \pm \textbf{1,200}$	1.3


Table 2. Characterization of LMW EPS derivatives sulfated by either conventional heating
(EPS DRS) or microwave radiation (EPS DRS-MW) at three different EPS/SO₃·py w/w ratios.

HS, high sulfate; MS, medium sulfate; LS, low sulfate; %S, mean sulfur content measured by elemental
analysis; Mw, weight average molecular weight; *Ip* (Mw/Mn), polydispersity index.

260

Sulfated EPS derivatives obtained by conventional and microwave-assisted sulfation methods 261 were analyzed by ATR-FTIR and compared to EPS DR_{7.8k} before sulfation (Figure 3 and S3). 262 The raw spectra (Figure S3) were normalized with respect to the C=O stretching band at 1650 263 cm⁻¹ to better visualize the differences in the sulfur content between the samples (Figure 3). 264 Indeed, carboxylic acid groups are not involved in sulfation reaction and their band intensity 265 could be considered constant. On normalized ATR-FTIR spectra (Figure 3), the broad band 266 corresponding to O-H at 3600-3000 cm⁻¹ was considerably narrowed for both EPS DRS_{HS} and 267 EPS DRS-MW_{HS} samples having the highest sulfur content, due to the esterification of the 268 hydroxyl groups, when compared to EPS DR_{7.8k} or EPS DRS_{LS.MS} with low and medium sulfur 269 contents. The strong O=S=O asymmetric stretching band at 1262 cm⁻¹ clearly increased with 270 increasing sulfur content. For both highly sulfated derivatives, EPS DRS_{HS} and EPS DRS-271 MW_{HS}, prepared by the two sulfation methods, the intensity of O=S=O band was comparable. 272 Similar results were observed for C-O-S symmetric vibration band at 816 cm⁻¹. An important 273

absorption band was observed for all derivatives at 1100-1010 cm⁻¹ attributed to the C-O
stretching vibration of pyranosyl rings.



276

Figure 3. ATR-FTIR normalized spectra with respect to the C=O band at 1650 cm⁻¹ of slightly sulfated EPS $DR_{7,8k}$ before sulfation, highly sulfated EPS DRS_{HS} obtained by conventional sulfation method and EPS $DRS-MW_{LS, MS, HS}$ prepared using microwave radiation. HS = high sulfate, MS = medium sulfate, LS = low sulfate, MW = Microwave.

281

By taking into account the physico-chemical characterizations, it appeared clearly that similarly 282 sulfated derivatives were obtained using both conventional and microwave-assisted sulfation 283 methods. However, the main advantage of the microwave-assisted sulfation is the reaction time 284 that can be considerably decreased (10 min instead of 120 min). To confirm that both methods 285 lead to similar derivatives, the structures of the EPS derivatives with the highest sulfate 286 contents, EPS-DRS_{HS} and EPS DRS-MW_{HS}, were further analyzed by NMR to get some 287 insights into their sulfation pattern. A comparison of their ¹H,¹³C-DEPT-HSQC with respect to 288 EPS DR_{7.8k} clearly confirmed an extensive sulfation for both samples, as indicated by a marked 289

¹H downfield shift for several CH and CH₂ signals (Figure 4).³⁰ Their quite broad shape 290 suggested that the obtained polysaccharides have a heterogeneous structure. Indeed, the only 291 insight into their sulfation pattern could be inferred from the absence of any signal assignable 292 to unsulfated CH₂ moieties. This indicated that a quantitative degree of sulfation at the primary 293 hydroxyl of Gal and Glc residues of both polysaccharide samples was achieved. This is not 294 unexpected, due to the generally higher reactivity of primary vs. secondary alcohols. 295 Furthermore, a comparison between the ¹H, ¹³C-DEPT-HSQC NMR spectra of EPS-DRS_{HS} and 296 EPS DRS-MW_{HS} samples revealed no significant differences (Figures S4-S6). This confirmed 297 that conventional and microwave-assisted sulfation reactions proceeded similarly on EPS 298 DR_{7.8k}. From elemental analysis, the DS of 14 and 18 per octasaccharide repeating unit were 299 determined, respectively, for EPS-DRS_{HS} (12.2 %S, 15.3 %C) and EPS DRS-MW_{HS} (13.7 %S, 300 13.6 %C). By considering that (i) the highest DS theoretically possible is 21, (ii) two sulfated 301 positions are already present in native infernan and (iii) all the four primary hydroxyl groups (2 302 on the backbone and 2 on the side chain) result sulfated as evidenced by NMR (Figure 5), 8 and 303 12 sulfate groups remain, respectively, in EPS-DRS_{HS} and EPS DRS-MW_{HS}. Although, the 304 accessibility of secondary hydroxyl groups on the side chains (11 groups available) during 305 sulfation seems higher in contrast to the backbone (4 groups available), the ¹H, ¹³C-DEPT-306 307 HSQC spectra suggesting a heterogeneous structure for both derivatives do not indicate a high regioselectivity for sulfate group insertion on side chain vs. backbone secondary positions. 308

309

310





Figure 4. Superimposition of ¹H,¹³C-DEPT-HSQC NMR spectra (400 MHz, D₂O, 298 K, zoom) of EPS DR_{7,8k} (blue/green) and EPS DRS-MW_{HS} (black/red; top) or EPS DRS_{HS} (black/red; bottom).



318

Figure 5. The postulated structure for the octasaccharide repeating unit of infernan highly sulfated derivatives EPS DRS_{HS} and EPS DRS-MW_{HS}.

321

322 CONCLUSIONS

The present study explored a microwave-assisted sulfation method applied to LMW derivative 323 prepared from infernan EPS to obtain sulfated GAG-mimetics. The new method was compared 324 to the conventional one that we classically use to prepare highly sulfated polysaccharides 325 326 displaying biological properties similar to GAGs. For both methods, the same sulfation conditions, including EPS/SO₃·py ratios and temperature were applied, except for the reaction 327 time, which was twelve-fold shorter for the microwave-assisted sulfation (10 min) in 328 comparison to the classical one (120 min). Derivatives obtained in both cases displayed very 329 330 similar physico-chemical characteristics in terms of sulfur content and molecular weight distribution. Moreover, by tuning EPS/SO₃·py ratio, the sulfur content was increased to reach 331 the amount known for sulfated GAGs (EPS/SO₃·py 1/5 w/w ratio). In order to get further insight 332 into their fine structure, and in particular the sulfation pattern, LMW derivatives displaying the 333 highest sulfur content prepared by both methods were analyzed by NMR. An extensive sulfation 334 was evidenced for both samples, with a slightly higher degree for the one obtained through the 335

microwave-assisted reaction. Both derivatives showed a highly heterogeneous structure showing all four primary hydroxyls substituted by sulfate groups. Remaining sulfates are likely randomly distributed on secondary hydroxyl groups between infernan side chains and its backbone. NMR analysis confirmed that the microwave-assisted sulfation with considerably shorter reaction time, leads to a highly-sulfated derivative sharing similar structural features with the one obtained by the classical sulfation method.

343 AUTHOR INFORMATION

344 **Corresponding Author**

* E-mail address: Sylvia.Colliec.Jouault@ifremer.fr. Tel: + 33 2 40 37 40 93.

346

347 Author Contributions

The manuscript was written through contributions of all authors. All authors have given approval to the final version of the manuscript.

350

351 Acknowledgment

- The authors would like to acknowledge the French GagoSciences Network (GdR GAG 3739).
- Financial supports were also provided by University of Naples Federico II (FRA-2020-B grant,
- project GLYCOPLAGENT, to E.B.) and Région Centre Val de Loire (APR-IR FLOWSYN and
- INFLUX). Authors thank the projects CHemBio (FEDER-FSE 2014-2020-EX003677),
- 356 Techsab (FEDER-FSE 2014-2020-EX011313), QUALICHIM (APR-IA-PF 2021-00149467),
- the RTR Motivhealth (2019-00131403), and the Labex programs SYNORG (ANR-11-LABX-
- 358 0029) and IRON (ANR-11-LABX-0018-01) for their financial support of ICOA, UMR 7311,
- 359 University of Orléans, CNRS.

360

- 361 Notes
- The authors declare no competing financial interest.

363 **REFERENCES**

- (1) Karamanos, N. K.; Piperigkou, Z.; Theocharis, A. D.; Watanabe, H.; Franchi, M.; Baud, S.; Brezillon, S.; Gotte,
 M.; Passi, A.; Vigetti, D.; Ricard-Blum, S.; Sanderson, R. D.; Neill, T.; Iozzo, R. V. Proteoglycan Chemical Diversity
- 366 Drives Multifunctional Cell Regulation and Therapeutics. *Chemical Reviews* **2018**, *118*, 9152-9232.
- 367 (2) Gandhi, N. S.; Mancera, R. L. The Structure of Glycosaminoglycans and their Interactions with Proteins.
 368 *Chemical Biology & Drug Design* 2008, *72*, 455-482.
- 369 (3) Schnabelrauch, M.; Scharnweber, D.; Schiller, J. Sulfated Glycosaminoglycans As Promising Artificial
- Extracellular Matrix Components to Improve the Regeneration of Tissues. *Curr. Med. Chem.* 2013, *20*, 25012523.

- 372 (4) DeAngelis, P. L. Glycosaminoglycan polysaccharide biosynthesis and production: today and tomorrow.
- 373 Applied Microbiology and Biotechnology **2012**, *94*, 295-305.
- (5) Mende, M.; Bednarek, C.; Wawryszyn, M.; Sauter, P.; Biskup, M. B.; Schepers, U.; Brase, S. Chemical
 Synthesis of Glycosaminoglycans. *Chemical Reviews* 2016, *116*, 8193-8255.
- (6) Zhang, X.; Lin, L.; Huang, H.; Linhardt, R. J. Chemoenzymatic Synthesis of Glycosaminoglycans. *Acc. Chem. Res.* 2020, *53*, 335-346.
- (7) Gao, C. Z.; Edgar, K. Efficient synthesis of novel glycosaminoglycan analogs. *Abstracts of Papers of the American Chemical Society* 2019, 257.
- 380 (8) Oreste, P.; Zoppetti, G. Semi-synthetic heparinoids. *Handb. Exp. Pharmacol.* **2012**, 403-422.
- (9) Badri, A.; Williams, A.; Linhardt, R. J.; Koffas, M. A. G. The road to animal-free glycosaminoglycan
 production: current efforts and bottlenecks. *Curr. Opin. Biotechnol.* 2018, *53*, 85-92.
- (10) Bedini, E.; Laezza, A.; Parrilli, M.; Iadonisi, A. A review of chemical methods for the selective sulfation and
 desulfation of polysaccharides. *Carbohydr. Polym.* 2017, *174*, 1224-1239.
- 385 (11) Wang, J. L.; Bao, A. J.; Meng, X. H.; Guo, H. Y.; Zhang, Y. D.; Zhao, Y. L.; Kong, W. B.; Liang, J. Y.; Yao, J.;
- Zhang, J. An efficient approach to prepare sulfated polysaccharide and evaluation of anti-tumor activities in
 vitro. *Carbohydr. Polym.* 2018, 184, 366-375.
- 388 (12) Feng, Y. L.; Li, W. Q.; Wu, X. Q.; He, L. A.; Ma, S. Y. Rapid and efficient microwave-assisted sulfate
- modification of lentinan and its antioxidant and antiproliferative activities in vitro. *Carbohydr. Polym.* 2010, *82*,
 605-612.
- (13) Deming, J. Deep ocean environmental biotechnology. *Curr. Opin. Biotechnol.* **1998**, *9*, 283-287.
- (14) Finore, I.; Di Donato, P.; Mastascusa, V.; Nicolaus, B.; Poli, A. Fermentation Technologies for the
 Optimization of Marine Microbial Exopolysaccharide Production. *Mar. Drugs* 2014, *12*, 3005-3024.
- (15) Delbarre-Ladrat, C.; Sinquin, C.; Lebellenger, L.; Zykwinska, A.; Colliec-Jouault, S. Exopolysaccharides
- produced by marine bacteria and their applications as glycosaminoglycan-like molecules. *Frontiers in Chemistry* **2014**, 2.
- (16) Zykwinska, A.; Marchand, L.; Bonnetot, S.; Sinquin, C.; Colliec-Jouault, S.; Delbarre-Ladrat, C. Deep-sea
 Hydrothermal Vent Bacteria as a Source of Glycosaminoglycan-Mimetic Exopolysaccharides. *Molecules* 2019,
 24.
- 400 (17) Raguenes, G. H.; Peres, A.; Ruimy, R.; Pignet, P.; Christen, R.; Loaec, M.; Rougeaux, H.; Barbier, G.;
- 401 Guezennec, J. G. *Alteromonas infernus* sp. nov., a new polysaccharide-producing bacterium isolated from a 402 deep-sea hydrothermal vent. *J. Appl. Microbiol.* **1997**, *82*, 422-430.
- 403 (18) Roger, O.; Kervarec, N.; Ratiskol, J.; Colliec-Jouault, S.; Chevolot, L. Structural studies of the main
- 404 exopolysaccharide produced by the deep-sea bacterium Alteromonas infernus. *Carbohydr. Res.* 2004, 339,
 405 2371-2380.
- 406 (19) Rederstorff, E.; Rethore, G.; Weiss, P.; Sourice, S.; Beck-Cormier, S.; Mathieu, E.; Maillasson, M.; Jacques,
- 407 Y.; Colliec-Jouault, S.; Fellah, B. H.; Guicheux, J.; Vinatier, C. Enriching a cellulose hydrogel with a biologically 408 active marine exopolysaccharide for cell-based cartilage engineering. *Journal of Tissue Engineering and*
- 408 active marine exopolysaccharide for cell-based cartilage engineering. *Journal of Tissue Engineering* 409 *Regenerative Medicine* 2017, *11*, 1152-1164.
- 410 (20) Chopin, N.; Sinquin, C.; Ratiskol, J.; Zykwinska, A.; Weiss, P.; Cerantola, S.; Le Bideau, J.; Colliec-Jouault, S. A
- Direct Sulfation Process of a Marine Polysaccharide in Ionic Liquid. *BioMed Research International* 2015, 2015,
 508656. doi:.
- 413 (21) Merceron, C.; Portron, S.; Vignes-Colombeix, C.; Rederstorff, E.; Masson, M.; Lesoeur, J.; Sourice, S.;
- 414 Sinquin, C.; Colliec-Jouault, S.; Weiss, P.; Vinatier, C.; Guicheux, J. Pharmacological modulation of human
- 415 mesenchymal stem cell chondrogenesis by a chemically oversulfated polysaccharide of marine origin: potential
- 416 application to cartilage regenerative medicine. *Stem cells (Dayton, Ohio)* **2012**, *30*, 471-480.
- 417 (22) Zykwinska, A.; Marquis, M.; Godin, M.; Marchand, L.; Sinquin, C.; Garnier, C.; Jonchere, C.; Chedeville, C.;
- 418 Le Visage, C.; Guicheux, J.; Colliec-Jouault, S.; Cuenot, S. Microcarriers Based on Glycosaminoglycan-Like Marine
- 419 Exopolysaccharide for TGF-beta 1 Long-Term Protection. *Mar. Drugs* **2019**, *17*.

- 420 (23) Gelebart, P.; Cuenot, S.; Sinquin, C.; Halgand, B.; Sourice, S.; Le Visage, C.; Guicheux, J.; Colliec-Jouault, S.;
- 421 Zykwinska, A. Microgels based on Infernan, a glycosaminoglycan-mimetic bacterial exopolysaccharide, as BMP-
- 422 2 delivery systems. Carbohydr. Polym. 2022, 284.
- 423 (24) Heymann, D.; Ruiz-Velasco, C.; Chesneau, J.; Ratiskol, J.; Sinquin, C.; Colliec-Jouault, S. Anti-Metastatic
- 424 Properties of a Marine Bacterial Exopolysaccharide-Based Derivative Designed to Mimic Glycosaminoglycans.
 425 *Molecules* 2016, *21*, 309.
- 426 (25) Zykwinska, A.; Berre, L. T.-L.; Sinquin, C.; Ropartz, D.; Rogniaux, H.; Colliec-Jouault, S.; Delbarre-Ladrat, C.
- 427 Enzymatic depolymerization of the GY785 exopolysaccharide produced by the deep-sea hydrothermal
- bacterium Alteromonas infernus: Structural study and enzyme activity assessment. *Carbohydr. Polym.* 2018,
 188, 101-107.
- 430 (26) Kamerling, J. P.; Gerwig, G. J.; Vliegenthart, J. F.; Clamp, J. R. Characterization by gas-liquid
- 431 chromatography-mass spectrometry and proton-magnetic-resonance spectroscopy of pertrimethylsilyl methyl
- 432 glycosides obtained in the methanolysis of glycoproteins and glycopeptides. *Biochemical Journal* 1975, 151,
 433 491-495.
- 434 (27) Montreuil, J.; Bouquelet, S.; Debray, H.; Fournet, B.; Spik, G.; Strecker, G.: *Carbohydrate Analysis: a* 435 *practical approach*; Oxford University Press: New York, 1986.
- 436 (28) Akoumany, K.; Zykwinska, A.; Sinquin, C.; Marchand, L.; Fanuel, M.; Ropartz, D.; Rogniaux, H.; Pipelier, M.;
- 437 Delbarre-Ladrat, C.; Colliec-Jouault, S. Characterization of New Oligosaccharides Obtained by An Enzymatic
- Cleavage of the Exopolysaccharide Produced by the Deep-Sea Bacterium Alteromonas infernus Using its Cell
 Extract. *Molecules* 2019, 24.
- 440 (29) Zsiska, M.; Meyer, B. SYNTHESES OF DISACCHARIDES WITH (1-4)-BETA GLYCOSIDIC LINKAGES RELATED TO
- THE 4-SULFATES AND 6-SULFATES AND THE 4,6-DISULFATES OF CHONDROITIN. *Carbohydr. Res.* 1991, 215, 261277.
- (30) Vessella, G.; Traboni, S.; Pirozzi, A. V. A.; Laezza, A.; Iadonisi, A.; Schiraldi, C.; Bedini, E. A Study for the
- Access to a Semi-synthetic Regioisomer of Natural Fucosylated Chondroitin Sulfate with Fucosyl Branches on N acetyl-Galactosamine Units. *Mar. Drugs* 2019, *17*.
- 446