

Coteau's jewelled porcelain, a summit of ceramic art: An on-site Raman and pXRF study

Philippe Colomban, Burcu Kirmizi, Jean-Baptiste Clais, Michele Gironda

► To cite this version:

Philippe Colomban, Burcu Kirmizi, Jean-Baptiste Clais, Michele Gironda. Coteau's jewelled porcelain, a summit of ceramic art: An on-site Raman and pXRF study. 5th International Conference on Innovation in Art Research and Technology (inArt 2022), Jun 2022, Paris, France. hal-03964545

HAL Id: hal-03964545 https://hal.science/hal-03964545v1

Submitted on 31 Jan 2023 $\,$

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Coteau's jewelled porcelain, a summit of ceramic art: An on-site Raman and pXRF study





^a Sorbonne Université, CNRS, MONARIS UMR8233, 4 Place Jussieu, 75005 Paris, France ^b Yıldız Technical University, Dept. of Conservation and Restoration of Cultural Property, Beşiktaş 34349 Istanbul, Turkey ^c Musée du Louvre, Département des objets d'art, quai F. Mitterand, 75001 Paris, France ^d XGLab S.R.L – Bruker, 23 Via Conte Rosso, 20134 Milan, Italy





Background and Scope of the Study

The gilt-decorated porcelains of Joseph Coteau (1740–1801) and Philippe Parpette (1738–1806) unifying metal and ceramic enamel techniques have been produced from ~ 1770 to 1800 but this type of production is rare and poorly documented. Enamelled decorations of these objects display gold foils ("paillons") coated with lead-based transparent and opaque enamels fired on the porcelain glaze. Rare items were produced at different factories (Sèvres Royal Factory, Comte d'Artois Factory) and it is reported that some copies were made during the 19th century [1-2].

We present here the first non-invasive Raman study of four cups and two pairs of vases (also analysed by pXRF) belonging to the productions of these factories, made by Coteau or Parpette. The decors made of enamel on gold foil ('paillon') were applied both on soft-paste and hard-paste porcelain body. The characterization of the enamels and glazes of gilt-enamelled porcelains is significant in terms of addressing the question of the link between metal and porcelain enamelling techniques during the 18th century and may potentially offer criteria of identification for distinguishing artefacts produced at different time periods [3].

Analytical Techniques

- Mobile Raman set-up (HORIBA Jobin-Yvon Longjumeau France)
- 532 nm Ventus 300 mW laser (Laser Quantum, Fremont, CA, USA) and ×50 long wd objective (NIKON France SAS, Champigny-sur-Marne, France), x200 long wd objective (Mitutoyo)
 - Advantages:
- high spatial resolution (in μ scale)
- contactless usage
- the structural information obtained for crystalline matter/ glassy phases.

[1] R. De Plinval de Guillebon, Un phénomène périodique: la mode du décor d'or appliqué et d'émail sur la porcelaine française (XVIIe-XIXe siècles), Rev. Soc. Amis Sèvres 1, 7-22, 1992

[2]. T. Preaud, Sèvres enameled porcelain: Eight dies (and a quarrel) rediscovered, *The Burlington magazine* 128[999], 390-39, 1986


[3] P. Colomban, B. Kırmızı, J-B. Clais, M. Gironda, An on-site Raman and pXRF study of Joseph Coteau and Philippe Parpette's jewelled porcelain: a summit of ceramic art, Journal of Cultural Heritage, 46, 82-94, 2020

- Portable Elio XRF instrument (XGLab Bruker, Italy)
- 40 kV tube voltage, 100 µA current, 40 s acquisition time
 - Advantages:
- non-invasive elemental analysis
- fast data collection




Sévres Factory vase (OA10946) with CC mark (1780) H:40 / D:16 cm

Comte d'Artois Factory vase (OA7739) with "coteau" in red and "Cuit au charbon de terre" in black marks H:34.5 cm / L: 22 cm











Wavenumber / cm⁻

Representative Raman spectra recorded on the Sévres vase (OA10946) (p: bead on gold foil; d: area under (lost) gold foil; m: medallion)



Representative XRF spectra recorded on the glaze and enamels of the Sèvres vase



Results-Discussion

- Glassy Si-O Matrix
- All the cups and the vase-OA10946 (Sèvres Royal F. mark): variations of lead-alkali type of glaze with ~ 970-1000 / ~ 1040-1080 cm⁻¹ doublet

a) A-type: the strongest component at ~1065 to 1080 cm⁻¹ b) B-type: the strongest component at ~ 1040 to 1050 cm⁻¹


• The vase-OA7739 (Comte d'Artois F.): broad band peaking at 450–500 cm⁻¹ \rightarrow hard-paste aluminosilicate glaze

Enamels

- OA10946: Cassiterite (635-770 cm⁻¹) @ white enamel beads Lead arsenate (810 cm⁻¹) @ white surface of the medallion
- Lead arsenate (815 cm⁻¹) @ white and red enamel beads OA7739: Cassiterite (632-772 cm⁻¹) @ turquoise enamel beads on the top Au° nanoparticles (fluorescence + 815 cm⁻¹) @ red enamel prepared by

Wavenumber / cm⁻¹

Representative Raman spectra recorded on the Comte d'Artois vase (OA7739) (p: bead on gold foil décor)




Representative XRF spectra recorded on the glaze and enamels of the Comte d'Artois vase

Perrot' technique

Bernard Perrot was a renowned glassmaker in the 17th century France. His particular method of producing red (ruby) glass includes the precipitation of gold nanoparticles from the acid solution with the use of As-salt which remains with colloidal Au^o particles dispersed in the glassy matrix. The use of As-salt is confirmed by the presence of the specific As-O mode at ~ 810 cm⁻¹ in the Raman spectrum of red glass/enamel [4]. This method differs from the more common technique of using tin salt for the precipitation of colloidal gold, as practiced by the German chemist J. Kunckel (the so-called Cassius purple).

Representative Raman spectra recorded on the glazes and white enamels of the R350 cup



✤ R350 cup was made using a technique different from the other cups, with its glaze and enamels having similar glass compositions. A regular 18th century production at Sèvres Factory is doubtful since the factory mark at the back side is not usual. Cassiterite was used as opacifier in the white and red enamels of this cup, indicating a possible Coteau production but with a mark applied after or a 19th century copy.

✤ OA7739 vase shows the use of two opacifiers, cassiterite for turquoise enamel beads and lead arsenate for white enamels close to the foot and top of the vase. The latter decor should have been added after to adapt the decor with the addition of bronze handle pair.

[4] P. Colomban, B. Kırmızı, Non-invasive on-site Raman study of polychrome and white enamelled glass artefacts in imitation of porcelain assigned to Bernard Perrot and his followers, Journal of Raman *Spectroscopy*, 51(1), 133-146, 2020



Jewelled cup (R350) with CC mark (1780) H: 40 / D:16 cm

Conclusion

The on-site Raman and pXRF study of J. Coteau and/or P. Parpette possible productions was able to characterize the different materials and enamelling techniques used, despite the limited number of studied artefacts. Assignments to possible Coteau/Parpette productions were discussed based on historical information, factory marks and the results of spectroscopical analysis, regarding the glass compositions used and the opacifiers.

* C. Gougeon from Musée du Louvre, is kindly acknowledged for her help in the managing of measurements.