

### **Eulerian description for anisotropic hyper-élastic materials**

Emmanuelle Rouhaud, Benoît Panicaud

#### **To cite this version:**

Emmanuelle Rouhaud, Benoît Panicaud. Eulerian description for anisotropic hyper-élastic materials. Colloque Mécamat Aussois 2023, Jan 2023, Aussois (FR), France. hal-03979833

### **HAL Id: hal-03979833 <https://hal.science/hal-03979833v1>**

Submitted on 9 Feb 2023

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# **Description eulérienne pour lesmatériaux anisotropes hyper-élastiques**



Author Emmanuelle Rouhaud, Benoît Panicaud Université de technologie de Troyes

# Introduction

Several approaches are possible to construct a model for elastic materials undergoing finite transformations:

- Rate type, hypo-elastic models with the use of objective transports: does not guarantee a reversible behavior.
- Thermodynamics of irreversible processes with an intrinsic dissipation rate equal to zero. For adiabatic or isothermal reversible transformations the first principle of thermodynamics leads to:

where  $\psi$  is the specific internal energy (an energy per unit mass),  $\sigma$  is the Cauchy stress tensor,  $d$  is the rate of deformation and  $\rho$  is the mass density. The dot over the quantity indicates a total derivative with respect to time.

$$
\boldsymbol{\sigma}:\boldsymbol{d}-\rho\dot{\psi}=0\qquad \qquad (1)
$$

where **D** is the left Cauchy-Green deformation tensor and is the right equation known as Doyle-Ericksen formula; *g* is the ambiant metric.

Why is it necessary to derive the model in the reference configuration? One could wonder how to treat the derivation with respect to time in the reference configuration: is it possible to take into account the variation of the density  $\rho_0$  in space? Is it possible to write such an equation with an energy that is not per unit of undeformed volume? Equation  $D = \dot{E}$  is written for the reference configuration, does it have a counterpart in an Eulerian description? This raises the question of the geometric nature of  $\dot{E}$  and thus  $D$ . Is it then possible to derive the equivalent of Equation 5 without resorting to the reference configuration?



Questions

# The Lie derivative

The Lie derivative in the velocity field  $\mathscr{L}_v(.)$  of a scalar *a*, a scalar density  $\alpha$ , a second order contravariant tensor **A** or covariant tensor **B** is:

$$
\mathscr{L}_v a = \dot{a} \qquad \mathscr{L}_v \alpha = \dot{\alpha} + \alpha \nabla . v \qquad \mathscr{L}_v \mathbf{A} = \dot{\mathbf{A}} - (\nabla v) \mathbf{A} - \mathbf{A} (\nabla v)^T \qquad \mathscr{L}_v \mathbf{B} = \dot{\mathbf{B}} + (\nabla v) \mathbf{B} + \mathbf{B} (\nabla v)^T
$$

(7)

Interesting relations:

$$
\mathscr{L}_v \rho = 0,
$$
  $\mathscr{L}_v \mathbf{g} = 2\mathbf{d},$   $\mathscr{L}_v \mathbf{e} = \mathbf{d}$   $\mathscr{L}_v \mathbf{b} = 0$  with  $\mathbf{b} = (F^T)^{-1}F^{-1}$ 

where *F* is the deformation gradient and  $e = \frac{1}{2}$ 2  $(g - b)$  is the Euler-Almansi strain tensor. The first equation is the mass conservation. (8)

# Eulerian anisotropic hyper elasticity

Rewrite Equation 1 ( $\boldsymbol{\sigma}$  :  $\boldsymbol{d} - \rho \dot{\psi} = 0$ ) as:

$$
\frac{1}{2}\boldsymbol{\sigma} : \boldsymbol{d} - \rho \mathscr{L}_v \psi = 0 \qquad \to \qquad \frac{1}{2}\boldsymbol{\sigma} : \boldsymbol{d} - \mathscr{L}_v(\rho \psi) = 0 \qquad \qquad \frac{1}{2}\boldsymbol{\sigma} : \boldsymbol{d} - \mathscr{L}_v W = 0 \qquad \text{with} \qquad W = \rho \psi \tag{9}
$$

Choose the energy density such that  $W(\rho, C, e)$  where  $C$  is a fourth order tensor containing material parameters and verifying  $\mathscr{L}_v C = 0$  (or for the isotropic case,  $W(\rho, C_i, I_i(\boldsymbol{e}))$  where  $I_i(\boldsymbol{e})$  corresponds to a number  $i$  of invariants of the strain tensor  $\boldsymbol{e}$  and  $C_i$  are material parameters), then:

$$
\frac{\partial W}{\partial \rho} \stackrel{=0}{\mathscr{L}_v} \rho + \frac{\partial W}{\partial C} \stackrel{=0}{\mathscr{L}_v} \mathcal{C} + \left(2 \frac{\partial W}{\partial g} - \sigma\right) : d = 0 \quad \text{then} \quad \sigma = 2 \frac{\partial W}{\partial g}
$$

(10)

Conclusion

It is possible to derive an elastic model in the Eulerian configuration for anisotropic materials in the context of finite deformations.

- The Lie derivative is used.
- The mass conservation is used to treat properly the variation of the mass density.

• The relation  $\mathscr{L}_v e = d$  is geometrically sound and is the Eulerian counterpart of  $D = \dot{E}$ .