

# Synthesis and Characterization of Original Fluorinated Cyclic Carbonates and Xanthates from Fluorinated Epoxides

Ali Alaaeddine, Lolwa Haydar, Vincent Ladmiral, Wassim El Malti, Sylvain Caillol, Bruno Améduri

## ▶ To cite this version:

Ali Alaaeddine, Lolwa Haydar, Vincent Ladmiral, Wassim El Malti, Sylvain Caillol, et al.. Synthesis and Characterization of Original Fluorinated Cyclic Carbonates and Xanthates from Fluorinated Epoxides. Comptes Rendus. Chimie, 2023, 10.5802/crchim.216. hal-03989242v1

# HAL Id: hal-03989242 https://hal.science/hal-03989242v1

Submitted on 14 Feb 2023 (v1), last revised 14 Feb 2023 (v2)

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution 4.0 International License





Type of the Paper (Article)

# Synthesis and Characterization of Original Fluorinated Cyclic Carbonates and Xanthates from Fluorinated Epoxides

4 Ali Alaaeddine <sup>1</sup>, Lolwa Haydar <sup>1</sup>, Vincent Ladmiral <sup>1</sup>, Wassim El Malti <sup>2</sup>, Sylvain Caillol <sup>1</sup> and Bruno Améduri <sup>1,\*</sup>

5

6 7

8

9

10

11

12

13

14

15 16

17

18 19



<sup>2</sup> College of Engineering and Technology, American University of the Middle East, Kuwait

\* Correspondence: Bruno.ameduri@enscm.fr

**Abstract:** The development of efficient methods for the cycloaddition of CX<sub>2</sub> (carbon dioxide (X=O) or carbon disulfide (X=S)) with fluorinated epoxides to produce five-membered cyclic carbonates (CCs) or xanthates (XAs) is a very attractive topic. In this work, the cycloaddition of CX<sub>2</sub> with hexafluoropropene oxide (HFPO), 2-(trifluoromethyl)oxirane (TFEO), and 1,4-bis(2',3'-epoxypropyl) perfluorobutane (BEPFB) catalyzed by lithium bromide (LiBr) is described. The listed reactions were optimized in terms of temperature, solvent, pressure, and reaction time to lead to a series of original fluorinated five-membered CCs and XAs in high yields (81-93%). The resulting compounds were characterized by FTIR, <sup>1</sup>H, <sup>19</sup>F, and <sup>13</sup>C NMR spectroscopy.

**Keywords:** carbon dioxide (CO<sub>2</sub>); carbon disulfide (CS<sub>2</sub>); cycloaddition; cyclic carbonates; renewable carbon source; xanthates.

## 20 21

- 22
- 23

Citation: Lastname, F.; Lastname, F	24
Lastname, F. Title. Molecules 2022,	25
27, x. https://doi.org/10.3390/xxxxx	27
Academic Editor: Firstname	28
Lastname	29
Received: date	30
Accepted: date	31
Published: date	32
<b>Publisher's Note:</b> MDPI sta	33 ys 34

rubisher's rote: wiD11 stay34 an eutral with regard to jurisdictional claims in published maps and institutional affiliations. 36 37



 39

 Copyright:
 © 2022 by the authors.

 40

 Submitted for possible open access

 publication under the terms and

 conditions of the Creative Commons<sup>2</sup>

 Attribution
 (CC BY) licens<sup>43</sup>

 (https://creativecommons.org/licens<sup>44</sup>

 s/by/4.0/).
 45

## 1. Introduction

Regarded as a greenhouse gas, carbon dioxide (CO<sub>2</sub>) is often considered as a useless and detrimental waste. Its increasing concentration in the atmosphere is partly responsible for climate change. Nonetheless, CO<sub>2</sub> can also be regarded as a cheap, abundant, and renewable carbon source. In addition, it is non-toxic (even though it is asphyxiant) and is especially useful as a phosgene substitute [1]. Many interesting organic compounds, including dimethyl carbonate [2], cyclic carbonates (CCs) [3], and urethanes [4] can be synthesized using CO<sub>2</sub> as a building block [5,6].

Although the synthesis of CCs was first reported in the 1930s, the synthesis of five-membered (or more) CCs is gaining increased attention. They are used to synthesize polycarbonates [7–9], as aprotic polar solvents for organic reactions [10], electrolytes [11] or solvents for lithium-ion batteries [12,13], and as intermediates in the manufacture of fine chemicals [14–16]. CCs are highly implemented in polymer science ring-opening polymerizations and reactions with amines, alcohols, thiols, and carboxylic acids [17]. For example, difunctional CCs can advantageously be reacted with diamines to produce polyhydroxyurethanes, promising substitutes to polyurethanes, without using highly toxic and carcinogenic isocyanates [14,18–22].

Several approaches can be used to synthesize five-membered CCs [23–25]. The most efficient method is the insertion of CO<sub>2</sub> into epoxide rings. This reaction requires a catalyst such as an alkali metal salts [26–28], metal oxides [29], Schiff base [30], ion-exchange resins [31], polymers such as modified polystyrene [32], ionic liquids [33], SiO<sub>2</sub> modified by quaternary ammonium or phosphonium salts [34], gold nanoparticles supported on resins [35], or CO<sub>2</sub> adducts of N-heterocyclic carbenes [36]. Endo *et al.* reported that alkali metal salts could be used as catalysts to synthesize CCs involving crown ethers as co-catalysts [27]. Huang and Shi found that alkali metal salts could efficiently catalyze cycloaddition of CO<sub>2</sub> with epoxides in the presence of PPh<sub>3</sub> and phenol [28]. Cellulose

could also improve the coupling reaction of CO2 and epoxides catalyzed by KI [37].

Cyclic xanthates (XAs) constitute another family of interesting five-membered cyclic reactive species. They are highly reactive and can be easily prepared from epoxides and carbon disulfide (CS<sub>2</sub>) at low temperatures (20-25°C) [38,39]. This reaction is usually carried out in organic solvent or water in the presence of a catalyst, such as amines, alkali metal salts, quaternary ammonium salts, potassium alcoholates, and transition metal complexes [40–44]. Petrov *et al.* demonstrated that fluorinated epoxides react with CS<sub>2</sub> selectively, leading to the corresponding cyclic XAs [45].

Although research on the synthesis and use of CCs- and to a lesser degree on cyclic XAs-based compounds is extensive, a few fluorinated derivatives bearing such functional groups have been reported [45]. Fluorinated materials usually exhibit outstanding properties [46–48] such as chemical resistance, thermal stability, hydrophobic and oleophobic properties, low dielectric constants and dissipation factors, excellent weathering, and interesting surface properties fulfilling the requirements for various high added-value applications. Therefore, the synthesis of compounds that carry both a fluorinated segment and cyclic carbonates or xanthates moiety would be highly interesting as reactive fluorinated intermediates.

This present study reports the cycloaddition of CX<sub>2</sub> [carbon dioxide (X=O) or carbon disulfide (X=S)] with three fluorinated epoxides: hexafluoropropylene oxide (HFPO), 2-(trifluoromethyl)oxirane (TFEO), and 1,4-bis(2',3'-epoxypropyl)perfluorobutane (BEPFB) (Figure 1) [13]. In the presence of lithium bromide (LiBr) as a catalyst, the cycloaddition produced six new five-membered CCs (HFPO-CC1, TFEO-CC3, BEPFB-CC5) and XAs (HFPO-CS2, TFEO-CS4, BEPFB-CS6).





#### 2. Results and Discussion

CCs can be prepared through the coupling reaction of CO<sub>2</sub> and strained heterocycles using a suitable catalyst [16,24]. This approach benefits from eliminating phosgene as a reagent and is 100% atom economical, making it a highly desirable transformation.

The insertion of CO<sub>2</sub> and CS<sub>2</sub> into HFPO, TFEO, and BEPFB was examined (Scheme 1), and various experimental conditions (choice of solvent, reaction duration, and temperature) have been investigated to improve the carbonation reaction. The results are summarized in Table 1.

82

83



**Scheme 1.** Synthesis of original five-membered fluorinated cyclic carbonates, CCs (HFPO-CC1, TFEO-CC3, BEPFB-CC5) and cyclic xanthates, XAs (HFPO-CS2, TFEO-CS4, BEPFB-CS6)

Table 1. Reactions of HFPO, TFEO, and BEPFB with CO2 or CS2  $^{\rm a}$ 

D	Epoxide	X in	Solvent	Т	t	Yield <sup>b</sup>
Kun #		CX <sub>2</sub>		(°C)	(h)	(%)
1		0	DMF	25	24	25
2		0	DMF	50	24	45
3		1 O Dic	1,4-	50	24	63
0			Dioxane	00	21	00
4	CFo	0	THF	50	24	56
5	F	0	1,4-	70	24	72
5	0 F	Diox	Dioxane	70	24	12
6 c		0	neat	80	24	0
7		0	Acetone	65	24	85
8		0	Acetone	65	14	81
<b>9</b> d		S	Acetone	65	14	83
10	F <sub>3</sub> C	0	DMF	80	24	93
11 d	0>	S	Acetone	65	14	91
12 e		0	Acetone	65	24	33
13 e	<pre>✓ X X ✓</pre> O F F F F	0	Acetone	65	96	85

4 (	of	14
-----	----	----

14 e	S	Acetone	65	96	87

<sup>a</sup> Experimental conditions: The carbonation reactions were performed in pressure reactors under 4 bar of CO<sub>2</sub> and in the presence of 5 mol % of LiBr, or with 3 eq. of CS<sub>2</sub>, T (°C), t(h). <sup>b</sup> Yields obtained after purification. <sup>c</sup> Reaction conducted without solvent in the presence of KBr/Lecithin as catalyst [49]. <sup>d</sup> This reaction was performed with 16 mol % of LiBr. <sup>e</sup> These reactions were performed with 10 mol % of LiBr.

First, the synthesis of HFPO-CC1 carried out with CO<sub>2</sub> in DMF at 25 °C or 50 °C proceeded with relatively modest yields (Table 1, runs 1 & 2). Subsequently, using 1,4-dioxane or THF as solvent (Table 1, runs 3 & 4) and increasing the temperature to 70 °C did prove beneficial, but the yields reached 72% at best (Table 1, run 5). The KBr/lecithin catalytic system, known to afford good results, was also tried in the carbonation of HFPO (Table 1, run 6). Surprisingly, this reaction did not yield any CC under the implemented conditions without any solvent. On the other hand, the carbonation in acetone at 65 °C gave the best yields (Table 1, runs 7 and 8), reaching 81% in 14 hours and 85 % in 24 hours.

The analog HFPO-based cyclic XA HFPO-CS2 was successfully synthesized in high yields (83%) using the same conditions by refluxing acetone in excess of CS<sub>2</sub> for 14 hours (Table 1, run 9). However, this reaction led to the formation of a minor by-product, HFPO-CS2' (Scheme 2). Earlier attempts to react oxiranes and CS<sub>2</sub> resulted in complex mixtures [7], and the formation of these regioisomers, HFPO-CS2 and HFPO-CS2', depends on the catalyst and the reaction conditions [50]. Selective formation of XAs (5-substituted 1,3-oxathiolane-2-thiones) was attained catalyzed by LiBr in appropriate solvents [44]. Thus, the non-catalyzed reactions conducted in this work were not expected to lead to the regioselective formation of cyclic XA [51]. A previous work has shown that triethylamine as a catalyst led to mixtures of products under high pressure [50]. On the other hand, lithium bromide [44], hydrotalcite [52], sodium methoxide [53], tributylphosphine, tetradentate Schiff-base aluminum complexes [41], and lithium perchlorate [54] selectively produced 1,3-oxathiolane-2-thiones.



Scheme 2. The reaction of HFPO with CS<sub>2</sub> catalyzed by LiBr

Trifluoromethyloxirane (TFEO) was nearly totally (93% yield) transformed into the corresponding CC, TFEO-CC3, by reaction with CO<sub>2</sub> in DMF in the presence of LiBr at 80°C (Table 1, run 10). Similar to the HFPO-CS2 case, the XA counterpart (TFEO-CS4) was easily obtained as a mixture of regioisomers in 91% yield using similar conditions as for HFPO (Table 1, run 11).

The reactions of CX<sub>2</sub> (X = O or S) with BEPFB proved to be slower than those performed with HFPO and TFEO (Table 1, runs 8-14). This could be ascribed to the strong electro-attractive effect of the fluorine atoms and the trifluoromethyl groups present on the epoxy rings of HFPO and TFEO. These strong electron-withdrawing groups induce a partial polarization of the carbon-carbon bond of the epoxide, which in turn enhances the electrophilic character of the carbon atom bearing the fluorine or trifluoromethyl group and its reactivity towards the bromide anion of the catalyst. The ring-opening of the epoxide by the bromide anion is believed to be the rate-determining step of the reaction of CO<sub>2</sub> and CS<sub>2</sub> onto epoxides. HFPO with a fully fluorinated backbone reacts with CO<sub>2</sub> or CS<sub>2</sub> quantitatively in 14 h (yield of 81% and 83%, respectively). In comparison, the reaction with BEPFB needs 96 h to lead to carbonate BEPFB-CC5 or xanthate BEPFB-CS6 in high yields.

The FTIR spectrum of BEPFB-CC5 (Figure S8 in SI) confirmed the formation of the CC with the characteristic bands of the carbonate function: C=O bond stretching vibration at 1776 cm<sup>-1</sup>, and other vibrations corresponding to C-C and C-O bonds appear at 1047 cm<sup>-1</sup> and 1106 cm<sup>-1</sup>, respectively. Similar observations are noted on the FTIR spectrum of BEPFB-CS6 (Figure S11 in SI) with the characteristic bands of the XA function: C=S bond stretching vibration at 1777 cm<sup>-1</sup>.

The following section describes the NMR spectra of these novel fluorinated cyclic-carbonate BEPFB-CC5 and xanthate BEPFB-CS6, which possess the most complex chemical structures (Figure 2-4). The other products synthesized in this study have been characterized by <sup>1</sup>H, <sup>19</sup>F, and <sup>13</sup>C NMR spectroscopy and the corresponding spectra are shown in the SI (Figures S1-7 and S9-10).

Figure 2 displays the <sup>1</sup>H NMR spectra of cyclic-carbonate **5** (BEPFB-CC5) and xanthate **6** (BEPFB-CS6). These spectra clearly evidence the vanishing of the signals of the diepoxide at 2.6, 2.8, and 3.2 ppm replaced by AB systems (located at 4.6 and 4.2 ppm for **5**; 3.9 and 3.7 ppm for **6**), corresponding to the non-equivalent hydrogen atoms CH<sub>4</sub>H<sub>b</sub> of the carbonate groups. The same observation can be made for the CH group of the carbonate ring with the chemical shift at 5.2 ppm for **5** and 5.6 ppm for **5** and **6**, respectively, low field-shifted by the presence of the carbonyl group compared to the epoxide (3.2 ppm). Both hydrogens in CH<sub>2</sub>CF<sub>2</sub> groups appear as one complex system centered at 2.9 ppm due to fluorine coupling in  $\alpha$  and  $\beta$  positions.



**Figure 2.** <sup>1</sup>H NMR spectra of BEPFB-CS6 (top spectrum), BEPFB-CC5 (middle spectrum), and BEPFB (bottom spectrum) (DMSO-d6, 20 °C, 400 MHz)

The <sup>19</sup>F NMR spectrum of BEPFB-CC5 (Figure 3) displays an AB system at -112 ppm assigned to the CH<sub>2</sub>CF<sub>A</sub>F<sub>B</sub>CF<sub>2</sub> groups of A and B diastereoisomers. Indeed, the chemical shifts are different because the product is a mixture of two diastereoisomers due to the presence of an asymmetric carbon on the cyclic carbonate. The signals at -123 ppm are assigned to the central difluoromethylene groups (CH<sub>2</sub>CF<sub>2</sub>CF<sub>2</sub>). Similar observations were noted on the <sup>19</sup>F NMR spectrum of BEPFB-CS6 (Figure S9 in the SI).





Figure 3. <sup>19</sup>F NMR spectrum of BEPFB-CC5 (upper spectrum) and BEPFB (bottom spectrum) (DMSO-d6, 20 °C, 235.2 MHz)

BEPFB-CC5 was also characterized by <sup>13</sup>C NMR spectroscopy(Figure 4). The resulting spectrum exhibits the signal of the carbonyl groups of the CC at 154 ppm. As expected, the four CF<sub>2</sub> peaks appear between 106 and 120 ppm. Due to the presence of the carbonyl group, the signal corresponding to the CH groups of the cyclocarbonate is low field shifted to 70 ppm compared to that of the CH in the epoxide that is noted at 44 ppm. Similar results were observed in the <sup>13</sup>C NMR spectrum of BEPFB-CS6 (Figure S10 in the SI) except for the resonance of the XA moiety, highlighted at 212 ppm.



Figure 4. <sup>13</sup>C NMR spectrum of BEPFB-CC5 (upper spectrum) and BEPFB (bottom spectrum) (DMSO, 20 °C, 100.6 MHz)

170

160

161 162

163

164

165

166

167

168

- 173
- 174

#### 3. Materials and Methods

#### Materials

1,4-bis(2',3'-epoxypropyl)perfluorobutane (BEPFB) was provided by TOSOH Finechemicals Corporation (Shunan, Japan). 2-(trifluoromethyl)oxirane (TFEO) provided by SynQuest (Alachua, Fa, USA). Hexafluoropropene oxide (HFPO), carbon disulfide (CS<sub>2</sub>), lithium bromide (LiBr), sodium sulfate (Na<sub>2</sub>SO<sub>4</sub>), acetone (analytical grade), dichloromethane (DCM, analytical grade), methanol (analytical grade), N,N-dimethylformamide (DMF), 1,4-dioxane and tetrahydrofuran (THF, analytical grade) were purchased from Sigma-Aldrich. The deuterated solvents used in NMR spectroscopy were purchased from Euroiso-top (purity>99.8%).

#### Characterization

#### Nuclear Magnetic Resonance (NMR)

The NMR spectra were recorded on a Bruker AC 400 instrument, using deuterated chloroform (CDCl<sub>3</sub>), deuterated dimethylsulfoxide (DMSO-d<sub>6</sub>), or deuterated acetone (acetone-d<sub>6</sub>) as the solvents. Tetramethylsilane (TMS) or trichloromonofluoromethane (CFCl<sub>3</sub>) were used as references for <sup>1</sup>H (or <sup>19</sup>F) nuclei. Coupling constants and chemical shifts are given in hertz (Hz) and part per million (ppm), respectively. The experimental conditions for recording <sup>1</sup>H, <sup>13</sup>C, (or <sup>19</sup>F) NMR spectra were as follows: flip angle 90° (or 30°), acquisition time 4.5 s (or 0.7 s), pulse delay 2 s (or 2 s), number of scans 128 (or 512), and a pulse width of 5 µs for <sup>19</sup>F NMR.

#### Fourier Transform Infrared Spectroscopy (FTIR)

The FTIR spectra were recorded on a Nicolet 210 FTIR spectrometer. The characteristic absorptions mentioned in the text were strong bands reported in cm<sup>-1</sup>.

#### Autoclave operations

The carbonation reactions were performed in Hastelloy Parr autoclave systems (HC 276, 100 mL) equipped with a manometer, a mechanical Hastelloy anchor, a rupture disk (3000 PSI), inlet, and outlet valves. An electronic device regulated and controlled both the stirring and heating of the autoclave. Before reaction, the autoclave was pressurized with 30 bars of nitrogen to check for leaks. The autoclave was then conditioned for the reaction with a vacuum of 10<sup>-2</sup> mbar for 40 minutes to remove any trace of oxygen. The liquid and dissolved solid phases were introduced via a funnel. Then, the gases were introduced by double weighing (i.e., the weight difference before and after filling the autoclave with the gas).

#### Synthetic procedures

#### Synthesis of 4,4,5-trifluoro-5-(trifluoromethyl)-1,3-dioxolan-2-one (HFPO-CC1)

In a round-bottom flask (100 mL), LiBr (209 mg, 2.4 mmol) was dissolved in acetone (30 mL). The solution was transferred into a reactor via a funnel. The reactor was cooled to -30 °C, and Hexafluoropropene oxide HFPO (8 g, 4.8 mmol) was introduced by double weighing and then CO<sub>2</sub> (4 bar). The reaction was carried out at 50 °C for 15 hrs. Then, a pressure drop (30 bar) was noticed, probably due to the consumption of the HFPO and CO<sub>2</sub>. At 35 °C, a rapid increase in temperature to 56 °C is observed, which shows that the reaction is exothermic. During the hour that followed this exothermic event, the pressure decreased from 30 to 12 bar for a temperature maintained at 50 °C. After the reaction, the autoclave was degassed (releasing unreacted HFPO and CO<sub>2</sub>), and acetone was evaporated under a vacuum. The remaining crude was dispersed in deionized water (50 mL). The aqueous mixture was extracted three times with dichloromethane (200 mL). The organic phase was dried with Na<sub>2</sub>SO<sub>4</sub>, filtered, and the dichloromethane evaporated. The final product is a yellow liquid obtained in 81% yield (<sup>19</sup>F NMR spectrum, Figure S1 in the SI).

 <sup>19</sup>F NMR (235.2 MHz, CDCl<sub>3</sub>, δ): -135.1, -132.8, -129.8, -122.5 (CF), -87.2, -83.6, -78.2 (CF<sub>2</sub>), -81.8 (CF<sub>3</sub>).

#### Synthesis of 4,4,5-trifluoro-5-(trifluoromethyl)-1,3-oxathiolane-2-thione (HFPO-CS2)

In a round-bottom flask (100 mL), LiBr (209 mg, 2.4 mmol) and carbon disulfide (CS<sub>2</sub>, 11.00 g, 144 mmol) were dissolved in acetone (30 mL). The solution was transferred into a reactor via a funnel. The reactor was cooled to -30 °C, and HFPO (8 g, 481 mmol) was introduced by double weighing. The reaction was carried out at 50 °C for 15 hrs. The purification was similar to that used for HFPO-CC1. The product was obtained as a colorless oil with 83% yield (<sup>19</sup>F and <sup>13</sup>C NMR spectra, Figures S2 and S3 in the SI).

<sup>19</sup>F NMR (235.2 MHz, CDCl<sub>3</sub>, δ): -132.8, -130.1, -122.8 (CF), -89.0, -87.4, -83.9, -78.5 (CF), -82.1 (CF<sub>3</sub>).

<sup>13</sup>C NMR (100.6 MHz, CDCl<sub>3</sub>, δ): 101.9- 108.9 (C-F), -113.6-125.5 (CF<sub>2</sub> and CF<sub>2</sub>), 159.1 and 162. 5 (C=S).

#### Synthesis of 4-(trifluoromethyl)-1,3-dioxolan-2-one (TFEO-CC3).

Trifluoroethyleneoxide (15.01 g, 153 mmol) and LiBr (644 mg, 7.7 mmol) were dissolved in DMF (40 mL). The solution was transferred into a reactor, and the atmosphere was replaced with CO<sub>2</sub> (8 bar). The reaction was carried out at 80 °C for 24 hrs. The reactor is degassed after reaction and cooling to release the unreacted CO<sub>2</sub>. The crude reaction product was then distilled with a Kugelrohr distillation apparatus. After purification, the product was obtained as a colorless liquid (<sup>1</sup>H, and <sup>19</sup>F NMR spectra, Figures S4 and S5 in the SI).

<sup>1</sup>H NMR (400.1 MHz, CDCl<sub>3</sub>, δ): 4.53 (m, 1H, H<sub>3a</sub>), 4.68 (m, 1H, H<sub>3b</sub>), 5.03 (1H, H<sub>2</sub>). <sup>13</sup>C NMR (100.6 MHz, CDCl<sub>3</sub>, δ): 31.1 (s, CF<sub>3</sub>), 36.2 (s, C<sub>3a</sub>), 36.3 (s, C<sub>3b</sub>), 162.4 (s, C<sub>1</sub>). <sup>19</sup>F NMR (235.2 MHz, CDCl<sub>3</sub>, δ): -80.2 (s, CF<sub>3</sub>).

#### Synthesis of 5-(trifluoromethyl)-1,3-oxathiolane-2-thione (TFEO-CS4)

In a two-neck round-bottom flask (100 mL), trifluoroethyleneoxide (10.2 g, 104.1 mmol) and carbon disulfide (9.0 mL, 104.1 mmol, 1 eq) were introduced at 0 °C with a catalytic amount of LiBr (1.48 g, 17.2 mmol, 16.5 %mol) in THF (50 mL). After 20 min, the reaction was allowed to proceed at room temperature for 12 h. The mixture was then poured into ethyl acetate and washed twice with water. The organic phase was dried over magnesium sulfate before evaporating the solvent under a vacuum to obtain the pure product as a yellowish liquid (<sup>1</sup>H and <sup>19</sup>F NMR spectra, Figures S6 and S7 in the SI). <sup>1</sup>H NMR (400.1 MHz, CDCl<sub>3</sub>, δ): 3.84 (m, 2H, H<sub>3</sub>), 5.34 (1H, H<sub>2</sub>).

<sup>13</sup>C NMR (100.6 MHz, CDCl<sub>3</sub>, δ): 31.1 (s, CF<sub>3</sub>), 36.2 (s, C<sub>3a</sub>), 36.3 (s, C<sub>3b</sub>), 162.4 (s, C<sub>1</sub>). <sup>19</sup>F NMR (235.2 MHz, CDCl<sub>3</sub>, δ): -77.6 (s, CF<sub>3</sub>).

Synthesis

4-[2,2,3,3,4,4,5,5-octafluoro-6-(2-oxo-1,3-dioxolan-4-yl)hexyl]-1,3-dioxolan-2-one (BEPFB-CC5)

The procedure was similar as that of the synthesis of HFPO-CC1. 1,4-bis(2',3'-epoxypropyl)perfluorobutane (10.02 g, 31.8 mmol) and LiBr (276 mg, 3.18 mmol) were dissolved in acetone (30 mL). The solution was transferred into a reactor, and the atmosphere was replaced with  $CO_2$  (4 bar). The reaction was carried out at 65 °C for 96 hrs. During the reaction, an increase in the pressure inside the reactor was observed (up to 12 Bar) followed by a decreased pressure from 12 bar to 6 bar for a temperature maintained at 65 °C. After reaction and cooling, the reactor is degassed. The crude product was washed with acetone (100 mL), filtered and evaporated under a vacuum, and led to the desired product. The product was obtained as a white powder (<sup>1</sup>H, <sup>19</sup>F, <sup>13</sup>C NMR spectra, and FTIR spectrum, Figures 2, 3, and 4 and Figure S8 in the SI)

 $^{1}$ H NMR (400.1 MHz, CDCl<sub>3</sub>,  $\delta$ ): 2.90 (m, CH<sub>2</sub>CF<sub>2</sub>, 4H), 4.63 and 4.22 (m, OCH<sub>2</sub>, 4H), 5.20 (m, CH, 1H).

of

<sup>19</sup>F NMR (235.2 MHz, CDCl<sub>3</sub>, δ): -112.3 (AB system, CH<sub>2</sub>CF<sub>A</sub>F<sub>B</sub>CF<sub>2</sub>), -123.2 (s, 274 CH<sub>2</sub>CF<sub>2</sub>CF<sub>2</sub>). 275 <sup>13</sup>C NMR (100.6 MHz, CDCl<sub>3</sub>, δ): 154.4 (C=O), 106. 6-120.72 (CF<sub>2</sub>), 70.2 (CH), 60.2 276 (OCH<sub>2</sub>), 39.3 (CH<sub>2</sub>CF<sub>2</sub>). 277 278 Synthesis of 4-[2,2,3,3,4,4,5,5-octafluoro-6-(2-thioxo-1,3-oxathiolan-4-yl)hexyl]-1,3-oxathiolane-2-thi 279 one (BEPFB-CS6) 280 A similar procedure as that of the synthesis of HFPO-CS2. LiBr (276 mg, 1.59 mmol), 281 carbon disulfide (7.00 g, 10 mmol) and 1,4-bis(2',3'-epoxypropyl)perfluorobutane (5.03 g, 282 15 mmol) were dissolved in acetone (30 mL). The solution was introduced into a reactor 283 via a tight funnel. The reaction was carried out at 65 °C for 96 hrs. After opening the re-284 actor, the crude reaction product was washed with dichloromethane (100 mL), filtered, 285 286 and dried under a vacuum to lead to the desired product. The pure product was obtained quantitatively as a white powder (<sup>1</sup>H, <sup>19</sup>F, <sup>13</sup>C NMR spectra and FTIR spectrum, Figure 2 287 288 and Figure S9-S11 in the SI). <sup>1</sup>H NMR (400.1 MHz, CDCl<sub>3</sub>, δ): 3.02 (m, CH<sub>2</sub>CF<sub>2</sub>, 4H), 3.92 and 3.77 (m, OCH<sub>2</sub>, 4H), 289 5.60 (m, CH, 1H). 290 <sup>1</sup>9F NMR (235.2 MHz, CDCl<sub>3</sub>, δ): -111.9 (AB system, CH<sub>2</sub>CF<sub>A</sub>F<sub>B</sub>CF<sub>2</sub>), -124.0 (s, 291 CH<sub>2</sub>CF<sub>2</sub>CF<sub>2</sub>). 292 <sup>13</sup>C NMR (100.6 MHz, CDCl<sub>3</sub>, δ): 212.8 (C=S), 107. 5 -120.2 (CF<sub>2</sub>), 84.6 (CH); 62.0 293 294 (OCH<sub>2</sub>), 39.1 (CH<sub>2</sub>CF<sub>2</sub>). 4. Conclusions 295 In this study, a series of fluorinated epoxides were efficiently carbonated or modi-296 fied into xanthate in mild conditions. These reactions efficiently led to the desired cyclic 297 carbonates and cyclic xanthates in high yields (81-93 %) at 65 °C catalyzed by LiBr. Such 298 novel carbonates and xanthates (1-6) were characterized by <sup>1</sup>H, <sup>19</sup>F, <sup>13</sup>C NMR, and FTIR 299 spectroscopies. These synthesized carbonates and xanthates may find interesting appli-300 cations. The bis(cyclocarbonate)s can produce novel fluorinated polyhydroxyurethanes 301 (under progress) or polycarbonates. The cycloxanthates are potential solvents for liquid 302 electrolytes in Lithium-ion batteries [13] and efficient chain transfer agents in controlled 303 radical (co)polymerization of fluorinated monomers [55]. They can be used as precursors 304 for poly(thio)urethane materials via ring-opening reaction using primary or secondary 305 amines. These polymers possess thiols analogous to the hydroxyl groups of 306 307 polyhydroxyurethanes. In addition, this functionality provides an exciting opportunity to prepare functional polymers via thiol-ene, thiol-yne of thia-Michael addition. 308 309 310 311 312 313 314 315 316

- 317
- 318

**Supplementary Materials:** The following supporting information can be downloaded at: www.mdpi.com/xxx/s1, Figure S1: <sup>19</sup>F NMR spectrum of HFPO-CC1 (1) recorded in CDCl<sub>3</sub> (20 °C, 235.3 MHz); Figure S2: <sup>19</sup>F NMR spectrum of HFPO-CS2 (2) and HFPO-CS2' (2') recorded in CDCl<sub>3</sub> (20 °C, 235.3 MHz); Figure S3: <sup>13</sup>C NMR spectrum of HFPO-CS2 (2) and HFPO-CS2' (2') recorded in CDCl<sub>3</sub> (20 °C, 100.6 MHz); Figure S4: <sup>1</sup>H NMR spectrum of TFEO-CC3 (3) recorded in CDCl<sub>3</sub> (20 °C, 400.1 MHz); Figure S5: <sup>19</sup>F NMR spectrum of TFEO-CC3 (3) recorded in CDCl<sub>3</sub> (20 °C, 235.3 MHz); Figure S6: <sup>1</sup>H NMR spectrum of TFEO-CS4 (4) recorded in CDCl<sub>3</sub> (20 °C, 400 MHz); Figure S7: <sup>19</sup>F NMR spectrum of TFEO-CS4 (4) recorded in CDCl<sub>3</sub> (20 °C, 400 MHz); Figure S8: FTIR spectrum of BEPFB-CC5 (5); Figure S9: <sup>19</sup>F NMR spectrum of BEPFB-CS6 (6) (upper spectrum) and BEPFB (lower spectrum) recorded in DMSO-d<sub>6</sub>, (20 °C, 235.3 MHz); Figure S10: <sup>13</sup>C NMR spectrum of BEPFB-CS6 (6) (upper spectrum) and BEPFB (lower spectrum) recorded in DMSO-d<sub>6</sub> (20 °C, 100.66 MHz); Figure S11: FTIR spectrum of BEPFB-CS6 (6).

Author Contributions: Conceptualization, B.A. and A.A.; methodology, A.A. and B.A.; validation, formal analysis, data curation, visualization, and supervision, B.A., A.A., V.L., S.C., and W.M.; investigation, L.H., B.A., A.A., V.L., S.C., and W.M.; resources, B.A., V.L., and S.C.; writing—original draft preparation, A.A., L.H., and W.M.; writing—review and editing, B.A., A.A., V.L., S.C. and W.M.; project administration, A.A. and B.A.. All authors have read and agreed to the published version of the manuscript.

#### **Funding:**

The authors thank CEA for financial support.

Data Availability Statement: Not applicable.

Acknowledgments: The authors are grateful to the Institut de Chimie of the CNRS and Arkema (Colombes and Pierre-Benite, France) for financial support by supplying us with free materials, TOSOH Finechemicals (Shiba, Japan), and SynQuest (Alachua, Fa, USA) that made this research possible. The authors thank Ecole Nationale Supérieure de chimie de Montpellier (ENSCM) and the Université Libanaise (UL) as well as Prof. B. Boutevin (ENSCM), Dr. V. Besse (ENSCM) and Dr. D. Naoufal (UL).

Conflicts of Interest: The authors declare no conflict of interest.

#### 363 References

- 364 (1) Shaikh, A.-A. G.; Sivaram, S. Organic Carbonates. Chem. Rev. 1996, 96 (3), 951–976. https://doi.org/10.1021/cr950067i.
- Tian, J.-S.; Miao, C.-X.; Wang, J.-Q.; Cai, F.; Du, Y.; Zhao, Y.; He, L.-N. Efficient Synthesis of Dimethyl Carbonate from
   Methanol, Propylene Oxide and CO2 Catalyzed by Recyclable Inorganic Base/Phosphonium Halide-Functionalized
   Polyethylene Glycol. *Green Chem.* 2007, 9 (6), 566–571. https://doi.org/10.1039/B614259A.
- 368 (3) Yoshida, M.; Ihara, M. Novel Methodologies for the Synthesis of Cyclic Carbonates. *Chemistry A European Journal* 2004, 10
   369 (12), 2886–2893. https://doi.org/10.1002/chem.200305583.
- Yoshida, M.; Hara, N.; Okuyama, S. Catalytic Production of Urethanes from Amines and Alkyl Halides in Supercritical
   Carbon Dioxide. *Chem. Commun.* 2000, No. 2, 151–152. https://doi.org/10.1039/A908819I.
- Jessop, P. G.; Ikariya, T.; Noyori, R. Homogeneous Hydrogenation of Carbon Dioxide. *Chem. Rev.* 1995, 95 (2), 259–272.
   https://doi.org/10.1021/cr00034a001.
- Grignard, B.; Gennen, S.; Jérôme, C.; Kleij, A. W.; Detrembleur, C. Advances in the Use of CO2 as a Renewable Feedstock
   for the Synthesis of Polymers. *Chem. Soc. Rev.* 2019, 48 (16), 4466–4514. https://doi.org/10.1039/C9CS00047J.
- Ochiai, B.; Endo, T. Carbon Dioxide and Carbon Disulfide as Resources for Functional Polymers. *Progr. Polym. Sci.* 2005, 30
   (2), 183–215. https://doi.org/10.1016/j.progpolymsci.2005.01.005.
- 378 (8) Sakakura, T.; Kohno, K. The Synthesis of Organic Carbonates from Carbon Dioxide. *Chem. Commun.* 2009, No. 11,
   379 1312–1330. https://doi.org/10.1039/B819997C.
- Zhang, Y.-Y.; Zhang, X.-H.; Wei, R.-J.; Du, B.-Y.; Fan, Z.-Q.; Qi, G.-R. Synthesis of Fully Alternating Polycarbonate with
   Low Tg from Carbon Dioxide and Bio-Based Fatty Acid. *RSC Adv.* 2014, 4 (68), 36183–36188.
   https://doi.org/10.1039/C4RA06157H.
- (10)Bayardon, J.; Holz, J.; Schäffner, B.; Andrushko, V.; Verevkin, S.; Preetz, A.; Börner, A. Propylene Carbonate as a Solvent for 383 Hydrogenations. Angewandte Chemie International Edition 2007, (31), 384 Asymmetric 46 5971-5974. https://doi.org/10.1002/anie.200700990. 385
- Tsuda, T.; Kondo, K.; Tomioka, T.; Takahashi, Y.; Matsumoto, H.; Kuwabata, S.; Hussey, C. L. Design, Synthesis, and
   Electrochemistry of Room-Temperature Ionic Liquids Functionalized with Propylene Carbonate. *Angewandte Chemie International Edition* 2011, 50 (6), 1310–1313. https://doi.org/10.1002/anie.201005208.
- Ota, H.; Sakata, Y.; Otake, Y.; Shima, K.; Ue, M.; Yamaki, J. Structural and Functional Analysis of Surface Film on Li Anode
   in Vinylene Carbonate-Containing Electrolyte. *J. Electrochem. Soc.* 2004, *151* (11), A1778. https://doi.org/10.1149/1.1798411.
- (13) Galiano, H.; Cadra, S.; Ameduri, B.; Besse, V.; Alaaeddine, A. Specific Fluorinated Compounds Used as an Organic Solvent
   for Lithium Salts. EP3019469A1, May 18, 2016.
- Fukuoka, S.; Kawamura, M.; Komiya, K.; Tojo, M.; Hachiya, H.; Hasegawa, K.; Aminaka, M.; Okamoto, H.; Fukawa, I.;
   Konno, S. A Novel Non-Phosgene Polycarbonate Production Process Using by-Product CO2 as Starting Material. *Green Chem.* 2003, 5 (5), 497–507. https://doi.org/10.1039/B304963A.
- (15) Pescarmona, P. P.; Taherimehr, M. Challenges in the Catalytic Synthesis of Cyclic and Polymeric Carbonates from Epoxides
   and CO2. *Catal. Sci. Technol.* 2012, 2 (11), 2169–2187. https://doi.org/10.1039/C2CY20365K.
- (16) Clements, J. H. Reactive Applications of Cyclic Alkylene Carbonates. Ind. Eng. Chem. Res. 2003, 42 (4), 663–674.
   https://doi.org/10.1021/ie020678i.
- (17) Liu, A.-H.; Yu, B.; He, L.-N. Catalytic Conversion of Carbon Dioxide to Carboxylic Acid Derivatives. *Greenhouse Gases:* Science and Technology 2015, 5 (1), 17–33. https://doi.org/10.1002/ghg.1461.

- 402 (18) Brocas, A.-L.; Cendejas, G.; Caillol, S.; Deffieux, A.; Carlotti, S. Controlled Synthesis of Polyepichlorohydrin with Pendant
   403 Cyclic Carbonate Functions for Isocyanate-Free Polyurethane Networks. *Journal of Polymer Science Part A: Polymer Chemistry* 404 2011, 49 (12), 2677–2684. https://doi.org/10.1002/pola.24699.
- (19) Benyahya, S.; Habas, J.-P.; Auvergne, R.; Lapinte, V.; Caillol, S. Structure–Property Relationships in Polyhydroxyurethanes
   Produced from Terephthaloyl Dicyclocarbonate with Various Polyamines. *Polymer International* 2012, *61* (11), 1666–1674.
   https://doi.org/10.1002/pi.4257.
- 408 (20) Benyahya, S.; Desroches, M.; Auvergne, R.; Carlotti, S.; Caillol, S.; Boutevin, B. Synthesis of Glycerin Carbonate-Based
   409 Intermediates Using Thiol–Ene Chemistry and Isocyanate Free Polyhydroxyurethanes Therefrom. *Polym. Chem.* 2011, 2 (11),
   410 2661–2667. https://doi.org/10.1039/C1PY00289A.
- (21) Cornille, A.; Auvergne, R.; Figovsky, O.; Boutevin, B.; Caillol, S. A Perspective Approach to Sustainable Routes for
   Non-Isocyanate Polyurethanes. *European Polymer Journal* 2017, *87*, 535–552. https://doi.org/10.1016/j.eurpolymj.2016.11.027.
- 413 (22) Carré, C.; Ecochard, Y.; Caillol, S.; Avérous, L. From the Synthesis of Biobased Cyclic Carbonate to Polyhydroxyurethanes:
  414 A Promising Route towards Renewable Non-Isocyanate Polyurethanes. *ChemSusChem* 2019, 12 (15), 3410–3430.
  415 https://doi.org/10.1002/cssc.201900737.
- (23) Decortes, A.; Castilla, A. M.; Kleij, A. W. Salen-Complex-Mediated Formation of Cyclic Carbonates by Cycloaddition of
   (23) CO2 to Epoxides. *Angewandte Chemie International Edition* 2010, 49 (51), 9822–9837. https://doi.org/10.1002/anie.201002087.
- 418 (24) North, M.; Pasquale, R.; Young, C. Synthesis of Cyclic Carbonates from Epoxides and CO2. *Green Chem.* 2010, 12 (9),
  419 1514–1539. https://doi.org/10.1039/C0GC00065E.
- 420 (25) Besse, V.; Camara, F.; Voirin, C.; Auvergne, R.; Caillol, S.; Boutevin, B. Synthesis and Applications of Unsaturated
  421 Cyclocarbonates. *Polym. Chem.* 2013, *4* (17), 4545–4561. https://doi.org/10.1039/C3PY00343D.
- Liang, S.; Liu, H.; Jiang, T.; Song, J.; Yang, G.; Han, B. Highly Efficient Synthesis of Cyclic Carbonates from CO2 and
  Epoxides over Cellulose/KI. *Chem. Commun.* 2011, 47 (7), 2131–2133. https://doi.org/10.1039/C0CC04829A.
- Kihara, N.; Hara, N.; Endo, T. Catalytic Activity of Various Salts in the Reaction of 2,3-Epoxypropyl Phenyl Ether and
   Carbon Dioxide under Atmospheric Pressure. J. Org. Chem. 1993, 58 (23), 6198–6202. https://doi.org/10.1021/jo00075a011.
- 426 (28) Huang, J.-W.; Shi, M. Chemical Fixation of Carbon Dioxide by NaI/PPh3/PhOH. J. Org. Chem. 2003, 68 (17), 6705–6709.
   427 https://doi.org/10.1021/j00348221.
- Yamaguchi, K.; Ebitani, K.; Yoshida, T.; Yoshida, H.; Kaneda, K. Mg–Al Mixed Oxides as Highly Active Acid–Base
  Catalysts for Cycloaddition of Carbon Dioxide to Epoxides. J. Am. Chem. Soc. 1999, 121 (18), 4526–4527.
  https://doi.org/10.1021/ja9902165.
- (30) Barkakaty, B.; Morino, K.; Sudo, A.; Endo, T. Amidine-Mediated Delivery of CO2 from Gas Phase to Reaction System for
  Highly Efficient Synthesis of Cyclic Carbonates from Epoxides. *Green Chem.* 2010, 12 (1), 42–44.
  https://doi.org/10.1039/B916235F.
- (31) Du, Y.; Cai, F.; Kong, D.-L.; He, L.-N. Organic Solvent-Free Process for the Synthesis of Propylene Carbonate from
   Supercritical Carbon Dioxide and Propylene Oxide Catalyzed by Insoluble Ion Exchange Resins. *Green Chem.* 2005, 7 (7),
   518–523. https://doi.org/10.1039/B500074B.
- 437 (32) Qi, C.; Ye, J.; Zeng, W.; Jiang, H. Polystyrene-Supported Amino Acids as Efficient Catalyst for Chemical Fixation of Carbon
   438 Dioxide. *Advanced Synthesis & Catalysis* 2010, 352 (11–12), 1925–1933. https://doi.org/10.1002/adsc.201000261.
- (33) Kawanami, H.; Sasaki, A.; Matsui, K.; Ikushima, Y. A Rapid and Effective Synthesis of Propylene Carbonate Using a
   Supercritical CO2–Ionic Liquid System. *Chem. Commun.* 2003, No. 7, 896–897. https://doi.org/10.1039/B212823C.
- (34) Han, L.; Choi, H.-J.; Choi, S.-J.; Liu, B.; Park, D.-W. Ionic Liquids Containing Carboxyl Acid Moieties Grafted onto Silica:
   Synthesis and Application as Heterogeneous Catalysts for Cycloaddition Reactions of Epoxide and Carbon Dioxide. *Green*
- 443 *Chem.* **2011**, *13* (4), 1023–1028. https://doi.org/10.1039/C0GC00612B.

- (35) Shi, F.; Zhang, Q.; Ma, Y.; He, Y.; Deng, Y. From CO Oxidation to CO2 Activation: An Unexpected Catalytic Activity of
  Polymer-Supported Nanogold. J. Am. Chem. Soc. 2005, 127 (12), 4182–4183. https://doi.org/10.1021/ja042207o.
- (36) Zhou, H.; Zhang, W.-Z.; Liu, C.-H.; Qu, J.-P.; Lu, X.-B. CO2 Adducts of N-Heterocyclic Carbenes: Thermal Stability and
  Catalytic Activity toward the Coupling of CO2 with Epoxides. *J. Org. Chem.* 2008, 73 (20), 8039–8044.
  https://doi.org/10.1021/jo801457r.
- Liang, S.; Liu, H.; Jiang, T.; Song, J.; Yang, G.; Han, B. Highly Efficient Synthesis of Cyclic Carbonates from CO2 and
   Epoxides over Cellulose/KI. *Chem. Commun.* 2011, 47 (7), 2131–2133. https://doi.org/10.1039/C0CC04829A.
- (38) Besse, V.; Foyer, G.; Auvergne, R.; Caillol, S.; Boutevin, B. Access to Nonisocyanate Poly(Thio)Urethanes: A Comparative
  Study. *Journal of Polymer Science Part A: Polymer Chemistry* 2013, *51* (15), 3284–3296. https://doi.org/10.1002/pola.26722.
- (39) Ochiai, B.; Nakayama, J.; Mashiko, M.; Kaneko, Y.; Nagasawa, T.; Endo, T. Synthesis and Crosslinking Reaction of
  Poly(Hydroxyurethane) Bearing a Secondary Amine Structure in the Main Chain. *J. Polym. Sci. Part A: Polym. Chem.* 2005, 43
  (23), 5899–5905. https://doi.org/10.1002/pola.21078.
- (40) Sudo, A.; Motokucho, S.; Endo, T. A New Series of Cyclic 5-Membered Dithiocarbonates Having Urethane Tether:
  Application as an Adhesion Promoter to Epoxy-Amine Curing System. J. Polym. Sci. Part A: Polym. Chem. 2008, 46 (7),
  2588–2592. https://doi.org/10.1002/pola.22589.
- Wang, Y.-M.; Li, B.; Wang, H.; Zhang, Z.-C.; Lu, X.-B. Cooperative Catalysis with Binary Lewis Acid–Lewis Base System for
  the Coupling of Carbon Disulfide and Epoxides. *Applied Organometallic Chemistry* 2012, 26 (11), 614–618.
  https://doi.org/10.1002/aoc.2908.
- 462 (42) Endo, T.; Choi, W.; Sanda, F. Substituent Effects on the Control of Cationic Isomerization and Polymerization of
   463 Five-Membered Cyclic Dithiocarbonates. *Heterocycles* 2000, 52 (1), 125. https://doi.org/10.3987/COM-99-S41.
- (43)Motokucho, S.; Takeuchi, D.; Sanda, F.; Endo, T. Synthesis of Cyclic Trithiocarbonates from Cyclic Ethers and Carbon 464 Disulfide Catalyzed Titanium Complex. Tetrahedron 2001, 57 (33), 7149-7152. 465 by https://doi.org/10.1016/S0040-4020(01)00685-8. 466
- 467 (44) Kihara, N.; Nakawaki, Y.; Endo, T. Preparation of 1,3-Oxathiolane-2-Thiones by the Reaction of Oxirane and Carbon
  468 Disulfide. J. Org. Chem. 1995, 60 (2), 473–475. https://doi.org/10.1021/jo00107a034.
- (45) Petrov, V. A.; Marshall, W. Synthesis of Trifluoromethylated Heterocycles Using Partially Fluorinated Epoxides. J. Fluorine
   (47) Chem. 2011, 132 (1), 41–51. https://doi.org/10.1016/j.jfluchem.2010.11.003.
- 471 (46) Smith, D. W.; Iacono, S. T.; Iyer, S. S., Handbook of Fluoropolymer Science and Technology, Wiley, New-York, 2014. ISBN:
  472 978-0-470-07993-5.
- 473 (47) Ameduri, B. Fluoropolymers: The Right Material for the Right Applications. *Chem. Eur. J.*, 2018, 24, 18830-18842.
  474 https://doi.org/10.1002/chem.20180270.
- 475 (48) Ameduri, B.; Fomin, S., *Fascinating Fluoropolymers and Their Applications*; vol. 1 and 2; Elsevier Ltd., Amsterdam, 2020. ISBN:
  476 9780128218730.
- (49)Song, J.; Zhang, B.; Zhang, P.; Ma, J.; Liu, J.; Fan, H.; Jiang, T.; Han, B. Highly Efficient Synthesis of Cyclic Carbonates from 477 CO2 478 and Epoxides Catalyzed by KI/Lecithin. Catalysis Today 2012, 183 (1), 130-135. 479 https://doi.org/10.1016/j.cattod.2011.08.042.
- (50) Taguchi, Y.; Yasumoto, M.; Shibuya, I.; Suhara, Y. The Synthesis of 1,3-Dithiolan-2-Ones On the Reaction of Oxiranes with
   Carbon Disulfide under High Pressure. *Bulletin of the Chemical Society of Japan* 1989, 62 (2), 474–478.
   https://doi.org/10.1246/bcsj.62.474.
- (51)Clegg, W.; Harrington, R. W.; North, M.; Villuendas, P. A Bimetallic Aluminum(Salen) Complex for the Synthesis of 483 Org. 1,3-Oxathiolane-2-Thiones and 1,3-Dithiolane-2-Thiones. I. Chem. 2010, 75 (18), 6201-6207. 484 485 https://doi.org/10.1021/jo101121h.

- 486 (52) Maggi, R.; Malmassari, C.; Oro, C.; Pela, R.; Sartori, G.; Soldi, L. Reaction between Epoxides and Carbon Disulfide under
  487 Hydrotalcite Catalysis: Eco Compatible Synthesis of Cyclic Dithiocarbonates. *Synthesis* 2008, (1), 53–56.
  488 https://doi.org/10.1055/s-2007-1000820.
- 489 (53) Yavari, I.; Ghazanfarpour-Darjani, M.; Hossaini, Z.; Sabbaghan, M.; Hosseini, N. Methoxide Ion Promoted Efficient
  490 Synthesis of 1,3-Oxathiolane-2-Thiones by Reaction of Oxiranes and Carbon Disulfide. *Synlett* 2008, (06), 889–891.
  491 https://doi.org/10.1055/s-2008-1042927.
- Wu, J.-Y.; Luo, Z.-B.; Dai, L.-X.; Hou, X.-L. Tributylphosphine-Catalyzed Cycloaddition of Aziridines with Carbon
   Disulfide and Isothiocyanate. J. Org. Chem. 2008, 73 (22), 9137–9139. https://doi.org/10.1021/jo801703h.
- 494 (55) Banerjee, S.; Patil, Y.; Gimello, O.; Ameduri, B. Well-Defined Multiblock Poly(Vinylidene Fluoride) and Block Copolymers
  495 Thereof: A Missing Piece of the Architecture Puzzle. *Chem. Commun.* 2017, 53 (79), 10910–10913.
  496 https://doi.org/10.1039/C7CC06122F.