



HAL
open science

Magnetic nanoparticles: multifunctional tool for cancer therapy

Sumera Khizar, Eslam Elkalla, Nadia Zine, Nicole Jaffrezic-Renault,
Abdelhamid Errachid, Abdelhamid Elaïssari

► **To cite this version:**

Sumera Khizar, Eslam Elkalla, Nadia Zine, Nicole Jaffrezic-Renault, Abdelhamid Errachid, et al..
Magnetic nanoparticles: multifunctional tool for cancer therapy. *Expert Opinion on Drug Delivery*,
2023, 20 (2), pp.189-204. 10.1080/17425247.2023.2166484 . hal-03996447

HAL Id: hal-03996447

<https://hal.science/hal-03996447>

Submitted on 8 Nov 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.


Magnetic nanoparticles: Multifunctional tool for cancer therapy

Sumera Khizar, Eslam Elkalla, Nadia Zine, Nicole Jaffrezic-Renault, Abdelhamid Errachid, Abdelhamid Elaissari*

Univ Lyon, University Claude Bernard Lyon-1, CNRS, ISA-UMR 5280, F-69100 Lyon, France

*Corresponding author. ISA, University Claude Bernard Lyon-1, 5 rue de La Doua, Villeurbanne 69100, France. Email address: abdelhamid.elaissari@univ-lyon1.fr

Graphical Abstract:



ABSTRACT

Introduction: Cancer is among the most diseases resulting in massive deaths globally. Traditional therapies used to treat cancer possess harmful adverse effects. Taking these facts into consideration, researchers explored new-fangled therapeutic possibilities with enhanced benefits. Nanoparticle development used in cancer detection in addition to therapy showed substantial progress over the past few years.

Area covered: Herein, the latest research regarding cancer treatment employing MNPs in chemo-, immuno-, gene-, and radio- therapy along with hyperthermia is summarized in addition to their physio-chemical feature, advantages, and limitations for clinical translation have also been discussed.

Experts opinion: MNPs are being extensively investigated and get developed into effective therapeutic modules in cancer therapies. MNPs are extremely functionalizable tools aimed at cancer therapy owing excellent superparamagnetic, chemical, biocompatible, physical, and

26 biodegradable properties.

27

28 **Keywords:** Cancer, chemotherapy, gene therapy, hyperthermia, immunotherapy, magnetic
29 nanoparticles, radiotherapy

30

31 **Article highlights**

32

33 • Among various nanoparticles, magnetic nanoparticles (MNPs) emerged as innovative
34 treatment agents modernizing therapeutic usages in cancer therapy.

35

36 • MNPs modified with various coatings are developed to improve physico-chemical
37 features.

38

39 • Commonly, SPIONs (superparamagnetic iron oxide nanoparticles) are engaged in
40 tailored medicine intended for cancer theranostics.

41

42 • MNPs are being incorporated with immunotherapy, radiotherapy, chemotherapy,
43 hyperthermia, and gene therapy to treat cancer effectively.

44

45 • Despite the benefits of consuming MNPs in cancer therapy, there is still space for
46 improvement in engineering MNPs for targeting tumor cells more effectively.

47

48 **1. Introduction**

49 Anti-cancerous drugs delivered to targeted sites are one of the effective treatment methods used
50 to treat cancer along with fewer adverse effects. For targeted therapeutics, nanoparticles emerged
51 as a new generation of multi-functional control tools at the micro-nano level. A more effective
52 method is recognized with the functionalization of nano-vehicles with target molecules. These
53 functional moieties assist in which interaction of these nanoparticles with particular receptors
54 present in specific tumors, permitting their attachment to the tumor [1,2]. Another encouraging
55 approach is magnetic cancer therapy intended for improvement regarding imaging-guided
56 delivery along with therapeutic action [3]. Magnetic cancer therapy possibly is employed to treat
57 various kinds of tumors; in which magnetic drug delivery vehicles are manipulated by applying a
58 strong magnetic field [4].

59 Magnetic nanoparticles (MNPs) possess exceptional characteristics, for instance, small
60 dimensions, high surface area, and superparamagnetic nature, and are therefore useful for a
61 variety of applications [5]. Nanoparticles of iron oxide are the most commonly consumed
62 nanostructured materials used for targeted therapeutic applications. They comprise nanoparticles
63 of Fe₃O₄ (magnetite) and γ-Fe₂O₃ (maghemite), which perform a vital part in cancer diagnosis,
64 delivery of a drug, plus hyperthermia [6]. Furthermore, the superparamagnetic behavior of MNPs
65 can efficiently extravasate and target diseased and infected tissue (lesions) or cancerous sites [7].

66 All these MNPs properties are entirely employed in cancer therapy, where drugs encapsulated
67 with them or attached to their surface possibly are directed to preferred particular *in vivo* locate
68 by applying a magnetic field externally [8].
69 Various shapes have been synthesized for improving magnetization by reducing surface
70 anisotropy and increasing exchange anisotropy [9]. Different methodologies are accessible for
71 fabricating MNPs in various forms like nanowires, nanorods, and nanocubes. These techniques
72 include wet chemistry or “bottom-up” methods namely solvothermal, hydrothermal, co-
73 precipitation, sol-gel, electrochemical, flow injection synthesis, and laser pyrolysis procedures
74 [10]. In the last era, the core/shell morphology of MNPs containing a core of iron has been
75 extensively used from the perspective of magnetic influence and loading/release of particular
76 drugs [11]. MNPs attain controllable as well as precise release of the drugs by bonding drug
77 moieties through linkers having the ability to be cleaved or to shell of polymer enclosing them
78 having capability regarding releasing of drugs [12].
79 There are different approaches for improving some features for instance bad biodegradability,
80 biocompatibility as well as chemical inconstancy in biological environments. All this depends on
81 the functionalization of the MNPs surface. MNPs can be modified covalently by biocompatible
82 and biodegradable polymers [13]. MNPs can be combined with additional functional
83 nanomaterials by coating or successive growth particularly antibodies, ligands, or receptors to
84 create them interacting with biomolecules with considerable affinity, consequently giving
85 controlled “tagging” that deliberate high sensitivity for various biomedical applications [14]. Or
86 MNPs can be integrated with other metallic nanoparticles that give distinctive properties
87 permitting dissimilar functional molecules to get bonded to definite parts of particles and act as
88 diagnostic and therapeutic agents [15].
89 Researchers have been investigating the usage of MNPs for targeted cancer therapy since late
90 1970s due to improvement of behavior in therapeutic agents as well as their delivery to targeted
91 sites without any adverse effects [16,17]. Frequently, chemotherapeutic drugs, antibodies, and
92 drugs related to other diseases are attached to MNPs and are delivered to targeted areas inside
93 human body [18]. The employment of MNPs in drug delivery systems enhances their safety,
94 biocompatibility, targeting ability regarding other particular drugs, and less toxicity [19]. Large
95 surface area/volume is mainly beneficial and because of that large number of therapeutic
96 molecules can be attached to them easily, in addition to their manipulation by magnetic field aid
97 imaging of delivery of drugs to the targeted sites [20]. Consequently, MNPs have been coupled
98 for therapy along with diagnosis, mainly in cancer [21]. MNPs in drug delivery systems increase
99 the drug accumulation at the desired sites through magnetic manipulation or hyperthermia can be
100 induced in them by a magnetic field, causing cell death or triggering drug release from thermo-
101 responsive magnetic carriers [22].
102 Recently, MNPs are comprehensively employed in experimental investigations for treating
103 cancer and consequently different magnetic formulations have been developed, presenting
104 optimistic therapeutic impacts on various cancer types [23]. Different magnetic nanoparticles
105 with different coatings have been synthesized to improve their non-toxicity, biocompatibility,

106 safety, bio-distribution, stability, etc. Therefore, here we focused on MNPs and deliver an
107 inclusive review, considering detailed aspects of cancer treatment by integrating immunotherapy,
108 radiotherapy, chemotherapy, hyperthermia, and gene therapy with MNPs.

109

110 **2. Physio-chemical features and mechanism of magnetic nanoparticles (MNPs)**

111 MNPs have been synthesized consuming cobalt, nickel, and gadolinium, however iron oxide
112 (typically γ -Fe₂O₃ or Fe₃O₄) nanoparticles (IONPs) are most broadly investigated nanoparticles
113 in cancer therapeutics because of their less systemic toxicity and intense contrast features.
114 Generally MNPs consist of a magnetic core with and a polymer shell [24]. The surface coating
115 and modification of MNPs improves colloidal stability that permits electrostatic or covalent
116 binding of therapeutic payload, targeting constituents, in addition to imaging probes. It plays a
117 vital role in modifying properties of MNPs for instance general toxicity, pharmacokinetics, and
118 rate of clearance, non-specific adsorption of protein or interactions with cells, and persistent
119 release of drugs [25]. MNPs incorporation with polymer coating prevents their agglomeration,
120 and subsequently, offers a prolonged half-life, well-regulated drug release and, concurrently,
121 provides functional groups for conjugation of biomolecules [26].

122 Traditionally MNPs are synthesized by co-precipitation, hydrothermal, solvothermal,
123 sonochemistry, reverse microemulsion, and thermal decomposition techniques [10]. In recent
124 times, microfluidic and biogenic synthetic methods have been developed as novel approaches for
125 MNPs. Microfluidic systems offer a large number of benefits namely automation, process
126 screening, and constant synthesis. It provides control over reaction time, temperature, and
127 concentration, in addition to the final size, shape, and uniformity of MNPs [27]. However,
128 biogenic methods provide control over nanoparticle's size and shape through biological routes of
129 the organism, or biomineralization. Though, biogenic synthesis still suffers from low yields [28].
130 Dimensions, morphology, and charge on the MNPs surface could be tuned according to
131 numerous cancer therapeutic applications [29]. Ultimate charges on the surface of synthesized
132 MNPs are utilized used to attach nucleic acids to them electrostatically or increase circulation
133 times [30]. Mostly MNPs with spherical morphology is used in cancer treatment, but few
134 investigations have been conducted using different morphologies such as nanocubes or hollow
135 rods. During the last few years, MNPs especially IONPs gained incredible importance in cancer
136 therapeutics through drug/gene delivery, hyperthermia, radio- and immune- therapy. MNPs are
137 excellent nanomaterials owing to their high magnetic moments, superparamagnetism, magnetic
138 anisotropy, irreversibility regarding high-field magnetization, large surface area, magnetothermal
139 effect, and idyllic biocompatibility [31]. Furthermore, MNPs are present in different constructs:
140 single-phase particle form, core-shell comprising core with polymer coating, multicore, or
141 leaning chain arrangements [32]. A high aspect ratio concerning MNPs is favorable for cellular
142 internalization and surface functionalization, that permits high deformability and prolonged
143 bloodstream circulation time [33].

144 Among various magnetic configurations accessible for multipurpose cancer therapy, MNPs are
145 mainly designed with core shell morphology that sustains therapeutic and targeting and moieties.

146 Cancer therapeutic through MNPs also depends on shell functionality that not only protects the
147 core but also overcome limitations regarding immunogenicity and biocompatibility. Delivery of
148 drugs through MNPs systems have been an effective approach for cancer therapeutics due to the
149 tunable physicochemical characteristics of MNPs [26]. They can be fabricated to instruct
150 functionality for therapy for instance conjugation of bio/chemotherapeutics non-covalently or
151 covalently enhances biocompatibility and systemic circulation, employing active and passive
152 targeting mechanisms to the therapeutic site [34]. Immunotherapy to treat cancer utilizes the
153 patient's immunity system for identifying cancer cells, constraining their proliferation, and
154 attacking solid tumors even directly. Combining it with MNPs provides advantages such as
155 targeted delivery that can be tuned to have the required shape, size, charge, and modifications for
156 maximum delivery efficiency [35]. In addition, MNPs generate heat by thermal fluctuations of
157 spins in an AC magnetic field (hyperthermia), by irradiation with light (photothermal therapy),
158 or by conjugating it with photosensitizing agents (photodynamic therapy), which is used for
159 thermal ablation of cancer cells [36]. This heat is transferred to the cells and raises the
160 temperature of cancerous cells more than normal cells and causes death of cancerous cells [37].
161 The same heat can be used to control the release of drugs encapsulated in magnetic
162 nanocomposites with light or temperature responsive polymer coatings. Magnetic based cancer
163 theranostics is the integration of numerous moieties in single platform that could provide
164 influential paradigm designed for effectual treatment of cancers [38]. MNPs provide a way to
165 track the location of therapeutic agents or target the site by applying external magnetic field, to
166 control therapy process continuously, and ultimately evaluate efficacy of treatment [39].

167

168 **3. Applications of magnetic nanoparticles (MNPs) in cancer therapeutics**

169 MNPs are been permitted by FDA (Food and Drug Administration) as contrast agent (CA) in
170 MRI, to treat iron deficiency, bio-therapeutic transport, as transporter for drug regarding
171 magnetic targeted therapy in various parts of body, in hyperthermia, and photo-dynamic and -
172 thermal therapy [26]. Cancer therapy through diagnosis and monitoring depends on imaging or
173 using chemo/bio therapeutic agents for instance drugs, proteins, and nucleic acids. A tumor with
174 a clear image is beneficial to know the response of the patient when it is removed surgically and
175 further treatment is suggested. For imaging, CT scans (computerized tomography), magnetic
176 resonance imaging (MRI), echography, X-ray radiography, and PET (positron emission
177 tomography) are employed [7]. Amongst them, MRI possesses a strong effect in timely cancer
178 diagnosis, and SPIONs are the most effective contrast agent for MRI in comparison to other
179 contrast agents (for instance gadolinium-based contrast agents) because of their facile and
180 controlled synthesis regarding size and shape, easy surface decoration, low toxicity, good
181 biodegradability, reduced risk of accumulation, and tissue damage during MRI [40]. Presently
182 gadolinium-based contrast agents (GBCAs) are mostly used in clinical trials. However,
183 gadolinium is toxic to humans in its free form (Gd^{3+}). Free gadolinium is excreted very slowly
184 owing to its insolubility at physiological pH, and has an ionic radius close to calcium allowing it
185 to compete with it various physiological processes [41]. As a result, GBCAs remain in the body

186 for a long time, increasing their probability to dissociate and deposit in the body. IONPs based
 187 contrast agents were chosen over gadolinium-based contrast agents due to their low toxicity and
 188 researchers have found that they can produce similar MRI contrast with SPIONs [42]. The
 189 literature results show clinical research on SPIONs remains robust, particularly fuelled by the
 190 approval of ferumoxytol for intravenously administration. SPIONs have been tested on MR
 191 angiography, sentinel lymph node detection, lymph node metastasis evaluation; inflammation
 192 evaluation; blood volume measurement; as well as liver imaging. The risk of accumulation and
 193 tissue damage is reduced when compared to GBCAs. Therefore in comparison to GBCAs,
 194 SPIONs are the most effective contrast agents for MRI [43]. MNPs for drug delivery
 195 applications are impossible to be unobserved. They are employed to carry drug carriers via
 196 attaching chemotherapeutic drugs or antibodies. Usually, MNPs are loaded with
 197 chemotherapeutic drugs for cancer therapy. MNPs for cancer therapy are typically employed in
 198 numerous ways to attain an enhanced therapeutic efficiency, integrated with chemotherapy,
 199 radiotherapy, magnetic hyperthermia, photothermal therapy (PTT), and photodynamic therapy
 200 [44]. An immediate treatment observation is possible by specific integration of various drugs
 201 with SPIONs that have revealed encouraging potential providing adaptable and sensitive
 202 platform for point-of-care (POC) therapeutic applications. SPIONs can be injected immediately
 203 into infected tissue, controlled by magnetic field, externally applied for generating heat with aid
 204 of Néel and Brownian relaxation processes [45,46]. The section discusses the MNPs employment
 205 for cancer therapeutics. Table 1 summarizes some of the information about magnetic
 206 nanocomposites in cancer treatment.

207 **Table 1.** Different magnetic nanocomposites for cancer treatment

Type of MNP	Size	Therapeutic applications	Ref
Iron oxide nanoparticles	10-100 nm	Breast, epithelial colorectal cancers	[47-49]
SPIONs	10-50 nm	Breast, brain, prostate, and lung cancers	[50,51]
Bismuth-iron oxide nanoparticles	55- 150 nm	Breast cancer	[52-54]
Silica-coated iron oxide nanoparticles	150-170 nm	Liver and breast cancers	[55,56]
Iron oxide/gold nanocomposites	50-70 nm	Breast cancer	[57-59]
Zinc oxide/iron oxide nanocomposites	20-80 nm	Breast cancer	[60,61]

Graphene oxide/iron oxide nanocomposites	100-300 nm	Breast, liver, cervical, and blood cancer	[62-65]
---	------------	--	---------


208

209 **3.1. Chemotherapy**

210 MNPs conjugation with chemotherapeutic drugs for obtaining nanosystems for
211 delivery possesses numerous benefits counting magnetic targeting, magnetic thermotherapy, *in*
212 *vivo* imaging, and collective delivery regarding chemotherapeutic agents. To increase drug
213 targeting efficiency further for chemotherapy via MNPs, particularly SPIONs [66], other
214 targeting molecules comprising antibodies, transferrin, aptamers, folate, hyaluronic acid, and
215 targeting peptides can be coated on SPIONs surface [67]. Magnetic nanoparticles have been
216 widely studied and gradually emerged as another method of tumor treatment, having great
217 potential to assist in the treatment of cancers, especially liver, breast, prostate, and pancreatic
218 cancers [68]. There is no continuous optimization in the treatment process. Magnetic carriers
219 possessing therapeutic doses regarding adsorbed Tc99, doxorubicin, and paclitaxel, have been
220 investigated for cancer treatment [69].

221 Polydopamine (PDA)-coated MNPs modified by SH- β CD (mono-6-thio- β -cyclodextrin) were
222 prepared and loaded with doxorubicin. Cellular internalization of the prepared particles in liver
223 cancer was imaged by confocal microscopy. The developed nanomaterials with
224 chemotherapeutic drug and PDA layer could absorb NIR (near-infrared) light. They showed
225 significant effectiveness in a combined photo, chemo, and thermal treatment of liver cancer.
226 Furthermore, they also exhibit enhanced T2 contrast, verified by MRI of these nanoparticles.
227 Consequently, the prepared nanomaterial is an effective nanosystem having significant
228 theranostic potential [70]. A multimodal nanoplatform to treat hepatocellular carcinoma (HCC)
229 *in vitro* was developed. The nanoplatforms were based on polydopamine (PDA)-coated Fe₃O₄
230 nanoparticles and spheres (sMAG) with PAMAM dendrimers and functionalized with NHS-
231 PEG-Mal (N-hydroxysuccinimide–polyethylene glycol–maleimide) linker that permits their
232 functionalization with a folic acid derivative. The nanomaterials with folic acid-targeting moiety
233 displayed high efficiency in killing cancer cells in the dual chemo- and photothermal therapy
234 (CT-PTT) of the liver cancer cells as compared to modalities implemented separately. Materials
235 have activity comparable to free doxorubicin (DOX) with a concentration above 10 μ g/mL. It is
236 worth mentioning that a functionalized magnetic sphere with DOX more intensely affected the
237 HepG2 cells than smaller functionalized nanoparticles with DOX in the performed chemotherapy
238 [71]. In another work multifunctional nanocarriers based on PAMAM dendrimers generation (G)
239 4.0, 5.0 and 6.0 fixed to polydopamine (PDA) coated Fe₃O₄ nanoparticles were synthesized and
240 applied in combined chemo- and photothermal therapy (CT-PTT) of liver cancer cells. The
241 combined effect of the above-mentioned modalities results in higher mortality of cancer cells in
242 contrast to their individual performance. Additionally, *in vitro* studies exposed that dual therapy
243 was more effective in triggering desired cell death mechanism apoptosis. The integration of
244 MNPs with dendrimers increases the functionality of dendrimers leading to hybrid

245 multifunctional nanostructures that are promising smart drug delivery systems to treat cancer
 246 [72]. Nanocarrier dextran/polylactic acid (DEX/PLA) and Fe_3O_4 (magnetite) nanoparticles
 247 carrying the drug were prepared for improving DOX targeting in the treatment of liver cancer
 248 and decreasing its possible toxicity to organs. Drug release from prepared nanoparticles inside
 249 the body was carried in different pH solutions. The drug is released rapidly in first 24 hours and
 250 successive release was slow (Figure 1). At the same time, release of the drug in acidic medium is
 251 better from nanoparticles compared with free drug. As cancerous tissues have acidic
 252 surroundings, drug can precisely reach cancerous site and inhibit its growth. The *ex vivo* besides
 253 *in vivo* results found prepared nanocarriers have intense targeting regarding liver cancerous
 254 tissue and could be applied in targeted therapy providing a novel approach for clinical therapy
 255 regarding liver cancer [73].
 256



257
 258 Figure 1. Releasing ability of drug from magnetite nanoparticles loaded with drug (DOX) at (a)
 259 pH of 4 (b) pH of 6.28, and (c) pH of 7.4. Reprinted with permission from the reference [73].
 260

261 Magnetite (Fe_3O_4) nanoparticles covered by HPG (hyperbranched polyglycerol) along with FA
 262 (folic acids) loaded with curcumin were prepared to treat cervical cancer. Functionalized
 263 nanoparticles ($\text{FA@HPG@Fe}_3\text{O}_4$) aggregates less compared with non-functionalized
 264 ($\text{HPG@Fe}_3\text{O}_4$) nanoparticles. These nanoparticles showed maximum loading capacity for drug
 265 found to be equal to 82 and 88%, respectively. Functionalized nanocarriers were captivated by
 266 L929 mouse fibroblasts as well as HeLa cells more as compared to $\text{HPG@Fe}_3\text{O}_4$ nanoparticles.
 267 Thus they have potential to be engaged within systems regarding delivery of drugs for cancer
 268 treatment. For diagnosis, HeLa cells incubation with prepared nanoparticles reduces MRI signal
 269 intensity and biggest variation was perceived after their incubation with functionalized
 270 nanoparticles [74]. Paclitaxel (PTX) is a strong chemotherapeutic drug to treat solid advanced
 271 carcinomas. Yet, its limited medical consumption is due to its poor solubility in water. A
 272 formulation (NP-PTX-FA) involving core of SPIONs coated with polyethylene glycol to
 273 conjugate hydrophobic PTX and folic acid (FA). This formulation targets breast cancerous cells
 274 and permits controllable PTX release. NP-PTX-FA holds high capacity regarding drug loading
 275 equals to 22.8 wt%. Drug is released in acidic conditions similar to intracellular pH concerning

276 breast cancerous cells. FA bonding results in higher uptake by target sites, increasing
277 cytotoxicity, compared with free drug, to target cells. This formulation possesses significant
278 perspective for improving therapy regarding breast cancer as well as potential for delivering
279 hydrophobic drugs to treat different types of cancer [75]. A versatile nanocomposite was
280 designed to target breast cancer. It comprised of docetaxel (DXL), polyvinyl alcohol (PVA)
281 network intended for controllable release, and silica-coated MNPs for targeted delivery. The
282 developed nanocomposite is directed magnetically for cancer therapy. 10% DXL loaded into
283 pH/thermal PVA responsive gel. 96 % DXL is selectively released through interaction of green
284 and near-infrared (NIR) light and caused 75% of cell death in *in vitro* studies. 70% growth
285 inhibition regarding tumor was displayed by *in vivo* experiments with biosafety investigations
286 verifying less adverse side effects to other organs [76].

287 An innovative thermal/pH responsive amphiphilic copolymer comprising magnetite
288 nanoparticles with biodegradable and hydrophobic block of PLA and hydrophilic P(NIPAAm-
289 co-HEMA-co-MAA-co-TMSPMA) section had been developed for combined chemotherapy.
290 Cationic (doxorubicin) and anionic (methotrexate) anti-cancerous drugs were loaded
291 instantaneously to nanoparticles for combined cancer therapy. Efficiency of encapsulation
292 regarding DOX was 95.04% and for MTX was 97.29%. Double profile related to release of
293 drugs exposed tumor aided release behavior. They are non-toxic to MCF-7 cell lines shown by
294 cytotoxicity studies. Antitumor characteristics concerning DOX/MTX-loaded nanoparticles were
295 considerably greater than free drugs verified via MTT analysis and immediate analysis by PCR
296 consuming cell MCF7 lines. Consequences showed that such engineered particles possibly are
297 efficiently consumed in directed DOX as well as MTX delivery to cancerous sites besides for
298 more usages in *in vivo* applications [77].


299

300 **3.2. Immunotherapy**

301 Cancer immunotherapy is leading-edge approach eliminating cancerous cells via increasing
302 immunity of host. Conversely, low rate of response along with risks of persuading toxicity
303 elevated improbability in therapy. MNPs are multipurpose theranostic device used for targeted
304 delivery concerning numerous immunotherapeutics in addition to observe cell/tissue reactions.
305 Immunotherapy inhibits tumor resistant elusion demonstrates noteworthy clinical realization.
306 Though, therapeutic reaction is inadequate to definite number of patients, and immunotoxicity in
307 addition to autoimmunity are bargained therapeutic advantages [78].

308 Immunotherapy for cancer has appeared as extremely hopeful therapeutic technique for a number
309 of cancers. Fucoidan and dextran based MNPs (IO@FuDex₃) were linked with anti-PD-L1
310 (checkpoint inhibitor) and anti-CD3 also anti-CD28 (T-cell activators). They possess ability to
311 repair immunosuppressive cancer microenvironment via reviving tumor sensitive lymphocytes.
312 Off targets impacts can be minimalized via magnetic navigation regarding tumor. Therapy that
313 integrates IO@FuDex₃ with magnetic navigation decreases adverse happenings as well as
314 prolongs average survival from 32 days to 63 days with less than 1% dosage in comparison to
315 soluble anti-PD-L1. Therefore, incorporating T-cell activators and anti-PD-L1 with MNPs in

316 nanomedicine form enhance therapy index of immunotherapy [79]. A MNP delivery system was
 317 developed loaded with ICG (indocyanine green) and R837 (immunostimulator hydrochloride)
 318 aimed at spatial and temporal immunotherapy/PTT combination in cancer (Figure 2). It
 319 comprises core of magnetite nanoparticles to load ICG coated with layer of DPA-PEG
 320 (polyethylene glycol polyphenols) for loading R837, forming MIRDs. The developed MIRDs
 321 lead to prolong circulation, guiding agents for MRI, as well as magnetic targeting. MIRDs
 322 targeted towards tumors, on irradiation with near-infrared (NIR) triggered ablation of tumor and
 323 give rise to release of antigens related to tumor inducing immunological reaction. Here,
 324 combined PTT and immunotherapy repressed growth of tumors, metastasis, as well as recurrence
 325 that lead to effective anticancerous therapy along fewer adverse effects [80].



326
 327 Figure 2. MNPs functionalized by polyphenols aimed at spatial- sequential controllable
 328 immunothermal/phototherapy regarding cancer. Reprinted with permission from the reference
 329 [80].

330
 331 A biomimetic Fe_3O_4 (magnetite)-SAS(sulfasalazine)@PLT (platelet) are established as
 332 different method for sensitizing active ferroptosis and produce slight immunogenicity, improving
 333 rate of response regarding non-inflamed cancer aimed at immunotherapy. They activated
 334 ferroptotic cell death by preventing glutamate-cystine antiporter method Xc-path. It considerably
 335 increases effectiveness of planned cell death 1 immune checkpoint blockade treatment in
 336 addition to attaining constant elimination of tumor in model of mouse having metastatic 4T1
 337 tumors. Investigations performed in proteomics also exposed induction of immune reaction
 338 specific to tumor and efficient repolarization of macrophages from M2 immuno-suppressive
 339 phenotype into M1 antitumor phenotype. Accordingly, ferroptosis facilitated by Fe_3O_4 -
 340 SAS@PLT related to immunotherapy possess pronounced prospective for medical handling
 341 regarding tumor metastasis [81].

342 A simple system founded on combined stimulation of immunity and killing of cancerous cells
 343 directly via integrated TLR (Toll like receptor) ligation consuming R837 (imiquimod) as
 344 TLR7 agonist and polyIC as TLR3, with OVA (ovalbumin) and micelles of

345 phospholipids enclosing MNPs doped with zinc. TLR agonists activated immune reaction in LNs
346 (lymph nodes) with no pro-inflammatory cytokines release. It presented exceptional
347 effectiveness against violent melanoma B16-F10 cells testifying OVA had been enhanced by
348 immunity checkpoint abolition concerning immune-oppressive automated death-ligand 1 (PD-
349 L1) on cancerous cells. This vaccine can be tracked with magnetic field along with nuclear
350 imaging from injection site of injection to tumor and LNs. Generally, collective TLR agonists
351 with MNPs and immune obstruction have substantial probability aimed at preclinical as well as
352 clinical vaccines formulation for cancer treatment by immunotherapy [82]. Hollow magnetite
353 nanoparticles have also been employed for reprogramming M2 TAMs to M1 TAMs, intended for
354 releasing proinflammatory cytokines in addition to employee T cells for killing cancer cells.
355 MNPs were enclosed by poly (acrylic acid) (PAA) after being loaded by l-arginine (l-Arg). Then
356 they were modified as LPMNPs that has ability of releasing l-Arg depending on pH of PAA. *In*
357 *vivo* as well as *in vitro* investigations validate that the develop MNPs efficiently do the
358 reprogramming of M2 into M1 macrophages, triggering T cells, discharging TNF- α , besides
359 generating extraordinary NO, resulting in immunotherapy [83].

360


361 **3.3. Hyperthermia**

362 Hyperthermia is encouraging method to treat cancer. The usage of MNPs as heating mediators
363 delivers an innovative approach to improve treatment regarding tumor and, subsequently, quality
364 of patient's life [84,85]. In current clinical trials of hyperthermia using MNPs to treat tumors, AC
365 (alternating current) magnetic field of 100 kHz is safe to be applied on patient. Though,
366 systematic magnetic hyperthermia as temperature function on therapeutic efficacy is scarcely
367 examined [86].

368 MNPs coated by biocompatible poly-L-lysine had been developed aimed at magnetic
369 hyperthermia to determine their therapeutic efficacy. They were verified for hyperthermia
370 appropriateness via calorimetric estimations and SAR (specific absorption rate) was also
371 measured. SAR value at 8 kAm^{-1} field and 190 kHz frequency were 14 to 15 Wg^{-1} . These
372 particles were also tested in MRI. The heating characteristics along with parameters of MRI
373 possess pronounced ability for advancement of targeted cancer therapy in future [87]. A
374 magnetic guanidinylated chitosan (MGC) nanobiocomposite was designed and evaluated by *in*-
375 *vitro* hyperthermia for the cancer therapy. Size distribution of prepared composite was found to
376 be in between 30-34 nm during synthesis process with a core-shell structure. By using AC
377 magnetic field SAR and saturation magnetization value were 70.59 w/g and 43.66 emu/g
378 respectively [88].

379 *In vivo* as well as *in vitro* comparative analysis reliant upon temperature regarding effectiveness
380 concerning nanoparticles of cobalt ferrites was done in two models of murine tumors that is 4T1
381 (breast) and CT26 (colon) cancer. *In vitro* killing capacity by using these nanoparticles gets
382 increased with increase in temperature (Figure 3). CT26 cancer cells have more sensitivity than
383 4T1 on heating to $43 \text{ }^\circ\text{C}$. Similarly *in vivo* data also revealed curing of non-metastatic CT26
384 cells, whereas only preventing growth of metastatic 4T1 tumor with no improvement of complete

385 survival. Higher temperature that is greater than 47 °C lead to whole clearance of 4T1 primary
 386 tumor, 25 to 40% prolong rates of survival, in addition to active inhibition concerning metastasis
 387 compared with surgical abstraction. Therefore, particular temperature should be well-defined for
 388 ensuring positive antitumor therapy [89].
 389



390
 391 Figure 3. MNPs prevent primary growth of tumor in addition to metastases propagation through
 392 temperature-controllable hyperthermia. Reprinted with permission from the reference [89].
 393

394 Cancer cells possess distinctive metabolic feature that had been explored for biosynthesizing
 395 MNPs for possible hyperthermia uses. Cancerous cells were mixed mixture of zinc gluconate and
 396 FeCl₂ that significantly increase intracellular iron and zinc measure inside cells. There is rise in
 397 temperature after thirty minutes exposure to alternating magnetic field. Nanoparticles of iron and
 398 zinc oxide were formed. MNPs are SPIONs with magnetite and maghemite mixture. Optimizing
 399 conditions for treatment lead to a rise in temperature of about 5 to 6 °C on applying magnetic
 400 field to treated cells. The simple treatment procedure, cell specificity able to synthesize SPIONs,
 401 and hyperthermia perceived in cancerous cells specified a hopeful approach towards achieving
 402 operative hyperthermia aimed at cancer therapy [90]. Ultrasmall SPIONs (USPIONs) are
 403 prepared via single-step method. Discrete nanoparticles were separated from unstable
 404 agglomerated nanoparticles by post-synthetic purification, resulting in USPIONs preserving
 405 colloidal and chemical stability for long time. The improved nanoparticles displayed higher
 406 saturation magnetization along with better heating efficacy for hyperthermia measurements.
 407 Unusually, these nanoparticles showed notable double T1/T2 signal improvement, therefore
 408 could be employed as MRI contrast agents. Such encouraging results established that these
 409 nanoparticles are outstanding candidates to develop theranostic nanosystems having potential in
 410 hyperthermia and imaging applications [91]. A three dimensional cross-linked chitosan hydrogel

411 was fabricated consuming chitosan polymeric chains and synthetic terephthaloyl
412 diisothiocyanate. It had high stability and uniformity in aqueous solution and high porosity was
413 applied as new substrate to generate novel nanocomposite comprising magnetic terephthaloyl
414 thiourea cross-linked chitosan and evaluated for hyperthermia process. The size distribution of
415 nanocomposites was estimated in between 30 to 40 nm. Under AC magnetic field, the SAR was
416 found to be 66.92 w/g with saturation magnetization of 78.43 emu/g [92]. A novel magnetic
417 nanocomposite made of aromatic polyamide was investigated in hyperthermia aimed at cancer
418 therapy. The magnetite nanoparticles were modified by phenylenediamine derivatives and
419 terephthaloyl chloride via polymerization reaction. Exceptional morphologies of rose flower and
420 spheres were observed of the developed nanocomposites. On exposure to external AC magnetic
421 field, SAR was measured was 191.97 w/g for 0.5 mg/mL of a sample, with saturation
422 magnetization of 4.3 emu/g [93].


423 Hydrophilic surface modified SPIONs were prepared to treat liver cancer by hyperthermia.
424 Short-chain molecules, for instance 4-aminobenzoic acid (4ABA), 1,4-diaminobenzene
425 (14DAB), plus 3,4-diaminobenzoic acid (34DABA) along molecules of terephthalic acid
426 (TA)/2-aminoterephthalic acid (ATA)/trimesic acid (TMA)/pyromellitic acid (PMA) were used
427 to functionalize SPIONs. Heating abilities of SPIONs were evaluated by calorimeter regarding
428 their surface coatings, concentrations, medium for dispersion, besides applied alternating
429 magnetic fields. All SPIONs were superparamagnetic in behavior, but SPIONs coated
430 with 14DAB- 4ABA-, 4ABA-TA-, and 34DABA- displayed greater magnetization ($M_s = 55$ to
431 71 emu/g) with good dispersibility in water. 34DABA-coated SPIONs exposed rapid thermal
432 reaction on applying magnetic field and extended therapy temperature to low concentration
433 equals to 0.5 mg (mL)⁻¹ in comparison to 4ABA-, 14DAB-, and 4ABA-TA-coated SPIONs.
434 Furthermore, 34DABA-coated SPIONs showed great heating efficiencies with SAR of 432.1
435 W/g and killing efficacy of about 61 to 88% in liver HepG2 cancer cells in comparison to
436 water/magnetic field based thermotherapy. Thus, 34DABA-coated SPIONs are favorable heating
437 mediators for hyperthermia and could be utilized as operative nanomedicines aimed at treatments
438 of cancer [94]. The thermal reaction of tumor tissue to hyperthermia depends on the MNPs
439 configuration setup along with its different parameters. Injection approach effects mass transfer
440 during treatment, which is related to the success of hyperthermia cancer treatment. In one of the
441 study mechanical response of tumor tissue to single and three site injections was compared. The
442 results indicated that increasing injection sites enhances heat and mass transfer fluxes slightly;
443 but more expressively influenced by rate of injection. The three-point injection improved
444 distribution of nanoparticles and heat uniformly, which increased tissue damage and reduced the
445 risk of tissue necrosis [95].

446

447 **3.4. Radiotherapy**

448 Tumor radio-sensitization could possibly get improved by integrating classical radiotherapy with
449 various drugs or MNPs. Currently, MNPs are being investigated to be applied in radionuclides
450 delivery, α - or β - emitters, as well as radiosensitizers for inducing damage to DNA of cancerous

451 cells by generating ionic radiation or free radicals [96]. They propose distinctive benefits over
452 existing radiotherapy practices via decreasing damage to off-target tissues because of non-
453 particular treatment nature via active and passive targeting [97]. Additionally, MNPs holds high
454 atomic number (Z) as well as display significant absorption of X-ray photons, resulting in
455 increase in production of secondary electrons for DNA destruction on increasing dose of
456 radiations. SPIONs enhance radiotherapy effectiveness and specificity regarding DNA
457 destruction via catalyzing production of ROS through ionizing rays causing considerably strong
458 oxidative pressure, particularly hydroxyl radicals which destroy DNA of cells [98,99].
459 Currently, MNPs coated with gold (Au@IONPs) gained significant consideration towards cancer
460 therapeutics. *In vitro* studies were carried out to find out anti-cancerous impact regarding
461 Au@IONPs nanoparticles with core-shell morphology in thermo-radiotherapy. Furthermore,
462 apoptosis level stimulated in glioma U87-MG human cells was examined after getting combined
463 therapy (hyperthermia + Au@IONPs + radiotherapy). After incubating nanoparticles with cells,
464 hyperthermia was done for one hour (43 °C) and after that they were instantaneously exposed to
465 6 megavolts of X-ray. The MTT results showed no substantial cytotoxicity regarding
466 nanoparticles at below concentration of 10 µg/mL and also enhanced cytotoxic effect concerning
467 radiation and hyperthermia was observed. Reason of cell death had been apoptosis due to
468 combined effect of nanoparticles, radiation, and hyperthermia on cancerous cells. Thus, prepared
469 nanoparticles are good radio-thermo-sensitizer that activates noteworthy apoptosis levels for
470 cancer treatment [100]. A novel platform based on MNPs modified with cationic polymer for
471 promoting radiotherapy to treat glioma. Modified MNPs induced cytotoxicity to in glioma cells
472 on radiations besides encouraging substantial survival advantages in athymic and
473 immunocompetent mice having glioma. Taking advantage of magnetic features of MNPs, it was
474 discovered that nanoparticles were taken up by MDSC (myeloid derived suppressor cells) inside
475 tumor of brain. Efficiency of nanoparticles was estimated by glioma cells destructions in addition
476 to repolarization of MDSCs from immuno-suppressive to pro-inflammatory phenotype that
477 helped antitumor impact as well as radio-therapeutic impacts synergistically (Figure 4). These
478 nanoparticles offers fast targeting dual platform aimed at radiotherapy of glioma through
479 immediate tumor abolition and management of myeloid phenotypes in central nervous system
480 [101].



481
 482 Figure 4. MNPs resulting in extreme cytotoxicity specific to cancer. MDSCs, incompletely
 483 exposed in addition to repolarized in M1-like phenotype producing anti-cancerous impact after
 484 radiation therapy along with MNPs. The combined influence showed positive efficacy. Reprinted
 485 with permission from the reference [101].

486
 487 Magnetite nanoparticles coated with PEG are favorable candidate as radiation sensitizer for
 488 radiotherapy. They improved cancer therapy and decreases adverse impacts regarding radiations.
 489 On exposition to radiations surface coating of PEG possibly be fully or partially destroyed. This
 490 makes iron ions more accessible and perform as a catalyst to produce ROS species that improves
 491 the cancer radiation therapy. Cytotoxicity studies revealed percentage killing of cells employing
 492 Fe_3O_4 coated with PEG is greater for MCF-7 in comparison with L929. However, percentage
 493 with bare MNPs is greater for both when compared with PEG coated MNPs. Thus, PEG coating
 494 enhanced biocompatibility of MNPs that makes them appropriate for radiotherapy and also
 495 upholds innovative opportunities in field of cancer radiotherapy for improving clinical
 496 effectiveness in dissimilar cancer types [102]. MNPs conjugated with quercetin (QMNPs) were
 497 prepared to investigate their sensitivity towards breast cancer in radiotherapy treatment. *In vitro*
 498 results presented that HePG-2, MCF-7, and A459 cancerous cells incubation along these
 499 nanoparticles effectively for twenty-four hours prevented cancerous cell growth depending on
 500 concentration with values of IC_{50} equal to 77.5, 11, and $104 \text{ nmol}(\text{mL})^{-1}$, correspondingly.
 501 Irradiation (IR) coupling with QMNPs powerfully blocked proliferation of MCF-7 cancerous
 502 cells. QMNPs had no toxicity assessed by renal, hepatic, and hematological markers. In addition,
 503 in white albino female rats, they prevented cancer growth and persuasively improved adjacent
 504 radiotherapy inside MNU (N-methyl-N-nitrosourea) prompted breast cancer. Such radio-
 505 sensitizing along anti-cancerous happenings had been because of immunomodulation, cell cycle
 506 detention, cytotoxicity, in addition to effectiveness by apoptosis generation. Conclusively, MNPs
 507 with radiotherapy possess prospective targeted therapy for treating breast cancer [103].
 508 SPIONs have demonstrated fascinating characteristics beneficial for diagnostic and therapeutic
 509 application. Radio-sensitizing properties regarding SPIONs in brachytherapy and electron beam

510 radiotherapy had been investigated. *In vitro* investigations were performed consuming HeLa
511 cells with SPIONs. Irradiations doses ranged from 0 to 10 Gy were done by 0.38 MeV ¹⁹²Ir
512 brachytherapy as well as electron beams of 6 and 12 MeV energy. Radio-sensitization
513 classification was done through evaluating improvement in ratio of sensitization (SER), gained
514 from survival loops. Results showed SPIONs encourage radio-sensitization in electron beams
515 particularly at low energy having value of SER of 1.5. It is further noticeable in brachytherapy
516 having SER of 2. High concentration of SPIONs is increases radio-sensitization impacts more. In
517 summary, radio-sensitization is influenced by energy of radiation as well as SPIONs
518 concentration. Additional categorization concerning radio-sensitization persuaded by SPIONs
519 might permit medical translation regarding SPIONs as per radio-sensitizer for radiotherapy
520 [104].


521

522 **3.5. Gene therapy**

523 Gene therapy signifies a different substitute to manage diseases with no adequate cure. Gene
524 therapy to treat cancer made good progress in the last three decades. Comparatively gene therapy
525 has better safety with tolerable adverse effects than chemotherapy for the treatment of cancer
526 [105]. The major dissimilarity between gene therapy and chemotherapy is that in chemotherapy
527 drugs are being delivered, whereas in gene therapy targeted biological moieties for instance
528 RNA, DNA, or else siRNA, peptides, and proteins are been delivered to cancer site, and by this
529 manner death of the cells possibly is induced. When one part of the body has cancer, human
530 damaged DNA is categorized by presence of atypical proteins. This could be treated by replacing
531 defected gene in cancer cells [106]. On the other hand, siRNA suppressed protein activities,
532 occurring because of cancer cells. siRNA integrated with nanoparticles could be carried and
533 delivered to cells, since medicinal RNA are very degradable when injected directly in
534 bloodstream. siRNA-MNP complex becomes practically unidentifiable for human body. Their
535 cellular uptake gets improved with longer circulation time. Because of vascular nature of tumor,
536 MNPs enter and accumulates in tumor [107].

537 Magnetite nanoparticles coated with polydiacetylenes ($\text{Fe}_3\text{O}_4\text{@PDA}$) possess better
538 photothermal ability and could be applied for efficient loading and delivery of siRNA. They are
539 further coated with mesenchymal stem cells (MSCs), forming membrane. $\text{Fe}_3\text{O}_4\text{@PDA}$ -
540 siRNA@MSCs (MSCs membrane with nanoparticles of $\text{Fe}_3\text{O}_4\text{@PDA}$ -siRNA) conserved
541 photothermal effectiveness besides MRI ability received from nanoparticles of $\text{Fe}_3\text{O}_4\text{@PDA}$.
542 Prepared nanocomposites displayed unique capabilities to deliver siRNA to cells (DU145).
543 Additionally, they deliver siRNA opposing gene Plk1 restricts endogenous gene Plk1 expression
544 in addition apoptosis in cells DU145. Combined photothermal therapy with gene silencing
545 presented clear antitumor efficiency in xenograft DU145 mice model. Primary *in vivo* and *in*
546 *vitro* examinations revealed that the developed nanocomposites have substantial potential as
547 carrier aimed at photothermal and gene therapy [108]. Suicide-gene therapy is hopeful method to
548 treat uterine leiomyoma (UL), tumor occurring in women categorized via specific localization.
549 The competence regarding $\alpha\beta 3$ integrin-targeted arginine-rich peptide carrier R6p-cRGD

550 attached electrostatically to MNPs aimed at targeted delivery of DNA to UL cells. MNPs
 551 addition caused decrease in required time for fruitful transfection by immediate escalation in
 552 efficacy. After plasmid delivery, therapeutic impact onto prime UL cells was evaluated. It
 553 encodes simple herpes virus 1 (HSV-1) thymidine kinase gene. Treating by ganciclovir,
 554 increases efficiency to twenty percent in suicide-gene treatment inside UL cells introduced by
 555 pPTK-1 plasmid. Finally, consumption of MNPs with cationic peptides are promising carriers to
 556 develop non-viral modular carriers aimed at suicide-gene delivery in UL cells [109].
 557 Magnetically mediated suicide-gene therapy is favorable for suicide gene therapy. M-MSNs
 558 comprising MNPs with nanoparticles of mesoporous silica were synthesized. Then carboxyl-
 559 modified M-MSNs had been loaded with PEG-g-PLL and GCV. After that they were attached to
 560 M-MSNs surface that offered positively charged surface for absorption of TK plasmid (Figure
 561 5). They were evaluated for their role in MRI, magnetically targeted as well as hyperthermia-
 562 assisted suicide gene therapy of hepatocellular carcinoma (HCC). Rod-shaped MSNs showed
 563 greater capacity for loading, rapid release of pro-drug, improved magnetic gene delivery, in
 564 addition to enhanced hyperthermia in comparison with spherical MSNs. M-MSNs showed
 565 extremely active double magnetic improved *in vivo* suicide-gene therapy along reduced
 566 methodical toxicity. It also has capability for monitoring therapy outcome via MRI. Attributed to
 567 magnetic targeting and hyperthermia, developed M-MSNs are possibly better candidate aimed at
 568 HCC suicide gene therapy [110].



569
 570 Figure 5. M-MSNs aimed at suicide-gene therapy regarding hepatocellular carcinoma cells
 571 mediated magnetically. Reprinted with permission from the reference [110].
 572

573 SPIONs functionalized with galactose (Gal) and polyethylenimine (PEI) bonded siRNA tightly,
 574 defend siRNA from nuclease decomposition in system. Encapsulation of siRNA with SPIONs
 575 prolongs its half-life and its transfection in cancerous cells with no *in vitro* cytotoxicity. Also,

576 encapsulated siRNA can be accumulated instantaneously, precisely target siRNA to targeted
577 cells, prolonging time of siRNA in tumor in addition to inhibition of growth of tumor.
578 Consequently, it provides a newfangled targeting approach to liver cancer therapy. The
579 developed nanoparticles hold pronounced potential for gene therapy of tumor [111]. In another
580 work, MNPs (magnetite) functionalized with polyethyleneimine (PEI) were synthesized for
581 delivering siRNAs targeting BCL2 (B-cell lymphoma-2) and BIRC5 (Baculoviral IAP repeat-
582 containing 5) to oral Ca9-22 cancerous cells aimed at therapeutics. Nanoparticles blocked siRNA
583 depending on concentration analyzed via gel retardation. Higher gene silencing efficacies were
584 observed through measurable immediate western blotting and PCR. Additionally, the developed
585 nanocomplex delivering siRNAs to target BIRC5 and BCL2 inhibit considerably Ca9-22 cells
586 migration and viability. Thus developed siRNA-based approach was novel and promising
587 therapy to target BIRC5 and BCL2 regarding oral cancer [112]. A new approach was developed
588 towards RNA interference therapy of glioblastoma multiforme based on MNPs delivery of
589 double-stranded RNA (dsRNA) with homological sequences to mRNA of tenascin-C (TN-C),
590 named ATN-RNA. Polyethyleneimine (PEI) coated MNPs conjugated to dsRNA were
591 synthesized that showed high efficiency in ATN-RNA delivery. These nanocomposites results in
592 significant suppression of TN-C expression level and weakened migration of the tumor cells.
593 Furthermore, developed nanocomposites possess high contrast characteristics in magnetic
594 resonance imaging (MRI) and less cytotoxicity combining with lack of induction of interferon
595 response. This work is an effective combination of functional and non-immunostimulatory
596 dsRNA delivery system based on MNPs with high prospective for further application in
597 Glioblastoma multiforme (GBM) therapy [113].

598


599 **4. Advantages and limitations of magnetic nanoparticles for cancer therapy**

600 MNPs are amongst widely investigated nanostructured material, by reason of their possible
601 usages in different research fields wavering from data storing to catalyzing applications,
602 including cancer detection and therapy [114,115]. MNPs have many benefits, particularly high
603 ratio to surface area to volume, size of pores, modified surfaces, more than one interaction or
604 binding sites, making them greatly appropriate to be utilized for treatments of diverse diseases
605 [116].

606 Moreover, MNPs holds benefit over substitute metallic nanoparticles due to their control in size,
607 definite interaction as well as dispersion, prevention of accumulation via coating, in addition to
608 permeation of tissue and cell barriers [66]. Generally, MNPs attained substantial consideration
609 attributed to their exclusive behavior, configuration, and differentiated applications. In particular,
610 their separate magnetic characteristics and variable size, ease of functionalizing surface by
611 different molecules, compatibility with various cell and biomolecules, inductive magnetic
612 moment, chemical constancy holding enlarged surface area, large magnetic susceptibility,
613 besides superparamagnetism [117].

614 One of the major limitations in employing MNPs in therapeutic applications is impossibility to
615 concentrate them in 3-D (three-dimensional) area. Since by applying magnetic field externally,

616 MNPs organizes in 2-D (two-dimensional) space [118]. Furthermore, to retain MNPs in the
 617 targeted region is difficult after the removal of magnetic field. Another problem is related is time
 618 of exposure to applied magnetic field, it is not possible to expose patients for unlimitedly
 619 external magnetic field. This all reduced therapeutic effectiveness and limits it to intensity,
 620 frequency, as well as exposure time of applied field [24]. Toxicity of MNPs depends mainly on
 621 administration method, surface chemistry, biodegradability, etc. Normally shape, composition,
 622 surface area, coating, and dimensions MNPs are considered to determine cytotoxicity. MNPs
 623 functionalization is vital for confirming minimum toxic impacts [119]. In some cases, controlled
 624 release of ions for instance, cobalt ions from MNPs surface is helpful and can be consumed as
 625 toxic agents for cells, like chemotherapeutic drugs [120]. Therefore a comprehensive valuation
 626 regarding therapeutic and safety efficiency concerning MNPs must be executed before any
 627 treatment for clinical usage [121]. Another issue is lasting effects of MNPs inside the body.
 628 Commercially available MNPs are not biodegradable and their prolonged accumulation in tissues
 629 can be dangerous for healthy cells. It is important to know how MNPs interacts with cancerous
 630 and healthy cells in human body as well as their excretion [115,122].
 631 SPIONs (superparamagnetic iron oxide nanoparticles) accumulation becomes unstable inside
 632 biological medium or solutions that are same as body fluids [123]. They possess diverse adverse
 633 effects, for instance deterioration in functioning of brain, liver, skin, stomach that might persist
 634 for ten years [124]. MNPs faced different physiological barriers lessening therapeutics
 635 localization at targeted site, which limit their use in cancer theranostics. Another limitation is
 636 particular targeting to cancer bearing site that reduces dosage and effectiveness regarding MNPs
 637 [125]. Few of the advantages along with disadvantages are illustrated in Figure 6.



638
 639 Figure 6. Some of the advantages and disadvantages regarding MNPs.
 640

641 **5. Conclusions**

642 Magnetic nanoparticles are being extensively explored for cancer therapeutics in combination
 643 with various therapies. Different MNPs are synthesized and functionalized with various coatings
 644 to enhance non-toxicity, biocompatibility, safety, bio-distribution, stability, etc. Massive
 645 consideration to MNPs was had been given because of their utilization in primary cancer

646 recognition and, hence, offer novel prospects for medicating cancer along with other diseases.
647 MNPs bonding to drugs, genes, antibodies, enzymes, and proteins assist in direct targeting of
648 definite cancerous site employing magnetic field that is externally applied. Current advancement
649 has focused to increase three-dimensional accuracy in activated release of drug, in addition to
650 improvement in magnetic targeting regarding drug to deeper tissues. In this review, we highlight
651 recent development in cancer therapy by integrating MNPs with chemo-, immune-, gene-, radio-
652 therapy in addition to hyperthermia. Since together they lead forward in a better way to amend or
653 treat cancer. Noteworthy progress was made utilizing with MNP platforms for pre-clinical cancer
654 therapy. Additionally, MNPs display pronounced potential to be used for monitoring cancer
655 treatment and providing critical evidence to doctors permitting them for adapting treatment
656 approaches to deliver optimum care.

657 In future work critical information is still needed to develop better MNPs properties in addition
658 to technologies aimed at economical magnetic systems. Moreover, researchers tried to overcome
659 difficulties particularly knowing bio-nano interactions inside humans, crossing biological as well
660 as methodological barriers particular to cancer kind, evading late lysosome/endosome system in
661 cytosol inside cells, besides prolong toxicity. MNPs synthesis along their functionalization with
662 biotherapeutic as well as chemotherapeutic agents are being under progress to develop multi-
663 module therapeutic tactics by unifying MNPs with different therapies in addition to consuming
664 numerous drugs in different formulation aimed at cancer therapy. Fusion of immunomodulatory
665 and other targeting ligands assisted in cancer targeting and ultimately its therapy. Better
666 laboratory practices need to be industrialized to overcome industrial barriers. For scaling up
667 magnetic systems for cancer therapy, advancement in coil technology is mandatory for making
668 resource-effectual system.

669 In spite of many positive results gained from consuming MNPs as theranostic agent, there are
670 still some features to be improved for instance capacity to load drug and enhancing affinity for
671 targeting tumor cells. MNPs might be suitable for medical usage through integrated multimodal
672 treatment in future and vividly influence treatment regarding cancer. Numbers of pre-clinical
673 tests with MNPs have been perceived, though, no single formulation comprising MNPs being
674 accepted aimed at cancer therapeutic till date. However, it's been anticipated that it would
675 evolve into medical investigations, on account of their pronounced potential to treat cancer. We
676 have confidence that delay in fruitful consumption of MNPs for clinics are motivated by making
677 new formulations for cancer therapy.

678

679 **6. Experts opinion**

680 MNPs are explored broadly during last few years but still it is a great challenge to engineer them
681 to improve diagnosis and treatment of diseases. With respect to MNPs, central idea has been to
682 attach conventional anti-cancerous drugs to magnetic small spheres superficially, before
683 directing them inside human body. After getting inside to the body, drug loaded MNPs
684 accumulated in tumor by means of externally applied strong magnetic fields. By employing
685 MNPs, drug payload would be significantly reduced. Hence, unwanted and adverse effects

686 related to systematic chemotherapeutics delivery, particularly nausea, loss of hair, in addition to
 687 destabilized immunity, was prohibited. In spite of these facts, drug loaded MNPs are not in
 688 medical use, and is in developing stage at extraordinary speed.

689 Cancer therapeutic approaches consuming MNPs depends upon transmitting energy to MNPs,
 690 being introduced to body, from magnetic field. MNPs are favorable in medical sciences due to
 691 their stability in aqueous solutions, biocompatibility, low toxicity, over and above exceptional
 692 chemical as well as physical features particularly superparamagnetism. Among MNPs, SPIONs
 693 are commonly employed in tailored medicine aimed at cancer diagnosis and therapy. A list of
 694 SPIONs in clinical trials and already in the market is presented in Table 2. Moreover, predicting
 695 the best formulation of MNPs for humans is achieved with the help of better theoretical animal
 696 models. For “*in vivo*” application, hydrodynamic size of MNPs is important factor, being
 697 constrained by anatomical feature of human body. Due to this fact, they are mostly carried in
 698 solutions of water. Nanoparticles having size lesser than one-fifty nanometers are able to cross
 699 endothelial barrier, however MNPs with reduced size can penetrate blood–brain barrier [126].
 700 Additionally, MNPs except with size smaller than 10 nm, don’t have fast renal clearance and
 701 would not be internalized by the reticuloendothelial system (RES) [127]. MNPs have tendency of
 702 forming aggregates that is significant in magnetic resonance examinations.

703 **Table 2.** A list of SPIONs in clinical trials regarding cancer therapy.

Product	Size (nm)	Morphology	Coating agent	Application	Targeting moiety	Ref
SPIONs	40-50	Roughly spherical	Poly(ethylene glycol)/Dextran	Breast/Brain cancer	Folic acid	[128]
SPIONs	9-20	Polygonal and roughly spherical	Poly(ethylene glycol)	Prostate cancer	A10 RNA aptamer	[129]
SPIONs	8-13	Spherical	3-(aminopropyl) trimethoxysilane	Brain tumors	Methotrexate	[50,130]
SPIONs	10-30	Spherical	Dextran	Liver tumors	-	[131]
Ultrasmall SPIONs	5-15	Spherical	3-(aminopropyl) trimethoxysilane	Lung cancer	Arginine-glycine-aspartic acid	[132]

704
 705 MNPs toxicity is one of the serious causes regarding their biomedical applications. It reduces
 706 therapeutic efficiency along with immunity or inflammatory activation because of their
 707 agglomeration in organs. On entrance in cells, the toxicity can upset nuclear activities, leakage of
 708 cell membranes that results in adversative metabolic action, proliferation of cells, and viability
 709 consequences. Even though MNPs and SPIONs are FDA approved, but their usage in treating
 710 cancer should be wisely directed and organized, since their large amount might be
 711 unsafe. Excessive use of MNPs can cause changes in living cells because of ROS production
 712 cytoskeletal destruction, mitochondrial impairment, as well as DNA configuration alteration.
 713 One challenge is scaling up of the magnetic system. Prototypes devices for small-sized animals
 714 could be built exploiting stable magnets with benchtop amplifiers, whereas establishing large

715 systems need high-powered electromagnets.
 716 MNPs display substantial promise for theranostic applications as contrast enhancers and
 717 therapeutic agents for cancers. MNPs indicate the potential to be engaged in treating
 718 cancer treatments because of their specific characteristics that deliver acute data to physicians
 719 offering ultimate care. MNPs have been investigated extensively attributed to their ease of
 720 synthesis and functionalization; still, inadequate formulations get permitted for clinical uses.
 721 However, there is room to translate MNPs from lab to clinic that requires complete
 722 understanding concerning MNPs effects on human physiological reactions. Research showed
 723 numerous formulations consisting MNPs have unsuccessful results to produce satisfactory
 724 treatment levels in large animals and humans; similar to results that were perceived in small
 725 animals. For MNPs translation to clinics, ability to load drug, improving their specificity and
 726 affinity to target cells, in addition to obtain required release of drug depending on tumor
 727 microenvironment must be considered with the help of superior animal theoretical models. Table
 728 3 summarizes some features of the reported magnetic nanoparticles intended for cancer therapy.
 729 Taking account of countless advantages, we are confident that combine diagnostic and
 730 multimodal therapy consuming MNPs would propel forward their clinical employment and
 731 considerably influence cancer therapy in near future.

732 **Table 3.** Some features regarding the reported magnetic nanoparticles intended for cancer
 733 therapy.

Material	Target	Specific feature	Type of treatment	Advantages	Ref
Polycaprolactone-SPIONs	Liver cancer	Polymer (PCL)	Hyperthermia	Better dispersibility, structural stability, and cytocompatibility	[133]
Polyaspartamide-SPIONs	Cancer cells	Biotin	Hyperthermia	Better heating capability and enhanced cellular uptake	[134]
Polyacrylic acid-SPIONs	Breast cancer	Anti-HER2 antibody	Hyperthermia	Ultra-small size, High stability, and resistance to accumulation	[135]
GdPO ₄ -CS-Fe ₃ O ₄	Breast cancer	-	Photothermal therapy	Increased apoptosis and prevent cancer recurrence	[136]
SPIONs/Cur/Ver loaded PLGA nanoparticle	HepG2Liver cancer	Poly lactic co glycolic acid (PLGA)	Chemotherapy/thermotherapy	Minimum toxicity, enhanced stability and maximum treatment efficacy	[137]
Cetyltrimethyl ammonium bromide encapsulated IONPs	HeLa cells	-	Chemotherapy	Large-scale simple production, modifiable uniform size of pore size, high surface area, and pore volumes	[138]
Trastuzumab	MCF-7	Conjugated	Photothermal	Minimum cytotoxicity	[139]

conjugated porphyrin-SPIONs		antibodies	therapy	and water-solubility	
Poly-L-lysine-coated MNPs	Colorectal cancer cells	Conjugate specific antibodies	Immunotherapy	Selective targeting	[140]
Iron oxide nanoparticles FeONPs	MCF-7	-	Radiotherapy (X-ray irradiation)	Additional oxidative stress	[141]
SPIONs	Colon cancer	-	Radiotherapy (150 MeV proton beams)	Enhanced oxidative stress to damage DNA of cells	[142,143]
Cationic coated MNPs	Brain cancer	-		High efficiency, non-viral vehicles, and survival rate	[106]

734

735 Among all these therapeutic methods, chemotherapeutic and hyperthermia are most promising
736 strategies and holds a pronounced potential to become a first line treatment for cancers. Other
737 approaches are still in progress and could become a safe option to treat various cancers. *In vivo*
738 or *in vitro* analysis verifies that SPIONs could modify living cells due to deterioration of
739 cytoskeleton, generation of ROS, mitochondrial damage, and structural changes in DNA [144].
740 MNPs toxicity is also due to their agglomerations that become unstable in physiological media.
741 For effective use of SPIONs, their shape, the dimensions, coating shell are vital parameters that
742 must be considered. Some research work claims that adverse effects regarding MNPs used in
743 chemotherapy, radiotherapy, gene therapy, immunotherapy, and hyperthermia might be
744 effectively addressed by the body's self-defense system [145]. MNPs as a therapeutic tool is a
745 new and important research domain, which is still in the phase of continuous development and
746 should be, investigated more.

747

748 **Disclosure statement**

749 Authors have no competing interest to disclose.

750

751 **References**

- 752 1. Rosiere R, Van Woensel M, Gelbcke M, et al. New Folate-Grafted Chitosan Derivative To
753 Improve Delivery of Paclitaxel-Loaded Solid Lipid Nanoparticles for Lung Tumor Therapy by
754 Inhalation. *Mol Pharmaceutics*. 2018 Mar 5;15(3):899-910.
- 755 2. Liebow PNPJBL, inventor Magnetic nanoparticles for selective therapy 2001.
- 756 3. Jia L, Zhang P, Sun H, et al. Optimization of Nanoparticles for Smart Drug Delivery: A Review.
757 *Nanomaterials*. 2021 Oct 21;11(11):2790.
- 758 4. Wei J, Shuai X, Wang R, et al. Clickable and imageable multiblock polymer micelles with
759 magnetically guided and PEG-switched targeting and release property for precise tumor
760 theranosis. *Biomaterials*. 2017 Nov;145:138-153.
- 761 5. Din FU, Aman W, Ullah I, et al. Effective use of nanocarriers as drug delivery systems for the
762 treatment of selected tumors. *Int Journal Nanomedicine*. 2017;12:7291-7309.
- 763 ** Din FU., et al. discussed features of different types of nanocarriers (organic, inorganic and

- 764 hybrid) along with their relevance in cancer therapy and elaborated the targeting mechanisms and
765 surface functionalization on nanocarriers and application of nanocarriers in the respective tumor.
- 766 6. Kalubowilage M, Janik K, Bossmann SH. Magnetic Nanomaterials for Magnetically-Aided Drug
767 Delivery and Hyperthermia. *Appl Sci*. 2019;9(14):2927.
- 768 7. Wu M, Huang S. Magnetic nanoparticles in cancer diagnosis, drug delivery and treatment. *Mol*
769 *Clin Oncol*. 2017 Nov;7(5):738-746.
- 770 *Wu M., et al. provides a framework for the application of MNPs in medicine, such as cancer
771 diagnosis, drug delivery and treatment.
- 772 8. Chang D, Lim M, Goos J, et al. Biologically Targeted Magnetic Hyperthermia: Potential and
773 Limitations. *Front Pharmacol*. 2018;9:831.
- 774 9. Liu JF, Jang B, Issadore D, et al. Use of magnetic fields and nanoparticles to trigger drug release
775 and improve tumor targeting. *Wiley Interdiscip Rev Nanomed Nanobiotechnol*. 2019
776 Nov;11(6):e1571.
- 777 10. Khizar S, Ahmad NM, Zine N, et al. Magnetic Nanoparticles: From Synthesis to Theranostic
778 Applications. *ACS Appl Nano Mater*. 2021;4(5):4284-4306.
- 779 11. Gunn MZKW, inventor Magnetic nanoparticle compositions and methods 2006.
- 780 12. Price PM, Mahmoud WE, Al-Ghamdi AA, et al. Magnetic Drug Delivery: Where the Field Is
781 Going. *Front Chem*. 2018;6:619.
- 782 13. Mylkie K, Nowak P, Rybczynski P, et al. Polymer-Coated Magnetite Nanoparticles for Protein
783 Immobilization. *Materials*. 2021 Jan 6;14(2):248.
- 784 14. Hormes CLSSRKH, inventor In Vivo Imaging and Therapy with Magnetic Nanoparticle
785 Conjugates 2009.
- 786 15. Materón EM, Miyazaki CM, Carr O, et al. Magnetic nanoparticles in biomedical applications: A
787 review. *Appl Surf Sci Adv*. 2021;6:100163.
- 788 16. Gordon RT, inventor Cancer treatment method 1976.
- 789 17. Gordon RT, inventor Use of magnetic susceptibility probes in the treatment of cancer 1983.
- 790 18. Shi J, Kantoff PW, Wooster R, et al. Cancer nanomedicine: progress, challenges and
791 opportunities. *Nat Rev Cancer*. 2017 Jan;17(1):20-37.
- 792 19. Schladt TD, Schneider K, Schild H, et al. Synthesis and bio-functionalization of magnetic
793 nanoparticles for medical diagnosis and treatment. *Dalton Trans*. 2011 Jun 28;40(24):6315-43.
- 794 20. Sun C, Lee JSH, Zhang M. Magnetic nanoparticles in MR imaging and drug delivery. *Adv Drug*
795 *Deliv Rev*. 2008 Aug 17;60(11):1252-1265.
- 796 21. Stephen MZOP, inventor Glypican-3 targeting of liver cancer cells using multifunctional
797 nanoparticles 2012.
- 798 22. Moros M, Idiago-Lopez J, Asin L, et al. Triggering antitumoural drug release and gene
799 expression by magnetic hyperthermia. *Adv Drug Deliv Rev*. 2019 Jan 1;138:326-343.
- 800 23. Baghban R, Afarid M, Soleymani J, et al. Were magnetic materials useful in cancer therapy?
801 *Biomed Pharmacother*. 2021 Dec;144:112321.
- 802 24. Navya PN, Kaphle A, Srinivas SP, et al. Current trends and challenges in cancer management and
803 therapy using designer nanomaterials. *Nano Converg*. 2019 Jul 15;6(1):23.
- 804 25. Zhu K, Ju Y, Xu J, et al. Magnetic Nanomaterials: Chemical Design, Synthesis, and Potential
805 Applications. *Acc Chem Res*. 2018 Feb 20;51(2):404-413.
- 806 26. Mukherjee S, Liang L, Veisheh O. Recent Advancements of Magnetic Nanomaterials in Cancer
807 Therapy. *Pharmaceutics*. 2020 Feb 11;12(2):147.
- 808 ** Mukherjee S., et al. provides a detailed overview about the cancer therapeutic applications of
809 MNPs including drug delivery, cancer immunotherapy, magnetic hyperthermia, photodynamic
810 therapy, and anti-cancer agents.
- 811 27. Mosayebi J, Kiyasatfar M, Laurent S. Synthesis, Functionalization, and Design of Magnetic
812 Nanoparticles for Theranostic Applications. *Adv Healthc Mater*. 2017 Dec;6(23).
- 813 28. Uebe R, Schuler D. Magnetosome biogenesis in magnetotactic bacteria. *Nat Rev Microbiol*. 2016
814 Sep 13;14(10):621-37.

- 815 29. Tong S, Quinto CA, Zhang L, et al. Size-Dependent Heating of Magnetic Iron Oxide
816 Nanoparticles. *ACS Nano*. 2017 Jul 25;11(7):6808-6816.
- 817 30. Yoshida S, Duong C, Oestergaard M, et al. MXD3 antisense oligonucleotide with
818 superparamagnetic iron oxide nanoparticles: A new targeted approach for neuroblastoma.
819 *Nanomedicine*. 2020 Feb;24:102127.
- 820 31. Ali A, Shah T, Ullah R, et al. Review on Recent Progress in Magnetic Nanoparticles: Synthesis,
821 Characterization, and Diverse Applications. *Front Chem*. 2021;9:629054.
- 822 32. Angelakeris M. Magnetic nanoparticles: A multifunctional vehicle for modern theranostics.
823 *Biochim Biophys Acta Gen Sub*. 2017 Jun;1861(6):1642-1651.
- 824 33. Ferreira M, Sousa J, Pais A, et al. The Role of Magnetic Nanoparticles in Cancer
825 Nanotheranostics. *Materials*. 2020 Jan 7;13(2):266.
826 * Ferreira M., et al. describes current designs, characterization techniques, synthesis methods, and
827 the role of magnetic nanoparticles as promising nanotheranostic agents.
- 828 34. Ulbrich K, Hola K, Subr V, et al. Targeted Drug Delivery with Polymers and Magnetic
829 Nanoparticles: Covalent and Noncovalent Approaches, Release Control, and Clinical Studies.
830 *Chem Rev*. 2016 May 11;116(9):5338-431.
- 831 35. Xie W, Guo Z, Gao F, et al. Shape-, size- and structure-controlled synthesis and biocompatibility
832 of iron oxide nanoparticles for magnetic theranostics. *Theranostics*. 2018;8(12):3284-3307.
- 833 36. Hosu, Tertis, Cristea. Implication of Magnetic Nanoparticles in Cancer Detection, Screening and
834 Treatment. *Magnetochemistry*. 2019;5(4):55.
- 835 37. Fatima H, Charinpanitkul T, Kim KS. Fundamentals to Apply Magnetic Nanoparticles for
836 Hyperthermia Therapy. *Nanomaterials*. 2021 May 1;11(5):1203.
- 837 38. Shen Z, Chen T, Ma X, et al. Multifunctional Theranostic Nanoparticles Based on Exceedingly
838 Small Magnetic Iron Oxide Nanoparticles for T1-Weighted Magnetic Resonance Imaging and
839 Chemotherapy. *ACS nano*. 2017 Nov 28;11(11):10992-11004.
- 840 39. Hu Y, Mignani S, Majoral JP, et al. Construction of iron oxide nanoparticle-based hybrid
841 platforms for tumor imaging and therapy. *Chem Soc Rev*. 2018 Mar 5;47(5):1874-1900.
- 842 40. Zhou Q, Wei Y. For Better or Worse, Iron Overload by Superparamagnetic Iron Oxide
843 Nanoparticles as a MRI Contrast Agent for Chronic Liver Diseases. *Chem Res Toxicol*. 2017 Jan
844 17;30(1):73-80.
- 845 41. Fraum TJ, Ludwig DR, Bashir MR, et al. Gadolinium-based contrast agents: A comprehensive
846 risk assessment. *J Mag Res Imaging*. 2017 Aug;46(2):338-353.
- 847 42. van Zandwijk JK, Simonis FFJ, Heslinga FG, et al. Comparing the signal enhancement of a
848 gadolinium based and an iron-oxide based contrast agent in low-field MRI. *PLoS one*.
849 2021;16(8):e0256252.
- 850 43. Yang H, Wang H, Wen C, et al. Effects of iron oxide nanoparticles as T2-MRI contrast agents on
851 reproductive system in male mice. *J Nanobiotechnol*. 2022 2022/03/02;20(1):98.
- 852 44. Revia RA, Zhang M. Magnetite nanoparticles for cancer diagnosis, treatment, and treatment
853 monitoring: recent advances. *Mater Today (Kidlington)*. 2016 Apr;19(3):157-168.
- 854 45. Thiesen B, Jordan A. Clinical applications of magnetic nanoparticles for hyperthermia. *Int J*
855 *Hyperther*. 2008 Sep;24(6):467-74.
- 856 46. Stetter MKW, inventor Dynamic superparamagnetic markers 2001.
- 857 47. Nafiujjaman M, Revuri V, Nurunnabi M, et al. Photosensitizer conjugated iron oxide
858 nanoparticles for simultaneous in vitro magneto-fluorescent imaging guided photodynamic
859 therapy. *Chem Commun*. 2015 Apr 4;51(26):5687-90.
- 860 48. Soetaert F, Korangath P, Serantes D, et al. Cancer therapy with iron oxide nanoparticles: Agents
861 of thermal and immune therapies. *Adv Drug Deliv Rev*. 2020;163-164:65-83.
- 862 49. Espinosa A, Di Corato R, Kolosnjaj-Tabi J, et al. Duality of Iron Oxide Nanoparticles in Cancer
863 Therapy: Amplification of Heating Efficiency by Magnetic Hyperthermia and Photothermal
864 Bimodal Treatment. *ACS Nano*. 2016 Feb 23;10(2):2436-46.

- 865 50. Janko C, Ratschker T, Nguyen K, et al. Functionalized Superparamagnetic Iron Oxide
866 Nanoparticles (SPIONs) as Platform for the Targeted Multimodal Tumor Therapy. *Front Oncol.*
867 2019;9:59.
- 868 51. Musielak M, Piotrowski I, Suchorska WM. Superparamagnetic iron oxide nanoparticles
869 (SPIONs) as a multifunctional tool in various cancer therapies. *Rep Prac Oncol Radiother.* 2019
870 Jul-Aug;24(4):307-314.
- 871 52. Rameshkumar C, Gayathri R, Subalakshmi R. Synthesis and characterization of undoped
872 bismuth ferrite oxide nanoparticles for the application of cancer treatment. *Mater Today:*
873 *Proceed.* 2021;43:3662-3665.
- 874 53. Shahbazi MA, Faghfouri L, Ferreira MPA, et al. The versatile biomedical applications of
875 bismuth-based nanoparticles and composites: therapeutic, diagnostic, biosensing, and
876 regenerative properties. *Chem Soc Rev.* 2020 Feb 21;49(4):1253-1321.
- 877 54. Badrigilan S, Shaabani B, Gharehaghaji N, et al. Iron oxide/bismuth oxide nanocomposites
878 coated by graphene quantum dots: "Three-in-one" theranostic agents for simultaneous CT/MR
879 imaging-guided in vitro photothermal therapy. *Photodiagnosis Photodyn Ther.* 2019 Mar;25:504-
880 514.
- 881 55. Mdlovu NV, Lin K-S, Mavuso FA, et al. Preparation, characterization, and in-vitro studies of
882 doxorubicin-encapsulated silica coated iron oxide nanocomposites on liver cancer cells. *J Taiwan*
883 *Inst Chem Eng.* 2020;117:190-197.
- 884 56. Fathy MM, Fahmy HM, Saad OA, et al. Silica-coated iron oxide nanoparticles as a novel nano-
885 radiosensitizer for electron therapy. *Life Sci.* 2019 Oct 1;234:116756.
- 886 57. Dheyab MA, Aziz AA, Jameel MS, et al. Synthesis and coating methods of biocompatible iron
887 oxide/gold nanoparticle and nanocomposite for biomedical applications. *Chin J Phys.*
888 2020;64:305-325.
- 889 58. Ghaznavi H, Hosseini-Nami S, Kamrava SK, et al. Folic acid conjugated PEG coated gold-iron
890 oxide core-shell nanocomplex as a potential agent for targeted photothermal therapy of cancer.
891 *Artif Cells Nanomed Biotechnol.* 2018 Dec;46(8):1594-1604.
- 892 59. Yin NQ, Wu P, Yang TH, et al. Preparation and study of a mesoporous silica-coated Fe₃O₄
893 photothermal nanoprobe. *RSC Adv.* 2017;7(15):9123-9129.
- 894 60. Jana TK, Jana SK, Kumar A, et al. The antibacterial and anticancer properties of zinc oxide
895 coated iron oxide nanotextured composites. *Colloids Surf B Biointerfaces.* 2019 May 1;177:512-
896 519.
- 897 61. Ali R, Aziz MH, Gao S, et al. Graphene oxide/zinc ferrite nanocomposite loaded with
898 doxorubicin as a potential theranostic mediu in cancer therapy and magnetic resonance imaging.
899 *Ceram Int.* 2022;48(8):10741-10750.
- 900 62. Gonzalez-Rodriguez R, Campbell E, Naumov A. Multifunctional graphene oxide/iron oxide
901 nanoparticles for magnetic targeted drug delivery dual magnetic resonance/fluorescence imaging
902 and cancer sensing. *PLoS one.* 2019;14(6):e0217072.
- 903 63. Narayanaswamy V, Obaidat IM, Kamzin AS, et al. Synthesis of Graphene Oxide-Fe₃O₄ Based
904 Nanocomposites Using the Mechanochemical Method and in Vitro Magnetic Hyperthermia. *Int J*
905 *Mol Sci.* 2019 Jul 9;20(13).
- 906 64. Niu Z, Murakonda GK, Jarubula R, et al. Fabrication of Graphene oxide-Fe₃O₄ nanocomposites
907 for application in bone regeneration and treatment of leukemia. *J Drug Deliv Sci Technol.*
908 2021;63:102412.
- 909 65. Sharma H, Mondal S. Functionalized Graphene Oxide for Chemotherapeutic Drug Delivery and
910 Cancer Treatment: A Promising Material in Nanomedicine. *Int J Mol Sci.* 2020 Aug
911 30;21(17):6280.
- 912 66. Malhotra N, Lee JS, Liman RAD, et al. Potential Toxicity of Iron Oxide Magnetic Nanoparticles:
913 A Review. *Molecules.* 2020 Jul 10;25(14):3159.
- 914 67. Zhi D, Yang T, Yang J, et al. Targeting strategies for superparamagnetic iron oxide nanoparticles
915 in cancer therapy. *Acta Biomater.* 2020 Jan 15;102:13-34.

- 916 68. Li X, Li W, Wang M, et al. Magnetic nanoparticles for cancer theranostics: Advances and
917 prospects. *J Control Release*. 2021 Jul 10;335:437-448.
918 * Li X., et al. describes the recent improvements in MNPs for clinical applications as well as
919 discusses the future research prospects and potential of MNPs in cancer theranostics.
- 920 69. Kent VAVDDVCMAB, inventor Magnetically responsive compositions for carrying biologically
921 active substances and methods of production and use 2005.
- 922 70. Mrowczynski R, Jedrzak A, Szutkowski K, et al. Cyclodextrin-Based Magnetic Nanoparticles for
923 Cancer Therapy. *Nanomaterials*. 2018 Mar 16;8(3):170.
- 924 71. Jedrzak A, Grzeskowiak BF, Golba K, et al. Magnetite Nanoparticles and Spheres for Chemo-
925 and Photothermal Therapy of Hepatocellular Carcinoma in vitro. *Int J Nanomed*. 2020;15:7923-
926 7936.
- 927 72. Jędrzak A, Grzeškowiak BF, Coy E, et al. Dendrimer based theranostic nanostructures for
928 combined chemo- and photothermal therapy of liver cancer cells in vitro. *Colloids Surf B*
929 *Biointerfaces*. 2019 2019/01/01/;173:698-708.
- 930 73. Wang L, Liang L, Shi S, et al. Study on the Application of Doxorubicin-Loaded Magnetic
931 Nanodrugs in Targeted Therapy of Liver Cancer. *Appl Bionics biomechan*. 2022;2022:2756459.
- 932 74. Ramezani Farani M, Azarian M, Heydari Sheikh Hossein H, et al. Folic Acid-Adorned
933 Curcumin-Loaded Iron Oxide Nanoparticles for Cervical Cancer. *ACS Appl Bio Mater*. 2022 Mar
934 21;5(3):1305-1318.
- 935 75. Jeon M, Lin G, Stephen ZR, et al. Paclitaxel- Loaded Iron Oxide Nanoparticles for Targeted
936 Breast Cancer Therapy. *Adv Therapeutics*. 2019;2(12):1900081.
- 937 76. Taheri-Ledari R, Zhang W, Radmanesh M, et al. Multi-Stimuli Nanocomposite Therapeutic:
938 Docetaxel Targeted Delivery and Synergies in Treatment of Human Breast Cancer Tumor. *Small*.
939 2020 Oct;16(41):e2002733.
- 940 77. Sadr SH, Davaran S, Alizadeh E, et al. PLA-based magnetic nanoparticles armed with thermo/pH
941 responsive polymers for combination cancer chemotherapy. *J Drug Deliv Sci Technol*.
942 2018;45:240-254.
- 943 78. Cheng HW, Tsao HY, Chiang CS, et al. Advances in Magnetic Nanoparticle-Mediated Cancer
944 Immune-Theranostics. *Adv Healthc Mater*. 2021 Jan;10(1):e2001451.
- 945 79. Chiang CS, Lin YJ, Lee R, et al. Combination of fucoidan-based magnetic nanoparticles and
946 immunomodulators enhances tumour-localized immunotherapy. *Nat Nanotechnol*. 2018
947 Aug;13(8):746-754.
- 948 80. Zhang F, Lu G, Wen X, et al. Magnetic nanoparticles coated with polyphenols for spatio-
949 temporally controlled cancer photothermal/immunotherapy. *J Control Release*. 2020 Oct
950 10;326:131-139.
- 951 81. Jiang Q, Wang K, Zhang X, et al. Platelet Membrane-Camouflaged Magnetic Nanoparticles for
952 Ferroptosis-Enhanced Cancer Immunotherapy. *Small*. 2020 Jun;16(22):e2001704.
- 953 82. Bocanegra Gondan AI, Ruiz-de-Angulo A, Zabaleta A, et al. Effective cancer immunotherapy in
954 mice by polyIC-imiquimod complexes and engineered magnetic nanoparticles. *Biomaterials*.
955 2018 Jul;170:95-115.
- 956 83. Wu X, Cheng Y, Zheng R, et al. Immunomodulation of Tumor Microenvironment by Arginine-
957 Loaded Iron Oxide Nanoparticles for Gaseous Immunotherapy. *ACS Appl Mater Interfaces*. 2021
958 May 5;13(17):19825-19835.
- 959 84. Périco EA, Hemery G, Sandre O, et al. Fundamentals and advances in magnetic hyperthermia.
960 *Appl Phys Rev*. 2015;2(4):041302.
- 961 85. Zhu H, inventor targeted nanoparticle drug for magnetic hyperthermia treatment on malignant
962 tumors 2011.
- 963 86. Gavilan H, Avugadda SK, Fernandez-Cabada T, et al. Magnetic nanoparticles and clusters for
964 magnetic hyperthermia: optimizing their heat performance and developing combinatorial
965 therapies to tackle cancer. *Chem Soc Rev*. 2021 Oct 18;50(20):11614-11667.

- 966 87. Kubovcikova M, Koneracka M, Strbak O, et al. Poly-L-lysine designed magnetic nanoparticles
967 for combined hyperthermia, magnetic resonance imaging and cancer cell detection. *J Magn Magn*
968 *Mater.* 2019;475:316-326.
- 969 88. Eivazzadeh-Keihan R, Radinekiyan F, Asgharnasl S, et al. A natural and eco-friendly magnetic
970 nanobiocomposite based on activated chitosan for heavy metals adsorption and the in-vitro
971 hyperthermia of cancer therapy. *J Mater Res Technol.* 2020;9(6):12244-12259.
- 972 89. Garanina AS, Naumenko VA, Nikitin AA, et al. Temperature-controlled magnetic nanoparticles
973 hyperthermia inhibits primary tumor growth and metastases dissemination. *Nanomed*
974 *Nanotechnol Biol Med.* 2020 Apr;25:102171.
- 975 90. Kaushik S, Thomas J, Panwar V, et al. In Situ Biosynthesized Superparamagnetic Iron Oxide
976 Nanoparticles (SPIONS) Induce Efficient Hyperthermia in Cancer Cells. *ACS Appl Bio Mater.*
977 2020 Feb 17;3(2):779-788.
- 978 91. Sanchez-Cabezas S, Montes-Robles R, Gallo J, et al. Combining magnetic hyperthermia and dual
979 T1/T2 MR imaging using highly versatile iron oxide nanoparticles. *Dalton Trans.* 2019 Mar
980 19;48(12):3883-3892.
- 981 92. Eivazzadeh-Keihan R, Radinekiyan F, Maleki A, et al. A novel biocompatible core-shell
982 magnetic nanocomposite based on cross-linked chitosan hydrogels for in vitro hyperthermia of
983 cancer therapy. *Int J Biol Macromol.* 2019 Nov 1;140:407-414.
- 984 93. Eivazzadeh-Keihan R, Radinekiyan F, Maleki A, et al. A new generation of star polymer:
985 magnetic aromatic polyamides with unique microscopic flower morphology and in vitro
986 hyperthermia of cancer therapy. *J Mater Sci.* 2019;55(1):319-336.
- 987 94. Kandasamy G, Sudame A, Luthra T, et al. Functionalized Hydrophilic Superparamagnetic Iron
988 Oxide Nanoparticles for Magnetic Fluid Hyperthermia Application in Liver Cancer Treatment.
989 *ACS Omega.* 2018 Apr 30;3(4):3991-4005.
- 990 95. Dahaghin A, Emadiyanrazavi S, Haghpanahi M, et al. A comparative study on the effects of
991 increase in injection sites on the magnetic nanoparticles hyperthermia. *J Drug Deliv Sci Technol.*
992 2021;63:102542.
- 993 96. Ivkov R, inventor Magnetic nanoscale particle compositions, and therapeutic methods related
994 thereto 2006.
- 995 97. Mi Y, Shao Z, Vang J, et al. Application of nanotechnology to cancer radiotherapy. *Cancer*
996 *Nanotechnol.* 2016;7(1):11.
- 997 98. Nabavinia M, Beltran-Huarac J. Recent Progress in Iron Oxide Nanoparticles as Therapeutic
998 Magnetic Agents for Cancer Treatment and Tissue Engineering. *ACS Appl Bio Mater.* 2020 Dec
999 21;3(12):8172-8187.
- 1000 99. Russell E, Dunne V, Russell B, et al. Impact of superparamagnetic iron oxide nanoparticles on in
1001 vitro and in vivo radiosensitisation of cancer cells. *Radiat Oncol.* 2021 Jun 12;16(1):104.
- 1002 100. Neshastehriz A, Khosravi Z, Ghaznavi H, et al. Gold-coated iron oxide nanoparticles trigger
1003 apoptosis in the process of thermo-radiotherapy of U87-MG human glioma cells. *Radiat Environ*
1004 *Biophys.* 2018 Nov;57(4):405-418.
- 1005 101. Wu C, Muroski ME, Miska J, et al. Repolarization of myeloid derived suppressor cells via
1006 magnetic nanoparticles to promote radiotherapy for glioma treatment. *Nanomed Nanotechnol Biol*
1007 *Med.* 2019 Feb;16:126-137.
- 1008 102. Anuje M, Pawaskar PN, Khot V, et al. Synthesis, Characterization, and Cytotoxicity Evaluation
1009 of Polyethylene Glycol-Coated Iron Oxide Nanoparticles for Radiotherapy Application. *J Med*
1010 *Phys.* 2021 Jul-Sep;46(3):154-161.
- 1011 103. Askar MA, El-Nashar HA, Al-Azzawi MA, et al. Synergistic Effect of Quercetin Magnetite
1012 Nanoparticles and Targeted Radiotherapy in Treatment of Breast Cancer. *Breast Cancer : Basic*
1013 *clin Res.* 2022;16:11782234221086728.
- 1014 104. Rahman WN, Kadian SNM, Ab Rashid R, et al. Radiosensitization characteristic of
1015 superparamagnetic iron oxide nanoparticles in electron beam radiotherapy and brachytherapy. *J*
1016 *Phys Conf Ser.* 2019;1248(1):012068.

- 1017 105. Belete TM. The Current Status of Gene Therapy for the Treatment of Cancer. *Biol Targ Ther.* 2021;15:67-77.
1018
- 1019 106. Manescu Paltanea V, Paltanea G, Antoniac I, et al. Magnetic Nanoparticles Used in Oncology. *Materials.* 2021 Oct 10;14(20):5948.
1020
1021 * Manescu Paltanea V., et al described cancer cell monitorization based on different types of
1022 magnetic nanoparticles, chemotherapy, immunotherapy, magnetic hyperthermia, gene therapy
1023 and ferroptosis.
- 1024 107. Grapa CM, Mocan L, Crisan D, et al. Biomarkers in Pancreatic Cancer as Analytic Targets for
1025 Nanomediated Imaging and Therapy. *Materials.* 2021 Jun 4;14(11):3038.
- 1026 108. Mu X, Li J, Yan S, et al. siRNA Delivery with Stem Cell Membrane-Coated Magnetic
1027 Nanoparticles for Imaging-Guided Photothermal Therapy and Gene Therapy. *ACS Biomater Sci*
1028 *Eng.* 2018 Nov 12;4(11):3895-3905.
- 1029 109. Shtykalova S, Egorova A, Maretina M, et al. Magnetic Nanoparticles as a Component of Peptide-
1030 Based DNA Delivery System for Suicide Gene Therapy of Uterine Leiomyoma. *Bioengineering.*
1031 2022 Mar 8;9(3):112.
- 1032 110. Wang Z, Chang Z, Lu M, et al. Shape-controlled magnetic mesoporous silica nanoparticles for
1033 magnetically-mediated suicide gene therapy of hepatocellular carcinoma. *Biomaterials.* 2018
1034 Feb;154:147-157.
- 1035 111. Yang Z, Duan J, Wang J, et al. Superparamagnetic iron oxide nanoparticles modified with
1036 polyethylenimine and galactose for siRNA targeted delivery in hepatocellular carcinoma therapy.
1037 *Int J Nanomed.* 2018;13:1851-1865.
- 1038 112. Jin L, Wang Q, Chen J, et al. Efficient Delivery of Therapeutic siRNA by Fe₃O₄ Magnetic
1039 Nanoparticles into Oral Cancer Cells. *Pharmaceutics.* 2019 Nov 17;11(11):615.
- 1040 113. Grabowska M, Grzeskowiak BF, Szutkowski K, et al. Nano-mediated delivery of double-stranded
1041 RNA for gene therapy of glioblastoma multiforme. *PloS one.* 2019;14(3):e0213852.
- 1042 114. Zhou Z, Yang L, Gao J, et al. Structure-Relaxivity Relationships of Magnetic Nanoparticles for
1043 Magnetic Resonance Imaging. *Adv Mater.* 2019 Feb;31(8):e1804567.
- 1044 115. Chen Y, Ding X, Zhang Y, et al. Design and synthesis of magnetic nanoparticles for biomedical
1045 diagnostics. *Quant Imaging Med Surg.* 2018 Oct;8(9):957-970.
- 1046 116. Hayashi K, Tokuda A, Nakamura J, et al. Tearable and Fillable Composite Sponges Capable of
1047 Heat Generation and Drug Release in Response to Alternating Magnetic Field. *Materials.* 2020
1048 Aug 17;13(16).
- 1049 117. Anik MI, Hossain MK, Hossain I, et al. Recent progress of magnetic nanoparticles in biomedical
1050 applications: A review. *Nano Select.* 2021;2(6):1146-1186.
- 1051 118. Schneider-Futschik EK, Reyes-Ortega F. Advantages and Disadvantages of Using Magnetic
1052 Nanoparticles for the Treatment of Complicated Ocular Disorders. *Pharmaceutics.* 2021 Jul
1053 27;13(8).
- 1054 119. Miri A, Najafzadeh H, Darroudi M, et al. Iron Oxide Nanoparticles: Biosynthesis, Magnetic
1055 Behavior, Cytotoxic Effect. *Chem Open.* 2021 Mar;10(3):327-333.
- 1056 120. Balakrishnan PB, Silvestri N, Fernandez-Cabada T, et al. Exploiting Unique Alignment of Cobalt
1057 Ferrite Nanoparticles, Mild Hyperthermia, and Controlled Intrinsic Cobalt Toxicity for Cancer
1058 Therapy. *Adv Mater.* 2020 Nov;32(45):e2003712.
- 1059 121. Markides H, Rotherham M, El Haj AJ. Biocompatibility and Toxicity of Magnetic Nanoparticles
1060 in Regenerative Medicine. *J Nanomater.* 2012;2012:1-11.
- 1061 122. Skocaj M, Bizjak M, Strojjan K, et al. Proposing Urothelial and Muscle In Vitro Cell Models as a
1062 Novel Approach for Assessment of Long-Term Toxicity of Nanoparticles. *Int J Mol Sci.* 2020
1063 Oct 13;21(20):7545.
- 1064 123. Popova M, Koseva N, Trendafilova I, et al. Design of PEG-modified magnetic nanoporous silica
1065 based miltefosine delivery system: Experimental and theoretical approaches. *Microporous*
1066 *Mesoporous Mater.* 2021;310:110664.

- 1067 124. Chen X, Kang R, Kroemer G, et al. Broadening horizons: the role of ferroptosis in cancer. *Nat*
1068 *Rev Clin Oncol*. 2021 May;18(5):280-296.
- 1069 125. Popova M, Trendafilova I, Szegedi Á, et al. Novel SO₃H functionalized magnetic nanoporous
1070 silica/polymer nanocomposite as a carrier in a dual-drug delivery system for anticancer therapy.
1071 *Microporous Mesoporous Mater*. 2018;263:96-105.
- 1072 126. Hajal C, Campisi M, Mattu C, et al. In vitro models of molecular and nano-particle transport
1073 across the blood-brain barrier. *Biomicrofluidics*. 2018 Jul;12(4):042213.
- 1074 127. Shubayev VI, Pisanic TR, Jin S. Magnetic nanoparticles for theragnostics. *Adv Drug Deliv Rev*.
1075 2009 2009/06/21/;61(6):467-477.
- 1076 128. Angelopoulou A, Kolokithas-Ntoukas A, Fytas C, et al. Folic Acid-Functionalized, Condensed
1077 Magnetic Nanoparticles for Targeted Delivery of Doxorubicin to Tumor Cancer Cells
1078 Overexpressing the Folate Receptor. *ACS Omega*. 2019 Dec 24;4(26):22214-22227.
- 1079 129. Anuje M, Pawaskar P, Sivan A, et al. Use of Poly (Ethylene Glycol) Coated Superparamagnetic
1080 Iron Oxide Nanoparticles as Radio Sensitizer in Enhancing Colorectal Cancer Radiation Efficacy.
1081 *J Med Phys*. 2021 Oct-Dec;46(4):278-285.
- 1082 130. Ferraris C, Cavalli R, Panciani PP, et al. Overcoming the Blood-Brain Barrier: Successes and
1083 Challenges in Developing Nanoparticle-Mediated Drug Delivery Systems for the Treatment of
1084 Brain Tumours. *Int J Nanomed*. 2020;15:2999-3022.
- 1085 131. Albukhaty S, Al-Musawi S, Abdul Mahdi S, et al. Investigation of Dextran-Coated
1086 Superparamagnetic Nanoparticles for Targeted Vinblastine Controlled Release, Delivery,
1087 Apoptosis Induction, and Gene Expression in Pancreatic Cancer Cells. *Molecules*. 2020 Oct
1088 15;25(20):4721.
- 1089 132. Nowak-Jary J, Machnicka B. Pharmacokinetics of magnetic iron oxide nanoparticles for medical
1090 applications. *J Nanobiotechnol*. 2022 Jun 27;20(1):305.
- 1091 133. Hedayatnasab Z, Dabbagh A, Abnisa F, et al. Polycaprolactone-coated superparamagnetic iron
1092 oxide nanoparticles for in vitro magnetic hyperthermia therapy of cancer. *Europ Polym J*.
1093 2020;133:109789.
- 1094 134. Nguyen MP, Nguyen MH, Kim J, et al. Encapsulation of superparamagnetic iron oxide
1095 nanoparticles with polyaspartamide biopolymer for hyperthermia therapy. *Europe Polym J*.
1096 2020;122:109396.
- 1097 135. Zuvin M, Koçak M, Ünal Ö, et al. Nanoparticle based induction heating at low magnitudes of
1098 magnetic field strengths for breast cancer therapy. *J Magn Magn Mater*. 2019;483:169-177.
- 1099 136. Zhao P-P, Ge Y-W, Liu X-L, et al. Ordered arrangement of hydrated GdPO₄ nanorods in
1100 magnetic chitosan matrix promotes tumor photothermal therapy and bone regeneration against
1101 breast cancer bone metastases. *Chem Eng J*. 2020;381:122694.
- 1102 137. Kandasamy G, Sudame A, Maity D, et al. Multifunctional magnetic-polymeric nanoparticles
1103 based ferrofluids for multi-modal in vitro cancer treatment using thermotherapy and
1104 chemotherapy. *J Mol Liq*. 2019;293:111549.
- 1105 138. Teng Y, Du Y, Shi J, et al. Magnetic iron oxide nanoparticle-hollow mesoporous silica
1106 Spheres: Fabrication and potential application in drug delivery. *Curr Appl Phys*. 2020;20(2):320-
1107 325.
- 1108 139. Khaniabadi PM, Shahbazi-Gahrouei D, Aziz AA, et al. Trastuzumab conjugated porphyrin-
1109 superparamagnetic iron oxide nanoparticle: A potential PTT-MRI bimodal agent for herceptin
1110 positive breast cancer. *Photodiagnosis Photodyn Ther*. 2020 Sep;31:101896.
- 1111 140. Zatovicova M, Jelenska L, Hulikova A, et al. Carbonic anhydrase IX as an anticancer therapy
1112 target: preclinical evaluation of internalizing monoclonal antibody directed to catalytic domain.
1113 *Curr pharm Design*. 2010;16(29):3255-63.
- 1114 141. Klein S, Sommer A, Distel LV, et al. Superparamagnetic iron oxide nanoparticles as
1115 radiosensitizer via enhanced reactive oxygen species formation. *Biochem Biophys Res Commun*.
1116 2012 Aug 24;425(2):393-7.

1117 142. Kirakli EK, Takan G, Hoca S, et al. Superparamagnetic iron oxide nanoparticle (SPION)
1118 mediated in vitro radiosensitization at megavoltage radiation energies. *J Radioanalyt Nucl Chem.*
1119 2018;315(3):595-602.
1120 143. Abdul Rashid R, Zainal Abidin S, Khairil Anuar MA, et al. Radiosensitization effects and ROS
1121 generation by high Z metallic nanoparticles on human colon carcinoma cell (HCT116) irradiated
1122 under 150 MeV proton beam. *Open Nano.* 2019;4:100027.
1123 144. Mou Y, Wang J, Wu J, et al. Ferroptosis, a new form of cell death: opportunities and challenges
1124 in cancer. *J Hematol Oncol.* 2019 Mar 29;12(1):34.
1125 145. Ahmad T, Sarwar R, Iqbal A, et al. Recent advances in combinatorial cancer therapy via
1126 multifunctionalized gold nanoparticles. *Nanomed Nanotechnol Biol Med.* 2020;15(12):1221-
1127 1237.

1128

1129