

Multi-frequency shear modulus measurements discriminate tumorous from healthy tissues

Stéphane Nicolle, Jean-François Palierne, David Mitton, Hélène Follet, Cyrille B. Confavreux

▶ To cite this version:

Stéphane Nicolle, Jean-François Palierne, David Mitton, Hélène Follet, Cyrille B. Confavreux. Multi-frequency shear modulus measurements discriminate tumorous from healthy tissues. Journal of the mechanical behavior of biomedical materials, 2023, 140, pp.105721. 10.1016/j.jmbbm.2023.105721. hal-03999379

HAL Id: hal-03999379 https://hal.science/hal-03999379v1

Submitted on 21 Feb 2023 $\,$

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Multi-frequency shear modulus measurements discriminate tumorous from healthy tissues

S. Nicolle, J.-F. Palierne, D. Mitton, H. Follet, C.B. Confavreux

PII: S1751-6161(23)00074-7

DOI: https://doi.org/10.1016/j.jmbbm.2023.105721

Reference: JMBBM 105721

To appear in: Journal of the Mechanical Behavior of Biomedical Materials

Received Date: 19 July 2022

Revised Date: 7 February 2023

Accepted Date: 8 February 2023


Please cite this article as: Nicolle, S., Palierne, J.-F., Mitton, D., Follet, H., Confavreux, C.B., Multifrequency shear modulus measurements discriminate tumorous from healthy tissues, *Journal of the Mechanical Behavior of Biomedical Materials* (2023), doi: https://doi.org/10.1016/j.jmbbm.2023.105721.

This is a PDF file of an article that has undergone enhancements after acceptance, such as the addition of a cover page and metadata, and formatting for readability, but it is not yet the definitive version of record. This version will undergo additional copyediting, typesetting and review before it is published in its final form, but we are providing this version to give early visibility of the article. Please note that, during the production process, errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal pertain.

© 2023 Published by Elsevier Ltd.




Mouse samples



Subcutaneously injected with human breast cancer cells

Experiment and Modelling



Analysis and Conclusions

Mann-Whitney test	p-value for K	p-value for n
Fat – Tumor	0.00025	0.43
Muscle – Tumor	0.84	0.00041
Skin – Tumor	0.14	0.000019

Bold: significant difference at level $\alpha = 0.05$

$$K_{\text{fat}} << K_{\text{tumor}} \approx K_{\text{muscle}} \approx K_{\text{skin}}$$

 \rightarrow Tumors are distinguished from fat by the modulus magnitude

$$n_{\text{tumor}} \approx n_{\text{fat}} < n_{\text{muscle}} \approx n_{\text{skin}}$$

 \rightarrow Tumors are distinguished from muscle and skin by the **modulus frequency dependence**

- 1 Multi-frequency shear modulus measurements discriminate tumorous from
- 2 healthy tissues
- 3

4 S. Nicolle^{a,*}, J.-F. Palierne^b, D. Mitton^a, H. Follet^c, C. B. Confavreux^{c,d}

- 5
- 6 ^aUniv Lyon, Univ Gustave Eiffel, Univ Claude Bernard Lyon 1, LBMC UMR_T 9406, F-69622
- 7 Lyon, France;
- 8 <u>stephane.nicolle@univ-eiffel.fr</u> (S. Nicolle) and <u>david.mitton@univ-eiffel.fr</u> (D. Mitton)
- 9 ^bÉcole Normale Supérieure de Lyon, CNRS UMR5672, Laboratoire de Physique, F-69342 Lyon,
- 10 France;
- 11 <u>jfpalier@ens-lyon.fr</u> (J.-F. Palierne)
- 12 ^c Univ Lyon, Université Lyon 1, INSERM, LYOS UMR 1033, 69008, Lyon, France;
- 13 <u>helene.follet@inserm.fr</u> (H. Follet)
- 14 ^dCentre Expert des Métastases Osseuses (CEMOS), Departement de Rhumatologie, Hôpital Lyon
- 15 Sud, Hospices Civils de Lyon, Lyon, France;
- 16 <u>cyrille.confavreux@chu-lyon.fr</u> (C.B. Confavreux)
- 17
- *Corresponding author: Laboratoire de Biomécanique et de Mécanique des Chocs (LBMC),
 Université Gustave Eiffel Campus de Lyon, case 24, 25 Avenue François Mitterrand 69675 Bron
 cedex, France. Tel.: +33 (0)472 14 23 50; Fax: +33 (0)472 37 68 37; e-mail:
 stephane.nicolle@univ-eiffel.fr (S. Nicolle)
- 22
- 23
- 24
- 25
- 23
- 26
- 27

1 Abstract

2 As far as their mechanical properties are concerned, cancerous lesions can be confused 3 with healthy surrounding tissues in elastography protocols if only the magnitude of moduli is 4 considered. We show that the frequency dependence of the tissue's mechanical properties allows 5 for discriminating the tumor from other tissues, obtaining a good contrast even when healthy and 6 tumor tissues have shear moduli of comparable magnitude. We measured the shear modulus $G^*(\omega)$ of xenograft subcutaneous tumors developed in mice using breast human cancer cells, 7 8 compared with that of fat, skin and muscle harvested from the same mice. As the absolute shear modulus $|G^*(\omega)|$ of tumors increases by 42% (from 5.2 to 7.4 kPa) between 0.25 and 63 Hz, it 9 10 varies over the same frequency range by 77% (from 0.53 to 0.94 kPa) for the fat, by 103% (from 11 3.4 to 6.9 kPa) for the skin and by 120% (from 4.4 to 9.7 kPa) for the muscle. These measurements fit well to the fractional model $G^*(\omega) = K(i\omega)^n$, yielding a coefficient K and a power-law 12 13 exponent n for each sample. Tumor, skin and muscle have comparable K parameter values, that of 14 fat being significantly lower; the *p*-values given by a Mann-Whitney test are above 0.14 when 15 comparing tumor, skin and muscle between themselves, but below 0.001 when comparing fat with 16 tumor, skin or muscle. With regards the *n* parameter, tumor and fat are comparable, with *p*-values 17 above 0.43, whereas tumor differs from both skin and muscle, with *p*-values below 0.001. Tumor 18 tissues thus significantly differs from fat, skin and muscle on account of either the K or the n19 parameter, *i.e.* of either the magnitude or the frequency-dependence of the shear modulus.

20

21 Keywords: shear viscoelastic properties, tumorous tissues, soft tissues, MR elastography

22

1 1. Introduction

Emerging imaging and computational tools in medicine require a solid knowledge of the mechanical properties of pathological and healthy tissues, key ingredients of the computational models used in clinical imaging and computer-assisted surgical techniques.

5 As a first example, finite element models are increasingly used for surgeons' training, for predicting the organ deformation during a needle biopsy or for developing non-rigid registration 6 7 algorithms transforming images of an organ, taken at the time of diagnosis, to images projected during a conventional operation, robot-guided operation, or during radiotherapy (Tanner et al., 8 9 2002; Samani et al., 2004; Griesenauer et al., 2017). Approximating the tissues in these models by simple linear elastic materials is often a first approach. However, the ability of FE models to 10 11 correctly deform, provide the right haptic feel, or realistically distort preoperative images into 12 intraoperative ones critically depends on the accuracy of mechanical models of tissues going 13 beyond linear elasticity (Samani et al., 2007; Pathmanathan et al., 2008).

14 As a second example, the tissue elasticity measured using ultrasound or magnetic 15 resonance elastography holds promise as a biomarker for cancer diagnostic in deep organs, the 16 tumor usually being stiffer than the surrounding tissues (Hoyt et al., 2008a; Glaser et al., 2012; 17 Ramião et al., 2016; Samani et al., 2007; Wells et Liang, 2011). First thought of as the virtual 18 counterpart of the time-honored manual palpation, elastography initially used the linear elasticity 19 theory to reconstruct the elasticity images of soft tissues from information on propagating sound 20 waves (Krouskop et al., 1998; Sarvazyan et al., 2011; Wells et Liang, 2011; Gennisson et al., 21 2013). Taking advantage of both the direct elastogram interpretation and the simpler algorithmic 22 methods allowed by the linear elastic approach, a number of experimental works assess the Young 23 modulus or the shear modulus (two linear elastic parameters) of soft tissues from ex vivo and in 24 vivo protocols (Krouskop et al., 1998; Lawrence et al., 1998; McKnight et al., 2002; Gennisson 25 et al., 2013).

In many situations, soft tissues are thus reduced to their isotropic linear elastic properties for computational reasons when they exhibit anisotropy and nonlinear viscoelasticity. However,

these last characteristics cannot always be ignored and can even be used in particular to improve
the imaging tools and the interpretation of the resulting data to identify tumors.

For instance, in a preliminary work, Sinkus *et al.* (2000) surmised that tissue anisotropy could be used to distinguish benign from malignant tumors, the first ones being isotropic and the second ones anisotropic. However, Sinkus *et al.*, (2005) found later that some regions of healthy breast tissue can also be strongly anisotropic, making the tumor indistinguishable.

7 The large strain properties of tissues have been extensively studied as a most crucial feature 8 to discriminate soft tissues. Generally, soft tissues stiffen as the deformation increases. 9 Misinterpretation of results at different compression levels can thus occur when two neighboring 10 tissues exhibit different nonlinear behaviors. In this regard, some studies provide contradictory 11 results and opposite recommendations for the elastographic protocol: Krouskop et al. (1998) and 12 Wellman et al. (1999) observed from compression tests on cancerous breast samples excised from 13 patients that tumors exhibit stronger strain-nonlinearity than surrounding tissues, to the point that 14 the tumors can be distinguished from healthy tissues at high compressive strain while they are 15 indistinguishable from normal tissues at low compressive strain. The recommendation is then to increase the strain level during elastography to better discriminate the malignant tissues from the 16 17 surrounding tissues. On the other hand, Barr and Zhang (2012), using elastography on patient's 18 breast tissues in clinical situation, found that the contrast between Young's modulus of tumorous 19 and normal tissues decreases with increasing strain, normal tissue stiffening more than cancerous 20 tissue. Umemoto et al. (2014) reach the same conclusion through indentation tests on surgical samples of breast with cancerous lesions. These last two works then recommend that the 21 22 practitioner minimizes the precompression to better distinguish tumorous tissues from the 23 surrounding ones.

Viscoelastic properties of the tissues can also help discriminate benign from malignant tumors according to Sinkus *et al.* (2007) and Siegmann *et al.* (2010), the malignant ones having a more fluid behavior characterized by a higher loss (viscous) modulus than the benign ones. This

4

conclusion is however moderated by Xydeas *et al.* (2005), who stated that shear viscosity alone
 does not represent a good parameter for lesion classification.

3 Another feature of biological soft tissues seen as viscoelastic materials is that their modulus depends on the measurement frequency. First, together with the aforementioned large strain 4 5 behavior, this could contribute to the disparity of reported 'elastic' moduli in the literature using 6 elasticity instead of viscoelasticity when experiments are carried out at different frequencies. Second, the linear viscoelastic modulus of soft biological tissues generally increases with 7 8 frequency, the increase rate depending on the tissue (Kiss et al., 2004; Nicolle et al., 2013; Yeung 9 et al., 2019). In this work, we use this frequency dependence to distinguish breast tumors from 10 normal tissues. To this purpose, we compared the frequency-dependent behavior of tumor tissue 11 based on human breast cancer cells developed subcutaneously in a murine model (Peyruchaud et 12 al., 2001; Schmidt et al., 2016) together with surrounding normal tissues such as fat, skin and 13 muscle taken from the same mice. In order to avoid the abovementioned nonlinear stiffening, the viscoelastic behavior of each tissue is probed at very small strain. 14

15

16 **2. Materials and Methods**

17 2.1 Sample Origin

Using a xenograft model (Schmidt *et al.*, 2016), tumors were resected from immunocompromised six-week-old BALB/c nude female mice (Janvier Laboratories®) following a protocol approved by the Claude Bernard Lyon I University Ethical Committee for Animal Experimentation (DR2015-39).

Seven mice were anesthetized using an induction box with a 1 L air/min stream, 3% isoflurane concentration, and maintained with a mask at 2% isoflurane. The mice were then subcutaneously injected with MDA-B02 human breast cancer cells (Peyruchaud *et al.*, 2001) - *B02 being cells isolated from human mammary carcinoma* - (2.10⁶ cells in 100 µL Phosphate Buffered Saline (PBS) solution using a 1 mL syringe, Myjector 070151, Terumo Japan). After injection, tumor development was monitored through palpation and caliper, and as soon as its diameter was close


to 1 cm (more suitable for the subsequent mechanical test) or the surrounding tissues showed the
first signs of necrosis, the tumor was resected after having anesthetized and euthanatized the mouse
via cervical dislocation. The resected tumor was then immersed in phosphate-buffered saline
(PBS) until preparation for the mechanical test performed on the same day.


5 For further comparison of mechanical properties with healthy tissues, skin, muscle and fat 6 tissues were removed from each mouse in addition to the tumor. Skin was harvested from the 7 abdomen and the legs, muscle was removed from legs and fat was removed from the abdomen.

8

9 2.2 Sample Preparation

Due to two tumors in an advanced state of necrosis, only five tumors (B02) out of seven planned were usable. Slices of an average thickness of $790 \pm 2 \,\mu\text{m}$ (two slices by tumor) were cut by using a custom double-bladed scalpel as described in Nicolle *et al.* (2013). As tumors became necrotic before reaching a size large enough to cover the 10 mm diameter plates of the rheometer (Fig. 1), we adapted the measurement method to accommodate smaller and irregularly-shaped samples, as described in a forthcoming section.





(b)

Figure 1: Typical sample too small to match the glass plate of the rheometer (a). Size of tumor
B02 samples relative to the size of the glass plate (b).

19

16

The muscle samples were taken from the thighs with no particular attention paid to the direction of the fibers, although we are aware of the proven anisotropy of the muscle (Green *et al.*, 2013). The muscle slices were cut longitudinally along the femur, thus the fibers' direction lies

1 presumably in the slice plane. These samples covered the 10 mm diameter plates of the rheometer 2 and were slightly compressed between the rheometer plates to make them flat. The final average 3 thickness of muscle samples was $980 \pm 160 \,\mu$ m.

Each piece of skin was first stripped from the underlying connective and adipose layers,
and then cut using a punch to obtain a dermis sample of 10 mm diameter and of average
thickness 590 ± 195 μm.

7 The fat samples were 'fluid' enough to fill the 10 mm diameter plates of the rheometer with
8 about 500 μm thickness.

9 Once prepared, each sample was immediately immersed in a saline solution and preserved
10 at 4°C until the test. The number of samples tested for each type of tissue is given in Table 1.


11

12 2.3 Mechanical Tests

The mechanical device used in this study is a custom squeezing deformation rheometer 13 14 designed to determine the linear viscoelastic behavior of materials at acoustic frequencies. 15 Samples are placed between parallel circular plates of r = 5 mm radius separated by an adjustable 16 gap h. In order to prevent slip, the samples were glued to the plates using cyanoacrylate adhesive (Nicolle and Palierne, 2012). They were then surrounded with a saline solution in order to prevent 17 dehydration of the tissue, according to Nicolle and Palierne (2010). The entire device was finally 18 19 brought to body temperature (37°C) in a hermetic enclosure to prevent thermal gradients and water 20 losses.

The upper plate of the rheometer is vertically driven by a piezoelectric actuator through an oscillatory motion $\delta^* = \delta_0 e^{i\omega t}$, of amplitude $\delta_0 = 2$ nm and angular frequency $\omega = 2\pi f$ [our use of complex quantities follows standard practice, see Appendix]. An incompressible sample with no-slip boundary condition then undergoes a squeezing deformation with a local Poiseuille parabolic displacement profile (Fig. 2). The typical shear applied to the sample is given by the following order of magnitude considerations. The volume displaced by the motion of the plate is

1 $\Box \delta_0 r^2$ causing an outwards bulge of amplitude d and volume $\Box hrd$ at the edge (Fig. 2) where 2 r and r^2 are the order of magnitude of the plate perimeter and area, respectively. Equating these 3 volumes gives $d \sim \delta_0 r/h$, therefore the strain magnitude is of the order of $d/h \sim \delta_0 r/h^2$. With 4 typical gap $h = 800 \ \mu m$, the strain order of magnitude is $d/h \sim \delta_0 r/h^2 \sim 2 \times 10^{-5}$, well within the 5 linear regime, ensuring that the sample is not altered by the measurement.



6

Figure 2: The upper plate of radius *r* is initially separated from the lower plate by a height *h*, then
it is subjected to a vertical displacement δ which produces a parabolic-shaped bulge on the free
edge of the sample whose the maximum displacement is *d*.

10

12

11 The lower plate registers the oscillatory transmitted force

$$F^* = (F' + iF'')e^{i\omega t} \tag{1}$$

13 where F' and F'' are the in-phase and quadrature component of the complex force F^* , 14 respectively. As derived in the Appendix, this force can be written as the product

15
$$F^* = \beta G^* \delta^*$$
 (2)

being separately proportional to upper plate motion δ^* , to a shape factor β depending on the sample geometry, and to the sample's frequency-dependent complex shear modulus $G^*(\omega) = G'(\omega) + iG''(\omega)$. The real and imaginary parts G' and G'' are real numbers named the storage and the loss modulus, respectively. The fact that G^* is complex is responsible for a phase

lag between the oscillating quantities F^* and δ^* , which is a characteristic of viscoelasticity. For 1 circular plates of radius r separated by gap $h \square r$, the shape factor assumes the analytic form 2 $\beta = 3\pi r^4/2h^3$ (Reynolds 1886, our equation (A.11) with A = B = r). The tumor samples were 3 too small to fill the rheometer plates; their shapes were thus recorded and the shape factor β was 4 5 numerically computed for each of them according to equations (A.9)-(A.10) of Appendix, the 6 Poisson equation (A.9) being numerically solved using MathematicaTM (Wolfram Research, Inc., 7 100 Trade Center Drive, Champaign, IL 61820-7237, USA, version 13.0). Precise shape 8 determination however proved not to be critical since applying formula (A.11) to the best-fitting 9 ellipse (having the same area and second order moments ratio as the sample shape), as given by ImageJ (National Institute of Health, Bethesda, USA, Rasband 1997-2012), produces β values 10 11 within 4% of those exactly computed.

12 In short, the material viscoelastic modulus $G^* = F^* / \beta \delta^*$ is obtained from imposing the oscillatory 13 displacement δ^* , determining the form factor β and measuring the transmitted force F^* .

14 We fit our measurements of $G^*(\omega)$ to the linear part of the model proposed in Kiss *et al.* 15 (2004) and Nicolle *et al.* (2013) for biological soft tissues, drawing from Bagley and Torvik 16 (1986). The frequency-dependent complex modulus $G^*(\omega)$ is written

17

$$G^* = K(i \omega)^n = G' + iG'',$$
with $G' = K\omega^n \cos \frac{n\pi}{2}$ and $G'' = K\omega^n \sin \frac{n\pi}{2}$
(3)

18 in terms of two parameters: the coefficient K (Pa·s^{*n*}) and the power-law exponent n19 (dimensionless). The absolute modulus is the positive real quantity

20
$$|G^*| = \sqrt{{G'}^2 + {G''}^2} = K\omega^n$$
 (4)

The dimensionless parameter *n* characterizes the elastic/viscous balance, with n=0 for elastic materials and n=1 for Newtonian fluids. Graphically, *n* is the slope of $|G^*|$ vs ω in a log-log plot showing as a straight line, and *K* is the intercept at $\omega = 1$ rad s⁻¹, *i.e.* $f = 1/2\pi$ Hz.

A condition of physical admissibility is that *n* satisfies 0≤n≤1 in order to prevent divergence of
 the relaxation modulus (Tschoegel 1989, Chap. 6). A characteristic of the power-law frequency
 dependence is that the loss ratio

4

$$\frac{G''}{G'} = \tan\frac{n\pi}{2} \tag{5}$$

is a function of *n* only, independent of frequency. This constant ratio is a strong property of powerlaw models, it follows from either $G' \propto \omega^n$ or $G'' \propto \omega^n$, as a consequence of causality (Tschoegl 1989, Chap. 8).

8 The material parameters (K, n) are obtained for each sample by fitting the power-law model (3) 9 to the measured $G'(\omega)$ and $G''(\omega)$. We used the Levenberg-Marquardt algorithm provided by 10 OriginPro2020TM (OriginLab Corporation, One Roundhouse Plaza, Suite 303, Northampton, MA 11 01060, United States, version 2020) to fit simultaneously G' and G'' with the same (K, n) 12 parameters in "multi-data fit mode" by using "statistical" weighting, inversely proportional to the 13 data value, thus minimizing the quantity

14
$$\chi^{2} = \sum_{i} \frac{\left(G_{i}' - K\omega_{i}^{n} \cos\frac{n\pi}{2}\right)^{2}}{G_{i}'} + \frac{\left(G_{i}'' - K\omega_{i}^{n} \sin\frac{n\pi}{2}\right)^{2}}{G_{i}''}$$
(6)

15 where the sum extends to the 13 measurement frequencies $\omega_i = 2\pi f_i$, $f_i = 10^{(i-4)/5}$ Hz 16 = 0.251...63.1 Hz, i = 1...13, spanning 2½ decades. Such weighting increases the fit sensitivity 17 to *G*", of comparatively smaller magnitude than *G'*.

We performed two-by-two statistical comparisons of the *n* and *K* parameters distributions
 of the different tissues using a nonparametric Mann-Whitney test (provided by OriginPro2020TM,
 with a 0.05 significance level). The inter-sample variability of experimental data was also
 examined in relation to the variability of the model parameters.

- 22
- 23
- 24
- 25

1 **3. Results**

2 The power-law model (3) is fit to the measured $G'(\omega)$ and $G''(\omega)$ for each one of the 39 3 samples. For the four different tissues under investigation, namely B02 tumor, muscle, skin and 4 fat, the distribution of the fitted K and n parameters is given in Figure 3 and 4, and the average K 5 and *n* are reported in Table 1. The standard deviations given therein are inter-sample variabilities, 6 whereas the fitting uncertainty for the K and n value associated with each given sample is much 7 lower, about one tenth of the inter-sample variability. The relative inter-sample variability of K is 8 80% for fat and 50-55% for the other tissues; these values are typical of material constants of 9 biological tissues (Cook *et al.*, 2014). The relative inter-sample variability of the index n is 10 comparatively smaller, being about 7% to 24%. [Strictly speaking, since the physical dimension of K is Pa sⁿ, in comparing different K we compare values of $K/(1\text{Pa} \cdot \text{s}^n)$, *i.e.* the numerical value 11 12 of K in the MKS unit system.]. In addition, it can also be noted from Figure 5 that the intra-13 individual variability ($K = 3600 \pm 2600$; $n = 0.13 \pm 0.01$) represents a major contribution to the 14 total population variability ($K = 3160 \pm 1710$; $n = 0.133 \pm 0.009$ in Table 1) for skin.

15




Figure 3: Distribution of the parameter *K* (dynamic modulus at ω = 1 rad/s, coming from the fit
of all results obtained for each tissue. The set of data (diamonds) is represented for each
distribution. Comparison of these distributions by using a nonparametric Mann-Whitney test: (ns)
non-significant, (*) significant (*p*-value < 0.05), (**) very significant (*p*-value < 0.001),
(***) extremely significant (*p*-value < 0.0001). B02: subcutaneous tumor (human breast cancer
cells (B02))





Figure 4: Distribution of the parameter *n* (frequency-dependence of the dynamic modulus), for all
tissue samples. Comparison of these distributions by using a nonparametric Mann-Whitney test:
(ns) nonsignificant, (*) significant (*p*-value < 0.05), (**) very significant (*p*-value < 0.001),
(***) extremely significant (*p*-value < 0.0001). B02: subcutaneous tumor (human breast cancer
cells (B02))



1

Figure 5: Distribution of the model parameters *K* and *n* for the entire population of skin samples
(14 samples), and for skin samples from a single individual (4 samples).

4

5		#	K (Pa·s ⁿ)	n (-)
6	B02	10	4400 ± 2340	0.098 ± 0.018
7	Muscle	9	4430 ± 2400	0.138 ± 0.020
8	Skin	14	3160 ± 1710	0.133 ± 0.009
9	Fat	6	520 ± 400	0.109 ± 0.022

Table 1: Average material parameters of the fractional model (3) for mice tissues: subcutaneous
inter-sample variabilities, which are about ten times the parameters fitting precision for each given
sample.

13

14 The average moduli G' and G'' of tumor, muscle, skin and fat tissue are plotted versus 15 frequency on Figure 6, together with the model response according to equation (3) using the 16 average material parameters given in Table 1; the coefficient of determination R^2 averages to 0.95

for G' and 0.68 for G'' [in calculating R^2 , G' and G'' values are separately referred to their 1 2 respective average. Referring them to their common average would result in an unnaturally high R^2 , about 0.99]. For any given sample, the measured G' and G'' and their fit by equation (3) look 3 very similar to the averages reported in Figure 6. Although not warranted in general for non-linear 4 5 models (Robertson and Cook, 2014), the fact that our model (3), provided average K and nparameters, gives such a good fit to the average G' and G'' is due to the fact that it is linear in K 6 7 and that the only non-linear parameter, n, has a quite low variability, less than 2.2% of its (0...1) 8 admissible range, thus making the fit an almost linear fit over *K* only.










Figure 6: Symbols: average storage and loss modulus *vs* frequency of B02 tumor muscle, skin and fat. Continuous lines: fit by model (3) using the parameters of Table 1. B02 tumor: $R^2 = 0.864$ for G' and 0.617 for G'', Muscle: $R^2 = 0.982$ for G' and 0.602 for G'', Skin: $R^2 = 0.971$ for G' and 0. 873 for G'', Fat: $R^2 = 0.979$ for G' and 0.636 for G''.

15

1 Figure 3 and Table 1 show that the parameter K is quite similarly distributed for B02 tumor, 2 muscle and skin tissues, the only tissue with a recognizably different distribution of K being fat. 3 A Mann-Whitney test finds significant differences only between fat and the other tested tissues, as 4 reported on Figure 3. By contrast, as shown in Figure 4 and Table 1, the distributions of parameter 5 *n* reveal two different groups: the low-*n* fat and B02 tumor tissues, with *n* about 0.10, and the 6 (relatively) high-n muscle and skin, with n about 0.13. The Mann-Whitney test reveals no 7 significant difference between (high-*n*) muscle and skin, on the one hand, and between (low-*n*) fat 8 and B02 tumor, on the other hand, whereas significant differences appear between low-n and high-9 *n* tissues (Figure 4).

10 The aim of this study, differentiating B02 tumorous tissue from healthy tissues, cannot be 11 realized by just comparing the measured moduli. Figure 7a displays the average storage and loss 12 moduli of all tested tissues: it appears clearly that, within the entire explored frequency range, 13 tumor, skin and muscle are bunched together and can only be set apart from fat. Indeed, the intersample variability of G' and G'' is dominated by the variability of the K parameter, of 50% to 14 80% relative value, comparable with the spread of the average G' or G'' for tumor, skin and 15 muscle. The same issue arises when considering the absolute modulus $|G^*|$, which is the only 16 quantity reported in some studies: Figure 7b shows a similar confusion of $|G^*|$ for tumor, skin and 17 18 muscle, the only tissue standing out being fat.





1 Examining the model parameters K and n however brings a clearer perspective: the fat 2 being singled out due to its very low K, the tumor's lower n (0.10) can be distinguished from skin 3 and muscle's higher n (0.13). Tumor B02 (n = 0.098) thus appears as the most elastic tissue 4 compared to fat (n = 0.104), skin (n = 0.133) and muscle (n = 0.134), its lower *n* value making its 5 modulus less frequency-dependent. Over the 0.25-63 Hz frequency range we explored, the 6 modulus of the tumor increases by 42%, from 5.2 kPa to 7.4 kPa, whereas that of fat increases by 7 77%, from 0.53 kPa to 0.94 kPa, that of skin increases by 103%, from 3.4 kPa to 6.9 kPa, and that 8 of muscle increases by 120%, from 4.4 kPa to 9.7 kPa.

9

10 4. Discussion

11 New clinical tools such as elastography and computational patient-specific models require 12 a solid knowledge of the mechanical properties of pathological and healthy soft tissues, a task 13 made difficult by the anisotropy, the nonlinearity and the viscoelasticity of soft tissues. This 14 explains in part the disparity of the properties reported in the literature under various experimental 15 protocols.

16 Because soft tissues are viscoelastic, we propose that healthy and pathological tissues be 17 distinguished not only according to their moduli but also by considering the frequency dependence 18 of these moduli. Tissue's viscoelasticity is related to their microstructure, roughly speaking to the 19 density and arrangement of cells, as well as the network of fibers such as collagen. Cross-links in 20 the fiber network contribute to elasticity, while loose and dangling parts of the network add to the 21 viscosity (Sack et al., 2013). In particular, due to excessive and uncontrolled remodeling of the 22 extracellular fiber matrix, tumor tissues are known to be stiffer and more elastic (i.e. less 23 frequency-dependent) than normal tissues (Cox and Erler, 2011; Pepin et al., 2015; Li et al., 2019).

24 In this study, we observe that the shear modulus of the tumor tissue clearly differs from that of the fat, by almost an order of magnitude. It is however very close to that of the skin and 25 muscle, making the tumor indistinguishable from such fibrous tissues. However, the modulus' 26 27 frequency dependence, characterized by the fractional exponent n, is lower for the tumor (n =

1 0.098) than for the skin (n = 0.133) and the muscle (n = 0.138), although statistically 2 indistinguishable from that of fat (n = 0.109). This means that the tumors appear more elastic than 3 surrounding tissues in accordance with the abovementioned remodeling of their extracellular 4 matrix.

5 The primary importance of the moduli's frequency dependence warrants reliable experimental determinations. The model (3) predicts that log-log plots of G' and G'' versus ω 6 7 are straight lines, the gap between them, ruled by (5), being univocally related to their common 8 slope n. Mechanical measurements perform properly in this respect (our results, Kiss et al. (2004), 9 Holt et al. (2008)). By contrast, MRE (magnetic resonance elastography) seems inclined to produce moduli $G' \propto \omega^n$ and $G'' \propto \omega^n$, according to (3), with however an exponent *n* greater than 10 the value $2/\pi \arctan G''/G'$ prescribed by relation (5) (Sack *et al.*, 2009, Riek *et al.*, 2011); even 11 12 greater than 1, the limit of physically possible exponents (Sinkus et al., 2007, Bohte et al., 2017). Papazoglou et al. (2012) present both mechanical and MRE data on agar-based gels mimicking 13 biological tissues: whereas their mechanical data agree with our equations (3) and (5), their MRE 14 data show the aforementioned tendency to higher exponents n. MRE is thus a promising technique, 15 as it allows in vivo mechanical measurements, but not yet wholly reliable in the assessment of 16 17 frequency dependence.

18 That the tumor is more elastic than the healthy tissues is corroborated by Sack *et al.* (2013) 19 who observed that the exponent *n* slightly decreases with the fibrosis grade of liver, decreasing 20 from 0.266 for a normal liver to 0.238 for a fibrotic liver of grade F4, in relation with the 21 densification of the extracellular matrix occurring in tumorous tissue. This conclusion is confirmed 22 by Sauer *et al.* (2019) who proved that the power law exponent decreases with an additional 23 crosslinking of the collagen network composing the stromal tissue.

The mechanical properties found in this study are compared with those reported in the literature in Table 2. Despite differences in origin of the samples, in techniques and protocols used, the current data are found to be consistent with the values presented in this Table, which reports both *in vitro* and *in vivo* studies. The comparison *in vivo/in vitro* is never straightforward in the

1 mechanical studies since the deformation geometry is controlled in vitro but the physiological 2 conditions are not strictly satisfied, causing postmortem effects (Chatelin et al., 2011), while the 3 in vivo conditions preclude an exact control of the deformation geometry. Nevertheless, our 4 rheometric data converge in magnitude with those coming from MRE, which shows that the *in* 5 *vitro* conditions applied in the current study (saline solution at body temperature for hydrating the 6 tissue during the test, according to Nicolle and Palierne (2010)) satisfactorily reproduce the *in vivo* 7 conditions of MRE. This is supported by Kerdok et al. (2006), who found similar moduli in 8 mechanical measurements on *in vivo* and *ex vivo* liver, perfused with a saline solution at body 9 temperature. Contrary to their protocol, however, our tissue samples are hydrated but not 10 pressurized. How pressurization affects the tissue viscoelasticity remains to be determined; 11 moreover, as discussed by Kerdok *et al*, these effects are likely organ-dependent.

At this stage, it can be stated that when the tumor tissues and the surrounding tissues have comparable stiffness, a multi-frequency assessment of the small-strain shear modulus is in order, to facilitate the distinction of a tumor from a healthy tissue environment, in particular in the cases of benign tumors and suspicious lesions sought using MRE protocols.

A concern of this study is whether the tested tumors are representative of breast cancers. Although human in origin, the tumor cells were developed subcutaneously in mice instead of human breasts. The comparison of the viscoelastic properties was made between the tumor, the skin and the muscle coming from different anatomical regions in mice, not with the surrounding tissues present in the breast, such as the adipose and the fibroglandular tissues. It would be worthwhile to validate the present observations and conclusions on pathological breast tissues resected from patients.

23

24 **5.** Conclusions

The methods developed in this study allow measuring irregularly shaped samples of centimeter size to assess their viscoelastic properties in *in vitro* conditions. By comparing subcutaneous tumor with fat, muscle and skin in a murine model, we show that the frequency

dependence of the tissues' viscoelastic properties allows distinguishing tumors from other soft tissues, even of comparable moduli, the tumor's modulus being less frequency-dependent than that of normal tissues. The present results thus call for a deeper investigation of the viscoelastic properties of healthy (adipose and fibroglandular tissues) and pathological breast tissues at different grades (fibroadenoma and carcinoma tissues).

6

Journal Pre-proof

Skin Current Study Nicolle <i>et al.</i> (2017) Lamers <i>et al.</i> (2013) Rieger and Deem (1974) Holt <i>et al.</i> (2008) Corr <i>et al.</i> (2009)	Species mouse rat human human human porcine	Exp. Techniques rheometer rheometer rheometer tensile tests rheometer tensile tests	/G[*]/ at 1 Hz 4 kPa 7.3 kPa 2.7 kPa - -	Exponent <i>n</i> 0.133 0.137 - 0.173 0.16 0.17 – 0.22		
Muscle Current Study Tan et al. (2015) Hoyt <i>et al.</i> (2008b) Riek <i>et al.</i> (2011)	Species mouse bovine human bovine	Exp. Techniques rheometer rheometer sonoelastography MR elastography	/ G [*] / at 1 Hz 5.6 kPa 5.7 kPa -	Exponent <i>n</i> 0.138 - - 0.25	/G[*]/ at 140 H 11.3 kPa [†] - 9.95 kPa -	z/G^* between 200 Hz and 800 Hz 11.9 to 14.5 kPa [†] ; $/G^*/ = 4430\omega^{0.138}$ - 12.25 to 35.9 kPa [†] ; $/G^*/ = 3640\omega^{0.25}$
Fat Current Study Samani <i>et al.</i> (2007) Chen <i>et al.</i> (2013) Lawrence <i>et al.</i> (1998) Lorenzen <i>et al.</i> (2002)	Species mouse human human human	Exp. Techniques rheometer indentation tests MR elastography MR elastography MR elastography	/G[*]/ at 0.1 H z 0.49 kPa [†] 1.1 kPa [‡] - -	z /G*/ at 40 Hz 0.92 kPa - 0.33 kPa -		veen 50 and 100 Hz median = 2 kPa)

[†] Using our Eq. (3) with material parameters from Table (1). [‡] Young's modulus / 3 (owing to incompressibility)

Table 2: Comparison of the current data to the literature $(/G^*/$ is the absolute shear modulus, the exponent *n* characterizes the frequency-dependence of the

shear modulus through the power law $|G^*| = K\omega^n$)

1

2 Appendix: deformation of a sample of arbitrary shape in the rheometer

Reynolds (1886) considered the squeeze flow of a Newtonian fluid as a special case of lubricating flow; here we extend his equations (9-29) to linear viscoelasticity in harmonic regime and to arbitrary geometry. [We follow the IUPAC recommendations pertaining to linear viscoelasticity (Kaye *et al.* 2008, §5): Asterisks designate complex quantities, being either oscillating quantities, here $\delta^*, \mathbf{d}^*, p^*, \mathbf{\sigma}^*$ or F^* , whose real part corresponds to the physical quantity, or (non-oscillating) ratios of oscillating quantities such as G^* , assuming non-real values when there is a phase lag between these quantities.]

10 The sample is a slab of thickness h and arbitrary section S, placed between two plates, its upper 11 and lower faces following the corresponding plate's motion without slip; the upper face thus moving by $\delta^* = \delta_0 e^{i\omega t}$ in the perpendicular direction whereas the lower face remains fixed. Let 12 the upper and lower plates be in the (x-y)-plane at $z = h + \delta^*$ and z = 0, respectively. Assuming 13 $\delta_0 \square h$, calculations will be carried out at linear order in δ_0/h , within the frame of linear 14 viscoelasticity, and, in the lubrication approximation (Reynolds 1886), at the lowest significant 15 order in $h/r \square 1$ (r being a typical linear extension of surface S, its radius if S is circular). 16 The no-slip boundary conditions for the space- and time-dependent displacement field $\mathbf{d}^*(x, y, z, t)$ 17 18 read

19
$$\begin{cases} \mathbf{d}^* = \mathbf{0}, & z = 0\\ \mathbf{d}^* = d_z^* \mathbf{e}_z = \delta^* \mathbf{e}_z, & z = h \end{cases}$$
 (A.1)

20 with \mathbf{e}_z the unit vector in the z-direction. The material obeys the incompressibility condition

$$\nabla \cdot \mathbf{d}^* = 0 \tag{A.2}$$

22 where ∇ is the three-dimensional gradient operator, and the dynamics equation reduces to

23
$$\nabla p^* = G^* \Delta \mathbf{d}^* \tag{A.3}$$

1 where $\Delta = \nabla^2$ is the Laplacian operator, when the inertial term $\rho \partial^2 \mathbf{d}^* / \partial t^2 = -\rho \omega^2 \mathbf{d}^*$ is 2 negligible, *i.e.* when $|\rho \omega^2 \mathbf{d}^* / G^* \Delta \mathbf{d}^*| \square \omega^2 \tau^2 \square 1$, where $\tau = h \sqrt{\rho / |G^*|}$ is the characteristic time 3 of transverse waves [in our measurements, $|G^*| \sim 10^3 \text{ Pa}$, $\rho \sim 10^3 \text{ kg m}^{-3}$ and $h \sim 10^{-3} \text{ m}$, 4 therefore $\tau \sim 10^{-3} \text{ s}$; this sets an upper frequency limit $f = \omega / 2\pi < 1/2\pi\tau = 160 \text{ Hz}$].

5 The displacement is written as the sum of a Poiseuille parabolic profile \mathbf{d}_{\square}^* parallel to the plates,

6 driven by the pressure gradient, and a z-component $d_z^* \mathbf{e}_z$ obeying boundary conditions (A.1):

7
$$\mathbf{d}^* = \mathbf{d}^*_{\square} + d^*_z \mathbf{e}_z, \qquad \mathbf{d}^*_{\square} = -\frac{z(h-z)}{2G^*} \nabla_{\square} p^*$$
(A.4)

8 with $\nabla_{\Box} = \mathbf{e}_x \partial/\partial x + \mathbf{e}_y \partial/\partial y$. Rewriting the divergence of the displacement as 9 $\nabla \cdot \mathbf{d}^* = \nabla_{\Box} \cdot \mathbf{d}_{\Box}^* + \partial d_z^*/\partial z$, integrating incompressibility condition (A.2) over z from 0 to h and 10 using boundary conditions (A.1) results in

11
$$\Delta_{\square} p^* = \frac{12}{h^3} G^* \delta^*$$
 (A.5)

12 where $\Delta_{\Box} = \nabla_{\Box}^2 = \partial^2 / \partial x^2 + \partial^2 / \partial y^2$ is the two-dimensional Laplacian. The boundary condition for 13 the pressure is that it vanishes at the edge of the sample, i.e. on the boundary ∂S of S:

14
$$p^*(x, y) = 0$$
 for $(x, y) \in \partial S$ (A.6)

A fundamental feature of squeezing deformations is that the typical magnitude of \mathbf{d}_{\Box} is much greater than that of d_z^* : Because the sample volume is constant, outward (resp. inward) bulging of the sample edge occurs when the plates get closer (resp. farther away). The perimeter length is $\sim r$, the area of the free surface at the sample edge is thus $\sim hr$ and the bulge volume is $\sim hr d_{\Box}$, equal to the volume $S\delta^*$ swept by the upper plate motion, so we have $d_{\Box}^* \sim \delta^* r/h$ with $r \Box h$.

20 Since the *z*-component magnitude is $d_z^* \sim \delta^*$, one has

21
$$d_{\square}^* \sim \frac{r}{h} d_z^* \quad \square \quad d_z^* \sim \delta^*$$
 (A.7)

1	The force on the plates obtains by integrating the surface force
2	$\mathbf{\sigma}^* \cdot \mathbf{e}_z = G^* (\nabla \mathbf{d}^* + (\nabla \mathbf{d}^*)^T) \cdot \mathbf{e}_z - p^* \mathbf{e}_z$ over <i>S</i> at $z = h$. According to (A.5), the pressure
3	magnitude is $p^* \sim G^* \delta^* S / h^3$, whereas due to condition (A.1) the only non-zero component of
4	$G^*(\nabla \mathbf{d}^* + (\nabla \mathbf{d}^*)^T)$ at $z = h$ is $G^* \partial \mathbf{d}^* / \partial z = h \nabla_{\Box} p^* / 2 + G^* \mathbf{e}_z \partial d_z / \partial z$, negligible with respect to p^*
5	since $h\nabla_{\Box} p^* \sim hp^*/r \sim G^* \delta^* r/h^2$ and $G^* \partial d_z/\partial z \sim G^* \delta^*/h$. The force the material exerts on the
6	upper plate is then in the <i>z</i> -direction and reduces to
7	$F^* = -\int_S p^* \mathrm{d}S \tag{A.8}$
8	The solution to the problem then follows: Let the function $\phi(x, y) \ge 0$ be defined within <i>S</i> and on
9	the boundary ∂S , such that
10	$\begin{cases} \Delta \phi = -1 & \text{within } S \\ \phi = 0 & \text{on } \partial S \end{cases} $ (A.9)
11	$12 C^* S^* / 1 C S S S^* / 1 C S S S S S S S S S S S S S S S S S S$

11 then the pressure (A.5) reads $p^* = -\frac{12}{h^3} G^* \delta^* \phi$ and the force F^* can be written $F^* = \beta G^* \delta^*$, where

12
$$\beta = \frac{12}{h^3} \int_S \phi \,\mathrm{d}S \tag{A.10}$$

13 As an example, when S is an ellipse of semi-axes A and B along the x- and y-axes, one has 14 $\phi = (1 - x^2/A^2 - y^2/B^2)/(2/A^2 + 2/B^2)$, therefore

15
$$\beta = \frac{3\pi}{h^3} \frac{A^3 B^3}{A^2 + B^2}$$
(A.11)

16

17

18 Acknowledgements

19 The authors are deeply grateful to Lamia Bouazza and Sandra Geraci for their technical supports 20 on cells development and animals' experiment, and with the use of the ALECS platform. This 21 work was partly funded by LabEx Primes (ANR-11-LABX-0063) and MSD AVENIR Research 22 Grant (CBC), and Philippe Clézardin (Labex DevWeCan). 1

6 **References**

- 7 Bagley, R.L., Torvik, P.J., 1986. On the fractional calculus model of viscoelastic behavior. Journal
- 8 of Rheology 30(1), 133-155. https//doi.org/10.1122/1.549887

9 Barr, R.G., Zhang, Z., 2012. Effects of precompression on elasticity imaging of the breast. Journal

10 of Ultrasound in Medicine 31(6), 895-902. https//doi.org/10.7863/jum.2012.31.6.895

Bohte, A.E., Nelissen, J.L., Runge, J.H., Holub, O., Lambert, S.A., de Graaf, L., Kolkman, S., van
der Meij, S., Stoker J., Strijkers, G.J., Nederveen, A.J., Sinkus, R., 2017. Breast magnetic
resonance elastography: a review of clinical work and future perspectives. NMR in
Biomedicine 31:e3932. https://doi.org/10.1002/nbm.3932

Chatelin, S., Oudry, J., Périchon, N., Sandrin, L. Allemann, P., Soler, L., Willinger, R., 2011. *In vivo* liver tissue mechanical properties by transient elastography : Comparison with dynamic
mechanical analysis. Biorheology 48, 75-88. https://doi.org/10.3233/BIR-2011-0584

Chen J., Brandt K., Ghosh K., Grimm R., Glaser K., Kugel J., Ehman R., 2013. Noncompressive
MR elastography of breasts. Proceedings of the International Society of Magnetic Resonance
Medicine 21, 1736. https://archive.ismrm.org/2013/1736.html

Cook, D., Julias, M., Nauman, E., 2014. Biological variability in biomechanical engineering
research: Significance and meta-analysis of current modeling practices. Journal of Biomechanics
47, 1241-1250. https//doi.org/10.1016/j.jbiomech.2014.01.040

Corr, D.T., Gallant-Behm, C.L., Shrive, N.G., Hart, D.A., 2009. Biomechanical behavior of scar
tissue and uninjured skin in a porcine model. Wound Repair and regeneration 17, 250-259.
https://doi.org/10.1111/j.1524-475X.2009.00463.x

- Cox, T.R., Erler, J., T., 2011. Remodeling and homeostasis of the extracellular matrix:
 implications for fibrotic deseases and cancer. Disease Models and Mechanisms 4, 165-178.
 https://doi.org/10.1242/dmm.004077
- Gennisson JL, Deffieux T, Fink M, Tanter M., 2013. Ultrasound elastography: principles and
 techniques. Diagnostic and Interventional Imaging 94(5), 487-495.
 https://doi.org/10.1016/j.diii.2013.01.022
- Glaser, K.J., Manduca, A., Ehman, R.L., 2012. Review of MR elastography applications and
 recent developments. Journal of Magnetic Resonance Imaging 36(4), 757-774.
 https://doi.org/10.1002/jmri.23597
- Green, M.A., Geng, G., Qin, E., Sinkus, R., Gandevia, S.C., Bilston, L.E., 2013. Measuring
 anisotropic muscle stiffness properties using elastography. NMR in Biomedicine 26, 1387-1394.
 https://doi.org/10.1002/nbm.2964
- Griesenauer, R.H., Weis, J.A., Arlinghaus, L.R., Meszoely, I.M., Miga, M.I., 2017. Breast tissue
 stiffness estimation for surgical guidance using gravity-induced excitation. Physics in Medicine
 and Biology 62(12), 4756-4776. https://doi.org/10.1088/1361-6560/aa700a
- Holt, B., Tripathi, A., Morgan, J., 2008. Viscoelastic response of human skin to low magnitude
 physiologically relevant shears. Journal of Biomechanics 41, 2689-2695.
 https//doi.org/10.1016/j.jbiomech.2008.06.008
- 19 Hoyt, K., Castaneda B., Zhang, M., Nigwekar P., Di Sant'Agnese, P.A., Joseph, J.V., Strang, J.,
- 20 Rubens, D.J., Parker, K.J., 2008a. Tissue elasticity properties as biomarkers for prostate cancer.
- 21 Cancer Biomarkers 4(4-5), 213-225. https//doi.org/10.3233/CBM-2008-44-505
- 22 Hoyt, K., Kneezel, T., Castaneda, B., Parker, K.J., 2008b. Quantitative sonoelastography for the
- 23 in vivo assessment of skeletal muscle viscoelasticity. Physics in Medicine & Biology 53(15),
- 24 4063-4080. https//doi.org/10.1088/0031-9155/53/15/004

- Kaye, A. Stepto, R. F. T., Work, W. J., Alemán, J. V, Malkin, A. Ya., 2009. Definitions of terms
 relating to the non-ultimate mechanical properties of polymers (Recommendations 1998), Pure
 and Applied Chemistry 70(3), 701-754. https://doi.org/10.1351/pac199870030701
- Kerdok, A.E., Ottensmeyer, M.P., Howe, R.D., 2006. Effects of perfusion on the viscoelastic
 characteristics of liver. Journal of Biomechanics 39, 2221-2231.
 https://doi:10.1016/j.jbiomech.2005.07.005
- Kiss, M.Z., Varghese, T., Hall, T.J., 2004. Viscoelastic characterization of in vitro canine tissue.
 Physics in Medicine and Biology 49, 4207-4218. https://doi.org/10.1088/0031-9155/49/18/002
- 9 Krouskop, T.A., Wheeler, T.M., Kallel, F., Garra, B.S., Hall, T., 1998. Elastic moduli of breast
 10 and prostate tissues under compression. Ultrasonic Imaging 20(4), 260-274.
 11 https//doi.org/10.1177/016173469802000403
- Lawrence, A.J., Muthupillai, R., Rossman, P.J., Smith, J.A., Manduca, A., Ehman, R.L., 1998.
 Magnetic resonance elastography of the breast: Preliminary experience. Proceedings of the
 International Society for Magnetic Resonance in Medicine, Sydney, Australia. Magnetic
 Resonance Elastography of the Breast ISMRM http://cds.ismrm.org > ismrm-1998
- Lamers, E., van Kempen, T.H.S., Baaijens, F.P.T., Peters, G.W.M., Oomens, C.W.J., 2013. Large
 amplitude oscillatory shear properties of human skin. Journal of the Mechanical Behavior of
 Biomedical Materials 28, 462-470. https//doi.org/10.1016/j.jmbbm.2013.01.024
- Li, J., Zormpas-Petridis, K., Boult, J.K.R., Reeves, E.L., Heindl, A., Vinci, M., Lopes, F.,
 Cummings, C., Springer, C.J., Chesler, L., Jones, C., Bamber, J.C., Yuan, Y., Sinkus, R., Jamin,
 Y., Robinson, S.P., 2019. Investigating the contribution of collagen to the tumor biomechanical
 phenotype with noninvasive magnetic resonance elastography. Cancer Research 79(22), 58745883. https://doi.org/10.1158/0008-5472.CAN-19-1595

- Lorenzen J., Sinkus R., Lorenzen M., Dargatz M., Leussler C., Röschmann P., Adam G., 2002.
 MR elastography of the breast: preliminary clinical results. Röfo 174(7), 830-834.
 https://doi.org/10.1055/s-2002-32690
- McKnight, A.L., Kugel, J.L., Rossman, P.J., Manduca, A., Hartmann, L.C., Ehman, R.L., 2002.
 MR elastography of breast cancer: Preliminary results. American Journal of Roentgenology
- 6 178(6), 1411-1417. https//doi.org/10.2214/ajr.178.6.1781411
- Nicolle, S., Palierne, J.-F., 2010. Dehydration effect on the mechanical behaviour of biological
 soft tissues: observations on kidney tissues. Journal of the Mechanical Behavior of Biomedical
 Materials 3, 630-635. https://doi.org/10.1016/j.jmbbm.2010.07.010
- 10 Nicolle, S., Palierne, J.-F, 2012. On the efficiency of attachment methods of biological soft tissues
- in shear experiments. Journal of the Mechanical Behavior of Biomedical Materials 14, 158-162.
 https://doi.org/10.1016/j.jmbbm.2012.05.002
- Nicolle, S., Noguer, L., Palierne, J.-F., 2013. Shear mechanical properties of the porcine pancreas:
 Experiments and analytical modeling. Journal of the Mechanical Behavior of Biomedical
 Materials 26, 90-97. https//doi.org/10.1016/j.jmbbm.2013.05.029
- Nicolle, S., Decorps, J., Fromy, B., Palierne, J.-F., 2017. New regime in the mechanical behavior
 of skin: strain-softening occurring before strain-hardening. Journal of the Mechanical Behavior of
 Biomedical Materials 69, 98-106. https//doi.org/10.1016/j.jmbbm.2016.12.021
- Papazoglou, S., Hirsch, S., Braun, J., Sack, I., 2012. Multifrequency inversion in magnetic
 resonance elastography. Physics in Medicine and Biology 57 (2012) 2329–2346
 https//doi.org/10.1088/0031-9155/57/8/2329
- Pathmanathan, P., Gavaghan, D.J., Whiteley, J.P., Chapman, S.J., Brady, J.M., 2008. Predicting
 tumor location by modeling the deformation of the breast. IEEE Transactions on Biomedical
 Engineering 55(10), 2471-2480. https//doi.org/10.1109/TBME.2008.925714

1	Pepin, K.M., Ehman, R.L., McGee, K.P., 2015. Magnetic resonance elastography (MRE) in
2	cancer: Technique, Analysis and applications. Progress in Nuclear Magnetic Resonance
3	Spectroscopy 90-91, 32-48. https//doi.org/10.1016/j.pnmrs.2015.06.001
4	Peyruchaud, O., Winding, B., Pécheur, I., Serre, CM., Delmas, P., Clézardin, P., 2001. Early

5 Detection of Bone Metastases in a Murine Model Using Fluorescent Human Breast Cancer Cells: 6 Application to the Use of the Bisphosphonate Zoledronic Acid in the Treatment of Osteolytic 7 Lesions. Journal of Bone Mineral Research 16(11), 2027-2034. and 8 https//doi.org/10.1359/jbmr.2001.16.11.2027

9 Ramião, N.G., Martins, P.S., Rynkevis, R., Fernandes, A.A., Barroso, M., Santos D.C., 2016.
10 Biomechanical properties of breast tissues, a state-of-the-art review. Biomechanics and Modeling

11 in Mechanobiology 15, 1307-1323. https://doi.org/10.1007/s10237-016-0763-8

Rasband W.S., 1997–2012. ImageJ, U.S. National Institutes of Health, Bethesda, Maryland, USA,
https://imagej.nih.gov/ij/.

Reynolds, O., 1886. On the Theory of Lubrication and its Application to Mr BEAUCHAMP TOWER'S
Experiments, including an Experimental Determination of the Viscosity of Olive Oil. Proc. Roy.

16 Soc.177, 157-234. https//doi.org/10.1098/rstl.1886.0005

Rieger, M.M., Deem, D.E., 1974. Skin moisturizers. I – Methods for measuring water regain,
mechanical properties, and transepidermal moisture loss of stratum corneum. Journal of the
Society of Cosmetic Chemists 25, 239-252. https://library.scconline.org/v025n05/1

Riek, K., Klatt, D., Nuzha, H., Mueller, S., Neumann, U., Sack, I., Braun, J., 2011. Wide-range
dynamic magnetic resonance elastography. Journal of Biomechanics 44, 1380-1386.
https//doi.org/10.1016/j.jbiomech.2010.12.031

- 1 Robertson, D., Cook, D., 2014. Unrealistic statistics: How average constitutive coefficients can
- 2 produce non-physical results. Journal of the Mechanical Behavior of Biomedical Materials 40,
- 3 234-239. https://doi.org/10.1016/j.jmbbm.2014.09.006
- Sack, I., Beierbach, B., Wuerfel, J., Klatt, D, Hamhaber, U, Papazoglou, S, Martus, P, Braun, J,
 2009. The impact of aging and gender on brain viscoelasticity. NeuroImage 46, 652-657.
 https://doi.org/10.1016/j.neuroimage.2009.02.040
- Sack, I., Jöhrens, K., Würfel, J., Braun, J., 2013. Structure-sensitive elastography: on the
 viscoelastic powerlaw behavior of *in vivo* human tissue in health and disease. Soft Matter 9, 56725680. https://doi.org/10.1039/c3sm50552a
- Samani, A., Plewes, D., 2004. A method to measure the hyperelastic parameters of ex vivo breast
 tissue samples. Physics in Medicine and Biology 49, 4395-4405. https//doi.org/10.1088/00319155/49/18/014
- Samani, A., Zubovits, J., Plewes, D., 2007. Elastic moduli of normal and pathological human
 breast tissues: A inversion-technique-based investigation of 169 samples. Physics in Medicine &
 Biology 52(6), 1565-1576. https//doi.org/10.1088/0031-9155/52/6/002
- Sarvazyan, A., Hall T.J., Urban, M.W., Fatemi, M., Aglyamov, S.R., Garra, B.S., 2011. An
 overview of elastography-An emerging branch of medical imaging. Current Medical Imaging
 Reviews 7, 255-282. https://doi.org/10.2174/157340511798038684
- 19 Sauer, F., Oswald, L., Ariza de Schellenberger, A., Tzschätzsch, H., Schrank, F., Fischer, T.,
- 20 Braun, J., Mierke, C.T., Valiullin, R., Sack, I., Käs, J.A., 2019. Collagen networks determine
- 21 viscoelastic properties of connective tissues yet do not hinder diffusion of the aqueous solvent.
- 22 Soft Matter 15, 3055-3064. https//doi.org/10.1039/c8sm02264j

1	Schmidt, K.M., Geissler, E.K., Lang, S.A., 2016. Subcutaneous murine xenograft models: A
2	critical tool for studying human tumor growth and angiogenesis in vivo. Methods in Molecular
3	Biology 1464, 129-137. https//doi.org/10.1007/978-1-4939-3999-2_12

- 4 Siegmann, K.C., Xydeas, T., Sinkus, R., Kraemer, B., Vogel, U., Claussen, C.D., 2010. Diagnostic
- 5 Value of MR Elastography in Addition to Contrast-Enhanced MR Imaging of the Breast-Initial
- 6 Clinical Results. European Radiology 20, 318-325. https//doi.org/10.1007/s00330-009-1566-4
- Sinkus, R., Lorenzen, J., Schrader D., Lorenzen D., Dargatz M., Holz D., 2000. High-resolution
 tensor MR elastography for breast tumour detection. Physics in Medicine & Biology 45, 16491664. https://doi.org/10.1088/0031-9155/45/6/317
- 10 Sinkus, R., Tanter, M., Catheline, S., Lorenzen, J., Kuhl, C., Sondermann, E., Fink, M., 2005.

Imaging anisotropic and viscous properties of breast tissue by magnetic resonance-elastography.

12 Magnetic Resonance in Medicine 53, 372-387. https://doi.org/10.1002/mrm.20355

11

- Sinkus, R., Siegmann, K., Xydeas, T., Tanter, M., Claussen, C., Fink, M., 2007. MR Elastography
 of Breast Lesions: Understanding the Solid/Liquid Duality Can Improve the Specificity of
 Contrast-Enhanced MR Mammography. Magnetic Resonance in Medicine 58:1135–1144.
 https://doi.org/10.1002/mrm.21404
- Tan, K., Cheng, S., Jugé, L., Bilston, L.E., 2015. Characterizing skeletal muscle under large strain
 using eccentric and Fourier-Transform rheology. Journal of Biomechanics 48:3788-3795.
 https://doi.org/10.1016/j.jbiomech.2015.08.025
- 20 Tanner, C., Degenhard, A., Schnabel, J.A., Castellano-Smith, A.D., Hayes, C., Sonoda, L.I.,
- 21 Leach, M.O., Hose, D.R., Hill, D.L.G., Hawkes, D.J., 2002. Comparison of biomechanical breast
- 22 models : a case of study. Proceedings of SPIE Volume 4684, Medical Imaging 2002: Image
- 23 Processing, San Diego, California, United States. https//doi.org/10.1117/12.467155

- Tschoegl, N.W., 1989. The phenomenological theory of linear viscoelastic behavior: An
 introduction. Springer-Verlag Berlin Heidelberg, p 769. https//doi.org/10.1007/978-3-642-73602 5
- Umemoto, T., Ueno, E., Matsumara, T., Yamakawa, M., Bando, H., Mitake, T., Shiina, T., 2014. *Ex vivo* and *in vivo* assessment of the non-linearity of elasticity properties of breast tissues for
 quantitative strain elastography. Ultrasound in Medicine & Biology 40, 1755-1768.
 https://doi.org/10.1016/j.ultrasmedbio.2014.02.005
- Wellman, P.S., Howe, R.D., Dalton, E., Kern, K.A., 1999. Breast tissue stiffness in compression
 is correlated to histological diagnosis. Harvard BioRobotics Laboratory Technical Report, 1-15.
- 10 Wells, P.N.T., Liang, H.-D., 2011. Medical ultrasound: imaging of soft tissue strain and elasticity.
- 11 Journal of the Royal Society Interface 8(64), 1521-1549. https//doi.org/10.1098/rsif.2011.0054
- Yeung, J., Jugé, L., Hatt, A., Bilston, L.E., 2019. Paediatric brain tissue properties measured with
 magnetic resonance elastography. Biomechanics and Modeling in Mechanobiology 18, 14971505. https//doi.org/10.1007/s10237-019-01157-x
- Xydeas, T., Siegmann, K., Sinkus, R., Krainick-Strobel, U., Miller, S., Claussen, C.D., 2005.
 Magnetic resonance elastography of the breast: Correlation of signal intensity data with
 viscoelastic properties. Investigative Radiology 40(7), 412-420.
 https//doi.org/10.1097/01.rli.0000166940.72971.4a

Highlights

- The frequency dependence of moduli discriminates tumors from healthy tissues
- Tumors are more elastic than healthy tissues
- The spring-pot model describes the linear viscoelastic behavior of soft tissues
- Multi-frequency measurements could improve diagnosis by MR elastography

Journal Pre-proof

Declaration of interests

☑ The authors declare that they have no known competing financial interests or personal relationships that could have appeared to influence the work reported in this paper.

□ The authors declare the following financial interests/personal relationships which may be considered as potential competing interests:

Journal Presson