



HAL
open science

Temperature-dependent elasticity of single crystalline graphite

Franck Polewczyk, Jean-Marc Leyssale, Paul Lafourcade

► **To cite this version:**

Franck Polewczyk, Jean-Marc Leyssale, Paul Lafourcade. Temperature-dependent elasticity of single crystalline graphite. Computational Materials Science, 2023, 220, pp.112045. 10.1016/j.commatsci.2023.112045 . hal-04014084

HAL Id: hal-04014084

<https://hal.science/hal-04014084>

Submitted on 3 Mar 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Temperature-dependent elasticity of single crystalline graphite

Franck Polewczyk^{a,b,c}, Jean-Marc Leyssale^c, Paul Lafourcade^{a,b,*}

^aCEA DAM DIF, 91297 Arpajon, France

^bUniversity of Paris-Saclay, LCME, 91280 Bruyères-le-Châtel, France

^cUniversity of Bordeaux, CNRS, Bordeaux INP, ISM, UMR 5255, F-33400 Talence, France

Abstract

Despite its relevance in many high temperature processes, the elastic behavior of single crystalline graphite is so far entirely undocumented away from room temperature conditions. In this work we present a molecular dynamics investigation of graphite's second order elastic tensor dependence on temperature from 300 to 4000 K, using a series of popular interatomic potentials for carbon. Data and analytic expressions are presented for the elastic tensor under the two limiting situations known as isothermal, or quasi-static, and adiabatic deformation conditions, prevailing in the limits of slow and large deformation rates, respectively. Independently from the potential, we identify a strong non-linearity of elastic constants with respect to temperature. We show that despite conserving an important elastic anisotropy whatever the temperature, the latter is being reduced by a factor of ~ 5 when increasing temperature up to 4000 K. Also, we show that elastic anisotropy is about 20 times larger under isothermal conditions than under adiabatic conditions. Finally, we investigate the dynamics of the adiabatic to isothermal stress relaxations occurring right after ultra fast deformations such as those encountered under shock loading, showing that the relevant time and length scales are of the order of a few ps and nm, respectively, for deformations around a percent.

*Corresponding author

Email address: paul.lafourcade@cea.fr (Paul Lafourcade)

1. Introduction

When considering structural elements for devices experiencing ultra-high temperatures (UHT), like for instance thermal protection systems for atmospheric re-entry [1], involving temperatures in the 3000-4000 K range, very few materials are available [2]. Carbon based materials, and especially carbon/carbon (C/C) composites, combining high melting temperature, stiffness, strength and thermal conductivity, as well as low weight, are thus generally selected [3, 4]. However, despite numerous investigations, our knowledge of the properties of C/C composites and of their constituents, the well-known carbon fibers and pyrolytic carbon (pyC) matrices, remains limited to significantly lower temperatures. [5, 6, 7, 8, 9]. Therefore, the properties of interest – coefficients of thermal expansion, Young's moduli and Poisson coefficients along and normal to the fiber axes, etc. – have to be extrapolated to the temperatures of interest, which can be somehow heuristic.

Due to these extreme conditions that can be challenging, experiments are sometimes not suitable to identify and understand complex behaviors involved at the atomic and mesoscopic scales. To overcome this, virtual material approaches are becoming more and more popular. These approaches have indeed proven their value in understanding the thermo-mechanical and chemical behavior of high explosives [10, 11, 12], in investigating metals response under very high strain rates [13, 14, 15], as well as in studying the damage and mechanical behavior of ceramics and carbon composites [16, 17].

When bridging the gap between time and length scales, which is the essence of multiscale modeling, complex material architectures - as those in C/C composites - can be simulated under various thermodynamic conditions, provided one has a precise enough constitutive law for the individual elements of the microstructure. However, determining such constitutive laws under UHT conditions can be even more challenging than investigating the whole composite material, from the experimental point of view.

Atomistic simulation techniques, like molecular dynamics (MD) simulations, are, in theory, well-suited for such investigations. In the case of C/C composites, large-scale (2×10^5 atoms) atomistic models of the pyC matrices [18] have been proposed in recent years. However, their corresponding room temperature elastic constants [19] failed to reproduce the existing experimental data [8]. In particular, the longitudinal tensile moduli were significantly larger, by factors of 2 to 6, than the measurements, indicating that the models are either not accurate nor sufficiently large to properly capture the elastic behavior of the pyC. We note that, while currently no such atomistic model exist to describe the bulk properties of C fibers, some models of carbon fibers surfaces have been recently proposed [20].

Taking some distance with the accurate representation of actual C/C composites, we consider in this work the case of crystalline hexagonal graphite, which, conversely to the case of pyC matrices and carbon fibers, has a perfectly determined structure. Also, experimental

38 data only exists for the full elastic tensor of single crystalline graphite at room tempera-
39 ture [21, 22], which is not the case for fibers and matrices for which only longitudinal and
40 transverse Young's moduli are generally reported. On the other hand, to the best of our
41 knowledge, no experimental data is available concerning the elastic constants of graphite at
42 elevated temperatures.

43 In this work we use MD simulations to determine the temperature dependence of graphite's
44 unit cell lengths and elastic constants, which are fundamental parameters in deriving constitu-
45 tive laws for up-scaled thermo-mechanical models of graphite-based complex architectures,
46 inaccessible to atomic-scale modeling. Considering applications under somehow extreme
47 conditions such as shock loading, high strain-rate deformation or thermal aggression, these
48 properties are computed up to ultra high temperature, i.e. $T = 4000$ K, at ambient pressure,
49 i.e. $P = 1$ atm. Also, two types of elastic constants, corresponding to drastically different
50 conditions, are determined. On one hand, we compute the usual isothermal (or quasi-static)
51 elastic constants, in which strain rate is low with respect to all elastic relaxation modes of
52 the material. On the other hand, the so-called adiabatic elastic constants are computed, un-
53 der the application of instantaneous deformations without any subsequent atomic positions
54 relaxation. This method has already been used to compute the adiabatic elastic constants
55 of the triclinic compound TATB [23]. As explained by Wallace [24] and Sutton [25], any
56 given thermoelastic process should be associated with either adiabatic or isothermal elas-
57 tic constants. However, whether it should be one or the other is directly related to the
58 rate of elastic deformation. For example, adiabatic elastic constants are measured by ul-
59 trasonic pulse experiments while their isothermal counterpart are usually measured in direct
60 quasi-static mechanical tests at constant temperature. The difference between adiabatic and
61 isothermal elastic constants is in general temperature dependent, which will be shown in the
62 present work. In the end, analytical formulations of both elastic tensors will be provided as
63 a function of temperature, ready to be assigned to a continuum framework. However, if the
64 later involves a physical process that requires both adiabatic and isothermal elastic moduli
65 over various thermodynamic conditions, it should always be associated with corresponding
66 thermal stress/strain tensors as well as specific heat.

67 While extended benchmarks of carbon potentials have been published in recent years
68 [26, 27], the latter focused on the structure of quenched, then annealed, disordered car-
69 bons. So far, the abilities of such potentials to describe the lattice parameters and elastic
70 constants of graphite, and their evolution upon increasing temperature remains mostly un-
71 known. Therefore, and as no experimental data exists to validate the simulations, we consider
72 five popular empirical potentials: REBO [28], AIREBO [29], AIREBO-M [30], CEDIP [31]
73 and LCBOP II [32]. Comparison of the results obtained with these different potentials allows
74 us to determine reliable trends on the high temperature elastic behavior of graphite.

75 2. Methods

76 2.1. Interatomic potentials

77 Empirical potentials are frequently used to investigate elastic and fracture properties of
78 carbon-based systems [33, 34, 35]. Here we consider five potentials amongst the most widely
79 used: REBO [28], AIREBO [29], AIREBO-M [30], CEDIP [31] and LCBOPII [32]. The re-
80 active empirical bond order (REBO) potential of Brenner *et al.* [28] has been extensively
81 used in the literature, mostly to investigate elasticity and fracture of nanocarbons, including
82 graphene and carbon nanotubes [34, 36, 37]. The two versions of the adaptive intermolecular
83 reactive bond order potential (AIREBO and AIREBO-M) from Stuart *et al.* [29] are directly
84 derived from REBO. They complement the latter with a bond-order dependent integration
85 of van der Waals interactions and a torsional potential around single C-C bonds to better
86 describe hydrocarbons in the liquid state and aromatic stacking distances. In the AIREBO-M
87 potential, the Lennard-Jones term used to describe van der Waals interactions in AIREBO -
88 known to significantly overestimate repulsive forces under large compressive strains - is re-
89 placed with a more realistic Morse potential [30]. Another potential, namely SED-REBO [38]
90 is available in the literature and based on the second generation of REBO. Since this potential
91 is equivalent to REBO in terms of elasticity, it was not used in the present work. The last
92 two potentials considered in the present work are the environment dependent interatomic
93 potential for carbon (CEDIP) from Marks *et al.* [31] and the improved long-range carbon
94 bond-order potential (LCBOPII) from Los *et al.* [32]. Conversely to the previously mentioned
95 potentials in which bonding interactions are cut off at very short distances, via a switching
96 function operating in the 1.7-2 Å range, medium-range interactions are included in the both
97 CEDIP and LCBOPII potentials, which is a clear advantage for capturing fracture properties.
98 Another major consequence of medium-range interactions is that these potentials allow for
99 a quantitative prediction of the energy barrier for the graphite to diamond transition while
100 potentials of the REBO family do not [39]. However, LCBOPII differs from CEDIP since
101 it contains explicit long-range (dispersion) interactions while the former does not. Although
102 these two potentials have been considerably less used than REBO or AIREBO potentials,
103 a few reports suggest that these potentials are valuable candidates. Elastic and fracture
104 properties of low temperature and annealed amorphous carbon have been investigated using
105 CEDIP [40], while LCBOPII was used to study the pressure-induced graphite to diamond
106 phase transformation under shock conditions and homothetic strain [41, 42, 43].

107 2.2. Molecular dynamics simulations

108 Two different classical molecular dynamics (MD) codes are used in this work. The
109 LAMMPS (Large-scale Atomic/Molecular Massively Parallel Simulator) [44, 45] is used for all
110 simulations using REBO, AIREBO, AIREBO-M and CEDIP potentials while the STAMP [46]

111 (Simulations Temporelles Atomistiques Massivement Parallélisées) code is used to perform
112 simulations using LCBOPII potential as it is not currently implemented in LAMMPS. For
113 both codes, MD trajectories are integrated using a velocity-Verlet integrator [47] and a 0.5
114 fs timestep, ensuring a correct energy conservation under equilibrium microcanonical (NVE)
115 runs. Besides energy conservation tests, simulations are run in both canonical (NVT) and
116 isothermal-isobaric (NPT) ensembles, using a Nosé-Hoover style thermostat [48, 49] and
117 barostat [50] along with 0.1 ps and 1.0 ps damping constants, respectively. For the deter-
118 mination of graphite single crystal lattice parameters and elastic constants evolution with
119 temperature, a 3D-periodic orthorhombic simulation cell containing 3456 carbon atoms is
120 considered, consisting in a $6 \times 6 \times 6$ replication of the 16 atoms graphite orthorhombic unit
121 cell. In Section 3.6, a 107520 atoms 3D-periodic simulation cell consisting in a $20 \times 24 \times 14$
122 replication of the same unit cell is considered to investigate the dynamical aspects of stress
123 relaxation with sufficient statistics. In all the simulations, except the ones for computing the
124 elastic constants that require a change in the simulation box shape, i.e. when applying shear
125 strain, the cell angles are constrained to maintain a constant value of 90 %, accordingly to
126 the graphite orthorhombic unit cell. For the simulations in the isothermal-isobaric ensemble,
127 diagonal components of the stress tensor are controlled independently so that true hydro-
128 static conditions can be achieved, accordingly to the very large elastic anisotropy of graphite
129 single crystal.

130 *2.3. Lattice equilibration at finite temperature*

131 For each potential, the system is equilibrated in the isothermal-isobaric (NPT) ensemble
132 during 1 ns at a pressure of 1 atm and at 300 K and for temperatures ranging from 500 to
133 4000 K (i.e. close to graphite's melting point), by steps of 500 K. Lattice parameters are
134 systematically averaged over the last 250 ps of the NPT trajectory, during which the stress
135 tensor is checked to be fully hydrostatic, without any substantial evolution of simulation cell
136 lengths. As both REBO and CEDIP potentials do not include van der Waals interactions,
137 only the in-plane lattice parameters are allowed to evolve in the NPT simulations for these
138 two potentials, the out-of-plane parameter were arbitrarily held fixed to the value obtained
139 using the LCBOPII model at the considered temperature.

140 *2.4. Elastic constants calculation*

141 Graphite single crystal elasticity is known to possess a transverse isotropy symmetry,
142 which is an elastic symmetry derived from the orthotropic elastic symmetry, for which the

143 second-order elastic tensor possesses 9 independent elastic components:

$$\mathbf{C} = \begin{pmatrix} C_{11} & C_{12} & C_{13} & 0 & 0 & 0 \\ C_{12} & C_{22} & C_{23} & 0 & 0 & 0 \\ C_{13} & C_{23} & C_{33} & 0 & 0 & 0 \\ 0 & 0 & 0 & C_{44} & 0 & 0 \\ 0 & 0 & 0 & 0 & C_{55} & 0 \\ 0 & 0 & 0 & 0 & 0 & C_{66} \end{pmatrix} \quad (1)$$

144 where the Voigt contraction convention has been used to represent the elastic tensor \mathbf{C}
 145 as a second-order tensor. As an additional criterion to compare the results obtained with
 146 the different potentials, we first make the assumption that the graphite single crystal has
 147 an orthotropic symmetry, with 9 independent elastic constants. This hypothesis is always
 148 true because a material that possesses a transverse isotropic elasticity has by definition an
 149 orthotropic elasticity. However, for a material to have a transverse isotropic elasticity, it is
 150 required that, $C_{11} = C_{22}$, $C_{13} = C_{23}$, $C_{44} = C_{55}$ and $C_{66} = (C_{11} - C_{12})/2$, with all other
 151 components equal to zero. For graphite single crystal this implies that the elastic response to
 152 a deformation along the armchair or zigzag direction is strictly equivalent, which might not
 153 be true for certain potentials [36]. When a material is transversely isotropic, its second-order
 154 elastic tensor reads:

$$\mathbf{C} = \begin{pmatrix} C_{11} & C_{12} & C_{13} & 0 & 0 & 0 \\ C_{12} & C_{11} & C_{13} & 0 & 0 & 0 \\ C_{13} & C_{13} & C_{33} & 0 & 0 & 0 \\ 0 & 0 & 0 & C_{44} & 0 & 0 \\ 0 & 0 & 0 & 0 & C_{44} & 0 \\ 0 & 0 & 0 & 0 & 0 & (C_{11} - C_{12})/2 \end{pmatrix} \quad (2)$$

155 with 5 independent elastic component. In the following, we consider the general case with
 156 elastic orthotropic symmetry, in order to compare the elastic constants computed with dif-
 157 ferent potentials, and determine whether they verify the transverse isotropic symmetry. By
 158 construction, it is necessary to apply 6 deformation types to get the full second-order elastic
 159 tensor from MD simulations. As for the lattice constant calculations, elastic constants in-
 160 volving the out-of-plane direction are not investigated with REBO and CEDIP. Mechanical
 161 properties are computed by applying an homothetic strain to the entire system with atomic
 162 positions being remapped into the box, followed or not by an equilibration in the NVT ensem-
 163 ble whether we aim at calculating isothermal or adiabatic elastic constants. The differences
 164 between the two methods are shortly explained in the following sections.

165 2.4.1. Isothermal elastic constants

166 Isothermal elastic constants are computed as follows. Starting from the equilibrium lattice
167 parameters, a series of uniaxial engineering strains are uniformly applied to the graphite super-
168 cell. The considered strain range correspond to $\epsilon \in [-0.3, +1.0]$ %, with a 0.1 % increment,
169 for deformations along the principal axes, where negative and positive values correspond
170 to compressive and tensile strains, respectively. Note that the lower range of compressive
171 strain was chosen to avoid well-known compression-induced buckling elastic instabilities in
172 anisotropic materials [51, 12, 43, 52]. Shear strains are applied in the $[-1.0, +1.0]$ % range
173 with the same increment. After the strain is applied, the simulation cells are equilibrated
174 in the NVT ensemble for 1.0 ns, leading to the stress relaxation of the the system through
175 the relaxation of atoms positions. Stress tensors are then obtained by averaging stress com-
176 ponents over the last 100 ps of the trajectories and isothermal elastic constants C_{ij}^T are
177 determined via linear fits of the corresponding stress vs. strain curves.

178 2.4.2. Adiabatic elastic constants

179 Adiabatic elastic constants are obtained in a somehow opposite way. First, the system is
180 equilibrated for 1 ns in the NVT ensemble using the equilibrium lattice parameters obtained
181 from the NPT trajectory at 1 atm. Then, 20 independent configurations are selected from the
182 last 100 ps of the NVT simulation, on which finite adiabatic strains, spanning the same values
183 as those used in the isothermal case, are applied via pure homothetic transformations to
184 the simulation cells. The resulting 20 uncorrelated stress-strain curves, for each deformation
185 type, are then gathered to build the average stress-strain curve, from which the corresponding
186 adiabatic, or isentropic elastic components C_{ij}^S are obtained, where the superscript S relates
187 the elastic constant to entropy. This way, one deformation type gives directly access to 6
188 elastic constants.

189 3. Results

190 3.1. Room temperature lattice parameters

191 The lattice parameters of graphite single crystal at ambient temperature, i.e. $P = 1$ atm
192 and $T = 300$ K, predicted using the different potentials are given in Table 1. Experimental
193 data from Baskin and Meyer [53] are given for comparison. LCBOPII, REBO and CEDIP
194 potentials lead to values of the in-plane lattice parameter (a) that are in excellent agreement
195 with experiments, with a maximum deviation of 0.06 % obtained for CEDIP. On the other
196 hand, AIREBO and AIREBO-M potentials show a significant underestimation of a , by ~ 1.6
197 %, which results from the reparametrization of the REBO term in AIREBO to compensate
198 for the added torsional term which slightly destabilizes sp^2 carbon atoms [29]. Conversely,
199 AIREBO and AIREBO-M give a better prediction of the inter-layer spacing ($d_{002} = 0.5c$)

200 while LCBOPII overestimates it by 1.6 %. As discussed above, no c values could be predicted
 201 using REBO and CEDIP.

Table 1: Lattice parameters of graphite at $P = 1$ atm and $T = 3000$ K computed using the different potentials and compared to the experimental reference [53]. Relative errors in % with respect to the reference are reported in parentheses.

	a (Å)	c (Å)
Exp.	2.4590	6.7076
LCBOPII	2.4590 (0.000)	6.8180 (1.646)
AIREBO	2.4193 (-1.615)	6.7078 (0.004)
AIREBO-M	2.4193 (-1.616)	6.7078 (0.003)
REBO	2.4600 (0.042)	N/A
CEDIP	2.4605 (0.059)	N/A

202 3.2. Room temperature elastic properties

203 Isothermal elastic constants computed at $P = 1$ atm and $T = 300$ K using the different
 204 potentials are compared in Table 2 to experimental values from two reference papers. It
 205 has been previously presented that some potentials may slightly deviate from the expected
 206 transverse isotropy symmetry of graphite when regarding elasticity [19, 36]. Hence, as dis-
 207 cussed before, we adopt in the present work the general case of orthotropic symmetry of the
 208 second-order elastic tensor in order to compare the computed elastic constants of graphite
 209 single crystal.

Table 2: Isothermal elastic constants (in GPa) of graphite single crystal at $P = 1$ atm and $T = 300$ K computed using the different interatomic potentials under the assumption of an orthotropic elastic symmetry. The last column corresponds to the metric d_{ti}^{in} that is meant to measure the deviation from the transverse isotropy, computed from the in-plane components of the second-order elastic tensor.

	C_{11}	C_{22}	C_{33}	C_{12}	C_{13}	C_{23}	C_{44}	C_{55}	C_{66}	d_{ti}^{in}
Exp. [21]	1060.0		36.5	180.0		15.0		0.18	440.0	0.0
Exp. [22]	1109.0		38.7	139.0		0.0		5.0	485.0	0.0
LCBOPII	941.0	945.0	28.5	159.9	6.5	6.1	0.23	0.17	389.2	0.05
AIREBO	1000.9	1000.4	45.6	209.9	7.6	6.5	0.15	0.05	407.8	-1.54
AIREBO-M	936.5	913.1	29.6	190.4	7.6	7.9	0.04	0.01	406.2	-3.60
REBO	808.7	827.7	N/A	183.2	N/A	N/A	N/A	N/A	340.0	-5.19
CEDIP	920.6	921.40	N/A	252.9	N/A	N/A	N/A	N/A	334.6	-0.15

210 In a general way, all the force fields respect relatively well the hierarchy of the different
 211 elastic constants with $C_{11} > C_{66} > C_{12} > C_{33} > C_{13} > C_{44}$. The potentials also perform
 212 reasonably well from the quantitative perspective. Albeit being slightly lower than the ex-
 213 perimental references, the error on computed C_{11} ranges from about 10 % with AIREBO to

214 about 27 % with REBO. As for C_{11} , C_{66} is underestimated by 8 to 15 % with AIREBO and
 215 AIREBO-M, the largest error, 24-30 %, being obtained for REBO and CEDIP. Regarding
 216 C_{12} the value predicted with LCBOPII, 159.9 GPa, is almost in the middle of the two experi-
 217 mental reference values, the other potentials predicting slightly larger values, the largest, 253
 218 GPa, obtained with CEDIP being 40-80 % too large. Predicted C_{33} values are either about
 219 7-8 GPa larger (AIREBO) or lower (LCBOPII, AIREBO-M) than the experimental data.

220 Concerning the shear elastic constants C_{44} and C_{55} , there is a large experimental spreading
 221 of the data since Bosak *et al.* [22] and Blakslee *et al.* [21] predicted values of 5 GPa and
 222 0.18 GPa, respectively. LCBOPII, AIREBO and AIREBO-M potentials lead to consistent
 223 values in the 0-0.2 GPa range, i.e. close to the experimental data of Blakslee *et al.* [21].
 224 However, more recent theoretical [54] and experimental investigations [55] suggest that the
 225 value of 5 GPa is correct for C_{44} , the lower values obtained on compressed pyrolytic graphite
 226 by Blakslee *et al.* being attributed to glissile basal dislocations. Therefore, it seems that all
 227 the considered potentials underestimate C_{44} . As for C_{13} , the three potentials predict values in
 228 the 6-8 GPa range, that are intermediates to the values of Blakslee *et al.* [21] and Bosak *et*
 229 *al.* [22], 15 and 0 GPa, respectively, and almost perfectly equal to the value of 7.9 ± 3.5
 230 recommended by Cousins and Heggie [54].

231 Two metrics are defined to identify the deviation from transverse isotropy symmetry,
 232 regarding in-plane and our-of-plane symmetry, respectively:

$$d_{ti}^{in} = 100 \times \left[1 - \frac{1}{2} \times \left(\frac{C_{11}^2 + C_{22}^2}{2C_{11}C_{22}} + \frac{2C_{66}}{2\frac{C_{11}^2 + C_{22}^2}{C_{11} + C_{22}} - C_{12}} \right) \right] \quad (3)$$

$$d_{ti}^{out} = 100 \times \left[1 - \frac{1}{2} \times \left(\frac{C_{13}^2 + C_{23}^2}{2C_{13}C_{23}} + \frac{C_{44}^2 + C_{55}^2}{2C_{44}C_{55}} \right) \right] \quad (4)$$

234 where each ratio should be equal to 1 in the presence of an elastic tensor with transverse
 235 isotropy symmetry.

236 The values of d_{ti}^{in} are reported in the last column of Table 2, noticing that $d_{ti}^{in} = 0$ is
 237 expected experimentally. d_{ti}^{out} is not reported for the isothermal constants due to the very
 238 low values of C_{44} , and the necessarily large associated relative uncertainty. Amongst the
 239 different potentials LCBOPII is the one that produces the second-order elastic tensor with
 240 the closest symmetry to in-plane transverse isotropy, followed by CEDIP, the three other
 241 potentials showing much larger deviations.

242 In Table 3 are listed the adiabatic elastic constants computed with the different poten-
 243 tials. Since no experimental data correspond to adiabatic elastic constants measurements
 244 for graphite single crystal, we only discuss them in terms of their differences with isothermal
 245 elastic constants as well as their deviation from the transverse isotropy symmetry. As a

Table 3: Adiabatic elastic constants (in GPa) of graphite single crystal at $P = 1$ atm and $T = 300$ K computed using the different interatomic potentials under the assumption of an orthotropic elastic symmetry. The last two columns correspond the in-plane d_{ti}^{in} and out-of-plane d_{ti}^{out} metrics measuring the deviation from transverse isotropy.

	C_{11}	C_{22}	C_{33}	C_{12}	C_{13}	C_{23}	C_{44}	C_{55}	C_{66}	d_{ti}^{in}	d_{ti}^{out}
LCBOPII	1060.0	1061.0	32.3	116.6	3.8	4.2	5.9	5.8	471.7	-0.03	-0.26
AIREBO	1188.6	1188.5	48.5	98.9	4.2	4.2	7.0	7.0	544.6	0.02	0.0
AIREBO-M	1187.4	1186.8	32.2	99.1	3.0	3.1	7.5	7.4	543.8	0.05	-0.03
REBO	1058.9	1213.7	N/A	104.0	N/A	N/A	N/A	N/A	469.3	-3.62	N/A
CEDIP	1009.0	1009.3	N/A	181.5	N/A	N/A	N/A	N/A	413.0	0.08	N/A

246 general observation, and for all the potentials, the computed adiabatic elastic constants are
 247 much closer to the transverse isotropy symmetry than their isothermal counterparts, with
 248 one noticeable exception being the large C_{11}/C_{22} ratio, 1.146, obtained with REBO. One
 249 notice that the adiabatic values of C_{11} obtained with LCBOPII and REBO are almost per-
 250 fectly identical to the the experimental data of Blakslee et al. [21], which indicates that
 251 these potentials have been calibrated to reproduced the elastic constants of graphite using
 252 homogeneous deformation without relaxation of atomic positions, i.e. under adiabatic con-
 253 ditions. In addition, all the potentials lead to a value of the adiabatic constant C_{66} that is
 254 higher than the isothermal constant, whereas the adiabatic constant C_{12} is lower than the
 255 isothermal value. Under the assumption that graphite single crystal is transversely isotropic,
 256 the relationship $C_{66} = (C_{11} - C_{12})/2$ holds and a decrease in C_{12} systematically involves an
 257 increase in C_{66} , which could explain the observed trend.

258 3.3. Temperature evolution of lattice parameters

259 Figure 1 compares the evolution with temperature of the lattice parameters computed
 260 using the different potentials to available experimental data [56, 57, 58, 59]. Common
 261 to all the potentials is the observation of a monotonous increase in the in-plane lattice
 262 parameter (a) with temperature (see Figure 1a), which conflicts with experimental results
 263 showing that a passes through a minimum at about 700 K. The slight contraction observed
 264 experimentally at low temperatures can indeed not be captured by classical MD as pointed out
 265 in recent investigations comparing classical and quantum, path integral, MD in the case of
 266 monolayer graphene [60, 61]. Besides this, all potentials seems to significantly overestimate
 267 both in-plane and out-of-plane thermal expansion, even at large temperatures, CEDIP being
 268 the closest to experimental data. Quantitatively, predicted a values using REBO, CEDIP
 269 and LCBOPII are very close to the commonly accepted experimental data of Kellet and
 270 Richards [62] at low temperatures and differ by less than $\sim 1\%$ at $T = 3000$ K. Conversely,
 271 the values obtained for AIREBO and AIREBO-M are significantly lower, as already discussed
 272 above for the room temperature data.




Figure 1: Evolution of (a) in-plane and (b) out-of plane lattice parameters with temperature obtained computed with the different potentials. Experimental data from Nelson and Riley [56], Kellet and Richards [62, 59], Walker, McKinstry and Wright [58] and Kellett, Jackets and Richards [57] are given for comparison.

273 The potentials considered for the out-of-plane lattice parameter (c), namely LCBOPII,
 274 AIREBO and AIREBO-M, reproduces well the monotonous expansion observed experimen-
 275 tally with increasing temperature (see Figure 1b). Quantitatively speaking, while all poten-
 276 tials slightly overestimate thermal expansion, AIREBO and AIREBO-M provide values that
 277 are closer to experimental data than LCBOPII. The relative errors to the experiment value
 278 from Kellett *et al.* [57] at $T = 2500$ K are of 0.5 % for AIREBO and AIREBO-M and of
 279 1.95 % for LCBOPII.

280 3.4. Temperature evolution of elastic constants

281 Figure 2 shows the computed evolution with temperature of the six elastic coefficients
 282 defined above, assuming transverse isotropy elastic symmetry. Therefore C_{11} , C_{13} and C_{44}
 283 are taken as the mean values of equivalent orthotropic constants, $\frac{C_{11}+C_{22}}{2}$, $\frac{C_{13}+C_{23}}{2}$ and $\frac{C_{44}+C_{55}}{2}$,
 284 respectively. Regarding in the first place the in-plane stiffness, we observe that all related
 285 constants (C_{11} , C_{12} and C_{66}) decrease with increasing temperature. In the specific case of
 286 C_{11} , all potentials show an almost linear evolution (especially CEDIP), with a decrease of
 287 about 35-40 % when T decreases from 300 to 4000 K, in agreement with the decrease
 288 of graphene's Young modulus recently predicted for graphene [63] using the SED-REBO
 289 potential [38]. The decrease in C_{11} obtained with CEDIP is slightly less pronounced, only
 290 reaching ~ 25 % at $T = 4000$ K. The difference in behavior between CEDIP and the four
 291 other potentials is significant when regarding C_{12} and C_{66} . As for C_{11} , a linear decrease in C_{12}
 292 is observed for CEDIP, from about 250 to 220 GPa and from 335 to 230 GPa for C_{66} when
 293 T increases from 300 to 4000 K. The other potentials show much lower values for C_{12} and a
 294 clearly non-linear evolution with a strong decrease at low temperatures, from values scattered




Figure 2: Evolution with temperature of the isothermal elastic constants of graphite single crystal at $P = 1$ atm computed using the different potentials. For clarity, error bars are only given for data obtained with the LCBOPII potential. Error bars for the other data sets are expected to be of the same order. Dashed lines for C_{66} data correspond to predictions obtained from C_{11} and C_{12} assuming transverse isotropy symmetry.

295 in the 160-210 GPa range at 300 K, down to a plateau at large temperatures with values
 296 contained in the 50-80 GPa range. Conversely, the other potentials give values for C_{66}
 297 that are larger than those obtained with CEDIP. Furthermore, AIREBO and AIREBO-M show a
 298 non-monotonous behavior at low temperatures, with values that first increase, then decrease
 299 with increasing T . Values obtained at 4000 K for C_{66} range from 230 GPa (CEDIP) to ~ 280
 300 GPa (AIREBO, AIREBO-M). In Figure 2, we also represent the analytical C_{66} component,
 301 computed from the relation $C_{66} = (C_{11} - C_{12})/2$ for transverse isotropy symmetry, using
 302 dashed lines for every potential used. This shows directly that, under isothermal conditions,
 303 CEDIP and LCBOPII provide a good estimation of C_{66} for the transverse isotropy symmetry,
 304 whereas for REBO and AIREBO potentials, the computed value shifts from the analytical
 305 expression.

306 Now focusing on the elastic constants involving interlayer interactions, we observe that C_{33}
 307 is the most sensitive to an increase in temperature, with values dropping, more or less linearly,
 308 by a factor of $\sim 5-6$ when increasing T from 300 to 4000 K, whatever the potential. Unlike
 309 C_{33} , the behavior with increasing T of C_{13} and C_{44} significantly depends on the potential.
 310 While with LCBOPII, C_{13} almost linearly increases from 6 GPa at 300 K to ~ 18 GPa at
 311 4000 K with LCBOPII, it evolves from 7.5 GPa at 300 K to 9 GPa at 4000 K with AIREBO

312 and AIREBO-M by passing through maximum values of about 15 and 12 GPa at $T = 2000$
 313 K, with AIREBO and AIREBO-M, respectively. Finally, while C_{44} continuously increases from
 314 0.2 GPa at 300 K to 0.7 GPa at 4000 with LCBOPII, it remains more or less constant, at
 315 around 0.1 and 0.05 GPa with AIREBO and AIREBO-M, respectively.

316 The temperature evolution of adiabatic elastic constants is shown in Figure 3. As ex-
 317 plained before, the adiabatic elastic constants are calculated by applying instantaneous de-
 318 formations to an MD simulation cell that has been equilibrated in the NVT ensemble at zero
 319 deformation and target temperature. It then catches the instantaneous elastic response of a
 320 material and is cost-less compared to the calculation procedure of isothermal elastic constants
 321 that requires an equilibration in the NVT ensemble for each value of the deformation.




Figure 3: Same as Figure 2 for the adiabatic elastic constants.

322 All the potential but CEDIP show a continuous decrease of C_{11} with increasing T , up to
 323 about 20 to 25 % at 4000 K, in an almost linear fashion, at least for AIEBO and AIREBO-
 324 M. Conversely, the decrease in C_{11} obtained with CEDIP is only of about 5 %, and non
 325 monotonous, with a minimum value observed around 2500-3000 K. C_{12} also shows similar
 326 evolutions with REBO, AIREBO, AIREBO-M and LCBOPII, first decreasing down to mini-
 327 mum values at about 1000-1500 K with LCBOPII and 2000-2500 K with REBO, AIREBO
 328 and AIREBO-M, before increasing again. At 4000 K, C_{12} has decreased of about 50 % with
 329 AIREBO and AIREBO-M, 30 % with REBO, and 10 % with LCBOPII with respect to the
 330 300 K values. Again, CEDIP is an outlier with respect to the other potentials, with C_{12}
 331 continuously increasing, although non monotonically, with T , showing an increase of about

332 33 % over the considered T range. Regarding C_{66} all potentials show a similar monotonous
 333 decreasing trend, with values at 4000 K that are $\sim 20\text{-}25\%$ lower than at 300 K, LCBOP11
 334 showing the larger and less-linear decrease. Also, all the potentials satisfy well the transverse
 335 isotropy constraint, apart from CEDIP at large temperatures.

336 The three potentials considered for C_{13} show a similar, close to linear, increase with
 337 increasing T, from about 3-4 GPa at room temperature, to about 20-24 GPa at 4000 K.
 338 Similarly, C_{44} significantly increase with T, yet in a sublinear fashion, from about 6-7 GPa at
 339 room temperature, to ~ 60 GPa with AIREBO and AIREBO-M, and 35 GPa with LCBOP11,
 340 at 4000 K. The behavior observed for C_{33} is less clear, with a non-monotonous evolution
 341 observed for all potentials, showing considerably less variation in values than for C_{13} and C_{44} .




Figure 4: Comparison of MD data and polynomial fits for the temperature dependence of the isothermal and adiabatic elastic constants. symbols: MD data; lines: polynomial fits.

342 Due to the non-linear evolution of graphite single crystal elasticity (both isothermal and
 343 adiabatic) with temperature, we propose an analytical expression for this dependency based
 344 on polynomial fits. For the sake of simplicity, only the LCBOP11 potential is considered in

345 the remaining of the manuscript. Indeed, this potential was shown to produce reasonable
 346 lattice parameters and elastic constants, preserving well the transverse isotropy of graphite.
 347 Furthermore, it allows to capture out-of-plane elastic constants, which CEDIP and REBO
 348 cannot. We take the condition $T_{ref} = 300$ K as the reference configuration, leading to the
 349 following formulation of the isothermal/adiabatic spatial elasticity tensor along the ambient
 350 pressure isobaric pathway:

$$\mathbf{c}^{S/T}(T) = \mathbf{c}_{ref}^{S/T}(T_{ref}) \left(\mathbf{I} + \sum_{k=1}^N \mathbf{A}_k (T - T_{ref})^k \right) \quad (5)$$

351 where $\mathbf{c}_{ref}^{S/T}$ is the stiffness tensor at the reference state, with superscripts S and T correspond-
 352 ing to isothermal and adiabatic forms, respectively. \mathbf{A}^k is a tensor containing the polynomial
 353 fit coefficients and N is taken equal to 3. It is to be noted that the product between $\mathbf{c}_{ref}^{S/T}$
 354 and \mathbf{A}^k is done through the Hadamard product, i.e. component-wise.

355 The temperature-dependent isothermal and adiabatic elastic coefficients and their corre-
 356 sponding polynomial fits are represented in Figure 4. In addition, the polynomial coefficients
 357 for both isothermal and adiabatic elastic tensors are provided in the supplementary material.

358 3.5. Temperature dependence of elastic anisotropy

359 When dealing with highly anisotropic materials like graphite, different metrics computed
 360 from the elastic tensor can help to discriminate whether the proposed analytical formulation
 361 is reliable or not. One of these metrics is the universal anisotropy index [64] which computes
 362 the level of anisotropy of any material from its elastic constants. It is based on the bulk and
 363 shear moduli computed using the Voigt and Reuss approximation. The Voigt bound relates
 364 to the behavior of a material under an isotropic deformation-imposed process while the Reuss
 365 bound is related to the behavior of a material under an imposed hydrostatic pressure. It is
 366 obvious that any isotropic material will behave in the same way under both conditions. Yet,
 367 this is not the case in the presence of anisotropy. The universal anisotropy index reads:

$$A^U = \mathbf{c} : \mathbf{s} = 5 \frac{G^V}{G^R} + \frac{K^V}{K^R} - 6, \quad (6)$$

368 which takes a value of 0 for an isotropic material, since Voigt and Reuss estimates for bulk
 369 (K) and shear (G) modulus are identical. Figure 5 shows the evolution with temperature
 370 of A_{univ} along the 1 atm isobaric pathway computed from MD data and the isothermal and
 371 adiabatic analytical expressions.

372 First, we see that analytical formulations reproduce well both isothermal and adiabatic
 373 MD data, thus validating the polynomial fits. More importantly, Figure 5 shows that the
 374 elastic anisotropy is severely temperature dependent. At ambient temperature, anisotropy is
 375 very high compared to a large panel of materials [64, 65] and takes values of approximately




Figure 5: Universal Anisotropy Index as a function of temperature computed from (a) isothermal and (b) adiabatic elastic tensors, comparison between analytical formulation and MD data. All data were obtained with the LCBOP11 potential.

376 93 and 2169 in adiabatic and isothermal conditions, respectively. Concerning the evolution
 377 with temperature, the isothermal anisotropy decreases non-linearly with temperature and is
 378 divided by almost a factor of 5.40 at 4000 K with respect to the 300 K case. The adiabatic
 379 anisotropy follows a very similar evolution and the ratio between the 300 K and the 4000 K
 380 values is around 4.65.

381 3.6. Adiabatic vs. isothermal elastic constants: relationship and implications




Figure 6: Evolution of the ratio between isothermal (C_{ij}^T) and adiabatic (C_{ij}^S) elastic constants of graphite single crystal using the LCBOP11 potential as a function of temperature. All data were obtained with the LCBOP11 potential.

382 We show in Figure 6 the ratios of the isothermal over adiabatic elastic constants as a
 383 function of temperature. Interestingly, these ratios remain almost constant for C_{11} , C_{66} and
 384 C_{44} , with values around 0.8 for C_{11} and C_{66} , and about 0.02 for C_{44} , although a slight linear
 385 decrease with increasing T is observed, especially for C_{11} . Here it is important to note that
 386 any value different from unity of the $\frac{C_{ij}^T}{C_{ij}^S}$ ratio indicates that stress relaxation will take place
 387 during, or after, deformation, depending on the deformation rate. For instance, the value of
 388 ~ 0.8 obtained for C_{11} indicates that when single crystalline graphite is subjected to a fast
 389 uniaxial in-plane deformation, the increase in stress is systematically followed by a relaxation
 390 process. In other words, this means that the measured elastic tensor will depend on strain
 391 rate, with the adiabatic and isothermal constants constituting the instantaneous and quasi-
 392 static limits, respectively. Similarly, the extremely low value of the isothermal over adiabatic
 393 ratio for C_{44} implies a systematic accommodation of interlayer shear deformation at large
 394 times.

395 Conversely to the formerly discussed constants, the isothermal over adiabatic ratio sig-
 396 nificantly decreases with T , with a close to linear dependency, for the three other constants,
 397 indicating that stress relaxation is strongly temperature-dependent for these constants. Ra-
 398 tios for C_{12} and C_{13} both decrease from about 1.5 at 300 K to about 0.8 at 4000 K, while
 399 for C_{33} a decrease from about 0.85 at 300 K to about 0.15 at 4000 K is observed.




Figure 7: Evolution of **(a)** the stress component σ_{11} vs time after an instantaneous tensile strain ϵ_{11} is applied to the sample, for different values of ϵ_{11} . The blue and cyan dashed lines represent the limit values, corresponding to the analytic stress level using the isothermal and adiabatic C_{11} coefficients, respectively. **(b)** Focus on the case $\epsilon_{11} = 0.01$. The dark red line is the computed limit envelope of the stress signal over time while the pink dashed line is the result of the fitted exponential decay function, with characteristic time τ . The vertical gray line corresponds to the relaxation time t_r computed as described in the text.

400 In order to understand the transition from adiabatic to isothermal elastic response, we used
 401 MD simulations with the LCBOP II potential to study the mechanical response of a graphite

402 single crystal at various temperatures and strain amplitudes. A graphite single crystal of
 403 approximate dimensions $10 \times 10 \times 10 \text{ nm}^3$ containing 107520 atoms was equilibrated in the
 404 NVT ensemble for 50 ps for temperatures between 300 K and 4000 K. After the material is
 405 fully equilibrated, it is instantaneously dilated along the [100] direction for different strains
 406 ε between 0.1 % and 1 % in order to remain within the elastic domain, similar to the
 407 one used to compute the elastic constants. This deformation process is performed without
 408 any thermostat coupling in order to let the material relax over time without impacting the
 409 relaxation kinetics, which might be related to the thermostat damping constant. However,
 410 the deformation induced relaxation systematically involves heating of the system due to the
 411 total energy conservation. Yet, this process allows capturing the dynamics of the elastic
 412 response. Indeed, when the deformation is applied, the stress level is directly related to the
 413 adiabatic elastic constant C_{11}^S at the temperature right before the deformation, while after the
 414 relaxation process, the stress level corresponds to the isothermal elastic constant C_{11}^T at the
 415 temperature at the end of the relaxation process. What happens in between is then directly
 416 related to the transition between adiabatic and isothermal elastic response. Performing this
 417 procedure at different initial temperatures and different strains allows to identify how these
 418 conditions affect the transition, which can be related to the relaxation process behind the
 419 front of a shock-wave for example. In Figure 7, we display the time evolution of the stress
 420 component σ_{11} , for different longitudinal strains ε_{11} up to 1 %. The different blue and cyan
 421 dashed lines correspond to the analytical limits σ_{11}^∞ and σ_{11}^0 computed from isothermal and
 422 adiabatic elastic constants using linear elasticity:

$$\sigma_{11}^0 = C_{11}^S(T_0) \cdot \varepsilon_{11}, \quad (7)$$

$$\sigma_{11}^\infty = C_{11}^T(T_\infty) \cdot \varepsilon_{11}. \quad (8)$$

423 where T_0 and T_∞ correspond to the temperatures right before the deformation is applied and
 424 at the end of the relaxation process, respectively. A focus on the case $\varepsilon_{11} = 0.01$ is displayed
 425 in Figure 7, where the good agreement between the stress levels and the analytical values
 426 can be seen. However, one can see that the stress is oscillating around σ_{11}^∞ while decreasing
 427 in amplitude over time. This oscillation of the stress is due to the elastic energy stored in the
 428 material at the instantaneous deformation that is relaxing through elastic waves emissions.
 429 In order to extract a characteristic time from this temporal evolution, the first step consists
 430 in extracting the envelope of the stress signal, that is directly related to the decrease of
 431 the stress over time. We then consider the following exponential decay function that relates
 432 the stress versus time to the isothermal and adiabatic elastic constants using the previously

433 defined analytical limits:

$$\sigma_{11}(t) = \sigma_{11}^{\infty} + (\sigma_{11}^0 - \sigma_{11}^{\infty}) \exp(-t/\tau) \quad (9)$$

434 with τ the characteristic time associated to the exponential decay. We then define the
 435 characteristic relaxation time t_r as the time at which the decrease is completed at 95 %.
 436 The relaxation time for an initial temperature of 300 K and $\varepsilon = 0.01$ is displayed as a
 437 vertical gray line on Figure 7b. This procedure has been applied to stress signals for different
 438 strains $\varepsilon_{11} \in [0.001, 0.1]$ and for temperatures $T \in [300 \text{ K}, 4000 \text{ K}]$. Figure 8a shows that the
 439 relaxation time t_r for instantaneous in-plane tensile loads is in the ps range for the considered
 440 strain and temperature range and that it increases with applied strain while it decreases with
 441 temperature. In addition, it is also interesting to discuss elastic relaxation in terms of its
 442 characteristic length:

$$L_r(T, \varepsilon) = t_r(T, \varepsilon) \sqrt{C_{11}^T(T)/\rho(T)} \quad (10)$$

443 where the square root term corresponds to the longitudinal elastic wave velocity of graphite,
 444 computed from the ratio between the isothermal elastic constant $C_{11}^T(T)$ and the density
 $\rho(T)$ at finite temperature.




Figure 8: Evolution with strain and temperature of the characteristic **(a)** time and **(b)** length of the adiabatic to isothermal elastic stress relaxation after uniaxial in-plane compression. All data were obtained using the LCBOPII potential.

445
 446 As shown in Figure 8b, similarly to t_r , L_r evolves slightly with temperature, reaching sort
 447 of a plateau at large strains. Indeed, the lower bound of this characteristic length remains
 448 below 10 nm at $\varepsilon_{11} = 0.01$ for temperatures above 1000 K while it is always below 25 nm for
 449 the entire set of simulations. This implies that, when a tensile (for example after a reflection)
 450 shock-wave propagates along [100] direction in a graphite single crystal, a slab of width $< L_r$

451 = 15 nm behind the front is required to accommodate the local high strain-rate and to transit
452 from adiabatic to isothermal conditions. When considering high strain-rate deformation, one
453 can talk in terms of relaxation time instead of characteristic length, since no discontinuities
454 of particle velocities exist in the material. This would mean that if the dynamic deformation
455 process involves local deformations above 1 % within a time window lower than a few ps, the
456 process could be considered as adiabatic. On the other hand, a transition from adiabatic to
457 isothermal would be involved.

458 **4. Discussion and conclusion**

459 Equilibrium MD simulations of graphite single crystal have been performed on an ex-
460 tended thermodynamic domain (up to 4000 K) at ambient pressure using various potentials
461 of the literature, namely REBO, AIREBO, AIREBO-M, CEDIP and LCBOP11. The lattice
462 parameters evolution with temperature has been computed with the different models and
463 the LCBOP11 model has been identified as a good candidate to represent the thermal behav-
464 ior of graphite single crystal. Additionally, at each temperature, the spatial isothermal and
465 adiabatic elasticity tensors have been computed through the derivation of the Cauchy stress
466 with respect to strain, using the different models considered in this work. Adiabatic elastic
467 constants correspond to the instantaneous response of a material to a mechanical deforma-
468 tion of very short wavelength, i.e. as found in the vicinity of the shock-wave front or during
469 very high strain-rate deformation. On the opposite, isothermal elastic constants correspond
470 to a fully equilibrated mechanical response at longer time scales, i.e. after a shock-wave has
471 passed or under quasi-static or low strain-rate deformations.

472 Through the entire temperature range, both isothermal and adiabatic elastic coefficients
473 are found to evolve non-linearly with temperature, independently from the potential used.
474 Based on the good agreement with the literature for both lattice parameters evolution with
475 temperature and for ambient temperature isothermal elastic constants, the LCBOP11 model
476 seems appropriate to study the mechanical behavior of graphite at high temperature. An
477 analytical formulation for both isothermal and adiabatic spatial elasticity tensors as a function
478 of temperature has been introduced as a preliminary element in order to build a mesoscopic
479 model for the elastic behavior of graphite single crystal. The dependence on temperature is
480 reproduced through a component-wise third-order polynomial fit using the Hadamard product,
481 allowing to interpolate the elastic coefficients calculated using MD simulations.

482 Interestingly, it has been observed that isothermal and adiabatic elastic constants signif-
483 icantly differ from each other. A clear consequence of that is the difference in the elastic
484 anisotropy of graphite, the universal anisotropy index being larger by a factor of ~ 20 in the
485 isothermal case than in the adiabatic case, whatever the temperature. Also, temperature
486 has a tremendous influence on elastic anisotropy with a decrease by a factor of five of the

487 universal anisotropy index observed between 300 K and 4000 K. This is of high importance
488 since it has been shown that elastic softening deformation mechanisms such as elastic insta-
489 bilities and in particular buckling are driven by the material anisotropy [51, 12, 43, 52]. The
490 presented results actually suggest that such buckling transition may be suppressed at high
491 temperatures and/or under adiabatic conditions.

492 Finally, MD simulations were used to investigate the details of the adiabatic to isothermal
493 elastic relaxation by imposing an instantaneous deformation to a graphite single crystal at
494 different temperatures and strain levels. The simulations suggest that in the presence of a
495 tensile shock-wave going through a graphite crystal, a non negligible width of ~ 20 nm is
496 required to accommodate a 1 % instantaneous in-plane tension applied to graphite at room
497 temperature and to allow the local material state to transit from adiabatic to isothermal
498 stress response. Overall, this study provided a detailed, temperature dependent, analytic
499 model of the adiabatic and isothermal elasticity of single crystalline graphite, that can be
500 integrated into mesoscale models of graphite-based materials elasticity.

501 **5. Acknowledgments**

502 The authors would like to thank Dr. Christophe Denoual and Dr. Nicolas Pineau for their
503 help in both setting up the MD simulations using the LCBOPII potential and discussing the
504 results. This research is financially supported by the French Ministry of Defence - Defence
505 Innovation Agency. Atomistic simulations were performed using the computational resources
506 of the TGCC-CEA.

507 **References**

- 508 [1] J. Couzi, J. de Winne, B. Leroy, Improvements in Ablation Predictions for Reentry-Vehicles Nosetip, in:
509 R. A. Harris (Ed.), *Aerothermodynamics for space vehicles*, Vol. 426 of ESA Special Publication, 1999,
510 p. 493.
- 511 [2] I. L. Shabalín, *Ultra-high temperature materials II*, Springer, 2019.
- 512 [3] G. Savage, *Carbon/Carbon composites*, Chapman & Hall, London, 1993.
- 513 [4] C. Scarponi, Carbon-carbon composites in aerospace engineering, in: S. Rana, R. Figueiro (Eds.),
514 *Advanced Composite Materials for Aerospace Engineering*, Woodhead Publishing, 2016, pp. 385–412.
515 doi:10.1016/B978-0-08-100037-3.00013-4.
- 516 [5] M. Trinquocoste, J. Carlier, A. Derré, P. Delhaès, P. Chadeyron, High temperature thermal and mechanical
517 properties of high tensile carbon single filaments, *Carbon* 34 (7) (1996) 923–929. doi:10.1016/0008-
518 6223(96)00052-8.
- 519 [6] C. Sauder, J. Lamon, R. Pailler, Thermomechanical properties of carbon fibres at high temperatures (up
520 to 2000 °C), *Compos. Sci. Technol.* 62 (4) (2002) 499–504. doi:10.1016/S0266-3538(01)00140-3.
- 521 [7] C. Sauder, J. Lamon, R. Pailler, The tensile behavior of carbon fibers at high temperatures up to 2400
522 °C, *Carbon* 42 (4) (2004) 715–725. doi:10.1016/j.carbon.2003.11.020.
- 523 [8] C. Sauder, J. Lamon, R. Pailler, The tensile properties of carbon matrices at temperatures up to 2200°C,
524 *Carbon* 43 (10) (2005) 2054–2065. doi:10.1016/j.carbon.2005.03.020.

- 525 [9] C. Pradere, C. Sauder, Transverse and longitudinal coefficient of thermal expansion of carbon fibers at
526 high temperatures (300–2500k), *Carbon* 46 (14) (2008) 1874–1884. doi:10.1016/j.carbon.2008.07.035.
- 527 [10] M. P. Kroonblawd, L. E. Fried, High explosive ignition through chemically activated nanoscale shear bands,
528 *Phys. Rev. Lett.* 124 (2020) 206002. doi:10.1103/PhysRevLett.124.206002.
- 529 [11] M. P. Kroonblawd, B. A. Steele, M. D. Nelms, L. E. Fried, R. A. Austin, Anisotropic strength behavior of
530 single-crystal tatb, *Model. Simul. Mat. Sci. Eng.* 30 (1) (2021) 014004. doi:10.1088/1361-651X/ac3ca4.
- 531 [12] P. Lafourcade, C. Denoual, J.-B. Maillet, Mesoscopic constitutive law with nonlinear elasticity and phase
532 transformation for the twinning-buckling of tatb under dynamic loading, *Phys. Rev. Mater.* 3 (2019)
533 053610. doi:10.1103/PhysRevMaterials.3.053610.
- 534 [13] L. A. Zepeda-Ruiz, A. Stukowski, T. Opperstrup, V. V. Bulatov, Probing the limits of metal plasticity
535 with molecular dynamics simulations, *Nature* 550 (7677) (2017) 492–495. doi:10.1038/nature23472.
- 536 [14] L. A. Zepeda-Ruiz, A. Stukowski, T. Opperstrup, N. Bertin, N. R. Barton, R. Freitas, V. V. Bulatov,
537 Atomistic insights into metal hardening, *Nat. Mater.* 20 (3) (2020) 315–320. doi:10.1038/s41563-020-
538 00815-1.
- 539 [15] E. van der Giessen, P. A. Schultz, N. Bertin, V. V. Bulatov, W. Cai, G. Csányi, S. M. Foiles, M. G. D.
540 Geers, C. González, M. Hütter, W. K. Kim, D. M. Kochmann, J. LLorca, A. E. Mattsson, J. Rottler,
541 A. Shluger, R. B. Sills, I. Steinbach, A. Strachan, E. B. Tadmor, Roadmap on multiscale materials
542 modeling, *Model. Simul. Mat. Sci. Eng.* 28 (4) (2020) 043001. doi:10.1088/1361-651X/ab7150.
- 543 [16] V. Mazars, O. Caty, G. Couégnat, A. Bouterf, S. Roux, S. Denneulin, J. Pailhès, G. L. Vignoles, Damage
544 investigation and modeling of 3d woven ceramic matrix composites from x-ray tomography in-situ tensile
545 tests, *Acta Mater.* 140 (2017) 130–139. doi:https://doi.org/10.1016/j.actamat.2017.08.034.
- 546 [17] A. P. Gillard, G. Couégnat, S. Chupin, G. L. Vignoles, Modeling of the non-linear mechanical and ther-
547 momechanical behavior of 3d carbon/carbon composites based on internal interfaces, *Carbon* 154 (2019)
548 178–191. doi:10.1016/j.carbon.2019.07.101.
- 549 [18] B. Farbos, P. Weisbecker, H. E. Fischer, J.-P. Da Costa, M. Lalanne, G. Chollon, C. Germain, G. L.
550 Vignoles, J.-M. Leyssale, Nanoscale structure and texture of highly anisotropic pyrocarbons revisited with
551 transmission electron microscopy, image processing, neutron diffraction and atomistic modelling, *Carbon*
552 80 (2014) 472–489.
- 553 [19] B. Farbos, J.-P. Da Costa, G. L. Vignoles, J.-M. Leyssale, Nanoscale elasticity of highly anisotropic
554 pyrocarbons, *Carbon* 94 (2015) 285–294.
- 555 [20] F. Vuković, T. Walsh, Practical atomistic models of carbon fiber surfaces with
556 tuneable topology and topography, *Compos. Sci. Technol.* 216 (2021) 109049.
557 doi:https://doi.org/10.1016/j.compscitech.2021.109049.
- 558 [21] O. L. Blakslee, D. G. Proctor, E. J. Seldin, G. B. Spence, T. Weng, Elastic constants of compression-
559 annealed pyrolytic graphite, *J. Appl. Phys.* 41 (1970) 3373–3382.
- 560 [22] A. Bosak, M. Krisch, Elasticity of single-crystalline graphite: Inelastic x-ray scattering study, *Phys. Rev.*
561 *B* 75 (2007) 153408.
- 562 [23] P. Lafourcade, C. Denoual, J.-B. Maillet, Dislocation core structure at finite temperature inferred by
563 molecular dynamics simulations for 1,3,5-triamino-2,4,6-trinitrobenzene single crystal, *J. Phys. Chem. C*
564 121 (13) (2017) 7442–7449. doi:10.1021/acs.jpcc.6b11576.
- 565 [24] D. Wallace, *Thermodynamics of Crystals*, Wiley, 1972.
- 566 [25] A. Sutton, *Physics of Elasticity and Crystal Defects*, Oxford Series on Materials Modelling, OUP Oxford,
567 2020.
- 568 [26] C. de Tomas, I. Suarez-Martinez, N. A. Marks, Graphitization of amorphous car-
569 bons: A comparative study of interatomic potentials, *Carbon* 109 (2016) 681–693.

- doi:<https://doi.org/10.1016/j.carbon.2016.08.024>.
- [27] C. de Tomas, A. Aghajamali, J. L. Jones, D. J. Lim, M. J. López, I. Suarez-Martinez, N. A. Marks, Transferability in interatomic potentials for carbon, *Carbon* 155 (2019) 624–634. doi:<https://doi.org/10.1016/j.carbon.2019.07.074>.
- [28] D. W. Brenner, O. A. Shenderova, J. A. Harrison, S. J. Stuart, B. Ni, S. B. Sinnott, A second-generation reactive empirical bond order (rebo) potential energy expression for hydrocarbons, *J. Phys.: Condens. Matt.* 14 (4) (2002) 783–802.
- [29] S. J. Stuart, A. B. Tutein, J. A. Harrison, A reactive potential for hydrocarbons with intermolecular interactions, *J. Chem. Phys.* 112 (14) (2000) 6472–6486.
- [30] T. C. O'Connor, J. Andzelm, M. O. Robbins, Airebo-m: A reactive model for hydrocarbons at extreme pressures, *J. Chem. Phys.* 142 (2) (2015) 024903. doi:10.1063/1.4905549.
- [31] N. A. Marks, Generalizing the environment-dependent interaction potential for carbon, *Phys. Rev. B* 63 (3) (2001) 035401.
- [32] J. H. Los, L. M. Ghiringhelli, E. J. Meijer, A. Fasolino, Improved long-range reactive bond-order potential for carbon. i. construction, *Phys. Rev. B* 72 (2005) 214102.
- [33] R. Grantab, V. B. Shenoy, R. S. Ruoff, Anomalous strength characteristics of tilt grain boundaries in graphene, *Science* 330 (6006) (2010) 946–948.
- [34] P. Zhang, L. Ma, F. Fan, Z. Zeng, C. Peng, P. E. Loya, Z. Liu, Y. Gong, J. Zhang, X. Zhang, P. M. Ajayan, T. Zhu, J. Lou, Fracture toughness of graphene, *Nat. Commun.* 5 (2014) 3782. doi:10.1038/ncomms4782.
- [35] A. Gamboa, B. Farbos, P. Aurel, G. L. Vignoles, J.-M. Leyssale, Mechanism of strength reduction along the graphenization pathway, *Sci. Adv.* 1 (10) (2015) e1501009.
- [36] A. Gamboa, G. L. Vignoles, J.-M. Leyssale, On the prediction of graphene's elastic properties with reactive empirical bond order potentials, *Carbon* 89 (2015) 176–87.
- [37] Q. Lu, W. Gao, R. Huang, Atomistic simulation and continuum modeling of graphene nanoribbons under uniaxial tension, *Model. Simul. Mat. Sci. Eng.* 19 (5) (2011) 054006. doi:10.1088/0965-0393/19/5/054006.
- [38] R. Perriot, X. Gu, Y. Lin, V. V. Zhakhovsky, I. I. Oleynik, Screened environment-dependent reactive empirical bond-order potential for atomistic simulations of carbon materials, *Phys. Rev. B* 88 (2013) 064101.
- [39] J. H. Los, N. Pineau, G. Chevrot, G. Vignoles, J.-M. Leyssale, Formation of multiwall fullerenes from nanodiamonds studied by atomistic simulations, *Phys. Rev. B* 80 (2009) 155420.
- [40] C. de Tomas, I. Suarez-Martinez, N. A. Marks, Carbide-derived carbons for dense and tunable 3d graphene networks, *Appl. Phys. Lett.* 112 (25) (2018) 251907. doi:10.1063/1.5030136.
- [41] N. Pineau, Molecular dynamics simulations of shock compressed graphite, *J. Phys. Chem. C* 117 (2013) 12778–12786.
- [42] N. Pineau, L. Soulard, L. Colombet, T. Carrard, A. Pellé, P. Gillet, J. Clérouin, Molecular dynamics simulations of shock compressed heterogeneous materials. ii. the graphite/diamond transition case for astrophysics applications, *J. Appl. Phys.* 117 (2015) 115902.
- [43] P. Lafourcade, C. Denoual, J.-B. Maillat, Elastic instability in graphite single crystal under dynamic triaxial compression: Effect of strain-rate on the resulting microstructure, *J. Appl. Phys.* 128 (4) (2020) 045101. doi:10.1063/5.0009724.
- [44] S. Plimpton, Fast parallel algorithms for short-range molecular dynamics, *J. Comput. Phys.* 117 (1) (1995) 1–19.
- [45] A. P. Thompson, H. M. Aktulga, R. Berger, D. S. Bolintineanu, W. M. Brown, P. S. Crozier, P. J. in 't

- 615 Veld, A. Kohlmeyer, S. G. Moore, T. D. Nguyen, R. Shan, M. J. Stevens, J. Tranchida, C. Trott, S. J.
616 Plimpton, LAMMPS - a flexible simulation tool for particle-based materials modeling at the atomic, meso,
617 and continuum scales, *Comp. Phys. Comm.* 271 (2022) 108171. doi:10.1016/j.cpc.2021.108171.
- 618 [46] Soulard, L., Molecular Dynamics Study of the Micro-spallation, *Eur. Phys. J. D* 50 (3) (2008).
- 619 [47] L. Verlet, Computer" experiments" on classical fluids. ii. equilibrium correlation functions, *Phys. Rev.*
620 165 (1) (1968) 201.
- 621 [48] S. Nosé, A unified formulation of the constant temperature molecular dynamics methods, *J. Chem. Phys.*
622 81 (1) (1984) 511–519. doi:10.1063/1.447334.
- 623 [49] W. G. Hoover, Canonical dynamics: Equilibrium phase-space distributions, *Phys. Rev. A* 31 (3) (1985)
624 1695–1697. doi:10.1103/PhysRevA.31.1695.
- 625 [50] G. J. Martyna, D. J. Tobias, M. L. Klein, Constant pressure molecular dynamics algorithms, *J. Chem.*
626 *Phys.* 101 (5) (1994) 4177–4189. doi:10.1063/1.467468.
- 627 [51] P. Lafourcade, C. Denoual, J.-B. Mailet, Irreversible deformation mechanisms for 1,3,5-triamino-2,4,6-
628 trinitrobenzene single crystal through molecular dynamics simulations, *J. Phys. Chem. C* 122 (2018)
629 14954–14964.
- 630 [52] J.-M. Leyssale, G. Couégnat, S. Jouannigot, G. L. Vignoles, Mechanisms of elastic softening in
631 highly anisotropic carbons under in-plane compression/indentation, *Carbon* 197 (2022) 425–434.
632 doi:https://doi.org/10.1016/j.carbon.2022.06.063.
- 633 [53] Y. Baskin, L. Meyer, Lattice constants of graphite at low temperatures, *Phys. Rev.* 100 (1955) 544–544.
634 doi:10.1103/PhysRev.100.544.
- 635 [54] C. S. G. Cousins, M. I. Heggie, Elasticity of carbon allotropes. iii. hexagonal graphite: Review of data,
636 previous calculations, and a fit to a modified anharmonic keating model, *Phys. Rev. B* 67 (2003) 024109.
637 doi:10.1103/PhysRevB.67.024109.
- 638 [55] M. Grimditch, Shear elastic modulus of graphite, *J. Phys. C: Solid State Phys.* 16 (5) (1983) L143.
639 doi:10.1088/0022-3719/16/5/002.
- 640 [56] J. B. Nelson, D. P. Riley, The thermal expansion of graphite from 15 c. to 800 c.: part i. experimental,
641 *Proc. Phys. Soc.* 57 (6) (1945) 477–486. doi:10.1088/0959-5309/57/6/303.
- 642 [57] E. Kellett, B. Jackets, B. Richards, A study of the amplitude of vibration of carbon atoms in the graphite
643 structure, *Carbon* 2 (2) (1964) 175–183. doi:https://doi.org/10.1016/0008-6223(64)90058-2.
- 644 [58] P. L. Walker, H. A. McKinstry, C. C. Wright, X-ray diffraction studies of a graphitized carbon - changes
645 in interlayer spacing and binding energy with temperature., *Ind. Eng. Chem.* 45 (8) (1953) 1711–1715.
646 doi:10.1021/ie50524a033.
- 647 [59] E. A. Kellett, B. P. Richards, The *c*-axis thermal expansion of carbons and graphites, *J. Appl. Crystallogr.*
648 4 (1) (1971) 1–8. doi:10.1107/S0021889871006149.
- 649 [60] B. G. A. Brito, L. Cândido, G.-Q. Hai, F. M. Peeters, Quantum effects in a free-standing graphene
650 lattice: Path-integral against classical monte carlo simulations, *Phys. Rev. B* 92 (2015) 195416.
651 doi:10.1103/PhysRevB.92.195416.
- 652 [61] C. P. Herrero, R. Ramírez, Quantum effects in graphene monolayers: Path-integral simulations, *J. Chem.*
653 *Phys.* 145 (22) (2016) 224701. doi:10.1063/1.4971453.
- 654 [62] E. Kellett, B. Richards, The thermal expansion of graphite within the layer planes, *J. Nucl. Mater.* 12 (2)
655 (1964) 184–192. doi:https://doi.org/10.1016/0022-3115(64)90139-4.
- 656 [63] A. Gamboa-Suárez, H. Y. Seuret-Hernández, J.-M. Leyssale, Mechanical properties of pristine
657 and nanocrystalline graphene up to ultra-high temperatures, *Carbon Trends* 9 (2022) 100197.
658 doi:https://doi.org/10.1016/j.cartre.2022.100197.
- 659 [64] S. I. Ranganathan, M. Ostoja-Starzewski, Universal elastic anisotropy index, *Phys. Rev. Lett.* 101 (2008)

660 055504. doi:10.1103/PhysRevLett.101.055504.

661 [65] C. M. Kube, Elastic anisotropy of crystals, AIP Adv. 6 (9) (2016) 095209. doi:10.1063/1.4962996.