



HAL
open science

**Vibrational study of the Various Forms of (Solvated or Unsolvated) Mobile Proton in Materials for storage and production systems based on the Hydrogen vector.
Advantages, Limitations and Open Questions**

Philippe Colomban

► **To cite this version:**

Philippe Colomban. Vibrational study of the Various Forms of (Solvated or Unsolvated) Mobile Proton in Materials for storage and production systems based on the Hydrogen vector. Advantages, Limitations and Open Questions. *Asian Journal of Physics* , 2023, 32 (1-2), pp.71-76. 10.54955/AJP.32.1-2.2023.71-76 . hal-04088224

HAL Id: hal-04088224

<https://hal.science/hal-04088224>

Submitted on 4 May 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Vibrational study of the Various Forms of (Solvated or Unsolvated) Mobile Proton in Materials for storage and production systems based on the Hydrogen vector. Advantages, Limitations and Open Questions

Philippe Colombar

Laboratory "from molecule to nano-objects"(MONARIS UMR8233), Sorbonne Université, CNRS, 4 Place Jussieu, 75005 Paris, France

Abstract

The desire to use hydrogen as an energy carrier requires a better knowledge of the materials that can serve as electrolyte or electrode, i.e. solids containing mobile protons. We present here through some examples the contribution and the limits of vibrational spectroscopies (Infrared, Raman and inelastic neutron scattering) to understand the structure and dynamics of proton species and discuss the questions to be resolved.

=====

Since the discovery of the 'wandering proton' by Beintema in 1936 in uranium phosphate hydrate (HUP)[1], and then at the end of 1950s in Nafion® poly(perfluorosulphonic acid) membrane developed for the US Gemini orbiter [2,3] the attention paid to the search for solids with high proton conductivity was correlated with variations of oil prices: high just after the first oil crisis in 1975 and then very low until the vogue for ecological themes of the 21st century and subsequent impetus on energy systems based on Hydrogen vector [2]. The objective was to discover stable solids without electron conductivity to be used as electrolyte, or with high electron conductivity to be used as electrode, in a range of temperature making it possible to avoid having to resort expensive electrodes (made of Pt, Pd and Rh) to produce H₂-air fuel cells, water electrolyzers and converters of CO₂ into useful chemical compounds or, simply H-sensors [3-6]. Academic works on the optimization of materials synthesis and measurements of conductivity are the most frequent, although often carried out under conditions that are not very representative of those required by the technical and economic constraints (temperature range, 20-50 bar gas pressure, high current per surface unit).[6-8] Attempts to understanding the nature of protons, especially mobile ones, is much more limited, especially in recent years. However, from the first studies such as the Ensberger review in 1983 [9] or the first book devoted to Proton Conductors [3], the uniqueness of the proton was underlined. A recent review paper reports the state-of-the-art concerning the understanding of the nature of the chemical bond between the proton in the solid phase and its dynamics in the working temperature range, for temperatures between 250-450, 750-1000 or even 1200 K depending on the type of application [10] and a summary is given here.

How to highlight the presence of protonic species

Four methods are effective: variation of mass with temperature (Thermo-Gravimetric Analysis), incoherent neutron scattering (Elastic and Quasi elastic scattering, diffraction background), vibrational spectroscopy (Infrared, inelastic neutron and Raman scattering) and electrochemical evidence (production of H₂, etc.). [3,10, 11] The temperature at which the departure of protons or water (or NH₃) occurs gives information on the strength of the bond between the proton and its environment, typically around 400-500 K for the departure of water molecules, 700 K for de-hydroxylation or even more than 1000 K for some isolated protons [11]. Due to the very large value of the incoherent section of the H isotope, 80 b, i.e. 100 times and more than for most other elements,[12] the incoherent spectrum of a compound containing a little H corresponds to the modes involving proton displacement. The comparison of the signal of a compound before and after drying at ~400K makes it possible to differentiate the contributions of bulk and surface protons. [11] The use of perfectly densified single crystals or ceramics – and not powder – guarantees the quality of the results, whether for diffraction or neutron spectroscopy.[13,14,15] Due to its very polarizing nature, the proton species form dipoles and therefore infrared spectroscopy is the most effective method.[3,10,16,17] On the contrary, as the number of electrons involved in the M-H bonds is very low, the Raman spectra are not very intense but the proton is strongly disturbed and this modifies the Raman signatures of the host lattice. Different procedures

exist to obtain an infrared spectrum. The only ones that minimize the reactions between the sample and the environment (the small temperature difference between the solidification point of water and its boiling point leads to a large variation in the partial pressure of water and the formation of a strong gradient at the surface of the compounds, modifying the composition and local crystallinity) are the use of single crystals, dense ceramics or powders encapsulated in liquid paraffin (Nujol[®], Fluorolube[®]) to control the partial pressure of 'water and to avoid reaction with NaCl, KBr or even CsI wafers. Only CaF₂, KRS5[®] and Si wafer are reliable. Reflexion and Transmission measurements should be preferred in order to have the spectrum dominated by surface water and hydrox(carbonate) species.[10] Deuteration (or ³T isotopic substitution), H/D isotopic dilution and partial ion exchange procedures are very useful to 'simplify' the spectrum and its assignment.[10,18]

The well established protonic species

At least three types of 'protons' are considered, characterized mostly using vibrational spectroscopy [2,6-8]: i) covalently bonded proton, ii) isolated or ionic proton and iii) proton without visible signature.

In the first type, the proton establishes covalent bond with one acceptor ion, oxygen (OH, HO-H₂), nitrogen (HN-H₃), or sulfur (H-SO₄) is commonly considered [2-6]. These different species, namely hydroxyl ions (OH⁻), oxonium (H₃O⁺) / ammonium (NH₄⁺) ions, more solvated hydroxonium ions (H₅O₂⁺, H₇O₃⁺, etc.), etc. present clear signatures in infrared spectroscopy,[16,17,18,19] which are all the more characteristic – and visible – when the X-H...Y bond is not too strong [3,6]. Figure 1 shows typical Infrared signatures recorded on β alumina.




Fig. 1. Representative IR signatures of O-H, H₃O⁺ and H₅O₂⁺/H₇O₃⁺ species in β alumina (a), schematic of the structure (b, with view of the Beever-Ross and middle-oxygen sites; black circle: oxonium ion; open circle: oxygen ion) and sketch of the site occupation in the conducting plane. In a), from the top spectra recorded using a dispersion of powdered partially hydrated oxonium β alumina single crystal in fluorolube[®] mull in-between two CaF₂ wafers, comparison between the spectra of single crystal of β and β'' alumina phase, comparison of the spectra of single crystal of oxonium β and β'' alumina after partial ion exchange of ~30% of oxonium ions with silver ions [19]. Reliable relationship established between vibrational parameters (center of gravity of stretching band, bandwidth) and crystallographic data (O-H...X donor-acceptor distance)[16] allows determination of the H-bond distance with neighboring proton acceptors.[10,19]

New proton species

Inelastic incoherent neutron spectroscopic signatures recorded on a layer of oriented full hydrated and oxonium β alumina single crystals are presented in Figure 2.[20] The dominant species are oxonium and hydroxonium ions respectively and the spectra confirm the above assignments. However the behavior of the H_3O^+ ion is strange, the simulation of the spectrum is the best if we consider an ion with T_d symmetry; i.e. with a partial distribution of the protons around the ion oxygen.[20]

Note the large continuous background which indicates that not all the hydrogen atoms are engaged in covalent bonds. Indeed, because of its low mass, if the proton is not (significantly) bound, the proton recoils and this gives rise to this large continuous background, observed for all proton conductors [20-26] as well on other materials such as carbons [27]

The INS spectra obtained on other compounds where the infrared spectra identify oxonium and hydroxonium ions provide exceptional information. Keggin salts (also called POMs: polyoxometallates) which have been extensively studied [24,25], with well-established structures by both X-ray and neutron diffraction, present many hydration states and in particular oxonium and hydroxonium species. In fact, different forms are in a dynamic equilibrium depending on the temperature [3,9].

The INS spectra are very similar to those obtained on the β aluminas but for the almost dehydrated compound a very simple, unexpected spectrum is obtained: a peak at 1150 cm^{-1} and its harmonics, characteristic spectrum of an 'isolated' proton, ionic, or polaronic in its site. It is the second type of proton.




Fig. 2. Representative Inelastic (incoherent) neutron spectra of fully hydrated (top) and partly dehydrated beta alumina (bottom) (redrawn from ref [20]). Simulation of the spectrum for H_5O_2^+ and H_3O^+ ions are given; * contribution of the residual species. Note the strong background.

Nominally anhydrous proton conductors

The search for materials used as solid electrolyte in fuel cells and then electrolyzers led in the 1960s to identify perovskites as proton conductors at medium temperature.[3,10] Due to the possibility of creating oxygen vacancies perovskites are at high temperature anionic conductors. Different teams use these materials as electrolyte or after substitutions generating electronic conductivity as electrode of industrial prototypes. But the hydrogen content is very weak on the order of doping. Indeed it appears that only part of the oxygen vacancies created by partial substitution of zirconium (4^+ ion) by 3^+ ions (cerium, yttrium, erbium...) are filled in the presence of water vapor.

Figure 3 compares the Raman spectra of a dense ceramic of $\text{SrZr}_{0.9}\text{Er}_{0.1}\text{O}_{3-\delta}$ as a function of heat treatment sequence cycles (from RT to 900°C under ultra-high vacuum, i.e. de-protonation) and autoclave protonation (500°C, 40 bar H_2O , several days to protonate to core)[14]. The bulk proton content is measured by TGA, elastic neutron scattering and neutron diffraction.[10,11] If the densification of the ceramic is less than 95%, the quantity of proton species formed on the surface of the ceramic becomes much greater than the quantity inserted. In this case an infrared spectrum corresponding to strontium hydroxycarbonates (or barium for homologues) is observed. For a dense ceramic, no spectrum is detected either by infrared or by incoherent inelastic neutron scattering [10,14], which is understandable given the low hydrogen bulk content (e.g. $\text{H}_{0.02}\text{SrZr}_{0.9}\text{Er}_{0.1}\text{O}_{3-\delta}$). On the other hand, as illustrated in figure 3, protonation modifies the crystal lattice (symmetrization, the distortion of the ideally cubic perovskite lattice is reduced), the phase transition sequences and the Raman spectrum in the 700-900 cm^{-1} range where are presents the Zr-O elongation modes perturbed by the presence of nearby vacancies [14].The changes in the spectral signature of these modes is evident while the rest is unchanged. In particular the lattice modes below 200 cm^{-1} are unchanged because the structure is unchanged, which is confirmed by neutron diffraction, only the parameters are slightly modified: the volume of the unit-cell contracts from 278 to 277 Å^3 after protonation, which proves the disruption induced by the 0.02 H inserted. We see the effectiveness of Raman analysis to detect disturbances of the host lattice while proton species cannot be detected.




Fig. 3. Comparison of Raman spectra recorded on a dense sintered $\text{SrZr}_{0.9}\text{Er}_{0.1}\text{O}_{3-\delta}$ ceramic (>98% of the theoretical density), at the surface (surf) and in the core after breakage (bulk) before protonation with those recorded after protonation in an autoclave at 500°C under 40 bar H_2O for a few days. The composition of protonated ceramic is $\text{H}_{0.02}\text{SrZr}_{0.9}\text{Er}_{0.1}\text{O}_{3-\delta}$

Open questions and perspectives

This quick summary of the questions concerning the species of mobile protons in the solid phase makes it possible to formulate questions and highlights the imposing need to be able to work on single crystals and to go to the fundamental questions. The symmetry of the oxonium ion in beta alumina or the presence of the continuous background in neutron INS (the widely studied compounds) present points to be clarified. If the first ab initio calculations concerned the 'isolated' proton hydrates, there is no conclusive work once inserted into the solid networks at the temperature leading to their conduction properties. The quantum behavior of the proton and its possibilities of correlations (Quantum entanglement) remain to be studied in many compounds [28,29]. If we remember that the size of the proton is just halfway between that of the lithium ion and the electron, we understand that the understanding of the modification of the properties and the structure by a doping (a few % of the sites possible are only concerned) requires fine studies on single crystals and not on powder, the work on perfectly densified ceramics being only a last resort. Thus for perovskites it is necessary to identify which types of vacancies and how can be filled by oxygen ions and protons. This can only be done from single crystals. The study of the role and behavior of grain boundaries being a second step. Isotopic substitutions (H/D/T) and ion exchanges provide important experimental clarifications and they make it possible to differentiate static and dynamic disorders by measurements over a wide temperature range. The study of conductivity in the whole frequency range from DC to THz is necessary [30] as the modeling of the dynamics of the proton and its scattering mechanisms [31,32]. As from the technical-economic point of view, systems such as fuel cells, electrolyzers and converters of CO₂ into valuable products must be pressurized, studies in situ or operando in autoclave must be made.

References

- [1] J. Beintema, *Rec. Trav. Chim. Pays-Bas*, **57**, 155-175 (1938)
- [2] P. Colomban, *Solid State Ionics*, **334**, 125-144 (2019)
- [3] P. Colomban, Ed., *Proton conductors. Solids, membranes and gels-Materials and devices*, Cambridge University Press, Cambridge, United Kingdom, 1992.
- [4] P. Knauth, M.L. Di Vona, *Solid State Proton Conductors: Properties and Applications in Fuel Cells*, Wiley, New-York, 2012.
- [5] M. Marrony, *Proton Conducting Ceramics, from Fundamental to Applied Research*, Pan Stanford Publishing, Singapore, 2016.
- [6] B. Sala, O. Lacroix, S. Willemin, K. Rhamouni, H. Takenouti, A. Van der Lee, P. Goeuriot, B. Bendjeriou, P. Colomban, Procédé d'optimisation de la conductivité assurée par le déplacement des protons H⁺ et/ou des ions OH⁻ d'une membrane conductrice, Patent EP2168198A2. <https://patents.google.com/patent/EP2168198A2>
- [7] A. Slodczyk, O. Zaafrani, M.D. Sharp, J.A. Kilner, B. Dabrowski, O. Lacroix, Ph. Colomban, *Membranes* **3**, 311-330 (2013). <https://doi.org/10.3390/membranes3040311>
- [8] S. Upasen, P. B atocchi, F. Mavy, A. Slodczyk, P. Colomban, *Ceram. Int.* **41**, 14137-14147 (2015)
- [9] F.M. Ensberger, *J. Am. Ceram. Soc.* **66** 747-750 (1983). <https://doi.org/10.1111/j.1151-2916.1983.tb10555.x>
- [10] P. Colomban, *Solid State Ionics*, **393**, 116187 (2023)
- [11] P. Colomban, *Fuel Cells*, **13**, 6-18 (2013)
- [12] M. Bee, *Quasi-elastic neutron scattering*, Adam Hilger, Bristol; 1985
- [13] A. Slodczyk, P. Colomban, N. Malikova, O. Zaafrani, S. Longeville, J.M. Zanotti, O. Lacroix, B. Sala, *Solid State Ionics* **252** 7-11 (2013). <https://doi.org/10.1016/j.ssi.2013.06.012>
- [14] A. Slodczyk, P. Colomban, S. Upasen, F. Grasset, G. André, *J. Phys. Chem. Solids* **83**, 85-95 (2015)
- [15] P. Colomban, A. Slodczyk, *Eur. Phys. J. Special Topics.* **213**, 171-193 (2012) [10.1140/epjst/e2012-01670-7](https://doi.org/10.1140/epjst/e2012-01670-7)
- [16] A. Novak, *Structure and Bonding*, **18** 177-216 (1974). <https://link.springer.com/chapter/10.1007/BFb0116438>
- [17] P. Colomban, A. Novak, *J. Mol. Struct.*, **177**, 277-308 (1988)

- [18] M. PhamThi, P. Colomban, *J. Phys. Chem. Solids* **46** 565-578 (1985).
[https://doi.org/10.1016/0022-3697\(85\)90219-7](https://doi.org/10.1016/0022-3697(85)90219-7)
- [19] P. Colomban, G. Lucazeau, R. Mercier, A. Novak, *J. Chem. Phys.* **67** 5244-5251 (1977).
<https://doi.org/10.1063/1.434701>
- [20] P. Colomban, F. Fillaux, J. Tomkinson, G.J. Kearley, *Solid State Ionics* **77** 45-50 (1995).
[https://doi.org/10.1016/0167-2738\(94\)00259-U](https://doi.org/10.1016/0167-2738(94)00259-U)
- [21] F. Fillaux, N. Leygue, R. Baddour-Hadjean, S. Parker, P. Colomban, A. Gruger, A. Régis, L.T.L. Yu, *Chem. Phys.* **216** 281-293 (1997). [https://doi.org/10.1016/S0301-0104\(96\)00382-5](https://doi.org/10.1016/S0301-0104(96)00382-5)
- [22] F. Fillaux, *Solid State Ionics* **125** 69-79 (1999). [https://doi.org/10.1016/S0167-2738\(99\)00160-5](https://doi.org/10.1016/S0167-2738(99)00160-5)
- [23] P. Colomban, J. Tomkinson, *Solid State Ionics*, **97**, 123-134 (1997)
- [24] U. Mioc, M. Davidovic, N. Tjapkin, P. Colomban, A. Novak, *Solid State Ionics*, **46**, 103-109 (1991)
- [25] U. Mioc, S.K. Milonjic, D. Malovic, V. Stamenkovic, P. Colomban, M.M. Mitovic, R. Dimitrijevic, *Solid State Ionics*, **97**, 239-246 (1997)
- [26] F. Fillaux, N. Leygue, R. Baddour-Hadjean, S. Parker, P. Colomban, A. Gruger, A. Régis, L.T. Yu, *Chem. Phys.*, **216**, 281-293 (1997)
- [27] F. Fillaux, R. Papoular, A. Lautié, J. Tomkinson *J. Non-Crystall. Solids* **188** 161-168 (1995).
[https://doi.org/10.1016/0022-3093\(95\)00101-8](https://doi.org/10.1016/0022-3093(95)00101-8)
- [28] F. Fillaux, A. Cousson, M.J. Gutmann *Pure Appl. Chem.* **79** 1023-1039 (2007).
<http://dx.doi.org/10.1351/pac200779061023>
- [29] F. Fillaux, *Chem. Phys. Lett.* **408** 302-306 (2005). <https://doi.org/10.1016/j.cplett.2005.04.069>
- [30] P. Colomban, J.C. Badot, *Solid State Ionics*, **61**, 55-62 (1993).
- [31] S. Deng, Y. Zhang, *phys. Status solidi* **253** 1688-1696 (2016). <https://doi.org/10.1002/pssb.201600063>
- [32] A. Braun, Q. Chen, *Nature Comm.* **8** 15830 (2017). doi:10.1038/ncomms15830.