



HAL
open science

Realistic evaluation of tire wear particle emissions and their driving factors on different road types

Tiago de Oliveira, Bogdan Muresan, Sophie Ricordel, Laurence Lumiere,
Laurence Poirier, Johnny Gasperi

► **To cite this version:**

Tiago de Oliveira, Bogdan Muresan, Sophie Ricordel, Laurence Lumiere, Laurence Poirier, et al.. Realistic evaluation of tire wear particle emissions and their driving factors on different road types. Goldschmidt, Jul 2023, Lyon, France. hal-04104032

HAL Id: hal-04104032

<https://hal.science/hal-04104032>

Submitted on 23 May 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Realistic evaluation of tire wear particle emissions and their driving factors on different road types

Tiago De Oliveira^{1*}, Bogdan Merusan-Paslaru², Sophie Ricordel¹, Laurence Lumière², Laurence Poirier³, Johnny Gasperi¹

¹ Université Gustave-Eiffel, Laboratoire Eau et Environnement

² Université Gustave-Eiffel, Laboratoire Environnement-Aménagement, Sécurité et Eco-conception

³ Université de Nantes, Institut des Substances et Organismes de la Mer

*tiago.de-oliveira@univ-eiffel.fr

Abstract:

During its use, a tire undergoes significant physical stresses, including abrasion, related to driving conditions. In turn, tire abrasion emits particles called Tire Wear Particles (TWP). Considering their polymeric composition, TWP are considered as microplastics, which are widely distributed in soil, sediment, and road samples around highway or urban areas, confirming environmental contamination [1].

To provide knowledge regarding the sources and fate of TWP in the environment, TWP emissions under various realistic conditions have to be better examined and factors driving these emissions better assessed. Hence, this study evaluates TWP emissions of a fully instrumented vehicle driving five emblematic road types: rural, suburban, highway, beltway, and urban. Speed, distance and vehicle dynamic factors were recorded for each track. For the first time, the emissions were collected on filters with different cut-off thresholds from 0.39 to 10 μm resulting in seven fractions that were analyzed by pyrolysis coupled with gas chromatography-mass spectrometry. Analyzes targeted the polymeric content of tires, namely, styrene-butadiene-rubber (SBR). The derived emission data were then correlated with corresponding driving conditions and vehicle variables.

The measurements taken over the five routes show similar distributions for SBR-based TWP emissions by number, with maxima in the sub-micron fraction ($< 0.39 \mu\text{m}$). This is much

smaller than expected and confirms the ability of TWP to widely impregnate the atmosphere around roads and, consecutively, more distant environmental compartments. Upon applying a SBR-to-TWP conversion factor derived by quantifying SBR of the instrumented tire, sub-micron TWP emissions were the highest for highway (2.8 ± 0.8 mg/g of collected particle) followed by suburban, urban, beltway and rural routes. An analysis of variables finally indicated that neither the distance travelled nor the driving time are major determinants. Instead, speed (variations), vertical and lateral tire constrains, traffic fluidity exhibited significant correlations with TWP emission ($r > 0.81$, $p < 0.1$).

Keyword:

Tire wear particles, Instrumented vehicle, CG-MS pyrolysis, Real-world emission factors

Reference:

- [1] Goßmann, I., Halbach, M., Scholz-Böttcher, B.M., 2021. Car and truck tire wear particles in complex environmental samples – A quantitative comparison with “traditional” microplastic polymer mass loads. *Science of The Total Environment* 773, 145667. <https://doi.org/10.1016/j.scitotenv.2021.145667>