



HAL
open science

Determination of dielectric properties of mimicking biological tissues by electrochemical impedance spectroscopy

Mado Abraham, Sylvain Feruglio, Ahmed Hamraoui, Hakeim Talleb, Vincent Vivier, Kieu Ngo

► **To cite this version:**

Mado Abraham, Sylvain Feruglio, Ahmed Hamraoui, Hakeim Talleb, Vincent Vivier, et al.. Determination of dielectric properties of mimicking biological tissues by electrochemical impedance spectroscopy. 12th International Symposium on Electrochemical Impedance Spectroscopy (EIS2023), Jul 2023, Pékin, China. 10.1088/0031-9155/41/11/001 . hal-04163868

HAL Id: hal-04163868

<https://hal.science/hal-04163868>

Submitted on 17 Jul 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Determination of dielectric properties of mimicking biological tissues by electrochemical impedance spectroscopy

Mado Abraham¹, Sylvain Feruglio¹, Ahmed Hamraoui², Hakeim Talleb³, Vincent Vivier⁴, Kieu Ngo⁴

¹Sorbonne Université, CNRS, LIP6; ²Sorbonne Université, CNRS, LCMCP; ³Sorbonne Université, CNRS, GeePS;

⁴Sorbonne Université, CNRS, LRS, F-75005 Paris, France, kieu.ngo@sorbonne-universite.fr

Introduction and objective

Tissue-mimicking materials are widely used as substitutes in many medical branches, including surgical procedures, medical imaging, machine calibration, training, and simulations. Usually, these materials are fabricated either by chemical synthesis or additive manufacturing (3D printing), to mimic the mechanical, optical or, as in the present work, electrical properties of the targeted tissues.

The aim of this work is to fabricate a biomaterial that mimics, as closely as possible, the dielectric properties of bone in the context of spinal surgery, where low-frequency electrical stimulation is performed to verify the correct placement of titanium pedicle screws around the nerve structure [1].

Synthesis of the tissue-mimicking materials

In order to obtain a tissue mimicking the bone of the spine, different mixtures of hydrogels containing chitosan and hydroxyapatite (HAp) were prepared by varying the concentrations and/or the pH of the hydrogels.

➤ Preparation of 20 mL of chitosan-based gel:


- 120 μL of acetic acid + 240 μL NaOH + distilled water
- Addition of x mg of chitosan (x : 40 mg (1), 50 mg (2) and 60 mg (3)) to obtain different viscosities



Chitosan-based gel from least viscous (1) to most viscous (3)


➤ Preparation of HAp-based hydrogels: a two-step procedure (synthesis of HAp nanoparticles and mixing with gelatin to obtain HAp-based gels in desired concentration)

- (a) HAp nanoparticles: mixing of $\text{Ca}(\text{OH})_2 + \text{NH}_4\text{H}_2\text{PO}_4$ in pure water, curing under magnetic stirring for 48h; recovery by Büchner filtration; oven drying
- (b) Carrot of HAp-based gel after mixing HAp nanoparticles and gelatin



Experimental set-up

Two-electrode set-up




Cell #1: Gold planar electrodes




Cell #2: Platinum rod electrodes

$$Z_{\text{measured}} = \frac{1}{j\omega C} \quad \text{with } C = \frac{\epsilon_0 \times \epsilon_r \times S}{d} \rightarrow \epsilon_r = \frac{d}{j\omega \epsilon_0 S Z_{\text{measured}}} \quad \sigma = j\omega \epsilon_0 \epsilon_r$$





(a) Example of impedance spectra (Bode diagram) and (b) conductivity and relative permittivity of hydrogel containing chitosan (5mg/ml)


Conductivity and relative permittivity of synthesized hydrogels



Electrical properties of different mimicking biological tissues compared to those of cortical bone measured by Gabriel et al. [2] (a) conductivity and (b) relative permittivity



Electrical properties of different mimicking biological tissues compared to those of cancellous bone measured by Gabriel et al. [2] (a) conductivity and (b) relative permittivity



Conclusions

Different mixtures of hydrogels containing chitosan and HAp have been chemically prepared by varying the concentrations and/or the pH of hydrogel to obtain a tissue mimicking the bone of the spine. Electrochemical impedance spectroscopy measurements have been performed within these hydrogels to determine their electrical properties from 1 Hz to 1 MHz. It has been showed that hydrogels with 5mg/ml chitosan have similar electrical properties than those of cancellous bone.

References: [1] J. Zyss et al. Neurophysiologie Clinique. 2016, 46(3):234; [2] C. Gabriel et al. The dielectric properties of biological tissues: I. Literature survey, Phys. Med. Biol. 1996, 41(11):2231.