



# **Green Synthesis of Silver Nanoparticles using Egyptian Date Palm (*Phoenix dactylifera* L.) Seeds and Their Antibacterial Activity Assessment**

Mohamed E Abdel-Alim, Karam Samaan, Dominique Guillaume, Hashim Amla

## **► To cite this version:**

Mohamed E Abdel-Alim, Karam Samaan, Dominique Guillaume, Hashim Amla. Green Synthesis of Silver Nanoparticles using Egyptian Date Palm (*Phoenix dactylifera* L.) Seeds and Their Antibacterial Activity Assessment. *Bioactivities*, 2023, 1 (1), pp.1 - 8. <10.47352/bioactivities.2963-654x.180>. <hal-04177040>

**HAL Id: hal-04177040**

**<https://hal.science/hal-04177040v1>**

Submitted on 3 Aug 2023

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons CC BY 4.0 - Attribution - International License



# Green Synthesis of Silver Nanoparticles using Egyptian Date Palm (*Phoenix dactylifera* L.) Seeds and Their Antibacterial Activity Assessment

Mohamed E. Abdel-Alim\*, Karam Samaan, Dominique Guillaume, and Hashim Amla

Received : May 25, 2023

Revised : June 24, 2023

Accepted : June 24, 2023

Online : June 26, 2023

## Abstract

A simple, cost-effective and eco-friendly synthesis technique of silver nanoparticles (AgNPs) using the aqueous extracts of Egyptian date palm (*Phoenix dactylifera* L.) seeds and their antibacterial activity assessment have been conducted. The aqueous extract was used as reducing and stabilizer agents in the synthesis of AgNPs. Characterization of AgNPs was done using different methods including ultraviolet-visible spectroscopy (UV-Vis), Fourier transform infrared (FTIR), field emission-scanning electron microscope (FE-SEM), and X-ray diffraction (XRD). UV-Vis spectrum of the aqueous medium containing AgNPs showed an absorption peak at around 432 nm. FTIR spectra had shown that the biomolecules were responsible for the reduction and capping agents of AgNPs. XRD study showed the particles to be crystalline with a face-centered cubic (fcc) structure. The AgNPs exhibited significant anti-bacterial activity against *Bacillus subtilis*, *Escherichia coli*, *Enterococcus faecalis*, and *Staphylococcus aureus*. Overall, these findings suggest that biosynthesized AgNPs may be used as a potential therapeutic formulation against bacterial infections.

**Keywords:** antibacterial, *Phoenix dactylifera* L., seed, silver nanoparticles

## 1. INTRODUCTION

Silver has a long history of being used as an antimicrobial agent either on its own or in combination with other technologies. It has been extensively researched for its ability to inhibit bacterial growth and has been incorporated into various products and applications. These include creams and dressings for treating burns and ulcers, food packaging to prevent contamination, home appliances like refrigerators and washing machines, and numerous industrial uses [1]. With the advent of nanotechnology, the focus shifted to exploring the antibacterial capacity of silver nanoparticles (AgNPs). AgNPs are nanoscale particles with dimensions ranging from 1 to 100 nm, exhibiting unique electrical, optical, and catalytic properties [2]-[4]. The exceptional antibacterial activity displayed by AgNPs attracted significant attention from researchers and industries. AgNPs have

demonstrated antimicrobial activity against a wide range of microorganisms, including multidrug-resistant bacteria. This enhanced antibacterial activity is relevant in medical and healthcare applications, where AgNPs have been studied for incorporation into surgical tools, clothing, cosmetics, dental products, catheters, and dressings. The potential of AgNPs as antibiotics stems from their various mechanisms of action, allowing them to attack microorganisms on multiple fronts and effectively combat different types of bacteria [5]-[7].

Various synthesis methods have been developed for the production of AgNPs, including physical, chemical, and green synthesis techniques [8]. Physical methods involve the use of expensive equipment, high temperatures, and high pressures. On the other hand, chemical methods utilize toxic chemicals that can have detrimental effects on the environment and living organisms [9]. Consequently, the use of physical and chemical methods is restricted due to these drawbacks. As a result, green synthesis has emerged as a more environmentally friendly and cost-effective alternative. Green synthesis involves the utilization of plants, bacteria, fungi, algae, and other natural sources to produce AgNPs. This approach offers several advantages over traditional methods, as it is more sustainable and poses fewer risks to the environment and human health [10].

Recent studies have focused on the synthesis of

## Publisher's Note:


Pandawa Institute stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



## Copyright:

© 2023 by the author(s).

Licensee Pandawa Institute, Metro, Indonesia. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).



**Figure 1.** UV-Vis spectra of silver nanoparticles synthesized using Egyptian date palm seed extract.

AgNPs using natural extracts derived from leaves [11], seeds [12], and roots [13] of various plant species. These plants include *Allium ampeloprasum* [14], *Aerva lanata* [15], *Scutellaria barbata* [16], *Annona glabra* [17], etc. However, in these studies, the reduction of Ag(I) ions took a considerably long time. To compete with chemical methods and achieve faster synthesis rates with high monodispersion, there is a need for improved biosynthesis methods of AgNPs. Utilizing seed extracts of plants is a promising approach to meet this objective. Several research papers have reported the synthesis of AgNPs using seed extracts, including *Phyllanthus amarus* [18], *Tectona grandis* [19], *Piper nigrum* [20], *Artocarpus hirsutus* [21], and *Nigella sativa* [22] demonstrating their potential in achieving faster and more efficient synthesis rates.

The date palm tree (*Phoenix dactylifera*) is a tropical and subtropical tree that holds a significant place in human history as one of the oldest cultivated plants. For over 7,000 years, it has played a crucial role in the daily lives of people. The cultivation of date palm trees spans across 35 countries globally, covering approximately 2.9 million acres of land. The worldwide production of date fruit is estimated to exceed 7,000,000 metric tons. Notably, Iran is the second-largest producer, accounting for 14% of global production, with Egypt being the leading producer at 17% of global production [23]. Date seeds, referred to as stones or pits, are an essential component of the date fruit and

account for approximately 10 to 15% of its weight. These seeds of *P. dactylifera* are known to contain significant bioactive compounds, making their utilization highly desirable. Date seeds contain a variety of phytochemicals such as flavonoids, polyphenols, phytosterols, and carotenoids, similar to the fruit flesh [24]. This rich phytochemical composition makes date seeds promising candidates for deriving extracts that can be utilized in the synthesis of nanoparticles. In a study by Bhattacharjee et al., date seed extracts were used in the synthesis of FeS nanoparticles using  $\text{FeSO}_4 \cdot 7\text{H}_2\text{O}$  precursors. The researchers suggested that the extract played a role as a stabilizing agent for the particles and potentially acted as a reducing agent during the synthesis process [25]. Another study by Dash et al. employed date seed extracts to reduce Au(III) ions, resulting in the synthesis of gold nanoparticles with sizes ranging from 10 to 15 nm, all achieved at room temperature [26]. The main purposes of this work are to evaluate the potential of the seed extract of *P. dactylifera* for the biosynthesis of AgNPs and investigation of their antibacterial activities against *Bacillus subtilis*, *Escherichia coli*, *Enterococcus faecalis*, and *Staphylococcus aureus*.

## 2. MATERIALS AND METHODS

### 2.1. Materials

Date palm (*Phoenix dactylifera* L.) fruits (Tamar stage) were collected from Alexandria markets,

Alexandria Governorate, Egypt. Laboratory grade silver nitrate ( $\text{AgNO}_3$ ) and Mueller-Hinton agar were purchased from Merck. Double distilled de-ionized water was used for the experiments. All glass wares were properly washed with distilled water and dried in an oven.

## 2.2. Methods

### 2.2.1. Preparation of date seed aqueous extract

The date fruits were first de-pitted and the obtained date seeds were washed carefully with distilled water to remove any adhering flesh. The seeds were thereafter dried in an oven at  $50\text{ }^\circ\text{C}$  for 24 h. The dried seeds were then ground to powder. The obtained fine powder was stored in sealed glass containers at  $4\text{ }^\circ\text{C}$  until further use. To prepare the date seed extract conducted concerning the method reported Bhattacharjee et al. [25], 5 g of date seed powder was added to 50 mL of deionized water, and boiled for 10 min. The suspension was thereafter centrifuged at 5,000 rpm for 5 min to remove suspended particles and then the supernatant was filtered using a  $0.45\text{ }\mu\text{m}$  filter to obtain a clear brownish solution of date seed extract with total solids (TS) concentration of 7 g/L.

### 2.2.2. Green Synthesis of AgNPs

In a typical reaction procedure, 10 ml of the seeds extract was added to 90 ml of  $10^{-3}\text{ M}$  aqueous  $\text{AgNO}_3$  solution. The flask (aqueous phase) was then incubated at room temperature overnight. Any


color changes in the solution were observed [18].

### 2.2.3. Characterization of AgNPs


The formation and stability of AgNPs were observed by measurement of UV-Vis spectra on diluted samples. Distilled water served as the reference blank solution. The absorbance spectra of the AgNPs solution were recorded using a UV-Vis spectrophotometer within the wavelength range of 200 to 800 nm. The AgNPs produced were characterized using different instrumental techniques. To detect surface functional groups, the samples were characterized using a Fourier Transform Infrared spectrophotometer (FTIR, Shimadzu IR Prestige 21). The surface morphology of AgNPs was examined by field emission-scanning electron microscopy (FE-SEM, Carl Zeiss SIGMA). The crystal structure was studied using X-ray diffraction (XRD, PAN Analytical Expert Pro) techniques.

### 2.2.4. Antibacterial Activity Assessment

The antibacterial assays were assessed on Gram-positive and Gram-negative pathogens such as *Bacillus subtilis* (ATCC 6051), *Escherichia coli* (ATCC 25922), *Enterococcus faecalis* (ATCC 29212), and *Staphylococcus aureus* (ATCC 25923), which obtained from Cairo-MIRCEN (Microbiological Resource Center), Faculty of Agriculture, Ain Shams University by using the standard well-diffusion method. The antibacterial activity was measured based on the inhibition zone



**Figure 2.** FTIR spectra of silver nanoparticles synthesized using Egyptian date palm seed extract.



**Figure 3.** FESEM image of silver nanoparticles synthesized using Egyptian date palm seed extract

around the well impregnated with plant extract and synthesized AgNPs.

### 3. RESULTS AND DISCUSSIONS

#### 3.1. UV-Vis Characterization

The biosynthesis of AgNPs from *P. dactylifera* extract was confirmed by UV-Vis spectroscopy, which is a commonly used method to characterize biosynthesized metal/metal oxide nanoparticles. The maximum absorption was observed at 430 nm (Figure 1), which validated the presence of biosynthesized AgNPs in the solution. Similar results emerged from a study by Allemailem et al. that recorded the peak at 432 nm for AgNPs synthesized from Ajwa dates seed extract [27]. Ansari and Alzohairy showed that the maximum absorbance peak was seen at 429 nm for date seed extract. It is generally recognized that UV-Vis spectroscopy could be used to examine the size and shape-controlled nanoparticles in aqueous suspensions [28]. Farhadi et al. showed that, with the decrease in the amount of the extract, the size of AgNPs became smaller and temperature was indirectly proportional to the size of AgNPs [29].


#### 3.2. FTIR Analysis

FTIR spectroscopy was performed to identify the biomolecules responsible for capping and effectively stabilizing AgNPs. The significant peaks, corresponding wavenumbers, and possible functional group interpretations can be seen in Figure 2 of the FTIR spectra for both the dates seed extract and AgNPs. In the extract from *P. dactylifera* seeds, peaks were observed at 665, 1019, 1421, 1632, 2854, and 3410  $\text{cm}^{-1}$ .

Subsequently, after reacting with  $\text{AgNO}_3$ , these peaks shifted towards higher wavenumbers, while their intensities decreased, specifically at 1074, 1382, 1592, 2925, and 3381  $\text{cm}^{-1}$ . The presence of a band at 1019  $\text{cm}^{-1}$  indicates the N–H bonding vibration of amides. The bands between 1019 and 665  $\text{cm}^{-1}$  in the seed extract signify the C=C stretching mode in aromatic compounds, suggesting the presence of certain aromatic compounds like flavonoids. Egyptian date palm seed powder contains various bioactive compounds such as flavonoids, terpenoids, alkaloids, and glycosides. Additionally, researchers have demonstrated the existence of hydroxyl, carboxyl, and carbonyl functional groups in carbohydrates, flavonoids, tannins, and phenolic acids found in palm date fruit and seed extracts, which may contribute to the reduction of Ag(I) ions and stabilization of AgNPs. The involvement of flavonoids and phenolic compounds in the reaction mechanism during the formation of AgNPs can be attributed to their ability to donate electrons or hydrogen, with the keto form present in the backbone of flavonoid compounds being responsible for the reduction of Ag(I) to Ag(0).

#### 3.3. FE-SEM analysis

The FE-SEM image highlighted that the formed nanoparticles were spherical in shape and were fine and uniform in size (Figure 3). The green synthesized AgNPs from various plant extracts have also been described previously. Our results are consistent with those obtained by Allemailem et al. [27] who showed that the AgNPs prepared from Ajwa-dates seed extracts were mostly spherical in shape and 15 to 80 nm in diameter.



**Figure 4.** XRD pattern of silver nanoparticles synthesized using Egyptian date palm seed extract



**Table 1.** Antibacterial activity of silver nanoparticles synthesized using Egyptian date palm seed extract.

Bacterium Name	Zone of Inhibition (mm)
<i>Bacillus subtilis</i>	17
<i>Escherichia coli</i>	19
<i>Enterococcus faecalis</i>	20
<i>Staphylococcus aureus</i>	20

### 3.4. XRD analysis

The nanoparticles synthesized in this method are characterized using powder XRD to confirm the particles as silver and to know the structural information. Figure 4 shows the XRD pattern of AgNPs. The pattern clearly shows the main peaks at  $2\theta$  of 36.74, 44.28, 62.82 and 77.47 corresponding to the (111), (200), (220) and (311) planes, respectively. By comparing JCPDS (file no: 89-3722), the typical pattern of green-synthesized AgNPs is found to possess a face-centered cubic (fcc) structure. A similar result was observed by Anandalakshmi et al. [30] who identified crystalline peaks (38.19, 44.37, 64.56 and 77.47).

### 3.5. Antibacterial Activity Assessment

The activity of AgNPs against bacterial strains was observed at 100  $\mu\text{g/mL}$ , as indicated in Table 1. These results show that AgNPs display an evident significant effect against the tested bacterial strains. The green synthesized AgNPs demonstrated its antibacterial activity against both gram-positive and gram-negative bacteria, it was found that the zone inhibition of AgNPs against *Bacillus subtilis*, *Escherichia coli*, *Enterococcus faecalis*, and *Staphylococcus aureus* was 17, 19, 20 and 20 mm, respectively.

These findings are supported by an earlier study that showed that the highest antimicrobial activity was exhibited against *Enterococcus faecalis* and *Staphylococcus aureus*, whereas the lowest antimicrobial activity was noted against *Bacillus subtilis* and *Escherichia coli*. These bacterial group incubations around the wall are due to the release of diffusible inhibitory compounds from silver nanoparticles. The green synthesis of AgNPs has also paved a better methodological approach in the

medical field.

## 4. CONCLUSIONS

The green synthesis method is eco-friendly, of low cost and capable of producing AgNPs at room temperature. The current study reveals that the Egyptian date palm (*Phoenix dactylifera L.*) seeds extract may be a viable source for the green synthesis of AgNPs. The antimicrobial activity is well demonstrated against *Bacillus subtilis*, *Escherichia coli*, *Enterococcus faecalis*, and *Staphylococcus aureus*. The present study showed a simple, rapid, and economical route to synthesize AgNPs.

## AUTHOR INFORMATION

### Corresponding Author

**Mohamed E. Abdel-Alim** — Department of Chemistry, Alexandria University, Alexandria-5424041 (Egypt);

Email: [m.abdel-alim@yahoo.com](mailto:m.abdel-alim@yahoo.com)

 [orcid.org/0009-0002-4784-2953](https://orcid.org/0009-0002-4784-2953)

### Authors

**Karam Samaan** — Department of Botany & Microbiology, Alexandria University, Alexandria-5424041 (Egypt);

 [orcid.org/0009-0006-7204-0994](https://orcid.org/0009-0006-7204-0994)

**Dominique Guillaume** — Institut des Matériaux de Nantes Jean Rouxel, Nantes Université, Nantes-44000 (France);

 [orcid.org/0009-0001-7366-7178](https://orcid.org/0009-0001-7366-7178)

**Hashim Amla** — Nanosciences African Network, iThemba LABS-National Research Foundation, Somerest West-7129 (South Africa);

 [orcid.org/0009-0003-8888-118X](https://orcid.org/0009-0003-8888-118X)

### Author Contributions

F. E. E. G. Validation, Formal Analysis, Investigation, Writing – Original Draft Preparation, Writing – Review & Editing, and Project Administration; M. R. K. Conceptualization, Methodology, Visualization, and Supervision.

### Conflicts of Interest

The authors declare no conflict of interest.

## REFERENCES

- [1] D.-N. Phan, N. Dorjjugder, Y. Saito, G. Taguchi, H. Lee, J. S. Lee, and I.-S. Kim. (2019). "The mechanistic actions of different silver species at the surfaces of polyacrylonitrile nanofibers regarding antibacterial activities". *Materials Today Communications*. **21** [10.1016/j.mtcomm.2019.100622](https://doi.org/10.1016/j.mtcomm.2019.100622).
- [2] S. Saravanan, R. Kato, M. Balamurugan, S. Kaushik, and T. Soga. (2017). "Efficiency improvement in dye sensitized solar cells by the plasmonic effect of green synthesized silver nanoparticles". *Journal of Science: Advanced Materials and Devices*. **2** (4): 418-424. [10.1016/j.jsamd.2017.10.004](https://doi.org/10.1016/j.jsamd.2017.10.004).
- [3] A. Ahmad, Y. Wei, F. Syed, K. Tahir, A. U. Rehman, A. Khan, S. Ullah, and Q. Yuan. (2017). "The effects of bacteria-nanoparticles interface on the antibacterial activity of green synthesized silver nanoparticles". *Microbial Pathogenesis*. **102** : 133-142. [10.1016/j.micpath.2016.11.030](https://doi.org/10.1016/j.micpath.2016.11.030).
- [4] T. Rasheed, M. Bilal, H. M. N. Iqbal, and C. Li. (2017). "Green biosynthesis of silver nanoparticles using leaves extract of *Artemisia vulgaris* and their potential biomedical applications". *Colloids and Surfaces B: Biointerfaces*. **158** : 408-415. [10.1016/j.colsurfb.2017.07.020](https://doi.org/10.1016/j.colsurfb.2017.07.020).
- [5] T. Shankar, P. Karthiga, K. Swarnalatha, and K. Rajkumar. (2017). "Green synthesis of silver nanoparticles using *Capsicum frutescens* and its intensified activity against *E. coli*". *Resource-Efficient Technologies*. **3** (3): 303-308. [10.1016/j.reffit.2017.01.004](https://doi.org/10.1016/j.reffit.2017.01.004).
- [6] K. R. Aadil, S. I. Mussatto, and H. Jha. (2018). "Synthesis and characterization of silver nanoparticles loaded poly(vinyl alcohol)-lignin electrospun nanofibers and their antimicrobial activity". *International Journal of Biological Macromolecules*. **120** (Pt A): 763-767. [10.1016/j.ijbiomac.2018.08.109](https://doi.org/10.1016/j.ijbiomac.2018.08.109).
- [7] S. Mathew, C. P. Victório, J. Sidhi M S, and B. T. B.H. (2020). "Biosynthesis of silver nanoparticle using flowers of *Calotropis gigantea* (L.) W.T. Aiton and activity against pathogenic bacteria". *Arabian Journal of Chemistry*. **13** (12): 9139-9144. [10.1016/j.arabjc.2020.10.038](https://doi.org/10.1016/j.arabjc.2020.10.038).
- [8] C. V. Restrepo and C. C. Villa. (2021). "Synthesis of silver nanoparticles, influence of capping agents, and dependence on size and shape: A review". *Environmental Nanotechnology, Monitoring & Management*. **15**. [10.1016/j.enmm.2021.100428](https://doi.org/10.1016/j.enmm.2021.100428).
- [9] M. A. Kakakhel, W. Sajjad, F. Wu, N. Bibi, K. Shah, Z. Yali, and W. Wang. (2021). "Green synthesis of silver nanoparticles and their shortcomings, animal blood a potential source for silver nanoparticles: A review". *Journal of Hazardous Materials Advances*. **1** [10.1016/j.hazadv.2021.100005](https://doi.org/10.1016/j.hazadv.2021.100005).
- [10] T. A. Jorge de Souza, L. R. Rosa Souza, and L. P. Franchi. (2019). "Silver nanoparticles: An integrated view of green synthesis methods, transformation in the environment, and toxicity". *Ecotoxicology and Environmental Safety*. **171** : 691-700. [10.1016/j.ecoenv.2018.12.095](https://doi.org/10.1016/j.ecoenv.2018.12.095).
- [11] I. Sk, M. A. Khan, A. Haque, S. Ghosh, D. Roy, S. Homechudhuri, and M. A. Alam. (2020). "Synthesis of gold and silver nanoparticles using *Malva verticillata* leaves extract: Study of gold nanoparticles catalysed reduction of nitro-Schiff bases and antibacterial activities of silver nanoparticles". *Current Research in Green and Sustainable Chemistry*. **3**. [10.1016/j.crgsc.2020.05.003](https://doi.org/10.1016/j.crgsc.2020.05.003).
- [12] M. P. Patil, Y.-A. Seong, J.-O. Kim, Y. B. Seo, and G.-D. Kim. (2021). "Synthesis of silver nanoparticles using aqueous extract of *Cuscuta japonica* seeds and their antibacterial and antioxidant activities". *Inorganic Chemistry Communications*. **134** [10.1016/j.inoche.2021.109035](https://doi.org/10.1016/j.inoche.2021.109035).
- [13] F. Khuda, M. Jamil, A. Ali Khan Khalil, R. Ullah, N. Ullah, F. Naureen, M. Abbas, M. Shafiq Khan, S. Ali, H. Muhammad Umer Farooqi, and M.-J. Ahn. (2022). "Assessment of antioxidant and cytotoxic potential of silver nanoparticles synthesized from root extract of *Reynoutria japonica* Houtt". *Arabian Journal of Chemistry*. **15** (12). [10.1016/j.arabjc.2022.104327](https://doi.org/10.1016/j.arabjc.2022.104327).

- [14] V. Uma Maheshwari Nallal, K. Prabha, I. VethaPotheher, B. Ravindran, A. Baazeem, S. W. Chang, G. A. Otunola, and M. Razia. (2021). "Sunlight-driven rapid and facile synthesis of Silver nanoparticles using Allium ampeloprasum extract with enhanced antioxidant and antifungal activity". *Saudi Journal of Biological Sciences*. **28** (7): 3660-3668. [10.1016/j.sjbs.2021.05.001](https://doi.org/10.1016/j.sjbs.2021.05.001).
- [15] S. Joseph and B. Mathew. (2015). "Microwave assisted facile green synthesis of silver and gold nanocatalysts using the leaf extract of Aerva lanata". *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy*. **136** : 1371-9. [10.1016/j.saa.2014.10.023](https://doi.org/10.1016/j.saa.2014.10.023).
- [16] V. P. Veeraraghavan, N. D. Periadurai, T. Karunakaran, S. Hussain, K. M. Surapaneni, and X. Jiao. (2021). "Green synthesis of silver nanoparticles from aqueous extract of Scutellaria barbata and coating on the cotton fabric for antimicrobial applications and wound healing activity in fibroblast cells (L929)". *Saudi Journal of Biological Sciences*. **28** (7): 3633-3640. [10.1016/j.sjbs.2021.05.007](https://doi.org/10.1016/j.sjbs.2021.05.007).
- [17] L. D. Amarasinghe, P. Wickramarachchi, A. Aberathna, W. S. Sithara, and C. R. De Silva. (2020). "Comparative study on larvicidal activity of green synthesized silver nanoparticles and Annona glabra (Annonaceae) aqueous extract to control Aedes aegypti and Aedes albopictus (Diptera: Culicidae)". *Heliyon*. **6** (6): e04322. [10.1016/j.heliyon.2020.e04322](https://doi.org/10.1016/j.heliyon.2020.e04322).
- [18] J. Joseph, K. S. Deborah, R. Raghavi, A. M. Shamy, and W. Aruni. (2021). "Green synthesis of silver nanoparticles using Phyllanthus amarus Seeds and their antibacterial activity assessment". *Biomedical and Biotechnology Research Journal*. **5** (1): 35-38. [10.4103/bbrj.bbrj.139\\_20](https://doi.org/10.4103/bbrj.bbrj.139_20).
- [19] A. Rautela, J. Rani, and M. Debnath. (2019). "Green synthesis of silver nanoparticles from Tectona grandis seeds extract: characterization and mechanism of antimicrobial action on different microorganisms". *Journal of Analytical Science and Technology*. **10** (1). [10.1186/s40543-018-0163-z](https://doi.org/10.1186/s40543-018-0163-z).
- [20] P. Kanniah, P. Chelliah, J. R. Thangapandi, G. Gnanadhas, V. Mahendran, and M. Robert. (2021). "Green synthesis of antibacterial and cytotoxic silver nanoparticles by Piper nigrum seed extract and development of antibacterial silver based chitosan nanocomposite". *International Journal of Biological Macromolecules*. **189** : 18-33. [10.1016/j.ijbiomac.2021.08.056](https://doi.org/10.1016/j.ijbiomac.2021.08.056).
- [21] S. Shobana, S. Veena, S. S. M. Sameer, K. Swarnalakshmi, and L. A. Vishal. (2020). "Green Synthesis of Silver Nanoparticles Using Artocarpus hirsutus Seed Extract and its Antibacterial Activity". *Current Pharmaceutical Biotechnology*. **21** (10): 980-989. [10.2174/1389201021666200107115849](https://doi.org/10.2174/1389201021666200107115849).
- [22] K. Chand, C. Jiao, M. N. Lakhan, A. H. Shah, V. Kumar, D. E. Fouad, M. B. Chandio, A. Ali Maitlo, M. Ahmed, and D. Cao. (2021). "Green synthesis, characterization and photocatalytic activity of silver nanoparticles synthesized with Nigella Sativa seed extract". *Chemical Physics Letters*. **763**. [10.1016/j.cplett.2020.138218](https://doi.org/10.1016/j.cplett.2020.138218).
- [23] M. I. Hussain, M. Farooq, and Q. A. Syed. (2020). "Nutritional and biological characteristics of the date palm fruit (Phoenix dactylifera L.) – A review". *Food Bioscience*. **34**. [10.1016/j.fbio.2019.100509](https://doi.org/10.1016/j.fbio.2019.100509).
- [24] J. Osamede Airouyuwa, H. Mostafa, A. Riaz, and S. Maqsood. (2022). "Utilization of natural deep eutectic solvents and ultrasound-assisted extraction as green extraction technique for the recovery of bioactive compounds from date palm (Phoenix dactylifera L.) seeds: An investigation into optimization of process parameters". *Ultrasonics Sonochemistry*. **91** : 106233. [10.1016/j.ultsonch.2022.106233](https://doi.org/10.1016/j.ultsonch.2022.106233).
- [25] S. Bhattacharjee, F. Habib, N. Darwish, and A. Shanableh. (2021). "Iron sulfide nanoparticles prepared using date seed extract: Green synthesis, characterization and potential application for removal of ciprofloxacin and chromium". *Powder Technology*. **380** : 219-228. [10.1016/j.powtec.2020.11.055](https://doi.org/10.1016/j.powtec.2020.11.055).



- [26] S. S. Dash, A. K. Sikder, B. G. Bag, and S. Bandyopadhyay. (2013). "Phoenix dactylifera (Date Palm) seed extract mediated green synthesis of gold nanoparticles and its application as a catalyst for the reduction of 4-nitrophenol to 4-aminophenol". *Journal Nanomaterial and Biostar*. **3** : 42-46.
- [27] K. S. Allemailem, H. Khadri, M. Azam, M. A. Khan, A. H. Rahmani, F. Alrumaihi, R. Khateef, M. A. Ansari, E. A. Alatawi, M. H. Alsugoor, N. M. Almansour, B. Y. Alhatlani, and A. Almatroudi. (2022). "Ajwa-Dates (Phoenix dactylifera)-Mediated Synthesis of Silver Nanoparticles and Their Anti-Bacterial, Anti-Biofilm, and Cytotoxic Potential". *Applied Sciences*. **12** (9). [10.3390/app12094537](https://doi.org/10.3390/app12094537).
- [28] M. A. Ansari and M. A. Alzohairy. (2018). "One-Pot Facile Green Synthesis of Silver Nanoparticles Using Seed Extract of Phoenix dactylifera and Their Bactericidal Potential against MRSA". *Evidence-Based Complementary and Alternative Medicine*. **2018** : 1860280. [10.1155/2018/1860280](https://doi.org/10.1155/2018/1860280).
- [29] S. Farhadi, B. Ajerloo, and A. Mohammadi. (2017). "Green Biosynthesis of Spherical Silver Nanoparticles by Using Date Palm (Phoenix Dactylifera) Fruit Extract and Study of Their Antibacterial and Catalytic Activities". *Acta Chimica Slovenica*. **64** (1): 129-143. [10.17344/acsi.2016.2956](https://doi.org/10.17344/acsi.2016.2956).
- [30] K. Anandalakshmi, J. Venugobal, and V. Ramasamy. (2015). "Characterization of silver nanoparticles by green synthesis method using Pedalium murex leaf extract and their antibacterial activity". *Applied Nanoscience*. **6** (3): 399-408. [10.1007/s13204-015-0449-z](https://doi.org/10.1007/s13204-015-0449-z).