



HAL
open science

Layer-controlled nonlinear terahertz valleytronics in two-dimensional semimetal and semiconductor PtSe₂

Minoosh Hemmat, Sabrine Ayari, Martin Mičica, Hadrien Vergnet, Shasha Guo, Mehdi Arfaoui, Xuechao Yu, Daniel Vala, Adrien Wright, Kamil Postava, et al.

► To cite this version:

Minoosh Hemmat, Sabrine Ayari, Martin Mičica, Hadrien Vergnet, Shasha Guo, et al.. Layer-controlled nonlinear terahertz valleytronics in two-dimensional semimetal and semiconductor PtSe₂. *InfoMat*, 2023, 5 (11), pp.e12468. 10.1002/inf2.12468. hal-04208873

HAL Id: hal-04208873

<https://hal.science/hal-04208873v1>

Submitted on 15 Oct 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.





L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution 4.0 International License

RESEARCH ARTICLE

Layer-controlled nonlinear terahertz valleytronics in two-dimensional semimetal and semiconductor PtSe₂

Minoosh Hemmat¹ | Sabine Ayari¹ | Martin Mičica¹ | Hadrien Vergnet¹ | Shasha Guo² | Mehdi Arfaoui³ | Xuechao Yu⁴  | Daniel Vala^{5,6}  | Adrien Wright¹ | Kamil Postava^{5,6} | Juliette Mangeney¹ | Francesca Carosella¹ | Sihem Jaziri² | Qi Jie Wang⁷ | Zheng Liu²  | Jérôme Tignon¹ | Robson Ferreira¹ | Emmanuel Baudin¹ | Sukhdeep Dhillon¹ 

¹Laboratoire de Physique de l'Ecole normale supérieure, ENS, Université PSL, CNRS, Sorbonne Université, Université de Paris-Cité, Paris, France

²School of Materials Science and Engineering, Nanyang Technological University, Singapore, Singapore

³Laboratoire de Physique de la Matière Condensée, Département de Physique, Faculté des Sciences de Tunis, Université Tunis El Manar, Campus Universitaire, Tunis, Tunisia

⁴Key Laboratory of Multifunctional Nanomaterials and Smart Systems, Suzhou Institute of Nano-Tech and Nano-Bionics, Chinese Academy of Sciences, Suzhou, Jiangsu, the People's Republic of China

⁵IT4Innovations, National Supercomputing Center, VSB—Technical University of Ostrava, Ostrava-Poruba, Czech Republic

⁶Faculty of Materials Science and Technology, VSB—Technical University of Ostrava, Ostrava-Poruba, Czech Republic

⁷School of Electrical and Electronic Engineering & School of Physical and Mathematical Sciences, The Photonics Institute, Nanyang Technological University, Singapore, Singapore

Correspondence

Sukhdeep Dhillon, Laboratoire de Physique de l'Ecole normale supérieure, ENS, Université PSL, CNRS, Sorbonne Université, Université de Paris, 24 rue Lhomond, 75005 Paris, France.
Email: sukhdeep.dhillon@phys.ens.fr

Funding information

H2020 Future and Emerging Technologies, Grant/Award Number: 964735; H2020 Excellent Science, Grant/Award Number: 881603; Agence Nationale de la Recherche, Grant/Award Numbers: ANR-16-CE24-0023, ANR-2018-CE08-018-05; National Research Foundation Singapore, Grant/Award Number: NRF-CRP26-2021-0004; Region Ile de France; EquipMeso, Grant/Award Number: ANR-10-EQPX-29-01

Abstract

Platinum diselenide (PtSe₂) is a promising two-dimensional (2D) material for the terahertz (THz) range as, unlike other transition metal dichalcogenides (TMDs), its bandgap can be uniquely tuned from a semiconductor in the near-infrared to a semimetal with the number of atomic layers. This gives the material unique THz photonic properties that can be layer-engineered. Here, we demonstrate that a controlled THz nonlinearity—tuned from monolayer to bulk PtSe₂—can be realized in wafer size polycrystalline PtSe₂ through the generation of ultrafast photocurrents and the engineering of the bandstructure valleys. This is combined with the PtSe₂ layer interaction with the substrate for a broken material centrosymmetry, permitting a second order nonlinearity. Further, we show layer dependent circular dichroism, where the sign of the ultrafast currents and hence the phase of the emitted THz pulse can be controlled through the excitation of different bandstructure valleys. In particular, we show that a semimetal has a strong dichroism that is absent in the monolayer and few layer semiconducting limit. The microscopic origins of this TMD

Minoosh Hemmat, Sabine Ayari, and Martin Mičica contributed equally to this work.

This is an open access article under the terms of the [Creative Commons Attribution](https://creativecommons.org/licenses/by/4.0/) License, which permits use, distribution and reproduction in any medium, provided the original work is properly cited.

© 2023 The Authors. *InfoMat* published by UESTC and John Wiley & Sons Australia, Ltd.

bandstructure engineering are highlighted through detailed DFT simulations, and shows the circular dichroism can be controlled when PtSe₂ becomes a semimetal and when the K-valleys can be excited. As well as showing that PtSe₂ is a promising material for THz generation through layer controlled optical nonlinearities, this work opens up a new class of circular dichroism materials beyond the monolayer limit that has been the case of traditional TMDs, and impacting a range of domains from THz valleytronics, THz spintronics to harmonic generation.

KEYWORDS

2D transition metal dichalcogenides, Dirac semimetal, optical nonlinearities, terahertz, valleytronics

1 | INTRODUCTION

A wide breadth of two-dimensional (2D) transition metal dichalcogenides (TMD) semiconductors have been investigated in recent years, each with unique bandstructures with properties that are distinct from the bulk.^{1,2} Some of the most commonly studied materials include MoS₂, WS₂, MoSe₂, and WSe₂, and key features include tunable bandgap energies in the optical region in the monolayer (ML) or few monolayer regime, as well as giant exciton binding energies. These materials have shown great potential to impact a range of fields in photonics, from quantum optics,^{3–6} the emergence of valleytronics⁷ to layered controlled optical nonlinearities.⁸ For example, second harmonic generation has been shown to depend on the number of TMD layers, where an even number of stacked layers possess inversion symmetry while an odd number do not.^{9,10} Recently these advances have motivated the application of TMDs to the terahertz (THz) spectral range, historically technologically underdeveloped and where 2D TMDs hold great nascent promise. For example, ML MoS₂ has been demonstrated as a non-volatile switch for THz communications^{11,12} or as efficient ultrafast THz modulators.¹³ THz emission time domain spectroscopy (TDS) has proven to be ideal to probe the relevant ultrafast currents and nonlinearities as a sensitive and non-contact technique.¹⁴ Indeed, recent work has shown that optical interband excitations can generate ultrafast THz photocurrents and subsequent nonlinear THz generation in the semiconductors MoSe₂^{15,16} and WSe₂.¹⁷ This has permitted novel insights into the various transport phenomena such as photogalvanic effects to shift-currents in these 2D semiconductor materials. THz emission TDS has also shown valuable insights into ultrafast transport in “zero” bandgap Dirac and Weyl materials. For example, the semimetal TaAs,¹⁸ the Topological Insulator Bi₂Se₃¹⁹ and

graphene²⁰ have shown ultrafast currents that can be controlled through the polarization of the light excitation. Furthermore, semimetals have shown an important application potential as sensitive THz detectors.^{21–23}

However, the transition from semiconductor to semimetal and its effect on the THz photocurrents and nonlinearities generated in TMDs has not been investigated in a single material system, as typical TMDs rapidly transit from a direct to indirect gap with thicknesses greater than one ML. On the other hand, the recently discovered TMD PtSe₂²⁴ has garnered considerable interest. Together with relatively large electronic mobilities,²⁵ the layer controlled bandgap can be tuned slowly from a semiconductor to a Dirac semimetal,²⁶ covering a vast energy scale, from the near-infrared for MLs to the THz region for multilayers. This has permitted, for example, the recent demonstration of atmospheric stable midinfrared detectors based on 2D materials.²⁷ Prior investigations of the nonlinear properties of PtSe₂ have been restricted to PtSe₂ as a saturable absorber with no demonstrations on the layer dependent nonlinearities.²⁸ Very recent studies have investigated THz photocurrents in PtSe₂ but were limited to a single thickness of 2.4 nm²⁹ or 50 nm,³⁰ limiting the understanding of the effect of the bandstructure. Further, these studies have assumed an entirely centrosymmetric nature and neglected the effect of the substrate. The latter is primordial to consider in 2D materials, such that the origin of the generated photocurrents can be understood in the context of the layer dependent bandstructure.

The present contribution shows the first observation of layer dependent, polarization and valley selective excitation of ultrafast photocurrents in air stable, wafer scale, ML to multilayer PtSe₂ at room temperature. We show amplitude and phase resolved THz emission from this 2D material under optical femtosecond excitation, permitting access to the processes of ultrafast photocurrent

generation. We demonstrate that this is a result of a second-order nonlinear response with the THz pulse generated from the ultrafast photocurrents induced by the nonlinear conductivity of PtSe₂. In particular, we show second order contributions from both linear and circular “photon drag” (PDE) and “photogalvanic” (PGE) effects and the critical role of the environment, with the substrate inducing a structural asymmetry in the inherent centrosymmetry of PtSe₂. This is strongly illustrated by THz photocurrents that show an opposite phase change with left and right circular polarization (LCP and RCP) optical excitation for semimetal multilayer PtSe₂ but remain the same for the few layer semiconducting case. These results are corroborated theoretically through extensive DFT simulations of the layer dependent bandstructure showing an important circular dichroism (CD) for semimetal PtSe₂ owing to the excitation of opposite valleys and the strong interaction with the substrate. This work shows that CD is not limited to the ML limit as in other TMDs with natural non-centrosymmetry, and can be finely controlled in the novel layer dependent bandstructure of PtSe₂.

2 | LAYER CONTROLLED EXCITATION OF PtSe₂ VALLEYS

Figure 1A shows the principle of our approach where we exploit the layer dependent energy gaps and the valley properties of PtSe₂. It shows the simulated spin-resolved bandstructure for the two extremes of ML (left) and multilayer (right) PtSe₂ on a substrate. The PtSe₂ is excited with an optical pulse at 1.5 eV, generating ultrafast THz photocurrents that radiate as a short THz pulse. In the ML case, the states at the K points are not accessible for photon energies of 1.5 eV and the interband response is governed by (indirect) transitions around the Γ point. Here the bands have mixed spin up–spin down character, thus the optical absorption is not selective to a specific circular polarization (LCP or RCP) of the incident light. However, this situation changes drastically with multilayer PtSe₂ since the material becomes semimetallic with increasing of the number of layers (typically greater than a few monolayers) and the interband transitions at the K points become accessible for photon energies of 1.5 eV, dominating the optical response. Through symmetry




FIGURE 1 Schematic of helicity dependent generation of THz photocurrents in substrate coupled PtSe₂. (A) Simulated spin-resolved band structure (red for spin up and blue for spin down) of ML (left) and multilayer (right) PtSe₂ on a substrate under circular right (RCP) and left (LCP) femtosecond excitation pulse at 1.5 eV. For the ML indirect interband excitations around Γ point (orange) are possible, while for multilayer PtSe₂, direct interband transitions in the vicinity of K(K') under circular left (right) polarized light can be excited. (B) Schematic illustration of contributions of circular photon drag (PDE) and photogalvanic effects (PGE) and the generation of THz pulses in ML (left, helicity-independent, currents generated with same sign) and multilayer (right, helicity-dependent, currents generated with opposite sign) PtSe₂ with substrate.




FIGURE 2 Ultrafast THz nonlinear emission from semimetal PtSe₂. (A) Schematic of the experimental setup for THz emission using THz time domain spectroscopy. The magnified schematic illustrates the geometry for THz radiation generation from PtSe₂ sample in reflection configuration. A 100 fs laser Ti:Sapphire oscillator excites the PtSe₂ and induces an ultrafast photocurrent and hence a free space THz pulse, which is consequently detected by EO sampling. (B) TM polarized Electric field of single cycle THz pulse as a function of time generated through femtosecond linear (TM) polarization excitation of multilayer (38.5 nm) semimetal PtSe₂. Fourier transformed spectra of THz electric field is shown in the inset of (B). (C) Peak-to-peak THz electric field amplitude dependence on incident average pump power for the 38.5 nm semimetal PtSe₂. The red circles are the experimental data and the blue line is a linear fit.

breaking owing to the substrate, K and K' points have a strong and opposite spin nature that results in a strong CD in PtSe₂, that is, interband transitions in the vicinity of the $K(K')$ points couple exclusively to LCP (RCP) light. We show that this results in the generation of THz photocurrents and the resulting THz emission with opposite signs when excited with LCP or RCP light. This is not possible in the case of ML semiconducting PtSe₂. This is schematically represented in Figure 1B showing the presence of PDEs and PGEs and the polarization role on the

directionality of the generated current in the y direction (q_x is the photon momentum).

In this work, large area polycrystalline PtSe₂ thin films grown by thermally assisted conversion (TAC) of platinum^{24,31–33} were studied. These types of films were chosen as the large uniform areas facilitate THz investigations (owing to the large wavelengths of THz photons) and where exfoliated samples of any size are notoriously difficult to fabricate. Samples were realized with a range of thicknesses from a monolayer semiconductor to

multilayer semimetal. (0.55, 1.1, 2.2, 3.85, 5.5, 11, 16.5, 27.5, and 38.5 nm). The samples were characterized using Raman microscopy and atomic force microscopy (AFM) to confirm the quality of the samples as well as measuring film thicknesses (see [Supplementary material](#) for further details).

2.1 | THz nonlinear emission from PtSe₂

To investigate the ultrafast photogenerated currents, THz emission TDS with a 100 femtosecond Ti:Sapphire oscillator was employed. A schematic of the experimental setup is shown in Figure 2A. The laser excites the PtSe₂ at an angle of 45, generating an ultrafast current and resulting in the emission in free space of a THz pulse. The generated current induces a radiated electric field of the form

$$\mathbf{E}(\mathbf{n}, r) = \frac{ik}{c} (\mathbf{n} \wedge \mathbf{J}_\omega) \wedge \mathbf{n} \frac{e^{ikr}}{r}, \quad (1)$$

where \mathbf{n} is the propagation direction, r is the distance to the source current, $\mathbf{J}_\omega = \int \mathbf{j}(\mathbf{x}) d^3x$ is the integrated source current, k is the wavevector of the emitted radiation and $\omega = kc$. The electric field of the generated THz signal is then detected using standard electro-optic (EO) sampling with a 1 mm thick ZnTe crystal. The complete temporal THz field is then constructed using a scanning delay line (see Figure 2A). Importantly, this amplitude and phase resolved technique is sensitive to the direction of the generated photocurrents in a non-contact geometry. A characteristic time-dependent single cycle THz wave pulse in transverse magnetic (TM) polarization (Electric field E_{xz}) for multilayer semimetal PtSe₂ (38.5 nm thick) is reported in Figure 2B. The excitation average power is 250 mW @ 76 MHz corresponding to a pulse energy of 3.3 nJ and was TM polarized. The corresponding THz spectrum—obtained by Fourier transform of the temporal signal—is represented in the inset of Figure 2B. We observe a spectrally broad emission extending from a few hundred GHz to 2.5 THz (limited by the detection crystal). Figure 2C shows the peak-to-peak THz electric field as a function of the infrared pump average power. The observed linear relation between THz field amplitude and IR pump amplitude highlights that THz emission is a result of a second order nonlinear photocurrent generation.

2.2 | Polarization dependency of THz signal

To elucidate the actual physical mechanism for the THz pulse in PtSe₂, we investigated the role of the polarization

of the optical excitation and the angle of incidence on the polarization of the generated THz pulse, permitting to determine the effects on the generated photocurrents. For any material, the second order nonlinear photocurrent generated from one incident wave E with angular frequency ω and wavevector \mathbf{q} writes³⁴:

$$j_\lambda^{(2)}(0, 0) = \sigma_{\lambda\nu\eta}^{(2)}(\omega, \mathbf{q}) E_\nu(\mathbf{q}, \omega) E_\eta^*(\mathbf{q}, \omega), \quad (2)$$

where $\sigma_{\lambda\nu\eta}^{(2)}$ is the second-order nonlinear conductivity tensor that can be decomposed up to first order in photon momentum:

$$\sigma_{\lambda\nu\eta}^{(2)}(\omega, \mathbf{q}) = \sigma_{\lambda\nu\eta}^{(2)}(\omega, 0) + \Phi_{\lambda\mu\nu\eta}(\omega) q_\mu. \quad (3)$$

In a 2D system the index λ runs only over the two in-plane coordinates x and y while the indices ν and η can include the normal coordinate z . The first term corresponds to PGEs for which the absorption of a photon results in the appearance of a nonlinear current owing to the creation of spatially asymmetric charge distribution within the material (giving a second order nonlinearity, $\chi^{(2)}$). The second term corresponds to PDEs for which the nonlinear current appears in reaction to the partial transfer of the incoming light momentum, q , that is, this is essentially through a non-vertical transition between two bands, facilitated through the incident light momentum. For centrosymmetric materials, such as free standing PtSe₂, PGE are forbidden by symmetry. Equation (2) can be rewritten as the following expressions after separating PGE and PDE photocurrent terms:

$$j_\lambda^{(PGE)} = \chi_{\lambda\nu\eta} \{E_\nu, E_\eta^*\} + i\gamma_{\lambda\mu} \left(\vec{E} \wedge \vec{E}^* \right)_\mu, \quad (4)$$

$$j_\lambda^{(PDE)} = T_{\lambda\mu\nu\eta} q_\mu \{E_\nu, E_\eta^*\} + iR_{\lambda\mu\nu} q_\mu \left(\vec{E} \wedge \vec{E}^* \right)_\nu, \quad (5)$$

where $\chi_{\lambda\nu\eta}$ and $T_{\lambda\mu\nu\eta}$ are the linear tensor terms while $\gamma_{\lambda\mu}$ and $R_{\lambda\mu\nu}$ are circular terms.

We present in the following a set of measurements that ultimately leads to the determination of the above tensor components of the nonlinear conductivity and therefore the principal origins of the second order nonlinear photocurrents. It is based on varying the input pump polarization and its impact on the polarization of the THz beam, which is directly related to the type of photocurrents that are generated. This was performed through the introduction of a half waveplate (HWP) or a quarter waveplate (QWP) in the path of the NIR beam as well as analyzing different polarizations of THz signal




FIGURE 3 Pump polarization and sample angle dependency of the PtSe₂ THz generation—nonlinear tensor determination. (A) Schematic illustration of THz emission TDS in reflection configuration in the presence of a QWP for LCP and RCP or HWP for linear femtosecond excitation. Sample is excited at $\alpha = 45^\circ$ and the THz electric field (TE and TM) dependency on the orientation of the pump polarization is measured. (B) Schematic of the THz emission spectroscopy in transmission configuration, where β is the sample angle where a linear polarized pump beam excites the PtSe₂ and THz-TM emitted pulse is measured. (C) THz-TE amplitude as a function of the QWP angle. (D) THz-TM amplitude as a function of HWP angle. (E) Results from transmission configuration where the angle of sample changes in relation to the pump beam and THz-TM amplitude is measured. Blue circles represent experimental results with their error bars and the red line is the fitting. The sample was a 38.5 nm thick PtSe₂ layer.

from the PtSe₂ layers in reflection geometry as shown in Figure 3A. (Transmitted beam is not detected in this geometry). The orthogonal components—TE and TM

modes—of THz electric signal were separately measured by using a polypropylene polarizer after the sample where TE is the vertical component of THz electric field

(E_y), parallel to the surface of the sample, and TM is the horizontal component (E_{xz}). In this configuration, while the incident beam angle was fixed at $\alpha = 45^\circ$, the circular polarization of the pump beam changed from LCP to RCP by rotating the QWP. The measured TE polarization of THz signal as a function of pump polarization angle θ is shown in Figure 3C. Interestingly we observe a change in the sign of the THz field with LCP and RCP, which is discussed further below. The results were found to be well fitted to the following phenomenological equation where the THz electric field is calculated after adapting Equation (1) to the TDS measurement geometry (see [Supplementary material](#) for a full development, as well as results on TM THz polarization).

$$E_{\text{THz,TE}} = (C/2) \sin(4\theta_{\lambda/4}) + E \sin(2\theta_{\lambda/4}) - D, \quad (6)$$

where the $2\theta_{\lambda/4}$ and the $4\theta_{\lambda/4}$ terms correspond to the circular and linear contribution, respectively, to the THz signal. The same measurement was performed with a HWP instead of a QWP to investigate the effect of linear polarization on TM polarized THz emission (Figure 3D). Experimental data showing THz peak-to-peak signal as a function of polarization angle were fitted using the equation:

$$E_{\text{THz,TM}} = A + B \cos(4\theta_{\lambda/2}). \quad (7)$$

In these expressions, D is a constant term and is independent of the nonlinear effects while the coefficients A, B, C and E are related to the contributions of both PDE and PGE. In order to separate these effects, the setup of Figure 3A was modified for measurements in transmission geometry, and where the excitation polarization was set to TM and the THz TM signal change was measured when the sample was rotated (Figure 3B,E). In this geometry, the incidence and the detection direction were aligned ($\alpha = 0^\circ$), and the sample orientation (expressed by the β angle in Figure 3B) changed. The THz emission electric field was calculated to be the following equation to which the experimental data were fit:

$$E_{\text{THz,TM}} = \cos(\beta) \sin(\beta - \alpha) [F + G \sin^2(\beta - \alpha) + H \cos(\beta - \alpha)]. \quad (8)$$

Through the determination of these coefficients from the above fits, we can extract the tensor components of the nonlinear conductivity of Equations (4) and (5), adapting an approach used for graphene.³⁵ Further details of each of the following tensors is given in the [Supplementary](#)

[material](#). Extra tensor terms of PtSe₂ average to zero owing to its polycrystalline nature. Interestingly, the terms considered are adapted for polycrystalline materials meaning that they are robust against rotation. The contribution of the linear PDE: $T_1 = T_{xxxx} + T_{xyyy} = 159 \pm 38$ (m V⁻¹ s⁻¹), $T_2 = T_{xxxx} - T_{xyyy} = 162 \pm 38$ (m V⁻¹ s⁻¹), $T_3 = 2T_{xxzz} = 98 \pm 49$ (m V⁻¹ s⁻¹) and $T_4 = T_{xxzz} = 67 \pm 16$ (m V⁻¹ s⁻¹) and the linear PGE: $\chi_{xxz} + \chi_{zxx} = -104 \pm 41$ (m V⁻¹ s⁻¹), are found to be present and of similar magnitude. The total circular contribution of the PDE and the PGE are smaller than the individual linear parts with $R_2 - R_1 - \sqrt{2}\gamma = R_{xyz} - R_{yxz} - \sqrt{2}\gamma_{xy} = 24 \pm 0.02$. (The individual components of circular PDE and PGE cannot be separated in this analysis). This shows that both PGE and PDE are present in PtSe₂ for the nonlinear THz generation. Importantly the presence of PGE points to the breaking of the PtSe₂ crystal symmetry. Note that as PtSe₂ is polycrystalline, a huge number of grains contribute to the THz emission. However, each grain is expected to be large enough to permit a band structure description, thus individually supporting the existence of a PDE, which is independent of the intrinsic orientation of its unit cell atoms with respect to the substrate. In addition, the interaction with the substrate brings a vertical (z) perturbation to each grain, such that the PGE discussed above holds for each grain taken individually. Together, the nonlinear current contributions from different grains do not cancel out. The microscopic origins and the involved states governing these effects are discussed below.

2.3 | PtSe₂ thickness dependence of THz emission—From monolayer to multilayer

This section presents the strong effect of the semiconductor to semimetal transition on the THz emission that occurs when increasing the number of MLs. The DFT calculated band structure of the PtSe₂ along the high-symmetry lines of the Brillouin Zone (BZ) for the two extremes of a ML and multilayer structures are shown in Figure 4, where spin-orbit coupling is included. This shows that ML PtSe₂ is a semiconductor with an indirect band gap equal to 1.15 eV (see Section 4), with the valence band maximum (VBM) residing at the Γ point and conduction band minimum (CBM) along the $\Gamma - M$ line, which is dominated by d states of Pt and p states of Se (Figure 4). As the thickness increases, the bandgap decreases and the electronic structure evolves into a semimetal for $N > 4$ (Figure 4C and [Supplementary material](#)). (Reported experimental investigations of this transition with number of layers, however, have shown a variety of results spanning from a few monolayers to tens




FIGURE 4 Layer dependent bandstructure of PtSe₂. PtSe₂ band structure including spin-orbit coupling for (A) ML and (B) multilayer cases (10 ML). Energies are referenced to the Fermi level. (C) Indirect bandgap at Γ -M and direct bandgap at K points as a function of number of PtSe₂ layers.




FIGURE 5 Layer controlled THz and optical properties of PtSe₂—From monolayer to bulk. (A) THz peak amplitude as function of thickness of the PtSe₂ samples. The measurements were done in reflection geometry at 45° with TM polarization of the optical pump and THz TM generated pulse. (B) Optical transmission for different PtSe₂ thicknesses extracted over the UV, visible and near infrared spectral regions. (C) THz TE electric field of 5.5 nm (top) and 38.5 nm PtSe₂ (down) under linear (TM), LCP and RCP polarization laser excitation.

of monolayers^{31,36}). This transition originates from the strong electronic interlayer hybridization of the p_z orbital of the Se atom (see Figure S4 in the Supplementary material).^{25,37,38} It should be also noted that the energy gap at the K points decreases with the increasing number of PtSe₂ layers, becoming resonant with 1.5 eV for layers > 10 ML, with important consequences for the THz emission properties (see below).

Considering these large changes in the bandstructure with number of MLs in PtSe₂, we investigated the THz emission properties in the reflection geometry described above for the range of samples with thicknesses down to one ML. Figure 5A represents the measured peak THz electric field amplitude for different PtSe₂ thicknesses showing a non-trivial response. As the number of layers are increased starting from a ML, the peak field appears to increase linearly with a sharp change around 5.5 nm thick PtSe₂ where the THz field reaches a plateau or starts to drop slowly until 16.5 nm and then starts to increase again. Approximately around the thicknesses of 5.5 nm, multilayer PtSe₂ is expected to have become a semimetal and the K valleys become accessible to the optical pump. This behavior suggests that the change in bandstructure has an important impact on the THz generation mechanism. The excitation of the K valleys could also be at the origin of the saturation of the THz field for PtSe₂ films greater than 5.5 nm and discussed further in the microscopic origins section.

To further correlate these observations to changes in bandstructure, the optical transmission of the samples was determined (see Section 4). The results are depicted in Figure 5B where a sharp red shift is observed in the transmission as the thickness is increased beyond 5.5 nm. This sudden modification of the absorption properties reinforces the hypothesis of a transition at around 5.5 nm thick PtSe₂. Similar transmission measurements were performed on PtSe₂ thin films by He et al.³⁹ Small differences between results can be attributed to different substrate used in this study (quartz instead of sapphire), different sample preparation and quality of the surface. A 5.5 nm thickness corresponds to ~10 MLs, and where the K points theoretically begin to be resonant with the 1.5 eV optical excitation. It should be noted that our simulations agree with previous published calculations that predict a faster decrease of the bandgap (Γ and K points) with number of layers than in experiments. Therefore, the K points are expected to be resonant for 1.5 eV for slightly thicker PtSe₂ layers. This difference is possibly a result in the great sensitivity of the electronic bandstructure to the interlayer distance and coupling, the growth method and/or the strong interaction of these materials with the environment as discussed further below.

This bandstructure flexibility of PtSe₂ with layers and its sensitivity to the environment can also be used to control the properties of the THz pulse and in particular through the asymmetry induced CD when optical interband transitions are excited at the K points. Figure 5C shows the generated TE THz pulse from the few layer 5.5 nm (upper) and multilayer 38.5 nm (lower panel) PtSe₂ layers under LCP (red), RCP (blue), and linear (yellow) polarization. We observe completely different behaviors of the thin and thick samples. For the thick sample the THz signal changes sign with the chirality of the circular polarization, indicating a CD and photocurrents that are generated in opposite directions (see Figure 3C and Equation 6). However, for the thin samples, little dependency on the incoming circular polarization is observed. The 3.8 nm sample showed a similar response to the 5.5 nm thick one (see below). When the optical transmission of these samples are compared (Figure 5B), we clearly see that only the thick samples display a permittivity peak at the laser excitation energy (1.5 eV) corresponding to excitation around the K points of the bandstructure. Indeed, the interband transition at the K point is expected at a much higher energy for the few layer samples (at 2.5 eV for the ML case—see Figure 4C). To highlight further the observed trends for different PtSe₂ thicknesses under circularly polarized light, the linear effects were extracted as $(E_{\cup} + E_{\cap})/2$ and the circular effects as $(E_{\cup} - E_{\cap})/2$ ⁴⁰ from the above plots. These are shown in Figure 6 for 3.85, 5.5 and 38.5 nm PtSe₂ for both TM (a, c, and e) and TE (b, d, and f) polarizations. As expected only the THz TE signal displays a circular effect. However, it is only observed for the thickest films (> 5.5 nm), despite the linear effects being similar for TM polarization. This further highlights the strong effect of the PtSe₂ bandstructure on the THz properties. Further, it should be noted that if only PDEs were present, a CD would be expected for thin PtSe₂, showing that PGEs play an important role.

2.4 | Microscopic origins of circular dichroism in thick PtSe₂

We have shown above that the THz electric field in PtSe₂ depends strongly on the number of layers, the polarization and angle of the incident beam, and that both PDE and PGE contribute. We now consider the microscopic origins of polarization-dependent photocurrents and the existence of CD related to excitations with opposite photon helicities, LCP and RCP. In particular, we determine the optical matrix elements (OMEs) between the top valence band (VB1) and the bottom conduction band (CB1) electronic states (see Section 4), which is directly




FIGURE 6 Legend on next page.




FIGURE 7 Layer and photon energy dependent circular dichroism in PtSe₂. Momentum dependence of circular polarization of deposited ML (top panel) and 10 ML (bottom panel) of PtSe₂ between the top of the valence band (VB1) and the bottom of the conduction band (CB1): (A, B, E, F) the k -resolved direct interband optical matrix elements $\mathcal{P}_{cv}^{\pm}(\mathbf{k})$, (C–G) the degree of optical polarization over all energies $\eta(K, \hbar\omega_{cv})$ and (D–H) $\eta(K)$, for a fixed excitation energy ($\hbar\omega_{cv} = 1.5 \pm 0.06$ eV).

proportional to the interband photocurrent that gives rise to the polarization dependent nonlinear THz emission. It should be noted that free standing PtSe₂ possesses centrosymmetric space group $P\bar{3}m1$ for the global structure and polar point groups C_{3v} and D_{3d} for the Se and Pt sites, respectively. This results in a bandstructure that is two-fold degenerate and, for any BZ wavevector, one has two interband transitions for the same photon energy, with same intensity (same absolute value of their OME) but for opposite helicities. This leads to a vanishing CD over the whole BZ as shown in Figure S5 in the Supplementary material. The presence of an external perturbation, breaking the centrosymmetry, lifts the band degeneracy and triggers a CD effect. Here, the sample deposition breaks the vertical centrosymmetry between the bottom (substrate) and upper (vacuum) regions around the ML. To better understand its effect we consider a toy model whereby a small phenomenological shift is imposed on the position of Se atoms of the lower ML plan to mimic a deposition effect (slightly shifting only their site energies leads to qualitatively same effects).

Figure 7 shows the k -resolved direct interband OMEs $\mathcal{P}_{cv}^{\pm}(\mathbf{k}) = 1/\sqrt{2} [P_x^{cv}(\mathbf{k}) \pm iP_y^{cv}(\mathbf{k})]$, and the degree of optical polarization $\eta(\mathbf{k}, \hbar\omega_{cv}) = \frac{|P_{cv}^+(\mathbf{k})|^2 - |P_{cv}^-(\mathbf{k})|^2}{|P_{cv}^+(\mathbf{k})|^2 + |P_{cv}^-(\mathbf{k})|^2}$ owing to the interband excitation over all energies and energy filtered at 1.5 eV in momentum space for deposited ML (top—A, B, C, D) and multilayer (bottom panel—E, F, G, H) PtSe₂ for LCP and RCP light (σ_{\pm}). The energy-filtered CD response around 1.5 eV is obtained by only retaining the contributions of states with $\hbar\omega_{cv}(k) = \hbar\omega \pm 0.06$ eV. The dependence on the transition energy $\hbar\omega_{cv}(\mathbf{k}) = \varepsilon_c(\mathbf{k}) - \varepsilon_v(\mathbf{k})$ is implicit through \mathbf{k} . Figure 7 shows significant CD in the high-symmetry direction $\Gamma - K$ with $\eta = \pm 1$ and negligible spin polarization near the Γ point. This microscopic chiral selection rule arises from the asymmetry of the global crystal space group induced by the substrate and leads to valley-dependent optical selection rules for LCP and RCP excitation in both ML and multilayer PtSe₂, that is, excitation with LCP or RCP polarized light only leads to an absorption at the K

FIGURE 6 Contributions of circular $(E_{\cup} - E_{\cup})/2$ and linear $(E_{\cup} - E_{\cup})/2$ effects to PtSe₂ THz emission. Circular and linear effects shown by blue and red lines, respectively, are obtained from measurements in reflection geometry with LCP and RCP excitations. Figures on the left show these effects for THz TM emission and right figures are for the THz TE emission for (A and B) 3.85 nm PtSe₂ (C and D) 5.5 nm PtSe₂ and (E and F) 38.5 nm PtSe₂ at 1.5 eV photon energy.

or K' point respectively. However, Figure 7D shows that ML PtSe₂ results in a complete lack of CD for energies of 1.5 eV around the K points. (The optical transition in the vicinity of the K (K') point requires an excitation of 2.5 eV. PDE contributions for thin layers from the indirect transitions around Γ point will vanish owing to the scattering assisted nature of the transitions). As the PtSe₂ thickness is increased beyond the semimetal transition, the CD at the K points increases greatly, as the K points become resonant with the optical excitation at 1.5 eV as shown in Figure 7G for the multilayer structure. Although traditional ML TMDs have already been shown to exhibit such strong CD owing to their inherent broken inversion symmetry (giving rise to the field of valleytronics), PtSe₂ is distinct in that the CD is not limited to the ML and its inherent centrosymmetric nature. Here the multilayer semimetal PtSe₂ shows a strong valley selective CD through interactions with the substrate, resulting in the opposite sign in the generated ultrafast THz photocurrents.⁴¹

This microscopic approach can also bring insights into the THz field behavior with PtSe₂ layers (Figure 5A). The deposition perturbation is expected to act on all atoms within a characteristic distance d_c from the substrate (and not only on the low-plan atoms). Thus, increasing the number of layers from 1 ML should lead initially to an increase of the PGE, which would nevertheless saturate for thicknesses bigger than d_c . Second, the wavevector region for resonant excitation at 1.5 eV shifts toward the K and K' points with increasing number of layers (Figure 4), so that the energy detuning with respect to excitation at these high-symmetry points decreases with increasing sample thickness. Both trends collaborate to an initial increase of the PGE with increasing sample thickness, followed by a plateau in the THz-amplitude signal. This is in qualitative agreement with the measures in Figure 5A. Regarding the limit to the number of layers that contribute to the induced asymmetry, this will be related to when the difference in energy between the first and higher energy interband transitions around the K points become smaller than the exciting laser bandwidth (see [Supplementary material](#)). In addition, note that d_c should depend not only on the details of the sample-substrate interactions, but also be affected by the increasing number of free-carriers that appear owing to the increasing semimetallic character of PtSe₂. Indeed, while the direct-to-indirect transition is expected for a few layers, the spectral region where valence and conduction bands overlap slowly increases with increasing number of layers. That means that the density of free carriers in the sample also slowly increases, and as a consequence also the electrostatic screening of the external perturbation. This may explain the slow decrease of the THz amplitude in Figure 5A. The important increase in

Figure 5A for very thick samples may be attributed to an increasing PDE contribution. Indeed, the PDE is expected to occur for any sample thickness and not depend on the presence of a symmetry-breaking perturbation. However, as a second-order effect, its strength is substantially attenuated for thin samples because the photon energy is highly non-resonant with respect to the K and K' transition (that dominates at 1.5 eV in the bulk limit) and becomes more and more resonant as the number of layers increases. In addition, the appearance of an increasing density of free carriers in the sample may also bring a further contribution to the PDE (although non-resonant).

3 | CONCLUSION

To conclude, this work has investigated ultrafast photocurrents and the resulting THz nonlinearities in PtSe₂ and highlighted the valley control of these nonlinearities via the number of atomic layers. Unlike other 2D materials, this work shows the important effect of the thickness of this TMD and how the transition from semiconducting to semimetallic behavior can be used to control the ultrafast photocurrents. Further, we show the potential of valleytronics in thick PtSe₂ layers compared to the ML layer limit for other TMDs. Indeed, by engineering the TMDs thickness such that different K valleys can be excited with a chosen laser excitation and circular polarization, leads to the control of the photocurrent direction and hence the THz emitted phase. These conclusions are supported by extensive bandstructure simulations that shows the presence of circular dichroism for multilayers (> 10 ML) but is absent for few MLs. Vivaly, the role of the environment is shown to be crucial to explain our results, which permits to break the centrosymmetric nature of PtSe₂ to induce a giant second order nonlinearity and circular dichroism. Finally, these effects were shown on large area wafer level samples, potentially easing their use in THz applications compared to exfoliated structures. As well as understanding and bringing insights into layer controlled nonlinearities and transport phenomena in 2D THz materials, these results are promising for PtSe₂ to be potentially exploited in THz valleytronics, spintronics, harmonic generation and optoelectronic applications.

4 | EXPERIMENTAL SECTION/METHODS

4.1 | Materials

Large areas of PtSe₂ samples were fabricated by thermally assisted conversion (TAC) of Pt metal on a quartz

substrate. The thickness of Pt metal varies from 0.1 to 7 nm thick. The resulting thickness of PtSe₂ was measured by atomic force microscopy (AFM, see [Supplementary material](#)) giving a conversion ratio of 5.5 between selenized thin film and the original Pt film. Micro-Raman spectroscopy was performed at room temperature with a Renishaw Invia system equipped with a 532 nm laser (see [Supplementary material](#)).

4.2 | Experimental setup

In order to investigate the ultrafast generated photocurrents and THz nonlinearities in PtSe₂ samples, THz emission time-domain spectroscopy (TDS) was performed. A NIR 100-fs pulsed Ti:Sapphire laser source (Coherent Mira 900) with a central wavelength of $\lambda = 800$ nm (1.5 eV) and repetition rate of 76 MHz was used to characterize coherently the THz emission and photocurrents generated in PtSe₂ samples. The polarization of the pump beam was TM before the use of the waveplates. The output beam was split in two parts. The intense part (pump) excites the sample to generate a THz pulse while the weak part (probe) passes through a delay line. The typical average incident power on sample was 250 mW. The beam diameter at the focus was estimated to be approximately 100 μm resulting in a pump energy of approximately 42 $\mu\text{J cm}^{-2}$. The generated THz pulse is detected using the probe and a 1 mm-thick ZnTe electro-optic crystal. The electro-optic detection part of the setup consists of a waveplate, Wollaston prism and two balanced photodiodes (Figure 2). In reflection configuration, the pump beam was incident at an angle of 45° relative to the normal of the sample and then focused down to ~ 100 μm . A half waveplate (HWP) or a quarter waveplate (QWP) was introduced in the pump beam path to change the polarization of the beam (initially TM polarized) and study their effect on THz emission when both incident and detection angle of the pump beam were fixed. The THz beam after the sample, and its transverse electric (TE) or transverse magnetic (TM) polarization was measured separately. This was done by placing a THz polarizer after the sample and rotating it so that the two modes could be measured independently accordingly. In transmission configuration, the polarization of the pump beam was fixed as linear in TM mode. The angle of the pump beam and the detection angle were changed and the THz emission in TM polarization was studied. Transmission spectra in UV-Vis-NIR region were obtained using an Agilent Cary 7000 double beam spectrophotometer with a clean substrate without PtSe₂ layers placed in the reference beam path.

4.3 | Theoretical calculations

The structural relaxation and electronic properties were performed by Quantum Espresso (QE) code with density functional theory (DFT) based on Generalized Gradient Approximation (GGA) of Perdew–Burke–Ernzerhof (PBE) exchange-correlation functional.^{42–44} Self and non-self-consistent DFT calculations are performed to obtain the Kohn–Sham eigenvalues and eigenfunctions. After obtaining the DFT-KS eigensystem, we use YAMBO code^{45,46} to calculate the direct interband matrix elements $P^{cv}(\mathbf{k}) = \langle \psi_{c\mathbf{k}} | \hat{p} | \psi_{v\mathbf{k}} \rangle$. A plane-wave basis set is employed at a cutoff energy 680 eV, and a total of 200 bands are included to ensure convergence of all computed quantities. After convergence, a phenomenological vertical shift of 0.1 Å downwards is imposed on the low-plan Se atoms and the full band structure and interband optical matrix elements are recalculated. A very dense k-point mesh (15 129 grid points) over the reducible hexagonal Brillouin zone is sampled in the calculations of the k-resolved CD.

ACKNOWLEDGMENTS

The authors acknowledge funding from European Union's Horizon 2020 research and innovation program under grant agreement No. 964735 (FET-OPEN EXTREME-IR). The research leading to these results has received partial funding from the European Union “Horizon 2020” research and innovation program under grant agreement No. 881603 “Graphene Core 3”, the ANR-16-CE24-0023 “TeraMicroCav” and ANR-2018-CE08-018-05 “BIRDS”. Zheng Liu acknowledges the funding support from the National Research Foundation Singapore under CRP program (Grant No. NRF-CRP26-2021-0004). Xuechao Yu is grateful for the technical support from the Nano-X from Suzhou Institute of Nano-Tech and Nano-Bionics, Chinese Academy of Sciences (SINANO). This work was granted access to the HPC resources of MesoPSL financed by the Region Ile de France and the project EquipMeso (reference ANR-10-EQPX-29-01) of the program Investissements d'Avenir supervised by the Agence Nationale pour la Recherche.

CONFLICT OF INTEREST STATEMENT

The authors declare no conflict of interest.

ORCID

Xuechao Yu  <https://orcid.org/0000-0003-1425-1911>

Daniel Vala  <https://orcid.org/0000-0003-2067-7177>

Zheng Liu  <https://orcid.org/0000-0002-8825-7198>

Sukhdeep Dhillon  <https://orcid.org/0000-0002-5487-9570>

REFERENCES

- Manzeli S, Ovchinnikov D, Pasquier D, Yazyev OV, Kis A. 2D transition metal dichalcogenides. *Nat Rev Mater*. 2017;2(8):17033.
- Tan C, Cao X, Wu X-J, et al. Recent advances in ultrathin two-dimensional nanomaterials. *Chem Rev*. 2017;117(9):6225-6331.
- Tan LB, Cotlet O, Bergschneider A, et al. Interacting polaron-polaritons. *Phys Rev X*. 2020;10(2):021011.
- Xia F, Wang H, Xiao D, Dubey M, Ramasubramaniam A. Two-dimensional material nanophotonics. *Nat Photonics*. 2014;8(12):899-907.
- Gonzalez Marin JF, Unuchek D, Watanabe K, Taniguchi T, Kis A. MoS₂ photodetectors integrated with photonic circuits. *npj 2D Mater Appl*. 2019;3(1):14.
- Lopez-Sanchez O, Lembke D, Kayci M, Radenovic A, Kis A. Ultrasensitive photodetectors based on monolayer MoS₂. *Nat Nanotechnol*. 2013;8(7):497-501.
- Liu Y, Gao Y, Zhang S, He J, Yu J, Liu Z. Valleytronics in transition metal dichalcogenides materials. *Nano Res*. 2019;12(11):2695-2711.
- Wen X, Gong Z, Li D. Nonlinear optics of two-dimensional transition metal dichalcogenides. *InfoMat*. 2019;1(3):317-337.
- Li Y, Rao Y, Mak KF, et al. Probing symmetry properties of few-layer MoS₂ and h-BN by optical second-harmonic generation. *Nano Lett*. 2013;13(7):3329-3333.
- Kumar N, Najmaei S, Cui Q, et al. Second harmonic microscopy of monolayer MoS₂. *Phys Rev B*. 2013;87(16):161403.
- Kim M, Ducournau G, Skrzypczak S, et al. Monolayer molybdenum disulfide switches for 6G communication systems. *Nat Electron*. 2022;5(6):367-373.
- Kim M, Ge R, Wu X, et al. Zero-static power radio-frequency switches based on MoS₂ atomistors. *Nat Commun*. 2018;9(1):2524.
- Tan T, Jiang X, Wang C, Yao B, Zhang H. 2D material optoelectronics for information functional device applications: status and challenges. *Adv Sci*. 2020;7(11):2000058.
- Schleicher JM, Harrel SM, Schmuttenmaer CA. Effect of spin-polarized electrons on terahertz emission from photoexcited GaAs. *J Appl Phys*. 2009;105(11):113116.
- Fan Z, Xu M, Huang Y, et al. Terahertz surface emission from MoSe₂ at the monolayer limit. *ACS Appl Mater Interfaces*. 2020;12(42):48161-48169.
- Yagodkin D, Nádvořník L, Gueckstock O, Gahl C, Kampfrath T, Bolotin KI. Ultrafast photocurrents in MoSe₂ probed by terahertz spectroscopy. *2D Mater*. 2021;8(2):025012.
- Si K, Huang Y, Zhao Q, et al. Terahertz surface emission from layered semiconductor WSe₂. *Appl Surf Sci*. 2018;448(46):416-423.
- Gao Y, Kaushik S, Philip EJ, et al. Chiral terahertz wave emission from the Weyl semimetal TaAs. *Nat Commun*. 2020;11(1):720.
- Braun L, Mussler G, Hruban A, et al. Ultrafast photocurrents at the surface of the three-dimensional topological insulator Bi₂Se₃. *Nat Commun*. 2016;7(1):13259.
- Maysonave J, Huppert S, Wang F, et al. Terahertz generation by dynamical photon drag effect in graphene excited by femtosecond optical pulses. *Nano Lett*. 2014;14(10):5797-5802.
- Zhang J, Zhang T, Yan L, et al. Colossal room-temperature terahertz topological response in type-II weyl semimetal NbIrTe₄. *Adv Mater*. 2022;34(42):2204621.
- Qiu Q, Huang Z. Photodetectors of 2D materials from ultraviolet to terahertz waves. *Adv Mater*. 2021;33(15):2008126.
- Hu Z, Zhang L, Chakraborty A, et al. Terahertz nonlinear hall rectifiers Based on Spin-Polarized Topological Electronic States in 1T-CoTe₂. *Adv Mater*. 2023;2209557.
- Wang Y, Li L, Yao W, et al. Monolayer PtSe₂, a new semiconducting transition-metal-dichalcogenide, epitaxially grown by direct selenization of Pt. *Nano Lett*. 2015;15(6):4013-4018.
- Zhao Y, Qiao J, Yu Z, et al. High-electron-mobility and air-stable 2D layered PtSe₂ FETs. *Adv Mater*. 2017;29(5):1604230.
- Ansari L, Monaghan S, McEvoy N, et al. Quantum confinement-induced semimetal-to-semiconductor evolution in large-area ultra-thin PtSe₂ films grown at 400 °C. *npj 2D Mater Appl*. 2019;3(1):33.
- Sefidmooye Azar N, Bullock J, Shrestha VR, et al. Long-wave infrared photodetectors based on 2D platinum diselenide atop optical cavity substrates. *ACS Nano*. 2021;15(4):6573-6581.
- Yang Z, Han L, Zhang J, et al. Passively Q-switched laser using PtSe₂ as saturable absorber at 1.3 μm. *Infrared Phys Technol*. 2020;104:103155.
- Zhang L, Zhang D, Hu F, et al. Generation and control of ultrafast circular photon drag current in multilayer PtSe₂ revealed via terahertz emission. *Adv Opt Mater*. 2023;11(2):2201881.
- Cheng L, Xiong Y, Kang L, et al. Giant photon momentum locked THz emission in a centrosymmetric dirac semimetal. *Sci Adv*. 2023;9(1):eadd7856.
- Wang L, Zhang S, McEvoy N, et al. Nonlinear optical signatures of the transition from semiconductor to semimetal in PtSe₂. *Laser Photonics Rev*. 2019;13(8):1900052.
- Gatensby R, Hallam T, Lee K, McEvoy N, Duesberg GS. Investigations of vapour-phase deposited transition metal dichalcogenide films for future electronic applications. *Solid State Electron*. 2016;125:39-51.
- Yim C, Lee K, McEvoy N, et al. High-performance hybrid electronic devices from layered PtSe₂ films grown at low temperature. *ACS Nano*. 2016;10(10):9550-9558.
- Karch J, Olbrich P, Schmalzbauer M, et al. *arXiv preprint arXiv:1002.1047*. 2010.
- Jiang C, Shalygin VA, Panevin VY, et al. Helicity-dependent photocurrents in graphene layers excited by midinfrared radiation of a CO₂ laser. *Phys Rev B*. 2011;84(12):125429.
- Xie J, Zhang D, Yan X-Q, et al. Optical properties of chemical vapor deposition-grown PtSe₂ characterized by spectroscopic ellipsometry. *2D Mater*. 2019;6(3):035011.
- Zhang L, Yang T, Sahdan MF, et al. Precise layer-dependent electronic structure of MBE-grown PtSe₂. *Adv Electron Mater*. 2021;7(11):2100559.
- Zhao Y, Qiao J, Yu P, et al. Extraordinarily strong interlayer interaction in 2D layered PtSe₂. *Adv Mater*. 2016;28(12):2399-2407.
- He J, Jiang W, Zhu X, et al. Optical properties of thickness-controlled PtSe₂ thin films studied via spectroscopic ellipsometry. *Phys Chem Chem Phys*. 2020;22(45):26383-26389.
- Ni Z, Wang K, Zhang Y, et al. Giant topological longitudinal circular photo-galvanic effect in the chiral multifold semimetal CoSi. *Nat Commun*. 2021;12(1):154.
- Xiao D, Liu G-B, Feng W, Xu X, Yao W. Coupled spin and valley physics in monolayers of MoS₂ and other group-VI dichalcogenides. *Phys Rev Lett*. 2012;108(19):196802.

42. Giannozzi P, Baroni S, Bonini N, et al. QUANTUM ESPRESSO: a modular and open-source software project for quantum simulations of materials. *J Phys Condens Matter*. 2009;21(39):395502.
43. Giannozzi P, Andreussi O, Brumme T, et al. Advanced capabilities for materials modelling with quantum ESPRESSO. *J Phys Condens Matter*. 2017;29(46):465901.
44. Perdew JP, Burke K, Ernzerhof M. Generalized gradient approximation made simple. *Phys Rev Lett*. 1996;77(18):3865-3868.
45. Sangalli D, Ferretti A, Miranda H, et al. Many-body perturbation theory calculations using the yambo code. *J Phys Condens Matter*. 2019;31(32):325902.
46. Marini A, Hogan C, Grüning M, Varsano D. Yambo: an ab initio tool for excited state calculations. *Comput Phys Commun*. 2009;180(8):1392-1403.

SUPPORTING INFORMATION

Additional supporting information can be found online in the Supporting Information section at the end of this article.

How to cite this article: Hemmat M, Ayari S, Mičica M, et al. Layer-controlled nonlinear terahertz valleytronics in two-dimensional semimetal and semiconductor PtSe₂. *InfoMat*. 2023;5(11):e12468. doi:[10.1002/inf2.12468](https://doi.org/10.1002/inf2.12468)