



HAL
open science

Advances in quantitative electron probe microanalysis of lithium in different materials

P Schweizer, Emmanuelle Brackx, Philippe Jonnard

► **To cite this version:**

P Schweizer, Emmanuelle Brackx, Philippe Jonnard. Advances in quantitative electron probe microanalysis of lithium in different materials. LCPMR 2023 - International Workshop on the Characterisation and Quantification of Lithium. ” from the Micro- to the Nano-Scale, from Mining to Energy”, Karim Zaghbi; Philippe Jonnard; Raynald Gauvin, Jun 2023, Paris, France. 10.1002/xrs.3329 . hal-04219921

HAL Id: hal-04219921

<https://hal.science/hal-04219921>

Submitted on 27 Sep 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

ADVANCES IN QUANTITATIVE ELECTRON PROBE MICROANALYSIS OF LITHIUM IN DIFFERENT MATERIALS

P. Schweizer¹, E. Brackx¹ and P. Jonnard²

¹ CEA, DES, ISEC, DMRC, Univ Montpellier, Marcoule, France

² Sorbonne Université, Faculté des Sciences et Ingénierie, UMR CNRS, Laboratoire de Chimie Physique - Matière et Rayonnement, 4 Place Jussieu, F-75252 Paris Cedex 05, France

pia.schweizer@cea.fr

Electron probe microanalysis (EPMA) is a reliable and widely used technique to do non-destructive, accurate material characterisation for scientific and industrial applications. Nevertheless, despite of the great interest in lithium (Li) and the urgent need to do accurate non-destructive analysis at a micron scale, quantification of Li using EPMA has not been performed successfully yet. Recently developed periodic multilayers allow spectroscopy in the energy range around the characteristic Li K emission ~50 eV [1] but the detection and quantification of Li by a microprobe equipped with a bent crystal spectrometer and standard commercialised multilayers without diffraction gratings still is challenging.

The difficulties of Li detection are caused by different factors: the fluorescence yield of Li is extremely low, few characteristic photons are produced by the decays of the Li 1s core hole, favoring the emission of Auger electrons. Because of their low energy, the photons are strongly absorbed before even leaving the sample and its eventual coating. The signal therefore is principally coming from a thin surface layer that can be subject to contamination and that may be sensitive to electron bombardment. Further photon absorption by the microprobe components, especially by separation windows, will additionally decrease the measured intensity. As the Li K emission (2p – 1s transition) involves valence electrons, the shape of the Li emission band is highly dependent on the density of states (DOS) in the valence band and so highly dependent on the chemical state of the lithium atoms. Chemical shifts of some eV and strong peak shape alterations can occur and should be expected for EPMA of light elements [2,3], complicating quantitative analysis.

This work shows some promising results of quantitative EPMA of Li in different materials including battery compounds and metal alloys with Li concentrations down to 2 %. This was made possible after the integration of a new detection system as well as work on the quantification procedure using real standards and correction programs suited for low voltage EPMA.

Even if additional investigation is needed, the advances are of great interest to researchers working on lithium characterisation. We show that EPMA is a powerful tool to do quantitative analysis of Li even if it is contained in heavy matrices with elements showing characteristic emission bands in the same spectral range as Li. This novel Li quantification method is more accessible than other techniques using synchrotron radiation and less expensive than detection using a SEM or an electron microprobe equipped with multilayer gratings.

[1] Polkonikov, V., Chkhalo, N., Pleshkov, R., Giglia, A., Rividi, N., Brackx, E., Le Guen, K., Ismail, I., Jonnard, P., *Appl. Sci.* 2021, *11*, 6385.

[2] Schweizer, P., Brackx, E., Jonnard, P., *X-Ray Spectrom.* 2022, *51* (4), 403.

[3] Hassebi, K., Le Guen, K., Rividi, N., Verlaquet, A., Jonnard, P., X-ray spectrom. (<http://doi.org/10.1002/xrs.3329>) in press.