

Effective elastic properties of 3D printed specimens, in a context of property optimization

Ajmi Makki, Bernard Simon, Souissi Slim, Elloumi Ahmed, Maréchal Pierre

► To cite this version:

Ajmi Makki, Bernard Simon, Souissi Slim, Elloumi Ahmed, Maréchal Pierre. Effective elastic properties of 3D printed specimens, in a context of property optimization. The 4th Edition of EUROMAGH BIOCOMPOSITES Conference (EUROMAGH 2023), Apr 2023, Marrakech, Morocco. hal-04220274

HAL Id: hal-04220274 https://hal.science/hal-04220274

Submitted on 29 Sep 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

The 4th Edition of EUROMAGH BIOCOMPOSITES Conference (EUROMAGH 2023) April 26-27, 2023, University Cadi Ayyad, Marrakech, Morocco

Effective elastic properties of 3D printed specimens, in a context of property optimization

Makki Ajmi¹, Simon Bernard², Slim Souissi¹, Ahmed Elloumi¹, Pierre Maréchal²*

Laboratoire des Systèmes Électromécaniques (LASEM),
National Engineering School of Sfax, University of Sfax, 3038 Sfax, Tunisia
Laboratoire Ondes et Milieux Complexes (LOMC), UMR 6294 CNRS,
Université Le Havre Normandie, 76600 Le Havre, France
*Correspondence to: pierre.marechal@univ-lehavre.fr

Keywords: Additive manufacturing; fused filament fabrication; PLA; effective properties; tensile tests.

1. INTRODUCTION

Additive manufacturing by fused filament deposition (FFF) of polymer filament has been widely spread and popularized during the 2010 years. Since then, a wide variety of printers, polymer materials and printing parameters have been investigated [1; 2]. In this context, the specimen design was carried out *via* FreeCAD (<u>https://www.freecadweb.org/</u>) then converted for the FFF printing *via* Prusa Slicer (<u>https://github.com/prusa3d/PrusaSlicer</u>). The data processing of the tensile tests was performed *via* Scilab (<u>https://www.scilab.org/</u>). Thus, a Prusa 3D printer was selected and implemented for the fabrication of standardized PLA specimens [3; 4]. A parametric study on the type of filling allowed to illustrate the variability of the effective mechanical properties obtained *in fine*, through tensile tests measurements.

2. MATERIALS AND METHODS

Although widely used, the optimal use of 3D printers often results from an empirical experience. The work presented here stands in the framework of the tensile characterization of polymer following the ISO 527-1 [3] standard with specimens according to the ISO 527-2 standard [4]. The effective mechanical properties of FFF printed polymers strongly depends on the fabrication process. Each FFF printing parameter has an influence on the actual properties obtained *in fine* [1; 2]. A set of tensile specimens was manufactured according to ISO 527-2 [4], with constant parameters (straight filling pattern, layer thickness of 0.3 mm, extrusion at 215°C, platen at 60°C, printing at 50 mm/s), while two printing parameters are varied, combining the filling rate $\{60\%; 100\%\}$ and the printing angles $\{+45^{\circ}/-45^{\circ}; +90^{\circ}/0^{\circ}\}$. Several PLA samples of each configuration have been fabricated and characterized by tensile strength tests according to the ISO 527-1 standard [3].

3. MAIN RESULTS

The experimental study lead to compare the effective elastic properties obtained by averaging the results of the two nearest measurements. Thus, the experimental values of the elastic properties are evaluated according to the ISO 527-1 standard, with a quasi-static tensile test in the strain range $\varepsilon \in [0.05\%; 0.25\%]$ [5]. The four evaluated parameters are the Young's modulus E (GPa), Poisson's ratio v, maximum stress R_m (MPa) and porosity ratio p (%) and are denoted as $P_{f\alpha} = \{E, v, R_m, p\}$, where the indexes $\{f, \alpha\} = \{1, 2\}$ correspond to each value of the two studied parameters, *i.e.* the filling rate $f = \{60\%; 100\%\}$ and printing angle $\alpha = \{+45^{\circ}/-45^{\circ}; +90^{\circ}/0^{\circ}\}$, respectively. As a result, four sets of values are obtained: $P_{11} = \{1.50 \text{ GPa}, 0.30, 34.0 \text{ MPa}, 14.3\%\}$, $P_{12} = \{1.55 \text{ GPa}, 0.24, 36.5 \text{ MPa}, 14.0\%\}$, $P_{21} = \{2.05 \text{ GPa}, 0.32, 45.0 \text{ MPa}, 0.75\%\}$ and $P_{22} = \{1.90 \text{ GPa}, 0.30, 44.6 \text{ MPa}, 3.30\%\}$, constituting reference results to be discussed in terms of specific stiffness E/ρ and specific tensile strength R_m/ρ for a future parametric optimization.

4. CONCLUSION

As a conclusion, the printing parameters such as the filling rate and the printing angles have been investigated as a way to mitigate the effective elastic properties of the samples, and as an optimization parameter of the raw material printing in view of a targeted application.

5. MAIN REFERENCES

[1] Popescu, D., Zapciu, A., Amza, C., Baciu, F. and Marinescu, R.: "FDM process parameters influence over the mechanical properties of polymer specimens: A review", *Polymer Testing*, vol.69, p.157-166, 2018, (doi.org/10.1016/j.polymertesting.2018.05.020).

[2] Verbeeten, W.M., Lorenzo-Bañuelos, M. and Arribas-Subiñas, P.J.: "Anisotropic ratedependent mechanical behavior of Poly(Lactic Acid) processed by Material Extrusion Additive Manufacturing", *Additive Manufacturing*, vol.31, p.100968, 2020, (doi.org/10.1016/j.addma.2019.100968).

[3] 527-1, ISO: "DIN EN ISO 527-1, Plastics-Determination of Tensile Properties, Part 1: General Principles", 2012, .

[4] 527-2, ISO: "DIN EN ISO 527-2, Plastics-Determination of Tensile Properties, Part 2: Test conditions for moulding and extrusion plastics", 2012, .

[5] Bouhamed, N., Souissi, S., Maréchal, P., Amar, M.B., LENOIR, O., Léger, R. and Bergeret, A.: "Ultrasound evaluation of the mechanical properties as an investigation tool for the wood-polymer composites including olive wood flour", *Mechanics of Materials*, vol.148, p.103445, 2020, (doi.org/10.1016/j.mechmat.2020.103445).