



Native defects association enabled room-temperature p-type conductivity in β -Ga₂O₃

Zeyu Chi, Corinne Sartel, Yunlin Zheng, Sushrut Modak, Leonid Chernyak, Christian Schaefer, Jessica Padilla, Jose Santiso, Arie Ruzin, Anne-Marie Gonçalves, et al.

► To cite this version:

Zeyu Chi, Corinne Sartel, Yunlin Zheng, Sushrut Modak, Leonid Chernyak, et al.. Native defects association enabled room-temperature p-type conductivity in β -Ga₂O₃. Journal of Alloys and Compounds, 2023, pp.172454. 10.1016/j.jallcom.2023.172454 . hal-04236493

HAL Id: hal-04236493

<https://hal.science/hal-04236493>

Submitted on 10 Oct 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Native defects association enabled room-temperature *p*-type conductivity in β -Ga₂O₃

Zeyu Chi¹, Corinne Sartel¹, Yunlin Zheng², Sushrut Modak³, Leonid Chernyak³,
Christian M Schaefer⁷, Jessica Padilla⁷, Jose Santiso⁷, Arie Ruzin⁴,
Anne-Marie Gonçalves⁵, Jurgen von Bardeleben², Gérard Guillot⁶,
Yves Dumont¹, Amador Pérez-Tomás⁷, Ekaterine Chikoidze*¹

¹Groupe d'Etude de la Matière Condensée (GEMaC), Université Paris-Saclay, UVSQ – CNRS, 45
Av. des Etats-Unis, 78035 Versailles Cedex, France

² Institut des Nano Sciences de Paris (INSP), CNRS UMR7588, Sorbonne Université, 4 place
Jussieu, 75252 Paris, France

³Department of Physics, University of Central Florida, Orlando, FL 32816, USA

⁴Department of Physical Electronics, School of Electrical Engineering, Tel Aviv University, Tel
Aviv 69978, Israel

⁵Institut Lavoisier de Versailles (ILV), Université Paris-Saclay, UVSQ – CNRS, 45 Av. des Etats-
Unis, 78035 Versailles Cedex, France

⁶Univ. Lyon, CNRS, ECL,UCBL,INSA Lyon, CPE, Institut des Nanotechnologies de Lyon, 69621
Villeurbanne Cedex, France

⁷Catalan Institute of Nanoscience and Nanotechnology (ICN2), CSIC and the Barcelona Institute of
Science and Technology, Barcelona, Spain

*ekaterine.chikoidze@uvsq.fr

Abstract:

The room temperature hole conductivity of the ultra-wide bandgap semiconductor β -Ga₂O₃ is a pre-requisite for developing the next-generation electronic and optoelectronic devices based on this oxide. In this work, high-quality *p*-type β -Ga₂O₃ thin films grown on *r*-plane sapphire substrate by metalorganic chemical vapor deposition (MOCVD) exhibit $\rho = 5 \times 10^4 \text{ } \Omega \cdot \text{cm}$ resistivity at room temperature. A low activation energy of conductivity as $E_{a2} = 170 \pm 2 \text{ meV}$ was determined, associated to the $V_O^{++} - V_{Ga}^-$ native acceptor defect complex. Further, taking advantage of cation (Zn) doping, the conductivity of Ga₂O₃:Zn film was remarkably increased by three orders of magnitude, showing a long-time stable room-temperature hole conductivity with the conductivity activation energy of around 86 meV. $V_O^{++} - Zn_{Ga}^-$ defect complex has been proposed as a corresponding shallow acceptor.

Key workds: ultra-wide band gap semiconductor, β -Ga₂O₃, point defect, electronic properties

1. Introduction

Being the mainstream of the ultra-wide bandgap (UWBG) semiconductors, beta-gallium oxide (β -Ga₂O₃) has a bandgap (E_g) up to 5.0 eV, a room-temperature electron mobility (μ) of higher than 200 cm²/(V·s) [1,2], and a theoretically estimated critical breakdown field (E_{CR}) of 8 MV/cm [3], leading to high Baliga's figures of merit (BFOMs) [4]. Such properties make β -Ga₂O₃ attracts much scientific and technological attention in optoelectronics [5,6], solar-blind photodetectors [7,8], and power electronics (field effect transistors [3,9], Schottky barrier diodes [10,11]). However, to realize the full functionality of any emerging electronic technology based on UWBG semiconductors, both n - and p -type conductivity (i.e., bipolarity) should be attained. The room-temperature electron concentration of β -Ga₂O₃ can reach $10^{19} - 10^{20}$ cm⁻³ by Si, Sn, Ge, and Nb doping [12–15]. While β -Ga₂O₃ displays significant resistance to the formation of shallow acceptor levels by doping [16,17]. In fact, the potential for achieving p -type or n -type conductivity in wide band gap materials through doping depends on the characteristics of the native point defects, such as their formation enthalpies and position relative to the valence and conduction bands. Therefore, it is critical to identify, experimentally investigate, and control the concentration of these native point defects in β -Ga₂O₃ through growth parameters to determine the feasibility of achieving room temperature hole conductivity.

Theoretically, by the thermodynamic analysis, native point defects have been investigated revealing that gallium oxide has a significant advantage due to the high formation energy of donor vacancies. It makes the compensation mechanism by point defects less favorable, and thus creates favorable conditions for the realization of native hole conductivity in β -Ga₂O₃ [18]. The origin of hole conductivity was attributed to single acceptor V_{Ga} ionization energy (E_i) determined to be about 1.2 eV from the Hall effect measurements of the highly compensated β -Ga₂O₃/c-Al₂O₃ thin films grown by metal organic chemical vapour deposition (MOCVD) technique [19]. Moreover, native

point defects have the ability to form complex-like defects through their associations. Indeed, the study of native vacancy pairs in β -Ga₂O₃ has a long history. According to Vasiltsiv *et al.* [20], the vacancies pair $V_{Ga}-V_O$ are charge-active centres that, together with single Ga vacancies, can act as acceptors. Binet and Gourier [21] claimed to have this native defect complex even in unintentionally doped *n*-type Ga₂O₃ bulk. Very recently, this defect complex was predicted to have comparable or even lower formation energy than single vacancies in Oxygen-rich conditions [22]. Furthermore, abundant gallium and oxygen vacancy complexes were identified by positron-electron annihilation signals irrespective of conductivity of bulk Ga₂O₃ crystals [23]. Very recently, Zhu *et al.* [24] proposed that the native $V_{Ga}-V_O$ divacancy defects level can be at 4.42 eV from conduction band by photoluminescence (PL), confirming the results of Binet and Gourier [21]. Recently, *p*-type conductivity with a hole concentration of $\sim 10^{17} \text{ cm}^{-3}$ in N doped β -Ga₂O₃ thin films has been demonstrated [25,26], later, the conductivity was attributed to the shallow acceptor $N_O - V_{Ga}$ complex defect by ab-initio calculations [27].

These complexes can play very important role in optical and electrical properties of the material. The probability of the creation of native defect associates and their impact on the electrical and optical properties of II-VI compounds has also been extensively studied [28]. Several reports showed the *p*-type conductivity in ZnS can be significantly enhanced by shallow complex-like defects $V_{Zn}^- - V_S^{++}$ [29,30], or $Ag_{Zn}^- - V_S^{++}$ with Ag doping [28]. Additionally, Reynolds *et al.* [32] introduced shallow acceptor complex $V_{Zn}-N_O-H_i$ with an ionization energy of 130 meV into ZnO employing a set of growth and annealing procedures.

Can native defects in Ga₂O₃ exhibit similar behavior? Interestingly, it has been observed that post-annealing in an oxygen atmosphere can result in room-temperature hole conductivity ($\rho = 1 \times 10^4 \Omega \cdot \text{cm}$) in Ga₂O₃/*c*-Al₂O₃, thanks to the appearance of a shallow acceptor level with 0.17 eV activation energy. This center was attributed to $V_O^{++} - V_{Ga}^-$ defect complex [19]. Indeed, in a close stoichiometry state, single oxygen vacancy tends to be in the double-charged (V_O^{++}) state rather than in the a single-charge (V_O^+) state [33]. Point defects tend to associate with one another driven by

Coulomb interaction, since the system always tries to reach the state of minimum free energy. Later, the same shallow defect complex with Cathodoluminescence (CL) activation energies 88 – 101 meV, which was corroborated by electron-beam-induced current (EBIC) measurements in as grown p -type $\text{Ga}_2\text{O}_3/c\text{-Al}_2\text{O}_3$ thin films [31].

The motivation of this work was the elaboration of $\beta\text{-Ga}_2\text{O}_3$ thin films by MOCVD with important number of shallow acceptor complex defect, yielding room-temperature hole conductivity.

2. Ga_2O_3 thin films

To achieve a high number of native defects in $\beta\text{-Ga}_2\text{O}_3$ thin films, it is crucial to obtain a low compensation regime, which means minimizing the number of native donor defects. We have grown $\beta\text{-Ga}_2\text{O}_3$ by MOCVD technique on r -oriented sapphire substrate. It is known that $\beta\text{-Ga}_2\text{O}_3$ films grown on r -sapphire differs significantly from those grown on c -oriented sapphire substrates [35–40]. Additionnaly, Nakagomi *et al.* [41–43] reported distinct structural properties, revealed by X-ray diffraction (XRD) and transmission electron microscopy (TEM) measurements, which were attributed to the oxygen atomic arrangements on the surface of substrates. Indeed, when a $\beta\text{-Ga}_2\text{O}_3$ crystal is constructed on a sapphire substrate, gallium atoms form chemical bonds with the oxygen atoms on the sapphire surface. In the case of growth on r -oriented sapphire, the arrangement of three oxygen atoms and one aluminum atom in the (113) n -plane corresponds to the arrangement of three oxygen atoms and one gallium atom on the (-201) plane of $\beta\text{-Ga}_2\text{O}_3$ [41]. Such a well-fitted atomic arrangement is not favorable to oxygen vacancy (donor defect) creation, we can thus assume that it may be favorable for low compensation in p -type $\beta\text{-Ga}_2\text{O}_3$.

In our study, we have performed a detailed crystallographic study of $\beta\text{-Ga}_2\text{O}_3/r\text{-Al}_2\text{O}_3$ films. It was recently reported that no peak of the film is observable in $\theta/2\theta$ scan and that ($\bar{2}01$) planes are tilted about 30° from the normal of the substrate [37]. Nevertheless, the authors hypothesized that out-of-plane (OP) peaks should be too weak to measure and concluded that the plane of the films

should be (100) and/or (001). Thus, there are ambiguities about β -Ga₂O₃ films on *r*-sapphire. We propose here to deepen the structural analysis.

We got the same results in the $\theta/2\theta$ scan for undoped β -Ga₂O₃ films grown on *r*-sapphire as in the work cited [37], *i.e.* no peak except 012 of the substrate and its harmonics. In β -Ga₂O₃ $\bar{2}01$ pole figure (PF) (**Figure 1 (a)**), two spots of $\bar{2}01$, labelled *A* and *A'*, were indeed found out of the normal of the film by $\chi = \pm 30.2^\circ$ toward Al₂O₃ *a*-axis azimuth. Orientations *A* and *A'* are equivalent by mirror symmetry of the substrate. Two other spots labelled *B* and *B'* were found at the high tilt angle of $\chi = 80.8^\circ$. Orientations *A* and *B* are not equivalent with respect to the substrate. The intensity of spot *B* is almost two orders of magnitude lower than that of spot *A*, indicating that the proportion of orientations *B* and *B'* is less than 5% of the film. In β -Ga₂O₃ 001 PF (**Figure 1 (b)**), four spots were also observed. It can be noticed that no spot is located at the centre of the PF, *i.e.* (001) is not the film plane. Knowing that the angle between the spots $\bar{2}01$ and 001 should be about 49.9° , each spot of 001 can be coupled to a spot of $\bar{2}01$ and therefore labelled as orientations *A*, *A'*, *B* or *B'*.

The angular positions of the spots $\bar{2}01$ and 001 fully fix orientations *A* and *B* of the film and allow to deduce all the other orientations. We still cross-checked and measured the PFs of 111 and 400 reflections. For the 400 PF with the diffraction angle of 30.06° , the reflections $\bar{4}01$ and 110 with closing diffraction angles of respectively 30.49° and 30.32° were also observed. Reflections collected and related respectively to orientation *A* and to orientation *B* are summarized in **Figure 2**. Orientation *A* can be reproduced from the epitaxy of β -Ga₂O₃($\bar{2}01$) on *c*-sapphire (sample C) which was grown simultaneously with the one on *c*-sapphire (sample R), by a rotation of 152° around the normal to the substrate and then a tilt of -30.2° toward the substrate *a*-axis. The angular positions of the spots measured agree with those calculated with the bulk lattice parameters, indicating that the film is unstrained within the measurement accuracy.

For orientation *B*, some spots such as 400 and 110 are common to orientation *A* but should be labelled self-consistently with reversed indices. It follows that this is the case for all *hk0* reflections.

Inverting $hk0$ reflections between orientations A and B corresponds to a rotation of 180° around the c -axis of the unit-cell, the c -axis being unchanged and common to the two orientations. In other terms, orientation A and B can be understood as twins.

Strain in the film is detailed by XRD and grazing incidence XRD (GIXRD) scans (**Figure 3**). As there is no strictly OP reflection for the present case, we considered $\bar{4}01$ reflection of orientation A (denoted $\bar{4}01_A$) and 401 reflection of orientation B (denoted 401_B) which are off the sample normal by about 14° (**Figure 2**). These reflections provide then almost OP strain of orientations A and B . Their measurements were done in asymmetric geometry by $\omega/2\theta$ and ω scans (**Figure 3 (a), (c)**). Similarly, $3\bar{1}4_A$ reflection is off the plane by only 0.8° and $5\bar{1}4_B$ reflection by 0.5° . The reflections provide information on in-plane (IP) strain and were measured by IP scans (**Figure 3 (b), (d)**). The measured Bragg angles correspond to those expected with an uncertainty of $0.1 - 0.2\%$, in agreement with the PF result that strain is not sizable within the measurement accuracy. The absence of noticeable strain also results in a small misorientation of the planes (Insets in **Figure 3**).

In the case of growth on r -sapphire substrate, the plane of the Ga_2O_3 films does not correspond to any basic lattice plane. Two main equivalent orientations have $(\bar{2}01)$ planes tilted respectively $\pm 30.2^\circ$ toward the substrate a -axis. Two minor equivalent orientations constitute less than 5% of the film and can be seen as twins of the main orientations. No strain was measured in the film. The OP and IP misorientation of the planes is small and within $\pm 0.2^\circ$.

It remains that the epitaxy of the film on r -sapphire is intriguing and leaves questions that should be explored further. If the plane of the film does not correspond to any basic plane, what is the exact film/substrate interface to achieve epitaxy? One possibility would be that lattice matching would occur from facets that could be present on the surface of the substrate. We found by X-ray reflectivity a very high surface roughness (> 5 nm) in the sample. It indicates that the growth does not occur layer-by-layer but rather in a 3D fashion. The growth mode and the presence of minor orientations could also promote strain relaxation in films on r -sapphire.




Figure 1. Pole figures in sample R. (a) $\beta\text{-Ga}_2\text{O}_3 \bar{2}01$ pole figure where the azimuths of Al_2O_3 a-axis and $[12\bar{1}]$ directions are indicated by magenta dashed lines. A and A', as well as B and B', mark a pair of equivalent spots by mirror symmetry of the substrate. (b) $\beta\text{-Ga}_2\text{O}_3 001$ pole figure.




Figure 2. Orientation projections of reflections measured in sample R and related to orientation A (a) and to orientation B (b). The reflections collected in PF measurements are indicated by red dots. The reflections used in IP and asymmetric OP scans are symbolized by blue dots. The orientations of the unit-cells deduced, namely that of the invariant c-axis ($[001]$), are indicated by black dots. The red dashed circles outline the sets of $hk0$ and $h0l$ reflections.




Figure 3. XRD and GIXRD scans in sample R. Reflections are subscripted by A and B for orientations A and B, respectively. Orientation A is characterized by asymmetric OP $\bar{4}01_A$ reflection (a) and quasi-IP $3\bar{1}4_A$ reflection (b). Orientation B is characterized by asymmetric OP 401_B reflection (c) and quasi-IP $5\bar{1}4_B$ reflection (d). OP rocking curves (ω -scans) and corresponding IP azimuthal curves (ϕ -scans) are in the insets. $2\theta_{IP}$ is the IP diffraction angle measuring the IP component of the diffracting vector.

Figure 4 (a) shows the top view scanning electron microscopy (SEM) image of the $\text{Ga}_2\text{O}_3/r\text{-Al}_2\text{O}_3$ sample, it exhibits a coarser morphology with grains look like needles (ridges). The thickness was determined at 453 nm (**Figure 4 (b)**). **Figure 4 (c)** represents the Raman scattering spectra of the r -plane sapphire substrate and the $\text{Ga}_2\text{O}_3/r\text{-Al}_2\text{O}_3$ sample. Observed spectral features of Ga_2O_3 can be unambiguously attributed to the β -phase phonon lines [44–46]. In addition to XRD results, it evidences that the sample has the single β -phase. The spectrum is comparable with our previously reported Raman spectrum of $\beta\text{-Ga}_2\text{O}_3$ on the c -sapphire substrate [19]. Reflectance and transmittance measurements on undoped $\text{Ga}_2\text{O}_3/r\text{-sapphire}$ were carried out at room temperature in 200 – 2500 nm wavelength range, having high transparency over 80% at visible and near-infrared wavelength ranges, as shown in **Figure 4 (d)**. The absorption coefficient α was then calculated, $(\alpha h\nu)^2$ vs. $h\nu$ (Tauc plot) was used to estimate the optical bandgap. There is only one contribution to the bandgap at 4.60 ± 0.04 eV as shown in the inset of **Figure 4 (d)**.

The electrical resistivity for undoped $\text{Ga}_2\text{O}_3/r\text{-Al}_2\text{O}_3$ was measured from 300 to 850 K in a Van der Pauw configuration. Four electrical contacts of silver paste were painted at each corner of the square-shaped ($1 \times 1 \text{ cm}^2$) sample and then annealed at high temperature. **Figure 4 (e)** shows the temperature dependent resistivity, with $\rho = 5.4 \times 10^4 \text{ } \Omega \cdot \text{cm}$ resistivity at 300 K. Two slopes can be distinguished from the $\ln(\sigma)$ versus $1/T$ plot, the activation energy of conductivity is determined: $E_{a1} = 414 \pm 7 \text{ meV}$ and $E_{a2} = 170 \pm 2 \text{ meV}$ (**Figure 4 (f)**). E_{a1} most probably corresponds to single V_{Ga} related defect acceptor center when sample is of low compensation regime, while the second E_{a2} to $\text{V}_\text{O}^{++} - \text{V}_{\text{Ga}}^-$ native defect association. [19] From the room temperature Hall effect measurements, the hole concentration and mobility are $p = 5.7 \times 10^{13} \text{ cm}^{-3}$ and $\mu < 1 \text{ cm}^2/(\text{V} \cdot \text{s})$, respectively.




Figure 4. (a) Top view SEM image of β -Ga₂O₃/r-Al₂O₃ sample. (b) SEM cross-section image showing the thickness of 453 nm for the thin film. (c) Raman spectra of *r*-plane sapphire substrate (phonon modes labelled “*”) and the Ga₂O₃/r-Al₂O₃ sample. (d) Room temperature transmittance spectrum for Ga₂O₃/r-Al₂O₃ sample, the optical bandgap (E_g) = 4.60 eV estimated by Tauc’s plot (inset). (e) Temperature dependent resistivity in the range of 300 – 850 K, (f) Two activation energies were determined as E_{a1} = 0.414 eV and E_{a2} = 0.170 eV by the $\ln(\sigma)$ versus $1/T$ plot for undoped β -Ga₂O₃/r-Al₂O₃.

This result is significant as it suggests that β -Ga₂O₃, similarly to wide band gap II-VI semiconductors, tends to create native defect associations that act as shallow acceptor centres. It should be underlined that evidently, the probability of defects pairing strongly depends on the concentration of native defects (V_O ; V_{Ga}) and the vicinity of their positions. These favorable conditions are determined by the growth parameters (temperature, pressure) and the crystal structure.

The possibility of obtaining a room temperature hole conductivity in undoped MOCVD Ga₂O₃ with an activation energy of E_{a2} = 170 meV encouraged us to attempt to further increase the

conductivity. To this end, we need to make shallower the $V_O^{++} - V_{Ga}^-$ complex. To this end, we opted for the cation doping.

3. Enhancement of hole conductivity by Zn doping

With our extensive experience in using Zn as a dopant, we have opted to incorporate it into β -Ga₂O₃ to increase the hole conductivity. It was reported on the base of electron paramagnetic resonance (EPR) that, Zn in tetrahedral and octahedral sites acts a deep acceptor (0.65 eV and 0.78 eV, respectively) [47]. Consistent with this finding, we demonstrated that at the doping level of 10^{16} cm⁻³, Zn is indeed a deep acceptor in β -Ga₂O₃ thin films with an ionization energy of 0.7 eV [48]. Computational study suggested that substitutional Zn dopant atoms may replace Ga atoms on the tetrahedral Ga₍₁₎ sites, which were predicted to be preferential sites [49,50]. However, it is noted that hybrid functional calculations and experiment found that Zn atoms may substitute both tetrahedral and octahedral sites with nearly equal energies [47,51].

Upon replacing a Ga atom, Zn reduces the oxygen vacancy concentration, promoting the recharging of V_O^+ and placement of V_O^{++} in the nearest neighbor site to Zn, and play donor's role for positive charge (Zn_{Ga} defect) compensating [52]. Our thermodynamic analysis [53] has shown that as the concentration of incorporated Zn increases (from 10^{15} to 10^{18} cm⁻³), the concentration of double-charged oxygen vacancy V_O^{++} also significantly increases (up to 10^{18} cm⁻³). This will strongly promote the association of two native acceptor-donor defects V_O^{++} -Zn_{Ga}⁻, since the proximity of V_O^{++} to Zn_{Ga}⁻ can reduce its electronic level.

Figure 5 illustrates the $V_O^{++} - Zn_{Ga}^-$ complex-like defects in Zn doped β -Ga₂O₃. Further experimental studies, such as high resolution transmission electron microscopy, infra-red spectroscopy, positron-electron annihilation, are required to identify the exact sites and nature of defect complexes in Zn: β -Ga₂O₃.




Figure 5. Hypothetical crystal structure model of Zn-doped β -Ga₂O₃ containing a $V_O^{++} - Zn_{Ga(1)}^-$ defect complex. A slab cut between $(\bar{2}01)$ planes within a $2 \times 3 \times 2$ replicated unit cell is depicted. The polyhedral highlight tetrahedral (green) and octahedral (purple) coordination of the Ga₍₁₎ and Ga₍₂₎ atoms by O atoms, respectively. A substitutional Zn atom replacing Ga on a tetrahedral Ga₍₁₎ site is highlighted. OVITO Pro 3.7.12 was used for visualization [54] based on a β -Ga₂O₃ crystal structure file (Data retrieved from the Materials Project for Ga₂O₃ (mp-886) from database version v2022.10.28 [55])

The Zn doped β -Ga₂O₃ thin film was grown on *r*-plane of 1-inch sapphire substrates. Secondary-ion mass spectroscopy (SIMS) analysis showed that Zn concentrations in the samples are $[Zn] = 1.0 \times 10^{19} \text{ cm}^{-3}$. XRD analysis does not display any significant difference in structure and strain for Zn: β -Ga₂O₃ thin film with respect to undoped β -Ga₂O₃ thin film, nor the surface morphology by SEM images, while the thickness was determined at 320 nm. The optical bandgap at room temperature for all Zn doped β -Ga₂O₃ film is around $E_g = 4.74 \text{ eV} \pm 0.05 \text{ eV}$, which is slightly larger than for undoped samples. All bandgaps in doped and undoped films were determined by the same Tauc plot.

A. Electronic structure and Valence band of Zn:Ga₂O₃

X-ray photoelectron spectroscopy (XPS) has been employed to study the above-mentioned Zn incorporation effect. The room temperature photoemission spectrum for the Ga2*p*, Zn2*p*, and O1*s*

core levels is shown in **Figure 6 (a)-(d)**. The binding energy value of the core level for the Ga $2p_{3/2}$ states at 1119.3 eV (as determined by Michling *et al.* [56]) on the cleaved β -Ga $_2$ O $_3$ single crystals was used for calibrating the binding energy positions of the XPS spectra. The XPS spectra from the surface of a control sample of a 500 nm thick commercial (Novel Crystal Technology, Inc.) epilayer of nominally *n*-type Si-doped β -Ga $_2$ O $_3$ ($N_d - N_a = 2 \times 10^{19} \text{ cm}^{-3}$) grown on a single crystal β -Ga $_2$ O $_3$ were used as a benchmark for the β -Ga $_2$ O $_3$ /r-sapphire core levels and valence band determination. The XPS spectrum has again been calibrated with respect to the Ga $2p$ energy at 1119.3 eV. The Zn:Ga $_2$ O $_3$ Ga $2p$ doublet separation between the primary Ga $2p_{3/2}$ and the secondary Ga $2p_{1/2}$ was determined to be $\Delta\text{Ga}2p = 26.8 \text{ eV}$, while the peak of Ga $2p_{1/2}$ appeared at 1146.12 eV (**Figure 6 (a)**). For the reference Si:Ga $_2$ O $_3$ sample, those values were determined to be very similar with $\Delta\text{Ga}2p = 26.9 \text{ eV}$ and Ga $2p_{1/2}$ at 1146.22 eV. For both, the Ga $2p$ states show a reasonably sharp structure with a full width at half maximum (FWHM) of $\sim 1.8 \text{ eV}$. As shown in **Figure 6 (b)**, there is a small asymmetric contribution of Ga-Zn states appearing at larger binding energies in agreement with our previous article [57]. The Zn $2p$ split-orbit component doublet was determined to be at 1023.32 eV and 1046.62 eV, for Zn $2p_{3/2}$ and Zn $2p_{1/2}$, respectively and with a separation of $\Delta\text{Zn}2p = 23.3 \text{ eV}$ shown in **Figure 6 (c)**. The value of the Ga $2p_{3/2}$ is larger than the usual value reported for ZnO ($\sim 1021 - 1023 \text{ eV}$) [58] which again is believed to be due to the contribution of Zn-Ga states. The main O $1s$ level for Zn:Ga $_2$ O $_3$ appeared at 532.22 eV while the reference Si:Ga $_2$ O $_3$ was 532.12 eV (**Figure 6 (d)**). The O $1s$ level exhibited secondary (O $_{II}$) and tertiary (O $_{III}$) shoulders at $\sim 533.5 \text{ eV}$ and $\sim 534.9 \text{ eV}$ or some $\sim 1.3 \text{ eV}$ and $\sim 2.9 \text{ eV}$ from the main Ga-O peak, respectively. This triple contribution shape of the O $1s$ core level was similar to the one determined for the reference and was ascribed to ad-atoms at the surface as hydroxides (-OH) and C=O, for (O $_{II}$) and (O $_{III}$), respectively [59]. There are, however, some O $1s$ features visible when compared to the reference sample. There is a small Zn-O contribution at low binding energies ($\sim 530 \text{ eV}$) compatible with Zn-O bonds. Besides, the Zn:Ga $_2$ O $_3$ O $1s$ peak was found to be wider and shifted towards higher binding energies (compared to the Si:Ga $_2$ O $_3$ reference), and an indication of potential intermixing of Ga-O (and Zn-O) oxidation valence.

It has now been well established that the monoclinic gallium oxide valence band density of states is predominantly of O2p character (as it usual in metal oxides) while the conduction band states are predominantly derived from Ga4s and Ga4p states mixed with some contributions of O2p. In **Figure 7 (a)-(b)**, valence band photoemission spectra from our layers are shown. The three maxima of the O2p valence band correspond to the three different oxygen sites in β -Ga₂O₃ (O⁽¹⁾, O⁽²⁾ and O⁽³⁾). The valence band width for both, the reference Si-doped sample and the Zn-doped sample, is around 8 eV, which agrees with previous reports [60]. Nevertheless, an exceptionally large number of tail states extend deeper in the bandgap for the β -Ga₂O₃:Zn film surface compared to the reference *n*-type β -Ga₂O₃ sample. This, in practice, indicates a much-reduced Fermi level value (from the edge of the valence band), with the equilibrium energy level located in the lower part of the bandgap and an acceptor *p*-type nature of the layer surface. The presence of such states related to divacancy complex close to the valence band edge have already been investigated in previous ab-initio studies such as the one of Usseinov *et al.* [22]. As shown in **Figure 7 (d)**, the experimental relative density and position of the divacancy states, compared to the O2p states, also are also in agreement with these atomistic simulations: Among all combinations of paired vacancies, the creation of V_{Ga1}-V_{O(1,2,3)} complexes is energetically more favorable than similar V_{Ga2}-V_{O(1,2,3)} complexes and the lowest-energy configuration is for the V_{Ga1}-V_{O1} pair vacancy.




Figure 6. Detail (intensity normalized) of the main XPS peaks for (a) gallium ($\text{Ga}2p_{1/2} - \text{Ga}2p_{3/2}$), (b) gallium ($\text{Ga}2p_{3/2}$), (c) Zinc ($\text{Zn}2p$), (d) oxygen ($\text{O}1s$), of Zn doped Ga_2O_3 grown on $r\text{-Al}_2\text{O}_3$ substrate.




Figure 7. (a) Experimental XPS high-resolution valence band of Zn doped β -Ga₂O₃ thin film, and Si doped β -Ga₂O₃ single crystal as a reference. (b) Idem (log-scale), for evidencing the tail states signature of acceptors at the valence band region (VBM). (c) Unit cell of β -Ga₂O₃ with unique positions of Ga and O denoted ($Ga_{(1)}$, $Ga_{(2)}$; $O_{(1)}$, $O_{(2)}$, $O_{(3)}$). (d) Total density of states for $V_{Ga(1)}^0$, $V_{O(1)}^0$ and $(V_{Ga(1)} - V_{O(1)})^0$ (defects states in band gap region have been magnified by a factor 5, green-dashed-vertical line represents the Fermi level) [22].

B. Optical properties of Zn:Ga₂O₃

Photoluminescence spectra (at room temperature) of undoped and Zn-doped Ga₂O₃ sample exhibit a broad emission band between 350 – 620nm and an additional band at around 330nm for only undoped sample (**Figure 8 (a)**). The later ultraviolet luminescence (UVL) band is commonly ascribed to the recombination of self-trapped excitons, considering the absence of near-band edge emission and their lack of β -Ga₂O₃ for sub-bandgap excitation [34]. As for the broadband, it is very similar to what has been reported for our undoped Ga₂O₃ thin films with four characteristics luminescence bands (after deconvolution): ultraviolet (UVL' and UVL) at 375 nm and 415 nm; blue luminescence (BL) at 450 nm; and green luminescence (GL) at 520 nm.

We have studied Zn doped sample in details by cathodoluminescence measurements at (20 – 140 °C) temperatures. We observe thermal quenching of CL signal as the temperature is raised from 20 to 140 °C. Raw CL spectra for these two temperatures are shown in **Figure 8 (b)**. The plot of integrated CL intensity as a function of inverse temperature is shown in **Figure 8 (c)**, which illustrates the thermal quenching of the CL emission with increase in temperature. This behavior is empirically modelled with the following equation:

$$I(T) = I_0 / (1 + e^{\Delta E_{CL}/kT}) \quad (1)$$

Here, $I(T)$ is the temperature dependent integrated CL intensity, I_0 is a scaling constant, ΔE_{CL} is the temperature dependent activation energy pertaining to the thermal quenching effect, k is the Boltzmann constant and T is the temperature in Kelvin. The activation energy ΔE_{CL} obtained from the fit to equation 1 was 548 meV. The thermal quenching of CL emission with increase in temperature can be explained with de-trapping of electrons from meta-stable trap levels. This behavior is also seen in other wide bandgap semiconductors such as GaN [61–63] and ZnO [64]. Additionally, thermal quenching of blue (emission peak centred at 2.85 eV) photoluminescence within the temperature range of 300 – 550 K was observed by Binet and Gourier [21]. According authors a fast electron–hole recombination occurs at the acceptor site with strong electron–phonon coupling giving rise to

the blue emission. An estimated activation energy of 0.42 eV in *n*-type Ga₂O₃ bulk crystal ($E_g = 4.9$ eV) related to this emission is close to ΔE_{CL} observed in this report. This activation energy was attributed to hole de-trapping or the native acceptor related ionization energy. For our sample we can deduce that there is acceptor center (Ga vacancy related) located at around 0.55 ± 0.04 eV from the top of the valence band.

The obtained activation energy is for the aggregate CL intensity for the limited temperature range of 20 °C to 140 °C. Expanding the temperature range down to 4 K. on the lower side and Gaussian decomposition of the constituent participating defect levels would reveal a complete picture of the CL probing of carrier recombination dynamics; This aspect will be explored in detail in a future study.




Figure 8. (a) Photoluminescence spectra for undoped (UID in the figure) and Zn doped samples at 294K. (b) Comparison of cathodoluminescence emission spectra for Zn doped Ga₂O₃ on *r*-sapphire at 20 and 140 °C. (b) Thermal quenching of CL observed in Zn doped Ga₂O₃ on *r*-sapphire in the temperature range of 20 to 140 °C. The activation energy obtained from equation 1 is 548 ± 42 meV.

C. Electrical transport properties of Zn:Ga₂O₃

Since Ga₂O₃ is well known for possibility of exhibiting the surface conductivity [60,65–68], for precaution we have conducted study to eliminate this hypotheses in our case. We performed an electrochemical investigation using cyclic voltammetry. The surface states of the sample implanted in the electrolyte can be analyzed based on information such as anodic and cathodic significant currents and potentials, the oxidation and reduction onset potentials obtained by the

voltammograms [69]. Indeed, various semiconductor materials such as InP [70], TiO₂ [71], 3C-SiC [72], GaN [73] have been studied by voltammetric techniques. **Figure 9 (a)** shows the first cycle of the voltammogram performed on the Zn doped Ga₂O₃ thin film. The current density was calculated by the current divided by the area immersed in the electrolyte, it is 0.5 cm² for this sample. Although the potential was swept from -3.3 to 2.7 V, i.e. the polarization is larger than the Zn:Ga₂O₃ energy band gap, neither anodic nor cathodic significant current, which is characteristic of a surface 2D conduction, was observed. Knowing that the electrochemical response of oxidation or reduction is caused by the mobility of the free carriers (loss or gain depending on the polarity) on the interface sample/electrolyte. Observing such a low current without significant electrochemical response reveals that the room temperature conductivity of the Zn doped Ga₂O₃ sample does not originate from the surface. (Moreover, the curve is not perfectly flat, possibly due to the resistance of the electrical contact between the metal and the sample).

The same electrical transport measurement configurations were used for undoped β -Ga₂O₃ and Zn doped β -Ga₂O₃/r-Al₂O₃ films. **Figure 9 (b)** shows the linear current–voltage (I–V) behavior at 300 K, indicating the Ohmic characteristics of the contacts. The first measurement showed that this sample exhibits a room temperature $\rho = 4.3 \times 10^1 \Omega \cdot \text{cm}$ resistivity. The sample was remeasured at room temperature after 18 months, resulting $\rho = 6.1 \times 10^1 \Omega \cdot \text{cm}$. Resistivity versus temperature curve suggests that the sample exhibits a semiconducting behavior (**Figure 9 (c)**). Measurement has been carried out down to liquid nitrogen temperature, showing $\rho = 1.6 \times 10^5 \Omega \cdot \text{cm}$ at 80 K. Plotting the $\ln(\sigma)$ versus $1/T$ plot reveals a single slope indicating the only one conduction mechanism with activation energy determined as $E_a = 86 \pm 0.4 \text{ meV}$ (**Figure 9 (d)**).




Figure 9. (a) Cyclic voltammogram for Zn:Ga₂O₃ thin film. (b) Ohmic I–V characteristics of electrical contacts at 300 K. (c) Temperature dependent resistivity in the range of 80 – 850 K. (d) The activation energy of the conductivity was determined as 86 ± 0.4 meV by the $\ln(\sigma)$ versus $1/T$ plot in the temperature range of 80 – 850 K. (e) Seebeck voltage versus temperature (f) Hall hole concentrations versus temperature (g) Hall hole mobilities versus temperature.

The positive sign of the Seebeck voltage has been determined for Zn:Ga₂O₃ thin films, confirming the majority carriers to be holes. **Figure 9 (e)** Seebeck coefficient was estimated, $S = +7$ - $10 \text{ } \mu\text{V}/^\circ\text{C}$ at 100-160°C. It is clear from experiment that Zn doping can decrease activation energy as compared to the undoped sample. To estimate the carrier concentration at room temperature, Hall effect measurement was carried out with a particular procedure to eliminate error with a 15-second

delay between current applying and voltage measurements at an applied magnetic field of ± 1.6 T. Consequently, the hole concentration and the hole mobility at room temperature were determined to be $2 \times 10^{18} \text{ cm}^{-3}$, and $\sim 0.1 \text{ cm}^2/(\text{V} \cdot \text{S})$, respectively. The hole concentration remains $> 10^{18} \text{ cm}^{-3}$, while the mobility was slightly decreased and $< 1 \text{ cm}^2/(\text{V} \cdot \text{S})$ in the measurement temperature range (**Figure 9 (f)-(g)**). It indicates that the acceptor defects ($V_O^{++} - Zn_{Ga}^-$ as hypothesized) are shallow enough to be activated at room temperature. The tiny hole mobilities might be attributed to strong scattering processes of carriers on a significant number of native defects centres and large effective mass of holes.

4. Conclusion

The hole conductivity of the promising UWBG oxide $\beta\text{-Ga}_2\text{O}_3$ has been a hot issue recently, because it is a pre-requisite for the development of the $\beta\text{-Ga}_2\text{O}_3$ based next-generation bipolar electronic and optoelectronic devices. Generally, the possibility to obtain hole conductivity strongly depends what kind of point defects are dominant in the material (Frenkel, Schottky or associates), which itself depends on growth parameters of thin films. It is known that in wide band gap II-VI compounds realization of hole conductivity with doping is mainly related not with dopant related acceptor defect, but with creation of native defects charge states to assure electroneutrality of the system [28,74]. The motivation of our work was to demonstrate that in $\beta\text{-Ga}_2\text{O}_3$ as a ultrawide band gap III-VI material can obey the same rule, i.e., native defects can enable the realization of high hole conductivity thanks to shallow acceptor centre.

We demonstrated in this work that Zn doping of $\beta\text{-Ga}_2\text{O}_3/r\text{-sapphire}$ thin film grown by MOCVD technique can exhibit a long-time stable room-temperature hole conductivity with a conductivity activation energy of around 86 meV. The origin of this level might be attributed then the donor-acceptor complex $V_O^{++} - Zn_{Ga}^-$. We believe that this study will add new evidences and will help to break a “taboo” related to the feasibility of room temperature hole conductivity in Ga_2O_3 via traditional growth technique and doping. We showed that the effectiveness of acceptor dopant

depends on the concentration and the energetic level of cation and anion vacancies. We hope that we can inspire researchers to further study experimentally the point defects in β -Ga₂O₃. From the practical point of view, we expect our investigation will increase the portfolio of techniques to achieve the much wanted homoepitaxial p - n junction for the emerging Ga₂O₃ ultra-wide semiconductor power electronics technology enabling, for example, proper ultra-high power PiN diodes.

5. Experimental details

Thin film growth: The undoped and Zn doped Ga₂O₃ samples were grown in a RF-heated horizontal MOCVD reactor on *r*-sapphire (Al₂O₃) substrates. During the growth of undoped Ga₂O₃ samples, the flow rate of trimethylgallium (TMGa), and oxygen were kept at 12 $\mu\text{mol/min}$ and 1200 sccm, respectively. The growth temperature, pressure and time were set at 775 $^{\circ}\text{C}$ and 30 torr, 85 minutes, respectively. For the Zn doped Ga₂O₃ sample, keeping the same growth conditions and the precursors' flow of Ga and O₂, the Zn precursor diethylzinc (DEZn) flow was set at 2.3 $\mu\text{mol/min}$, the growth time was 60 mins. The TMGa and DEZn bubbler temperatures were fixed at -10 $^{\circ}\text{C}$ and 0 $^{\circ}\text{C}$, respectively. The thickness of undoped and Zn doped Ga₂O₃ were determined by MEB to be 453 and 320 nm, respectively.

Raman spectra: Raman spectra were recorded using a Renishaw Invia Reflex micro-Raman spectrometer at room temperature. The samples were excited using a cw Modu-Laser Stellar-REN laser emitting at 514.5 nm with a power of 2 – 4 mW. The reflecting microscope objective was 50 with a NA 0.75; the excitation spot diameter was 1 mm. The back-scattered light was dispersed by a monochromator with a spectral resolution of 1.4 cm^{-1} . The light was detected by a charge coupled device. The typical accumulation time was 30 s. Raman shifts were calibrated using an optical phonon frequency (520.5 cm^{-1}) of a silicon nanocrystal. Several reference Raman spectra for beta-Ga₂O₃ single crystal substrates and sapphire c-cut substrates have been also measured.

Optical transmittance/reflectance measurements: Optical transmission and reflectance spectra were measured in the 200 – 2500 nm wavelength range with a step of 2 nm using a Perkin Elmer LAMBDA 950 spectrophotometer.

X-ray diffraction measurements: The structure of the samples was studied using X-ray diffraction (XRD). Data were collected on a 5-circle diffractometer (Rigaku SmartLab) with Cu K $_{\alpha}$ radiation from a rotating anode. The film out-of-plane (OP) orientation and strain were measured by $\theta/2\theta$ scans and rocking curves (ω -scans). When no strictly OP reflection exists for a film, reflections

close to the normal to the sample were measured in asymmetric OP geometry by $\omega/2\theta$ scans. For OP scans, Cu K $_{\alpha 1}$ radiation was selected by a channel-cut Ge(220) 2-reflection monochromator. The film in-plane (IP) orientation and strain were probed by grazing incidence XRD (GIXRD) at the constant incidence of 0.5° without the monochromator. When no strictly IP reflection exists for a film, reflections close to IP were measured. The film global orientation texture was explored by x-ray pole figures (PFs), using the IP PF configuration [75].

Secondary-ion mass spectrometry (SIMS) measurements: SIMS measurements were performed using a Cameca IMS 7f equipment on to the samples to access the concentration and depth distribution of Zn dopant.

X-ray photoemission spectroscopy (XPS) measurements: XPS were performed with a Phoibos 150 analyzer (SPECS GmbH, Berlin, Germany) in ultra-high vacuum conditions (base pressure 3×10^{-10} mbar). XPS measurements were performed with a monochromatic Al K $_{\alpha}$ X-ray source (1486.74 eV).

Cathodoluminescence measurements: Cathodoluminescence (CL) spectra were measured inside a Phillips XL30 scanning electron microscope (SEM) with Gatan MonoCL2 attachment. The temperature of the specimen was varied with an integrated temperature-controlled stage in the temperature range of 20 °C to 140 °C. The CL signal is collected with the help of a parabolic mirror assembly and recorded with the help of a monochromator (grating blazed at 1200 lines/mm) and a Hamamatsu photomultiplier tube with a range of 150 – 850 nm.

Hall effect measurements: Ohmic contacts were prepared by silver paint at the four corners of the sample. Hall Effect measurements were performed by home built high impedance high temperature setup in a Van der Pauw configuration in the temperature range of 300 – 850 K applying the magnetic fields perpendicularly to the film plane varying from 0 to 1.6 T. All the measurements were carried out under nitrogen gas atmosphere.

Electrochemical measurement: Electrochemical experiments were performed in dark using the three electrodes set-up PARSTAT 2273 potentiostat/galvanostat. Pt wire and 1 mol dm⁻³ KCl silver/silver Chloride (Ag/AgCl, E°s = 199 mV vs. SHE) electrode respectively served as counter and reference electrodes. Zn doped Ga₂O₃ thin film was used as working electrode.

Acknowledgement:

The present work is a part of “GALLIA” International Research Project, CNRS, France. GEMaC colleagues acknowledge financial support of French National Agency of Research (ANR), project “GOPOWER”, CE-50 N0015-01.

Research at the University of Central Florida and Tel Aviv University was partially supported by the US-Israel Binational Science Foundation (award 2018010) and NATO (SPS MYP G5748).

Researchers would like to acknowledge Dr. François Jomard (GEMaC) for SIMS measurement and analysis.

References

- [1] Z. Feng, A. F. M. Anhar Uddin Bhuiyan, M. R. Karim, and H. Zhao, *MOCVD Homoepitaxy of Si-Doped (010) β -Ga₂O₃ Thin Films with Superior Transport Properties*, Appl. Phys. Lett. **114**, 250601 (2019).
- [2] A. K. Rajapitamahuni, A. K. Manjeshwar, A. Kumar, A. Datta, P. Ranga, L. R. Thoutam, S. Krishnamoorthy, U. Singiseti, and B. Jalan, *Plasmon–Phonon Coupling in Electrostatically Gated β -Ga₂O₃ Films with Mobility Exceeding 200 Cm² V^{−1} s^{−1}*, ACS Nano **16**, 8812 (2022).
- [3] M. Higashiwaki, K. Sasaki, A. Kuramata, T. Masui, and S. Yamakoshi, *Gallium Oxide (Ga₂O₃) Metal-Semiconductor Field-Effect Transistors on Single-Crystal β -Ga₂O₃ (010) Substrates*, Appl. Phys. Lett. **100**, 013504 (2012).
- [4] B. J. Baliga, *Power Semiconductor Device Figure of Merit for High-Frequency Applications*, IEEE Electron Device Lett. **10**, 455 (1989).
- [5] J. Lin, L. Zhou, Y. Shen, J. Fu, Y. Chen, L. Lei, R. Ye, Y. Shen, D. Deng, and S. Xu, *[Zn²⁺–Ge⁴⁺] Co-Substitutes [Ga³⁺–Ga³⁺] to Coordinately Broaden the near-Infrared Emission of Cr³⁺ in Ga₂O₃ Phosphors*, Phys. Chem. Chem. Phys. (2022).
- [6] H. Xie, L. Chen, Y. Liu, and K. Huang, *Preparation and Photoluminescence Properties of Eu-Doped α - and β -Ga₂O₃ Phosphors*, Solid State Commun. **141**, 12 (2007).
- [7] Y. Wang, Y. Xue, J. Su, Z. Lin, J. Zhang, J. Chang, and Y. Hao, *Realization of Cost-Effective and High-Performance Solar-Blind Ultraviolet Photodetectors Based on Amorphous Ga₂O₃ Prepared at Room Temperature*, Mater. Today Adv. **16**, 100324 (2022).
- [8] Y. Xu et al., *Ultrahigh-Performance Solar-Blind Photodetectors Based on High Quality Heteroepitaxial Single Crystalline β -Ga₂O₃ Film Grown by Vacuumfree, Low-Cost Mist Chemical Vapor Deposition*, Adv. Mater. Technol. 2001296 (2021).
- [9] M. Higashiwaki, K. Sasaki, T. Kamimura, M. Hoi Wong, D. Krishnamurthy, A. Kuramata, T. Masui, and S. Yamakoshi, *Depletion-Mode Ga₂O₃ Metal-Oxide-Semiconductor Field-Effect Transistors on β -Ga₂O₃ (010) Substrates and Temperature Dependence of Their Device Characteristics*, Appl. Phys. Lett. **103**, 123511 (2013).
- [10] A. Bhattacharyya, P. Ranga, M. Saleh, S. Roy, M. A. Scarpulla, K. G. Lynn, and S. Krishnamoorthy, *Schottky Barrier Height Engineering in β -Ga₂O₃ Using SiO₂ Interlayer Dielectric*, IEEE J. Electron Devices Soc. **8**, 286 (2020).
- [11] Y. Gao et al., *High-Voltage β -Ga₂O₃ Schottky Diode with Argon-Implanted Edge Termination*, Nanoscale Res. Lett. **14**, 8 (2019).
- [12] M. Baldini, M. Albrecht, A. Fiedler, K. Irmischer, R. Schewski, and G. Wagner, *Editors' Choice—Si- and Sn-Doped Homoepitaxial β -Ga₂O₃ Layers Grown by MOVPE on (010)-Oriented Substrates*, ECS J. Solid State Sci. Technol. **6**, Q3040 (2016).
- [13] K. D. Leedy et al., *Highly Conductive Homoepitaxial Si-Doped Ga₂O₃ Films on (010) β -Ga₂O₃ by Pulsed Laser Deposition*, Appl. Phys. Lett. **111**, 012103 (2017).
- [14] M. J. Tadjer, J. L. Lyons, N. Nepal, J. A. Freitas, A. D. Koehler, and G. M. Foster, *Review-Theory and Characterization of Doping and Defects in β -Ga₂O₃*, ECS J. Solid State Sci. Technol. **8**, Q3187 (2019).
- [15] W. Zhou, C. Xia, Q. Sai, and H. Zhang, *Controlling N-Type Conductivity of β -Ga₂O₃ by Nb Doping*, Appl. Phys. Lett. **111**, 242103 (2017).
- [16] Z. Chi, J. J. Asher, M. R. Jennings, E. Chikoidze, and A. Pérez-Tomás, *Ga₂O₃ and Related Ultra-Wide Bandgap Power Semiconductor Oxides: New Energy Electronics Solutions for CO₂ Emission Mitigation*, Materials **15**, 3 (2022).
- [17] S. J. Pearton, J. Yang, P. H. Cary, F. Ren, J. Kim, M. J. Tadjer, and M. A. Mastro, *A Review of Ga₂O₃ Materials, Processing, and Devices*, Appl. Phys. Rev. **5**, 011301 (2018).
- [18] E. Chikoidze et al., *P-Type β -Gallium Oxide: A New Perspective for Power and Optoelectronic Devices*, Mater. Today Phys. **3**, 118 (2017).

- [19] E. Chikoidze et al., *Enhancing the Intrinsic P-Type Conductivity of the Ultra-Wide Bandgap Ga₂O₃ Semiconductor*, J. Mater. Chem. C **7**, 10231 (2019).
- [20] V. I. Vasiltsiv, Y. M. Zakharko, and Y. I. Rym, *On the Nature of Blue and Green Luminescence Bands of Beta-Ga₂O₃*, Ukr. Fiz. Zhurnal **33**, 1320 (1988).
- [21] L. Binet and D. Gourier, *ORIGIN OF THE BLUE LUMINESCENCE OF β -Ga₂O₃*, J. Phys. Chem. Solids **59**, 1241 (1998).
- [22] A. Usseinov, A. Platonenko, Z. Koishybayeva, A. Akilbekov, M. Zdorovets, and A. I. Popov, *Pair Vacancy Defects in β -Ga₂O₃ Crystal: Ab Initio Study*, Opt. Mater. X **16**, 100200 (2022).
- [23] A. Karjalainen, I. Makkonen, J. Etula, K. Goto, H. Murakami, Y. Kumagai, and F. Tuomisto, *Split Ga Vacancies in N-Type and Semi-Insulating β -Ga₂O₃ Single Crystals*, Appl. Phys. Lett. **118**, 072104 (2021).
- [24] X. Zhu, Y.-W. Zhang, S.-N. Zhang, X.-Q. Huo, X.-H. Zhang, and Z.-Q. Li, *Defect Energy Levels in Monoclinic β -Ga₂O₃*, J. Lumin. **246**, 118801 (2022).
- [25] Z. Y. Wu, Z. X. Jiang, C. C. Ma, W. Ruan, Y. Chen, H. Zhang, G. Q. Zhang, Z. L. Fang, J. Y. Kang, and T.-Y. Zhang, *Energy-Driven Multi-Step Structural Phase Transition Mechanism to Achieve High-Quality p-Type Nitrogen-Doped β -Ga₂O₃ Films*, Mater. Today Phys. **17**, 100356 (2021).
- [26] C. Ma et al., *Exploring the Feasibility and Conduction Mechanisms of P-Type Nitrogen-Doped β -Ga₂O₃ with High Hole Mobility*, J. Mater. Chem. C **10**, 6673 (2022).
- [27] C. Ma, Z. Wu, H. Zhang, H. Zhu, J. Kang, J. Chu, and Z. Fang, *P-Type Nitrogen-Doped β -Ga₂O₃: The Role of Stable Shallow Acceptor NO–VGa Complexes*, Phys. Chem. Chem. Phys. **25**, 13766 (2023).
- [28] A. M. Gurvich, *Introduction to the Physical Chemistry of Crystal Phosphors (In Russian)* (Moscow, 1982).
- [29] T. V. Butkhuzi, M. M. Sharvashidze, N. M. Gamkrelidze, K. V. Gelovani, T. G. Khulordava, N. P. Kekelidze, and E. E. Kekelidze, *The Regulation of Defect Concentrations by Means of Separation Layer in Wide-Band II-VI Compounds*, Semicond. Sci. Technol. **16**, 575 (2001).
- [30] A. N. Georgobiani, M. S. Kotlyarevskii, V. N. Mikhaleiko, and Yu. V. Shvetsov, *Nature of Luminescence in Zinc Sulfide with Intrinsic-Defect Hole Conductivity*, J. Appl. Spectrosc. **35**, 1097 (1981).
- [31] T. v. Butkhuzi, T. g. Tchelidze, E. g. Chikoidze, and N. p. Kekelidze, *Silver Doped P-Type ZnS Crystals*, Phys. Status Solidi B **229**, 365 (2002).
- [32] J. G. Reynolds, C. L. Reynolds, A. Mohanta, J. F. Muth, J. E. Rowe, H. O. Everitt, and D. E. Aspnes, *Shallow Acceptor Complexes in P-Type ZnO*, Appl. Phys. Lett. **102**, 152114 (2013).
- [33] T. Zacherle, P. C. Schmidt, and M. Martin, *Ab Initio Calculations on the Defect Structure of β -Ga₂O₃*, Phys. Rev. B **87**, 235206 (2013).
- [34] S. Modak et al., *Variable Temperature Probing of Minority Carrier Transport and Optical Properties in p -Ga₂O₃*, APL Mater. **10**, 031106 (2022).
- [35] L. Dimitroenco, G. Strikis, B. Polyakov, L. Bikse, S. Oras, and E. Butanovs, *The Effect of a Nucleation Layer on Morphology and Grain Size in MOCVD-Grown β -Ga₂O₃ Thin Films on C-Plane Sapphire*, Materials **15**, 8362 (2022).
- [36] V. Gottschalch, K. Mergenthaler, G. Wagner, J. Bauer, H. Paetzelt, C. Sturm, and U. Teschner, *Growth of β -Ga₂O₃ on Al₂O₃ and GaAs Using Metal-Organic Vapor-Phase Epitaxy*, Phys. Status Solidi A **206**, 243 (2009).
- [37] X. Liu, Q. Liu, B. Zhao, Y. Ren, B. W. Tao, and W. L. Zhang, *Comparison of β -Ga₂O₃ Thin Films Grown on r-Plane and c-Plane Sapphire Substrates*, Vacuum **178**, 109435 (2020).
- [38] V. I. Nikolaev, V. Maslov, S. I. Stepanov, A. I. Pechnikov, V. Krymov, I. P. Nikitina, L. I. Guzilova, V. E. Bougrov, and A. E. Romanov, *Growth and Characterization of β -Ga₂O₃ Crystals*, J. Cryst. Growth **457**, 132 (2017).

- [39] S. Rafique, L. Han, and H. Zhao, *Synthesis of Wide Bandgap Ga₂O₃ (E_g ~ 4.6–4.7 eV) Thin Films on Sapphire by Low Pressure Chemical Vapor Deposition*, Phys. Status Solidi A **213**, 1002 (2016).
- [40] T. Zhang, Z. Hu, Y. Li, Y. Zhang, Q. Feng, J. Ning, C. Zhang, J. Zhang, and Y. Hao, *Comparison of Ga₂O₃ Films Grown on m- and r-Plane Sapphire Substrates by MOCVD*, ECS J. Solid State Sci. Technol. **9**, 125008 (2020).
- [41] S. Nakagomi, S. Kaneko, and Y. Kokubun, *Crystal Orientations of β -Ga₂O₃ Thin Films Formed on m-Plane and r-Plane Sapphire Substrates*, Phys. Status Solidi B **252**, 612 (2015).
- [42] S. Nakagomi and Y. Kokubun, *Cross-Sectional TEM Imaging of β -Ga₂O₃ Thin Films Formed on c-Plane and a-Plane Sapphire Substrates*, Phys Status Solidi A **210**, 1738 (2013).
- [43] S. Nakagomi and Y. Kokubun, *Crystal Orientation of β -Ga₂O₃ Thin Films Formed on c-Plane and a-Plane Sapphire Substrate*, J. Cryst. Growth **349**, 12 (2012).
- [44] D. Machon, P. F. McMillan, B. Xu, and J. Dong, *High-Pressure Study of the β -to- α transition in Ga₂O₃*, Phys. Rev. B **73**, 094125 (2006).
- [45] V. I. Nikolaev, A. I. Pechnikov, S. I. Stepanov, I. P. Nikitina, A. N. Smirnov, A. V. Chikiryaka, S. S. Sharofidinov, V. E. Bougrov, and A. E. Romanov, *Epitaxial Growth of (2 $\bar{0}1$) β -Ga₂O₃ on (0001) Sapphire Substrates by Halide Vapour Phase Epitaxy*, Mater. Sci. Semicond. Process. **47**, 16 (2016).
- [46] T. Onuma, S. Fujioka, T. Yamaguchi, Y. Itoh, M. Higashiwaki, K. Sasaki, T. Masui, and T. Honda, *Polarized Raman Spectra in β -Ga₂O₃ Single Crystals*, J. Cryst. Growth **401**, 330 (2014).
- [47] T. D. Gustafson, J. Jesenovec, C. A. Lenyk, N. C. Giles, J. S. McCloy, M. D. McCluskey, and L. E. Halliburton, *Zn Acceptors in β -Ga₂O₃ Crystals*, J. Appl. Phys. **129**, 155701 (2021).
- [48] E. Chikoidze et al., *Electrical Properties of p-Type Zn:Ga₂O₃ Thin Films*, J. Vac. Sci. Technol. A **40**, 043401 (2022).
- [49] J. L. Lyons, *A Survey of Acceptor Dopants for β -Ga₂O₃*, Semicond. Sci. Technol. **33**, 05LT02 (2018).
- [50] D. Skachkov and W. R. L. Lambrecht, *Computational Study of Electron Paramagnetic Resonance Parameters for Mg and Zn Impurities in β -Ga₂O₃*, Appl. Phys. Lett. **114**, 202102 (2019).
- [51] J. Jesenovec, J. Varley, S. E. Karcher, and J. S. McCloy, *Electronic and Optical Properties of Zn-Doped β -Ga₂O₃ Czochralski Single Crystals*, J. Appl. Phys. **129**, 225702 (2021).
- [52] D. Guo, X. Qin, M. Lv, H. Shi, Y. Su, G. Yao, S. Wang, C. Li, P. Li, and W. Tang, *Decrease of Oxygen Vacancy by Zn-Doped for Improving Solar-Blind Photoelectric Performance in β -Ga₂O₃ Thin Films*, Electron. Mater. Lett. **13**, 483 (2017).
- [53] E. Chikoidze et al., *Ultra-High Critical Electric Field of 13.2 MV/cm for Zn-Doped p-Type β -Ga₂O₃*, Mater. Today Phys. **15**, 100263 (2020).
- [54] A. Stukowski, *Visualization and Analysis of Atomistic Simulation Data with OVITO—the Open Visualization Tool*, Model. Simul. Mater. Sci. Eng. **18**, 015012 (2009).
- [55] *Mp-886: Ga₂O₃ (Monoclinic, C2/m, 12)*, <https://materialsproject.org/materials/mp-886>.
- [56] M. Michling and D. Schmeißer, *Resonant Photoemission at the O1s Threshold to Characterize β -Ga₂O₃ Single Crystals*, IOP Conf. Ser. Mater. Sci. Eng. **34**, 012002 (2012).
- [57] E. Chikoidze et al., *P-Type Ultrawide-Band-Gap Spinel ZnGa₂O₄: New Perspectives for Energy Electronics*, Cryst. Growth Des. **20**, 2535 (2020).
- [58] M. C. Biesinger, L. W. M. Lau, A. R. Gerson, and R. St. C. Smart, *Resolving Surface Chemical States in XPS Analysis of First Row Transition Metals, Oxides and Hydroxides: Sc, Ti, V, Cu and Zn*, Appl. Surf. Sci. **257**, 887 (2010).
- [59] R. Al-Gaashani, S. Radiman, A. R. Daud, N. Tabet, and Y. Al-Douri, *XPS and Optical Studies of Different Morphologies of ZnO Nanostructures Prepared by Microwave Methods*, Ceram. Int. **39**, 2283 (2013).

- [60] J. E. N. Swallow, J. B. Varley, L. a. H. Jones, J. T. Gibbon, L. F. J. Piper, V. R. Dhanak, and T. D. Veal, *Transition from Electron Accumulation to Depletion at β -Ga₂O₃ Surfaces: The Role of Hydrogen and the Charge Neutrality Level*, APL Mater. **7**, 022528 (2019).
- [61] Z. Liu, Y. Huang, X. Yi, B. Fu, G. Yuan, J. Wang, J. Li, and Y. Zhang, *Analysis of Photoluminescence Thermal Quenching: Guidance for the Design of Highly Effective p-Type Doping of Nitrides*, Sci. Rep. **6**, 32033 (2016).
- [62] M. A. Reshchikov, *Mechanisms of Thermal Quenching of Defect-Related Luminescence in Semiconductors*, Phys. Status Solidi A **218**, 2000101 (2021).
- [63] M. A. Reshchikov, A. A. Kvasov, M. F. Bishop, T. McMullen, A. Usikov, V. Soukhoveev, and V. A. Dmitriev, *Tunable and Abrupt Thermal Quenching of Photoluminescence in High-Resistivity Zn-Doped GaN*, Phys. Rev. B **84**, 075212 (2011).
- [64] M. Watanabe et al., *Negative Thermal Quenching of Photoluminescence in ZnO*, Phys. B Condens. Matter **376–377**, 711 (2006).
- [65] P. D. C. King, I. McKenzie, and T. D. Veal, *Observation of Shallow-Donor Muonium in Ga₂O₃: Evidence for Hydrogen-Induced Conductivity*, Appl. Phys. Lett. **96**, 062110 (2010).
- [66] T. C. Lovejoy et al., *Band Bending and Surface Defects in β -Ga₂O₃*, Appl. Phys. Lett. **100**, 181602 (2012).
- [67] J. B. Varley, J. R. Weber, A. Janotti, and C. G. Van de Walle, *Oxygen Vacancies and Donor Impurities in β -Ga₂O₃*, Appl. Phys. Lett. **97**, 142106 (2010).
- [68] L. Vines, C. Bhodoo, H. von Wenckstern, and M. Grundmann, *Electrical Conductivity of In₂O₃ and Ga₂O₃ after Low Temperature Ion Irradiation: Implications for Intrinsic Defect Formation and Charge Neutrality Level*, J. Phys. Condens. Matter **30**, 025502 (2017).
- [69] K. T. Kawagoe, J. B. Zimmerman, and R. M. Wightman, *Principles of Voltammetry and Microelectrode Surface States*, J. Neurosci. Methods **48**, 225 (1993).
- [70] M. Fregnaux, M. Bouttemy, D. Aureau, S. Bechu, A. Etcheberry, and A.-M. Goncalves, *(Invited) Outstanding Contributions of Liquid Ammonia on III-V Semiconductors (Photo)-Electrochemistry*, ECS Trans. **109**, 31 (2022).
- [71] A. Fattori, L. M. Peter, H. Wang, H. Miura, and F. Marken, *Fast Hole Surface Conduction Observed for Indoline Sensitizer Dyes Immobilized at Fluorine-Doped Tin Oxide–TiO₂ Surfaces*, J. Phys. Chem. C **114**, 11822 (2010).
- [72] N. Yang, H. Zhuang, R. Hoffmann, W. Smirnov, J. Hees, X. Jiang, and C. E. Nebel, *Nanocrystalline 3C-SiC Electrode for Biosensing Applications*, Anal. Chem. **83**, 5827 (2011).
- [73] Q. Liu, J. Li, W. Yang, X. Zhang, C. Zhang, C. Labbé, X. Portier, F. Liu, J. Yao, and B. Liu, *Simultaneous Detection of Trace Ag(I) and Cu(II) Ions Using Homoepitaxially Grown GaN Micropillar Electrode*, Anal. Chim. Acta **1100**, 22 (2020).
- [74] M. Aven, *Physics and Chemistry of II-VI Compounds* (North-Holland, 1967).
- [75] K. Inaba and S. Kobayashi, *Various Pole Figure Measurement Techniques with SmartLab, Assisting Thin Film Characterization*, 7 (2018).