

Experimental determination of the H–Hf phase diagram using *in situ* neutron diffraction

Maxime Dottor^a, Jean-Claude Crivello^a, Laetitia Laversenne^b, Jean-Marc Joubert^{a,*}

^a Univ Paris Est Creteil, CNRS, ICMPE, UMR 7182, 2 rue Henri Dunant, 94320 Thiais, France

^b University Grenoble Alpes, CNRS, Grenoble INP, Institut Néel, 38000 Grenoble, France

* Corresponding author. jean-marc.joubert@cnrs.fr

Figures




Figure S1. Cell parameters and volume of the α -Hf phase as a function of temperature in a sample of initial composition $\text{HfD}_{0.217}$ (experiment 1). For cell parameters, error bars (0.001 \AA) are commensurate with the symbol size.




Figure S2. Cell parameters and volume of α -Hf phase as a function of overall deuterium content at $700 \text{ } ^\circ\text{C}$ (experiment 1). For cell parameters, error bars (0.001 \AA) are commensurate with the symbol size.




Figure S3. Displacement parameters of the δ - HfD_{2-x} phase as a function of temperature (experiment 1).




Figure S4. ND pattern of $\text{HfD}_{1.215}$ at 700°C (experiment 1).




Figure S5. Cell parameters and volume of α -Hf phase as a function of overall deuterium content at 250 °C (experiment 2). For cell parameters, error bars (0.001 Å) are commensurate with the symbol size.




Figure S6. ND pattern of $\text{HfD}_{1.92}$ at 300°C (experiment 2).




Figure S7. ND patterns of $\text{HfD}_{0.994}$ sample during heating and cooling where the dotted lines represent the superstructure peaks of the δ' - HfD_{2-x} phase (experiment 3).




Figure S8. Cell parameters and volume of α -Hf as a function of temperature in a sample of initial composition $\text{HfD}_{0.994}$ (experiment 3). For cell parameters, error bars (0.001 \AA) are commensurate with the symbol size.




Figure S9. Displacement parameters of the δ -HfD_{2-x} phase as a function of temperature (experiment 3).




Figure S10. ND pattern of HfD_{0.944} at 830°C (experiment 3).




Figure S11. HfH_{1.5} structure. The left figure shows the structure as determined in the present work. The right figure shows the same structure after an origin shift allowing to compare with the CaF₂ crystal structure.

Table

Table S1. Phase distribution of the hydrogenated and deuterated hafnium powder sample determined *ex situ* by Rietveld refinement of XRD data.

Sample	Hydrogenation/Deuteration temperature	Phase	Percentage (wt%)
HfH_{1.000}	400 °C	δ'-HfD _{2-x}	49 (1)
		γ-HfD	19 (1)
		α-Hf	32 (1)
HfD_{1.001}	400 °C	δ'-HfD _{2-x}	48 (1)
		γ-HfD	18 (1)
		α-Hf	34 (1)
HfD_{0.994}	400 °C (Before PND)	δ'-HfD _{2-x}	58 (1)
		γ-HfD	28 (1)
		α-Hf	14 (1)
	400 °C (After PND)	δ'-HfD _{2-x}	31 (1)
		γ-HfD	34 (1)
		α-Hf	35 (1)