



HAL
open science

PEDOT:PSS/PEO: a melt-processable blend for flexible conductive electrodes?

Caroline Duc, Jérémie Soulestin, Cédric Samuel

► To cite this version:

Caroline Duc, Jérémie Soulestin, Cédric Samuel. PEDOT:PSS/PEO: a melt-processable blend for flexible conductive electrodes?. *Advanced Nano Materials* 2019, Jul 2019, Aveiro, Portugal. hal-04249500

HAL Id: hal-04249500

<https://hal.science/hal-04249500v1>

Submitted on 20 Oct 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Public Domain

PEDOT:PSS/PEO: a melt-processable blend for flexible conductive electrodes?

Caroline Duc^{1,2}, Jérémie Soulestin², Cédric Samuel²

^{1,2}Ecole Nationale Supérieure Mines Telecom Lille Douai, Institut Mines Telecom Lille Douai (IMT Lille Douai),

¹Département Sciences Atmosphériques et Génie de l'Environnement (SAGE), Douai, France

²Département Technologie des Polymères et Composites & Ingénierie Mécanique (TPCIM), Douai, France

INTRODUCTION

Large R&D efforts are currently observed in smart polymer materials with advanced functionalities coupled to additive processing/prototyping concepts such as fused deposition modeling (FDM). In these fields, melt-processable flexible electrodes with high electronic conductivity represents one of the key challenge to address¹. Polymer filled with carbon or metallic nano/micro-objects is currently the unique solution for FDM. However, this route is clearly restricted: low conductivity, high rigidity, narrow processing conditions, extrusion die degradation, etc²...

In this context, the substitution of (nano)fillers by intrinsic conductive polymers such as poly(3,4-ethylene dioxythiophene) : polystyrene sulfonate (PEDOT:PSS) can be of high interests to develop highly-conductive flexible electrodes by FDM (or other prototyping processes)^{3,4}. The objective of this work is to investigate the use of PEDOT:PSS/poly(ethylene oxide) (PEO) blends to develop a melt-processable material for flexible electrodes. Here, we study the impact of PEO content on the electronic conductivity of PEDOT:PSS/PEO blends at various processing stages.

EXPERIMENTAL STUDY

The blends were prepared from aqueous solutions of PEDOT:PSS (Clevios PH1000 HERAEUS), ethylene glycol and PEO (Mv = 200,000, Sigma Aldrich). Solutions were homogenized by stirring and sonication and thin films were then prepared either by (i) drop-casting (DC) (on a hot plate, 70°C for 45 min and 120°C for 1h) or (ii) extrusion/thermocompression (ExTC) (120°C, water evaporation at 70°C before melt processing). Films were post-treated by water or sulfuric acid (96 %) for 5 min at room temperature. Films were gently rinsed 3 times with water and dried in an oven (70°C for 4 h and baked on a hot plate at 120°C for 5 min). The electrical properties of the films were measured by the Van Der Pauw 4-probes technique. Morphologies were revealed by Scanning Electron Microscopy equipped with an Energy Dispersive X-Ray spectrometer (EDX).

RESULTS AND DISCUSSION

The Table 1 shows the impact of PEO and ExTC on the electronic conductivity of as-prepared PEDOT:PSS/PEO blends. A drastic drop of the electronic conductivity is observed after ExTC processing independently of the PEDOT:PSS concentration. The conductivity of the PEDOT:PSS with 60%wt PEO is divided by a factor 2000 after ExTC. These trends can be partly attributed to the

loss of the homogeneous distribution of the PEDOT:PSS in PEO as depicted in Fig. 1.

However, the conductivity of the PEDOT:PSS/PEO blends produced by ExTC can be significantly enhanced by post-treating with sulfuric acid to reach interesting conductivities close to 4 S/cm. This treatment tends to increase the predominance and the organization of the conductive phase.

Processing	90 % wt PEO	60 %wt PEO
Drop-casting (DC)	0,23±0,03	245±72
DC/thermocompression (TC)	0,22±0,04	107±17
ExTC	$(4,5±0,4).10^{-5}$	0,12±0,02
ExTC + water post-treatment	$(6,0±0,7).10^{-4}$	0,18±0,02
ExTC + acidic post-treatment	0,32±0,03	4±2

Table 1 Impact of the PEO content and processing on the conductivity of PEDOT:PSS/PEO blends (conductivity given in S/cm).




Fig. 1 Distribution of sulfur by EDX in PEDOT:PSS/PEO processed by DC (a) and ExTC (b) (Scale bar: 25 μ m).

CONCLUSION

Within this study, PEDOT:PSS/PEO blends were processed by extrusion technologies into thin film and high electronic conductivity could be maintained using an adequate post-treatment. With conductivity similar to some commercial polymer/carbon composites², PEDOT:PSS/PEO blends represents a promising alternative to produce flexible electrodes using conventional and advanced processing technologies of the plastic industry.

REFERENCES

1. S. C. Ligon et al, Chem. Rev. 117, 10212–10290 (2017) / 2. K. Gnanasekaran et. al, Appl. Mater. Today 9, 21–28 (2017) / 3. Q. Wu, Q. et al, Sci. Rep. 7, 41566 (2017) / 4. J. Chang et al, ACS Appl. Mater. Interfaces 10, 19116–19122 (2018).

ACKNOWLEDGMENTS

Authors acknowledge the European Community for the financial support in the frame of the INTERREG V FWVL – BIOHARV project (GoToS3 portofolio).