



HAL
open science

Sustainable Bio&Waste Resources for Construction New insulating construction material from prototypes from biobased and waste resources

Feriel Bacoup

► To cite this version:

Feriel Bacoup. Sustainable Bio&Waste Resources for Construction New insulating construction material from prototypes from biobased and waste resources. 12th conference of biobased materials, May 2019, Cologne, Germany. hal-04255088

HAL Id: hal-04255088

<https://hal.science/hal-04255088>

Submitted on 23 Oct 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Goals of the project

- Study a range of bio-based and waste-based materials poorly valued and locally available in the France (Channel) England area : (i) **Corn-pith**, (ii) **Waste polyester** and (iii) **Wheat straw**.
- Development **low carbon thermal insulation prototypes**: carbon footprint 25% lower than standards insulation materials for the building.
- Testing these prototypes in laboratories and on pilot sites & Evaluate the economical cost and environmental impact of these new materials.
- Elaborate a future **industrialization strategy** and raise awareness among **construction professionals** into using these prototypes

European funding of 1.26M€

→ for a total budget of 1.8M€

- European Regional Development Fund (ERDF)**: the SB&WRC project is part of the "Climate Change and Sustainable Energy" theme of the European Strategy 2020.
- Interreg France (Channel) England**: the program supports the development economic and environmental management of the France-England cross-border area. The SB&WRC project is part of the "Low Carbon Technologies" theme.




Partners and perimeter of the project

A French-British cooperation



Companies English universities French universities Associations



A 32 month project

UniLaSalle Prototype 1: Valorization of Corn-pith in insulating material


- Evaluation and deployment of Prototype 1, **thermal insulation based on corn-pith**, an agricultural byproduct.
- Thermocompression** is used to elaborate particleboard.
- The challenge for the development of this prototype is to **preserve the intrinsic properties of the material** by adding the least natural binder possible while having a **correct mechanical strength** for it to be manipulated.

Thermocompression process



Tests pilots and deployments


Partnership between CoDEM and Unilasalle



Results : 3 panels 1100*1100*25mm³
Technical deployment at Bath University



Maize



SEM of Corn-pith

- 400 000 ton of Maize is available in area of project

Departement for Environment, Food and Rural Affairs, 2016 ; Agreste, 2017
EP 3149085, S. Grass, Method for the production of superabsorbent pellets and/or of a fibrous material from crop residues, patent, (2014)

Performances of prototype

Thermal conductivity
 $\lambda = 0,042 \text{ w}\cdot\text{m}^{-1}\cdot\text{k}^{-1}$

3-point bending :

Handle panel and easy to cut
Maximal bending strength = 0,03 MPa

fire testing

Burning time of panel from corn-pith (30min) is higher than the control (15 seconds)



Prototype 2 : Insulation panel based on bedding waste polyester

- Reuse of textile waste from beddings as thermal insulants in buildings.
- ESITC Caen is in charge of characterizing raw materials, studying the thermal properties of the mini-prototypes designed by the University of Brighton, deploying and characterizing the real-sized prototype 2.
- Prototype 2 is built out of bedding waste polyester associated with wooden panels.

Characteristics of polyester




Waste polyester

Characteristics	Content in water (%)	Absolute bulk density(Kg/m³)	Glass transition temperature (°C)	Fusion temperature(°C)
Valeur	0,14	1474	96	246

Thermal characteristics of mini-prototype 2

- The mini-prototype 2 is 200 x 300 x 100 mm sized. It consists of a wood frame, polyester (insulating material) and a Tyvek coating.



Mini-prototype 2

Temperature (°C)	Thermal Conductivity (W/(m·K))
-10	0,042
0	0,045
10	0,050
20	0,056
30	0,064


Thermal conductivity results measured at different T (°C)

The results of the thermal conductivity of the mini-prototype 2 show the insulation potential of this material.


Tests pilots

A real scale reproduction of this mini-prototype will be produced.

The prototype 2 tested in the rooms climate of the ESITC Caen so to evaluate its thermal performance.



Real size prototype (200x200x40cm) Hot Box system [ASTM C1363]



Prototype 3: Valorization of wheat straw insulation material



strawbales

- Prototype 3 is **wheat straw-based insulation material**. In order to obtain the lowest environmental impact of this material, the project selected strawbales as a model as it requires very few transformations or energy.
- Wall application, insulation only (self-bearing, non-load-bearing), associated with a timber structure for example.
- Dimensions used : 600 x 600 x 100 mm.

Targeted mechanical properties

- No minimal requirement as the prototype is non load-bearing.
- According to EN 826: compressive resistance corresponding to a strain of 10% (high deformation).
- Consider a "not to exceed strain value" for a determined load > value to determine.
- Mechanical performances will be improved with a coating.

Targeted carbon footprint

- A reduction of carbon emissions by 25% in comparison to mineral and glass wool products is targeted.

Targeted thermal performance

- Thermal conductivity: the objective is to reach the value of FASBAa, close to 0.04 W.m⁻¹.K⁻¹, to be competitive with other insulation materials.
- This value can be obtained by changing the orientation of the straw in comparison to its initial orientation (from the baler).

Targeted fire resistance

- UK Building Regulations: 30 minutes (it has been measured 90 minutes in the literatureb).
- Fire resistance will be highly influenced by the coating.

An environmental study of 3 prototypes is in progress



PERSPECTIVES

The 3 prototypes have a very good potential of valorization as thermal insulants materials in buildings. For a possible commercialization of these 3 prototypes, an economic and environmental analysis are in progress by Nomadeis and BATH University respectively.