



HAL
open science

Chlorinated Solvent-Free Living Cationic Ring-Opening Polymerization of Epichlorohydrin Using BF₃•OEt₂ as Co-Initiator: Toward Perfectly Functionalized Poly(epichlorohydrin) Diols

Georgy V Timofeev, Maksim I Hulnik, Irina V Vasilenko, Francois Ganachaud, Guy Jacob, Sergei V. Kostjuk

► To cite this version:

Georgy V Timofeev, Maksim I Hulnik, Irina V Vasilenko, Francois Ganachaud, Guy Jacob, et al.. Chlorinated Solvent-Free Living Cationic Ring-Opening Polymerization of Epichlorohydrin Using BF₃•OEt₂ as Co-Initiator: Toward Perfectly Functionalized Poly(epichlorohydrin) Diols. ACS Applied Polymer Materials, 2023, 5 (8), pp.6549-6561. 10.1021/acsapm.3c01105 . hal-04257779

HAL Id: hal-04257779

<https://hal.science/hal-04257779>

Submitted on 25 Oct 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

This document is confidential and is proprietary to the American Chemical Society and its authors. Do not copy or disclose without written permission. If you have received this item in error, notify the sender and delete all copies.

**Chlorinated Solvent-Free Living Cationic Ring-Opening
Polymerization of Epichlorohydrin Using $\text{BF}_3 \cdot \text{OEt}_2$ as Co-
initiator: Towards Perfectly Functionalized
Poly(epichlorohydrin) Diols**

Journal:	<i>ACS Applied Polymer Materials</i>
Manuscript ID	ap-2023-01105j.R1
Manuscript Type:	Article
Date Submitted by the Author:	n/a
Complete List of Authors:	Timofeev, Georgy; Research Institute for Physical Chemical Problems of the Belarusian State University HULNIK, MAKSIM; Research Institute for Physical Chemical Problems of the Belarusian State University, Vasilenko, Irina; Navukova dasliedcy instytut fizika chimicznych prabliem Bielaruskaha dzjarzaunaha univiersiteta, Ganachaud, Francois; IMP@INSA, IMP UMR 5223 Jacob, Guy; ArianeGroup SAS Kostjuk, Sergei; Bjelaruski dzjarzhawny wnivjersitet, Chemistry Department

SCHOLARONE™
Manuscripts

1
2
3
4
5
6
7 Chlorinated Solvent-Free Living Cationic Ring-
8
9
10
11
12
13 Opening Polymerization of Epichlorohydrin Using
14
15
16
17
18
19 $\text{BF}_3 \cdot \text{OEt}_2$ as Co-initiator: Towards Perfectly
20
21
22
23
24
25 Functionalized Poly(epichlorohydrin) Diols
26
27
28
29
30
31

32
33 *Georgy V. Timofeev,^{†,‡} Maksim I. Hulnik,^{†,‡} Irina V. Vasilenko,[‡] Francois Ganachaud[§], Guy*

34
35
36 *Jacob[⊥] and Sergei V. Kostjuk^{*,†,‡,§,§}*

37
38
39
40 [†] Research Institute for Physical Chemical Problems of the Belarusian State University,

41
42
43
44 14 Leningradskaya st., 220030 Minsk, Belarus

45
46
47
48 [‡]Department of Chemistry, Belarusian State University, Leningradskaya st. 14, 220006, Minsk,

49
50
51
52
53
54
55
56
57
58
59
60
Belarus

§ INSA-Lyon, IMP, CNRS, UMR5223, 20 Boulevard Einstein, F-69621 Villeurbanne, France

1
2
3
4 [‡] ArianeGroup SAS, Centre de Recherche du Bouchet, 9 Rue Lavoisier, Vert le Petit, France
5
6
7

8 [§] Sechenov First Moscow State Medical University, Institute for Regenerative Medicine,
9

10
11 Moscow, 119991, Russia
12
13

14
15 KEYWORDS: Cationic Ring-Opening Polymerization; Living Polymerization;
16
17

18 Poly(epichlorohydrin); Functional Oligomers; Activated Monomer Mechanism; Solid Propellants
19
20
21
22

23
24 ABSTRACT: The cationic ring-opening polymerization of epichlorohydrin co-initiated by
25
26

27 $\text{BF}_3 \cdot \text{Et}_2\text{O}$ has been investigated here. Fast synthesis of pure poly(epichlorohydrin) diols
28
29

30 ($F_n(\text{OH}) \sim 2.0$) with controlled molar mass (M_n up to 4000 g mol^{-1}) and low dispersity ($\mathcal{D} < 1.25$)
31
32

33
34 were performed both in toluene and in bulk. An original approach was developed here, consisting
35
36

37 in first generating *in situ* the initiator through $\text{BF}_3 \cdot \text{Et}_2\text{O}$ -catalyzed reaction of ECH with water,
38
39

40 leading to a mixture of oligomers with better solubility in the reaction medium than conventional
41
42

43 initiators previously used. Then, through a second monomer starved-feed step, polymerization
44
45

46 proceeds exclusively through the activated monomer mechanism, allowing perfect control of the
47
48

49 polymer growth. The developed procedure was successfully upscaled to 100 g of polymer to
50
51

52 validate a future industrial production of PECH, as well as its derivative glycidyl azide polymer
53
54
55
56
57
58
59
60

1
2
3 (GAP), the most important energetic binder for solid propellants. Additionally, a separate study
4
5
6
7 was performed to elucidate the reasons for coloration of the polymer observed in the course of
8
9
10 polymerization and/or under storage.
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

INTRODUCTION

Epichlorohydrin (ECH) homopolymers (PECH) and copolymers represent an important class of functional polymeric materials for wide range applications such as in automotive industry,¹ biomedical field,² or energy storage.^{3,4} PECH is also the starting polymer to prepare glycidyl azide polymer (GAP), the most important energetic binder for solid propellants.^{5,6,7} This polymer is currently intensively used in place of hydroxyl-terminated polybutadiene, since it provides much higher specific impulse and burn rate.⁷ For the preparation of such propellants, hydroxyl-terminated liquid GAP polymer is mixed with inorganic oxidizer and cured by reaction with isocyanates of functionality ≥ 2 . As a result, a three-dimensional cross-linked polyurethane network with elastomeric properties is formed.⁷ To ensure efficient chain extension in parallel to few crosslinking reactions, the functionality in hydroxyl groups of GAP, and thus of synthesized PECH, should be strictly equal to 2.⁸ Also, because of environmental concerns, all fuels used in aviation and aerospace industries should not contain any banned molecules, in particular chlorinated solvents.

ECH can be polymerized via coordinative,^{9,10,11,12,13,14} anionic^{4,15,16,17} and cationic^{18,19,20,21,22,23,24,25,26,27,28,29,30} mechanisms. Catalytic ring-opening polymerization (ROP) of


1
2
3 ECH was originally discovered by Vandenberg.^{1,9,10} Vandenberg's catalyst is prepared by mixing
4
5
6
7 1 eq. of trialkyl aluminum with 0.5 eq. of H₂O and 0.5 eq. of acetylacetone to generate, as it was
8
9
10 proposed recently, a bis(μ -oxo)dialkylaluminum active species.³¹ It allows synthesizing high
11
12
13 molar mass PECH ($M_n > 50,000 \text{ g mol}^{-1}$) often with isotactic configuration of a polymer chain.
14
15
16 Many other monometallic^{12,13,14} and bimetallic³² multicomponent catalytic systems for the
17
18
19 synthesis of high molar mass PECH were later reported. Despite of the possibility to prepare high
20
21
22 molar mass and often stereoregular (co)polymers of ECH, catalytic ROP of ECH suffers from
23
24
25 some difficulties in controlling the molar mass and chain-end functionality. In some instances also,
26
27
28 incomplete monomer conversion was observed.^{9,10,11,12,13,14,31,32} It was reported recently about the
29
30
31 catalytic regioselective polymerization of ECH using Zn-Co(III) double metal cyanide complex,
32
33
34 which favors formation predominantly of PECH diols, albeit of low molar masses ($M_n < 3,500 \text{ g}$
35
36
37 mol^{-1}) and relatively high dispersity ($\mathcal{D} > 1.5$) with semi-crystalline properties (solid-liquid
38
39
40 transition around 100 °C).³³
41
42
43
44
45
46

47 Living anionic ROP of ECH was achieved by Carlotti et al.^{15,16} using Oct₄NBr/^tBu₃Al initiating
48
49
50 system. This initiating system allows preparing well-defined heterofunctional PECH with
51
52
53 controlled molar masses (up to $M_n = 80,000 \text{ g mol}^{-1}$) and low dispersity ($\mathcal{D} < 1.23$) as well as random
54
55
56
57
58
59
60

1
2
3 and block copolymers of ECH and propylene oxide.^{15,16} Triethylaluminum adduct of (2-
4
5
6
7 dibenzylamino)ethoxydiethylaluminum induces slow living anionic ROP of ECH (several days to
8
9
10 complete conversion) affording heterofunctional PECHs with low dispersity ($\mathcal{D} < 1.3$) and molar
11
12
13 masses ranging between 14 and 44 kg mol⁻¹.³⁴ Note that direct living anionic ROP of glycidyl
14
15
16 azide was recently successfully performed using triethyl borane in conjunction with Bu₄NBr as an
17
18
19 initiator, to generate heterofunctional GAP.³⁵
20
21
22
23

24 Clearly, PECHs synthesized by catalytic or anionic means are not ideal tools for the preparation
25
26
27 of GAP, principally because of the lack of desired functionality. In stark contrast, the cationic ROP
28
29
30 of ECH in conjunction with a molecular diol as an initiator results systematically in dihydroxy-
31
32
33 terminated PECH.^{18,19,20,21,22,23,24,25,26,27,28,29} Two different mechanisms, i.e. activated chain end
34
35
36 (ACE) and activated monomer (AM) mechanisms, simultaneously operate during the ROP of
37
38
39 ECH, depending on the reaction conditions (Scheme 1).¹⁸ In ACE mechanism, the active
40
41
42 propagating species are oxonium ions located at the chain ends and propagation occurs through
43
44
45 the addition of neutral monomer molecules to these oxonium ions (Scheme 1a). Since the main
46
47
48 chain (or terminal) oxygen atoms can also attack the propagating oxonium ion, macrocyclic by-
49
50
51
52
53
54
55
56
57
58
59
60

products (Scheme 1a) are generated that finally lead to ill-defined mixture of linear PECH diol and cyclic oligomers.



Scheme 1. ACE (a) and (b) AM Mechanisms.

1
2
3
4 In contrast to ACE mechanism, in AM mechanism, the chain end is neutral and propagation
5
6
7 occurs through the nucleophilic attack of the hydroxyl group at the chain end onto activated (i.e.
8
9
10 protonated) monomer. Since cyclization is not possible in the AM mechanism, pure PECH diols
11
12
13 form under these conditions. ACE mechanism is prominent in conditions where i) the
14
15
16 concentration of co-initiator (Lewis acid or Brønsted acid) is higher than the concentration of
17
18
19 initiator (alcohols or other protogenic species) and ii) the concentration of monomer is much higher
20
21
22 than the content of initiator. Therefore, to shift the propagation from ACE to AM mechanism and
23
24
25 to suppress the formation of cyclic oligomers, the cationic ROP of ECH should proceed at low
26
27
28 instantaneous concentration of monomer.¹⁸
29
30
31

32
33
34 Cationic ROP of ECH was already largely described in the literature, using catalytic systems
35
36
37 based on such Lewis acids as $\text{BF}_3 \cdot \text{Et}_2\text{O}$,^{18,19,20,21,22,23,24,25,26} SnCl_4 ,²⁷ $\text{Et}_3\text{O}^+\text{PF}_6^-$,²⁸ as well as
38
39
40 1,4-butanediyl ditriflate²⁹ and some acidic clays.³⁰ The ROP of ECH in the presence of acidic clays
41
42
43 was done in bulk, so that the resulting polymer was characterized by low M_n , broad multimodal
44
45
46 molar mass distribution and contains a large fraction of cyclic by-products.³⁰ 1,4-Butanediyl
47
48
49 ditriflate initiates slow polymerization of ECH to afford the expected PECH diol with M_n from
50
51
52 3400 to 15,000 g mol^{-1} and relatively high dispersity ($\text{Đ} \sim 1.5$) at moderate yields (20–50%).²⁹
53
54
55
56
57
58
59
60

1
2
3
4 Triethyloxonium hexafluorophosphate ($\text{Et}_3\text{O}^+\text{PF}_6^-$) in conjunction with ethylene glycol allowed to
5
6
7 synthesize well-defined PECH diol ($\bar{D} \sim 1.3$) of low molar masses ($M_n < 1,000 \text{ g mol}^{-1}$).²⁸
8
9

10 The comparison of efficiency of $\text{BF}_3 \cdot \text{Et}_2\text{O}$ and SnCl_4 in the cationic ROP of ECH revealed that
11
12
13 $\text{BF}_3 \cdot \text{Et}_2\text{O}$ afforded PECH with higher functionality in chain-end hydroxyl groups and lower
14
15
16 dispersity, even if the corresponding polymerizations were performed at slightly different
17
18
19 ECH/1,4-butanediol (BD) ratios.²⁷ The best control of the synthesis of PECH diols free of cycles
20
21
22 with controlled molar mass ($M_n \leq 2500 \text{ g mol}^{-1}$) and low dispersity ($\bar{D} < 1.20$) was published by
23
24
25 Penczek et al. in 1991.¹⁸ They used an ethylene glycol (EG)/ $\text{BF}_3 \cdot \text{Et}_2\text{O}$ initiating system in CH_2Cl_2
26
27
28 or in bulk and proceeded by slow addition of ECH (48 h) at 20 °C. Since then, many other diols
29
30
31 such as BD,^{20,21,22,27} diethylene glycol,^{21,23} 1,2-propanediol,²³ hexylene diol,²³
32
33
34 1,4-cyclohexanediol²³ and even polyethylene glycols ($M_n = 200 - 600 \text{ g mol}^{-1}$)²⁴ were used as
35
36
37 initiators of cationic ROP of ECH in conjunction with $\text{BF}_3 \cdot \text{Et}_2\text{O}$, mainly at 0 °C. However, PECHs
38
39
40 obtained with these different initiators are often characterized by relatively high dispersity
41
42
43 ($\bar{D} = 1.40 - 2.15$) and a functionality lower than 2.0; moreover, their SEC traces display shoulder
44
45
46 or even a separate peak in the low molar mass region, indicating the formation of cyclic by-
47
48
49 products.^{20,21,22,23,24,25,26,27} The main differences between these works and Penczek's one¹⁸ lie in
50
51
52
53
54
55
56
57
58
59
60

1
2
3 the nature of initiator, the polymerization temperature as well as the initiator to co-initiator ratio
4
5
6
7 ($[\text{EG}]/[\text{BF}_3 \cdot \text{Et}_2\text{O}] \sim 50$).
8
9

10 Recently, Kim et al.^{20,21} observed an induction period during ROP of ECH with BD/ $\text{BF}_3 \cdot \text{Et}_2\text{O}$
11
12
13 initiating system ($[\text{BD}]/[\text{BF}_3 \cdot \text{Et}_2\text{O}] = 1 - 5$) at temperatures below 10 °C, followed by highly
14
15
16 exothermic polymerization raising significantly the reaction temperature. Such induction period
17
18
19 was rationally attributed to the poor solubility of initiator (BD) in dichloromethane at low reaction
20
21
22 temperature. Interestingly, the decrease of $\text{BF}_3 \cdot \text{Et}_2\text{O}$ concentration (below $[\text{BD}]/[\text{BF}_3 \cdot \text{Et}_2\text{O}] = 2$)
23
24
25 resulted in an increase of exothermicity during the polymerization, after the induction period
26
27
28
29
30
31 ceased.^{20,21}
32
33

34 The main purpose of this study was originally to better understand the mechanisms of ECH ROP
35
36
37 to find conditions avoiding the use of chlorinated solvents. In this contribution, we report detailed
38
39
40 mechanistic study of $\text{BF}_3 \cdot \text{Et}_2\text{O}$ -catalyzed ROP of ECH in toluene solution and bulk conditions. A
41
42
43 simple and efficient initiating system was developed for fast synthesis of perfectly-functionalized
44
45
46 PECH diols ($F_n(\text{OH}) \sim 2.0$) of controlled molar masses (M_n up to 4000 g mol⁻¹) and low dispersity
47
48
49 ($\text{Đ} < 1.25$). Such procedure was easily upscaled to 100 g of polymer. Additionally, a detailed
50
51
52
53
54 characterization of the synthesized PECHs was performed with the aim to elucidate the reasons
55
56
57
58
59
60

1
2
3 leading to the coloration of the polymers during the storage of non-purified samples. Coloration in
4
5
6
7 the course of polymerization was observed before by some authors,^{18,20,21,22} but never explained.
8
9
10
11
12

13 **EXPERIMENTAL SECTION**

14 **Materials and methods**

15
16
17
18
19
20 Epichlorohydrin (Aldrich, $\geq 99\%$), 1,4-butanediol (BD, Aldrich, 99%), 3-chloro-1,2-
21
22
23
24 propanediol (CLPD, Aldrich, 99%) were dried with CaH_2 and then distilled from CaH_2 under
25
26
27 reduced pressure. Boron trifluoride diethyl etherate ($\text{BF}_3 \cdot \text{Et}_2\text{O}$, Merck, for synthesis) was distilled
28
29
30 under reduced pressure. Toluene (Aldrich, 98%) and CH_2Cl_2 (Ecos-1, reagent grade) were treated
31
32
33
34 with concentrated H_2SO_4 (Ecos-1, technical grade), sodium carbonate solution (Ecos-1, reagent
35
36
37 grade), distilled water until reaching neutral pH, dried over CaCl_2 (Sigma-Aldrich, anhydrous,
38
39
40 $\geq 97\%$), refluxed and distilled over sodium (Sigma-Aldrich, $\geq 99\%$) (for experiments done in
41
42
43
44 toluene) and CaH_2 (Sigma-Aldrich, $\geq 97\%$) (for experiments done in CH_2Cl_2), respectively.
45
46
47
48 Nitromethane (Aldrich, $\geq 95\%$) was dried and distilled over CaH_2 . Acetonitrile (Carlo Erba,
49
50
51 99.5%) was refluxed with P_2O_5 (Ecos-1, reagent grade), distilled over P_2O_5 and finally distilled
52
53
54 under argon atmosphere over CaH_2 . In some experiments, monomer, solvent (toluene) and
55
56
57
58
59
60

1
2
3
4 $\text{BF}_3 \cdot \text{Et}_2\text{O}$ were used without any purification (*vide infra*). CDCl_3 (Sigma-Aldrich, $\geq 99.8\%$),
5
6
7 dimethyl sulfoxide- d_6 (Sigma-Aldrich, 99.9%), tetrahydrofuran (anhydrous, Sigma-Aldrich,
8
9
10 $\geq 99.9\%$), trifluoroacetic anhydride (Aldrich, $\geq 99\%$), 4,4'-methylenebisphenyl isocyanate
11
12
13 (Sigma-Aldrich, 98%), 1,8,9-anthracenetriol or dithranol (Alfa Aesar, 97+%) and sodium iodide
14
15
16
17 (Aldrich, 99.9%) were used as received.
18
19

20
21 Size exclusion chromatography (SEC) was performed on an Agilent 1200 apparatus with
22
23 Nucleogel GPC LM-5, 300/7,7 column and one precolumn (PL gel 5 μm guard) and an Ultimate
24
25
26
27 3000 Thermo Scientific apparatus with Agilent PL gel 5 μm MIXED-C column and one precolumn
28
29
30 (PL gel 5 μm guard 50 \times 7.5mm) thermostated at 30°C. The detection was achieved with a
31
32
33
34 differential refractometer thermostated at 35°C. Tetrahydrofuran was eluted at a flow rate of
35
36
37 1.0 mL/min. The calculations of molar mass and dispersity are based on polystyrene standards
38
39
40 (Polymer Labs, Germany).
41
42
43

44 ^1H NMR spectra were recorded in CDCl_3 at 25°C on a Bruker AC-500 spectrometer. ^{13}C and
45
46
47 ^{13}C DEPT-135 NMR spectra were recorded in DMSO-d_6 at 25°C on a Bruker AC-500
48
49
50 spectrometer. A pulse delay of 10 s was given for recording the ^{13}C NMR spectra and about
51
52
53
54 15000 scans were accumulated.
55
56
57
58
59
60

1
2
3 MALDI-TOF MS was performed on a Voyager mass spectrometer (AB Sciex) equipped with a
4
5
6 pulsed N₂ laser (337 nm) and a time-delayed extracted ion source. Spectra were recorded in the
7
8
9
10 positive-ion mode using a reflectron and with an accelerating voltage of 20 kV. Solutions of
11
12
13 dithranol (20 mg/mL), polymer sample (10 mg/mL) and sodium iodide (10 mg/mL) were prepared
14
15
16
17 in THF. These solutions were then mixed in the ratio of matrix/sample/cationizing salt = 10:2:1
18
19
20 and 0.5 µL aliquots were applied to a MALDI sample target for analysis. The instrument was
21
22
23 calibrated externally using poly(ethylene glycol) standards of appropriate molar masses. All mass-
24
25
26 to-charge ratios (m/z) quoted are monoisotopic, i.e. they include the most abundant isotopes of the
27
28
29 elements present in the corresponding ion.
30
31
32

33
34 The content of H₂O in some reactants was determined by a semi-micro method on an automatic
35
36
37 titrator Titrino 848/877 using the Karl-Fischer method. Determination of the hydroxyl number of
38
39
40 PECH samples was performed via acid-base titration according to ASTM D4274 -16.
41
42

43 **Polymerization procedures**

44
45
46
47 Polymerizations were carried out in a 50 mL three-necked flask, connected with a vacuum
48
49
50 system, equipped with a magnetic (solution polymerization) or mechanical (bulk polymerization)
51
52
53 stirrer, a thermocouple to control the reaction temperature and a rubber septum to introduce the
54
55
56
57
58
59
60

1
2
3 reagents. Before polymerization, the flask was systematically vacuumed and filled with argon
4
5
6
7 three times.
8
9

10 In a typical polymerization experiment in toluene with *in situ* prepared initiator, the flask was
11
12
13 charged with 0.05 mL of H₂O, 0.034 mL of BF₃•Et₂O and 0.43 mL of ECH
14
15
16 (ECH/H₂O = 2/1 mol/mol) and plunged in a water bath at 20 °C. This heterogeneous mixture was
17
18
19 stirred for 1 – 1.5 h until it became a homogeneous transparent viscous liquid. Then 17.3 mL of
20
21
22
23 toluene/ECH mixture (1/2 v/v) was added by a syringe pump at a rate of 2.6 mL/h (in respect to
24
25
26 pure ECH) for 4.5 h. After the completion of monomer addition, the mixture was stirred for an
27
28
29 additional 2.5 hours. The reaction was then quenched by addition of distilled water. The reaction
30
31
32
33 mixture was washed with sodium bicarbonate solution (5 wt.%), then several times with distilled
34
35
36 water until the washing water comes back to neutral pH. The solvent was evaporated using a rotary
37
38
39 evaporator under reduced pressure and the resulting polymer was dried in vacuum at 60°C. The
40
41
42 monomer conversion was determined gravimetrically.
43
44
45
46

47 Polymerization of epichlorohydrin in bulk with *in situ* prepared initiator was carried as followed.
48
49
50 The flask was charged with 0.05 mL of H₂O, 0.023 mL of BF₃•Et₂O and 0.46 mL of ECH
51
52
53 (ECH/H₂O = 2/1 mol/mol) and placed in a water bath at 20 °C. This heterogeneous mixture was
54
55
56
57
58
59
60

1
2
3 stirred for 1 – 1.5 h until forming a transparent viscous liquid. Then the water bath was heated to
4
5
6
7 40 °C and 5.4 mL of ECH was added via a syringe pump at a rate of 1 mL/h during 5.4 h. After
8
9
10 monomer feeding, the mixture was stirred for one additional hour. Finally, the polymer was dried
11
12
13
14 in vacuum at 60 °C. The monomer conversion was determined gravimetrically.
15

16 **Chain-end titration**

17
18
19
20 The number average functionality on hydroxyl groups (F_n) was calculated as the ratio of molar
21
22
23 mass determined by size-exclusion chromatography to molar mass calculated from ^1H NMR
24
25
26
27 spectrum based on the content of hydroxyl groups (Figure S1), which is sensitive to the presence
28
29
30 of cyclic by-products.
31

32
33
34 The molar mass as well as the content of secondary and primary hydroxyl groups at the chain
35
36
37 ends were determined from ^1H NMR spectra of synthesized PECHs (Figure S1). Because of the
38
39
40 overlapping of protons of methylene ($-\text{CH}_2-\text{OH}$) and methine ($-\text{CH}(\text{CH}_2\text{Cl})-\text{OH}$)
41
42
43 end-groups with the signals of main chain protons, the hydroxyl end-groups were converted into
44
45
46 ester end-groups by reaction with excess of trifluoroacetic anhydride.¹⁸ This reaction was
47
48
49
50 performed directly in the NMR tube containing the solution of PECH in CDCl_3 . The content of
51
52
53
54
55
56
57
58
59
60

1
2
3 secondary hydroxyl groups was calculated from ^1H NMR spectrum (Figure S1) according to the
4
5
6
7 following equation:

$$\% \text{ secondary OH} = \frac{[(d)]}{[(d) + [(d')/2]]} \quad (1)$$

11
12
13 All PECH samples synthesized in this work were found to bear mainly secondary terminal
14
15
16
17 hydroxyl groups (≥ 96 mol%).

18
19
20 The molar mass of the PECHs ($M_{n,\text{NMR}}$) was calculated from ^1H NMR spectrum (Figure S1)
21
22
23 according to equation presented below:

$$M_{n,\text{NMR}} = \left[\frac{[(a+b+c)/5]}{[(d')/4 + [(d)/2]} \right] \times 92.5 + M_I \quad (2)$$

24
25
26
27
28
29
30 where M_I is the molar mass of the fragment of initiator introduced in the polymer chain, if any
31
32
33
34 (*vide infra*).

35
36
37 Since $M_{n,\text{SEC}}$ is calculated against polystyrene standards, it is not absolute and must be corrected.
38
39
40 To do so, some polymers known to be perfectly difunctional and not containing any macrocycles
41
42
43 (confirmed by MALDI TOF MS for certain samples) were titrated to calculate their hydroxyl
44
45
46
47 number and deduce their absolute molar mass (Table S1). The obtained values ($M_{n,\text{titration}}$) were
48
49
50 close to M_n determined by ^1H NMR according to chain-end versus main chain proton integration
51
52
53 (eq. (2)), thus confirming the perfect functionality of analyzed samples. Finally, $M_{n,\text{SEC}}$ was plotted
54
55
56
57
58
59
60

1
2
3
4 against $M_{n,titration}$ and a correction coefficient of 0.93 was deduced from this plot (Table S1, Figure
5
6
7 S2). Considering the fact that molar masses determined by ^1H NMR spectroscopy are sensitive to
8
9
10 the presence of macrocyclic chains, that have no end-groups, the difference between $M_{n,NMR}$ and
11
12
13 corrected $M_{n,SEC}$ values were later used for the calculation of the number average functionality on
14
15
16 hydroxyl end groups ($F_n(\text{OH})$) without the need for chemical titration. Then, in the following, the
17
18
19 number average functionality of the chains was calculated as $F_n = [M_n(\text{SEC})/M_n(\text{NMR})] \times 2 \times 0.93$.
20
21
22
23
24
25
26

27 RESULTS AND DISCUSSION

28 29 30 Solution Polymerization

31 32 33 *Preliminary experiments with butanediol as an initiator*

34
35
36
37 An initial series of experiments was conducted using 1,4-butanediol/ $\text{BF}_3 \cdot \text{Et}_2\text{O}$ initiating system
38
39
40 in conditions similar to those reported by Kim et al, i.e. $[\text{BD}]/[\text{BF}_3 \cdot \text{Et}_2\text{O}] = 6:1$, temperature: 0°C
41
42
43 for a theoretical M_n of $\approx 2500 \text{ g mol}^{-1}$.^{20,21} Firstly, the effect of solvents of different polarities such
44
45
46 as CH_2Cl_2 , toluene, acetonitrile and nitromethane on the cationic ROP of ECH was briefly
47
48
49 investigated. Toluene was selected as the most suited substitute to CH_2Cl_2 , since this solvent led
50
51
52
53 to polymers with the closest properties from CH_2Cl_2 -prepared ones (Table S2). Still here, PECHs
54
55
56
57
58
59
60

1
2
3 synthesized in these two solvents showed bimodal molar mass distribution (MWD) (Figure S3)
4
5
6 and the functionality at the chain end was typically much lower than expected for an ideal
7
8
9 telechelic hydroxyl-terminated poly(epichlorohydrin) ($F_n \approx 1$ against an expected value of 2, Table
10
11
12 S2). Both the presence of a low molar mass peak in SEC curves and the observed low number
13
14
15 average functionality on hydroxyl groups indicate that ACE mechanism competes with AM one,
16
17
18 thus leading to the formation of macrocyclic by-products.^{18,19,20,21,22,23,24,25} We also looked at the
19
20
21 effect of temperature of reaction: raising the temperature from 0 to 30 °C increases the solubility
22
23
24 of initiator (BD) as well as its complex with $\text{BF}_3 \cdot \text{Et}_2\text{O}$ in toluene (Figure S4), as also reported by
25
26
27 Kim et al.; this in turn allowed preparing better-defined PECH with improved MWD and
28
29
30 functionality (Table S3, Figure S5).^{20,21,22}
31
32
33
34
35
36

37 Next, the ratio $[\text{BD}]/[\text{BF}_3 \cdot \text{Et}_2\text{O}]$ was systematically decreased (Table S4). In all cases, an
38
39
40 induction period of several hours followed by exotherms of different magnitudes were observed.
41
42
43 The induction period can be ascribed to slow initiation and/or polymerization of ECH due to the
44
45
46 poor solubility of initiator (BD) and/or its complex with $\text{BF}_3 \cdot \text{Et}_2\text{O}$ in toluene (Figure S4). The
47
48
49 accumulation of monomer in the reaction mixture then results in a significant runaway of
50
51
52
53 polymerization after BD has been fully consumed, responsible for the exotherm. Again, the ACE
54
55
56
57
58
59
60

1
2
3 mechanism operating here (Scheme 1) decreases the functionality and increases the dispersity of
4
5
6 synthesized PECH chains (Table S4). This loss of control is particularly obvious when decreasing
7
8
9
10 $[\text{BF}_3 \cdot \text{Et}_2\text{O}]/[\text{BD}]$ down to 1/25 or less. In addition, the slower polymerization at low $\text{BF}_3 \cdot \text{Et}_2\text{O}$
11
12
13 concentration led to incomplete monomer conversion at $[\text{BF}_3 \cdot \text{Et}_2\text{O}]/[\text{BD}] < 1/25$ (Table S4).
14
15
16

17 In order to gain deeper insight into the mechanism of ROP of ECH with $\text{BD}/\text{BF}_3 \cdot \text{Et}_2\text{O}$ initiating
18
19 system, PECH synthesized under the best conditions at this stage (run S17, Table S4) was
20
21 characterized by MALDI TOF MS. The spectrum shows the presence of several populations of
22
23 polymer chains of different structures in low and high molar mass regions, respectively (Figure 1,
24
25 full spectrum in Figure S6). The major population of chains in the low molar mass region
26
27 corresponds to the diol $\text{HO}-(\text{ECH})_n-\text{OH}$ cationized by Na^+ (e.g. for $n = 15$,
28
29 $m/z = 1428.8 \text{ g mol}^{-1}$), i.e. which does not embed any fragment of initiator in the polymer chain
30
31 (Figure 1a). The small population with slightly lower molar mass (-18 m/z) can be assigned to
32
33 cyclic chains $(\text{ECH})_n$ (e.g. for $n = 15$, $m/z = 1410.9 \text{ g mol}^{-1}$). The two minor peaks that appear in
34
35 the low molar mass region at -37 m/z and -69 m/z in Figure 1a correspond to $\text{HO}-(\text{ECH})_n-\text{OH}$
36
37 oligomers that lost one and two HCl molecules per chain, respectively (*vide infra*) (Figure 1a).
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60




Figure 1. Zooms of (a) low molar mass and (b) high molar mass parts of MALDI TOF MS spectrum of PECH synthesized with BD/BF₃OEt₂ initiating system (run S17, Table S4). Full spectrum is given in Figure S6.

In contrast, two major populations of chains of almost equal intensities are present in the high molar mass region of the MALDI TOF MS spectrum (Figure 1b). One family of chains again corresponds to HO-(ECH)_n-OH cationized by Na⁺ (for n = 25, m/z = 2354.5 g mol⁻¹). Another population (m/z = 2334.7 g mol⁻¹) could be assigned either to cyclic polymer chains (ECH)_n or PECH diol chains containing one fragment of initiator, i.e. HO-(ECH)_k-BD-(ECH)_m-OH: the peak difference between these two structures is only 2 m/z. The formation of cyclic chains of high

1
2
3 molar mass is unlikely, while the presence of 1,4-butanediol fragment in a polymer chain was
4
5
6 confirmed by ^1H NMR on the PECH sample reacted with trifluoroacetic anhydride (Figure S7).
7
8
9
10 Indeed, ^1H NMR spectrum shows a clear signal at 1.67 ppm assigned to the protons of the
11
12
13 $-\text{CH}_2-$ group of BD fragment in the polymer chain. Moreover, the molar mass calculated from ^1H
14
15
16 NMR spectrum assuming one initiator fragment in the polymer chain ($M_n=2960 \text{ g mol}^{-1}$) is higher
17
18
19 than the theoretical one ($M_n=2470 \text{ g mol}^{-1}$), the latter which is higher than the one based on the
20
21
22 terminal hydroxyl groups ($M_n=2370 \text{ g mol}^{-1}$). These data confirm the presence of a mix of both
23
24
25
26 types of poly(epichlorohydrin) diols in the sample, i.e. with and without the initiator fragment
27
28
29 inside the polymer chain.
30
31
32

33
34 One reasonable explanation for the presence of a significant fraction of $\text{HO}-(\text{ECH})_n-\text{OH}$ chains
35
36
37 could be the competition brought by adventitious water, as efficient an initiator as BD. Indeed, as
38
39
40 determined by Karl Fisher titration, the content of H_2O in BD (28.2 mM) and in monomer
41
42
43 (9.2 mM) is quite high, even after drying with CaH_2 , and anyhow much higher than in toluene
44
45
46 (2.9 mM). In addition, the presence of only $\text{HO}-(\text{ECH})_n-\text{OH}$ chains in the low molar mass region
47
48
49 indicates that at least part of adventitious water comes from the monomer slowly added into the
50
51
52
53 reactor during the polymerization.
54
55
56
57
58
59
60

1
2
3
4 Using toluene as a solvent and applying temperatures at 20 °C or above seem to give as good
5
6
7 conditions for cationic ROP of ECH with BD as initiator as reported before in CH₂Cl₂. However,
8
9
10 the use of BD/BF₃•Et₂O initiating system still shows several limitations: (i) a high amount of
11
12
13 BF₃•Et₂O is required to moderate the polymerization exotherm (BD/BF₃•Et₂O =1/6);
14
15
16
17 (ii) synthesized PECHs exhibit relatively high dispersity ($\bar{M}_w/\bar{M}_n=1.3 - 1.4$) and too low a functionality
18
19
20 ($F_n(\text{OH})=1.80-1.90$); (iii) competitive initiation via adventitious H₂O prevents the synthesis of
21
22
23 well-defined PECH diols; and finally (iv) the induction period followed by the sharp, uncontrolled
24
25
26 increase of the temperature are detrimental to industrial application.
27
28
29
30
31
32

33 *Living polymerization of ECH in toluene*

34
35
36
37 In the following, we decided to use H₂O as the initiator of BF₃•Et₂O-catalyzed cationic ROP of
38
39
40 ECH. A first test in presence of adventitious H₂O as initiator has shown that the polymerization is
41
42
43 slow because of the relatively low concentration of initiator. This led to an accumulation of
44
45
46 monomer in the medium during the starved addition and promoted the ACE mechanism,
47
48
49 generating predominantly low molar mass macrocyclic poly(epichlorohydrin)s (Table 1, Table S5,
50
51
52 Figure S8). Although it is out of the scope of the present study, this method could be considered
53
54
55
56
57
58
59
60

as a cheaper and more efficient alternative to $B(C_6F_5)_3$ -catalyzed synthesis of macrocyclic polyethers.³⁶

Table 1. Effect of the Type of Initiator (I) on the $BF_3 \cdot Et_2O$ -Catalyzed Cationic ROP of Epichlorohydrin.^a


run	initiator ^b	T_{max} (°C)	conv. (%)	$M_{n,theo}^c$ (g mol ⁻¹)	$M_{n,NMR}$ (g mol ⁻¹)	$M_{n,SEC}$ (g mol ⁻¹)	\bar{D}	$F_n(OH)^d$
1 ^e	none	25	19	–	2790	630	1.51	0.43
2	H ₂ O	25	99	2475	2380	2510	1.16	2.00
3	CLPD	25	94	2350	2340	2370	1.20	1.98
4	BD	74	92	2300	1980	1940	1.32	1.86

^a Conditions: $[ECH]/[I] = 26$; $[BF_3 \cdot Et_2O]/[I] = 1/15$; $T = 25$ °C; $ECH/toluene = 1/1$ v/v; $V(ECH) = 12.7$ mL; time = 7 h. Rate of monomer addition (in respect to pure monomer): 2.5 mL/h; ^b Abbreviations: BD: butanediol; CLPD: 3-chloro-1,2-propanediol; ^c Theoretical M_n calculated as $M_n = [ECH]/[initiator] \times 92.5 \times conv.$; ^d Number average functionality at the chain end determined as $F_n = ([M_n(SEC)/M_n(NMR)] \times 2 \times 0.93)$; ^e Reaction time: 4.5 h; $V(ECH) = 3.95$ mL; $ECH/toluene = 2/1$ v/v; $[ECH]/[BF_3 \cdot Et_2O] = 623$. Rate of monomer addition (with respect to pure monomer): 1.5 mL/h.

Then, a precise amount of H₂O was added to the polymerization system. In this case, the polymerization proceeded in two stages: (i) *in situ* preparation of initiator in aqueous suspension (ECH/H₂O from 1.5:1 to 1.05:1 mol/mol) (1.5 – 4h) followed by (ii) slow addition of

1
2
3 monomer/toluene mixture (rate of addition: 2.5 mL/h, ~ 5 h). The chosen molar ratio of ECH to
4
5
6 water is crucial and should be well below 1.5 to control the temperature during *in situ* initiator
7
8
9 preparation (Table S6), especially in a view of a scale up (*vide infra*). During this stage, a mixture
10
11
12 of CLPD, the monoadduct of ECH with water, and ECH oligomers are generated, the content of
13
14
15 the former increasing with decreasing ECH/H₂O ratio (Figure S9). Note that for successful *in situ*
16
17
18 initiator preparation, ECH should be added into the system just after premixing of BF₃•Et₂O with
19
20
21 water. Indeed, postponing the monomer addition to 4.5 h resulted in significant slowing down of
22
23
24 the polymerization (Table S7), most probably, because of partial hydrolysis of BF₃ in aqueous
25
26
27 environment, as we showed it in a previous study.³⁷ In ideal conditions, H₂O/BF₃•Et₂O initiating
28
29
30 system allows synthesizing well-defined PECH (M_n ≈ 2500 g mol⁻¹) of low dispersity (Đ ≤ 1.2)
31
32
33 and perfect chain-end functionality (F_n(OH) ≈ 2.0) without any visible change in the reaction
34
35
36 temperature (Table 1). Similar results in terms of control of M_n, dispersity and functionality were
37
38
39 obtained introducing directly commercial CLPD as the initiator whereas, in strong contrast, BD
40
41
42 initiator led to an induction period accompanied by a high reaction exotherm in the same reaction
43
44
45 conditions (Table 1).
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

The living nature of the polymerization was then investigated by building M_n and \mathcal{D} vs. $[M]/[I]$ plots (Figure 2a). The molar mass increases in direct proportion to $[M]/[I]$ ratio and a good correlation between theoretical and experimental values of M_n (both determined by SEC and ^1H NMR spectroscopy) is observed up to $M_n \approx 3500 \text{ g mol}^{-1}$ (Figure 2a).



1
2
3
4 **Figure 2.** (a) M_n and \bar{D} vs. $[M]/[I]$ plot, (b) SEC traces at different $[M]/[I]$ ratios for cationic ROP
5
6
7 of ECH with $H_2O/BF_3 \cdot Et_2O$ initiating system (see Table S8 for detailed experimental conditions).
8
9
10 (c) Fragment of MALDI TOF MS spectrum of PECH ($M_n=2510 \text{ g mol}^{-1}$; $\bar{D}=1.16$) synthesized
11
12
13 with $H_2O/BF_3 \cdot Et_2O$ initiating system in toluene (run 2, Table 1). Series of peaks are mainly
14
15
16 separated either by 92.5 or 94.5 m/z depending on the majority of stable chlorine isotopes Cl^{35} and
17
18
19
20 Cl^{37} the ECH units contains, respectively.³³
21
22
23

24 Some deviation from the theoretical line was noted at higher molar masses because of
25
26
27 competitive initiation of polymerization by water supplied continuously with the monomer; severe
28
29
30 drying of reactant by molecular sieves increased to some extent the molar mass of synthesized
31
32
33 polymers (see Table S8). The dispersity of synthesized poly(epichlorohydrin)s only slightly
34
35
36 increased with increasing $[M]/[I]$ ratio (Figure 2a, Table S8), while SEC traces shifted towards
37
38
39 larger molar masses as $[M]/[I]$ ratio increased (Figure 2b). In addition, the number average
40
41
42 functionality of hydroxyl group was measured close to 2 and did not depend on $[M]/[I]$ ratio for
43
44
45 all ratios studied (Table S8). These results indicate that cationic ROP of ECH with $H_2O/BF_3 \cdot Et_2O$
46
47
48 initiating system proceeds in a living fashion, allowing synthesizing fully functionalized
49
50
51
52 poly(epichlorohydrin) diols without visible traces of macrocyclic side compounds.
53
54
55
56
57
58
59
60

MALDI TOF MS analysis of PECH samples of different molar masses was performed to confirm the exclusive presence of PECH diols (two full spectra in Figure S10, zoom on one spectrum in Figure 2c). The major population of chains corresponds to HO-(ECH)_n-OH cationized by Na⁺. Similarly to previous MALDI TOF MS spectrum (Figure 1), the two other minor populations were assigned to HO-(ECH)_n-OH that lost one or two HCl molecules per chain. No signals of macrocyclic PECH chains (ECH)_n were tracked here (Figure 2c and Figure S10).

The preparation of pure PECH diol was finally confirmed by reacting a PECH diol sample (M_n = 3160 g mol⁻¹, Đ = 1.20) with 4,4'-methylenebis(phenyl isocyanate) to readily generate a high molar mass polyurethane (M_n = 17,900 g mol⁻¹; Đ = 2.48) (Figure S11). In addition, PECH diol distribution almost completely disappeared in the SEC spectrum, thus confirming the perfect chain-end functionality (Figure S11).

To summarize, H₂O/BF₃•Et₂O is a simple but very efficient initiating system for living cationic ROP of ECH, affording macrocyclic-free PECHs with M_n between 500 and 4100 g mol⁻¹, low dispersity (Đ ≤ 1.25) and exceptionally high chain-end functionality (F_n(OH) ≈ 2.0).

Towards industrially-suitable conditions

1
2
3
4 Previously-reported monomer-starved conditions to obtain PECH with high chain-end
5
6
7 functionality are typically between 20 and 48 h, that is too long for an industrial process.^{18,19,20,21,22}
8
9
10 We then investigated the influence of the rate of monomer addition on the cationic ROP of ECH
11
12
13 so as to optimize the reaction time. As shown in Table 2, the increase of rate of monomer addition
14
15
16 from 0.7 to 3.5 mL/h allowed to shorten significantly the polymerization time (from 18 down to
17
18
19 3.5 h), without impairing the monomer conversion and polymer functionality. Dispersity of
20
21
22 synthesized polymers only slightly increased when increasing the rate of monomer addition. Faster
23
24
25 monomer addition (4.5 mL/h) resulted in incomplete monomer conversion (~80%), but led
26
27
28 anyway to well-defined macrocyclic-free PECH diols with perfect functionality (Table 2,
29
30
31 Figure 3a).
32
33
34
35
36
37
38
39
40
41
42
43

44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
Table 2. Effect of the Rate of Monomer Addition on the Cationic ROP of Epichlorohydrin.^a

run	ECH addition rate (mL/h) ^b	Time (h)	conv. (%)	$M_{n,theo}^c$ (g mol ⁻¹)	$M_{n,NMR}$ (g mol ⁻¹)	$M_{n,SEC}$ (g mol ⁻¹)	\bar{D}	$F_n(OH)^d$
5	0.7	18.0	96	3370	2890	3060	1.21	2.01
6	1.5	8.0	94	3300	3190	3130	1.20	1.96
7	2.5	3.3	88	3110	2650	2790	1.25	2.01

8	3.5	3.6	93	3280	2645	2750	1.25	1.99
9	4.5	2.6	81	2860	2450	2460	1.27	1.97

^a Conditions: [ECH]/[H₂O]=38; [H₂O]/[BF₃•Et₂O]=15; toluene/ECH=1/2 v/v; V(ECH)_{total}=8.3 mL; temperature: 25 °C. ^b With respect to pure monomer. ^c Theoretical M_n calculated as M_n = [ECH]/[H₂O]×92.5×conv. ^d Number average functionality at the chain end determined as F_n = ([M_n(SEC)/M_n(NMR)]×2×0.93).

Interestingly, when more dilution was applied (toluene/ECH = 2/1 instead of 1/2 vol/vol) together with a higher rate of monomer addition (4.5 mL/h), the polymerization proceeded at lower rate, affording PECH with lower than quantitative functionality (Table S9) and containing macrocyclic by-products (Figure 3b). This result indicates that under “concentrated” conditions, the monomer is consumed faster by propagation, allowing maintaining the instantaneous concentration of ECH at very low level. Logically, reducing the rate of monomer addition under “diluted” conditions resulted in living cationic ROP of ECH to receive macrocycle-free PECH chains (Figure 3b, Table S9).




Figure 3. SEC traces of poly(epichlorohydrin) synthesized using the $\text{H}_2\text{O}/\text{BF}_3\cdot\text{Et}_2\text{O}$ initiating system in toluene, at different toluene/ECH ratios and different rates of monomer addition. Conditions: $[\text{ECH}]/[\text{H}_2\text{O}] = 38$; $[\text{H}_2\text{O}]/[\text{BF}_3\cdot\text{Et}_2\text{O}] = 15$; temperature: $25\text{ }^\circ\text{C}$. Toluene/ECH ratio (vol/vol): (a) 1:2; (b) 2:1. Numbers in Figure 3a correspond to runs in Table 2, while numbers in Figure 3b correspond to runs in Table S9, respectively.

Then, the effect of temperature was briefly investigated in the $\text{H}_2\text{O}/\text{BF}_3\cdot\text{Et}_2\text{O}$ initiating system. In general, similarly to ECH polymerization with $\text{BD}/\text{BF}_3\cdot\text{Et}_2\text{O}$ initiating system (Table S3, Figure S5), the decrease of reaction temperature below $20\text{ }^\circ\text{C}$ led to a slowing down of the reaction as well as to the generation of a fraction of macrocyclic by-products (Table S10, Figure S12). On

1
2
3 the contrary, increasing the temperature from 20 to 40 °C did not have any negative effects on the
4
5
6
7 reaction rate and preserved the properties of the synthesized PECHs (Table S10).
8
9

10 In all studies related to cationic, anionic or coordinative ROP of ECH, extensive drying and
11
12 purification of all reagents and monomer are generally done because of the known sensitivity of
13
14 used co-initiators/catalysts towards even traces of water. On the other hand, our team³⁷ and others³⁸
15
16
17 showed that $\text{BF}_3 \cdot \text{Et}_2\text{O}$ could be considered as a water-tolerant Lewis acid, as it slowly hydrolyzes
18
19
20 in aqueous environment. Well-defined PECH diols ($M_n \approx 2500 \text{ g mol}^{-1}$, $F_n(\text{OH}) \approx 2.0$) with quite
21
22
23 low dispersity ($\mathcal{D} < 1.2$) were obtained using non-purified reagents and monomer, as shown in Table
24
25
26
27
28
29
30 3. Moreover, neither the reaction rate, the molar mass, the dispersity nor the chain-end
31
32
33 functionality were affected in these raw conditions (Table S11, Figure S13).
34
35
36
37
38
39

40 *Intermediate conclusion on ECH polymerization in toluene solution*

41
42


43
44 $\text{H}_2\text{O}/\text{BF}_3\text{OEt}_2$ initiating system where the initiator is prepared *in situ* by reaction of ECH with
45
46
47 water allowed synthesizing well-defined PECH diols at much faster rate than $\text{BD}/\text{BF}_3 \cdot \text{Et}_2\text{O}$ ^{20,21} and
48
49
50 ethylene glycol/ $\text{BF}_3 \cdot \text{Et}_2\text{O}$ ¹⁸ initiating systems. This achievement is indebted to the much better
51
52
53 solubility of both CLPD and low molar mass oligomers formed in the course of *in situ* initiator
54
55
56
57
58
59
60

1
2
3 preparation in the reaction media, as compared to BD and ethylene glycol (Figure S4, Figure S14,
4
5
6
7 see also section “Scale-up of ECH polymerization” for more details). Polymerizations performed
8
9
10 under “concentrated” conditions are more efficient than in “diluted” conditions (compare Figure
11
12
13 3a and Figure 3b) thanks again to the better solubility of CLPD or ECH oligomers in monomer
14
15
16 than in toluene (Figure S14). An increase of polymerization temperature also results in enhanced
17
18
19 solubility of initiator/low molar mass oligomers and, in turn, facilitates the preparation of well-
20
21
22 defined PECH diols via a fast living ROP of ECH using $\text{H}_2\text{O}/\text{BF}_3 \cdot \text{Et}_2\text{O}$ initiating system. In
23
24
25 optimized conditions (temperature ≥ 25 °C; toluene/ECH 1:2 vol/vol), $\text{H}_2\text{O}/\text{BF}_3 \cdot \text{Et}_2\text{O}$ initiating
26
27
28 system allows synthesizing well-defined macrocycle-free PECH diols ($F_n(\text{OH}) \approx 2.0$) with M_n up
29
30
31 to 4000 g mol^{-1} and low dispersity ($\text{Đ} \leq 1.25$) at relatively high rate of monomer addition and a
32
33
34 total polymerization time of 3 – 4 h. The robustness and high potential for industrial use of this
35
36
37 initiating system is also strengthened by the possibility to conduct the polymerization using
38
39
40
41 unpurified reagents and monomer.
42
43
44
45
46
47
48
49

50 Bulk Polymerization

51
52
53
54
55
56
57
58
59
60

Motivated by the much better solubility of ECH oligomers in monomer than in toluene (Figure S14), the cationic ROP of ECH in bulk using $\text{H}_2\text{O}/\text{BF}_3\cdot\text{Et}_2\text{O}$ initiating system was then investigated. To account for the relatively high viscosity of PECH with $M_n \approx 2000 \text{ g mol}^{-1}$ at 20°C ,¹⁸ the ROP of ECH at $[\text{ECH}]/[\text{H}_2\text{O}] > 15$ was performed at 40°C under mechanical stirring (all previous experiments in toluene were performed using a magnetic stirrer) (Table S12). The bulk cationic ROP of ECH using $\text{H}_2\text{O}/\text{BF}_3\cdot\text{Et}_2\text{O}$ initiating system proceeds in a living fashion: the experimental values determined by both SEC and ^1H NMR correlate well with the theoretical line up to $M_n \approx 2500 \text{ g mol}^{-1}$, while dispersity remains low ($\mathcal{D} \leq 1.23$) (Figure 4a). SEC traces of PECH samples are symmetrical at all $[\text{M}]/[\text{I}]$ ratios studied here and shift towards higher molar masses with increasing $[\text{M}]/[\text{I}]$ ratio (Figure 4b).






Figure 4. (a) M_n and \bar{D} vs. $[M]/[I]$ plot, (b) SEC traces at different $[M]/[I]$ ratios for cationic ROP of ECH with $H_2O/BF_3 \cdot Et_2O$ initiating system in bulk (see Table S12 for detailed experimental conditions). Zooms of (c) low molar mass and (d) high molar mass parts of MALDI TOF MS spectrum of PECH ($M_n = 2270 \text{ g mol}^{-1}$; $\bar{D} = 1.23$; run S61 in Table S12) synthesized with $H_2O/BF_3 \cdot Et_2O$ initiating system in bulk.

Importantly, the functionality of the chain-ends does not depend on $[M]/[I]$ ratio and is close to quantitative for all $[M]/[I]$ ratios studied (Table S12). In order to confirm the absence of macrocyclic PECH chains and other side products in polymers obtained via bulk polymerization, MALDI TOF MS was performed (Figure 4c,d, full spectrum in Figure S15). The major population of chains in both low and high molar mass regions corresponds to polyepichlorhydrin diol $HO-(ECH)_n-OH$ cationized by Na^+ . Minor peaks (-36 and -68 m/z) can be assigned to PECH diol

1
2
3 chains that lost one and two HCl molecules, respectively. Finally, a small massif of peaks
4
5
6 corresponding to cyclic PECH (-18 m/z) is present only in the low molar mass part of MALDI
7
8
9
10 TOF MS spectra. Thus, bulk cationic ROP of ECH with $\text{H}_2\text{O}/\text{BF}_3\cdot\text{Et}_2\text{O}$ initiating system produces
11
12
13 predominantly PECH diol and a negligible fraction of cyclic by-products.
14
15

16
17 It should be noted that the synthesis of PECH of similar molar mass in bulk and using ethylene
18
19 glycol/ $\text{BF}_3\cdot\text{Et}_2\text{O}$ initiating system, was reported previously by Penczek et al.¹⁸ The main
20
21 improvement achieved in the present work using $\text{H}_2\text{O}/\text{BF}_3\cdot\text{Et}_2\text{O}$ initiating system is the successful
22
23 improvement achieved in the present work using $\text{H}_2\text{O}/\text{BF}_3\cdot\text{Et}_2\text{O}$ initiating system is the successful
24
25 reduction of the polymerization time (from 48 to 5 – 6 h) without any deleterious effect on the
26
27 dispersity and functionality at the chain end of synthesized PECHs. This is ascribed to the much
28
29 better solubility of *in situ* prepared initiator in reaction medium as compared to ethylene glycol.
30
31
32
33
34
35

36 37 **Reasons for polymer coloring**

38
39

40 PECHs synthesized both in solution and in bulk are transparent viscous liquids just after reaction,
41
42 but then become slightly yellow (especially those obtained in bulk) upon storage for several
43
44 months. The conditions of storage influence strongly the color intensity: a sample stored at -20 °C
45
46 remains transparent, while the strongest coloration is observed for the same sample stored at 45 °C
47
48
49
50
51 (FigureS16). The extension of the storage time also increases the intensity of the color, especially
52
53
54
55
56
57
58
59
60

1
2
3
4 for the sample stored at 45 °C (Figure S17). The coloration of PECHs prepared in bulk is
5
6
7 tentatively associated with the presence of traces of co-initiator in the samples that were not
8
9
10 purified (Figure S16). Indeed, a PECH sample obtained in bulk and washed with Na₂CO₃ and
11
12
13 water is still transparent even after 2 months of storage (compare samples 2 and 5, Figure S16).
14
15

16
17 The coloration of the sample upon storage does not affect the molar mass and the dispersity of
18
19 the synthesized polymers (Figure S18). Moreover, PECHs samples stored at
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60
Based on these observations, we can conclude that changes inside the main chain are most probably
responsible for the observed coloration of PECH samples. To check so, the structure of the PECH
stored at 45 °C was investigated by ¹³C and ¹³C-DEPT NMR spectroscopy (Figure 5). The signals
at 44.2 and 78.1 ppm were assigned to the main chain carbon atoms of chloromethyl (**c**) and
methine (**b**) groups in ¹³C NMR spectrum, respectively, while the carbon signal of the methylene
groups of the main chain (**a**) is splitting into three signals corresponding to regular head-to-tail
(68.7 ppm, H-T), inverse tail-to-tail (70.2 ppm, T-T) and head-to-head (70.6 ppm, H-H) units. The
carbon signals of terminal epichlorohydrin unit connected to hydroxyl group were identified with

1
2
3 the help of ^{13}C DEPT-135 NMR spectroscopy (Figure 5b) at the following chemical shifts: 47.1
4
5
6
7 (**c'**), 69.3 (**b'**) and 70.8 ppm (**a'**). In addition to these signals, a resonance at 15.2 ppm (**d**) in the
8
9
10 aliphatic part of ^{13}C NMR spectrum was assigned to the carbon of the methyl group close to an
11
12
13 internal main chain double bond (Figure 5). The signals at ca. 101.5 ppm (**e**) on both ^{13}C NMR
14
15
16 and ^{13}C DEPT-135 NMR spectra can be assigned to carbon atoms of internal olefinic methine
17
18
19 group in the main chain (Figure 5b). Another signal in the olefinic part of ^{13}C NMR spectrum at
20
21
22
23 162.0 ppm (**f**) corresponds to the signal of the tertiary carbon atom connected to an external main
24
25
26 chain double bond, as confirmed by ^{13}C DEPT-135 NMR (Figure 5b). Note that the signal of the
27
28
29 carbon atom of olefinic methylene group ($\text{CH}_2=$) is theoretically assigned at ca. 77 ppm and,
30
31
32
33 therefore, surely overlaps with the resonances of main chain carbon atoms.
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60





Figure 5. (a) ^{13}C and (b) ^{13}C DEPT-135 NMR spectra of PECH ($M_n = 2230 \text{ g mol}^{-1}$; $\bar{D} = 1.22$)

synthesized with $\text{H}_2\text{O}/\text{BF}_3 \cdot \text{Et}_2\text{O}$ initiating system in bulk and stored at $45 \text{ }^\circ\text{C}$ for 2 months.

Based on these data, the following mechanism for the sample yellowing is proposed (Scheme 2). HCl abstraction by a trace of Lewis acid, together with temperature and/or sunlight irradiation, can occur during the polymerization or storage of the bulk sample, leading to the formation of a *side* olefinic group in a main chain. Then, this double bond is protonated by water with the formation of a stable tertiary cation. The elimination of proton from the neighboring methylene group leads to the formation of a thermodynamically stable *internal* double bond. Similar repetition of reactions with neighboring chloromethyl group results in formation of conjugated double bonds (through the oxygen), which, most probably, are responsible for the observed coloration of PECH samples under long storage.



Scheme 2. Proposed mechanism for the formation of side and internal double bonds in poly(epichlorohydrin).

1
2
3
4
5
6
7 Note that for GAP application, the loss of HCl groups in the course of polymerization or during
8
9
10 the storage of PECH decreases the degree of functionalization by azide, which means undesirable
11
12
13 loss of energetic properties of solid propellants. Therefore, for the preparation of high quality
14
15
16
17 PECH diol, not only the polymerization process should be mastered, but also the conditions of
18
19
20 storage and/or transportation of polymer need controls.
21
22

23 **Scale-up of ECH polymerization**

24
25
26
27 The solution process in toluene was first successfully upscaled to 200 g of PECH using a low
28
29
30 $[\text{BF}_3 \cdot \text{Et}_2\text{O}]/[\text{H}_2\text{O}]$ ratio (1:26 mol/mol) and a slow monomer addition (Table S13). The *in situ*
31
32
33 initiator preparation as well as polymerization proceeded smoothly under such conditions since
34
35
36
37 reaction temperature did not exceed 35°C. Final results are a conversion above 98% after 23 h of
38
39
40
41 polymerization, PECH chains of M_n of 2300 g mol⁻¹, low dispersity ($\mathcal{D} < 1.15$) and quantitative
42
43
44 functionality ($F_n(\text{OH}) \approx 2.0$) (Table S13).
45
46

47 An attempt to decrease the polymerization time, using the best conditions found in small-scale
48
49
50 batch experiments (10 g ECH, run 9, Table 2) led to the following difficulties: i) an uncontrolled
51
52
53
54 reaction with a high temperature jump during *in situ* initiator preparation when $[\text{BF}_3 \cdot \text{Et}_2\text{O}]/[\text{H}_2\text{O}]$
55
56
57
58
59
60

1
2
3 was increased from 1:26 to 1:15; and ii) a significant temperature increase (up to 70°C) rapidly
4
5
6 after the beginning of the polymerization of ECH (typically in less than 1 h). This uncontrolled
7
8
9 rise of temperature was attributed to the much faster ROP of ECH than the initiator formation
10
11
12 under these homogeneous conditions. To solve this problem, we added some solvent (toluene) into
13
14
15 the reaction mixture to maintain the heterogeneity of the system during the *in situ* initiator
16
17
18 preparation. Doing so, the reaction mixture remained heterogeneous all along this first step, as
19
20
21 shown in Figure S20, and no temperature change was observed, even when preparing about 50 g
22
23
24 of initiator solution (for about 1 kg of final PECH content). Increasing the rate of addition of ECH
25
26
27 also resulted in an increase of the reaction temperature up to 75°C approximately after 30 min
28
29
30 since the beginning of the polymerization (Table S14). This temperature jump coincided with the
31
32
33 change of the state of reaction mixture from heterogeneous to homogeneous. Still, apart from this
34
35
36 exotherm, the characteristics of the final polymers were basically the same.
37
38
39
40
41
42
43

44 To better understand this solubility issue, oligomers of ECH with degree of polymerization (DP_n)
45
46
47 from 1 to 5 were synthesized (Table S15) and introduced in toluene or ECH. Oligo(ECH)s with
48
49
50 $DP_n \leq 3$ are poorly soluble in toluene, while perfect solubility was observed for oligoECHs with
51
52
53 $DP_n \geq 4$ (Figure S21a). All oligomers were fully soluble in ECH (Figure S21b).
54
55
56
57
58
59
60

1
2
3
4 In order to avoid the temperature rise during ROP of ECH, it was proposed to conduct a two-
5
6
7 stage polymerization consisting first in slow monomer addition in heterogeneous conditions (in
8
9
10 solution), followed by fast monomer addition in homogeneous conditions (in bulk). This approach
11
12
13 allowed controlling the exothermicity of polymerization with a maximal temperature not
14
15
16 exceeding 35°C (Table 3). The total reaction time was reduced from about 20 h (Table S14) to 8 –
17
18
19 9 h (Table 3), while well-defined PECHs with controlled molar mass ($M_n \sim 2600 \text{ g}\cdot\text{mol}^{-1}$), low
20
21
22 dispersity ($\mathcal{D} < 1.2$) and ideal functionality were obtained (Table 3).
23
24
25

26
27 Another strategy to prepare well-defined PECH at large scale under fast polymerization rate
28
29
30 without any temperature jump was tested: it consisted in using toluene-soluble oligoepichloro-
31
32
33 hydrin ($DP_n \geq 4$) as macroinitiator of ROP of ECH in conjunction with BF_3OEt_2 as co-initiator.
34
35
36
37 The desired PECH chains with controlled molar mass and low dispersity were obtained in less than
38
39
40 6 h (Table 3). Implementing the same protocol as in solution (conducting the polymerization in
41
42
43 two stages) allowed controlling the reaction temperature during the polymerization and
44
45
46 synthesizing well-defined PECH of $M_n \sim 2500 \text{ g mol}^{-1}$, low dispersity and expected functionality
47
48
49 (Table 3). It should be noted that thanks to the excellent solubility of both CLPD and low molar
50
51
52 mass PECH in ECH (Figure S21b), the polymerization in bulk could be easily upscaled to 100 g
53
54
55
56
57
58
59
60

of polymer and did not require a two-stage monomer addition and/or using ECH oligomers as initiator (Table 3).

Table 3. Scale-up of Cationic ROP of ECH with H₂O/BF₃OEt₂ Initiating System in Toluene and in Bulk.^a

run	process	1 st stage ECH rate addition (mL/h)	Time (h)	2 nd stage ECH rate addition (mL/h)	Time (h)	conv. (%)	M _{n,NMR} (g mol ⁻¹)	M _{n,SEC} (g mol ⁻¹)	Đ
14	solution	1.5	3.6	13.6	9	97	2510	2580	1.18
15	solution	3.2	2.8	13.6	8	97	2430	2480	1.18
16 ^c	solution	–	–	20.4	6	99	2560	2710	1.19
17 ^d	bulk	–	–	13.6	8	99	2590	2610	1.21

^a Conditions: [BF₃•Et₂O]/[H₂O] = 1/15; [ECH]/[H₂O] = 28; ECH_{total}: 100 g; ECH/toluene = 2:1 v/v for polymerization in solution; T = 25 °C; V(ECH)_{total} = 85 mL. F_n at chain-ends determined as F_n = [M_n(SEC)/M_n(NMR)] × 2 × 0.93 was 1.99 ± 0.2 for all experiments. No temperature jump was observed, the temperature of reaction continuously increased from 25 to 31 °C during the polymerization. M_{n,theo} = 2500 g mol⁻¹. ^b Total reaction time for 2 stages. ^c Oligoepichlorohydrin (DP_n = 4) was used as an initiator. ^d CLPD was used as an initiator.

CONCLUSIONS

1
2
3
4 In this work, a detailed fundamental mechanistic study of $\text{BF}_3 \cdot \text{Et}_2\text{O}$ -catalyzed cationic ring-
5
6
7 opening polymerization of epichlorohydrin was performed to reach industrially-relevant
8
9
10 polymerization conditions. First of all, the possibility to conduct the living cationic ROP of ECH
11
12
13 in non-chlorinated solvents (typically toluene) or in bulk was demonstrated. The solubility of
14
15
16 initiating complex in the reaction medium is a key issue for providing fast and living ROP of ECH.
17
18
19
20 It was unambiguously showed that the poor solubility in toluene of both molecular initiators (BD,
21
22
23 CLPD) and low molar mass oligomers (up to $\text{DP}_n = 3$) resulted in retardation of the initiating
24
25
26 process and accumulation of monomer in the reaction mixture at the beginning of the
27
28
29 polymerization. This monomer accumulation gave rise to an induction period, followed by a fast
30
31
32 polymerization accompanied by a significant increase of reaction temperature (up to boiling of
33
34
35 reaction mixture).

36
37
38
39
40 To solve this problem, we proposed a simple and efficient initiation approach consisting in first
41
42
43 forming the initiator through reaction of ECH with water ($\text{ECH}/\text{H}_2\text{O}=1:1.05$ or $1.5:1$ mol/mol) in
44
45
46 the presence of the water-tolerant $\text{BF}_3 \cdot \text{Et}_2\text{O}$ co-initiator. Doing so, CLPD and longer oligomers
47
48
49 displaying perfect solubility in reaction media were prepared *in situ*. As a result, the induction
50
51
52 period was reduced and, thereof, ROP of ECH could proceed at much faster rate (4 – 8 h) as
53
54
55
56
57
58
59
60

1
2
3 compared to previously described processes (20 – 48 h). The proposed initiating system
4
5
6
7 ($\text{H}_2\text{O}/\text{BF}_3 \cdot \text{Et}_2\text{O}$) could be efficiently used in a non-chlorinated solvent such as toluene as well as
8
9
10 in bulk conditions. In best conditions, fast synthesis of pure PECH diols ($F_n(\text{OH}) \approx 2.0$) with
11
12
13 controlled molar mass (M_n up to 4000 g mol^{-1}), low dispersity ($\mathcal{D} < 1.25$) was achieved. The
14
15
16 developed procedure for fast synthesis of PECH diol was successfully scaled-up to 100 g of
17
18
19 polymer, either in solution or in bulk, eventually using prepared oligoECHs as initiators. The
20
21
22 developed procedure was successfully upscaled to 100 g of polymer as an incentive to industrial
23
24
25
26
27 production of PECH as well as its derivative glycidyl azide polymer (GAP).
28
29

30 Finally, detailed characterization of the synthesized PECH was performed with the aim to
31
32
33 elucidate the reasons leading to the coloration of the polymers in the course of polymerization
34
35
36 observed by some authors^{18,20,21,22} or during the storage of non-purified samples (this work). Such
37
38
39 process occurs via the abstraction of HCl by Lewis acid with formation of side double bond
40
41
42 followed by its protonation/proton abstraction with the formation of internal conjugated double
43
44
45
46
47 bonds.
48
49
50
51
52

53 ASSOCIATED CONTENT
54
55
56
57
58
59
60

1
2
3
4 **Supporting Information.** Tables with polymerization data, ^1H and ^{13}C NMR spectra, SEC traces,
5
6
7 photos of initiator/solvent (monomer) mixtures, reaction mixture and obtained polymers,
8
9
10 MALDI TOF MS spectra. The following files are available free of charge.
11
12
13

14 **AUTHOR INFORMATION**

15 **Corresponding Author**

16
17
18
19
20
21
22 Sergei V. Kostjuk – Research Institute for Physical Chemical Problems of the Belarusian State
23
24
25 University, 14 Leningradskaya st., 220006 Minsk, Belarus; Department of Chemistry, Belarusian
26
27
28 State University, 14 Leningradskaya st., 220006 Minsk, Belarus; INSA-Lyon, IMP, CNRS,
29
30
31 UMR5223, 20 Boulevard Einstein, F-69621 Villeurbanne, France ; Sechenov First Moscow State
32
33
34
35 Medical University, Institute for Regenerative Medicine, Moscow, 119991, Russia E-mail:
36
37

38
39 kostjuks@bsu.by
40
41
42

43 **Author Contributions**

44
45
46 The manuscript was written through contributions of all authors. All authors have given approval
47
48
49 to the final version of the manuscript.
50
51
52

53 **Notes**

1
2
3
4 The authors declare no competing financial interest.
5
6
7
8
9

10
11 **ACKNOWLEDGMENT**
12
13

14 The authors thank EURENCO for financial support of this research. S.K. and F.G. thank
15
16
17
18 Dr. Geneviève Eck and Dr. Thibaud Alaime for useful discussions of the obtained results. This
19
20
21 work is also partially supported by State Program for Scientific Research of Belarus “Chemical
22
23
24 processes, reagents and technologies, bioregulators and bioorganic chemistry” (project 2.1.01.03).
25
26
27
28
29
30

31 **REFERENCES**
32
33
34

- 35 (1) Vandenberg, E. J. Award Address: Reflections on 50 years of polymer chemistry. *Polymer*
36
37
38 **1994**, *35*, 4933–4939. (doi: 10.1016/0032-3861(94)90647-5)
39
40
41
42 (2) Ikeda, T. Glycidyl Triazolyl Polymers: Poly(ethylene glycol) Derivatives Functionalized by
43
44
45 Azide–Alkyne Cycloaddition Reaction. *Macromol. Rapid Commun.* **2018**, *39*, 1700825. (doi:
46
47
48 10.1002/marc.201700825)
49
50
51
52
53
54
55
56
57
58
59
60

1
2
3
4 (3) Ikeda, Y.; Masui, H.; Matoba, Y. Ionic conductivity of polymer solid electrolyte prepared
5
6
7 from poly[epichlorohydrin-co-(ethylene oxide)] of high ethylene oxide content. *J. Appl. Polym.*
8
9
10 *Sci.* **2005**, *95*, 178–184; (doi: 10.1002/app.20814)
11
12

13
14 (4) Hayano, S.; Ota, K.; Hoang, T. B. Syntheses, Characterizations and Functions of Cationic
15
16
17 Polyethers with Imidazolium-Based Ionic Liquid Moieties. *Polym. Chem.* **2018**, *9*, 948-960. (doi:
18
19
20
21 10.1039/C7PY01985H)
22
23

24
25 5 Frankel, M. B.; Grant, L. R.; Flanagan, J. E. Historical Development of Glycidyl Azide
26
27
28
29 Polymer. *J. Propul. Power.* **1992**, *8*, 560–563; (doi: 10.2514/3.23514)
30
31

32
33 (6) Gaur, B.; Lochab, B.; Choudhary, V.; Varma, I. K. Azido Polymers – Energetic Binders for
34
35
36 Solid Rocket Propellants. *J. Macromol. Sci. Part C.* **2003**, *43*, 505–545; (doi:
37
38
39
40 10.1002/chin.200420263)
41
42

43
44 (7) Cheng, T. Review of Novel Energetic Polymers and Binders – High Energy Propellant
45
46
47 Ingredients for the New Space Race. *Des. Monom. Polym.* **2019**, *22*, 54–65. (doi:
48
49
50
51 10.1080/15685551.2019.1575652)
52
53

1
2
3
4 (8) Ivan, B.; Kennedy, J. P. Quantitative aspects of chain extension of telechelics. *Polym. Bull.*
5
6
7 **1980**, *2*, 351–356. (<https://doi.org/10.1007/BF00266713>)
8
9

10
11 9 Vandenberg, E. J. Organometallic Catalysts for Polymerizing Monosubstituted Epoxides. *J.*
12
13
14
15 *Polym. Sci.* **1960**, *47*, 486–489; (doi: 10.1002/pol.1960.1204714947)
16
17

18
19 (10) Vandenberg, E. J. Epoxide Polymers: Synthesis, Stereochemistry, Structure, and
20
21
22 Mechanism. *J. Polym. Sci. Part A: Polym. Chem.* **1969**, *7*, 525–567; (doi:
23
24
25 10.1002/pol.1969.150070210)
26
27

28
29 (11) Brochu, S.; Ampleman, G. Synthesis and Characterization of Glycidyl Azide Polymers
30
31
32
33 Using Isotactic and Chiral Poly(epichlorohydrin)s. *Macromolecules* **1996**, *29*, 5539 – 5545. (doi:
34
35
36 10.1021/ma951839f)
37
38

39
40 (12) Masuda, Y.; Hani, H. Organoaluminum – Cyclic Ether – Cyclic Imide Catalysts for the
41
42
43
44 Polymerization of Epoxides. *J. Polym. Sci.: Polym. Chem. Ed.* **1973**, *11*, 3103–3114. (doi:
45
46
47 10.1002/pol.1973.170111206)
48
49
50
51
52
53
54
55
56
57
58
59
60

1
2
3
4 (13) Araki, T.; Aoyagi, T.; Ueyama, N.; Aoyama, T.; Tani, H. Ethylaluminum Oxide Catalysts
5
6
7 from Et₂AlOLi–Et₂AlCl Binary System in Relation to Species of AlEt₃– Water Catalyst. *J. Polym.*
8
9
10 *Sci. Part A: Polym. Chem.* **1973**, *11*, 699 – 712. (doi: 10.1002/pol.1973.170110401)
11
12

13
14 (14) Xie, H-Q.; Guo, J-S.; Yu, G.-Q.; Zu, J. Ring-Opening Polymerization of Epichlorohydrin
15
16
17 and its Copolymerization with other Alkylene Oxides by Quaternary Catalyst System. *J. Appl.*
18
19
20 *Polym. Sci.* **2001**, *80*, 2446 – 2454. (doi: 10.1002/app.1351)
21
22

23
24 (15) Carlotti, S.; Labbe, A.; Rejsek, V.; Doutaz, S.; Gervais, M.; Deffieux, A. Living/Controlled
25
26
27 Anionic Polymerization and Copolymerization of Epichlorohydrin with Tetraoctylammonium
28
29
30 Bromide–Triisobutylaluminum Initiating Systems. *Macromolecules* **2008**, *41*, 7058 – 7062. (doi:
31
32
33 10.1021/ma801422c)
34
35
36

37
38 (16) Brocas, A-L.; Cendejas, G.; Caillol, S.; Deffieux, A.; Carlotti, S. Controlled Synthesis of
39
40
41
42 Polyepichlorohydrin with Pendant Cyclic Carbonate Functions for Isocyanate-Free Polyurethane
43
44
45
46 Networks. *J. Polym. Sci. Part A: Polym. Chem.* **2011**, *49*, 2677 – 2684. (doi: 10.1002/pola.24699)
47
48
49
50
51
52
53
54
55
56
57
58
59
60

1
2
3
4 (17) Rodriguez, C. G.; Ferrier, R. C., Jr.; Helenic, A.; Lynd, N. A. Ring-Opening Polymerization
5
6
7 of Epoxides: Facile Pathway to Functional Polyethers via a Versatile Organoaluminum Initiator.
8

9
10 *Macromolecules* **2017**, *50*, 3121 – 3130. (doi: 10.1021/acs.macromol.7b00196)
11
12

13
14 (18) Bideron, T.; Kubisa, P.; Penczek, S. Polyepichlorohydrin Diols Free of Cycles: Synthesis
15
16
17 and Characterization. *J. Polym. Sci. Part A: Polym. Chem.* **1991**, *29*, 619 – 628. (doi:
18
19
20
21 10.1002/pola.1991.080290502)
22
23

24
25 (19) Panda, S. P.; Sahu, S. K.; Thakur, J. V.; Kulkarni, S. G.; Kumbhar, C. G.; Sadafule, D. S.
26
27
28 Synthesis and Characterization of Hydroxyl Terminated Polyepichlorohydrin and
29
30
31 Polyglycidylazide. *Def. Sci. J.* **1996**, *46*, 399 – 403. (doi: 10.14429/dsj.46.4307)
32
33
34

35
36 (20) Kim, J. S.; Kweon, J. O.; Noh, S. T. Online Monitoring of Reaction Temperature during
37
38
39 Cationic Ring Opening Polymerization of Epichlorohydrin in Presence of BF₃ and 1,4-Butanediol.
40
41

42
43 *J. Appl. Polym. Sci.* **2014**, *131*, 39912. (doi: 10.1002/app.39912)
44
45

46
47 (21) Kim, J. S.; Kim, D. K.; Kweon, J. O.; Lee, J. M.; Noh, S. T.; Kim, S. Y. The Influence of
48
49
50 Initiator Diol-BF₃ Complex Solubility and other Factors on the Induction Period in BF₃ Catalyzed
51
52

1
2
3
4 Cationic Ring Opening Polymerization of Epichlorohydrin. *Macromol. Res.* **2014**, *22*, 436 – 444.

5
6
7 (doi: 10.1007/s13233-014-2056-3)
8
9

10
11 (22) Hafner, S.; Keicher, T.; Klapotke, T. M. Copolymers based on GAP and 1,2-Epoxyhexane
12
13 as Promising Prepolymers for Energetic Binder Systems. *Propellants Explos. Pyrotech.* **2018**, *43*,
14
15 126 – 135. (doi: 10.1002/prop.201700198)
16
17
18
19

20
21
22 (23) Murali Mohan, Y.; Padmanabha Raju, M.; Mohana Raju, K. Synthesis, Spectral and DSC
23
24 Analysis of Glycidyl Azide Polymers Containing Different Initiating Diol Units. *J. Appl. Polym.*
25
26 *Sci.* **2004**, *93*, 2157 – 2163. (doi: 10.1002/app.20682)
27
28
29
30

31
32
33 (24) Murali Mohan, Y.; Padmanabha Raju, M.; Mohana Raju, K. Synthesis and Characterization
34
35 of GAP-PEG Copolymers. *Int. J. Polym. Mater.* **2005**, *54*, 651 – 666. (doi:
36
37 10.1080/00914030490499134)
38
39
40

41
42
43 (25) Guanaes, D.; Bittencourt, E.; Eberlin, M. N.; Sabino, A. A. Influence of Polymerization
44
45 Conditions in the Molecular Weight and Polydispersity of Polyepichlorohydrin. *Eur. Polym. J.*
46
47 **2007**, *43*, 2141 – 2148. (doi: 10.1016/j.eurpolymj.2007.02.016)
48
49
50
51
52
53
54
55
56
57
58
59
60

1
2
3
4 (26) Grinevich, T.V.; Solov'yanov, A. A.; Vinogradov, D. B.; Bulatov, P. V.; Kuznetsov, G. P.;
5
6
7 Assovskii, I. G.; Berlin, A. A.; Tartakovskii, V. A. Oligo(glycidyl azides): New Approaches to
8
9
10 Synthesis and Properties. *Dokl. Chem.* **2014**, *454*, 39–41. (doi: 10.1134/S0012500814020062)
11
12

13
14 27 Francis, A. U.; Venkatachalam, S.; Kanakavel, M.; Ravindran, P. V.; Ninan, K. N. Structural
15
16
17 Characterization of Hydroxyl Terminated Polyepichlorohydrin Obtained using Boron Trifluoride
18
19
20 Etherate and Stannic Chloride as Initiators. *Eur. Polym. J.* **2003**, *39*, 831 – 841. (doi:
21
22 10.1016/S0014-3057(02)00302-6)
23
24
25

26
27
28
29 (28) Okamoto, Y. Cationic Ring-Opening Polymerization of Epichlorohydrin in the Presence of
30
31
32 Ethylene Glycol. *ACS Symp. Ser.* **1985**, *286*, 361 – 372. (doi: 10.1021/bk-1985-0286.ch025)
33
34
35

36
37 (29) Kim, C. S.; Kuo, K.; Fish, R.; Russell, J.; Curb, P.; Immoos, J. Telechelic Polymerization
38
39
40 of Epichlorohydrin using 1,4-Butanediyl Ditriflate as the Initiator. *Macromolecules* **1990**, *23*, 4715
41
42
43 – 4717. (doi: 10.1021/ma00223a032)
44
45
46

47
48 (30) Yahiaoui, A.; Belbachir, M.; Hachemaoui, A. An Acid Exchanged Montmorillonite Clay-
49
50
51 Catalyzed Synthesis of Polyepichlorohydrin. *Int. J. Mol. Sci.* **2003**, *4*, 548 – 561. (doi:
52
53 10.3390/i4100548)
54
55
56

1
2
3
4 (31) Ferrier Jr, R. C.; Pakhira, S.; Palmon, S. E.; Rodriguez, C. G.; Goldfeld, D. E.; Iyiola, O.
5
6
7 O.; Chwatko, M.; Mendoza-Cortes, J. L.; Lynd, N. A. Demystifying the Mechanism of Regio- and
8
9
10 Isoselective Epoxide Polymerization Using the Vandenberg Catalyst. *Macromolecules* **2018**, *51*,
11
12
13 1777 – 1786. (doi: 10.1021/acs.macromol.7b02091)
14
15
16

17
18 (32) Kuntz, I.; Kroll, W. R. Polymerization of Epoxides with Dialkylaluminum Acetylacetonate
19
20
21 Catalyst Systems. *J. Polym. Sci., Part A-1: Polym. Chem.* **1970**, *8*, 1601 – 1621. (doi:
22
23
24 10.1002/pol.1970.150080701)
25
26
27

28
29 (33) Wei, R-J.; Zhang, Y-Y.; Zhang, X.-H.; Du, B-Y.; Fan, Z-Q. Regio-Selective Synthesis of
30
31
32 Polyepichlorohydrin Diol using Zn–Co(III) Double Metal Cyanide Complex. *RSC Advances*
33
34
35 **2014**, *4*, 21765 – 21771. (doi: 10.1039/C4RA02394C)
36
37
38

39
40 (34) Rodriguez, C. G.; Ferrier Jr, R. C.; Helenic, A.; Lynd, N. A. Ring-Opening Polymerization
41
42
43 of Epoxides: Facile Pathway to Functional Polyethers via a Versatile Organoaluminum Initiator.
44
45
46 *Macromolecules* **2017**, *50*, 3121 – 3130. (doi: 10.1021/acs.macromol.7b00196)
47
48
49
50
51
52
53
54
55
56
57
58
59
60

1
2
3
4 (35) Boopathi, S.K.; Hadjichristidis, N.; Gnanou, Y.; Feng, X. Direct Access to Poly(glycidyl
5
6
7 azide) and its Copolymers through Anionic (Co-)Polymerization of Glycidyl Azide. *Nat.*
8
9
10 *Commun.* **2019**, *10*, 293. (doi: 10.1038/s41467-018-08251-1)
11
12

13
14 (36) Haque, F.M.; Schexnayder, C.M.; Matxain, J.M.; Barroso-Bujans, F.; Grayson, S.M.
15
16
17 MALDI-TOF MS Study of Macrocyclic Polyethers Generated by Electrophilic Zwitterionic Ring
18
19
20 Expansion Polymerization of Monosubstituted Epoxides with $B(C_6F_5)_3$. *Macromolecules* **2019**,
21
22
23
24 *52*, 6369–6381. (doi: 10.1021/acs.macromol.9b01050)
25
26
27

28
29 (37) Radchenko, A.V.; Kostjuk S.V.; Vasilenko I.V.; Ganachaud F.; Kaputsky F.N.
30
31
32 Controlled/Living Cationic Polymerization of Styrene with BF_3OEt_2 as Coinitiator in the Presence
33
34
35 of Water: Improvements and Limitations. *Eur. Polym. J.* **2007**, *43*, 2576–2583. (doi:
36
37
38 10.1016/j.eurpolymj.2007.03.026)
39
40
41

42
43 (38) Satoh, K.; Kamigaito, M.; Sawamoto, M. Direct Synthesis of Amphiphilic Random and
44
45
46 Block Copolymers of p-Hydroxystyrene and p-Methoxystyrene via Living Cationic
47
48
49 Polymerization with $BF_3 \cdot OEt_2/ROH$ Systems. *Macromolecules* **2000**, *33*, 5830–5835. (doi:
50
51
52 10.1021/ma000070q)
53
54
55

1
2
3
4
5
6
7
8
9
10
11
12
13
14
15
16
17
18
19
20
21
22
23
24
25
26
27
28
29
30
31
32
33
34
35
36
37
38
39
40
41
42
43
44
45
46
47
48
49
50
51
52
53
54
55
56
57
58
59
60

Table of Contents Graphic

Chlorinated Solvent-Free Living Cationic Ring-Opening Polymerization of Epichlorohydrin

Using $\text{BF}_3 \cdot \text{OEt}_2$ as Co-initiator: Towards Perfectly Functionalized Polyepichlorohydrin Diols

Georgy V. Timofeev, Maksim I. Hulnik, Irina V. Vasilenko, Francois Ganachaud, Guy Jacob

*and Sergei V. Kostjuk**

