

Integrated empirical and modelled determination of the human health impacts of building material VOCs

Rachna Bhoonah, Alice Maury-Micolier, Olivier Jolliet

▶ To cite this version:

Rachna Bhoonah, Alice Maury-Micolier, Olivier Jolliet. Integrated empirical and modelled determination of the human health impacts of building material VOCs. Building and Environment, 2023, 242, pp.110523. 10.1016/j.buildenv.2023.110523. hal-04266644

HAL Id: hal-04266644 https://hal.science/hal-04266644v1

Submitted on 31 Oct 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

- 1 Integrated empirical and modelled determination of the human health impacts of
- 2 **building material VOCs**
- 3 Rachna Bhoonah^a, Alice Maury-Micolier^b, Olivier Jolliet^{c, d}
- ^aMines Paris PSL, Centre Efficacité Energétique des Systèmes, 5 Rue Leon Blum, 91120
- 5 Palaiseau, France
- 6 bOctopus Lab, 237 Rue du Ballon, 59110 La Madeleine, France
- 7 ^cQuantitative Sustainability Assessment, Department of Environmental and Resource
- 8 Engineering, Technical University of Denmark, Bygningstorvet 115, 2800 Kgs. Lyngby,
- 9 Denmark
- 10 d Environmental Health Sciences, School of Public Health, University of Michigan, Ann
- 11 Arbor, MI 48109, USA

- 13 ORCID
- 14 Rachna Bhoonah: https://orcid.org/0000-0002-9476-4014
- 15 Alice Maury-Micolier: https://orcid.org/0000-0002-4615-1205
- 16 Olivier Jolliet: https://orcid.org/0000-0001-6955-4210
- ^{*}Corresponding author: rachna.bhoonah@minesparis.psl.eu

1. Introduction

Indoor air quality (IAQ) is of crucial concern since humans spend more than 90% of their time indoors[1] and are directly exposed to substances that can be harmful to their health. These substances, called pollutants, are either in the form of gases or are adsorbed to particulate matter (PM) and are either emitted directly by indoor sources (materials used in construction and furniture, human activities and humans themselves) or transferred from the outdoor environment through ventilation, infiltration and airing. Since people spend a lot of their time and get most of their intakes indoors, it is crucial to assess indoor pollutant concentrations and to identify their main sources in order to limit IAQ-related intake and health damage.

Materials have been identified as important continuous sources of chemicals present in indoor environments [2-4], which can directly affect human health or react with other substances such as ozone to form new harmful substances in the gas or particle phase [4]. Thus, a high number of studies have measured the emission of volatile organic compounds (VOCs) from specific materials [3,5–7]. Furthermore, since 2011, it is mandatory for manufacturers to measure VOC emissions of construction, wall and flooring materials under the regulatory labelling scheme in France[8]. However, measured data are only available and valid at a few specific points in time, during a restricted timespan of a few days to a few weeks. In order to obtain a complete emission profile and assess the cumulative intake of these VOCs, concentrations have to be extrapolated. Linear extrapolations cannot be applied since emissions themselves vary with the time dependent mass of the substance left in the material. Simple fit of decay exponential curves has also limited validity to reflect the potential increase of initial air concentration. Moreover, air chamber measurements and emissions depend on the actual ventilation rate and surfaces to volume ratio, and therefore need to be scaled up to real building usage conditions[9–11]. Thus there is a need to couple measurements with more elaborated emission models to determine the emission and resulting concentration profiles as a function of time.

Emission models of VOCs from materials are based on the mass balance of the substance emitted from the material and depend on chemical, material and building parameters. Two main parameters characterize the combined influence of material and chemical properties and are unique to each material-chemical combination: 1) the diffusion of these substances through the material, determined by the diffusion coefficient, D_m and 2) the material-air partition coefficient, K_{ma} , which is the ratio at equilibrium of the concentration of

the chemical at the surface of the material and in the boundary air layer at material surface. QPPRs (Quality Property-property Relationship) have been developed to compute material-specific properties such as D_m and K_{ma} , for multiple material types from chemical properties more commonly available such as molecular weight and K_{oa} [12,13]. Developed from large datasets of about 1000 measurements, these QPPRs reference values can be used to simulate average indoor concentrations when no specific emission data are available, but are associated with relatively large uncertainties of a factor 10 to a 100. Another key parameter is the mass fraction of volatile substances in the material, MF_0 , which determines the amount that can be emitted in air. Material compositions are often unknown, except for the average values that can be found for some material categories in e.g. the Pharos database, aggregating information on chemicals in building materials and associated human and environmental health hazards [14].

Measurements do not represent real-life occupied indoor environments and are only available at specific points in time, while models contain uncertainties and unknowns. The combination of the measurements to emission models could take advantage of the respective strengths of these approaches and help to predict more precisely the evolution of indoor VOC concentrations. Furthermore, since VOCs can have serious adverse effects on health, it is beneficial to model intake and health damages on building occupants in order to make judicious choices right at the design stage. The present paper therefore aims to propose and apply a framework combining measured emission data with a mass balance model of VOCs emission from materials. More specifically, the different objectives are:

- 1. Develop a framework to use multi-layered emission model for interpreting and generalising measured emission data from building materials
- 2. Perform a parameter optimisation and evaluate the quality of the approach based on sets of chemicals in gypsum board and bamboo flooring
- 3. Determine long-term chemical intakes and related human health impacts and compare across chemicals

First, we will present the framework developed to calibrate an emission model with emission data. The framework will then be applied to two mono-layered materials: gypsum board and bamboo flooring. In a case study, we will evaluate the health damages related to the intake of VOCs emitted by the gypsum board and bamboo flooring.

2. Material and methods




Figure 1: Methodology for extrapolating VOC emission data with an emission model: calibration, application and validation on different materials with measured data and determination of health damages from exposure

From a test chamber measurement pool of N substances emitted by the material under study, a minimum of 2 and maximum of N-1 substances are selected and coupled with an existing emission model and reference coefficient values in order to estimate the optimal diffusion and material-air partition coefficients unique to the material that best fit the measurements. The initial mass fraction, MF_0 , of each substance, specific to each material, that yield the lowest error of the predicted compared to the measured concentrations are then derived. The framework is validated by comparing the predicted concentrations to measured data for all N substances. Using the determined optimal parameters, the inhalation exposure to

material VOCs can be determined by the model and combined with exposure-response data to evaluate corresponding health damages.

2.1 Measured air concentration data in test chamber

Air concentration measurements of different substances emitted at different points in time by materials, for instance by material manufacturers. Since these measurements are made in test chambers, the following chamber characteristics are considered: 1) the chamber walls are made of very low absorption or emission materials such as glass or stainless steel, in order not to interfere with the tested material and 2) only one face of the material emits substances, the other being covered by an impermeable material. The ventilation rate and temperature during measurements must also be known.

In this study, we used data on two mono-layered materials: gypsum board and bamboo flooring. Air concentration data are available at 3 days (t_1) and/or 28 days (t_2) for the two materials from the manufacturer's data sheet (created in response to the regulatory labelling scheme [8]), with no uncertainty range available. For all two materials, the tests were carried out with an air change rate of 0.5 vol.h⁻¹ at 23 °C and a relative humidity of 50 %. A summary of relevant information is presented in Table 1.

Table 1: Main characteristics of the measurement of VOCs emissions from gypsum board and bamboo flooring

	Gypsum board	Bamboo flooring
Number of substances measured (at both t_1 and t_2)	21 (5)	11 (3)
Thickness of material (mm)	12.5	38
Density (kg.m ⁻³)	1150	1150
Chamber volume (m ⁻³)	0.123	0.25
Loading ratio (m ² .m ⁻³)	1	0.4

Out of the total number of chemicals measured, only those having two measurement points (at t_1 and t_2) were chosen for calibration and validation: 5 for gypsum board and 3 for bamboo flooring. Calibration substances were selected based on their emission dynamics, defined by their diffusion D_m (m²/s) and material-air partition K_{ma} (-) coefficients, as

explained in paragraph 2.3: hexanal, toluene and n-hexadecane for gypsum board, and acetic acid and phenol for bamboo flooring.

2.2 Emission model and main parameters of influence

The multi-layered material emission model used in this paper has been developed by Yan et al. [15], modified by Guo [16], and further adjusted by Micolier [17]. The material is divided into several layers. Each layer is considered to have a uniform substance concentration and is represented by a single node. The emission rate is obtained from the mass balance of substances at different nodes within the material and in air, as a function of the initial mass fraction of the substance in the material, MF_0 (kg_{chemical}/kg_{material}). The mass balance equations for each node are given in SI S.1. VOC emissions are driven by two major parameters, i.e. the diffusion coefficient on D_m and the material partition coefficients K_{ma} and this emission can be limited by its diffusion through the material (D-limited) or by its partition from the material to the boundary layer (K-limited).

These two parameters have been estimated from material and substance specific coefficients [12,13] as follows:

$$D_m = 10^{6.39 + \frac{\tau - 3486}{T} - 2.49log_{10}MW + b} \tag{1}$$

$$K_{ma} = 10^{-0.38 + 0.63.log_{10}.K_{oa} + 0.96 \frac{1.37.\nabla H_{\nu} - 14}{2.303.R} \left(\frac{1}{T} - \frac{1}{298.15}\right) + \beta$$
 (2)

MW (g/mol) is the molecular mass of the substance, T (K) is the absolute temperature of the room and b, τ (K) and β are material-specific coefficients, ∇H_{ν} (J/mol) the enthalpy of vaporisation and K_{oa} is the chemical's dimensionless octanol-air partition coefficient at 25 °C.

Coefficients b and β have several reference values as a function of the type of material independently of the considered chemical. These values have been obtained by Huang et al. (2017) and Huang and Jolliet (2019) based on the analysis of more than 1000 measured diffusion coefficients and material-air partitioning coefficients, with high R^2 , but still substantial remaining uncertainties: SE on $\log_{10} D$ and $\log_{10} K$ amount to ± 2.30 and ± 1.22 respectively, corresponding to uncertainty factors of 200 and 17. It is therefore interesting to take advantage of the measured concentrations to calibrate these parameters within their uncertainty range to the specific considered material.

2.3 Selection of substances for main parameter calibration

In order to optimise the parameters b (material-specific coefficient for diffusion) and β (material-specific coefficient for partition), a calibration is realised for each material using data for part of N substances for which measurements at two points in time (t_1 and t_2) are known, the other substances (at least one) being kept for the validation step. Excluding one substance for validation (from N-1), we select at least two and up to four substances for calibration, with the broadest range possible in their diffusion (D_m) and partition coefficients to cover various emission dynamics: the substance having the highest D_m and highest K_{ma} , and the one with the lowest D_m and lowest K_{ma} are chosen. If more than one substance remains, up to two additional substances are selected: the one(s) having the highest absolute difference between D_m and K_{ma} . Any remaining substance is kept for validation. A detailed description of the selection process is given in SI section S.2.

2.4 Parameters calibration

b and β are first varied within their range of uncertainty using a 50 x 50 grid, yielding 2500 combinations of D and K. For each of these combinations b- β , we perform the following iterative process: a) We first back-calculate the initial mass fraction $MF_{0,b-\beta}$ of the substance s under study¹ that correctly predicts the concentration at time t_1 , C_{t_1} . b) We then evaluate for each b- β combination the deviation $(d_{b-\beta_s})$ between the log of observed and predicted ratios of C_{t_1}/C_{t_2} calculated as:

$$d_{b-\beta_{s}} = \left| \left((log_{10}(C_{t_{1},m_{s}}) - log_{10}(C_{t_{2},m_{s}})) - (log_{10}(C_{t_{1},p_{s_{b-\beta}}}) - log_{10}(C_{t_{2},p_{s_{b-\beta}}})) \right) \right|$$

$$(3)$$

- 168 c) We calculate for each b- β combination, the mean deviation $(\overline{d}_{b-\beta})$ across all calibration substances
- d) We also determine for each b-β combination a penalty for diverging from the reference D_m and K_m values is applied to each b-β couple, calculated as:

¹ This step only serves the purpose of calibration. The actual mass fraction of the substance in the material is determined later based on all available measurements (see section below).

.

$$p_{b-\beta} = 0.1 \times (abs(\log_{10}(K_{ma,b-\beta}) - \log_{10}(K_{ma,ref}))$$

$$+ abs(\log_{10}(D_{m,b-\beta}) - \log_{10}(D_{m,ref})))$$
(4)

The optimal b- β combination is selected as the one minimizing $\varepsilon_{b-\beta_{tot}}$, the sum of the obtained average deviation plus the penalty $p_{b-\beta}$:

$$\varepsilon_{b-\beta_{tot}} = \sum_{s=1}^{n} \overline{d}_{b-\beta_s} + p_{b-\beta_s} \tag{5}$$

2.5 Mass fraction and resulting air concentration

Since initial mass fractions of substances inside the measured materials (MF_0) are usually unknown, we use the optimal parameters from the calibration step to determine MF_0 as the mass that minimizes the root mean squared log error (RMSLE) on all concentrations for all times (i=1,n) and substances (s=1,x):

$$e_{MF_0} = \sqrt{\frac{1}{n} \sum_{i=1}^{n} \sum_{s=1}^{x} \left(\log_{10}(C_{t_i, m_s} + 1) - \log_{10}(C_{t_i, p_{s, MF_0}} + 1) \right)^2}$$
 (6)

We then apply the emission model from Micolier (2019) to yield predicted air concentrations.

2.6 Health impacts calculation

Health impacts HI (DALY) are calculated in DALYs (disability-adjusted life years), a measure of the number of healthy life years lost due to sickness or premature death recommended by the World Health Organisation (Murray et al. 1996), currently used as an endpoint indicator in life cycle assessment (LCA), from the severity factor (DALY/cases), effect factor EF (cases/kg_{intake}), product intake fraction PiF (kg_{intake}/kg_{in product}) and the initial mass of substance in the material M_0 (kg_{in product}).

$$HI_{rep/dev} = (SF_{rep/dev} \times EF_{rep/dev} + SF_{general\ non\ cancer} \times EF_{general\ non\ cancer} + SF_{cancer} \times EF_{cancer})$$

$$\times PiF \times M_0$$
(7)

$$PiF = \frac{XF_{inh} \times V_{room} \int_{t=0}^{T} C_{in} dt}{M_0}$$
 (8)

Where *XF* (1/s) is the exposure factor representing the fraction of the air volume that is taken in by the occupants per time unit.

2.7 Case study

We selected as a case study a room with of 38.75 m² gypsum-covered walls and 15 m² bamboo flooring. The room is ventilated at 1 ACH and occupied by 3 persons 8 hours per working day and indoor temperature is set at 20°C.

2.8 Applicability and assumptions

The framework is applicable under the following conditions: 1) data is available on test chamber conditions, namely volume, air change rate and temperature, 2) dimensions of the material are known and 3) at least two measurement points for at least three substances are available, since emission data for at least two substances are used for calibration and the model is validated with at least one other substance.

The model is applied under the following assumptions: 1) the concentration of the substance is initially identical for all layers of the same material, 2) the concentration of the substance in each layer is uniform at any point in time, 3) the substances emitted are volatile, 4) D_m and K_{ma} are unique to all layers of the same material and 5) emissions occur under stable atmospheric conditions with constant pressure, relative humidity and temperature.

3. Results

3.1. Deviation of predicted values from measured values

The above framework is applied to the two mono-layered materials with available measurement data: gypsum board and bamboo flooring. Hexanal, toluene and n-hexadecane were selected for the calibration of the gypsum board parameters whereas acetic acid and phenol were used for bamboo flooring calibration. Figure 2 presents for each of these chemicals-material combinations the deviation between the log of observed and predicted ratios of concentrations C_{t_1}/C_{t_2} , as calculated by equation (3).




Figure 2: Heat maps of $d_{b-\beta_s}$, the deviation between the log of observed and predicted ratios of concentrations C_{t_1}/C_{t_2} for (a) hexanal, (b) toluene, (c) n-hexadecane emissions from gypsum board and (d) acetic acid,(e) phenol from bamboo flooring as a function of the material coefficient b for diffusion and β for material-air partition. The reference default values of b and β are indicated by a yellow dot at the centre and optimal values by a larger red dot. The scale of deviation, from -1 to 1, is given on the right side of (e).

The optimal parameters b and β minimize the average deviation across chemicals as determined by equation (5) (black-outlined red dots in Figure 2 and therefore fall in the light-green or light blue areas that correspond to values that make the model best agree with measurements and yield smallest deviations. For the gypsum board, the deviation primarily depends on the diffusion coefficient b, with deviation of up to a factor 10 ($d_{b-\beta_s}=-1$, dark blue area) between modelled and measured concentrations of hexanal and toluene at low diffusion coefficient. The optimal b and b combination is obtained for b=-6.10 and b = 1.3, which is close (within a factor 2 for the diffusion coefficient) to the reference values of -5.77 and 1.26.

For the bamboo flooring, emissions are sensitive to both diffusion and material-air partition coefficients when considering acetic acid and phenol. The low-deviation (light green) regions are quite limited. Based on the deviation and penalty, the optimal solutions of

b and β for bamboo flooring are -5.75 and 0.29, thus with a factor 10 lower on the material air partition coefficient from the default reference value of -5.61 and 1.36.

3.2. Predicted vs measured VOC air concentrations

For each substance, the optimal parameters are used to determine MF_0 based on equation (6) are applied to the model, and obtain the air concentration of different emitted substances as a function of time. Figure 3 compares the predicted concentration curves to the measurement points and present the mean predicted concentrations over 10, 100 and 10000 days, showing a relatively good concordance between measured and modelled values.




Figure 3: Evolution of the predicted concentrations for (a) n-hexadecane, (b) n-pentadecane, (c) nonanal emitted by gypsum board, and (d) acetic acid, (e) 2-ethyl 1-hexanol, (f) phenol emitted by bamboo flooring: The mean predicted concentrations over 10, 100 and 10000 days are presented by red, light blue and green lines respectively.

The volatile nature of the considered substances is reflected in the decrease in mean concentrations with increasing time frame. Since the first measured point is higher, its squared difference to the model tends to be higher as well and the concentration curves tend to be closer to this first measured value, within a factor 1.4.

3.3. Uncertainties

The model is validated against the test substances calibration, estimating the percentage error, the root mean squared log error (RMSLE) and the mean absolute log deviation (MALD). Since predicted concentration different substances can vary over orders of magnitude, selecting the error on the log of concentrations gives equal importance to relative errors across the entire range of concentration and avoids a bias towards substances with higher concentrations. Figure 4 compares the predicted and measured air concentration, with circle markers for the gypsum board and triangles for the bamboo flooring mono-layered material.




Figure 4: Measured v/s predicted concentrations for 3-day (bigger markers) and 28-day (smaller markers) measurements from gypsum board (circle markers) and bamboo flooring (triangle markers) for all substances with both measurements known. The substances with a black-outlined marker have been selected for the calibration process

Figure 4 shows good agreement between measured and modelled data for both the calibration data and for the test data with less than a factor two for the test substances pentadecane and nonanal (cyan and brown circles) in the gypsum flooring and for 2-ethyl 1-hexanol in the bamboo flooring (orange triangle).

Table 2 summarises the errors (percentage error, RMSLE and MALD) for the substances divided into three categories: all substances, only test substances and only substances selected for the calibration process.

Table 2: Relative error, Root Mean Squared Log Error, and Mean Absolute Log
Deviation (MALD) for all substances, only validation points and only substances selected for
the calibration

	All substances	Only test substances	Only calibration
% Error	22%	32%	16%
% Error 3d	18%	29%	11%
% Error 28d	26%	35%	20%
RMSLE	0.02	0.05	0.02
RMS uncertainty factor	1.05	1.13	1.04
MALD	0.19	0.30	0.13
MALD uncertainty factor	1.56	1.99	1.34

As expected, the error indicators are lower for substances used in the calibration procedure whereas, prediction remains within max a factor 2 of the observed value for the test substances. Relative error, for all substances and all measurements, on the predicted values is of 22%, corresponding to average errors on air concentration measurements, generally around 20%, but which could range from 5% to 25% [18,19].


For the bamboo flooring, the predicted initial mass fractions of 7.6×10^{-7} for phenol and 8.4×10^{-8} for toluene respectively 2 and 6 orders of magnitude lower than reported ones in Pharos. Lower predictions could be explained by the difference between the composition of the product under study and those referenced in Pharos. Calculated mass fractions correspond to the amount of substance in the material at the beginning of chamber tests. Thus, low-end values could also come from the time elapsed between the manufacture and the chamber tests, and, consequently, partial emission of substances (especially highly volatile ones) before measurements are taken.

3.4. Application to the case study

The case study parameters, optimal b and β and mass fractions calculated previously for both materials are applied to the model for substances studied (those with two measured data). For point with single measured data, MF_0 is back-calculated from the measured concentration using the same optimal b and β as for the other substances. The intake

fractions are calculated from equation (8) using concentrations and exposure fractions and the consequent health damages are evaluated using equation (7).

Figure 5 presents the intake (μ g) and health impacts (μ DALY) of substances emitted by gypsum board and bamboo flooring over short, medium and long-term exposure corresponding to 10, 100 and 10000 days respectively. 18 out of 21 substances emitted by gypsum board and 4 out of the 11 substances emitted by bamboo flooring have known toxicity data (effect factors).






Figure 5: Intake quantities (µg) for (a) 17 substances emitted by gypsum board and (b) 6 substances emitted by bamboo flooring and health impacts for different substances emitted by (c) gypsum board and (d) bamboo flooring over 10, 100 and 10000 days

Figure 5 shows that the differences between short, medium and long-term exposures to acetaldehyde emitted from gypsum board or acetic acid from bamboo flooring are not significant since these substances are highly volatile and rapidly emitted. For some substances

such as n-hexadecane emitted from gypsum board, the short-term impacts can be lower but long-term impacts higher than certain substances such as n-pentadecane, since their emission dynamics are different.

It can also be noted that impacts can be different for similar intake quantities, or that they can be higher for substances with lower intake quantities since there can be substantial variations between effect factors of different substances. For example, the intake quantity of acetic acid from bamboo flooring is of 1.90 x 10⁴ µg while for phenol it is of 1.24 x 10³ µg. Their respective health damages are 1.91 µDALY and 2.50 µDALY. Despite having over 10 times the intake quantity of phenol, acetic acid is responsible for less health impacts due to its lower effect factor. It can also be noted that the differences between the health damage from different substances are several orders of magnitude high and that the substances of concern in each material can be different. In the case of gypsum board, tetrachloroethylene is responsible for 53% of the total damage from VOC emissions, toluene for 19% and formaldehyde 17%. For bamboo flooring, phenol has the highest contribution, accounting for 52% of health impacts and acetic acid 48%. Table 3 summarises the health damages related to the exposure to VOCs emitted by the three materials for short, medium and long-term exposures. The equivalent damage for 1 m² flooring area per year is also given based on the long-term exposure.

Table 3: Health damages related to the intake of substances with known toxicity data for gypsum walls and bamboo floor for the office (3 persons in 15 m²) over three exposure periods, per unit floor area per year and per kg of material

Health impacts	Gypsum walls	Bamboo floor
10 days (μDALY)	23.18	1.16
100 days (μDALY)	57.60	3.60
10000 days (μDALY)	61.97	4.43
10000 days (µDALY/m²/year)	0.15	0.01
10000 days (µDALY/kg)	0.11	0.01

From Table 3, it can be noted that, for the functional unit of 1 m² floor area, gypsum board leads to more health damage on occupants than bamboo floor.

4. Conclusion

328

329

330

331

332

333

334

335

336

337

338

339

340

341

342

343

344

345

346

347

348

349

350

351

354

357

A framework was developed to calibrate a material VOC emission model depending on parameters having relatively high uncertainties (factor 10 to 100), and to calculate unknown VOC mass fractions using measured air concentration data. It allows to extrapolate measurements, only valid at few points in time and for short time spans, scale concentrations to real building contexts, and calculate full exposure and long-term health impacts on occupants. The framework was tested on two mono-layered materials, yielding an uncertainty factor of 1.1 (RMSLE) and a relative error of 22% between measurements and predictions, corresponding to typical VOC air concentration measurement uncertainties. Calculated parameters were applied to a case study of an office to calculate short, medium and long-term health impacts from the exposure to VOCs: 24 $\mu DALY$, 61 $\mu DALY$ and 66 $\mu DALY$ respectively. This framework, by providing full concentration profiles, can help manufacturers to devise material treatment strategies that aim at lowering impacts related to VOC off-gassing (e.g. artificial ageing). It can also help in decision-making process in the building sector: choice of low-impact materials and adequate ventilation rates to evacuate pollutants. The present method is dependent on emission data, but these are often confidential or incomplete. Due to regulations and growing concern regarding health implications of material VOCs, these data are expected to become more readily available in the future. Health impacts are possibly underestimated since toxicity data are lacking for a number of substances and should be updated when available, and also because, in real building contexts, gypsum board is often covered in paint which can lead to additional VOC emissions. Finally, chemical reactions in indoor air can consume existing chemicals or produce new ones and should be considered in IAQ health impact assessments [4].

5. Data availability

The ED10 and ED50 data used to support the findings of this study are included within the supplementary information files.

6. Acknowledgement

The authors would like to thank the financial support by the Chair ParisTech VINCI
Eco-design of buildings and infrastructure.

7. Conflicts of interest

The authors declare that there is no conflict of interest regarding the publication of this paper.

8. Supplementary Materials

The multilayered emission model is described in supplementary material S.1. Detailed description for the selection of substances based on their emission dynamics are given in S.2. In S.3. the equations used for the calculation of exposure factors XF and effect factors EF are given. The data used for the calculation of EF are given in Table S1 in S.4.

366 **9. References**

- 367 [1] U.S. Environmental Protection Agency. Report to Congress on indoor air quality: Volume 2. 368 EPA/400/1-89/001C. Washington, DC. 1989. shorturl.at/asN34 (accessed September 26, 2022).
- Huang L, Fantke P, Ritscher A, Jolliet O. Chemicals of concern in building materials: A high-throughput screening. J Hazard Mater 2022;424:127574. https://doi.org/10.1016/j.jhazmat.2021.127574.
- 372 [3] Shaw D. Investigation of building materials as VOC sources in indoor air 2004.
- Why Indoor Chemistry Matters. Washington, D.C.: National Academies Press; 2022. https://doi.org/10.17226/26228.
- Wilke O, Jann O, Brödner D. VOC- and SVOC-emissions from adhesives, floor coverings and complete floor structures. Indoor Air 2004;14 Suppl 8:98–107. https://doi.org/10.1111/j.1600-0668.2004.00314.x.
- Won D, Magee R, Lusztyk E, Nong G, Zhu J, Zhang J, et al. A Comprehensive VOC emission database for commonly-used building materials. Proc 7th Int Conf Healthy Build 2003.
- 380 [7] James JP, Yang X. Emissions of Volatile Organic Compounds from Several Green and Non-381 Green Building Materials: A Comparison. Indoor Built Environ 2005;14:69–74. 382 https://doi.org/10.1177/1420326X05050504.
- decree of 19 april,. Arrêté du 19 avril 2011 relatif à l'étiquetage des produits de construction ou de revêtement de mur ou de sol et des peintures et vernis sur leurs émissions de polluants volatils, Journal officiel lois et décrets 2011. 2011.
- 386 [9] Xu Y, Zhang Y. A general model for analyzing single surface VOC emission characteristics 387 from building materials and its application. Atmos Environ 2004;38:113–9. 388 https://doi.org/10.1016/j.atmosenv.2003.09.020.
- 389 [10] Rackes A, Waring MS. Do time-averaged, whole-building, effective volatile organic compound (VOC) emissions depend on the air exchange rate? A statistical analysis of trends for 46 VOCs in U.S. offices. Indoor Air 2016;26:642–59. https://doi.org/10.1111/ina.12224.
- 392 [11] Zhou X, Liu Y, Liu J. Alternately airtight/ventilated emission method: A universal experimental method for determining the VOC emission characteristic parameters of building materials. Build Environ 2018;130:179–89. https://doi.org/10.1016/j.buildenv.2017.12.025.
- Huang L, Fantke P, Ernstoff A, Jolliet O. A quantitative property-property relationship for the internal diffusion coefficients of organic compounds in solid materials. Indoor Air 2017;27:1128–40. https://doi.org/10.1111/ina.12395.
- Huang L, Jolliet O. A quantitative structure-property relationship (QSPR) for estimating solid material-air partition coefficients of organic compounds. Indoor Air 2019;29:79–88. https://doi.org/10.1111/ina.12510.
- 401 [14] Healthy Building Network. Pharos About. Pharos Healthy Build Netw 2000. https://pharos.healthybuilding.net/about (accessed May 29, 2023).
- 403 [15] Yan W, Zhang Y, Wang X. Simulation of VOC emissions from building materials by using the 404 state-space method. Build Environ 2009;44:471–8. https://doi.org/10.1016/j.buildenv.2008.04.011.
- 406 [16] Guo Z. A Framework for Modelling Non-Steady-State Concentrations of Semivolatile Organic Compounds Indoors I: Emissions from Diffusional Sources and Sorption by Interior Surfaces 2013. https://doi.org/10.1177/1420326X13488123.
- 409 [17] Micolier A. Development of a methodology for a consistent and integrated evaluation of the 410 health, energy and environmental performance of residential building design solutions. 411 Université de Bordeaux, 2019.

- 412 [18] Wilke O, Horn W, Wiegner K, Jann O, Bremser W, Brödner D, et al. Investigations for the Improvement of the Measurement of Volatile Organic Compounds from Floor Coverings within the Health-Related Evaluation of Construction Products. 2009.
- 415 [19] Jia C, Batterman SA, Relyea GE. Variability of indoor and outdoor VOC measurements: An analysis using variance components. Environ Pollut Barking Essex 1987 2012;169:152–9. https://doi.org/10.1016/j.envpol.2011.09.024.