



HAL
open science

ZnWO₄ grains characterisation for GRAiNITA – a new-generation calorimeter

Giulia Hull, Ianina Boiaryntseva, Jacques Lefrancois, I. Tupitsyna, A.-M. Dubovik, S. Barsuk, M.-H. Schune, S. Monteil, D. Breton, A. Boyarintsev

► **To cite this version:**

Giulia Hull, Ianina Boiaryntseva, Jacques Lefrancois, I. Tupitsyna, A.-M. Dubovik, et al.. ZnWO₄ grains characterisation for GRAiNITA – a new-generation calorimeter. IEEE Nuclear Science Symposium and Medical Imaging Conference, Nov 2022, Milan, Italy. hal-04269276

HAL Id: hal-04269276

<https://hal.science/hal-04269276>

Submitted on 3 Nov 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.


ZnWO₄ grains characterisation for GRAiNITA – a new-generation calorimeter

G. Hull¹, I. Boiaryntseva^{1,2}, J. Lefrancois¹, I. Tupitsyna², A.-M. Dubovik², S. Barsuk¹,
M.-H. Schune¹, S. Monteil³, D. Breton¹, A. Boyarintsev²

¹ Université Paris-Saclay, CNRS-IN2P3, IJCLab, Orsay, France

² Institute of Scintillation Materials of the National Academy of Science of Ukraine, Kharkiv, Ukraine


³ Université Blaise Pascal, CNRS-IN2P3, LP-Clermont, Aubiere, France



Introduction: The electromagnetic calorimeters for high-energy physics experiments are often based on the use of scintillator materials and, in order to contain the cost of the detectors, the sampling technique is privileged with respect to the use of uniform inorganic crystals. With **GRAiNITA**, we propose a new version of the Shashlik detector, for possible application in FCC e+e- experiments. The idea is to use, in the same volume, a mixture of high-Z scintillator grains and a high-density transparent liquid as absorber. Due to the stochastic confinement of the light, as in the LiquidO detection technique [1], the scintillation light remains localized in the zone of production and it can be collected on SiPMs, by means of wavelength shifting fibres, uniformly distributed in the detection volume. This new detector will provide extremely fine sampling of the electromagnetic shower and for this reason a very good photon energy resolution ($R \sim 2\%/\sqrt{E}$) is expected with respect to conventional Shashlik detectors (typically $R \sim 10\%/\sqrt{E}$, [2]).

The GRAiNITA detector

Opaque scintillator technique for the development of a new Shashlik calorimeter with extremely fine sampling



- For improved high energy and very good sampling
- For costs reduction costs: grains production is less expensive than volumetric crystals production
- For good energy measurements of the jets: study of the possibility of measuring the fraction of energy in the shower via Pulse Shape Discrimination.


Candidates scintillators: ZnWO₄ and BGO

Candidate absorber: CH₂I₂

ZnWO₄ can be produced directly in grain-shape via spontaneous crystallization

- LY= 10 kph/MeV
- $\tau = 20 \mu\text{s}$
- $Z_{\text{eff}} = 61$
- $\lambda_{\text{max}} = 490 \text{ nm}$
- Crystal price/grains price = 2.5

X-ray excited emission spectrum




	ZnWO ₄	CH ₂ I ₂	Mix
Density [g/cm ³]	7.62	3.32	5.47
Refractive index	2.1	1.74	
X ₀ [cm]	1.2	2.67	1.65
Molière radius [cm]	1.98	4.58	2.77

BGO can be reduced in the form of grains with the « Planetary Ball Milling » technique:

- LY= 8-10 kph/MeV
- $\tau = 300 \text{ ns}$
- $Z_{\text{eff}} = 73$
- $\lambda_{\text{max}} = 480 \text{ nm}$
- Crystal price/grains price > 1.1

X-ray excited emission spectrum



	BGO	CH ₂ I ₂	Mix
Density [g/cm ³]	7.13	3.32	5.47
Refractive index	2.15	1.74	
X ₀ [cm]	1.12	2.67	1.50
Molière radius [cm]	2.26	4.58	2.84

Crystal grains production

ISMA developed the technique to grow ZnWO₄ single crystal granules using the flux method. Several methods have been investigated:

- **NaCl as a solvent + ZnWO₄ salt:** ZnWO₄ grains yield $\approx 10 \text{ wt } \%$; 44% of grains with size > 1mm, 33% of grains with size between 0.5 and 1 mm.
- **Na₂WO₄ as a solvent + ZnO and WO₃:** ZnWO₄ grains yield $\approx 25 \text{ wt } \%$ but brownish color
- **Na₂WO₄ as a solvent + ZnWO₄ salt:** ZnWO₄ grains yield $\approx 85 \text{ wt } \%$, colorless and transparent, average size of grains $\approx 1 \text{ mm}$ lateral size.



1st batch: 40 g **2nd batch: 170 g** **3rd batch: 1380 g**
Size $\sim 1 \div 3 \text{ mm}$ Size $\sim 1 \div 2 \text{ mm}$ Size $\sim 1 \text{ mm}$

For GRAiNITA, ZnWO₄ crystalline grains were grown with the flux method from thoroughly mixed ZnWO₄ (5N) and Na₂WO₄ (4N) starting materials, as this resulted to be the best effective solution to obtain sub-millimetric grains. Starting materials were charged into Pt crucible, placed into the resistive heating furnace, heated up to $T=1250^\circ\text{C}$ and then kept for 10 hours at this temperature to assure complete homogenization of the melt. According to the required size of the grains, the melt was cooled down to $T=750^\circ\text{C}$ and then it was allowed to spontaneous cooling down to room temperature. Obtained ZnWO₄ crystalline grains were rinsed in distilled water at 100°C and dried at $T= 400^\circ\text{C}$.


ZnWO₄ scintillation properties: grains vs crystals

The experimental set-up:

- ZnWO₄ crystals: $2 \times 2 \times 4 \text{ cm}^3$ and $1 \times 1 \times 1 \text{ cm}^3$
- ZnWO₄ plates (cut from the same single crystal) : $2 \text{ cm} \times 2 \text{ cm}$, different thickness: 0.85 mm, 1.03 mm, 2.14 mm, 3.14 mm, 4.25 mm
- ZnWO₄ grains, approximate later size: $0.5 \div 1.5 \text{ mm}$
- High gain PMT Hamamastu R2083, silicon grease, teflon tape
- Integrator circuit: $\tau_{\text{RC}} = 100 \mu\text{s}$
- Digital oscilloscope: LeCroy WavePro 715Zi (acquisition at 100MS/s)
- ²⁴¹Am (60keV, completely absorbed in one grain), ¹³⁷Cs, ²²Na, ¹³³Ba sources
- Spectrophotometer: PerkinElmer Lambda 850 UV/Vis




1-cm³ ZnWO₄ and BGO ¹³⁷Cs spectra



The light yield and energy resolution of a 1cm³ ZnWO₄ crystal are comparable with that of a same-sized BGO. At 662 keV we measured an energy resolution of 12.9% for ZnWO₄ and 13% for BGO.

²⁴¹Am spectra for ZnWO₄ grains




The second production of grains shows a much smaller variance in the amplitude of the ²⁴¹Am peak at 60keV, thus indicating a better homogeneity in the grains light yield.


Crystals	Max Amp [mV]	Sigma [mV]
1 grain 1st batch	257.1	36.1
1 grain 1st batch	307.7	34.9
1 grain 2nd batch	302.5	32.9
1 grain 2nd batch	290.2	36.6
Grains 1st batch	260.7	59.2
Grains 2nd batch	292.7	43.1
0.85 mm plate	298.2	36.9
1.03 mm plate	300.3	34.0
2.14 mm plate	284.2	36.6
3.14 mm plate	266.9	35.1
4.25 mm plate	272.8	34.5
1 cm ³ crystal	181.4	26.7
2x2x4 cm ³ crystal	125.9	23.2

Peak of the ²⁴¹Am spectrum vs ZnWO₄ sample thickness

The amplitude of the ²⁴¹Am peak at 60 keV decreases as a function of the ZnWO₄ thickness. This effect is mostly due to light losses caused by the absorption of the light that is reflected multiples times in the diffusive material used to tightly wrap the scintillator.



Transmittance spectra for ZnWO₄ samples of different thickness



The transmittance of ZnWO₄ samples in the maximum emission range (490 nm) slightly decreases from 73% to 66% with increasing of sample thickness from 0.085 to 4 cm. The transmittance is limited mainly by the reflection losses due to the high refractive index of ZnWO₄.

The observed absorption bands around 370, 530 and 760 nm are due to the transitions in Cr³⁺ ions that are present in trace amount as uncontrolled impurity in ZnWO₄ single crystals [3].

Conclusions and future work

Crystalline grains of ZnWO₄, grown with the flux method, proved to have scintillation properties comparable with that of volumetric optics. The latest batch of grains produced by ISMA (delivered at the end of October) is enough to assemble a medium-size prototype with approximate size of 5 cm x 5 cm x 10 cm and equipped with 16 WLS fibers, and SiPMs for the signal read-out. At present, we are working on the selection of the best suited optical fiber to be coupled to ZnWO₄ and BGO grains, respectively, as well as on the selection of the best suited liquid to be used as absorber. In the next future, we intent to develop two medium-size GRAiNITA prototypes, employing BGO and ZnWO₄ grains respectively, and to characterize the detectors response with cosmic rays and during an in-beam campaign.

Acknowledgements: This work was supported by IJCLab and by the "PAUSE - Solidarité Ukraine" of the University Paris-Saclay

[1] A. Cabrera for the LiquidO Consortium, "Neutrino physics with an opaque detector", Comm. Phys. 4, 273 (2021)

[2] S. Barsuk for the LHCb Calorimeter Group, "The Shashlik electro- magnetic calorimeter for the LHCb experiment", LHCb-PROC-2004- 006, 11th Intern. Conf. On Calorimetry In HEP, Perugia (Italy) 2004

[3] Reynolds M.L., Hagston W.E., Garlick G.F.J., Experimental Observations of the Absorption, Infra-Red Emission, and Excitation Spectra of Cr³⁺ Ions in ZnWO₄, Physica Status Solidi (b), vol. 30, issue 1 (1968) pp. 113-117, [10.1002/pssb.19680300114](https://doi.org/10.1002/pssb.19680300114)