

Is amino-modification of HKUST-1 in PEI mixed-matrix membranes always favorable to CO 2 separation?

Ge Yang, Yanjiao Wang, Mengling Sun, Panpan Xu, Chunzheng Wang, Ke

Huang, Heqing Jiang, Svetlana Mintova, Hailing Guo

► To cite this version:

Ge Yang, Yanjiao Wang, Mengling Sun, Panpan Xu, Chunzheng Wang, et al.. Is a mino-modification of HKUST-1 in PEI mixed-matrix membranes always favorable to CO 2 separation?. Microporous and Mesoporous Materials, 2023, 359, pp.112649. 10.1016/j.micromeso.2023.112649 . hal-04283467

HAL Id: hal-04283467 https://hal.science/hal-04283467

Submitted on 13 Nov 2023 $\,$

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Is amino-modification of HKUST-1 in PEI mixed-matrix membranes always favorable to CO₂ separation?

Ge Yang^{a,b}, Yanjiao Wang^a, Mengling Sun^a, Panpan Xu^a, Chunzheng Wang^a, Ke Huang^a, Heqing Jiang^c, Svetlana Mintova^{a,d}, Hailing Guo^{a,*}

- a State Key Laboratory of Heavy Oil Processing, College of Chemistry and Chemical Engineering,
 China University of Petroleum (East China) Qingdao, 266555 (P.R. China).
- b College of Science, China University of Petroleum (East China), Qingdao, 266555 (P.R. China).
- c Qingdao Institute of Bioenergy and Bioprocess Technology, Chinese Academy of Sciences,
 Laoshan District, Qingdao CN-266101, China

d Laboratoire Catalyse et Spectrochimie (LCS), ENSICAEN, UNICAEN, CNRS, Normandie
 Université, 6 boulevard du Marechal Juin, 14050 Caen (France).

15

17

3

4

5 6 7

16 * Corresponding Author Email: <u>guohl@upc.edu.cn</u>

18 **1 Introduction**

Gas separation processes play important roles in industry production and daily life. 19 20 Compared with chemical separation processes with high energy consumption, membrane based separation technology shows the advantages of high energy 21 efficiency and easy operation^[1, 2]. Polymeric membranes are attractive for membrane 22 separation since they are economical and easily fabricated. While, due to the trade-off 23 effect between permeability and selectivity in polymeric membranes, mixed matrix 24 membranes (MMMs) loaded with various fillers including porous materials have 25 received considerable attention since they combine the properties of the filler and the 26 matrix, showing the potential to break performance limits^[3,5]. Among the various 27 fillers used, the MOFs are widely considered because the organic linkers enable 28 potentially stronger interaction with the polymers. 29

30

However, the separation performance of most MMMs is under the performance upper 31 boundary due to the effects of multiple factors such as loading, dispersion in casting 32 solvent, and interface compatibility^[6]. These factors determine the efficiency of the 33 filler phase and the state of non-selective interfacial voids in MMMs. Although MOFs 34 materials have shown stronger and better regulated "polymer-filler" interactions, 35 compared with other porous materials, the structural optimization of MOFs-based 36 MMMs is still the critical factor to develop high-performance MMMs^[7,9]. The main 37 effective structural optimization strategies include reduction of filler's particle size, 38 synthesis of nanosheets, modification of filler's surface or polymer chains by 39 functional groups, *in-situ* membrane preparation^[6, 9,11]. In general, grafting functional 40 groups onto MOFs has been considered as one of the best techniques since is easily 41 achieved by substituting the MOFs' functional ligand. Vankelecom's research on 42 UiO-66-based MMMs found that NH2-UiO-66 could not only enhanced the 43 interactions between the filler and the matrix, but also improve the adsorption of CO₂ 44 in NH₂-UiO-66, which was conducive to the separation of CO₂/CH₄^[12] Similar 45 performance optimizations have been reported for NH2-UiO-66/PMMA MMMs^[13], 46

NH₂-MIL-53/Pebax MMMs^[14], NH₂-MIL-53/PI MMMs^[15], NUS-8/PIM-1^[16]. The
 main focus is on the design of high-performing MOF-based MMMs with molecule
 sieving features and reinforced interface.

4

According to previous reports, the MMMs are not effective in H_2/CO_2 separation^{[6,} 5 ^{17]}. Due to the close molecular kinetic diameters of H_2 and CO_2 molecules and the 6 stronger polarity of CO₂, neither sieving effect nor adsorption enhancement effect can 7 significantly improve the performance of MMMs, especially the H₂/CO₂ selectivity. In 8 our recent work, we combined HKUST-1 nanoparticles with Polyetherimide(PEI) and 9 the resulted MMMs were used for H_2/CO_2 separation^[18]. The PEI is a 10 high-performance polymer with superior processability, which could be molded into 11 different forms^[19]. HKUST-1 ($Cu_3(BTC)_2$) is a porous materials with channels size of 12 9 Å, allowing the rapid permeation of gas molecules, but with low molecule sieving 13 property^[17]. The HKUST-1 has not been widely used for preparation of MMMs like 14 the UiO series, MIL series and ZIFs crystals^[6]. Our work took advantage of the large 15 pore of HKUST-1 nanocrystals to accelerate H₂ diffusion with low diffusion 16 resistance. Whereas, the permeability of CO₂ molecules was affected by 17 adsorption-desorption process in the HKUST-1, resulting in a higher diffusion 18 resistance. The phenomenon of increased H₂ permeability accompanied by decreased 19 CO₂ permeability was also observed by Liu^[20]. The separation mechanism of 20 HKUST-1/PEI MMMs controlled by "adsorption-diffusion" of H₂/CO₂ was proposed. 21 Based on this mechanism, we postulated that by increasing the adsorption-desorption 22 resistance of HKUST-1 to CO₂, permeance could improve the MMMs' performance 23 by amino-functionalization of the HKUST-1. The in-situ functionalization of 24 HKUST-1 is difficult, as its ligands (Trimesic acid, BTC) cannot be completely 25 replaced by functional ligands. NH2-functionalized HKUST-1 has been prepared by 26 partial replacement of the BTC with NH₂-BDC^[21,23]. Sun reported on the synthesis of 27 sub-NH₂-Cu-BTC with 2 µm crystal size resulting in stronger affinity between 28 NH₂-Cu-BTC and CO₂ molecules^[21]. Concerning the NH₂-HKUST-1 crystals, the 29 final substitution ratio and position of amino-functionalized ligands have not been 30 31 studied before, thereby the actual effect from the incomplete amino-functionalization is not clear. 32

33

Herein, we report the amino- functionalization of HKUST-1 crystals for enhancement of the diffusion resistance of CO₂ in MMMs. The modification procedure and the position of the amino groups on HKUST-1 crystals were studied in details.

37

38 **2 Experimental section**

39 **2.1 Materials**

40 Copper (II) nitrate trihydrate (Cu (NO₃)₂·3H₂O, 99.0%–102%) and sodium formate 41 (HCOONa, \geq 99%) were bought from Sinopharm Chemical Reagent Co., Ltd. (China). 42 1,3,5-benzenetricarboxylic acid, 2-aminoterephthalic acid, ethanol (C₂H₅OH) and 43 dichloromethane (CH₂Cl₂) were obtained from Shanghai Aladdin Biochemical 44 Technology Co., Ltd. (China). Polyetherimide (PEI) particles was supplied by

- 1 SABIC. The deionized water was homemade.
- 3 2.2 Synthesis of HKUST-1 and NH₂-HKUST-1 materials

The HKUST-1 nanocrystals were synthesized following the methodology reported 4 earlier^[18]. Solution A was obtained by dissolving Cu (NO₃)₂·3H₂O (1.09 g) in 5 6 deionized water (36.0 ml), and solution B was prepared by mixing 1,3,5-benzenetricarboxylic acid (0.63 g) with sodium formate (0.94g) in ethanol (36.0 7 mL). Then, solution B was slowly added in drops to solution A with magnetic stirring 8 (600 rpm), and then the mixture was transferred to a teflon autoclave for 9 crystallization at 120 °C for 3 h. The as-synthesized product was purified using a 10 centrifuge (5000 rpm, 15 min) and re-dispersed in deionized water; the procedure was 11 repeated three times and finally stabilized in ethanol. The product was freeze-dried 12 and the sample was denoted as HKUST-1. The *in-situ* ammonia functionalized sample 13 named NH₂-HKUST-1 was prepared only changing the solution B including 14 dissolution of 0.47g 1,3,5-Benzenetricarboxylic acid, 0.14g 2-Aminoterephthalic acid 15 and 0.94g sodium formate in 36.0 ml ethanol; the other steps remained the same. 16

17

2

18 2.3 Preparation of HKUST-1(NH₂-HKUST-1)/PEI mixed matrix membranes

Polyetherimide matrix solution (5.0 w.t. %) was obtained by dissolving pre-dried 19 treated PEI particles (0.25 g) in dichloromethane (5.0 g) until the mixture became a 20 clear uniform viscous solution. This concentration of the matrix solution was 21 beneficial for the dispersion of the MOF crystals uniformly in the casting solution. 22 Casting solution was prepared by dispersing different amounts of fillers (HKUST-1 23 and NH₂-HKUST-1 crystals after being vacuum-dried overnight) in the PEI matrix 24 solution, via three rounds of magnetic stirring (10 min) and sonication (10 min) to 25 ensure the uniformity of crystal particles. After thorough de-bubbling, the casting 26 solutions were carefully poured onto a horizontally placed glass plate, and scraped by 27 an automatic coating machine. The prepared mixed matrix membranes loading 28 HKUST-1 and NH₂-HKUST-1 crystals cloud be taken from the glass plate after the 29 solvent (CH₂Cl₂) was completely removed by drying at 25 °C, 60 °C, and 120 °C for 30 24h. The loading amount of HKUST-1 and NH₂-HKUST-1 crystals in the membranes 31 was 10.0 w.t. % and 30 w.t. %, and these membranes were denoted as 32 HKUST-1-10%/PEI, HKUST-1-30%/PEI, NH₂-HKUST-1-10%/PEI, 33 and NH₂-HKUST-1-30%/PEI, respectively. The pristine PEI membrane was prepared 34 without the addition of any HKUST-1 and NH₂-HKUST-1 crystals. 35

36

37 2.4 Characterization

X-ray diffraction (XRD, Bruker D8 Advance) was used to characterize the crystalline
phase and structure of HKUST-1 and NH₂-HKUST-1 nanocrystals with a scanning
rate of 2° min⁻¹ in the 3-90° 2 *Theta* range, and the mixed matrix membranes with a
scanning rate of 8° min⁻¹ in the 3-75° 2 *Theta* range. Scanning electron microscope
(SEM, JEOL-7900F) was applied to observe the crystal morphology and particle size
of HKUST-1 and NH₂-HKUST-1 crystals and the top-view and cross-sectional surface
features of mixed matrix membranes. Elementar (ELEMENTAR, UNICUBE) did the

element analysis (EA) under CHNS mode. Infrared spectrometer (Bruker Vertex 70V) 1 recorded the fourier transform infrared (FT-IR) spectra of both MOFs crystals and 2 MMMs with an average 64 scans in the 400-4000 cm⁻¹ range. X-Ray photoelectron 3 spectroscopy (XPS) was obtained by an ESCALAB 250Xi ThermoFischer 4 spectrometer with an Al Ka source gun. N₂ sorption measurements were carried out 5 on a Quantachrome, Autosorb IQ instrument to study the porous structure of 6 HKUST-1 and NH₂-HKUST-1 crystals at -196 °C. H₂ and CO₂ adsorption capacities 7 were also measured by a Quantachrome, Autosorb IQ instrument at 0 °C and 25 °C, 8 and the measurement was taken at 0 °C for crystal sample. The degassing condition of 9 the samples was 120 °C for 10 h. Thermogravimetric analyses (TG and DSC) were 10 performed from 35 °C to 800 °C under nitrogen atmosphere with a 5 °C min⁻¹ heating 11 rate by using a NETZSCH (STA 449 F5) analyzer 12

13

14 2.5 Gas separation performance test of MMMs

The gas separation performance test was based on the Wicke-Kallenbach technique. 15 Before testing, membranes were activated at 120 °C for 24h under vacuum. Then, all 16 the mixed matrix membrane were place a stainless-steel module with an effective 17 membrane area of 1.77 cm². Both the one-component gas (H_2 , CO_2) permeability and 18 mixed two-component gas permeability and separation (H2/CO2) would be 19 characterized. The flow rate of feed gas was 100 ml min⁻¹, and the flow rate of 20 sweeping gas (Ar) at the permeate side was 40 ml min⁻¹ in order to avoid 21 concentration polarization. For two-component mixed gas, the gas flow ratio was 1:1. 22 A transmembrane pressure drop of 0.5 bar was maintained for all tests. The 23 composition of the permeated gases was detected by a gas chromatography (Scion, 24 456-GC). Each membrane sample would be tested at least 3 times to get the average 25 permeation data. The gas permeability of component i (P_i) in Barrer (1 Barrer = 1 \times 26 10^{-10} cm³ (STP)·cm·cm⁻²s⁻¹·cmHg⁻¹) of mixed matrix membranes was evaluated 27 based on Equation (1): 28

$$P_i = \frac{10^{-10} l N_i}{A \Delta p_i} \tag{1}$$

where N_i is the volume flow rate (cm³(STP)·s⁻¹), l is the membrane's thickness (m), ΔP_i is the transmembrane pressure drop (cmHg), and A is the effective membrane's area (m²).

32 The MMMs' selectivity $(\alpha_{i/i})$ was calculated according to Equation (2):

$$\alpha_{i/j} = \frac{X_i/X_j}{Y_i/Y_j} \tag{2}$$

where X_i/X_j and Y_i/Y_j are the volumetric fractions of the permeate and feed gas, respectively.

35

36 2.6 Thermodynamic calculation of gas permeation behavior of MMMs

In this work, E_P , E_D and ΔH_S were used to describe the permeation behavior of gases in MMM, which are the activation energies of permeation and diffusion and enthalpy 1 of sorption^[24, 25]. The relation between E_P , E_D and ΔH_S is presented by Equation (3):

$$E_P = E_D + \Delta H_S \tag{3}$$

2 E_P was calculated according to the Arrhenius empirical Equation (4):

$$\ln P = a - \frac{E_P}{RT} \tag{4}$$

- 3 Where P is the gas permeability, T is the measurement temperature (K), and R is the
- 4 ideal gas constant.
- 5 ΔH_s can be calculated using the Clausius-Clapperron Equation (5):

$$\ln p = \frac{\Delta H_S}{R} \frac{1}{T} + C \tag{5}$$

6 Where p (MPa) is the testing pressure, T (K) is the measurement temperature, and R is

- 7 the ideal gas constant.
- 8

9 **3 Results and discussion**

3.1 Structure analysis of NH₂-HKUST-1 and HKUST-1 samples

The X-Ray diffraction patterns of NH₂-HKUST-1 and HKUST-1 samples, together 11 with a simulated XRD pattern of HKUST-are shown in Figure 1 a-c. The 12 characteristic peaks for NH₂-HKUST-1 and HKUST-1 assigned to (111), (200), (220), 13 (222), and (400) planes are present in the patterns and they are in good agreement 14 with the simulated XRD, thus indicating the purity of the *in-situ* amino-modified 15 sample. Assuming that the crystallinity of the HKUST-1 is 100%, the relative 16 crystallinity of the NH₂-HKUST-1 is 88.52%. The average crystal size of HKUST-1 17 determined using Scheller's formula is 110 nm and of NH₂-HKUST-1 is 70 nm. The 18 difference in crystal size was also confirmed by SEM (Figure S1). The changes in 19 crystallinity and crystal size of NH₂-HKUST-1 are probably due to the introduction of 20 hetero-structured amine based organic ligands (2-Aminoterephthalic acid). The 21 deprotonation ability of 2-Aminoterephthalic acid ($pK_a \approx 3.95$) is stronger than that of 22 trimesic acid (pK₁=2.12, pK₂=4.10, pK₃=5.18), causing 2-Aminoterephthalic acid to 23 act as an capping agent thus inhibiting further growth of the crystals and leading to 24 the reduction of the crystal size. The structures of HKUST-1 and NH₂-HKUST-1 25 samples have been refined and a slight increase of crystal cell parameter a from 26.32 26 to 26.33 Å after amination, due to the partial substitution of organic ligands in the 27 28 crystal structure is observed for NH₂-HKUST-1 sample.



Figure 1 XRD patterns of (a) HKUST-1 (simulated), (b) HKUST-1 and (c) NH₂-HKUST-1 samples

1

2

3

The substitution ratio of the 2-aminoterephthalic acid in the NH₂-HKUST-1 was 4 calculated based on the elemental analysis (Table S1). The ratio of m 5 (2-aminoterephthalic acid): m (1,3,5-trihydroxybenzene) is calculated to be 1 : 5, 6 7 which is lower than the feeding ratio 1:2 in the initial precursor mixture. Based on 8 the XPS result (Figure S2), the ratio of m (2-aminoterephthalic acid): m (1,3,5-trihydroxybenzene) (1 : 1.3) of the outer surface of NH₂-HKUST-1 was found 9 to be higher than that of the bulk crystals suggesting the role of amine ligand as an 10 inhibitor. Thus we hypothesized that the amino-modified NH₂-HKUST-1 sample 11 12 exhibits a "core-shell" structure as schematically presented in Figure 2. Due to the capping effect of the 2-aminoterephthalic acid entering the skeleton, the crystals stop 13 14 growing, forming an outer surface with a higher amino ligand concentration.



Figure 2 Schematic presentation of NH₂-HKUST-1 "core-shell" structure: the gray band
 is the outer surface of NH₂-HKUST-1 crystals with a higher amine ligand
 (2-aminoterephthalic acid) amount

The effect of amination on the crystals porous structure was studied by nitrogen adsorption (Figure 3). After amination, the HKUST-1 and NH₂-HKUST-1 samples show a reduction of the BET surface area from 792.5 m^2g^{-1} to 662.3 m^2g^{-1} , respectively. While, the external surface area increased, due to the smaller particle size of NH_2 -HKUST-1, the micropore volume decreased. The pore size remained the same in both samples, which is consistent with XRD results. However, the decrease of

pore volume from 0.30 cm³/g to 0.23 cm³/g indicates the occupation of the pores by





Figure 3 N₂ adsorption isotherms of (a) HKUST-1 and (b) NH₂-HKUST-1 recorded at
--196 °C; *Inset:* results deduced from the N₂ adsorption measurements.

8 The adsorption results of HKUST-1 and NH₂-HKUST-1 samples further confirmed 9 the occupation of the pore space by the -NH₂ groups. Additionally, the NH₂-HKUST-1 10 exhibits lower CO₂ adsorption capacity as shown in Figure S3 in contrast to previous 11 reports on surface functionalized MOFs materials^[26, 27]. This result can be explained 12 with the reduced free pore volume of NH₂-HKUST-1 occupied by the amino groups. 13 The decreased adsorption rate indicates that the amino groups do not act as active 14 sites on NH₂-HKUST-1's surface.

15

The form of the 2-aminoterephthalic acid ligand in the NH₂-HKUST-1 structure under the action of the central metal Cu²⁺ was calculated using the $pm6^{[28]}$ method of Gaussian^[29]. The binding energy of $-NH_2$ groups in the pores of the NH₂-HKUST-1 is -348.51 kJ/mol, while outside, at the surface of the crystals is -339.77 kJ/mol (Figure 4). This result indicates that amino groups are more likely to be confined in the channels of the NH₂-HKUST-1 which is consistent with the N₂ adsorption results presented above.



Figure 4 Binding energy of amino group in the NH₂-HKUST-1 sample: (a) inside the
 channels and (b) outside the crystals

In order to further prove that the amino ligand enters in the pores of the crystals, both 4 samples HKUST-1 and NH₂-HKUST-1 were subjected to FT-IR charcatreization 5 (Figure 5). The bands corresponding to the vibrations of C-O (1375 cm⁻¹), benzene 6 ring (1564 cm⁻¹) and C=O (1644 cm⁻¹) are observed in both samples. Two new bands 7 in the spectrum of NH₂-HKUST-1's at 3237 cm⁻¹ and 3151 cm⁻¹ appeared and they are 8 attributed to the vibration of N-H^[21, 30] (Figure 5b). Also the peak at 1687 cm⁻¹ is 9 related to -NH2^[15]. The bands at 1161 cm⁻¹ and 1545 cm⁻¹ are corresponding to the 10 C-N bond^[21]. The new bands proved the presence of amino groups in NH₂-HKUST-1 11 sample. 12



13 14

1

Figure 5 FT-IR spectra of (a) HKUST-1 and (b) NH₂-HKUST-1 crystals

The TG study of both HKUST-1 and NH₂-HKUST-1 reveals the structural change at 270 °C and a residual mass of around 40% suggesting that the amine ligand has little effect on the structure (Figure S4). Before the decomposition and combustion of the organic ligand (270 °C), the weight loss of MOF crystal is mainly due to dehydration process, including the first step related to the removal of physically absorbed water

and the second step related to the release of chemisorbed water^[31, 32]. Two 1 endothermic peaks between 100 °C and 270 °C could be observed from the DTG 2 curves (Figure S4 inserted figure), which correspond to the two dehydration processes. 3 In NH₂-HKUST-1, the first physical dehydration step ended at 187 °C, higher than 4 that in HKUST-1 (164 °C), due to the stronger interaction formed by amino groups 5 and water molecules. Additionally, the thermal degradation of NH₂-HKUST-1 started 6 at a lower temperature, due to the -NH₂ groups which decomposed at lower 7 temperature^[33]. 8

9

10 **3.2 Structural analysis of membranes**

In our previous work we demonstrated that loading of crystals in the membranes with 11 less than 30% can avoid their agglomeration^[18]. Therefore, in this work, we will focus 12 on the MMMs with 10% and 30% filling amount. Seen from Figure S5, mixed matrix 13 membranes with different amounts of fillers have XRD patterns belonging to PEI and 14 MOF crystals, proving that HKUST-1 maintained its structure during the membrane 15 16 preparation. The intensity of crystal peaks of MMMs with the same filler enhanced with the increase of loading amount. The signal intensity of HKUST-1 filled 17 membranes are more obvious than that of NH₂-HKUST-1 filled membranes, which is 18 consistent with crystals' XRD patterns (Figure 1). 19

20

As can be seen in SEM images (Figure S6), all the mixed matrix membranes are continuous and the HKUST-1 particles are evenly distributed. It is worth noting that when the filling amount reaches 30%, the cross-section morphology of HKUST-1-30%/PEI MMM exhibited more obvious polymer veins than that of NH₂-HKUST-1-30%/PEI, which was caused by plastic deformation^[34]. This was related to the different interaction strength between the NH₂-HKUST-1 crystals and the PEI, which will be discussed below.

28

with with HKUST-1 (HKUST-1-10%/PEI 29 Compared membranes and HKUST-1-30%/PEI), the NH₂-HKUST-1-10%/PEI and NH₂-HKUST-1-30%/PEI 30 show an additional peak at 3237 cm⁻¹ representative of N-H bond^[21] (Figure S7). 31 Previous works reported on amino-functional fillers forming hydrogen bonds with 32 organic matrix, and the vibration of -NH₂ showed a significant blue shift^[26, 35, 36]. 33 While, no significant shift of this peak in the NH2-HKUST-1-10%/PEI and 34 NH2-HKUST-1-30%/PEI membranes is observed, indicating that the chemical 35 environment of N-H bond has not changed after loading in PEI matrix. It is suggested 36 that the amino groups are mainly present in the pores rather than on the outer surface. 37 The C=O band belonging to the PEI's 5-membered ring due to react with the Cu²⁺ 38 unsaturated metal sites exhibits an obvious blue shift in all samples. In the 39 HKUST-1-30%/PEI MMM (Figure S7 c), the C=O band shifts from 1777.3 cm⁻¹ to 40 1779.8 cm⁻¹. However, in the NH₂-HKUST-1-30%/PEI (Figure S7 e), the band 41 shifting is less only from 1777.3 cm⁻¹ to 1778.3 cm⁻¹. The electron donor -NH₂ group 42 leaded to an increase in the electron cloud density of the NH₂-HKUST-1 crystal, 43 which might weakened the interaction between the PEI polymer and NH₂-HKUST-1 44

1 crystals in the membranes. In summary, the amination of HKUST-1 does not improve

- 2 the interactions between the NH_2 -HKUST-1 and the PEI as expected.
- 3

The XPS results also showed that the interaction between NH₂-HKUST-1 and PEI 4 was not further enhanced. The XPS spectra for Cu $2p_{3/2}$ of the pure crystals and 5 membranes are shown in Figure S8. The XPS spectra of HKUST-1 (Figure S8a) and 6 NH₂-HKUST-1 (Figure S8b) contain a distinct peak at 934.97 eV and 934.95 eV, and 7 a satellite peaks ranged from 948 eV to 937 eV^[37, 38], respectively. The 8 NH₂-HKUST-1(Cu) is similar to HKUST-1(Cu), suggesting that the -NH₂ groups do 9 not coordinate with Cu^{2+} but may be protruding into the pores^[39]. By comparing the 10 spectra recorded on the membranes and pure HKUST-1, NH₂-HKUST-1 crystals, the 11 signal intensity of Cu 2p_{3/2} decreased. In the HKUST-1-30%/PEI membrane, the peak 12 shift is due to the effect of C=O on Cu²⁺ resulting in an increase of the electron cloud 13 density of Cu²⁺. While, the shift decreases for the NH₂-HKUST-1-30%/PEI membrane, 14 confirming the weakened interactions. 15

16

The TG of the membranes shows a significant inflection point around 300 °C, which 17 is consistent with the TG results of pure HKUST-1, NH2-HKUST-1 materials, 18 resulting from the collapse of their structure (Figure S9). DSC analysis before 300 °C 19 reveals the glass transition temperature (Tg) of the PEI polymer. Glass transition 20 temperature reflects the lowest temperature at which molecular segments in a polymer 21 can move. As can be seen from Figure 6, the Tg rises after filling appropriate amount 22 of HKUST-1 and NH₂-HKUST-1 particles. The HKUST-1-30%/PEI membrane with 23 24 the strongest interactions between PEI matrix and HKUST-1 crystals, has the highest Tg of 213.6 °C, thus further explaining the higher effect of HKUST-1 than 25 NH₂-HKUST-1 on the PEI. 26



27

Figure 6 Differential scanning calorimetry (DSC) curves of (a) pure PEI membrane, (b)
 HKUST-1-10%/PEI, (c) HKUST-1-30%/PEI, (d) NH₂-HKUST-1-10%/PEI and (e)
 NH₂-HKUST-1-30%/PEI with the glass transition temperature (*Tg*)

31 **3.3** Gas separation performance of membranes

32 The H_2 and CO_2 single gas permeability of the pure PEI membrane and the mixed

matrix membranes were measured at 25 °C. The permeability and ideal selectivity 1 obtained for all membranes are depicted in Figure 7 and summarized in Table S2. 2 3 Overall, the H₂ permeability and selectivity of the MMMs improved with the addition of both HKUST-1 and NH₂-HKUST-1 compared with the parent PEI membrane. With 4 the increase of the loading amount of the same filler (HKUST-1 or NH₂-HKUST-1), 5 the H_2 permeability increased. However, all MMMs exhibited reduced CO_2 6 permeability, suggesting that both HKUST-1 and NH₂-HKUST-1 fillers did not affect 7 8 the CO₂ permeance. The different trends in permeability of H₂ and CO₂ stated that the effect of non-selective interface defects was low in MMMs. This is consistent with the 9 results presented in Figure S7, where the interactions between the filler (HKUST-1 10 and NH₂-HKUST-1) and the PEI matrix were proved. 11

12

29

In order to further understand the effect of amino-modification of HKUST-1 on 13 MMMs, the performance of NH₂-HKUST-1-30%/PEI and HKUST-1-30%/PEI was 14 compared. NH₂-HKUST-1 sample has smaller crystal size than the HKUST-1 (Figure 15 S1). Generally, the reduction in crystal size leads to enhanced interfacial forces 16 between the filler and the matrix. While, according to the IR and TG analysis of 17 MMMs, we found that the interfacial interactions were not enhanced in the 18 NH₂-HKUST-1-30%/PEI membrane. Therefore, we assume that the effect of 19 interfacial voids caused by size reduction has little effect on membrane's permeability. 20 The lower permeability of NH₂-HKUST-1-30%/PEI membrane for both H₂ and CO₂ 21 was mainly due to the pore blockage by -NH2 groups. While, there was a little 22 selectivity from 21.0 (HKUST-1-30%/PEI) 21.9 increase in ideal to 23 (NH₂-HKUST-1-30%/PEI), since the diffusion of large CO₂ molecule was more easily 24 limited by the narrowed diffusion channels. Thus, the amino groups located in the 25 of membranes' permeability; there 26 pores caused a loss membranes (NH₂-HKUST-1-10%/PEI and NH₂-HKUST-1-30%/PEI) were not subjected to 27 optimization. 28



Figure 7 Single gas separation performance of pristine PEI membrane and mixed

matrix membranes HKUST-1/PEI and NH₂-HKUST-1 measured at 25 °C

1

9

The mixed gas separation performance of the MMMs has the similar trend as the single component gas separation testing (Figure 8 and Table S3). The NH₂-HKUST-1-30%/PEI membrane showed a decrease gas permeability for both H₂ and CO₂ with a slight improved selectivity. However, due to the competitive adsorption of H₂ and CO₂, the mixed gas separation performance (both permeability and selectivity) of this membrane was lower than that of the single component gas separation performance.



Figure 8 Mixed gas separation performance of pristine PEI membrane and mixed
 matrix membranes HKUST-1/PEI and NH₂-HKUST-1 measured at 25 °C

The Robeson upper boundary (2008) was used to evaluate the H_2/CO_2 separation 12 performance of HKUST-1-30%/PEI and NH2-HKUST-1-30%/PEI MMMs (Figure 9 13 and Table S5)^[40]. First, we found that the H_2/CO_2 separation performances of 14 PEI-based MMMs, filling small pore MOFs (such as ZIF-8, ZIF-90, ZIF-12), were 15 close to the upper boundary. Compared with pure PEI membranes, the main 16 contribution of filler materials was the improvement of H₂ permeability. After adding 17 HKUST-1 or NH₂-HKUST-1, the H₂ permeability of HKUST-1-30%/PEI and 18 NH₂-HKUST-1-30%/PEI MMMs was improved more significantly, and the selectivity 19 also increased. As HKUST-1 does not have molecular sieving property for H₂/CO₂ 20 separation, its highly permeable channels mainly contributed to the performance's 21 optimization under the "adsorption-diffusion coupling control" mechanism. 22 Nevertheless, the amino-functionalization exhibited a negative effect on the high 23 permeability of MMMs due to the pore blockage. Second, there is a performance 24 gap between our work and other high efficient MMMs, which is mainly related to the 25 intrinsic separation performance of the matrix materials. Efficient matrices, such as 26 polybenzimidazole (PBI), polyimides (PIs), and polymers of intrinsic microporosity 27 (PIMs), generally exhibit high intrinsic gas permeability and selectivity. However, the 28 price, synthesis process, processibility and mechanical strength of matrices should 29

12

1 also be considered. The PBI matrix is an expensive and difficult to process, the PIMs

2 matrix shows poor mechanical properties. Compared with them, the PEIs showed



3 high mechanical stability and economically viable for applications.

4

Figure 9 H₂/CO₂ separation performance of MMMs via Robeson upper bound (2008)^[40];
 details are shown in Table S5^[41, 60]

As discussed in the introduction section, the main challenge for MMMs for H_2/CO_2 separation is the high adsorption and solubility of CO_2 in MMMs, which results in lower H_2/CO_2 selectivity compared to other gas pairs that requires high CO_2 permeability, such as CO_2/CH_4 . This work provides new strategy to achieve H_2/CO_2 separation by utilizing HKUST-1 crystals with big pores. While, the amino-functionalization of the HKUST-1 crystals leading to pore blockage has a negative effect on the separation.

14

15 **3.4 Gas separation mechanism**

In our previous work, we reported the "adsorption-diffusion coupling control" 16 separation mechanism under addition of large-pore HKUST-1 in the MMM for 17 separation of small H₂ molecules from CO₂ molecules, thus suggesting the diffusion 18 control H_2 permeation and adsorption prevention of CO_2 permeation^[18]. Here, we 19 studied the role of amino groups in the HKUST-1 crystals. According to the gas 20 separation results, we found that the diffusion of gas molecules was blocked by the 21 amino-functional groups of the NH₂-HKUST-1-30%/PEI mainly occupying the 22 permeable channels, resulting in decreased permeability for both H₂ and CO₂. In 23 addition, the small NH₂-HKUST-1 crystals used in this work did not show obvious 24 enhancement of the interfacial voids. Thermodynamic study was used to elucidate the 25 26 pore blockage and adsorption effect of -NH₂ groups (Table 1 and Figure S4). Firstly, 27 the activation energy of permeation (E_P) of the small H₂ molecules is lower than that of the big CO₂ molecules, resulting in high H₂/CO₂ selectivity of the membranes. 28 Secondly, the decreased $\Delta H_{S (H2 and CO2)}$ of NH₂-HKUST-1-30%/PEI membrane 29

1 showed that the amino groups has little effect on the adsorption property of the 2 MMMs, which may be due to the unexposed adsorption sites. The higher $E_{D(H2 \text{ and } CO2)}$ 3 for NH₂-HKUST-1-30%/PEI than for HKUST-1-30%/PEI probably is resulted from 4 the pore blockage. The $\Delta E_{D(CO2)}$ is bigger than the $\Delta E_{D(H2)}$, indicating that the pore 5 blockage with -NH₂ groups had a greater effect on the CO₂ molecules. Thereby, the 6 presence of amino groups in the HKUST-1's pores results in pore blockage, and 7 eventually led to the deterioration of the membranes permeability.

8	Table 1 Thermodynamic calculations of mixed matrix membranes					
	Gas	Membrane	E _P (kJ/mol)	Δ H _S (kJ/mol)	E _D (kJ/mol)	
	H_2	HKUST-1-30%/PEI	5.3	-12.4	17.7	
		NH2-HKUST-1-30%/PEI	6.0	-11.9	17.9	
	CO ₂	HKUST-1-30%/PEI	10.9	-24.8	35.7	
		NH ₂ -HKUST-1-30%/PEI	15.8	-21.8	37.6	

10 4 Conclusions

9

NH2-HKUST-1 was synthesized successfully and thoroughly characterized in 11 comparison to the parent HKUST-1 sample. FT-IR results confirmed the introduction 12 of -NH₂ in the HKUST-1's sample. The crystallinity and spatial distribution of amino 13 groups showed that the amino ligand (2-Aminoterephthalic acid) mainly is present on 14 the outer surface of NH₂-HKUST-1 due to the end-capping effect, forming a 15 "core-shell" crystal structure. While, the N₂ adsorption results and theoretical 16 calculation suggested that the -NH2 groups of the ligand tend to be constrained in the 17 pores of NH₂-HKUST-1 crystals under the action of Cu²⁺ resulting in pore blockage. 18 As a result, the mixed matrix membranes prepared (NH₂-HKUST-1/PEI) did not 19 exhibit enhanced interfacial interactions. Furthermore, the pore blockage seriously 20 affected the diffusion of the gas molecules, leading to decrease of the gas permeability 21 of the NH₂-HKUST-1-30%/PEI membrane. Despite the little improvement in 22 selectivity, the sacrifice of permeability makes the amino-modification not an 23 appropriate optimization strategy for preparation of MMMs. This work demonstrated 24 the negative effect of amino-modification/functionalization to the HKUST-1 materials 25 on MMMs performance. Further the spatial distribution of amino groups in the 26 HKUST-1 should be considered and optimize prior using for MMMs fabrication. 27

28

29 Declaration of Competing Interest

30 The authors declare that they have no known competing financial interests or personal

- relationships that could have appeared to influence the work reported in this paper.
- 32

33 Acknowledgements

This work was supported by National Key Research and Development Program of China of Ministry of Science and Technology (2022YFE0116000), National Natural Science Foundation of China (No. 22175200, No. 21975285), the Fundamental
 Research Funds for the Central Universities (No. 21CX06024A), and Qingdao
 Postdoctoral Research Project (No. qdyy20210005), Fujian Province Science and
 Technology Program, Innovation Fund (2022C0021).

5

6 **References**

- [1]L. Shao, B. T. Low, T. Chung, A. R. Greenberg, Polymeric Membranes for the Hydrogen
 Economy: Contemporary Approaches and Prospects for the Future, J. Membrane Sci.,
 327 (2009) 18-31. https://doi.org/10.1016/j.memsci.2008.11.019.
- [2]D. Sholl, R. Lively, Seven Chemical Separations to Change the World, Nature, 532 (2016)
 435-437. https://doi.org/10.1038/532435a.
- [3]M. Galizia, W. S. Chi, Z. P. Smith, T. C. Merkel, R. W. Baker, B. D. Freeman, 50Th
 Anniversary Perspective : Polymers and Mixed Matrix Membranes for Gas and Vapor
 Separation: A Review and Prospective Opportunities, Macromolecules, 50 (2017)
 7809-7843. https://doi.org/10.1021/acs.macromol.7b01718.
- 16 [4]M. Ahmadi, S. Janakiram, Z. Dai, L. Ansaloni, L. Deng, Performance of Mixed Matrix 17 Membranes Containing Porous Two-Dimensional (2D) and Three-Dimensional (3D) 18 Fillers for CO_2 Separation: A Review, Membranes. 8 (2018)1-50. 19 https://doi.org/10.3390/membranes8030050.
- [5]A. R. Kamble, C. M. Patel, Z. V. P. Murthy, A Review On the Recent Advances in Mixed
 Matrix Membranes for Gas Separation Processes, Renew. Sust. Energ. Rev., 145 (2021)
 111062. https://doi.org/10.1016/j.rser.2021.111062.
- [6]Q. Qian, P. A. Asinger, M. J. Lee, G. Han, K. Mizrahi Rodriguez, S. Lin, F. M. Benedetti,
 A. X. Wu, W. S. Chi, Z. P. Smith, MOF-Based Membranes for Gas Separations, Chem.
 Rev., 120 (2020) 8161-8266. https://doi.org/10.1021/acs.chemrev.0c00119.
- [7]W. K. Setiawan, K. Chiang, Silica Applied as Mixed Matrix Membrane Inorganic Filler
 for Gas Separation: A Review, Sustain. Environ. Res., 29 (2019) 29-32.
 https://doi.org/10.1186/s42834-019-0028-1.
- [8]D. Bastani, N. Esmaeili, M. Asadollahi, Polymeric Mixed Matrix Membranes Containing
 Zeolites as a Filler for Gas Separation Applications: A Review, J. Ind. Eng. Chem., 19
 (2013) 375-393. https://doi.org/10.1016/j.jiec.2012.09.019.
- [9]S. H. Goh, H. S. Lau, W. F. Yong, Metal–Organic Frameworks (MOFs)- Based Mixed
 Matrix Membranes (MMMs) for Gas Separation: A Review On Advanced Materials in
 Harsh Environmental Applications, Small, 18 (2022) 2107536.
 https://doi.org/10.1002/smll.202107536.
- [10]Y. Cheng, S. J. Datta, S. Zhou, J. Jia, O. Shekhah, M. Eddaoudi, Advances in
 Metal-Organic Framework-Based Membranes, Chem. Soc. Rev., 51 (2022) 8300-8350.
 https://doi.org/10.1039/d2cs00031h.
- [11]M. Kalaj, K. C. Bentz, S. Ayala, J. M. Palomba, K. S. Barcus, Y. Katayama, S. M. Cohen,
 MOF-Polymer Hybrid Materials: From Simple Composites to Tailored Architectures,
 Chem. Rev., 120 (2020) 8267-8302. https://doi.org/10.1021/acs.chemrev.9b00575.
- 42 [12]M. W. Anjum, F. Vermoortele, A. L. Khan, B. Bueken, D. E. De Vos, I. F. J.
 43 Vankelecom, Modulated UiO-66-Based Mixed-Matrix Membranes for CO₂ Separation,

- ACS Appl. Mater. Inter., 7 (2015) 25193-25201. https://doi.org/10.1021/acsami.5b08964. 1 2 [13]H. Molavi, A. Shojaei, S. A. Mousavi, Improving Mixed-Matrix Membrane 3 Performancevia Pmma Grafting From Functionalized NH2-UiO-66, J. Mater. Chem. A, 6 4 (2018) 2775-2791. https://doi.org/10.1039/C7TA10480D. 5 [14]S. Meshkat, S. Kaliaguine, D. Rodrigue, Mixed Matrix Membranes Based On Amine and 6 Non-Amine MiL-53(Al) in Pebax® MH-1657 for CO₂ Separation, Sep. Purif. Technol., 7 200 (2018) 177-190. https://doi.org/10.1016/j.seppur.2018.02.038. 8 [15]N. Tien-Binh, H. Vinh-Thang, X. Y. Chen, D. Rodrigue, S. Kaliaguine, Polymer Functionalization to Enhance Interface Quality of Mixed Matrix Membranes for High 9 10 CO_2/CH_4 Gas Separation, J. Mater. Chem. Α, 3 (2015)1522-15213. 11 https://doi.org/10.1039/c5ta01597a. 12 [16]Y. Pu, Z. Yang, V. Wee, Z. Wu, Z. Jiang, D. Zhao, Amino-Functionalized NUS-8 13 Nanosheets as Fillers in PIM-1 Mixed Matrix Membranes for CO₂ Separations, J. Membrane Sci., 641 (2022) 119912. https://doi.org/10.1016/j.memsci.2021.119912. 14 15 [17]F. N. Al-Rowaili, M. Khaled, A. Jamal, U. Zahid, Mixed Matrix Membranes for H₂/CO₂ 16 Gas Separation-A Critical Review. Fuel. 333 (2023)126285. 17 https://doi.org/10.1016/j.fuel.2022.126285. [18]Y. Wang, G. Yang, H. Guo, X. Meng, G. Kong, Z. Kang, R. Guillet-Nicolas, S. Mintova, 18 Preparation of HKUST-1/PEI Mixed-Matrix Membranes: Adsorption-Diffusion Coupling 19 20 Control of Small Gas Molecules, J. Membrane Sci., 643 (2022) 120070. https://doi.org/10.1016/j.memsci.2021.120070. 21 [19]F. Hamidavi, A. Kargari, A. Eliassi, Sorption and Permeation Study 22 of 23 Polyetherimide/Hydrophobic Silica Nanocomposite Membrane for Effective Syngas 24 $(H_2/CO/CO_2)$ Separation, Purif. Technol., 279 (2021)119774. Sep. 25 https://doi.org/10.1016/j.seppur.2021.119774. [20]J. Hu, H. Cai, H. Ren, Y. Wei, Z. Xu, H. Liu, Y. Hu, Mixed-Matrix Membrane Hollow 26 Fibers of Cu₃(BTC)₂ MOF and Polyimide for Gas Separation and Adsorption, Ind. Eng. 27 28 Chem. Res., 49 (2010) 12605-12612. https://doi.org/10.1021/ie1014958. 29 [21]B. Ge, Y. Xu, H. Zhao, H. Sun, Y. Guo, W. Wang, High Performance Gas Separation 30 Mixed Matrix Membrane Fabricated by Incorporation of Functionalized 31 Submicrometer-Sized Metal-Organic Framework, Materials, 11 (2018) 1421. 32 https://doi.org/10.3390/ma11081421. [22]K. Pirzadeh, K. Esfandiari, A. A. Ghoreyshi, M. Rahimnejad, CO₂ and N₂ Adsorption and 33 34 Separation Using Aminated UiO-66 and Cu₃(BTC)₂: A Comparative Study, Korean J. 35 Chem. Eng., 37 (2020) 513-524. https://doi.org/10.1007/s11814-019-0433-5. [23]Y. Wang, H. Ge, Y. Wu, G. Ye, H. Chen, X. Hu, Construction of an Electrochemical 36 Sensor Based On Amino-Functionalized Metal-Organic Frameworks for Differential 37 Pulse Anodic Stripping Voltammetric Determination of Lead, Talanta, 129 (2014) 38 39 100-105. https://doi.org/10.1016/j.talanta.2014.05.014. [24]K. A. Stevens, J. D. Moon, H. Borjigin, R. Liu, R. M. Joseph, J. S. Riffle, B. D. Freeman, 40 41 Influence of Temperature On Gas Transport Properties of Tetraaminodiphenylsulfone 42 (TADPS) Based Polybenzimidazoles, J. Membrane Sci., 593 (2020) 117427. 43 https://doi.org/10.1016/j.memsci.2019.117427. [25]A. Fuoco, B. Satilmis, T. Uyar, M. Monteleone, E. Esposito, C. Muzzi, E. Tocci, M. 44
 - 16

Longo, M. P. De Santo, M. Lanč, K. Friess, O. Vopička, P. Izák, J. C. Jansen, 1 2 Comparison of Pure and Mixed Gas Permeation of the Highly Fluorinated Polymer of 3 Intrinsic Microporosity PIM-2 Under Dry and Humid Conditions: Experiment and 594 4 Modelling, J. Membrane Sci., (2020)117460. 5 https://doi.org/10.1016/j.memsci.2019.117460.

- 6 [26]O. G. Nik, X. Y. Chen, S. Kaliaguine, Functionalized Metal Organic
 7 Framework-Polyimide Mixed Matrix Membranes for CO₂/CH₄ Separation, J. Membrane
 8 Sci., 413-414 (2012) 48-61. https://doi.org/10.1016/j.memsci.2012.04.003.
- 9 [27]H. Molavi, A. Shojaei, Mixed-Matrix Composite Membranes Based On UiO-66-Derived
 MOFs for CO₂ Separation, ACS Appl. Mater. Inter., 11 (2019) 9448-9461.
 https://doi.org/10.1021/acsami.8b20869.
- [28]J. J. P. Stewart, Optimization of Parameters for Semiempirical Methods V: Modification
 of NDDO Approximations and Application to 70 Elements, J. Mol. Model., 13 (2007)
 1173-1213. https://doi.org/10.1007/s00894-007-0233-4.
- [29]M. Jfg, W. Trucks, H. B. Schlegel, G. E. Scuseria, M. A. Robb, J. R. Cheeseman, G.
 Scalmani, V. Barone, B. Mennucci, G. A. Petersson, Gaussian 09, Revision a. 1;
 Gaussian (2009).
- 18 [30]B. C. E. Silva, K. Irikura, R. C. G. Frem, M. V. B. Zanoni, Effect of Cu(BDC-NH₂) Mof 19 Deposited On Cu/Cu₂O Electrode and its Better Performance in Photoelectrocatalytic 20 of Electroanal. 880 (2021) Reduction CO_2 , J. Chem., 114856. https://doi.org/10.1016/j.jelechem.2020.114856. 21
- [31]F. Israr, D. K. Kim, Y. Kim, S. J. Oh, K. C. Ng, W. Chun, Synthesis of Porous Cu- BTC
 with Ultrasonic Treatment: Effects of Ultrasonic Power and Solvent Condition, Ultrason.
 Sonochem., 29 (2016) 186-193. https://doi.org/10.1016/j.ultsonch.2015.08.023.
- [32]A. Domán, J. Madarász, K. László, In Situ Evolved Gas Analysis Assisted
 Thermogravimetric (Tg-FTIR and Tg/DTA–MS) Studies On Non-Activated Copper
 Benzene-1,3,5-Tricarboxylate, Thermochim. Acta, 647 (2017) 62-69.
 https://doi.org/10.1016/j.tca.2016.11.013.
- [33]R. Abedini, M. Omidkhah, F. Dorosti, Highly Permeable
 Poly(4-Methyl-1-Pentyne)/NH₂-MiL53(Al) Mixed Matrix Membrane for CO₂/CH₄
 Separation, RSC Adv. (2014) 36522-36537. https://doi.org/10.1039/C4RA07030E.
- [34]E. V. Perez, K. J. Balkus, J. P. Ferraris, I. H. Musselman, Metal-Organic Polyhedra 18
 Mixed-Matrix Membranes for Gas Separation, J. Membrane Sci., 463 (2014) 82-93.
 https://doi.org/10.1016/j.memsci.2014.03.045.
- [35]Q. Xin, J. Ouyang, T. Liu, Z. Li, Z. Li, Y. Liu, S. Wang, H. Wu, Z. Jiang, X. Cao,
 Enhanced Interfacial Interaction and CO₂ Separation Performance of Mixed Matrix
 Membrane by Incorporating Polyethylenimine-Decorated Metal–Organic Frameworks,
 ACS Appl. Mater. Inter., 7 (2015) 1065-1077. https://doi.org/10.1021/am504742q.
- [36]B. Zornoza, A. Martinez-Joaristi, P. Serra-Crespo, C. Tellez, J. Coronas, J. Gascon, F.
 Kapteijn, Functionalized Flexible MOFs as Fillers in Mixed Matrix Membranes for
 Highly Selective Separation of CO₂ From CH₄ at Elevated Pressures, Chem. Commun.,
 47 (2011) 9522-9524. https://doi.org/10.1039/c1cc13431k.
- 43 [37]A. S. Duke, E. A. Dolgopolova, R. P. Galhenage, S. C. Ammal, A. Heyden, M. D. Smith,
- 44 D. A. Chen, N. B. Shustova, Active Sites in Copper-Based Metal–Organic Frameworks:

- Understanding Substrate Dynamics, Redox Processes, and Valence-Band Structure, J.
 Phys Chem. C, 119 (2015) 27457-27466. https://doi.org/10.1021/acs.jpcc.5b08053.
- 3 [38]Y. Wu, H. Zhang, Y. Yan, J. Peng, High Efficient HKUST-1 Membrane Over Paper-Like
 4 Steel Fibers for Direct Catalytic Wet Peroxide Oxidation of Phenol, Mater. Chem. Phys.,
 5 252 (2020) 123119. https://doi.org/10.1016/j.matchemphys.2020.123119.
- [39]H. Wang, X. Yuan, Y. Wu, G. Zeng, X. Chen, L. Leng, Z. Wu, L. Jiang, H. Li, Facile
 Synthesis of Amino-Functionalized Titanium Metal-Organic Frameworks and their
 Superior Visible-Light Photocatalytic Activity for Cr(Vi) Reduction, J. Hazard. Mater.,
 286 (2015) 187-194. https://doi.org/10.1016/j.jhazmat.2014.11.039.
- [40]L. M. Robeson, The Upper Bound Revisited, J. Membrane Sci., 320 (2008) 390-400.
 https://doi.org/10.1016/j.memsci.2008.04.030.
- [41]G. Li, Z. Si, S. Yang, Y. Zhuang, S. Pang, Y. Cui, J. Baeyens, P. Qin, A Defects-Free
 ZIF-90/6FDA-Durene Membrane Based On the Hydrogen Bonding/Covalent Bonding
 Interaction for Gas Separation, J. Membrane Sci., 661 (2022) 120910.
 https://doi.org/10.1016/j.memsci.2022.120910.
- [42]X. Jiang, S. He, G. Han, J. Long, S. Li, C. H. Lau, S. Zhang, L. Shao, Aqueous One-Step
 Modulation for Synthesizing Monodispersed ZIF-8 Nanocrystals for Mixed-Matrix
 Membrane, ACS Appl. Mater. Inter., 13 (2021) 11296-11305.
 https://doi.org/10.1021/acsami.0c22910.
- [43]M. Usman, M. Y. Khan, T. Anjum, A. L. Khan, B. Hoque, A. Helal, A. S. Hakeem, B. A.
 Al-Maythalony, Controlled Covalent Functionalization of ZIF-90 for Selective CO₂
 Capture & Separation, Membranes, 12 (2022) 1055.
 https://doi.org/10.3390/membranes12111055.
- [44]M. Boroglu, I. Boz, B. Kaya, Effect of New Metal-Organic Framework (Zeolitic
 Imidazolate Framework [ZIF-12]) in Mixed Matrix Membranes On Structure,
 Morphology, and Gas Separation Properties, J. Polym. Eng., 41 (2021) 259-270.
 https://doi.org/10.1515/polyeng-2020-0288.
- [45]M. Safak Boroglu, M. Ugur, I. Boz, Enhanced Gas Transport Properties of Mixed Matrix
 Membranes Consisting of Matrimid and RHO Type ZIF-12 Particles, Chem. Eng. Res.
 Des., 123 (2017) 201-213. https://doi.org/10.1016/j.cherd.2017.05.010.
- [46]S. Japip, K. Liao, Y. Xiao, T. Chung, Enhancement of Molecular-Sieving Properties by
 Constructing Surface Nano-Metric Layer Via Vapor Cross-Linking, J. Membrane Sci.,
 497 (2016) 248-258. https://doi.org/10.1016/j.memsci.2015.09.045.
- [47]L. Hu, V. T. Bui, S. Pal, W. Guo, A. Subramanian, K. Kisslinger, S. Fan, C. Y. Nam, Y.
 Ding, H. Lin, In Situ Growth of Crystalline and Polymer- Incorporated Amorphous ZIFs
 in Polybenzimidazole Achieving Hierarchical Nanostructures for Carbon Capture, Small,
 18 (2022) 2201982. https://doi.org/10.1002/smll.202201982.
- [48]D. Carter, F. H. Tezel, B. Kruczek, H. Kalipcilar, Investigation and Comparison of Mixed
 Matrix Membranes Composed of Polyimide Matrimid with ZIF-8, Silicalite, and SAPO34, J. Membrane Sci., 544 (2017) 35-46. https://doi.org/10.1016/j.memsci.2017.08.068.
- [49]L. Diestel, N. Wang, A. Schulz, F. Steinbach, J. Caro, Matrimid-Based Mixed Matrix
 Membranes: Interpretation and Correlation of Experimental Findings for Zeolitic
 Imidazolate Frameworks as Fillers in H₂/CO₂ Separation, Ind. Eng. Chem. Res., 54 (2015)
 1103-1112. https://doi.org/10.1021/ie504096j.

[50]S. Yang, Y. Wang, P. Lu, H. Jin, F. Pan, Z. Shi, X. Jiang, C. Chen, Z. Jiang, Y. Li,
 Metal–Organic Frameworks Corset with a Thermosetting Polymer for Improved
 Molecular-Sieving Property of Mixed-Matrix Membranes, ACS Appl. Mater. Inter., 12
 (2020) 55308-55315. https://doi.org/10.1021/acsami.0c17426.

[51]R. Martinez-Tirado, N. Yuriychuk, M. Iglesias, M. López-González, E. M. Maya, Mixed
Matrix Membranes Containing a Biphenyl-Based Knitting Aryl Polymer and Gas
Separation Performance, Membranes, 11 (2021) 914.
https://doi.org/10.3390/membranes11120914.

[52]M. Arjmandi, M. Pakizeh, Mixed Matrix Membranes Incorporated with Cubic-MOF-5 for
Improved Polyetherimide Gas Separation Membranes: Theory and Experiment, J. Ind.
Eng. Chem., 20 (2014) 3857-3868. https://doi.org/10.1016/j.jiec.2013.12.091.

- [53]S. Zid, P. Alcouffe, M. Zinet, E. Espuche, Mixed-Matrix Membranes Based On
 Polyetherimide, Metal–Organic Framework and Ionic Liquid: Influence of the
 Composition and Morphology On Gas Transport Properties, Polymers, 14 (2022) 3489.
 https://doi.org/10.3390/polym14173489.
- [54]Y. Zhang, K. J. Balkus, I. H. Musselman, J. P. Ferraris, Mixed-Matrix Membranes
 Composed of Matrimid® and Mesoporous ZSM-5 Nanoparticles, J. Membrane Sci., 325
 (2008) 28-39. https://doi.org/10.1016/j.memsci.2008.04.063.
- [55]E. V. Perez, K. J. Balkus, J. P. Ferraris, I. H. Musselman, Mixed-Matrix Membranes
 Containing MOF-5 for Gas Separations, J. Membrane Sci., 328 (2009) 165-173.
 https://doi.org/10.1016/j.memsci.2008.12.006.
- [56]X. Ma, X. Wu, J. Caro, A. Huang, Polymer Composite Membrane with Penetrating
 ZIF- 7 Sheets Displays High Hydrogen Permselectivity, Angew. Chem. Int. Edit., 131
 (2019) 16302-16306. https://doi.org/10.1002/ange.201911226.
- [57]L. Zhu, D. Yin, Y. Qin, S. Konda, S. Zhang, A. Zhu, S. Liu, T. Xu, M. T. Swihart, H. Lin,
 Sorption- Enhanced Mixed Matrix Membranes with Facilitated Hydrogen Transport for
 Hydrogen Purification and CO₂ Capture, Adv. Funct. Mater., 29 (2019) 1904357.
 https://doi.org/10.1002/adfm.201904357.
- [58]A. I. Romero, M. L. Parentis, A. C. Habert, E. E. Gonzo, Synthesis of
 Polyetherimide/Silica Hybrid Membranes by the Sol–Gel Process: Influence of the
 Reaction Conditions On the Membrane Properties, J. Mater. Sci., 46 (2011) 4701-4709.
 https://doi.org/10.1007/s10853-011-5380-4.
- [59]M. Arjmandi, M. Pakizeh, O. Pirouzram, The Role of Tetragonal-Metal-Organic
 Framework-5 Loadings with Extra ZnO Molecule On the Gas Separation Performance of
 Mixed Matrix Membrane, Korean J. Chem. Eng., 32 (2015) 1178-1187.
 https://doi.org/10.1007/s11814-014-0315-9.
- [60]Q. Song, S. K. Nataraj, M. V. Roussenova, J. C. Tan, D. J. Hughes, W. Li, P. Bourgoin,
 M. A. Alam, A. K. Cheetham, S. A. Al-Muhtaseb, E. Sivaniah, Zeolitic Imidazolate
 Framework (ZIF-8) Based Polymer Nanocomposite Membranes for Gas Separation,
 Energ. Environ. Sci., 5 (2012) 8359-8369. https://doi.org/10.1039/c2ee21996d.
 - 19