



New polyurethane and polyurethane-acrylate materials prepared from aqueous dispersions

Maribel Pineda, Françoise Méchin, Jean-Pierre Pascault

► To cite this version:

Maribel Pineda, Françoise Méchin, Jean-Pierre Pascault. New polyurethane and polyurethane-acrylate materials prepared from aqueous dispersions. Polymers In Dispersed Media (PDM) 2004, Apr 2004, Lyon, France. hal-04285197

HAL Id: hal-04285197

<https://hal.science/hal-04285197>

Submitted on 14 Nov 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

NEW POLYURETHANE AND POLYURETHANE-ACRYLATE MATERIALS PREPARED FROM AQUEOUS DISPERSIONS

Maribel PINEDA, Françoise MECHIN, Jean-Pierre PASCAULT


Laboratoire des Matériaux Macromoléculaires-IMP, UMR CNRS n°5627,
INSA de Lyon, Villeurbanne, FRANCE

Object

The synthesis of curable aqueous based polyurethane dispersions and the analysis of the mechanical properties of films thereof (case of a UV-curable polyurethane-acrylate dispersion, thermally-curable polyurethane-glycidyl dispersions and two-component curable polyurethane dispersions)



PU Ionomer Dispersion

Synthesis of PU-ionomer aqueous dispersion




Important parameters:


- a) Addition rate of water solutions (TEA, EDA)
- b) Stirring rate
- c) Temperature during the dispersion formation



Effect of NCO/OH ratio prepolymer (viscosity at the time of phase inversion) and type of stirring device



Effect of the diisocyanate nature, (stirrer "b")




Characteristics of prepolymer and final dispersions: experiments with IPDI and ratio NCO/OH=1.4; stirrer C

Experiment #	prepolymer measured (theoretical 2.48)	M _w prepolymer (theoretical 6453) (g/mol)**	Temperature (prepolymer) (°C)	Temperature (TEA/H ₂ O) (°C)	Temperature (dispersion) (°C)	Mean diameter (μm)
1	2.57	5730	55	20	25	0.17
2	2.50	6030	55	21	27	0.12
2***					30	1.76
3	2.58	6220	58	20	33	0.16
4	2.55	6380	58	20	34	0.16

*NCO/OH $\text{a}_{\text{C}-\text{O}-\text{H}} = 14$; FINAL SOLID CONTENT= 35%

**From size exclusion chromatography according to polystyrene standards

***Prepolymer #2 was divided in 2 parts; dispersion #2 was obtained with a standard turbine instead of the high efficiency impeller c and shows 2 populations




precise control of temperature and addition rates at every stage
→ well-defined, reproducible molar masses and size distributions for both prepolymer and final PU dispersions, stability > 9 months


The thermal and mechanical properties

drying conditions: 12 days at room temperature & atmospheric pressure, then 24 h at 60°C, under a vacuum → film thickness ≈ 1mm


Effect of the photopolymerization reaction on the PU-acrylate (5) network




Effect of temperature on the PU-glycidol (6) network




External crosslinkers for the PU dispersions



Effect of crosslinkers on the PU-glycidol (6) network



Effect of HDI trimer crosslinker on the PU-Ethylene glycol (7) and PU-urea (1) network



- PUA networks still incompletely crosslinked
→ too high initial molar mass for PUA macromolecules
→ too low amount of photoinitiator?
- Using additional crosslinkers, entirely crosslinked materials are obtained
→ the functionality of the macromolecular precursors is close to 2
→ strong improvement of the thermal and mechanical behavior

Conclusions and future work

- A reproducible process was designed for the preparation of stable aqueous dispersions of isocyanate-terminated polyurethane macromolecules with versatile post-curing modes
 - Important parameters for prepolymer synthesis:
 - Effect of several ratios: NCO/OH, PCL:DMPA, % of DMPA neutralization
 - Parameters for the formation of PU aqueous dispersion:
 - Control of the size distribution and stability
- Starting from the same aqueous dispersions of isocyanate-terminated PU and using various chemistries (one- or two-component, thermal or UV initiation), thin or thick films with very good mechanical properties and thermal resistance can be obtained.
One-component systems could still be further improved (better UV-crosslinking, use of self-assembling end units...)
- Addition rate of TEA solution
• Temperature during dispersion formation $T^{\circ}\text{C} = 30-35^{\circ}\text{C}$