



## Characterization of polymer brushes deposited on gold surfaces by 1D and 3D-AFM in liquid

Dahlia Saad, Frédéric Dubreuil, Magali Phaner-Goutorbe

### ► To cite this version:

Dahlia Saad, Frédéric Dubreuil, Magali Phaner-Goutorbe. Characterization of polymer brushes deposited on gold surfaces by 1D and 3D-AFM in liquid. 2023 NANOScientific Forum Europe (NSFE2023), Sep 2023, Barcelona, Spain. hal-04286864

HAL Id: hal-04286864

<https://hal.science/hal-04286864>

Submitted on 15 Nov 2023

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Characterization of polymer brushes deposited on gold surfaces by 1D and 3D-AFM in liquid

Characterization of gold/thiol layer/liquid interfaces in different liquid environments by 1D-AFM and 3D-AFM to analyze their behavior for applications in biosensing and tribology


Dahlia SAAD<sup>1,2</sup>, Frédéric DUBREUIL<sup>1</sup>, Magali PHANER-GOUTORBE<sup>2</sup>

<sup>1</sup> Univ Lyon, Ecole Centrale de Lyon, LTDS, UMR5513, 69134 Ecully Cedex, France

<sup>2</sup> Univ Lyon, Ecole Centrale de Lyon, CNRS, INSA Lyon, Université Claude Bernard Lyon 1, CPE Lyon, INL, UMR5270, 69134 Ecully Cedex, France

(dahlia.saad@ec-lyon.fr, magali.phaner@ec-lyon.fr, frederic.dubreuil@ec-lyon.fr)

## Solid/Organic layer/liquid Interfaces




M. Ralph Uhlig (Thesis, Instituto de Ciencia de Materiales de Madrid, 2019) Page 18

- “Grafted onto” Organic layers
  - Sensing layers in biosensors
  - Protective layers for tribology applications

## Sample preparation

- Polymers dissolved in distilled water ( $C = 1,5 \text{ g/L}$ )
- 4 hours deposition on gold wafers



Poly (acrylic acid)  
PAA

Pure PAA

Pure PEO

50/50 PAA /PEO

Protein adsorption and trapping
 

- Biocompatible, non-toxic, biodegradable
- Interesting swelling properties


Protein repulsion and friction decrease
 

- Non-toxic
- Interesting repulsion properties

Carbon Hydrogen Oxygen

## Principle of 3D-AFM

Combination between 1D-AFM and 2D-AFM




T. Fukuma, Y. Ueda, S. Yoshioka, H. Asakawa, Phys. Rev. Lett. 104 (2010) 016101

- Technique for high resolution interfacial characterization
- Implementation in a conventional 2D-AFM
- Additional sine wave signal to the z-piezo (Lock-in amplifier)
- Image of the first liquid layers above the surface

## 1D-AFM Measurements


Force curves in pure water




Different adhesion forces:

- adhesion on gold: 1 – 1.5nN
- adhesion on PAA: 0.7 – 1nN
- adhesion on PEO: 0.1 – 0.5nN
- both PAA and PEO behaviors on PAA/PEO

## 3D-AFM implementation




Frequency shift tracking and extracting



$\Delta f \rightarrow \Delta F \rightarrow 3D \text{ force maps}$

$$F(z) = 2k \int_z^{\infty} \left( 1 + \frac{a^{1/2}}{8\sqrt{\pi(t-z)}} \right) \Omega(t) - \frac{a^{3/2}}{\sqrt{2(t-z)}} \frac{d\Omega(t)}{dt} dt$$


Sader et al. Appl. Phys. Lett. 84, 1801 (2004)



2D (xz) cross section representation of the interface

## 3D-AFM Measurements

2D (xz) cross-section images in PBS



Surface roughness effect?  
Polymer chain effect?

- Successfully implemented 3D-AFM
- Successfully generated 2D vertical images representing the interface
- Result analysis still in process

This 3D-AFM method is appropriate to visualize the interface between solid/polymer chains/liquid. It is promising to interpret the difference in behavior depending on the polymers' headgroups and the nature of the liquid. Our future work consists in improving the technique (vertical resolution, surface roughness,...) and calculating the force between the tip and the samples' surfaces and then generating a 3D force map of the interfaces. Furthermore, we are going to develop new interfaces by functionalizing silicon wafers with silane and then analyzing them using the improved version of 3D-AFM.

Funding: FRAMA2023