



Photovoltaic Conversion by Reciprocity

Jean-François Guillemoles

► To cite this version:

Jean-François Guillemoles. Photovoltaic Conversion by Reciprocity. QUEST 2023,
<https://www.quest-conference.com/>, Jun 2023, Paris, France. hal-04306587

HAL Id: hal-04306587

<https://hal.science/hal-04306587v1>

Submitted on 25 Nov 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial - NoDerivatives 4.0 International License

Photovoltaic Conversion by Reciprocity

Jean-François GUILLEMOLES
IPVF, UMR 9006, CNRS-X-ENSCP, Palaiseau, France

■ Nov. 2022



| PSL


ParisTech



Photovoltaic today

France : <45 €/MWh and
>3% electricity production

TW Volume



A positive upward spiral worldwide


25-45% Efficiency



New challenges



- TW scale
- Footprint and sustainability
- Reliability of the new technologies

0.2 €/Wp Cost




40% des modules sont installés depuis moins de 2 ans...


« What absorbs should emit »



Gustav Kirchhoff, 1859




- All related to exchange between causes and consequences
- All relevant to solar cell operation



Why luminescence and Solar cells


Luminophore

- Light in: electrons promoted
- Excitations relax and wander around
- And disappear:
 - Radiatively => light out
 - Or not (heat)



Solar Cell

- Light in : electrons promoted
- Excitations relax and wander around
- And disappear:
 - Radiatively => light out
 - Or not (heat)
 - Or collected at electrodes/ Or not (V_{oc})



⇒ Both are energy conversion systems
⇒ Both are mostly described by the same physical phenomena

Reciprocity relationship and conversion of light

Exact relationships between related phenomena

Also:


Stokes (1849) & Helmholtz (1856): optical reciprocity

Lorentz (1896): electromagnetic reciprocity

Max Planck (1900): Black Body radiation


Einstein (1917): Absorption, sp. & st. emission

Lars Onsager (1931) : microreversibility and reciprocity between fluxes and forces




A long list of reciprocities in photovoltaics:
Van Roesbroek 1954, Wurfel 1980, Donolato 1985,
Araujo 1994, MA Green 1997,
U. Rau 2007,
Wong 2012, JJ. Greffet 2018

*Absorption & Emission of photons,
Injection & Collection of electrons:
Reciprocity PV/LED*



Use of quantitative light emission from solar cells

Exact relationships between phenomena



Generalized Planck law:




$$\Phi(\hbar\omega) = \frac{\Omega}{4\pi^3\hbar^3c_0^2} (\hbar\omega)^2 \frac{1}{\exp\left(\frac{\hbar\omega - \Delta\mu}{kT}\right) - 1}$$

$$\Delta\mu \approx qV$$


(free energy/particle)

T & $\Delta\mu$ are the thermodynamic variables for the energy conversion process


Transport properties measurement



Transport properties measurement



$$S = \frac{\overrightarrow{\text{grad}}\mu_y}{\overrightarrow{\text{grad}}T} \iff \overrightarrow{\text{grad}}\mu_y = f(\overrightarrow{\text{grad}}T)$$




Ambipolar thermoelectric measurement, locally!

Multi-dimensional Luminescence Imaging

Device optimization at each fabrication step

- Contactless
- Non-destructive
- Local properties
- Method suitable for all PV absorbers




Hyperspectral imager

- $I_{PL}(x,y,\lambda)$
- Spectral resolution : 2 nm
- Spatial resolution : 1 μm (mega pixel)

Studying device operation (CW, RT, ...)

Imaging systems

- Hyperspectral imager
 - Spectral & Spatial
- Time-resolved fluorescence imaging
 - Temporal & Spatial




Time-resolved fluorescence Imaging

- $I_{PL}(x,y,t)$
- Time resolution : 250 ps
- Spatial resolution : 1 μm (mega pixel)


Studying Kinetic parameters

Proof of concept

Spectral information



Extracting $\Delta\mu$



$$\Phi_{PL}(E) = \frac{A(E)E^2}{4\pi^2\hbar^3c_0^2} \frac{1}{\exp\left(\frac{E - \Delta\mu}{kT}\right) - 1}$$

$$\Delta\mu_{eff}/q \approx V_{OC}$$


	Optical $\Delta\mu_{eff}/q$	Electric V_{OC}
GaAs	1,164 V	1,149 V
CIGS	0,808 V	0,801 V
Halide Perovskite	1,030 V	1,017 V

Delamarre et al. Appl. Phys. Lett. 100, 131108 (2012)

A. Delamarre et al., JAP 2014

Gilbert El-Hajje, et al., Energy & Environmental Science, 2016, 9, 2286 - 2294

Measuring non radiative recombination by PL



Proof of concept: Optical measurements of $I_{sc}(V_{oc})$ curve on GaAs cell

$$j_{rec} = j_{01} \exp\left(\frac{qV}{kT}\right) + j_{02} \exp\left(\frac{qV}{2kT}\right)$$

Measurement method	j_{01} (A/m ²)	j_{02} (A/m ²)
PL with HI	$(1.8 \pm 0.6) \times 10^{-16}$	$(8.9 \pm 1.5) \times 10^{-7}$
$j(V)$	$(7.4 \pm 0.1) \times 10^{-16}$	$(5.6 \pm 0.7) \times 10^{-7}$

- Efficiency with 5% rel. error
- Measuring all recombination mechanisms with PL





HI on full stack : optically extracting electric parameters

Collection efficiency f_T
determined from EL images at
incremental voltages

$$f_T(x, y) \approx \frac{kT}{q} \frac{\partial \ln \Phi_{EL}(E, V, x, y)}{\partial V}$$

J. Wong and M. Green, Phys. Rev. B 85, (2012)

- Microscopic and macroscopic inhomogeneities revealed on evaporated perovskite solar cells



El-Hajje et al., Energ. Env. Sci. (2016).


Amaury Delamarre, et al. IEEE Journal of Photovoltaics 2016, 6 (2), 528-531

Access to transport efficiency and superposition assumption

TR-FLIM : Proof of concept

Output : time-resolved PL maps


- 1D symmetry → Time-resolved PL profiles




Access to transport parameters

- Bulk lifetime $\tau_n = 75 \pm 1 \text{ ns}$
- Lateral rec. $S_n = (1 \pm 0.1) \times 10^5 \text{ cm/s}$
- Lateral diff. $L_{eff} = 200 \pm 10 \mu\text{m}$
- Photon recycling

... With a single experiment



Degradation studies



Degradation of the perovskite opto-electronic properties at different X-ray exposure times.

(a) PL intensity maps at 760 nm from the steady-state experiment

(b) Decay time fitted between $t=100\text{ns}$ and $t=300\text{ns}$ after the laser pulse in the pulsed experiment. The exact same regions are imaged on the two setups. The dotted ellipses represent the regions of interest used for the computation of the averaged spectra and decays.

















(c) PL spectra inside the damaged area (black ellipse in (a)) and pristine sample (green ellipse in (a)) for different exposure times.

(d) Decays inside the damaged area (black ellipse in (b)) and pristine sample (green ellipse in (b)) for different exposure times.

Correlation lifetime and Voc


X-Ray damage => CW and TRPL image correlations

Bulk recombinations increases



$$\Delta\mu = 2kT \ln \left(\frac{G}{n_t} \tau_{tr} \right)$$

$$n_t \approx 3 \times 10^3 \text{ cm}^{-3}$$



Local correlation
No free parameter

Absorption: required for photoluminescence interpretation

Classical techniques

- Not always relevant to our experimental conditions
- Rarely provides imaging



Generalized Planck's law

Challenges

- Small absorption values both critical and hard to measure
- Disentangle influences of layers and texturing

$$I_{PL}(z, E_{emit}) = A(E_{emit}) * \frac{2\pi}{\hbar^3 c_0^2} * \frac{E^2}{exp\left(\frac{E - \Delta\mu(z)}{k_B T}\right) - 1}$$

Absorptivity

[1]


Grey body radiation

$$\Delta\mu(z) = f(A(E_{excit}))$$


Photoluminescence
Excitation (PLE)

[1] Daub, E. & Würfel, P. Ultralow Values of the Absorption Coefficient of Si Obtained from Luminescence. *Phys. Rev. Lett.* **74**, 1020–1023 (1995).



Experimental results on halide perovskite



PLE spectra & Reflectivity maps



PL spectra for different excitation wavelengths



➤ **Absorption and thickness maps**

Acknowledgements

Special thanks to the spectroscopy team:

Baptiste Berenguier, Stefania Cacovitch, Amaury Delamarre, Géraud Delport, Marie Legrand, Laurent Lombez, Daniel Ory, Daniel Suchet, Guillaume Vidon, Philip Schultz, Davide Ceratti, Alexandre Py-Renaudie,...

To colleagues:

Stephane Collin, Andrea Cattoni, Amaury Delamarre, Jean Paul Kleider, Muriel Bouttemy, Arnaud Etcheberry,