



**HAL**  
open science

## Realization of nitroaromatic chromophores with intense two-photon brightness

Bartłomiej Sadowski, Marzena Kaliszewska, Guillaume Clermont, Yevgen Poronik, Mireille Blanchard-Desce, Piotr Piątkowski, Daniel Gryko

### ► To cite this version:

Bartłomiej Sadowski, Marzena Kaliszewska, Guillaume Clermont, Yevgen Poronik, Mireille Blanchard-Desce, et al.. Realization of nitroaromatic chromophores with intense two-photon brightness. *Chemical Communications*, 2023, 59 (78), pp.11708-11711. <10.1039/D3CC03347C>. <hal-04311533>

**HAL Id: hal-04311533**

**<https://hal.science/hal-04311533v1>**

Submitted on 28 Nov 2023

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



HAL Authorization

Dear Author


Please use this PDF proof to check the layout of your article. If you would like any changes to be made to the layout, you can leave instructions in the online proofing interface. First, return to the online proofing interface by clicking "Edit" at the top of the page, then insert a Comment in the relevant location. Making your changes directly in the online proofing interface is the quickest, easiest way to correct and submit your proof.

Please note that changes made to the article in the online proofing interface will be added to the article before publication, but are not reflected in this PDF proof.

If you would prefer to submit your corrections by annotating the PDF proof, please download and submit an annotatable PDF proof by clicking the button below.

 [Annotate PDF](#)

We have presented the graphical abstract image and text for your article below. This briefly summarises your work, and will be presented with your article online.



### Realization of nitroaromatic chromophores with intense two-photon brightness

Bartłomiej Sadowski,\* Marzena Kaliszewska, Guillaume Clermont, Yevgen M. Poronik, Mireille Blanchard-Desce,\* Piotr Piątkowski\* and Daniel T. Gryko\*

Effective manipulation of electronic effects within substituted nitroaromatics based on the dipyrrolonaphthyridinedione (DPND) core leads to fluorescent dyes with enhanced emission intensity as well as two-photon response.

Please check this proof carefully. Our staff will not read it in detail after you have returned it.

Please send your corrections either as a copy of the proof PDF with electronic notes attached or as a list of corrections. **Do not edit the text within the PDF or send a revised manuscript** as we will not be able to apply your corrections. Corrections at this stage should be minor and not involve extensive changes.

**Proof corrections must be returned as a single set of corrections, approved by all co-authors. No further corrections can be made after you have submitted your proof corrections as we will publish your article online as soon as possible after they are received.**

Please ensure that:

- The spelling and format of all author names and affiliations are checked carefully. You can check how we have identified the authors' first and last names in the researcher information table on the next page. **Names will be indexed and cited as shown on the proof, so these must be correct.**
- Any funding bodies have been acknowledged appropriately and included both in the paper and in the funder information table on the next page.
- All of the editor's queries are answered.
- Any necessary attachments, such as updated images or ESI files, are provided.

Translation errors can occur during conversion to typesetting systems so you need to read the whole proof. In particular please check tables, equations, numerical data, figures and graphics, and references carefully.

Please return your **final** corrections, where possible within **48 hours** of receipt following the instructions in the proof notification email. If you require more time, please notify us by email to chemcomm@rsc.org.

## Funding information

Providing accurate funding information will enable us to help you comply with your funders' reporting mandates. Clear acknowledgement of funder support is an important consideration in funding evaluation and can increase your chances of securing funding in the future.

We work closely with Crossref to make your research discoverable through the Funding Data search tool (<http://search.crossref.org/funding>). Funding Data provides a reliable way to track the impact of the work that funders support. Accurate funder information will also help us (i) identify articles that are mandated to be deposited in **PubMed Central (PMC)** and deposit these on your behalf, and (ii) identify articles funded as part of the **CHORUS** initiative and display the Accepted Manuscript on our web site after an embargo period of 12 months.

Further information can be found on our webpage (<http://rsc.li/funding-info>).

### What we do with funding information

We have combined the information you gave us on submission with the information in your acknowledgements. This will help ensure the funding information is as complete as possible and matches funders listed in the Crossref Funder Registry.

If a funding organisation you included in your acknowledgements or on submission of your article is not currently listed in the registry it will not appear in the table on this page. We can only deposit data if funders are already listed in the Crossref Funder Registry, but we will pass all funding information on to Crossref so that additional funders can be included in future.

### Please check your funding information

The table below contains the information we will share with Crossref so that your article can be found *via* the Funding Data search tool. **Please check that the funder names and grant numbers in the table are correct and indicate if any changes are necessary to the Acknowledgements text.**

Funder name	Funder's main country of origin	Funder ID (for RSC use only)	Award/grant number
Fundacja na rzecz Nauki Polskiej	Poland	501100001870	TEAM POIR.04.04.00-00-3CF4/16-00
Narodowe Centrum Nauki	Poland	501100004281	Sonata 2021/43/D/ST4/02267

## Researcher information

Please check that the researcher information in the table below is correct, including the spelling and formatting of all author names, and that the authors' first, middle and last names have been correctly identified. **Names will be indexed and cited as shown on the proof, so these must be correct.**

If any authors have ORCID or ResearcherID details that are not listed below, please provide these with your proof corrections. Please ensure that the ORCID and ResearcherID details listed below have been assigned to the correct author. Authors should have their own unique ORCID iD and should not use another researcher's, as errors will delay publication.

Please also update your account on our online [manuscript submission system](#) to add your ORCID details, which will then be automatically included in all future submissions. See [here](#) for step-by-step instructions and more information on author identifiers.

First (given) and middle name(s)	Last (family) name(s)	ResearcherID	ORCID iD
Bartłomiej	Sadowski		0000-0002-1323-2826
Marzena	Kaliszewska		
Guillaume	Clermont		
Yevgen M.	Poronik		
Mireille	Blanchard-Desce		0000-0002-1572-9545
Piotr	Piątkowski		0000-0001-8173-6017
Daniel T.	Gryko	A-7998-2008	0000-0002-2146-1282

## Queries for the attention of the authors

Journal: **ChemComm**

Paper: **d3cc03347c**

Title: **Realization of nitroaromatic chromophores with intense two-photon brightness**

For your information: You can cite this article before you receive notification of the page numbers by using the following format: (authors), Chem. Commun., (year), DOI: 10.1039/d3cc03347c.

Editor's queries are marked on your proof like this **Q1**, **Q2**, etc. and for your convenience line numbers are indicated like this 5, 10, 15, ...

Please ensure that all queries are answered when returning your proof corrections so that publication of your article is not delayed.

Query reference	Query	Remarks
Q1	Have all of the author names been spelled and formatted correctly? Names will be indexed and cited as shown on the proof, so these must be correct. No late corrections can be made.	
Q2	Fig. 1 contains labels (A) and (B), but these do not appear to be mentioned in the caption. Would you like to modify the caption or resupply the artwork (preferably as a TIF file at 600 dots per inch)?	
Q3	Have all of the funders of your work been fully and accurately acknowledged? If not, please ensure you make appropriate changes to the Acknowledgements text.	
Q4	Please check that ref. 15 has been displayed correctly.	
Q5	Ref. 15: Please provide the year of publication.	

# Realization of nitroaromatic chromophores with intense two-photon brightness†

Cite this: DOI: 10.1039/d3cc03347c

 Received 11th July 2023,  
 Accepted 4th September 2023

DOI: 10.1039/d3cc03347c

rsc.li/chemcomm

**Strong fluorescence is a general feature of dipyrrolonaphthyridinediones bearing two nitrophenyl substituents. Methyl groups simultaneously being weakly electron-donating and inducing steric hindrance appear to be a key structural parameter that allows for significant emission enhancement, whereas Et<sub>2</sub>N groups cause fluorescence quenching. The magnitude of two-photon absorption increases if 4-nitrophenyl substituents are present while the contribution of Et<sub>2</sub>N groups is detrimental.**

Recent developments in molecular photonics<sup>1</sup> and biochemistry<sup>2</sup> have increased the demand for novel organic materials with improved emission characteristics and enhanced resistance towards ambient conditions. Bearing in mind the stability of  $\pi$ -conjugated organic materials, one of the most common strategies is to decrease electron density, usually enabled by introducing an electron-deficient moiety into an aromatic backbone.<sup>3</sup> The nitro group ( $-\text{NO}_2$ ) is one of the strongest electron-withdrawing moieties, and by meeting this criterion, potentially sets the stage for novel materials with intriguing optical characteristics.


Nitroaromatics have, however, long been considered as non-fluorescent, and highly emissive examples of  $\text{NO}_2$ -containing chromophores have been sparsely reported in the literature (Fig. 1A).<sup>4</sup> Yet, they are promising candidates for constructing probes<sup>5</sup> tracking important biologically relevant species and as efficient two-photon absorbers.<sup>6</sup>

In recent years, some strategies have been developed to improve the luminescence performance of nitroaromatics.<sup>4b</sup>

From the mechanistic viewpoint, fluorescence can be successfully induced by blocking the d-PeT<sup>7</sup> process or when the nitro group does not participate in the  $S_0 \rightarrow S_1$  transition.<sup>8</sup> Applying a weaker electron-donating moiety for the construction of nitro-containing conjugates may also give rise to nitroaromatics with enhanced emission. Dyes containing nitro-functionalized thiophene,<sup>9</sup> fluorene,<sup>10</sup> tetrabenzofluorenes,<sup>11</sup> or phenothiazine<sup>12</sup> featuring enhanced emission have been described, but these approaches contain some drawbacks, such as a tendency for deexcitation *via* ISC (heavy atom effect of sulphur) or lack of significant spectral red-shifts of both the absorption and emission bands.

Due to its intriguing properties, the electron-deficient dipyrrolonaphthyridinedione (DPND) core<sup>13</sup> has recently been successfully employed in the construction of dyes with red/NIR emission,<sup>14</sup> OFETs,<sup>15</sup> stable singlet fission (SF) materials<sup>16</sup> and singlet oxygen (<sup>1</sup>O<sub>2</sub>) photosensitisers.<sup>17</sup> Studying quadrupolar, centrosymmetric DPNDs possessing two nitroaryl substituents at positions 3 and 9, we discovered that creating nitroaromatics

## A. Exemplary, highly fluorescent nitroaromatics:



## B. Nitroaryl-decorated DPNDs (this work):




Fig. 1 Exemplary highly emissive nitroaromatics and the idea of the present work.

<sup>a</sup> Centre of New Technologies, University of Warsaw, S. Banacha 2c, Warsaw 02-097, Poland. E-mail: b.sadowski@cent.uw.edu.pl

<sup>b</sup> Department of Chemistry, University of Warsaw, Zwirki i Wigury 101, Warsaw 02-089, Poland. E-mail: ppiatkowski@aus.edu

<sup>c</sup> Univ. Bordeaux, CNRS, Bordeaux INP, ISM, UMR 5255, Talence F-33400, France. E-mail: mireille.blanchard-desce@u-bordeaux.fr

<sup>d</sup> Institute of Organic Chemistry, Polish Academy of Sciences, Kasprzaka 44/52, Warsaw 01-224, Poland. E-mail: dtgryko@icho.edu.pl

† Electronic supplementary information (ESI) available: Experimental details, <sup>1</sup>H NMR and <sup>13</sup>C NMR spectra, and steady-state and time-resolved spectra. See DOI: <https://doi.org/10.1039/d3cc03347c>




Fig. 2 Structure of nitroaromatics studied in this work.

Table 1 Comparison of spectral data for the chosen compounds in three different solvents: 1,2-dichlorobenzene (DCB), CH<sub>2</sub>Cl<sub>2</sub> (DCM), and MeCN (ACN)

Cmpd	Solvent <sup>a</sup>	$\lambda_{\text{abs}}^b/\text{nm}$	$\lambda_{\text{fl}}^b/\text{nm}$	Stokes' shift <sup>c</sup> /cm <sup>-1</sup>	$\Phi_{\text{fl}}$	$\tau^d/\text{ns}$	$k_{\text{r}}^e \times 10^{-8}/\text{s}^{-1}$	$k_{\text{nr}}^e \times 10^{-8}/\text{s}^{-1}$
<b>1<sup>f</sup></b>	DCB	508	528	750	0.81	5.1	1.59	0.373
	DCM	504	523	720	0.73	5.7	1.28	0.474
	ACN	498	525	1030	0.65	5.7	1.14	0.614
<b>2<sup>f</sup></b>	DCB	569	605	1050	0.45	3.6	1.25	1.53
	DCM	562	601	1150	0.41	3.4	1.21	1.74
	ACN	559	599	1190	0.07	—	—	—
<b>5</b>	DCB	524	560	1230	0.96	4.7	2.04	0.085
	DCM	521	560	1340	0.34	1.9	1.79	3.47
	ACN	518	564	1570	0.005	—	—	—
<b>9</b>	DCB	555	602	1390	0.006	—	—	—
	DCM	549	608	1760	0.003	—	—	—
	ACN	542	584	1330	0.003	—	—	—
<b>14</b>	DCB	525	568	1440	0.76	4.9	1.55	0.490
	DCM	522	566	1490	0.58	3.2	1.81	1.31
	ACN	520	569	1660	0.075	—	—	—
<b>18</b>	DCB	575	669	2440	0.12	2.6	0.462	3.38
	DCM	565	670	2770	0.02	—	—	—
	ACN	557	688	3420	0.04	2.8	0.143	3.43

<sup>a</sup> DCB = 1,2-dichlorobenzene; DCM = dichloromethane; ACN = acetonitrile. <sup>b</sup> Absorption and fluorescence maxima. <sup>c</sup> Stokes' shifts. <sup>d</sup> Lifetimes of the emissive excited states obtained from time-correlated single photon counting (for  $\tau \gtrsim 1.5$  ns). <sup>e</sup> Radiative and non-radiative decay rate constants:  $k_{\text{r}} = \Phi_{\text{fl}}\tau^{-1}$  and  $k_{\text{nr}} = (1 - \Phi_{\text{fl}})\tau^{-1}$ . <sup>f</sup> The data were taken from ref. 18.

with acceptor–acceptor'–acceptor (A–A'–A) architecture constitutes a new viable strategy of preventing non-radiative deactivation.<sup>18</sup>

There is, however, still a huge gap in the knowledge of how positional isomerism of the nitro group relative to the chromophore core influences the emission characteristics of nitroaromatics.

To overcome this intrinsic limitation we now report how distinct structural modifications (different substitution patterns of nitroaryl moieties) alter the emissive properties and two-photon absorption characteristics<sup>19</sup> of these quadrupolar, A–A'–A dyes.

DPNDs possessing A–A'–A architecture, considered in this work, were assembled by employing a Pd-catalysed direct arylation<sup>14b</sup> between the DPND **1** and the corresponding aryl bromides (Fig. 1, see ESI† for synthetic details). As a result, a series of new quadrupolar nitroaromatics **4–10** and **13–18** were synthesized and fully described (Fig. 2). The same method was used for the synthesis of the previously described dyes **2**, **3**, **11** and **12**, which are included here for the complete assessment of

substitution-dependent optical behaviour. The complete series of dyes differ in the location of the nitro groups (*para* or *meta*), the structure of the linker (phenyl or biphenyl), and the effect of further substitution with electron-donating or -withdrawing substituents.

The effect of structural variations on the linear optical properties of all DPND derivatives in solution was subsequently examined by employing 1,2-dichlorobenzene (DCB), CH<sub>2</sub>Cl<sub>2</sub> (DCM), or MeCN (ACN) as solvents. The results are summarized in Table 1 and Fig. S2 (ESI†), and the spectral data are shown in Fig. S1–S26 (ESI†). As expected, nitroaromatics built around the DPND core display red-shifted absorption and emission bands compared with **1**, resulting from  $\pi$ -expansion of the chromophore and the presence of groups possessing distinct electronic character.

Upon inspection of Fig. 2, two series of dyes can be recognized: **2–10** bearing nitro groups at the *para* positions relative to the DPND core, and **11–18** where the –NO<sub>2</sub> occupies *meta* positions. Regardless of the location, some trends are common to both groups. First of all, the magnitude of the response




Fig. 3 Absorption and emission spectra of **1** (black solid and dotted lines), **11** (red solid and dotted lines), and **18** (blue solid and dotted lines) dyes in DCB. The **1**, **11**, and **18** emission spectra were excited at 480, 515, and 535 nm, respectively.

strongly depends on the presence of a substituent (Me, OMe) at the *ortho* position relative to the DPND core. Functionalization at this position increases the dihedral angle between the chromophore and the nitroaryl moiety, therefore decreasing conjugation, which results in a blue-shift of both the absorption and emission bands (2 vs. 3–4 and 11 vs. 12–15). Conversely, a reduced degree of rotation around the C—C single bond generally leads to an enhanced fluorescence response (Table 1 and Table S1 (ESI<sup>†</sup>), Fig. 3).

Dye 5 constitutes a special case among all the investigated nitroaromatics as it bears four *ortho*-located additional methyl groups that diminish the electronic coupling between substituents and the core, and effectively prevent the free rotation of aryl rings. This structural manipulation leads to a record-breaking value of  $\phi_{\text{fl}}$  among all nitro-DPNDs while the maxima of both  $\lambda_{\text{abs}}$  and  $\lambda_{\text{em}}$  are further hypsochromically shifted compared to those measured for 3 and 4 and just 15–30 nm bathochromically shifted vs. parent DPND 1.

The presence of an additional weak electron-donating substituent (Me or OMe) at the *ortho* position relative to the NO<sub>2</sub> group also enhances emission in all tested solvents (Table 1 and Table S1, ESI<sup>†</sup>). It marginally influences the position of both the absorption and emission bands in the case of 6 and 7 within the *para* series, while for the *meta* one, a small red-shift can be noted, especially for  $\lambda_{\text{em}}$  in 17. The potent effect of these structural factors, namely the presence of steric hindrance as well as an additional *ortho* substituent relative to the nitro group accumulates within 12, giving rise to an enormous  $\phi_{\text{fl}}$  value in relatively polar CH<sub>2</sub>Cl<sub>2</sub> (0.92).<sup>18</sup>

The incorporation of a substituent with a weak electron-accepting effect (–CF<sub>3</sub>, dye 8) or longer biaryl linkage (dye 10) does not really alter the absorption/emission characteristics as compared with 2 (Table 1 and Table S1 and Fig. S6 and S8, ESI<sup>†</sup>). At the same time, however, the presence of CF<sub>3</sub> groups leads to a sharp decrease of  $\phi_{\text{fl}}$  in polar solvents.

Finally, we investigated the influence of an auxochrome with a positive mesomeric effect (–NET<sub>2</sub>). It was found that groups featuring a strong mesomeric effect (–NO<sub>2</sub>, –NET<sub>2</sub>) placed at the *para* positions relative to the DPND core mainly govern both the absorption and emission properties of the studied DPNDs. This

Table 2 Two-photon absorption data of DPNDs 1–18 in DCM

Dye	$\lambda_{2\text{PA}}^{\text{max1}}/\text{nm}$	$\sigma_2^{\text{max1}}/\text{GM}$	$\lambda_{2\text{PA}}^{\text{max2,max3}}/\text{nm}$	$\sigma_2^{\text{max2,max3}}/\text{GM}$
1	830	27	750	44
2	820 (sh)	707	755(sh)/<690	1204/>3718
3	820	102	755/690	176/332
4	840	270	755(sh)/720(sh)	396/557
5	820	47	765/720	152/157
6	820	275	765(sh)/720(sh)	496/809
7	810	401	770/720	569/959
8	820(sh)	288	755/<690	607/>1134
9	860(sh)	0.7	755/720	4.3/5.6
10	840(sh)	319	765(sh)/720	856/1384
11	840	52	770(sh)/730	115/190
12	820	47	760(sh)/720(sh)	89/113
13	820	43	760(sh)/720	95/138
14	820	25	760(sh)/720(sh)	47/60
15	880	31	820(sh)/700	46/162
16	890	84	790/730	272/310
17	890	89	770(sh)/700	279/513
18	940	27	810/755	86/104

is particularly true for the diethylamino group in 18, giving rise to a significantly red-shifted emission (*ca.* 670 nm) but very weak fluorescence response (Fig. 3). The emission quenching is plausibly assigned to photo-induced electron transfer (PeT) occurring in the excited state.

Inspired by the large two-photon absorption (2PA) responses of nitroaromatics bearing arylolethynyl or arylolethynyl  $\pi$ -linkers between the nitro groups and the DPND core,<sup>19</sup> we investigated the 2PA properties of dyes 1–18 using the two-photon excited fluorescence (TPEF) method (see ESI<sup>†</sup>). The results are collected in Table 2 and Table S2, S3 (ESI<sup>†</sup>). No 2PA or very low response is observed in the spectral region corresponding to the lowest one-photon allowed excited state (*i.e.* above 1000 nm), due to symmetry reasons.<sup>20</sup> In contrast, significant 2PA broad bands (or shouldering) in the 800–850 nm range and even more intense 2PA bands closer to 700 nm are observed at higher energy (Fig. 4). The 2PA magnitude in the NIR1 region strongly depends on the structure of the dyes and the nature and position of the substituents (Table 2). The presence of NO<sub>2</sub> substituents at the *para* position is a key structural factor: analogous dyes from the *meta* series show much smaller 2PA responses, as noted from the comparison of dyes 2 and 1; 3 and 12; and 4 and 13 (Fig. S27, ESI<sup>†</sup>). For the derivatives having a




Fig. 4 Two-photon absorption spectrum of DPND 2, 6–9 in CH<sub>2</sub>Cl<sub>2</sub>.

1 *para* NO<sub>2</sub> group (2–10), the presence of an additional substituent generates a marked decrease of the 2PA both in the case of substituents positioned in the *ortho* (Fig. 4) or *meta* (Fig. S28, ESI†) position. For the derivatives having a *meta* NO<sub>2</sub> group (11–18), the influence of additional substituents is different depending on their position (Fig. S28, ESI†). Indeed, the presence of electron-donating MeO in the *para* position leads to a larger 2PA response compared to derivative 11. We yet note that DPNDs 9 and 18 possessing Et<sub>2</sub>N substituents have markedly weaker two-photon absorption (Fig. 4 and Fig. S3, ESI†) most probably due to steric hindrance. Finally, adding an additional 1,4-phenylene moiety in *para* NO<sub>2</sub> derivatives does not lead to an increase of the 2PA (Table 2 and Fig. S29, ESI†), indicating that the biphenyl twist may prevent extended delocalization favorable to 2PA enhancement.

To conclude, we found that strong fluorescence is a general feature in quadrupolar, centrosymmetric dipyrrolonaphthyridinediones possessing nitrophenyl substituents. Two-photon allowed transition to higher excited states is responsible for the main two-photon absorption band located around 700 nm. Combining the steric and electronic effect of various substituents enables the fine-tuning of both one-photon and two-photon absorption reaching emission at *ca.* 670 nm and a strong 2PA response (two-photon brightness > 1500 GM). Careful selection of the substitution pattern allows for effective control of the optical response, which builds the foundation for designing efficient one- or two-photon absorbers based on other cross-conjugated chromophores.

Conceptualization: B. S.; investigation: B. S., G. C., M. K., P. P.; supervision: D. T. G., M. B.-D., P. P.; visualization: B. S., Y. M. P.; writing – original draft: B. S, D. T. G.; writing – review & editing: D. T. G., M. B. D, B. S.

The work was financially supported by the Polish National Science Centre, Poland (Sonata 2021/43/D/ST4/02267) and the Foundation for Polish Science (TEAM POIR.04.04.00-00-3CF4/16-00).

## Conflicts of interest

There are no conflicts to declare.

## Notes and references

- (a) X. Yang, X. Lin, Y. S. Zhao and D. Yan, *Chem. – Eur. J.*, 2018, **24**, 6484–6493; (b) A. Minotto, P. A. Haigh, G. Łukasiewicz, E. Lunedei, D. T. Gryko, I. Darwazeh and F. Cacialli, *Light: Sci. Appl.*, 2020, **9**, 70.
- (a) P. Kasperkiewicz, Y. Altman, M. D'Angelo, G. S. Salvesen and M. Drag, *J. Am. Chem. Soc.*, 2017, **139**, 10115–10125; (b) W. Wang, C. A. Wildes, A. L. Spearman, T. L. Atallah, I. Lim, G. F. Globler, G. A. Matthews, K. M. Tye and A. Y. Ting, *Nat. Biotech.*, 2017, **35**, 864–871; (c) N. C. Payne, A. S. Kalyakina, K. Singh, M. A. Tye and R. Mazitschek, *Nat. Chem. Biol.*, 2021, **17**, 1168–1177; (d) E. D. Cosco, B. A. Arús, A. L. Spearman, T. L. Atallah, I. Lim, O. S. Leland, J. R. Caram, T. S. Bischof, O. T. Bruns and E. M. Sletten, *J. Am. Chem. Soc.*, 2021, **143**, 6836–6846; (e) J. B. Grimm, A. J. Sung, W. R. Legant, P. Hulamm, S. M. Matlosz, E. Betzig and L. D. Lavis, *ACS Chem. Biol.*, 2013, **8**, 1303–1310.
- (a) W. Zhu, Y. Wu, S. Wang, W. Li, X. Li, J. Chen, Z.-S. Wang and H. Tian, *Adv. Funct. Mater.*, 2011, **21**, 756–763; (b) H. Qu and C. Chi,

- Org. Lett.*, 2010, **12**, 3360–3363; (c) B. Song, Q. Zhang, W.-H. Ma, X.-J. Peng, X.-M. Fu and B.-S. Wang, *Dyes Pigm.*, 2009, **82**, 396–400.
- (a) M.-C. Chen, D.-G. Chen and P.-T. Chou, *ChemPlusChem*, 2021, **86**, 11–27; (b) Y. M. Poronik, B. Sadowski, K. Szychta, F. H. Quina, V. I. Vullev and D. T. Gryko, *J. Mater. Chem. C*, 2022, **10**, 2870–2904; (c) W. Rodriguez-Cordoba, L. Gutierrez-Arzaluz, F. Cortes-Guzman and J. Peon, *Chem. Commun.*, 2021, **57**, 12218–12235.
- (a) E. Braselmann, A. J. Wierzbza, J. T. Polaski, M. Chromiński, Z. E. Holmes, S.-T. Hung, D. Batan, J. R. Wheeler, R. Parker, R. Jimenez, D. Gryko, R. T. Batey and A. E. Palmer, *Nat. Chem. Biol.*, 2018, **14**, 964–971; (b) W. Chen, H. Luo, X. Liu, J. W. Foley and X. Song, *Anal. Chem.*, 2016, **88**, 3638–3646; (c) H. Song, Y. Zhou, H. Qu, C. Xu, X. Wang, X. Liu, Q. Zhang and X. Peng, *Ind. Eng. Chem. Res.*, 2018, **57**, 15216–15223; (d) A. Gomes, E. Fernandes and J. L. F. C. Lima, *J. Fluoresc.*, 2006, **16**, 119–139; (e) M. Abo, Y. Urano, K. Hanaoka, T. Terai, T. Komatsu and T. Nagano, *J. Am. Chem. Soc.*, 2011, **133**, 10629–10637; (f) J. A. Marsden, J. J. Miller, L. D. Shirlcliff and M. M. Haley, *J. Am. Chem. Soc.*, 2005, **127**, 2464–2476.
- (a) C.-K. Wang, P. Macak, Y. Luo and H. Ågren, *J. Chem. Phys.*, 2001, **114**, 9813–9820; (b) W. Ma, Y. Wu, D. Gu and F. Gan, *THEOCHEM*, 2006, **772**, 81–87; (c) H. Myung Kim and B. Rae Cho, *Chem. Commun.*, 2009, 153–164; (d) T. Verbiest, S. Houbrechts, M. Kauranen, K. Clays and A. Persoons, *J. Mater. Chem.*, 1997, **7**, 2175–2189.
- T. Ueno, Y. Urano, H. Kojima and T. Nagano, *J. Am. Chem. Soc.*, 2006, **128**, 10640–10641.
- K. Skonieczny, I. Papadopoulos, D. Thiel, K. Gutkowski, P. Haines, P. M. McCosker, A. D. Laurent, P. A. Keller, T. Clark, D. Jacquemin, D. M. Guldi and D. T. Gryko, *Angew. Chem., Int. Ed.*, 2020, **59**, 16104–16113.
- (a) A. Bolduc, Y. Dong, A. Guérin and W. G. Skene, *Phys. Chem. Chem. Phys.*, 2012, **14**, 6946–6956; (b) S. Hachiya, K. Asai and G.-I. Konishi, *Tetrahedron Lett.*, 2013, **54**, 3317–3320; (c) J. S. Siddle, R. M. Ward, J. C. Collings, S. R. Rutter, L. Porrès, L. Applegarth, A. Beeby, A. S. Batsanov, A. L. Thompson, J. A. K. Howard, A. Boucekkine, K. Costuas, J.-F. Halet and T. B. Marder, *New J. Chem.*, 2007, **31**, 841–851.
- (a) H. Kotaka, G.-i Konishi and K. Mizuno, *Tetrahedron Lett.*, 2010, **51**, 181–184; (b) M. A. B. Larsen, A. B. Stephansen, E. Alarousi, M. Pittelkow, O. F. Mohammed and T. I. Sølling, *Phys. Chem. Chem. Phys.*, 2018, **20**, 5942–5951.
- Y. Ueda, Y. Tanigawa, C. Kitamura, H. Ikeda, Y. Yoshimoto, M. Tanaka, K. Mizuno, H. Kurata and T. Kawase, *Chem. – Asian J.*, 2013, **8**, 392–399.
- M.-C. Chen, Y.-L. Lee, Z.-X. Huang, D.-G. Chen and P.-T. Chou, *Chem. – Eur. J.*, 2020, **26**, 7124–7130.
- M. Grzybowski, I. Deperasińska, M. Chotkowski, M. Banasiewicz, A. Makarewicz, B. Kozankiewicz and D. T. Gryko, *Chem. Commun.*, 2016, **52**, 5108–5111.
- (a) B. Sadowski, M. Loebnitz, D. R. Dombrowski, D. H. Friese and D. T. Gryko, *J. Org. Chem.*, 2018, **83**, 11645–11653; (b) B. Sadowski, M. F. Rode and D. T. Gryko, *Chem. – Eur. J.*, 2018, **24**, 855–864.
- M. Grzybowski, D. T. Gryko, B. Sadowski, K. Strassel, D. Kaelblein and P. Hayoz, *Polymers and compounds based on dipyrrolo[1,2-b:1',2'-g][2,6]naphthyridine-5,11-dione*, *Int. Pat.*, WO2017/068009 (A1).
- (a) L. Wang, L. Lin, J. Yang, Y. Wu, H. Wang, J. Zhu, J. Yao and H. Fu, *J. Am. Chem. Soc.*, 2020, **142**, 10235–10239; (b) L. Wang, W. Cai, J. Sun, Y. Wu, B. Zhang, X. Tian, S. Guo, W. Liang, H. Fu and J. Yao, *J. Phys. Chem. Lett.*, 2021, **12**, 12276–12282.
- J. Morgan, Y. J. Yun and A. J.-L. Aytou, *Photochem. Photobiol.*, 2022, **98**, 57–61.
- B. Sadowski, M. Kaliszewska, Y. M. Poronik, M. Czichy, P. Janasik, M. Banasiewicz, D. Mierzwa, W. Gadowski, T. D. Lohrey, J. A. Clark, M. Lapkowski, B. Kozankiewicz, V. I. Vullev, A. L. Sobolewski, P. Piatkowski and D. T. Gryko, *Chem. Sci.*, 2021, **12**, 14039–14049.
- B. Sadowski, H. Kita, M. Grzybowski, K. Kamada and D. T. Gryko, *J. Org. Chem.*, 2017, **82**, 7254–7264.
- (a) M. J. Wirth, A. Koskelo and M. J. Sanders, *Appl. Spectrosc.*, 1981, **35**, 14–21; (b) C. W. Stark, M. Rammo, A. Trummal, M. Uudsemaa, J. Pahapill, M.-M. Sildoja, S. Tshepelevitsh, I. Leito, D. C. Young, B. Szymański, O. Vakuliuk, D. T. Gryko and A. Rebane, *Angew. Chem., Int. Ed.*, 2022, **61**, e202212581.