

Supporting Information

Exploring the short and long-range order in connection with fluorine content in mixed anions copper hydroxyfluorides

Helies Hyrondelle^{1,*}, Matthew R. Suchomel¹, Vincent Rodriguez², Alexandre Fargues¹, Etienne Durand¹, François Weill¹, and Alain Demourgues^{1,*}

*Corresponding authors : helies.boumali@icmcb.cnrs.fr , alain.demourgues@icmcb.cnrs.fr

¹CNRS, University of Bordeaux, Bordeaux INP, ICMCB UMR CNRS 5026, F-33600 Pessac, France

²Institut des Sciences Moléculaires, UMR 5255 CNRS, University of Bordeaux, F-33405 Talence Cedex, France

Sample	Starting NH ₄ F/Cu ratio	Starting pH	Identified Phases	F ⁻ content *	Final Composition**
N-MW-1	0.5	7	Cu(OH) _{2-x} F _x (Structure derived from Cu-LF)	0.37(1)	Cu(OH) _{1.63} F _{0.37}
N-MW-2	1	7	Cu(OH) _{2-x} F _x (Structure derived from Cu-LF)	0.40(1)	Cu(OH) _{1.6} F _{0.4}
N-MW-3	1.5	7	Cu(OH) _{2-x} F _x (Structure derived from Cu-LF)	0.42(1)	Cu(OH) _{1.58} F _{0.42}
N-MW-4	2	7	Cu(OH) _{2-x} F _x (Structure derived from Cu-LF)	0.50(1)	Cu(OH) _{1.5} F _{0.5}

Table S1: Hydroxyl-rich phases obtained with different starting NH₄F/Cu molar ratio. *F- content determined by determined by fluoride ion-selective electrode. **Cu content determined by ICP-AES, OH content by electroneutrality




Figure S1: Full pattern profile matching refinement of two Cu-HF compositions: a) MW-2 (b) MW-3

Name	F- content	R _p (%)	wR _p (%)	a (Å)	b (Å)	c (Å)	B Angle
MW-2	0,95(1)	5,08	7,49	5,260(3)	6,360(4)	5,064(2)	112,92(1)
MW-3	1,46(1)	6,15	9,51	5,263(5)	6,355(2)	5,062(2)	113,09(1)

Table S2: Full pattern profile matching refinement parameters of two Cu-HF compositions corresponding to figure S1

Cu-HF $P2_1/a$

Atom	x	y	z	B _{iso}
Cu	0.2597	0.1225	0.0039	0.7
O	0.1611	0.3640	0.1700	0.7
F	0.3720	0.3836	0.7380	0.7

Cu-LF $P-3m1$

Atom	x	y	z	B _{iso}
Cu	0	0	0	0.7
O/F	0.3333	0.6667	0.328(4)	0.7

Table S3: Atomic positions of Cu-LF and Cu-HF phases, refined from X-ray diffraction for Cu-LF, fixed from literature ¹⁶ for $P2_1/a$