



HAL
open science

^3He gas diffusion in anisotropic porous media (ordered Al_2O_3 aerogels)

Hadi Loutfi, Geneviève Tastevin, Pierre-Jean Nacher, Andrey Stanislavovas, Vyacheslav Kuzmin, Kajum Safiullin, Murat Tagirov

► **To cite this version:**

Hadi Loutfi, Geneviève Tastevin, Pierre-Jean Nacher, Andrey Stanislavovas, Vyacheslav Kuzmin, et al.. ^3He gas diffusion in anisotropic porous media (ordered Al_2O_3 aerogels). Congrès du GERM 2023 "Résonance Magnétique aux Extrêmes", Jun 2023, Murol, France. hal-04336800

HAL Id: hal-04336800

<https://hal.science/hal-04336800>

Submitted on 11 Dec 2023

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial - NoDerivatives 4.0 International License



^3He gas diffusion in anisotropic porous media (ordered Al_2O_3 aerogels)

LOUTFI Hadi¹, TASTEVIN Geneviève¹, NACHER Pierre-Jean¹, STANISLAVOVAS Andrey²,
KUZMIN Vyacheslav², SAFIULLIN Kajum², TAGIROV Murat²

¹ Laboratoire Kastler Brossel, ENS-PSL University, CNRS, Sorbonne Université, Collège de France,
Paris, France

² Institute of Physics, Kazan Federal University, Kazan, Russia

Nuclear magnetic resonance (NMR) is an established non-invasive technique used to characterize diffusion of fluids in porous materials. Here, we report on NMR studies of gas diffusion and magnetic relaxation in ordered nanoporous Al_2O_3 aerogels with porosities of 76.5-98%. These studies are jointly made [1] at low temperature in Kazan and room temperature in Paris. At low temperature (4.2K), a strong reduction of ^3He apparent diffusion due to presence of the immobile adsorbed phase on aerogel walls was observed in Al_2O_3 aerogels [2]. Application of two-phase model apparent diffusion revealed a strong deviation of gas-phase diffusion and its anisotropy from Knudsen model as well. This behaviour is attributed to the action of the aerogel wall attractive potential on gas atom dynamics.

At room temperature, ^3He gas is laser-polarised for high sensitivity (polarisation of ~50%, at ~1 mbar) then compressed into Al_2O_3 aerogels. Each measurement uses a few mbar of ^3He mixed with 0 to 1 bar of ^4He gas. Litz wire PU coils were designed to optimize signal-to-noise ratio while achieving uniform sensitivity maps. Two coils with the same bore and different outer dimensions were made and tuned near 42 and 84 kHz ($Q \sim 100$) for operation in different NMR systems equipped with 1D and 3D gradient coils. CPMG sequences were used to investigate the dependency of T_2 on inter-echo time T_{cp} , pulsed gradient strength G , and gas pressure P . Gas diffusion regimes in ordered aerogels and other cells containing bulk gas or stacks of thin gas slabs are compared for a wide range of values of G , T_{cp} , and P . Effective diffusion coefficients within aerogel D_{eff} are inferred. Moreover, T_1 measurements are made using repeated small-angle flips. Long relaxation times (several minutes) with no applied gradients show that gas polarisation is well preserved in Al_2O_3 aerogel samples thanks to slow wall relaxation on this material.

First results on anisotropy of gas diffusion in low-density ordered aerogels and initial measurements of gradient-induced T_1 relaxation will be reported. Short-term prospects of these experiments will be discussed and compared with low temperature results.

[1] MARGIN project: anr.fr/Projet-ANR-19-CE30-0023

[2] Kuzmin et al., doi.org/10.1021/acs.jpcc.2c08251