



HAL
open science

A novel green process for the preparation of high MOF loading paper membrane

Pierre Tignol, Anne-Laurence Dupont, Vanessa Pereira Pimenta, Christian Serre, Bertrand Lavédrine

► To cite this version:

Pierre Tignol, Anne-Laurence Dupont, Vanessa Pereira Pimenta, Christian Serre, Bertrand Lavédrine. A novel green process for the preparation of high MOF loading paper membrane. 2023 French MOFs, COFs and Porous Polymers Conference, May 2023, Paris, France. . hal-04371343

HAL Id: hal-04371343

<https://hal.science/hal-04371343v1>

Submitted on 4 Jan 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

A novel green process for the preparation of high MOF loading paper membrane

P. Tignol^{1,2}, A-L. Dupont¹, V. Pimenta², C. Serre², B. Lavédrine¹


1. Centre de Recherche sur la Conservation (MNHN-CNRS-MC), Paris, France

2. Institut des Matériaux Poreux (ESPCI-ENS-CNRS-PSL), Paris, France




1 Introduction

MOFs are obtained in loose powder form requiring a shaping method for their practical use. Problems are often observed with beads or pellets, monoliths such as structural changes, pore blocking and/or low mass transport properties. To avoid these drawbacks, MOFs can be shaped as a paper.





Reaching a high MOF loading (>70wt%) while keeping good mechanical properties remains very challenging. We combined cellulose fibres with Nano-Fibrillated Cellulose (NFC) to improve the inter-fibre bonding. A 75wt% MIL-100(Fe) loaded paper without pore blockage and mechanically stable was obtained.

Scheme of the process




2 Characterizations of the MIL-100(Fe) paper membrane





XRD patterns of the MOF particles before and after shaping remain identical confirming that the process doesn't alter the crystallinity of the particles. The paper membrane degrades starting from 240°C (TGA not shown here). The N₂ adsorption isotherm indicates a fully preserved porosity with a S_{BET} of 1540 vs 1900 m².g⁻¹ for the MOF powder. Finally, nano-CT scan revealed a homogeneous spatial distribution of the particles and the fibres in the volume.

3D model of the paper membrane based on the CT scanning data (collab M. Pinto, S. Carvalho, Lisbon)



3 Dual-fibre concept


The mechanical properties of the 75 wt% MIL-100(Fe) loaded paper membrane with different ratio of fibres (cellulose:NFC) were investigated by evaluating their tensile strength as well as their flexibility.



These results highlight a synergistic effect of the fibres on the mechanical properties of the paper membrane. Conventional cellulosic fibres provide flexibility to the composite, while NFC enhances the mechanical strength by improving inter-fibre bonding and intermolecular bonds with MOF particles.

4 VOCs capture properties

MIL-100(Fe) as powder has been recently identified to selectively trap traces of organic acids through a chemisorption mechanism on Lewis acid sites [2]. We made a set-up to determine the adsorption capacity of the paper membrane with different VOCs (acetic, acid, formic acid, acrylic acid and furfural) in presence of moisture.



5 Conclusion

- ✓ Abundant and inexpensive binder used
- ✓ Rapid, simple, sustainable and scalable process
- ✓ High MOF loading (>70wt%)
- ✓ Capture properties identical to the powder

The paper membrane met all the specifications for a good adsorbent composite and showed high selectivity for the capture of polar VOCs. The next step is to study its separation performance.

References

[1] : H. Katsuzawa et al. *J. Fiber Soc. Japan.* 50, 452-457. 1994.

[2] : M. I. Sevrino et al. *Angew. Chem. Int. Ed.* 62, e202211583. 2023.