



**HAL**  
open science

## Healable ionoelastomer based on poly(ionic liquid)

Fengdi Li, Giao. T. M. Nguyen, Cédric Vancaeyzeele, Frederic Vidal, Cédric Plesse

► **To cite this version:**

Fengdi Li, Giao. T. M. Nguyen, Cédric Vancaeyzeele, Frederic Vidal, Cédric Plesse. Healable ionoelastomer based on poly(ionic liquid). Bordeaux Polymer Conference, Laboratoire de Chimie des Polymères Organiques, Jun 2022, Bordeaux, France. hal-04400043

**HAL Id: hal-04400043**

**<https://hal.science/hal-04400043v1>**

Submitted on 17 Jan 2024

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.


# Healable ionoelastomer based on poly(ionic liquid)

Fengdi Li, Giao. T. M. Nguyen, Cédric Vancaeyzeele, Frédéric Vidal\*, Cédric Plesse

Laboratory of Physicochemistry of Polymers and Interfaces, CY Cergy Paris University, 5 Mail Gay Lussac, 95000 Neuville Sur Oise, France

**KEYWORDS:** poly(ionic liquid), ionoelastomer, vitrimer

**ABSTRACT:** Ionoelastomers are elastomer based on poly(ionic liquid) (PIL) and have been introduced recently as liquid-free and stretchable ionic conductors.<sup>1-3</sup> These ionically conducting materials find their applications in all-solid stretchable and wearable electrochemical devices. In this presentation, we report a novel PIL based on imidazolium and bis(trifluoromethanesulfonyl)imide synthesized from commercially available copolymer rubber of polyepichlorohydrin and poly(ethyleneoxide). The PIL bearing allyl functional groups was then crosslinked with dynamic boronic ester crosslinkers through thiol-ene photoaddition. The resulting ionoelastomers are healable via vitrimer chemistry of boronic ester transesterification. The effect of crosslinker and additional poly(ethylene glycol) based dangling chains acting as free volume enhancer has been studied on thermomechanical properties and ionic conductivities. At optimal conditions, the resulting ionoelastomer is soft with a Young modulus of 0.2MPa, stretchable up to 300% elongation, and exhibits an ionic conductivity of  $1.6 \times 10^{-5} \text{ S} \cdot \text{cm}^{-1}$  at 30 °C. In addition, the vitrimer properties of the material have been demonstrated with Arrhenius-type stress relaxation, healability, and recyclability. The recycled materials were able to retain their original mechanical and conductive properties. The reported material has allowed obtaining sustainable high-performance polymer materials with high ionic conductivity and by combing the facile processability of thermoplastics with the performance advantages of permanent crosslinked thermosets via vitrimer chemistry.



**Scheme 1: Scheme for the formation of ionoelastomer and the dynamic exchange of boronic ester function**

- (1) Kim, H. J.; Chen, B.; Suo, Z.; Hayward, R. C. Ionoelastomer Junctions between Polymer Network of Fixed Anions and Cations. *Science* (80-. ). **2020**, *367* (6479), 773–776. <https://doi.org/10.1126/science.aay8467>.
- (2) Kim, H. J.; Paquin, L.; Barney, C. W.; So, S.; Chen, B.; Suo, Z.; Crosby, A. J.; Hayward, R. C. Low-Voltage Reversible Electroadhesion of Ionoelastomer Junctions. *Adv. Mater.* **2020**, *32* (25). <https://doi.org/10.1002/adma.202000600>.
- (3) Ming, X.; Zhang, C.; Cai, J.; Zhu, H.; Zhang, Q.; Zhu, S. Highly Transparent, Stretchable, and Conducting Ionoelastomers Based on Poly(Ionic Liquid)S. *ACS Appl. Mater. Interfaces* **2021**, *13* (26), 31102–31110. <https://doi.org/10.1021/acami.1c05833>.