



**HAL**  
open science

## **In-vitro biomechanical properties of porcine perineal tissues to better understand human perineal tears during delivery**

Marine Lallemand, Tiguida Kadiakhe, Jérôme Chambert, Arnaud Lejeune, Rajeev Ramanah, Nicolas Mottet, Emmanuelle Jacquet

► **To cite this version:**

Marine Lallemand, Tiguida Kadiakhe, Jérôme Chambert, Arnaud Lejeune, Rajeev Ramanah, et al.. In-vitro biomechanical properties of porcine perineal tissues to better understand human perineal tears during delivery. *Acta Obstetricia et Gynecologica Scandinavica*, In press, 10.1111/aogs.14791 . hal-04476075

**HAL Id: hal-04476075**

**<https://hal.science/hal-04476075>**

Submitted on 24 Feb 2024

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



Distributed under a Creative Commons Attribution - NonCommercial - NoDerivatives 4.0 International License

1 **In-vitro biomechanical properties of porcine perineal tissues to better**  
2 **understand human perineal tears during delivery**

3

4

5 Marine Lallemand<sup>1,2</sup>, Tiguida Kadiakhe<sup>2</sup>, Jérôme Chambert<sup>2</sup>, Arnaud Lejeune<sup>2</sup>, Rajeev  
6 Ramanah<sup>1,3</sup>, Nicolas Mottet<sup>1,3</sup>, Emmanuelle Jacquet<sup>2</sup>

7

8 <sup>1</sup> Department of Gynecologic Surgery, Besancon University Medical Centre, Besançon, France

9 <sup>2</sup> Department of Applied Mechanics, FEMTO-ST Institute, University of Franche-Comte, UMR  
10 6174 CNRS, Besançon, France

11 <sup>3</sup> Nanomedicine Imaging and Therapeutics Laboratory, INSERM EA 4662, University of  
12 Franche-Comte, Besançon, France

13

14 **Corresponding author**

15 Marine Lallemand

16 Service de Gynécologie- Obstétrique, CHU Besancon, bd Alexandre Fleming, 25000 Besancon,  
17 France

18 Email : [marine.lallemand@wanadoo.fr](mailto:marine.lallemand@wanadoo.fr)

19

20 **Conflict of interest:**

21 None

22

23

24 **ABSTRACT**

25

26 **Introduction :** Data concerning the mechanical properties of the perineum during delivery are  
27 very limited. In-vivo experimentations raise ethical issues. The aim of the study was to describe  
28 some of the biomechanical properties of each perineal tissue layer collected from sows in order  
29 to better understand perineal tears during childbirth.

30 **Material and methods:** Samples of each perineal tissue layers were obtained from the skin,  
31 the vagina, the external anal sphincter (EAS), the internal anal sphincter (IAS) and anal mucosa  
32 of fresh dead sows. They were tested in quasi-static uniaxial tension using the testing machine  
33 Mach-1®. The tests were performed at a displacement velocity of  $0.1 \text{ mm.s}^{-1}$ . Stress-strain  
34 curves of each perineal tissue layers before the first damage for each sow were obtained and  
35 modeled by hyperelastic Yeoh model described by three coefficients: C1, C2, and C3. Pearson  
36 correlation coefficient was calculated to measure the correlation between C1-coefficient and the  
37 duration between the first microfailure and the complete rupture for each perineal tissue layer.  
38 Pearson correlation was computed between C1-coefficient and the number of micro-failures  
39 before complete rupture for each tissue.

40 **Results:** Ten samples of each perineal tissue layer were analyzed. Mean values of C1-  
41 coefficient and corresponding standard deviations were  $46 \pm 15 \text{ kPa}$ ,  $165 \pm 60 \text{ kPa}$ ,  $27 \pm 10$   
42  $\text{kPa}$ ,  $19 \pm 13 \text{ kPa}$ ,  $145 \pm 28 \text{ kPa}$  for the perineal skin, the vagina, the EAS, the IAS and the anal  
43 mucosa, respectively. According to this same sample order, the first microfailure in the  
44 population of 10 sows appeared at an average of 54%, 27%, 70%, 131% and 22% of strain. A  
45 correlation was found between C1 hyperelastic-coefficient and the duration between the first  
46 microfailure and the complete rupture ( $r=0.7$ ,  $p=0.02$ ) or the number of micro-failures before  
47 complete rupture only for the vagina ( $r=0.7$ ,  $p=0.02$ ).

48 **Conclusions:** In this population of fresh dead sow's perineum, the vagina and the anal mucosa  
49 were the stiffest tissue. The IAS and EAS were the more extensible and the less stiff. A  
50 significantly positive correlation was found between C1-coefficient and the duration between  
51 the first microfailure and the complete rupture of the vagina, and the duration between the first  
52 microfailure and the complete rupture of the vagina.

53

54

55 **Key words**

56 stress-strain curve, perineum, childbirth, perineal tear, biomechanical properties, rupture,  
57 deformation

58

59 **Abbreviations**

60 EAS: external anal sphincter,

61 IAS, internal anal sphincter

62

63 **Key message**

64 C1-hyperelastic coefficients of perineal tissues (fresh dead sow) were ranked in ascending  
65 order: IAS, EAS, skin, anal mucosa and vagina. Similar human results could maybe explain  
66 anal sphincter integrity and isolated rectal buttonhole perineal tears in childbirth.

67

68

69

70 **INTRODUCTION**

71

72           The perineum is a soft structure made up of skin and muscles closing the pelvic. It  
73 is located under the levator ani muscle. Its mechanical properties ensure normal pelvic stability.  
74 During childbirth, the morphological and dynamic adaptation of the perineum to the fetal  
75 presentation depends on its resistance to the stresses induced by the presentation. Under the  
76 compressive efforts induced by the presentation, the perineum becomes thinner until sometimes  
77 it tears. Sometimes, it leads to more or less severe perineal tears. Stages III and IV correspond  
78 to obstetrical lesions of the anal sphincter and/or anal mucosa. These perineal lacerations can  
79 impact women's quality of life with anal incontinence, perineal pain, dyspareunia, recto-vaginal  
80 fistula and depression [1,2]. The rate of obstetrical anal sphincter injuries varies between 0.25  
81 and 6% depending on the study [3].

82           Data concerning the mechanical properties of the perineum and fetal stresses during  
83 delivery are very limited [4–10]. They result essentially from numerical models of the  
84 distension of the levator ani muscles. Only Zemčík et al., managed to quantify perineal strain  
85 during vaginal delivery using stereophotogrammetry [10]. But the perineum is a structure  
86 composed of different tissues whose behavior must be characterized in order to understand the  
87 tearing mechanism. Therefore, biomechanical parameters of the perineum are necessary to  
88 understand perineal tears. But, in-vivo experimentations raise ethical issues. To begin our work,  
89 we decided to study biomechanical properties of porcine perineum. A porcine model was  
90 chosen because of its similar morphological and immunohistochemical properties, and the  
91 results of microindentation tests as reported by the literature [11,12]. So the aim of our study  
92 was to describe some of the biomechanical properties of each perineal tissue layer collected  
93 from sows in order to better understand perineal tears during childbirth.

94

95 **MATERIAL AND METHODS**

96

97           We performed an experimental study on porcine perineal tissues. Ten samples of  
98 each perineal layer were analyzed. They were dissected from fresh dead sow provided by local  
99 slaughterhouse waste. The sow breed was the French pork butcher's pig. Sow were slaughtered  
100 24-48 hours before the experimentation. Sows were not frozen. For each sow, one sample was

101 obtained from the skin perineal layer, the vagina perineal layer, the external anal sphincter  
102 (EAS), the internal anal sphincter (IAS) and anal mucosa perineal layer (Figures 1 and 2.).

103 Perineal sows were refrigerated during the time before collection. In order to obtain  
104 samples in a reproducible way and preserve fiber integrity, a precise dissection method has  
105 been implemented (Figure 2.). The dissection was performed by an urogynecologist expert in  
106 anatomy of perineal tears. The used instruments were fine scissors and atraumatic forceps. No  
107 traction on the tissues was performed. A careful midline incision next to the vulvar area  
108 between the vaginal and anal openings was made. The external anal sphincter was immediately  
109 identified and isolated. The perineal skin was dissected from the anus to the ventral extremity  
110 into two dorso-ventral samples (right and left). Next, the ventral part of the vagina was incised  
111 at 6 o'clock to facilitate vaginal access. A right and left vaginal samples from the perineum  
112 were dissected on the rectovaginal septum side. Histologically, the vaginal sample included the  
113 vaginal wall composed of mucosa, lamina propria, muscularis and adventitia. Then, the  
114 external anal sphincter was carefully dissected and sectioned at 9 o'clock and 3 o'clock.  
115 Finally, the dorsal wall of the rectum and anus was incised at 12 o'clock. Two samples (right  
116 then left) of the anal mucosa and the internal anal sphincter were obtained. Only the samples on  
117 the right side were analyzed for the perineal skin, the perineal vagina, the perineal anal mucosa  
118 and the IAS. The left samples of these sows were analyzed in another study with non-  
119 comparable experimental conditions. EAS was taken. The entire EAS was collected between  
120 the vagina and the anus. Due to its thinness, it was not possible to divide it into two samples  
121 like the other layers. The entire EAS was used for sampling, along the fibers, in this study.  
122 Samples were oriented (dorso-ventral, left-right, cranio-caudal).

123 To obtain uniform stresses at the center of the sample during tensile testing,  
124 standardized samples were cut for each perineal layer with a scalpel and a caliber. Samples  
125 were obtained using a rectangular pattern 30 mm long and 10 mm wide in the cranio-caudal  
126 direction for all tissues except the EAS, which was in the latero-lateral direction (direction  
127 shown in Figure 3.).

128 Each sample end was covered with instant glue (Loctite 401®) and held in paper.  
129 These ends were inserted into the jaw in such a way as not to over- or under-tighten (Figure 3.).  
130 If the sample slipped, it would not be taken into account in the post-processing analysis.

131 Uniaxial tensile tests were carried out using Mach-1® mechanical tester  
132 (Biomomentum Inc, Canada). Tensile forces, stretching forces acting on the tissue, were

133 measured with a 250 N cell. A preload of 0.3 N was applied during two minutes before each  
 134 test to compare sample results. Sample sizes were measured after the pre-stress. The initial  
 135 measurements of thickness ( $t_0$ ), width ( $w_0$ ) and length ( $l_0$ ) measurements were obtain using a  
 136 digital caliper after preload in the middle of the sample to avoid compression tissue and  
 137 deformation near the jaws. The moving crosshead displacement ( $\Delta l$ ) of the tensile-testing  
 138 machine was recorded to an accuracy of 0.5  $\mu\text{m}$  in the direction of stress (traction), along with  
 139 force at a frequency of 100 Hz. The displacement was applied until failure. Tensile tests  
 140 stopped when the sample broke. The tests were performed at a displacement velocity of 0.1  
 141  $\text{mm}\cdot\text{s}^{-1}$  and at a constant temperature of 21°C to avoid dehydration.

142 The uniaxial engineering stress  $\sigma$  (kPa) in the loading direction was defined by:

$$\sigma = \frac{F}{A_0} = \frac{F}{t_0 \cdot w_0}$$

143 where  $F$  is the measured force,  $A_0$  is the initial cross-sectional area of the specimen.

144 The uniaxial engineering strain  $\varepsilon$  (%) in the loading direction is obtained by:

$$\varepsilon = \frac{\Delta l}{l_0}$$

145

146 Stress-strain curves of each perineal tissue before the first damage for each sow and  
 147 their mean were obtained. Unlike elastic materials where stress varies linearly with respect to  
 148 strain, soft tissues are hyperelastic. It means that these tissues have a non-linear elastic behavior  
 149 [13]. Like elasticity, hyperelasticity models reversible behavior. Non-linearity allows to take  
 150 account large deformations. Non-linear elastic behavior of these tissues were observed and  
 151 modeled by Yeoh model [14]:

$$\Psi = \sum_{i=1}^3 C_i (I_1 - 3)^i$$

152 This hyperelastic law is described by three coefficients:  $C_1$ ,  $C_2$ , and  $C_3$ . These  
 153 coefficients were identified by the method of least mean squares from experimental curves  
 154 using the Levenberg-Marquardt algorithm before the initial sign of damage appeared in each  
 155 tissue sample [15]. The damage, also called microfailure, is due to local and microscale effects.  
 156 Occurrence of damage results in the weakening of the tissue and makes it more likely to rupture  
 157 and tear. A microfailure is associated with the inflexion point on the experimental curve and is

158 identified by locating the maximum on the derivative of the curve. The inflexion of the curve  
159 shows a reduction in the tissue's ability to withstand mechanical stress, which is interpreted by  
160 the appearance of fiber rupture or delaminations in the tissue. This inflection generally precedes  
161 macroscopic tissue rupture.

162 Only C1-coefficients were analyzed because of its meaning: initial slope of stress-  
163 strain curve at low strains (less than 5%). A high C1 hyperelastic coefficient means that the  
164 tissue is stiff (rigid) with a small deformation in response to an applied force. On the contrary, a  
165 low C1 hyperelastic coefficient means that the tissue is easy to deform even in response to a  
166 low applied force.

167 Tangent modulus (kPa) E0 and E1 were calculated during low and high strain  
168 respectively. For each tissue, the mean stress and the mean strain were calculated up to the first  
169 rupture among all curves for the same tissue. Low strain was defined at the beginning of the  
170 master (mean) curve and used to define E0, i.e. at 0.4% deformation on average. E1 was  
171 defined as the tangent modulus of the curve at the end of the mean curve, i.e. at 59%  
172 deformation on average. Minimal E0 and E1 were calculated from the lowest curve for each  
173 layer of perineal tissue. Maximal E0 and E1 were calculated from the highest curve for each  
174 layer of perineal tissue.

175 Coefficients were expressed as mean  $\pm$  standard deviation. C1-hyperelastic  
176 coefficients were compared according to the perineal layer using an ANOVA model. If a  
177 statistically difference was found, pairwise comparisons using t-tests and including Bonferroni  
178 correction were performed identify which perineal layers were different from the others. In  
179 order to determine whether the C1 coefficient was predictive of tissue damage, Pearson  
180 correlation coefficient was calculated to measure the correlation between C1-coefficient and the  
181 duration between the first microfailure and the complete rupture for each tissue. Pearson  
182 correlation was computed between C1-coefficient and the number of micro-failures before  
183 complete rupture for each tissue. Statistical analysis was performed using R software (version  
184 4.3.0). For all analyses, we considered a p-value less than 0.05 to be statistically significant.

185

## 186 **RESULTS**

187 Ten samples of each layer were analyzed. Samples were described in Table 1. No  
188 sample slipped. Mean values of C1-coefficient and corresponding standard deviations were 46

189  $\pm 15$  kPa,  $165 \pm 60$  kPa,  $27 \pm 10$  kPa,  $19 \pm 13$  kPa,  $145 \pm 28$  kPa for the perineal skin, the  
190 vagina, the EAS, the IAS and the anal mucosa, respectively (Figure 4. and Table 2.). C1-  
191 hyperelastic coefficients were statistically different between perineal layers ( $p<0.001$ )  
192 (Supporting Information Appendix S1). C1-hyperelastic coefficients of the anal mucosa were  
193 statistically different to the C1-hyperelastic coefficients of the perineal skin, the EAS and IAS  
194 ( $p<0.001$ ). C1-hyperelastic coefficients of the perineal vagina were statistically different to the  
195 C1-hyperelastic coefficients of the perineal skin, the EAS and IAS ( $p<0.001$ ). The other  
196 perineal layers had statistically comparable C1-hyperelastic coefficients.

197           The vagina and the anal mucosa had the highest C1 hyperelastic coefficients. The  
198 mean ratio of C1 hyperelastic coefficients of the vagina to the anus was 0.3 (standard deviation  
199 of 0.1). The anal sphincter (external and internal) had the lowest hyperelastic coefficients.  
200 Tensile tests lasted less than 15 minutes for the IAS and less than 10 minutes for the other  
201 perineal layers.

202           Tangent modulus during low and high strain were presented Table 3. The E1  
203 modulus derived from the mean of the curves tended to triple compared with the E0 modulus  
204 for the skin and the vagina. Modulus E1 increased by a factor of 1.3 for SAE and SAI. Anal  
205 mucosa increased by a factor of 1.2.

206           The mean stress-strain curves and their standard deviation for each perineal tissue  
207 before the first damage in this population were drawn (Figure 5.). The first microfailure in the  
208 population of 10 sows appeared at least at 29%, 13%, 38%, 46% and 14% of strain for the  
209 perineal skin, the vagina, the EAS, the IAS and the anal mucosa, respectively (Table 4.). The  
210 first microfailure in the population of 10 sows appeared at an average of 54%, 27%, 70%,  
211 131% and 22% of strain for the perineal skin, the vagina, the EAS, the IAS and the anal  
212 mucosa, respectively. The external and internal anal sphincters were the most extensible and  
213 less stiff tissue. The vagina was the stiffest tissue. The anal mucosa was the less extensible  
214 tissue.

215           The duration between the first microfailure and the complete rupture of each tissue  
216 was  $79 \pm 105$  s,  $69 \pm 86$  s,  $146 \pm 168$  s,  $151 \pm 162$  s,  $166 \pm 108$  s for the perineal skin, the  
217 vagina, the EAS, the IAS and the anal mucosa, respectively (Table 5.). The number of  
218 microfailures before complete rupture of each tissue was  $16 \pm 14$ ,  $6 \pm 4$ ,  $23 \pm 19$ ,  $18 \pm 17$ ,  $38 \pm$   
219  $23$  for the perineal skin, the vagina, the EAS, the IAS and the anal mucosa, respectively (Table

220 5.). The mean ratio of vaginal to anal microfailures before complete rupture was 0.2 (standard  
221 deviation 0.2)

222 A significantly positive correlation was found between C1-coefficient and the  
223 duration between the first microfailure and the complete rupture of the vagina ( $r=0.7$   $p=0.02$ )  
224 (Table 4.). Also, a significantly positive correlation was found between C1-coefficient and the  
225 duration between the first microfailure and the complete rupture of the vagina ( $r=0.7$   $p=0.02$ )  
226 (Table 5.).

227 For the others tissue, no correlation was found between C1-coefficient and the  
228 duration between the first microfailure and the complete rupture of each tissue ( $p>0.05$ ) (Table  
229 4.). Also, no correlation between C1-hyperelastic coefficient and the number of micro-failures  
230 before complete rupture of each tissue except for vagina ( $p>0.05$ ) (Table-5).

231

## 232 **DISCUSSION**

233 In this study, some biomechanical properties of each perineal layer of the sow has  
234 been obtained. C1-coefficients for perineal skin, the vagina, the EAS, the IAS and the anal  
235 mucosa of fresh dead sow were measured.

236 In this population, the vagina and the anal mucosa were the stiffest. In other words,  
237 these rigid tissues had smaller deformation in response to an applied force. C1-coefficients of  
238 the vagina and the anal mucosa were higher than C1-coefficients of the perineal skin (165 and  
239 145 versus 46 kPa). This difference was also described by Gabriel et al. who compared the  
240 hyperelastic coefficient at low strain of the vagina and the abdominal skin of unfrozen cadavers  
241 without relevant pelvic organ prolapse (0.35 versus 0.14 MPa,  $p>0.05$ ) [16]. In the literature, no  
242 study assessed biomechanical properties of the anal mucosa. Only one rectal tissue evaluation  
243 was found [17]. Rubod et al. compared vaginal and rectal tissue on fresh female cadavers  
244 without prolapse performing multiaxial tension tests [17]. They demonstrated that the vagina  
245 was much more rigid and less extensible than the rectal tissue. In our study, the anal mucosa  
246 and the vagina were the less extensible tissues. Their first microfailure appeared at a mean  
247 strain of 22% and 27% respectively.

248 The IAS and EAS were the more extensible and the less stiff. The EAS is a skeletal  
249 muscle. Passive extensibility of skeletal muscles is an important component of total muscle  
250 function. It is well described in the literature [18]. Studies with animal muscles have shown that

251 passive extensibility is influenced by the size (mass) and length of muscle fibers, and the  
252 amount and arrangement of the connective tissues of the muscle belly. The resistance to passive  
253 lengthening is influenced by the readily adaptable amount of muscle tissue, including the  
254 contractile proteins and the non-contractile proteins of the sarcomere cytoskeletons.

255           Concerning IAS's biomechanical properties, no study was found in the literature.  
256 But a corroboration with vaginal smooth muscle cells could be done. Smooth muscle cells  
257 contribute to soft tissues' quasistatic and viscoelastic mechanical behavior [19–21]. According  
258 to Clark-Patterson et al., smooth muscle cells provide mobility by allowing the vagina to stretch  
259 under sustained pressures. By the same way, IAS could ensure mobility by allowing the anal  
260 mucosa to stretch under sustained pressures [22].

261           According to the tangent modulus, the skin and vagina seemed more resistant to  
262 deformation for high strain (much higher modulus). The stress applied to the tissues increased  
263 very quickly in the high strain zone which tends to show that these tissues will tear first during  
264 childbirth because the deformations of the perineal tissues are imposed by the passage of the  
265 fetus. The great ability of SAE and SAI to deformation (38 and 46%) is highlighted by lower  
266 values of E1 modulus for these tissues. The stresses applied was lower for the same level of  
267 deformation than those observed for the skin and the vagina. These data are compatible with  
268 what is observed in maternity wards. The skin and the vagina tend to tear first before the anal  
269 sphincter and the anal mucosa during childbirth.

270           In our study, the sow's anal sphincter was more extensible and less stiff than the  
271 vagina or the perineal skin. It could explain why severe perineal tears are rare in sows. If the  
272 same results are confirmed in humans, that could also maybe explain why the anal sphincter is  
273 not always torn during childbirth. In the same way, the sow's anal mucosa and its vagina were  
274 the less extensible tissues. If these biomechanical properties are also found in humans, it could  
275 maybe explain isolated rectal buttonhole perineal tear in obstetrics [23]. It is an isolated tear of  
276 the anal epithelium or rectal mucosa and vagina but without involving the anal sphincter. This  
277 kind of laceration is rare in human and only described in equine case report [24–26].

278           Concerning the experimental methodology, No failure or tears near the grip have  
279 been noticed. Operators trained before starting the study to avoid the learning phase and reduce  
280 these kinds of failure. Perineal stresses during delivery are not unidirectional. However, due to  
281 the size of the samples, only unidirectional traction tests at constant speed were performed.  
282 Yeoh model has been chosen because it described accurately the behavior of all the different

283 perineal tissues. A comparison of Yeoh, Mooney-Rivlin and Ogden models on pig skin (belly  
284 and back) confirmed that Yeoh model captures accurately the behavior of the pig skin [27]. It  
285 also highlighted the stability issues that arise when using the Ogden model as well as the failure  
286 of the Mooney-Rivlin model to properly describe the behavior of the tissues. Moreover, it  
287 requires a small number of parameters, its first parameter being interpreted as half the initial  
288 shear modulus.

289           At our knowledge, our study is the first one in the literature to attempt to describe  
290 biomechanical properties of each perineal layer in order to better understand perineal tears.  
291 This study focused on deformation. It concerns only the different tissues of the perineum,  
292 considered independently. This work is a preliminary step towards understanding the  
293 mechanisms involved. The next steps are aimed at identifying predictive parameters for the risk  
294 of perineal tears. These results could be used in simulation using Finite Element Model.  
295 Structural tests on the whole perineum are currently underway, and will be used to validate the  
296 model of the whole perineum with controlled boundary conditions. This ongoing study aims to  
297 identify predictive parameters for the risk of failure associated with extreme loading conditions  
298 (>250% deformation).

299           According to Rosenberg and Trevathan, non-human primates have the most similar  
300 pelvic anatomy to humans [28]. But its availability and its cost has led us seek another animal  
301 model. Ewes could have been used also but their availability remains difficult [29,30].  
302 Broodmares with a perineal body and who are also subject to obstetrical anal sphincter injury  
303 could also be an animal model [31]. However, the model is difficult to obtain. The simple,  
304 reproducible, low cost and most frequently animal model for pelvic floor research is the sow. It  
305 allows comparing measurement of mechanical properties with the literature. Plus, porcine  
306 models are usually used to educate physicians in sphincter injury repair [32–34]. Similarly to  
307 humans, utero-vaginal prolapse are common in sows [35,36]. In a recent industry study, 21% of  
308 sow deaths in the USA could be attributed to POP [37].

309           The perineal body is a fibromuscular structure located in the midline of the  
310 perineum and provides attachments of the perineal muscles in women [38]. Surprisingly, in our  
311 experience, sow's perineum seemed to not have a perineal body. In the literature, Bassett et al.  
312 study is the only article describing the anatomy of sow's perineum [39]. They did not report a  
313 perineal body. Plus, in the area between the vagina and the rectum of the sow, the only perineal  
314 muscle that was described is the anal sphincter. The retractor clitoridis muscle insertion is

315 located in the ventrolateral rectal wall. But, there is no perineal muscles other than the anal  
316 sphincter in this area. During our multiple dissections, the full area between the rectum and the  
317 vagina was excised, and the skin and the subcutaneous tissue removed such as described by  
318 Kochová et al. [40]. They called the resulting tissue the perineal body. But when we performed  
319 the same dissection as described by this research group, it seemed that they took the muscularis  
320 of the vagina, the adventitia of the vagina and fascia-like tissue. Kochová et al. has written in  
321 their work that they did not know the gross anatomy of the structures in the tissue samples. This  
322 discrepancy highlights the limits of the sow's model. The perineal body can be studied in  
323 humans using non-invasive technologies. Zemčik et al. studied the deformation of the perineum  
324 during normal delivery using stereophotogrammetry [10]. Chen et al. and Rostaminia et al.  
325 studied the perineal body stiffness in pregnant and non-pregnant women [41,42].

326 In addition to a relatively small study group, the sow's parity was not known. These  
327 sows were nullipara. According to Rynkevicius et al. and Drewes et al., biomechanical properties  
328 of the vaginal tissue after pregnancy would not recover to those of virgins [29,43]. These  
329 reasons could explain the interindividual variation among the sows. Furthermore, we did not  
330 study interactions between each layer of perineal layer. We investigated sow's cadaveric tissues.  
331 Postmortem changes must be considered. Indeed, stiffening of muscles appears 2 to 6 hours  
332 after death because of adenosine triphosphate (ATP) levels, which cause the binding of the  
333 muscle filaments of actin and myosin [44]. Even if the studied tissues cannot be considered to  
334 have intact chemomechanical properties, the results revealed significant differences in  
335 biomechanical behavior, providing new insights to better understand the mechanical responses  
336 of perineal structures to mechanical stress. In vivo experimentation is non-ethical. In vivo  
337 measurements using nondestructive tests should be performed to confirm these results.

338

## 339 CONCLUSION

340 In these perineal tissue samples of fresh dead sow, the vagina and the anal mucosa  
341 were the stiffest tissue. The IAS and EAS were the more extensible and the less stiff. A  
342 significantly positive correlation was found between C1-coefficient and the duration between  
343 the first microfailure and the complete rupture of the vagina and between C1-coefficient and  
344 the duration between the first microfailure and the complete rupture of the vagina. No  
345 correlation was found for the other perineal tissues. These results must be confirmed on humans  
346 using in vivo nondestructive tests.

347

348 **Ethics statement**

349 Sow's perineum were dissected from fresh dead sow provided by local slaughterhouse waste.  
350 Animals were not slaughtered for the study. No ethics application was needed since the animals  
351 were bred and killed for food production (French decree on the protection of animals used for  
352 scientific purposes).

353

354 **Author contributions:**

355 Marine Lallemand : conceptualization, data curation, formal analysis, methodology, writing-  
356 original draft; Tiguida Kadiakhe : conceptualization, data curation, formal analysis,  
357 methodology, writing-review; Jérôme Chambert : conceptualization, methodology, writing-  
358 review ; Arnaud Lejeune : conceptualization, methodology, writing-review; Rajeev Ramanah:  
359 writing-review ; Nicolas Mottet : writing-review; Emmanuelle Jacquet: conceptualization,  
360 methodology, writing-review.

361

362

363 **References**

- 364 [1] Viannay P, de la Codre F, Brochard C, et al. Prise en charge et conséquences des lésions  
365 obstétricales du sphincter anal (LOSA) : mise au point. *J Chir Viscérale* 2021;158:251–62.
- 366 [2] Attanasio LB, Ranchoff BL, Long JB, Kjerulff KH. Recovery from Obstetric Anal  
367 Sphincter Injury in a Prospective Cohort of First Births. *Am J Perinatol* 2022;10.1055/a-  
368 1788-4642.
- 369 [3] Thubert T, Cardaillac C, Fritel X, Winer N, Dochez V. Definition, epidemiology and risk  
370 factors of obstetric anal sphincter injuries: CNGOF Perineal Prevention and Protection in  
371 Obstetrics Guidelines. *Gynecol Obstet Fertil Senol* 2018;46:913–21.
- 372 [4] Pu F, Xu L, Li D, et al. Effect of different labor forces on fetal skull molding. *Med Eng*  
373 *Phys* 2011;33:620–5.
- 374 [5] Lapeer RJ, Prager RW. Fetal head moulding: finite element analysis of a fetal skull  
375 subjected to uterine pressures during the first stage of labour. *J Biomech* 2001;34:1125–33.

- 376 [6] Bamberg C, Deprest J, Sindhwani N, et al. Evaluating fetal head dimension changes during  
377 labor using open magnetic resonance imaging. *J Perinat Med* 2017;45:305–8.
- 378 [7] Ami O, Maran JC, Gabor P, et al. Three-dimensional magnetic resonance imaging of fetal  
379 head molding and brain shape changes during the second stage of labor. *PloS One*  
380 2019;14:e0215721.
- 381 [8] Silva MET, Oliveira DA, Roza TH, et al. Study on the influence of the fetus head molding  
382 on the biomechanical behavior of the pelvic floor muscles, during vaginal delivery. *J*  
383 *Biomech* 2015;48:1600–5.
- 384 [9] Yan X, Kruger JA, Nielsen PMF, Nash MP. Effects of fetal head shape variation on the  
385 second stage of labour. *J Biomech* 2015;48:1593–9.
- 386 [10] Zemčík R, Karbanova J, Kalis V, Lobovský L, Jansová M, Rusavy Z.  
387 Stereophotogrammetry of the perineum during vaginal delivery. *Int J Gynaecol Obstet.*  
388 2012;119:76-80..
- 389 [11] Debeer S, Le Luduec J-B, Kaiserlian D, et al. Comparative histology and  
390 immunohistochemistry of porcine versus human skin. *Eur J Dermatol EJD* 2013;23:456–  
391 66.
- 392 [12] Ranamukhaarachchi SA, Lehnert S, Ranamukhaarachchi SL, et al. A micromechanical  
393 comparison of human and porcine skin before and after preservation by freezing for  
394 medical device development. *Sci Rep* 2016;6:32074.
- 395 [13] Khaniki HB, Ghayesh MH, Chin R, Amabili M. Hyperelastic structures: A review on  
396 the mechanics and biomechanics. *Int J Non-Linear Mech* 2023;148:104275.
- 397 [14] Martins P a. LS, Natal Jorge RM, Ferreira AJM. A Comparative Study of Several  
398 Material Models for Prediction of Hyperelastic Properties: Application to Silicone-Rubber  
399 and Soft Tissues. *Strain* 2006;42:135–47.
- 400 [15] Gill PE, Murray W. Algorithms for the Solution of the Nonlinear Least-Squares  
401 Problem. *SIAM J Numer Anal* 1978;15:977–92.
- 402 [16] Gabriel B, Rubod C, Brieu M, et al. Vagina, abdominal skin, and aponeurosis: do they  
403 have similar biomechanical properties? *Int Urogynecology J* 2011;22:23–7.
- 404 [17] Rubod C, Brieu M, Cosson M, et al. Biomechanical properties of human pelvic organs.  
405 *Urology* 2012;79:968.e17-22.
- 406 [18] Gajdosik RL. Passive extensibility of skeletal muscle: review of the literature with  
407 clinical implications. *Clin Biomech Bristol Avon* 2001;16:87–101.

- 408 [19] Wagner HP, Humphrey JD. Differential Passive and Active Biaxial Mechanical  
409 Behaviors of Muscular and Elastic Arteries: Basilar Versus Common Carotid. *J Biomech*  
410 *Eng* 2011;133:051009..
- 411 [20] Greven K, Rudolph KH, Hohorst B. Creep after loading in the relaxed and contracted  
412 smooth muscle (taenia coli of the guinea pig) under various osmotic conditions. *Pflugers*  
413 *Arch* 1976;362:255–60.
- 414 [21] Greven K, Hohorst B. Creep after loading in relaxed and contracted (KCl or K<sub>2</sub>SO<sub>4</sub>  
415 depolarized) smooth muscle (taenia coli of the guinea pig). *Pflugers Arch* 1975;359:111–  
416 25.
- 417 [22] Clark-Patterson GL, Buchanan LM, Ogola BO, et al. Smooth muscle contribution to  
418 vaginal viscoelastic response. *J Mech Behav Biomed Mater* 2023;140:105702.
- 419 [23] Roper JC, Thakar R, Sultan AH. Isolated rectal buttonhole tears in obstetrics: case series  
420 and review of the literature. *Int Urogynecology J* 2021;32:1761–9.
- 421 [24] Kay AT, Spirito MA, Rodgerson DH, Brown SE. Surgical technique to repair grade IV  
422 rectal tears in post-parturient mares. *Vet Surg VS* 2008;37:345–9.
- 423 [25] Watkins J, Taylor T, Schumacher J. Rectal tears in the Horse: an analysis of 35 cases.  
424 *Equine Vet J* 1989;21:186–8.
- 425 [26] Speirs VC, Christie BA, van Veenendaal JC. The management of rectal tears in horses.  
426 *Aust Vet J* 1980;56:313–7.
- 427 [27] Dwivedi KK, Lakhani P, Kumar S, Kumar N. A hyperelastic model to capture the  
428 mechanical behaviour and histological aspects of the soft tissues. *J Mech Behav Biomed*  
429 *Mater* 2022;126:105013..
- 430 [28] Rosenberg K, Trevathan W. Birth, obstetrics and human evolution. *BJOG*  
431 2002;109:1199–206.
- 432 [29] Rynkevic R, Martins P, Hympanova L, Almeida H, Fernandes AA, Deprest J.  
433 Biomechanical and morphological properties of the multiparous ovine vagina and effect of  
434 subsequent pregnancy. *J Biomech* 2017;57:94–102.
- 435 [30] Rynkevic R, Martins P, Andre A, et al. The effect of consecutive pregnancies on the  
436 ovine pelvic soft tissues: Link between biomechanical and histological components. *Ann*  
437 *Anat Anat Anz Off Organ Anat Ges* 2019;222:166–72.
- 438 [31] Sheard L. Comparing two surgical techniques for repairing third-degree perineal  
439 lacerations in postpartum broodmares. *Vet Rec* 2021;189:e907.
- 440 [32] Temtanakitpaisan T, Bunyacejchevin S, Koyama M. Obstetrics anal sphincter injury and  
441 repair technique: a review. *J Obstet Gynaecol Res* 2015;41:329–33.

- 442 [33] Andrews V, Thakar R, Sultan AH. Structured hands-on training in repair of obstetric  
443 anal sphincter injuries (OASIS): an audit of clinical practice. *Int Urogynecol J Pelvic Floor*  
444 *Dysfunct* 2009;20:193–9..
- 445 [34] Emmanuelli V, Lucot J-P, Closset E, Cosson M, Deruelle P. Development and  
446 assessment of a workshop on repair of third and fourth degree obstetric tears. *J Gynecol*  
447 *Obstet Biol Reprod (Paris)* 2013;42:184–90.
- 448 [35] Supakorn C, Stock JD, Hostetler C, Stalder KJ. Prolapse Incidence in Swine Breeding  
449 Herds Is a Cause for Concern. *Open J Vet Med* 2017;7:85–97.
- 450 [36] Kiefer ZE, Koester LR, Studer JM, et al. Vaginal microbiota differences associated with  
451 pelvic organ prolapse risk during late gestation in commercial sows†. *Biol Reprod*  
452 2021;105:1545–61.
- 453 [37] Ross JW. Identification of putative factors contributing to pelvic organ prolapse in sows  
454 (Grant # 17-224) n.d.
- 455 [38] Siccardi MA, Bordoni B. Anatomy, Abdomen and Pelvis, Perineal Body. StatPearls,  
456 Treasure Island (FL): StatPearls Publishing; 2023.
- 457 [39] Bassett EG. The comparative anatomy of the pelvic and perineal regions of the cow,  
458 goat and sow. *N Z Vet J* 1971;19:277–90.
- 459 [40] Kochová P, Hympánová L, Rynkevic R, et al. The histological microstructure and in  
460 vitro mechanical properties of pregnant and postmenopausal ewe perineal body. *Menopause*  
461 *N Y N* 2019;26:1289–301.
- 462 [41] Rostaminia G, Awad C, Chang C, Sikdar S, Wei Q, Shobeiri SA. Shear Wave  
463 Elastography to Assess Perineal Body Stiffness During Labor. *Female Pelvic Med Reconstr*  
464 *Surg* 2019;25:443–7.
- 465 [42] Chen L, Low LK, DeLancey JO, Ashton-Miller JA. In Vivo Estimation of Perineal  
466 Body Properties Using Ultrasound Quasistatic Elastography in Nulliparous Women. *J*  
467 *Biomech* 2015;48:1575–9.
- 468 [43] Drewes PG, Yanagisawa H, Starcher B, et al. Pelvic Organ Prolapse in Fibulin-5  
469 Knockout Mice: Pregnancy-Induced Changes in Elastic Fiber Homeostasis in Mouse  
470 Vagina. *Am J Pathol* 2007;170:578–89.
- 471 [44] Martins PALS, Ferreira F, Natal Jorge R, Parente M, Santos A. Necromechanics: Death-  
472 induced changes in the mechanical properties of human tissues. *Proc Inst Mech Eng*  
473 2015;229:343–9.
- 474

475 **Legends**

476

477 **Table 1.** Description of samples and tensile tests for each perineal tissues.

478

479 **Table 2.** Hyperelastic coefficients according to the perineal tissue (Yeoh model).

480

481 **Table 3.** Parameter values from experimental stress-strain curves according to the perineal  
482 tissue (Yeoh model): E0 and E1 tangent modulus, Stress (kPa) at the first microfailure, Strain  
483 (%) at the first microfailure (minimal value, average value)

484

485 **Table 4.** Correlation between C1 hyperelastic coefficient and the duration between the first  
486 microfailure and the complete rupture of each tissue (Yeoh model)

487

488 **Table 5.** Correlation between C1 hyperelastic coefficient and the number of micro-failures  
489 before complete rupture of each tissue (Yeoh model)

490

491 **Figure 1.** Anatomy of the sow's perineum. An incision of the perineal skin between the Vagina  
492 and the anus was performed to reveal the external anal sphincter (EAS).

493

494 **Figure 2.** Obtention of the skin, the vagina, the IAS, the EAS and the anal mucosa samples of  
495 the sow. IAS: internal anal sphincter, EAS: external anal sphincter.

496

497 **Figure 3.** Test machine Mach-1® (Biomomentum Inc, Canada) and grips for soft tissues.

498

499 **Figure 4.** Stress-strain curves of each perineal tissue before first damage for each sow.

500

501 **Figure 5.** Mean stress-strain curves and their standard deviation for each perineal tissue before  
502 the first damage in this population (n=10 for each perineal layers).

503

504 **Supporting Information legend**

505

506 Appendix S1. *P*-values of pairwise comparisons using t-tests and including Bonferroni  
507 correction to identify which perineal layers were different from the others according to C1-  
508 hyperelastic coefficient.

509

510