

Human Serum Albumin in the presence of Small Platinum Nanoparticles

Xiaomin Yang, Erika Porcel, Laurent Marichal, Cesar Gonzalez Vargas, Amine Khitous, Daniela Salado-Leza, Xue Li, Jean-Philippe Renault, Serge Pin, Hynd Remita, et al.

▶ To cite this version:

Xiaomin Yang, Erika Porcel, Laurent Marichal, Cesar Gonzalez Vargas, Amine Khitous, et al.. Human Serum Albumin in the presence of Small Platinum Nanoparticles. Journal of Pharmaceutical Sciences, 2024, 10.1016/j.xphs.2024.02.002 . hal-04476809

HAL Id: hal-04476809 https://hal.science/hal-04476809

Submitted on 25 Feb 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

1	Title
2	Platinum Nanoparticles Stabilize Human Serum Albumin Structure
3	Xiaomin Yang ¹ , Erika Porcel ¹ , Laurent Marichal ² , Cesar Gonzalez Vargas ¹ , Amine
4	Khitous ¹ , Daniela Salado-Leza ^{1,3} , Xue Li ¹ , Jean-Philippe Renault ² , Serge Pin ² , Hynd
5	Remita ⁴ , Frank Wien ^{5#} , Sandrine Lacombe ^{1#}
6	¹ Université Paris-Saclay, CNRS, Institut des Sciences Moléculaires d'Orsay, 91405
7	Orsay, France
8	² Université Paris-Saclay, CEA, CNRS, NIMBE, 91191, Gif-sur-Yvette, France.
9	³ CONACyT, Faculty of Chemical Sciences, Autonomous University of San Luis Potosi,
10	78210 San Luis Potosi, Mexico
11	⁴ Université Paris-Saclay, CNRS, Institut de Chimie Physique, UMR 8000, 91405 Orsay,
12	France
13	⁵ Université Paris-Saclay, Synchrotron Soleil, 91190, Saint-Aubin, France
14	Corresponding Author:
15	Prof. Sandrine Lacombe
16	Université Paris-Saclay, CNRS, Institut des Sciences Moléculaires d'Orsay, 91405,
17	Orsay, France; Tel: +33 (1) 6915 8263 ; E-mail: sandrine.lacombe@u-psud.fr.
18	Prof. Frank Wien
19	Université Paris-Saclay, Synchrotron Soleil, 91190, Saint-Aubin, France; Tel: +33 (1)
20	6935 9665 ; E-mail: frank.wien@synchrotron-soleil.fr.
21	
22	Abstract

Noble metals, especially platinum nanoparticles (Pt NPs) have immense potential in
nanomedicine as therapeutic agents on account of their high surface area, intrinsic

25 catalytic properties, etc. However, our understanding of the interaction of nanoparticles 26 with biological entities, especially proteins, is far behind the explosive development of nanotechnology. In this study, we measure the structural and stability changes of 27 proteins at nanomolar concentrations upon interaction with Pt NPs using various 28 techniques. A large increase of 18°C in the thermal unfolding of human serum albumin 29 (HSA) with Pt NPs at the molar ratio 1:1 is observed using synchrotron radiation 30 circular dichroism (SRCD), due to Pt NPs increased thermal stability of HSA through 31 preferential hydration processes. The use of SRCD allows measuring critical parameters 32 on NPs-protein interactions, provides additional information for understanding the 33 34 influential role of PEG coating in NPs-cell interaction and has implications for nanomedicine and nanotoxicology. 35

Key words: Pt NPs, HSA, synchrotron radiation circular dichroism, thermal stability,
 thermodynamic properties

38 **1. Introduction**

After the pioneering work of Rosenberg in 1965, cis-platin have been widely used in 39 cancer therapy (Rosenberg et al., 1969). From then on, numerous new Pt compounds 40 41 have been discovered with better therapeutic performances than cis-platin (Dasari and 42 Tchounwou, 2014). Despite of the clinical success of the Pt complex, it suffers from a 43 lack of tumor tissue selectivity leading to some severe side effects (Medhat et al., 2017). 44 Advances in nanotechnology have provided new and powerful tools in the development 45 of multifunctional Pt NPs for effective detection and treatment of cancer, overcoming limitations associated with conventional cancer diagnosis and therapy (Srinivasan et al., 46 47 2015). Radiolytic synthesis (by gamma rays, X-rays, electron beams or other types of 48 ionizing radiation) provides a major advantage for a large-scale production of monodisperse particles as it generates a uniform distribution of reducing agents in the 49

50 entire solution during the irradiation process (Abidi et al., 2010; Belloni et al., 1998; 51 Holade et al., 2017; Uttayarat et al., 2015). Another advantage is that these 52 nanoparticles are freshly prepared in water without using potentially toxic solvents. The 53 functionalization of the NPs can be achieved during the radiolytic synthesis by adding 54 an appropriate substance to the reaction (Freitas de Freitas et al., 2018). The 55 functionalization with ligands or polymers such as poly(ethylene) glycol PEG enhances 56 the stability and control of their size (Wang et al., 2011).

Pt NPs have received considerable attention in nanomedicine due to their tunable, 57 highly sensitive optical, catalytic, and therapeutic properties. A promising area of 58 59 research involves the amplification of radiotherapy in the presence of Pt NPs at the tumor site (Lacombe et al., 2017). The properties of radioenhancement were 60 demonstrated for Pt NPs at nanoscale (Porcel et al., 2010; Schlathölter et al., 2016) and 61 62 at cellular level (KA et al., 2018; Salado-Leza et al., 2020; Yang et al., 2020c). For this use, intravenous administration of NPs is preferable than intra tumoral, to avoid pain to 63 64 the patient and ensure reproducible distribution via enhanced permeability and retention 65 effect (EPR). Thus, further exploration of the interaction of NPs with biological systems and blood proteins in particular is an important issue. 66

Proteins participate in most of the biological functions of the living matter and play a 67 crucial role in its maintenance. Their biologic activity highly depends on their three-68 dimensional secondary structure (Takano et al., 2016), while undesirable interactions 69 with NPs, may lead to protein aggregation or disfunction (Saptarshi et al., 2013). The 70 present study is focused on the interaction of Pt NPs with human serum albumin (HSA), 71 72 since serum albumins are major circulatory proteins, which play crucial roles in many important physiological functions like maintaining plasma oncotic pressure, 73 transporting cargo, antioxidant and enzymatic activities (Lee and Wu, 2015). Once NPs 74

enter systemic circulation, particle-protein interaction is the first phenomenon taking place before distribution into various organs (Mu et al., 2014). The impact of NPs, when they interact with blood proteins, is thus a major question to answer. In particular, a modification of the protein structure is expected to be dramatic, by changing physiological functions (Prasanth et al., 2018).

80 The analysis of the structure and stability of proteins in protein-Pt NPs is a key to investigate and understand the change of the proteins' properties after their interaction 81 with Pt NPs. The structure analysis can be performed with various techniques. Among 82 83 them, Circular Dichroism (CD) allows to characterize the secondary structure, and thus folding properties of proteins, and has recently been used to detect structure changes of 84 85 proteins interacting with NPs (Micsonai et al., 2015). Synchrotron Radiation Circular 86 Dichroism (SRCD) spectroscopy is superior to the conventional CD spectroscopy, thanks to the high intensity of photon emission, and the higher signal-to-noise levels of 87 the CD spectra. This allows to use lower amounts of proteins, and to observe subtle 88 89 conformational changes as shown by Wallace and Janes (Wallace and Janes, 2010). Additionally, the spectral range in SRCD extends down to 175 nm (compared to 190 nm 90 in CD). This enables elucidating finer details in the secondary structure of proteins 91 (Gobeaux and Wien, 2018), especially in the presence of nanoparticles (Sanchez-92 Guzman et al., 2020). SRCD allowed Laera et al. to discover that the thermal unfolding 93 temperature of HSA decreased by 6°C upon interaction with silver NPs. This indicates 94 95 that the HSA is significantly destabilized by the NPs, possibly due to a more flexible folded structure formed in the presence of the silver NPs (Laera et al., 2011). On the 96 contrary, Robin Capomaccio et al finds a melting temperature (T_m) of 69°C for free 97 HSA and of 75.4 °C for the AuNP-HSA complexes using SRCD, suggesting that Au 98 NPs stabilize HSA, both by increasing its thermal stability, and by reducing its 99

propensity to aggregate (Capomaccio et al., 2015). Recently, our group has shown that
Gd NPs (AGuIX) can modify the stability of HSA due to an indirect interaction (Yang
et al., 2020a).

103 In this study, Pt NPs were synthesized, characterized and their potential impact on 104 HSA was investigated. Our aim was to understand the interaction between Pt NPs and serum blood proteins by complementary techniques, an area in which the number of 105 available reports is limited. In particular, we measured the secondary structure of 106 107 proteins in low nanomolar concentrations, and in particular, the structural and thermal stability changes associated with proteins to Pt NPs up to 1:1 particle ratios using the 108 109 SRCD technique at DISCO, Synchrotron SOLEIL. This extremely sensitive technique has allowed us to show that Pt NPs have significantly increased the thermal stability of 110 HSA, and has also allowed accessing new detailed information about NPs-protein 111 112 interactions.

113 **2. Experimental**

114 **2.1. Materials and chemicals**

115 Tetraammine platinum (II) chloride salt $[Pt(NH_3)_4]Cl_2 \cdot H_2O$ (Sigma-Aldrich, USA), 116 poly(ethylene glycol) (H(OCH_2CH_2)nOH, M_W= 1000 g.mol⁻¹, Fluka), potassium 117 phosphate monobasic (KH_2PO_4), sodium phosphate dibasic (Na_2HPO_4), HSA was 118 purchased from Sigma-Aldrich, USA. HSA samples were prepared by dissolving HSA 119 powder in 10 mM phosphate buffer at pH 7.0. All chemicals were of analytical grade. 120 Pure water used in all experiments was filtered (18.4 M Ω cm) by a Milli-Q system 121 (Millipore, Milford, MA, USA).

122 2.2. Synthesis of Pt NPs

Pt NPs were synthesized by facile and ecofriendly one-step radiolysis. The procedureof synthesis and characteristics of these NPs are detailed in the French Patent

Application: Nanoparticules et procédé de preparation, FR1900008 (Salado-Leza et al., 125 2020; Yang et al., 2020b). Briefly, the reduction was achieved in aqueous solution using 126 Pt(NH₃)₄Cl₂ (10⁻² mol/L) as precursor and polyethylene glycol (PEG-OH 1000, 1 127 mol/L) as radical scavenger, stabilizer and biocompatible capping agent. After thorough 128 deaeration with flushing nitrogen gas, the solutions were irradiated by a γ -source 129 provided by a panoramic 60 Co γ -facility (E= 1.33 MeV, LET= 0.2 keV.µm-1) with dose 130 rate of 68.2 Gy.min⁻¹. Pt^{II} was completely reduced to Pt^{0} at a dose of 1,000 Gy (Porcel 131 132 et al., 2012; Porcel et al., 2010). The obtained Pt NPs were lyophilized for storage at 4 °C for months. 133

134 2.3. Characterization of Pt NPs

Morphological characterization was conducted by a TEM-STEM JEOL1400 (Ernest) transmission electron microscopy (TEM) with an accelerating voltage of 120 kV. For TEM observations, a drop of the Pt NPs solution was deposited onto copper grids (200 mesh, Agar Scientific Ltd). The grids were dried under a flow of N₂under ambient conditions before observations. Statistical analysis of Pt NPs diameter was converted to cumulative number-based distributions with 'Image J' program.

Electrokinetic properties (ζ–potential) of Pt NPs were measured with ζ–potential
analyzer model Zeta Potential WALLIS (Cordouan Technologies, France). Pt NPs were
diluted in Mili-Q water to reach 0.1 mM, and measured at 25°C in a disposable folded
capillary cell.

145 The optical absorption measurements were performed on a CARY 300 Scan UV-146 Visible Spectrophotometer (Int. Agilent) in the frequency range of 200 nm-800 nm at 147 room temperature before and after irradiation. The as-synthesized Pt NPs were diluted 148 with Milli-Q water to a final concentration of Pt [1 mM] for UV–visible absorption 149 measurements.

150 **2.4. Preparation of the samples**

The HSA mother solution (20 mg/mL) was prepared by dissolving HSA powder in 10 mM phosphate buffer at pH 7.4 (Shaw and Pal, 2008). The concentration of HSA was determined by absorbance measurements using molar extinction coefficients of 0,58 $(g/L)^{-1}$ cm⁻¹ at 280 nm (Dockal et al., 1999).

Pt NPs-HSA samples at different Pt NPs/HSA molar ratios (1:30 to 1:1) were prepared by mixing a 15 μ M HSA solution with different concentrations of Pt NPs in phosphate buffer at pH 7.0. The samples were incubated at room temperature for 40 minutes before measurements.

159 2.5. Dynamic light scattering

160 The hydrodynamic diameter of Pt NPs in the absence and presence of proteins (15 μ M) 161 (with molar ratios of Pt NPs/HSA from 1:30 to 1:1) was measured by dynamic light 162 scattering (DLS) using a Cordouan VASCO-2 particle size analyzer (Cordouan 163 Technologies, France). The Pt NPs were diluted in Mili-Q water to a final concentration 164 of 0.5 mM, and the measurements were conducted at 25°C in a semi-micro polystyrene 165 (PS) cuvette.

166 **2.6. Isothermal Titration Calorimetry (ITC)**

Adsorption isotherms of HSA on Pt NPs were performed by calorimetry using a 167 168 MicroCal PEAQ-ITC (Malvern). All the solutions were thoroughly degassed prior to the 169 titrations to avoid the formation of bubbles in the calorimeter cell. The reaction cell (280 μ L) was loaded with a HSA solution at 1 x 10⁻⁴ mol/L. The syringe (75 μ L) was 170 filled with a Pt NPs solution at 2 x 10^{-3} mol/L. The proteins and NPs were prepared in 171 172 the same phosphate buffer (pH 7.4) to prevent any pH effect. The experiments were done in duplicate at 20 °C by adding 2.4 µL of the Pt NPs solution to the HSA solution 173 174 with an equilibration interval of 200 s. Raw data were obtained as a plot of heat (µcal) against the injection number, and featured a series of peaks for each injection. These raw data peaks were transformed using the instrument software to obtain a plot of the enthalpy change per mole of injectant (ΔH^0 , kcal·mol⁻¹) against the molar ratio. Control experiments included the titration of the Pt NPs solution into buffer, buffer into HSA, and buffer into buffer, with the same used sample concentration. Corrected data refer to experimental data after subtraction of the control data.

181 2.7. Synchrotron radiation circular dichroism (SRCD)

182 SRCD spectra acquisition

183 The SRCD spectra of samples were measured on the DISCO beamline, SOLEIL184 synchrotron radiation facility, Saint-Aubin, France.

Prior to the measurement, the instrument was calibrated using an aqueous solution of (+) camphorsulphonic acid (CSA). To prepare the sample, 4 μ L Pt NPs–HSA solution was placed in CaF₂ cuvettes with a 50 μ m pathlength (Wien and Wallace, 2005).

The HSA spectra were collected between 170 and 261 nm with a step size of 1 nm and an integration time of 1200 ms/nm at 37°C. All the spectra were recorded in triplicate, averaged, baseline subtracted and zeroed using CDToolX software (Lees et al., 2004). Raw data ellipticity expressed in millidegrees (mdeg) was converted to molar circular dichroism values ($\Delta \varepsilon$). For the molar circular dichroism values ($\Delta \varepsilon$, M⁻¹.cm⁻¹ = L.mol⁻¹.cm⁻¹), the following Eq. 1 was applied:

194
$$\Delta \varepsilon = \theta \times \frac{(0.1 \times \text{MRW})}{(P \times C) \times 3298}$$
(1)

where the MRW (mean residue weight) of HSA is 113.8 Da (g.mol⁻¹), P (pathlength)
is 0.005 cm (measured by interferometry) and C (protein concentration) was ~1 mg/mL.

197 **Thermal denaturation**

Thermal denaturation studies were carried out by collecting SRCD spectra in a temperature range between 26 and 95°C with a step of 3°C. Three spectra were recorded with 5 minutes equilibration time for each temperature.

Ellipticity values were obtained from thermal denaturation curves for each of the three peaks (223 nm, 210 nm and 192 nm) at each temperature. They were normalized by setting the peak values at 26°C to 1.0. The decreasing of the relative intensity of protein with temperature has been fitted to a Boltzmann type equation Eq. 2 with the software OriginLab (Laera et al., 2011).

$$y = A + \frac{B-A}{1+e^{\frac{x-x_0}{dx}}}$$

207 (2)

208 (where X is the temperature, X_0 the melting temperature (T_m), and dx the width of the 209 thermal transition) for a simple two-state unfolding process. T_m of the protein defined as 210 the midpoint of the unfolding transition.

211 Structure analysis

The contents of α -helix, β -sheet, turn and other structures of HSA were calculated from SRCD spectra using BeStSel, a web server used for accurate secondary structure components determination (Micsonai et al., 2018; Micsonai et al., 2015).

215 **3. Results and discussions**

216 **3.1. Synthesis and characterization of Pt NPs**

The Pt NPs synthesized in water by radiolysis were precisely characterized using DLS, TEM and the zeta potential technique (**Figure 1**).

The Pt NPs observed by TEM show semi-spherical morphologies (Figure 1a) and a 219 uniform size distribution with an average metallic core diameter of 3.0±0.8 nm (Figure 220 221 **1b**). DLS measurements showed that Pt NPs have an average hydrodynamic diameter of 18±2.6 nm (Figure 1c). Significant differences between TEM analysis and DLS 222 223 measurement indicate the Pt NPs PEG coating. The zeta potential value of Pt NPs in MiliQ water is -14.2±4.1 mV. This result is in good agreement with experimental results 224 of other works (Ehi-Eromosele, 2016; Ibrahim et al., 2016), the PEG coated NPs have 225 226 an average negative ζ -potential of -14 mV and -17 mV, respectively, in water (pH 6~7), which leads to interparticle repulsion (Ehi-Eromosele, 2016). 227

228

[Figure 1]

The reduction of Pt complex and the formation of Pt NPs were monitored using UVvis absorption spectroscopy. Metallic NPs display strong optical absorptions due to their surface plasmon resonance (SPR). Platinum nanoparticles have a plasmon in the UV range (Salado-Leza et al., 2019; Yang et al., 2020b). **Figure 2** shows the UV-vis spectra of the aqueous solutions containing $[Pt(NH_3)_4]Cl_2$ and PEG-OH before and after irradiation.

235 The spectra reveal that, before irradiation, the aqueous solutions composed of [Pt(NH₃)₄]Cl₂ or [Pt(NH₃)₄]Cl₂ in the presence of PEG-OH, have the absorbance of the 236 main peak close to 240 nm and a small shoulder around 290 nm, which correspond to 237 the ligand-to-metal charge transfer (LMCT) band between $(NH_3)_4^{2+}$ and Pt^{II} ions 238 (Gharibshahi and Saion, 2012). After irradiation, the two initial absorption peaks 239 disappear due to the complete reduction of Pt^{II} into Pt⁰ leading to formation of Pt NPs. 240 241 Thus, there was no further charge transfer possible from ligand to metal ions (Inwati et al., 2016). Moreover, the appearance of a surface plasmon absorption band with a single 242

broad peak centered at around 270 nm indicated the presence of Pt NPs (Moores andGoettmann, 2006; Yang et al., 2020b).

The inserted picture in **Figure 2** shows the color of the colloidal solution, which changed from colorless (before irradiation) to dark brown (after gamma irradiation). The colour change is due to the radiolytic reduction of $[Pt(NH_3)_4]^{2+}$ ions to Pt^0 atoms indicating the formation of colloidal Pt NPs (Gharibshahi and Saion, 2012; Salado-Leza et al., 2020) as mentioned before.

250

[Figure 2]

251 **3.2. Dynamic light scattering analysis**

252 In the present work, DLS was used to measure the hydrodynamic diameter of 253 different concentrations of Pt NPs in the absence and presence of HSA at pH 7.4 in 10 mmol/L phosphate buffer. No significant change in the NPs size distribution after 254 255 exposure to HSA at room temperature. It demonstrated there was no complex formation, 256 which is probably due to the grafting of hydrophilic PEG-OH on Pt NPs having a high capacity to prevent the adsorption of proteins (Pelaz et al., 2015; Wang et al., 2015). 257 Furthermore, PEGylation might prevents the uptake of Pt NPs by Reticuloendothelial 258 System (RES) and enhance the circulation lifetime of NPs inside the body (Suk et al., 259 260 2016).

261

[Figure 3]

262 **3.3. Isothermal Titration Calorimetry**

The binding properties of the Pt NPs with HSA were consecutively studied using ITC. **Figure 4a** and **Figure 4b** show the plot of enthalpy change (ΔH^0) against Pt NPs-HSA molar ratio. The amount of heat due to the controls (dilution) is measured and subtracted from the amount of the heat obtained for the Pt NPs-protein system. ITC results did not show any significant binding, and no thermodynamic parameters could

268	be obtained. This finding is consistent with previous studies on telodendrimer-based
269	NPs having PEG in the surface (Li et al., 2012). Indeed, the functionalization of NPs by
270	PEG prevents interactions with proteins (Gref et al., 2000).

271

[Figure 4]

272

273 **3.4. Synchrotron radiation circular dichroism (SRCD)**

274 SRCD spectra acquisition

The adsorption of proteins on the surface of nanomaterials, may induce 275 276 conformational changes for some proteins, which influence the functionality and 277 biological activity of the proteins (Satzer et al., 2016; Shemetov et al., 2012). The 278 SRCD spectroscopy is widely used to study the conformation of proteins in aqueous 279 solution. The far UV SRCD spectra (170~261 nm) provide the variations in the 280 secondary structure of proteins as a result of the molecular interactions with other 281 materials (Prasanth et al., 2018). Figure 5 shows the SRCD spectra of pure HSA and 282 HSA in the presence of different concentrations of Pt NPs (0.5 mM, 1 mM, 2 mM, and 283 15 mM), corresponding to Pt NPs-HSA ratios of 1:30, 1:15, 1:7.5, and 1:1. The 284 spectrum exhibits two negative bands at 210 and 223 nm, one positive band at 192 nm, 285 characteristic of the α -helical structure. The negative peak at 223 nm is due to the $n \rightarrow \pi^*$ transition of the carbonyl group of peptide, while the parallel and perpendicular 286 excitation of the peptide $\pi \rightarrow \pi^*$ transition is responsible for the other negative peak at 287 210 nm and the positive peak at 192 nm (Gobeaux and Wien, 2018). 288

With the addition of different amounts of Pt NPs to the HSA aqueous solution, theSRCD spectra of the Pt NPs-HSA mixture remained unchanged for three repeated scans

at 37°C (Figure 5). This clearly indicates that Pt NPs does not induce a significant
conformation change of the protein at 37°C.

293

[Figure 5]

294 Thermal denaturation

The thermal stability of proteins without or with Pt NPs was assessed by recording the intensity of SRCD signal at 192 nm as a function of temperature. SRCD spectra of pure HSA and Pt NPs-HSA at different ratios from 1:30 to 1:1 were recorded at temperatures in the range of 26~95°C. The temperature scans of Pt NPs:HSA=1:7.5 are presented in **Figure 6**. The spectra clearly indicate that the temperature increase causes a gradual decrease of the alpha helical profile.

301

[Figure 6]

302 The decreasing of the relative intensity of protein with temperature in Figure 7, 303 showed that the thermal denaturation curves were shifted with the increasing ratio of Pt 304 NPs-HSA towards higher T_m . The resulting T_m is reported in **Table 1**. From the results, 305 we observe the T_m increases with increasing the Pt NPs concentration. The free HSA 306 has a T_m of 56°C, which is in good agreement with reported results that HSA undergoes 307 morphological changes at 56°C (Das et al., 2014). The T_m of Pt NPs-HSA=1:1 is 74°C, 308 increased 18°C compared to the T_m of free HSA. The tremendous increase in T_m 309 suggests that Pt NPs increase the thermal stability of HSA. It was shown by other groups that silver NPs decrease the thermal stability of HSA, while gold NPs (using the 310 311 same preparation method as silver NPs) did not significantly change it (Laera et al., 312 2011) even at same ratio of NPs-HSA. However, different experimental conditions must 313 be taken into consideration.

314 Structure analysis

A more detailed analysis of the two spectra using deconvolution software BeStSel allows estimating the percentage of secondary structure α -helix, β -sheet, turn and random coil elements present in each SRCD spectrum.

318 Figure 7 shows that the content of α -helix conformation of HSA decreases from 61% to 29%, on contrary β -sheet and random coil increase from 1% to 20% and 30% to 40% 319 respectively, with a subsequent increase of unfolded protein, as a function of the 320 increasing temperature. The turn component of HSA remains practically constant for all 321 322 the samples ~10% (in the interval 26~95°C). The same trends were found in the presence of Pt NPs, except the structuration in beta sheet was significantly lower at high 323 324 temperature with the addition of Pt NPs (ratios of Pt NPs-HSA ranging from 1:30 to 1:1). 325

326 Protein conformational compositions in pure HSA indicate an increase in β -sheet 327 conformation from 0% to 20% at the expenses of the α -helix content (which diminished 328 from 57% to 28%) when the temperature rises from 38°C to 89°C. As the temperature 329 increases, the cooperative hydrogen bonds that stabilized the helical structure weakened 330 and expose hydrophobic groups to the solvent, partially unfolding the protein structure, which favours the formation of beta-sheet-rich amyloid fibrils (Juárez et al., 2009). It 331 was shown that the presence of NPs can influence the protein fibrillation process 332 333 (Mahmoudi et al., 2013). In this case, the alpha helix decreased less in the presence of 334 Pt NPs than in pure HAS, and an increase in random coils substituted the α -helix loss, indicating that Pt NPs prevent inter-protein interactions, and thus increase the 335 336 conformational stability of proteins.

343

[Figure 7]

344 Thermodynamic analysis

The biological responses to NPs are influenced by the forces (such as electrostatic, hydrophobic or Van der Waals forces) present at the bio-nano interface (Mariam et al., 2017). Hence it is essential to have a complete understanding of the thermodynamics of Pt NPs-HSA interaction. The thermodynamic properties (enthalpy variation, entropy variation) obtained by fitting the temperature changes of local helix content to the Van't Hoff equation Eq. 3 (Greenfield, 2006):

$$351 lnK = \frac{-\Delta H^{\circ}}{RT} + \frac{\Delta S^{\circ}}{R} (3)$$

where K is the binding constant at the corresponding temperature, and R is universal gas 352 constant. ΔH^0 and ΔS^0 are presented in **Table 1**. We found out a gradual increase of 353 354 enthalpy variation and entropy variation in the presence of Pt NPs with increasing T_m . It can be seen that the enthalpy variation increases significantly from 87 kJ/mol of pure 355 HSA to 116 kJ/mol of Pt NPs-HSA=1:1. The same phenomenon was observed by other 356 groups. It was explained by Senske et al, that nanoparticles can stabilize the native 357 conformation of proteins compared to the unfolded state under external stresses such as 358 359 temperatures (Senske et al., 2014). This stabilization is explained by an unfavourable 360 interaction of the protein and the nanoparticles leading to a preferential exclusion of the nanoparticles from the protein surface and a preferential hydration of the protein. Since 361 362 the solvent accessible surface area is usually increased for the unfolded state, in the 363 presence of Pt NPs, this would increase the thermodynamically unfavourable situation 364 and require more energy for unfolding (unfolding enthalpy variation would increase with the Pt NPs concentration) than in water. As a result, the folding equilibrium should 365 366 tend to shifted toward the more folded, native state.

Finally, the assumption of the increase of the HSA stability with Pt NPs was supported by good agreement with the thermodynamic data and structure analysis for the thermal unfolding transition determined by far-UV SRCD.

[Figure 8]

370

371 **4. Conclusion**

372 In summary, we have successfully synthesized Pt NPs with homogeneous size 373 using radiolytic reduction method by gamma irradiation. The DLS and TEM images indicate that the synthesized Pt NPs are semi-spherical in shape and uniform in size. 374 UV-Vis spectra suggest the complete reduction of Pt^{II} and the formation of Pt NPs. The 375 coherent results of hydrodynamic diameter and ITC demonstrated that Pt NPs do not 376 377 bind to HSA even at the high ratio of 1 Pt NP per HSA. SRCD secondary spectra show 378 that even the high concentrations of Pt NPs do not induce significant change of the protein conformation. The thermal stability of protein is assessed by SRCD by 379 monitoring the spectral changes in the spectra with increasing temperature. More 380 381 importantly, an increase of 18°C in the thermal unfolding of HSA upon interaction with 382 Pt NPs was found, which support the fact that Pt NPs stabilize the HSA structure. This structure analysis showed that, as the temperature rises, the loss of α -helical content of 383 384 HSA was decreased whereas a significant reduction in β -sheet was observed. This is due 385 to increased stability of HSA in the presence of Pt NPs. The modification of the protein stability can be attributed to the preferential hydration of the protein. This stabilizing 386 387 effect renders Pt NPs highly promising and applicable to be used as biocompatible stabilizing agents for proteins. 388

389 Author contribution

X.Y. synthesized and characterized Pt NPs, performed and analysed the DLS, UV-Vis
spectroscopy, carried out the SRCD spectra analysis, data interpretation and drafted the
manuscript. E.P. supervised the experimental protocols. L.M., S.P., J.P.R., A.K.
conceived and performed the experiments of ITC. D.S.L, C. G., A. K. and X.L.
contributed to the paper modifications. F.W., X. Y., E. P., A.K., C. G. optimized and

performed the SRCD experiments. H.R., and D.S.L were engaged in nanoparticles
design, synthesis and characterization. S.L. conceived the entire project, reviewing and
editing the manuscript. All authors revised the manuscript.

398 Acknowledgements

X.Y. acknowledges support from China scholarship council (CSC, N° 201607040068).
We acknowledge support from the Université Paris Saclay for the "Inititative de
Recherche Stratégique" IRS NanoTheRad project. This work also benefited from the
RESPORE grant. SRCD measurements on DISCO beamline at SOLEIL synchrotron
light source were performed under the proposal 20171494. We thank Ruxandra Gref
(Institut des Sciences Moléculaires d'Orsay, Université Paris Saclay) for providing kind
help on ITC experiments.

406 **Reference**

- Abidi, W., Selvakannan, P., Guillet, Y., Lampre, I., Beaunier, P., Pansu, B., Palpant, B.,
 Remita, H., 2010. One-pot radiolytic synthesis of gold nanorods and their optical
 properties. The Journal of Physical Chemistry C 114, 14794-14803.
- Belloni, J., Mostafavi, M., Remita, H., Marignier, J.-L., Delcourt, M.-O., 1998.
 Radiation-induced synthesis of mono-and multi-metallic clusters and nanocolloids. New
- 412 Journal of Chemistry 22, 1239-1255.
- 413 Capomaccio, R., Jimenez, I.O., Colpo, P., Gilliland, D., Ceccone, G., Rossi, F., Calzolai,
- 414 L., 2015. Determination of the structure and morphology of gold nanoparticle-HSA
- 415 protein complexes. Nanoscale 7, 17653-17657.
- 416 Das, N.K., Ghosh, N., Kale, A.P., Mondal, R., Anand, U., Ghosh, S., Tiwari, V.K.,
- 417 Kapur, M., Mukherjee, S., 2014. Temperature induced morphological transitions from
- 418 native to unfolded aggregated states of human serum albumin. The Journal of Physical
- 419 Chemistry B 118, 7267-7276.
- 420 Dasari, S., Tchounwou, P.B., 2014. Cisplatin in cancer therapy: molecular mechanisms
- 421 of action. European journal of pharmacology 740, 364-378.

- 422 Dockal, M., Carter, D.C., Rüker, F., 1999. The three recombinant domains of human
 423 serum albumin structural characterization and ligand binding properties. Journal of
 424 Biological Chemistry 274, 29303-29310.
- 425 Ehi-Eromosele, C., 2016. The Effect of Polyethylene Glycol (PEG) Coating on the
- 426 Magneto-Structural Properties and Colloidal Stability Of Co0. 8Mg0. 2Fe2O4
- 427 Nanoparticles for Potential Biomedical Applications. Digest Journal of Nanomaterials428 and Biostructures.
- 429 Freitas de Freitas, L., Varca, G., dos Santos Batista, J., Benévolo Lugão, A., 2018. An
- 430 Overview of the Synthesis of Gold Nanoparticles Using Radiation Technologies.431 Nanomaterials-Basel 8, 939.
- Gharibshahi, E., Saion, E., 2012. Influence of dose on particle size and opticalproperties of colloidal platinum nanoparticles. International journal of molecular
- 434 sciences 13, 14723-14741.
- Gobeaux, F., Wien, F., 2018. Reversible assembly of a drug peptide into amyloid fibrils:
 a dynamic circular dichroism study. Langmuir 34, 7180-7191.
- Greenfield, N.J., 2006. Using circular dichroism collected as a function of temperature
 to determine the thermodynamics of protein unfolding and binding interactions. Nature
 protocols 1, 2527.
- 440 Gref, R., Lück, M., Quellec, P., Marchand, M., Dellacherie, E., Harnisch, S., Blunk, T.,
- 441 Müller, R., 2000. 'Stealth' corona-core nanoparticles surface modified by polyethylene
- 442 glycol (PEG): influences of the corona (PEG chain length and surface density) and of
- the core composition on phagocytic uptake and plasma protein adsorption. Colloids and
- 444 Surfaces B: Biointerfaces 18, 301-313.
- Holade, Y., Servat, K., Tingry, S., Napporn, T.W., Remita, H., Cornu, D., Kokoh, K.B.,
- 2017. Advances in electrocatalysis for energy conversion and synthesis of organicmolecules. ChemPhysChem 18, 2573-2605.
- 448 Ibrahim, I.M., Abbas, A.K., Naser, D.K., 2016. SYNTHESIS AND ZETA
 449 POTENTIAL OF NOBLE METALS (Pt, Au, Ag AND Cu) NANOPARTICLES
- 450 PREPARED BY PULSE LASER ABLATION. Science International 28.
- 451 Inwati, G.K., Rao, Y., Singh, M., 2016. In situ free radical growth mechanism of
- 452 platinum nanoparticles by microwave irradiation and electrocatalytic properties.
- 453 Nanoscale research letters 11, 458.

- Juárez, J., Taboada, P., Mosquera, V., 2009. Existence of different structural
 intermediates on the fibrillation pathway of human serum albumin. Biophysical journal
 96, 2353-2370.
- 457 KA, M.A., Ab Rashid, R., Lazim, R.M., Dollah, N., Razak, K.A., Rahman, W., 2018.
- Evaluation of radiosensitization effects by platinum nanodendrites for 6 MV photon
- beam radiotherapy. Radiation Physics and Chemistry 150, 40-45.
- Lacombe, S., Porcel, E., Scifoni, E., 2017. Particle therapy and nanomedicine: state ofart and research perspectives. Cancer nanotechnology 8, 9.
- 462 Laera, S., Ceccone, G., Rossi, F., Gilliland, D., Hussain, R., Siligardi, G., Calzolai, L.,
- 2011. Measuring protein structure and stability of protein–nanoparticle systems with
 synchrotron radiation circular dichroism. Nano letters 11, 4480-4484.
- Lee, P., Wu, X., 2015. Modifications of human serum albumin and their binding effect.
 Current pharmaceutical design 21, 1862-1865.
- 467 Lees, J., Smith, B., Wien, F., Miles, A., Wallace, B., 2004. CDtool-an integrated
- 468 software package for circular dichroism spectroscopic data processing, analysis, and469 archiving. Analytical biochemistry 332, 285-289.
- 470 Li, Y., Budamagunta, M.S., Luo, J., Xiao, W., Voss, J.C., Lam, K.S., 2012. Probing of
- the assembly structure and dynamics within nanoparticles during interaction with blood

472 proteins. ACS nano 6, 9485-9495.

- 473 Mahmoudi, M., Kalhor, H.R., Laurent, S., Lynch, I., 2013. Protein fibrillation and
- 474 nanoparticle interactions: opportunities and challenges. Nanoscale 5, 2570-2588.
- 475 Mariam, J., Sivakami, S., Dongre, P., 2017. Elucidation of structural and functional
- 476 properties of albumin bound to gold nanoparticles. Journal of Biomolecular Structure
- 477 and Dynamics 35, 368-379.
- 478 Medhat, A., Mansour, S., El-Sonbaty, S., Kandil, E., Mahmoud, M., 2017. Evaluation
- 479 of the antitumor activity of platinum nanoparticles in the treatment of hepatocellular
- 480 carcinoma induced in rats. Tumor Biology 39, 1010428317717259.
- 481 Micsonai, A., Wien, F., Bulyáki, É., Kun, J., Moussong, E., Lee, Y.-H., Goto, Y.,
- 482 Réfrégiers, M., Kardos, J., 2018. BeStSel: A web server for accurate protein secondary
- 483 structure prediction and fold recognition from the circular dichroism spectra. Nucleic
- 484 acids research 46, W315-W322.
- 485 Micsonai, A., Wien, F., Kernya, L., Lee, Y.-H., Goto, Y., Réfrégiers, M., Kardos, J.,
- 486 2015. Accurate secondary structure prediction and fold recognition for circular

- dichroism spectroscopy. Proceedings of the National Academy of Sciences 112, E3095-E3103.
- Moores, A., Goettmann, F., 2006. The plasmon band in noble metal nanoparticles: an
 introduction to theory and applications. New Journal of Chemistry 30, 1121-1132.
- 491 Mu, Q., Jiang, G., Chen, L., Zhou, H., Fourches, D., Tropsha, A., Yan, B., 2014.
- 492 Chemical basis of interactions between engineered nanoparticles and biological systems.
- 493 Chemical reviews 114, 7740-7781.
- 494 Pelaz, B., del Pino, P., Maffre, P., Hartmann, R., Gallego, M., Rivera-Fernandez, S., de
- 495 la Fuente, J.M., Nienhaus, G.U., Parak, W.J., 2015. Surface functionalization of
- 496 nanoparticles with polyethylene glycol: effects on protein adsorption and cellular uptake.497 ACS nano 9, 6996-7008.
- 498 Porcel, E., Li, S., Usami, N., Remita, H., Furusawa, Y., Kobayashi, K., Le Sech, C.,
- 499 Lacombe, S., 2012. Nano-Sensitization under gamma rays and fast ion radiation,
- Journal of Physics: Conference Series. IOP Publishing, p. 012006.
- 501 Porcel, E., Liehn, S., Remita, H., Usami, N., Kobayashi, K., Furusawa, Y., Le Sech, C.,
- Lacombe, S., 2010. Platinum nanoparticles: a promising material for future cancertherapy? Nanotechnology 21, 085103.
- Prasanth, S., RitheshRaj, D., Vineeshkumar, T., Sudarsanakumar, C., 2018.
 Spectroscopic exploration of interaction between PEG-functionalized Ag2S
 nanoparticles with bovine serum albumin. Chemical Physics Letters 700, 15-21.
- Rosenberg, B., Vancamp, L., Trosko, J.E., MANSOUR, V.H., 1969. Platinum
 compounds: a new class of potent antitumour agents. Nature 222, 385.
- 509 Salado-Leza, D., Porcel, E., Yang, X., Štefančíková, L., Bolsa-Ferruz, M., Savina, F.,
- 510 Dragoe, D., Guerquin-Kern, J.-L., Wu, T.-D., Hirayama, R., 2020. Green One-Step
- 511 Synthesis of Medical Nanoagents for Advanced Radiation Therapy. Nanotechnology,
- 512 Science and Applications 13, 61.
- 513 Salado-Leza, D., Traore, A., Porcel, E., Dragoe, D., Muñoz, A., Remita, H., García, G.,
- Lacombe, S., 2019. Radio-enhancing properties of bimetallic Au: Pt nanoparticles:
- experimental and theoretical evidence. International Journal of Molecular Sciences 20,5648.
- 517 Sanchez-Guzman, D., Giraudon--Colas, G.l., Marichal, L., Boulard, Y., Wien, F.,
- 518 Degrouard, J., Baeza-Squiban, A., Pin, S., Renault, J.P., Devineau, S., 2020. In situ
- analysis of weakly bound proteins reveals molecular basis of soft corona formation.
- 520 ACS nano 14, 9073-9088.

- Saptarshi, S.R., Duschl, A., Lopata, A.L., 2013. Interaction of nanoparticles with
 proteins: relation to bio-reactivity of the nanoparticle. Journal of nanobiotechnology 11,
 26.
- 524 Satzer, P., Svec, F., Sekot, G., Jungbauer, A., 2016. Protein adsorption onto 525 nanoparticles induces conformational changes: particle size dependency, kinetics, and 526 mechanisms. Engineering in life sciences 16, 238-246.
- 527 Schlathölter, T., Eustache, P., Porcel, E., Salado, D., Stefancikova, L., Tillement, O.,
- 528 Lux, F., Mowat, P., Biegun, A.K., Van Goethem, M.-J., 2016. Improving proton therapy
- 529 by metal-containing nanoparticles: nanoscale insights. International journal of 530 nanomedicine 11, 1549.
- 531 Senske, M., Törk, L., Born, B., Havenith, M., Herrmann, C., Ebbinghaus, S., 2014.
- 532 Protein stabilization by macromolecular crowding through enthalpy rather than entropy.533 Journal of the American Chemical Society 136, 9036-9041.
- 534 Shaw, A.K., Pal, S.K., 2008. Spectroscopic studies on the effect of temperature on pH-
- induced folded states of human serum albumin. Journal of Photochemistry andPhotobiology B: Biology 90, 69-77.
- Shemetov, A.A., Nabiev, I., Sukhanova, A., 2012. Molecular interaction of proteins and
 peptides with nanoparticles. ACS nano 6, 4585-4602.
- 539 Srinivasan, M., Rajabi, M., Mousa, S.A., 2015. Multifunctional Nanomaterials and
- Their Applications in Drug Delivery and Cancer Therapy. Nanomaterials-Basel 5, 1690-1703.
- Suk, J.S., Xu, Q., Kim, N., Hanes, J., Ensign, L.M., 2016. PEGylation as a strategy for
 improving nanoparticle-based drug and gene delivery. Advanced drug delivery reviews
 99, 28-51.
- Takano, Y., Kusaka, A., Nakamura, H., 2016. Density functional study of molecular
 interactions in secondary structures of proteins. Biophysics and physicobiology 13, 2735.
- 548 Uttayarat, P., Eamsiri, J., Tangthong, T., Suwanmala, P., 2015. Radiolytic synthesis of
 549 colloidal silver nanoparticles for antibacterial wound dressings. Advances in Materials
 550 Science and Engineering 2015.
- 551 Wallace, B.A., Janes, R.W., 2010. Synchrotron radiation circular dichroism (SRCD)
- 552 spectroscopy: an enhanced method for examining protein conformations and protein
- interactions. Biochemical Society Transactions 38, 861-873.

- 554 Wang, C.-L., Hsao, B.-J., Lai, S.-F., Chen, W.-C., Chen, H.-H., Chen, Y.-Y., Chien, C.-
- C., Cai, X., Kempson, I.M., Hwu, Y., 2011. One-pot synthesis of AuPt alloyed
 nanoparticles by intense x-ray irradiation. Nanotechnology 22, 065605.
- Wang, P., Wang, X., Wang, L., Hou, X., Liu, W., Chen, C., 2015. Interaction of gold
 nanoparticles with proteins and cells. Science and technology of advanced materials 16,
 034610.
- Wien, F., Wallace, B., 2005. Calcium fluoride micro cells for synchrotron radiation
 circular dichroism spectroscopy. Applied spectroscopy 59, 1109-1113.
- Yang, X., Bolsa-Ferruz, M., Marichal, L., Porcel, E., Salado-Leza, D., Lux, F.,
 Tillement, O., Renault, J.-P., Pin, S., Wien, F., 2020a. Human serum albumin in the
 presence of AGuIX nanoagents: Structure stabilisation without direct interaction.
 International journal of molecular sciences 21, 4673.
- 566 Yang, X., Salado-Leza, D., Porcel, E., González-Vargas, C.R., Savina, F., Dragoe, D.,
- 567 Remita, H., Lacombe, S., 2020b. A facile one-pot synthesis of versatile PEGylated 568 platinum nanoflowers and their application in radiation therapy. International journal of
- 569 molecular sciences 21, 1619.
- Yang, X., Salado-Leza, D., Porcel, E., González Vargas, C.R., Savina, F., Dragoe, D.,
 Remita, H., Lacombe, S., 2020c. A Facile One-Pot Synthesis of Versatile PEGylated
 Platinum Nanoflowers and Their Application in Radiation Therapy. International
 Journal of Molecular Sciences 21, 1619.
- 574 575
- 2.5
- 576

577

- 578
- 579
- 580
- 581

Captions to Figures





Figure 1 (a) TEM image and (b) HRTEM images of Pt NPs; (c) TEM size distribution

585 histogram of Pt NPs; (d) DLS size distribution by intensity of Pt NPs;



.



Figure 2 UV-vis absorption spectra of $Pt(NH_3)_4Cl_2$ (green line) solution $(10^{-3} \text{ mol.L}^{-1})$, PEG-OH (red line) solution $(10^{-1} \text{ mol.L}^{-1})$, and diluted Pt containing solutions $(10^{-3} \text{ mol.L}^{-1})$ before (blue line) and after (pink line) irradiation (optical path = 2 mm). Inset is the absorption spectra of samples in a wavelength range from 200 to 400 nm.

592









Figure 4. Isothermal titration calorimetry (ITC) plots of differential power throughoutthe titration (a), integrated heat as a function of the mole ratio of Pt NPs-HSA (b).

600



601

602 Figure 5 SRCD spectra of HSA alone and Pt NPs-HSA at NPs:HSA molar ratios of

603 1:30, 1:15 and 1:7.5 and 1:1, respectively at pH=7.4, 37°C.



Figure 6 Temperature scans of Pt NPs:HSA=1:7.5 with steps of 3° C (from 26° C to 95°C).



607

Figure 7 Thermal denaturation curves of pure HSA and the Pt NPs-HSA complex at

609 different ratios (1:30, 1:15, 1:7.5, and 1:1) monitored at 192nm.

610

611 612

Table 1. Values of the melting temperatures Tm, enthalpy variations ΔH° and entropy variations ΔS° for HSA and Pt NPs-HSA at different concentrations (ratios from 1:30 to 1:1) monitored at 192 nm.

Sample	Tm,⁰C	$\Delta H^{\circ}, kJ \cdot mol^{-1}$	$\Delta S^{\circ}, kJ \cdot mol^{-1} \cdot K^{-1}$
HSA	56 ± 0.3	87.3±1.9	0.26 ± 0.006
Pt NPs-HSA 1:30	61 ± 0.3	89.5 ± 1.3	0.27 ± 0.004
Pt NPs-HSA 1:15	64 ± 0.4	92.8±2.0	0.27 ± 0.006
Pt NPs-HSA 1:7.5	69 ± 0.4	101.3 ± 4.2	0.28 ± 0.010
Pt NPs-HSA 1:1	74 ± 0.4	116.4±4.5	0.35 ± 0.014



Figure 8 Contribution of the protein conformations: alpha-helix (a), beta sheet (b), turns
(c), and random coil (d), in the structure of HSA at different temperatures (from 26°C to
95°C), in the case of pure HSA and Pt NPs-HSA complex at different ratios (1:30, 1:15,
1:7.5, 1:1).