



Study of the mechanical properties of polymers reinforced with nanoparticles of adjustable size, shape and surface chemistry

Sakina Mefath, Fahmi Bedoui, Kondo Djimédo, Anh-Tu Ngo, Isabelle Lisiecki

► To cite this version:

Sakina Mefath, Fahmi Bedoui, Kondo Djimédo, Anh-Tu Ngo, Isabelle Lisiecki. Study of the mechanical properties of polymers reinforced with nanoparticles of adjustable size, shape and surface chemistry. C'Nano 2023 : The Nanoscience Meeting, Mar 2023, Poitiers, France. hal-04487607

HAL Id: hal-04487607

<https://hal.science/hal-04487607>

Submitted on 4 Mar 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Study of the mechanical properties of polymers reinforced with nanoparticles of adjustable size, shape and surface chemistry


MEFTAH Sakina^{1,2} – BEDOUI Fahmi¹ – KONDO Djimédo³ – NGO Anh-Tu² – LISIECKI Isabelle²

Laboratoire Roberval UTC Compiègne¹ - Laboratoire Monaris Sorbonne Université² - Institut d'Alembert Sorbonne Université³
sakina.meftah@utc.fr

Context & Objectif


To Investigate the effects of size, surface chemistry and morphology of iron oxide nanofillers on the mechanical and thermal properties of nanoreinforced polymers:

1. Ligand-coated maghemite ($\gamma\text{-Fe}_2\text{O}_3$) nanoparticles are synthesized by the thermal decomposition of an organometallic precursor.
2. Growth mechanisms are investigated through the effect of each key parameter (mentioned in the next section) on the nanoparticle characteristics (size, surface chemistry, morphology).
3. The aim is to synthesize tunable (1) sizes, (2) shapes and (3) surface chemistries.




Previous studies

Material studied




NPs size
Silica NP
Non-functionalized NPs


For NPs sizes smaller than 15 nm, only the theoretical study has been performed.



Modulus of elasticity




Degradation temperature



Glass-transition temperature


Polymer Testing Volume 56, December 2016, Pages 337-343

Synthesis



J. Phys. Chem. C 2014, 118, 3795–3810


Growth control



These key parameters have an impact on the size, surface chemistry, morphology and crystallinity of the NPs.

Some results

Water trace




Dehydration condition of the precursor

Conditions

Solvent : Diethyl ether
Ligand : Oleic acid
Heating rate 45°C/min

Reflux time




Nanoparticles growth
All scale bars are at 100nm

Solvent : Hexadecene
Ligand : Oleic acid
Heating rate 5°C/min

Plateau

Reflux temperature



Reflux temperature (defined by the solvent boiling point) varies the size of the nanoparticles

Ligand : Oleic acid
Heating rate 45°C/min

Conclusion

Perspectives

- ✓ The effects of trace of water, temperature & reflux time, impurities in the precursor on the NPs size and morphology were observed.

- the study will be further pursued for growth control and tuning of structural and chemical properties of nanoparticles in order to elaborate and investigate the mechanical properties of nano-reinforced polymers



**Institut de science
des matériaux**
ALLIANCE SORBONNE UNIVERSITÉ