Electronic Supporting Information

Efficient and sustainable tandem annulation-decarboxylation reaction using ecocatalysis

Laure Liénart,^a Yves-Marie Legrand,^a Franck Pelissier,^a Philippe Gaveau,^b Peter Hesemann,^b Eddy Petit,^c Claude Grison,^a* Claire M. Grison^a*1

^a ChimEco, Univ Montpellier, CNRS UMR 5021, Montpellier, France; ^b ICGM, Univ Montpellier, CNRS UMR5253, ENSCM, Montpellier, France; ^c IEM, Univ Montpellier, CNRS UMR 5635, ENSCM, Montpellier, France.

Table of contents

| Char | acterisation of ecocatalysts [®] | 2 |
|------------------------|--|---|
| 1.1. | MP-AES analyses of ecocatalysts [®] | 2 |
| 1.2. | XRPD diffractograms of ecocatalysts [®] | 2 |
| Synth | nesis and characterisation of cyclohexenones | 5 |
| 2.1. correlat | Synthesis of 3-methyl-2-cyclohexenone: experimental conditions used for the Spearman ion matrix | 5 |
| 2.2. coffee g | Synthesis of 3-methyl-2-cyclohexenone using Eco1-E-spent C. arabica from different spen grounds | t 6 |
| 2.3. | Recycling and reuse of ecocatalysts [®] | 6 |
| 2.4. | Method of calculation of green metrics | 6 |
| 2.5. 2.5.1 2.5.2 | Procedure and characterisation of cyclohexenones General procedure for the scope of isolated cyclohexenones ¹ H and ¹³ C NMR spectra of cyclohexenones | 7 7 9 |
| | <i>Char</i> 1.1. 1.2. <i>Synth</i> 2.1. correlat 2.2. coffee g 2.3. 2.4. 2.5. 2.5.1 2.5.2 | Characterisation of ecocatalysts[®] 1.1. MP-AES analyses of ecocatalysts[®] 1.2. XRPD diffractograms of ecocatalysts[®] Synthesis and characterisation of cyclohexenones 2.1. Synthesis of 3-methyl-2-cyclohexenone: experimental conditions used for the Spearman correlation matrix 2.2. Synthesis of 3-methyl-2-cyclohexenone using Eco1-E-spent C. arabica from different spen coffee grounds 2.3. Recycling and reuse of ecocatalysts[®] 2.4. Method of calculation of green metrics 2.5. Procedure and characterisation of cyclohexenones 2.5.1. General procedure for the scope of isolated cyclohexenones 2.5.2. ¹H and ¹³C NMR spectra of cyclohexenones |

^{*} Corresponding author. Tel.: +33786854454.

E-mail address: <u>claire.grison.2@cnrs.fr</u>; claude.grison@cnrs.fr

1. Characterisation of ecocatalysts[®]

1.1. MP-AES analyses of ecocatalysts®

| | mean of wt(%) (standard deviation) | | | | | | | | | | | | |
|---------------------------------|---------------------------------------|----------------|-----------------|----------|----------|----------------|---------------|----------------|----------------|----------------|----------|----------|----------------|
| Ecocatalyst [®] | Al | Ca | Cd | Cr | Cu | Fe | К | Mg | Mn | Na | Ni | Pb | Zn |
| Eco1-E-Salix | 0.07 | 19.4 | 0.01 | 0 | 0 | 0.12 | 13.1 | 3.00 | 0.02 | 0.26 | 0 | 0,01 | 0,21 |
| alba | (0.03) | (2.8) | (0.01) | (0) | (0) | (0.03) | (5.9) | (0.89) | (0.01) | (0.03) | (0) | (0.02) | (0.04) |
| Eco1-E- Fallopia japonica | 0.13 (0.04) | 8.93 (2.02) | 0.007 (0.01) | 0 (0) | 0 (0) | 0.13 (0.03) | 29.2 (1.8) | 3.98 (0.23) | 0.06 (0.02) | 0.14 (0.04) | 0 (0) | 0 (0) | 0.04 (0.05) |
| Eco1-E-Arundo | 0.01 | 1.37 | 0.03 | 0 | 0.01 | 0.025 | 36.2 | 1.01 | 0.03 | 0.08 | 0 | 0 | 0.01 |
| donax | (0) | (0.51) | (0.02) | (0) | (0.07) | (0.01) | (4.3) | (0.06) | (0.01) | (0.05) | (0) | (0) | (0.01) |
| Eco1-E-spent | 0.19 | 21.49 | 0.01 | 0 | 0.15 | 0.39 | 4.93 | 7.33 | 0.19 | 1.97 | 0 | 0 | 0.05 |
| Coffea arabica | (0.11) | (1.66) | (0.01) | (0) | (0.02) | (0.09) | (2.70) | (0.28) | (0.02) | (0.56) | (0) | (0) | (0.01) |

Table S1. Elemental composition of ecocatalysts[®] determined by MP-AES.

1.2. XRPD diffractograms of ecocatalysts[®]



Figure S1. XRPD of Eco1-E-F. japonica



Figure S2. XRPD of Ecol-E-S. alba



Figure S3. XRPD of Eco1-E-A. donax



Figure S4. XRPD of Ecol-E-spent C. arabica

2. Synthesis and characterisation of cyclohexenones

2.1. Synthesis of 3-methyl-2-cyclohexenone: experimental conditions used for the Spearman correlation matrix

Table S2. Details of experimental conditions of 38 reactions used for calculating the Spearman correlation matrix. *These conditions have been reproduced 9 times and the yield corresponds to the mean of the 9 yields.

| Exp. | (eco)catalyst | K | Mg | Ca | Na | cat. | temp. | time | glycerol | yield |
|------|--|--------|--------|--------|--------|---------|------------------------|----------------------|----------|------------------|
| 1 | | (eq.) | (eq.) | (eq.) | (eq.) | (g/moi) | <u> (°C)</u> 180 | (min) 30 | (eq.) | <u>(%)</u> 45 |
| 2 | | 0,0012 | 0,0027 | 0,0041 | 0,0007 | 2 | 180 | 30 | 0,5 | |
| 2 | Ecol-E-spent | 0,0058 | 0,0034 | 0,0001 | 0,0014 | 2 | 180 | 30 | 0,5 | 65 |
| 3 | C. arabica | 0,0130 | 0,0218 | 0,0323 | 0,0058 | 16 | 100 | 20 | 0,5 | 05 |
| 4 | | 0,0343 | 0,0300 | 0,0745 | 0,0152 | 10 | 100 | 30 | 0,5 | 20 |
| 5 | | 0,0000 | 0,0017 | 0,0000 | 0,0000 | 0 | 180 | 30 | 0,5 | 30 |
| 6 | | 0,0000 | 0,0033 | 0,0000 | 0,0000 | 0 | 180 | 30 | 0,5 | 60 |
| 7 | MgO | 0,0000 | 0,0066 | 0,0000 | 0,0000 | 0 | 180 | 30 | 0,5 | 55 |
| 8 | - | 0,0000 | 0,0131 | 0,0000 | 0,0000 | 1 | 180 | 30 | 0,5 | 71 |
| 9 | | 0,0000 | 0,0525 | 0,0000 | 0,0000 | 2 | 180 | 30 | 0,5 | 67 |
| 10 | | 0,0000 | 0,1000 | 0,0000 | 0,0000 | 4 | 180 | 30 | 0,5 | 88 |
| 11 | | 0,0109 | 0,0000 | 0,0000 | 0,0000 | 1 | 180 | 30 | 0,5 | 45 |
| 12 | K ₂ CO ₂ | 0,0263 | 0,0000 | 0,0000 | 0,0000 | 2 | 180 | 30 | 0,5 | 62 |
| 13 | 112003 | 0,0526 | 0,0000 | 0,0000 | 0,0000 | 4 | 180 | 30 | 0,5 | 60 |
| 14 | | 0,1000 | 0,0000 | 0,0000 | 0,0000 | 7 | 180 | 30 | 0,5 | 72 |
| 15 | Eco1-E-A. donax | 0,2137 | 0,0110 | 0,0109 | 0,0004 | 25 | 180 | 30 | 0,5 | 65 |
| 16 | Eco1-E-S. alba | 0,0406 | 0,0110 | 0,0660 | 0,0004 | 10 | 180 | 30 | 0,5 | 67 |
| 17 | Eco1-E-F. japonica | 0,0479 | 0,0110 | 0,0110 | 0,0051 | 11 | 180 | 30 | 0,5 | 68 |
| 18 | Eco1-E-A. donax | 0,0499 | 0,0026 | 0,0025 | 0,0001 | 5,86 | 180 | 30 | 0,5 | 57 |
| 19 | MgO | 0,0000 | 0,0131 | 0,0000 | 0,0000 | 1 | 180 | 30 | 0,5 | 71 |
| 20 | CaCO ₃ | 0,0000 | 0,0000 | 0,0440 | 0,0000 | 4 | 180 | 30 | 0,5 | 14 |
| 21 | Ca ₅ (PO ₄) ₃ OH | 0,0000 | 0,0000 | 0,0440 | 0,0000 | 4 | 180 | 30 | 0,5 | 0 |
| 22 | MgO & CaCO ₃ & Ca ₅ (PO ₄) ₃ OH | 0,0000 | 0,0130 | 0,0320 | 0,0000 | 4 | 180 | 30 | 0,5 | 82 |
| 23 | Eco1-E-spent C. arabica (350 °C) | 0,0085 | 0,0181 | 0,0293 | 0,0263 | 36 | 180 | 90 | 0,5 | 57 |
| 24 | Eco1-E-spent C. arabica (no TT) | 0,0030 | 0,0027 | 0,0066 | 0,0103 | 131 | 180 | 30 | 0,5 | 5 |
| 25 | K_2CO_3 | 0,0109 | 0,0000 | 0,0000 | 0,0000 | 1 | 180 | 30 | 0 | 29 |
| 26 | K_2CO_3 | 0,0109 | 0,0000 | 0,0000 | 0,0000 | 1 | 180 | 30 | 0,5 | 45 |
| 27 | Eco1-E-spent <i>C. arabica</i> | 0,0075 | 0,0109 | 0,0162 | 0,0029 | 4 | 180 | 30 | 0 | 34 |
| 28 | | 0,0075 | 0,0109 | 0,0162 | 0,0029 | 4 | 100 | 30 | 0,5 | 0 |
| 29 | | 0,0075 | 0,0109 | 0,0162 | 0,0029 | 4 | 120 | 30 | 0,5 | 0 |
| 30 | Ecol-E-spent | 0,0075 | 0,0109 | 0,0162 | 0,0029 | 4 | 140 | 30 | 0,5 | 16 |
| 31 | C. arabica | 0,0075 | 0,0109 | 0,0162 | 0,0029 | 4 | 160 | 30 | 0,5 | 56 |
| 32 | | 0,0075 | 0,0109 | 0,0162 | 0,0029 | 4 | 200 | 30 | 0,5 | 84 |

| 33 | | 0,0075 | 0,0109 | 0,0162 | 0,0029 | 4 | 220 | 30 | 0,5 | 92 |
|-----|-----------------------------------|--------|--------|--------|--------|---|-----|----|-----|-----|
| 34 | | 0,0075 | 0,0109 | 0,0162 | 0,0029 | 4 | 180 | 90 | 0,5 | 82 |
| 35 | Ecol-E-spent | 0,0075 | 0,0109 | 0,0162 | 0,0029 | 4 | 220 | 45 | 0,5 | 92 |
| 36 | C. arabica | 0,0075 | 0,0109 | 0,0162 | 0,0029 | 4 | 220 | 90 | 0,5 | 72 |
| 37* | Eco1-E-spent <i>C. arabica</i> | 0,0075 | 0,0109 | 0,0162 | 0,0029 | 4 | 180 | 30 | 0,5 | 81* |
| 38 | - | 0,0000 | 0,0000 | 0,0000 | 0,0000 | 0 | 180 | 30 | 0,5 | 0 |

2.2. Synthesis of 3-methyl-2-cyclohexenone using Eco1-E-spent C. arabica from different spent coffee grounds



collection date of spent coffee ground

Figure S5: Yield comparison for the synthesis of 3-methyl-2-cyclohexenone using Ecol-E-spent C. arabica from spent coffee grounds collected at different seasons. Conditions of the reaction: ethylacetoacetate (2 equiv.), Ecol-E-spent C. arabica (0.01 equiv.) of Mg), butenone (1 equiv.) and glycerol (0.5 equiv.), 180 °C, 30 min. Yields were quantified by GC-FID analysis.

2.3. Recycling and reuse of ecocatalysts[®]

| Table S3. Experimenta | al conditions for t | he recycling of E | Ecol-E-spent C. arabica |
|-----------------------|---------------------|-------------------|-------------------------|
|-----------------------|---------------------|-------------------|-------------------------|

| run | ecocatalyst® | temp. (°C) | time (min) | yield (%) |
|-----|-------------------------|------------|------------|-----------|
| 1 | | | | 72 |
| 2 | | | | 63 |
| 3 | Eco1-E-spent C. arabica | 220 | 45 | 63 |
| 4 | | | | 37 |
| 5 | | | | 38 |

2.4. Method of calculation of green metrics

E-factor

$$E_{factor} = \frac{\text{total mass of all wastes (for all runs, reaction and workup)}}{\text{total mass of final product (for all runs)}}$$

Process Mass Intensity (PMI)

$$PMI = \frac{\text{total mass of reactants}}{\text{mass of final product}}$$

Energy

$$E(h. °C) = (reaction time) \times (reaction temperature)$$

Since data of electric power are not available for each electric equipment used to perform a chemical reaction followed by its workup in literature, the calculation of energy could not be done in Joules and was simplified.

Space Time Yield (STY)

STY $(g.h^{-1}.L^{-1}) = \frac{\text{masse of product}}{\text{volume of reactor } \times \text{ reaction time}}$

Turn-Over Number (TON)

 $TON = \frac{\text{total moles of limiting reactants of all runs}}{\text{moies of catalysts used for all runs}} \times \text{mean of all yields}$

Turn-Over Frequency (TOF)

TOF $(h^{-1}) = \frac{TON}{reaction time of all catalysed reactions}$

2.5. Procedure and characterisation of cyclohexenones

2.5.1. General procedure for the scope of isolated cyclohexenones

The β -keto ester (2 equiv.), Eco1-E-spent *C. arabica* (0.011 equiv. of Mg), conjugated enone (or enal) (1 equiv.) and glycerol (0.5 equiv.) were mixed in a micro-wave reactor (CEM Discover[®] 2.0). The reaction mixture was ramped to temperature for 10 minutes until 180 °C, then was stirred for 45 minutes at 180 °C. The reaction procedure was repeated four times for subsequent purification. After cooling to room temperature, the Eco1-E-spent *C. arabica* was filtered through sinter with ethyl acetate (20 mL) and the collected solution was concentrated under reduced pressure. The crude product was purified by distillation under vaccum.

3-methyl-2-cyclohexen-1-one (3). The reaction of ethyl acetoacetate (30 mmol, 3.83 mL, 2 equiv.), Eco1-E-spent *C. arabica* (0.17 mmol, 53 mg, 0.011 equiv. of Mg), 3-buten-2-one (15 mmol, 1.39 mL, 1 equiv.) and glycerol (7.5 mmol, 0.6 mL, 0.5 equiv.) provided **3** in 65% yield/70% purity. The product was isolated by liquid-liquid extraction with NaOH 0.5M (3 x 18 mL) and ethyl acetate (25 mL). The product **3** was isolated in 55% yield as a light yellow liquid by distillation. ¹H NMR (600 MHz, CDCl₃) δ : 5.86 (bs, 1H), 2.32 (m, 2H), 2.27 (t, J = 6.0 Hz, 2H), 2.00-1.95 (m, 2H), 1.94 (s, 3H); ¹³C NMR (150 MHz, CDCl₃) δ : 199.8, 162.9, 126.7, 37.1, 31.0, 24.5, 22.6.

3-ethyl-2-cyclohexen-1-one (7). The reaction of ethyl acetoacetate (30 mmol, 3.83 mL, 2 equiv.), Eco1-E-spent *C. arabica* (0.17 mmol, 53 mg, 0.011 equiv. of Mg), 1-penten-3-one (15 mmol, 1.53 mL, 1 equiv.) and glycerol (7.5 mmol, 0.6 mL, 0.5 equiv.) provided **7** in 73% yield/76% purity. The crude product was isolated by liquid-liquid extraction with NaOH 0.5M (3 x 18mL) and ethyl acetate (25 mL). The product **7** was isolated in 63% yield as a light yellow liquid. ¹H NMR (600 MHz, CDCl₃) δ : 5.87 (s, 1H), 2.35 (m, 2H), 2.28 (t, J = 6.0 Hz, 2H), 2.25-2.21 (q, J = 7.4 Hz, 2H), 2.00-1.95 (m, 2H), 1.10-1.07 (t, J = 7.4 Hz, 3H); ¹³C NMR (150 MHz, CDCl₃) δ : 200.0, 167.9, 124.5, 37.3, 30.8, 29.6, 22.6, 11.2.

3,6-dimethyl-2-cyclohexen-1-one (8). The reaction of ethyl 2-methylacetoacetate (30 mmol, 4.24 mL, 2 equiv.), Eco1-E-spent *C. arabica* (0.17 mmol, 53 mg, 0.011 equiv. of Mg), 3-buten-2-one (15 mmol, 1.39 mL, 1 equiv.) and glycerol (7.5 mmol, 0.6 mL, 0.5 equiv.) provided **8** in 69% yield/75% purity. The crude product was isolated by liquid-liquid extraction with NaOH 0.5M (5 x 18mL) and ethyl acetate (25 mL). The product **8** was isolated

in 67% yield as a light yellow liquid. ¹H NMR (600 MHz, CDCl₃) δ : 5.81 (s, 1H), 2.36-2.21 (m, 3H), 2.04-2.00 (m, 1H), 1.91 (s, 3H), 1.70-1.64 (m, 1H), 1.10 (d, J = 7.2 Hz, 3H); ¹³C NMR (150 MHz, CDCl₃) δ : 202.5, 161.9, 126.4, 40.7, 31.0, 30.9, 24.5, 15.4.

2,3-dimethyl-2-cyclohexen-1-one (9). The reaction of ethyl 3-oxovalerate (30mmol, 4.29mL, 2 equiv.), Eco1-E-spent *C. arabica* (0.17 mmol, 53 mg, 0.011 equiv. of Mg), 3-buten-2-one (15 mmol, 1.39 mL, 1 equiv.) and glycerol (7.5 mmol, 0.6 mL, 0.5 equiv.) provided **9** in in 79% yield/72% purity. The crude product was isolated by liquid-liquid extraction with NaOH 0.5M (3 x 24 mL) and ethyl acetate (30 mL). The product **9** was isolated in 74% yield as a light yellow liquid. ¹H NMR (600 MHz, CDCl₃) δ : 2.37 (m, 2H), 2.33-2.31 (m, 2H), 1.94-1.90 (m, 5H), 1.75 (s, 3H); ¹³C NMR (150 MHz, CDCl₃) δ : 199.3, 155.3, 131.2, 37.7, 32.9, 22.4, 21.6, 10.9.

3,5-dimethyl-2-cyclohexen-1-one (10). The reaction of ethyl acetoacetate (30 mmol, 3.83 mL, 2 equiv.), Ecol-E-spent *C. arabica* (0.17 mmol, 53 mg, 0.011 equiv. of Mg), 3-penten-2-one (15 mmol, 2.31 mL, 1 equiv.) and glycerol (7.5 mmol, 0.6 mL, 0.5 equiv.) provided **10** in 90% yield/100% purity as a light yellow liquid. ¹H NMR (600 MHz, CDCl₃) δ : 5.83 (s, 1H), 2.38 (dd, J = 16.2, 3.6 Hz, 1H), 2.27 (dd, J = 18.0, 4.2 Hz, 1H), 2.20-2.12 (m, 1H), 2.01-1.96 (m, 2H), 1.92 (s, 3H), 1.04 (d, J = 6.6 Hz, 3H); ¹³C NMR (150 MHz, CDCl₃) δ : 200.3, 162.2, 126.5, 45.4, 39.6, 30.2, 24.5, 21.3.

Isophorone (11). The reaction of ethyl acetoacetate (30 mmol, 3.83 mL, 2 equiv.), Eco1-E-spent *C. arabica* (0.17 mmol, 53 mg, 0.011 equiv. of Mg), mesityl oxide (15 mmol, 1.81 mL, 1 equiv.) and glycerol (7.5 mmol, 0.6 mL, 0.5 equiv.) provided **12** in 6% yield/68% purity. The crude product was isolated by liquid-liquid extraction with NaOH 0.5M (3x6mL) and ethyl acetate (8 mL). The product **12** was isolated in 6% yield as a light yellow liquid. ¹H NMR (600 MHz, CDCl₃) δ : 5.86 (m, 1H), 2.18 (s, 2H), 2.15 (s, 2H), 1.92 (s, 3H), 1.01 (s, 6H); ¹³C NMR (150 MHz, CDCl₃) δ : 200.1, 160.5, 125.6, 50.9, 45.4, 33.7, 28.4, 24.7.

5-Methyl-2-cyclohexen-1-one (12). The reaction of ethyl acetoacetate (30 mmol, 3.83 mL, 2 equiv.), Eco1-E-spent *C. arabica* (0.17 mmol, 53 mg, 0.011 equiv. of Mg), crotonaldehyde (15 mmol, 1.39 mL, 1 equiv.) and glycerol (7.5 mmol, 0.6 mL, 0.5 equiv.) provided **13** in 33% yield/100% purity as a light yellow liquid. ¹H NMR (600 MHz, CDCl₃) δ : 6.95 (ddd, J = 15.0, 10.2, 8.4 Hz, 1H), 6.02-5.98 (m, 1H), 2.50-2.37 (m, 2H), 2.28-2.16 (m, 1H), 2.14-1.98 (m, 2H), 1.06 (d, J = 10.2 Hz, 3H); ¹³C NMR (150 MHz, CDCl₃) δ : 200.2, 150.0, 129.7, 46.4, 34.1, 30.5, 21.3.

4-methyl-2-cyclohexen-1-one (13). The reaction of ethyl acetoacetate (30 mmol, 3.83 mL, 2 equiv.), Eco1-E-spent *C. arabica* (0.17 mmol, 53 mg, 0.011 equiv. of Mg), methacrolein (15 mmol, 1.39 mL, 1 equiv.) and glycerol (7.5 mmol, 0.6 mL, 0.5 equiv.) provided **11** in 33% yield/80% purity. ¹H NMR (600 MHz, CDCl₃) δ : 6.78 (ddd, J = 10.2, 2.4, 1.2 Hz, 1H), 5.92 (ddd, J = 10.2, 2.4, 1.2 Hz, 1H), 2.54-2.52 (m, 1H), 2.47-2.44 (m, 1H), 2.36-2.31 (m, 1H), 2.10-2.07 (m, 1H), 1.68-1.61 (dddd, J = 16.8, 13.2, 9.0, 4.2 Hz, 1H), 1.13 (d, J = 7.2 Hz, 3H); ¹³C NMR (150 MHz, CDCl₃) δ : 200.1, 156.6, 128.9, 37.2, 31.4, 31.2, 20.5.

2.5.2. ¹H and ¹³C NMR spectra of cyclohexenones

3-methyl-2-cyclohexen-1-one (3)



Figure 7. ¹³C NMR spectrum (150MHz, CDCl₃) of 3



3-ethyl-2-cyclohexen-1-one (7)



3,6-dimethyl-2-cyclohexen-1-one (8)





Figure 8. ¹³C NMR spectrum (150MHz, CDCl₃) of 9







Isophorone (11)



5-Methyl-2-cyclohexen-1-one (12)



4-methyl-2-cyclohexen-1-one (13)