



**HAL**  
open science

## Nuclear spin relaxation mediated by donor-bound and free electrons in wide CdTe quantum wells

Boris Gribakin, Valentina Litvyak, Mladen Kotur, Régis André, Maria Vladimirova, Dmitri Yakovlev, Kirill Kavokin

► **To cite this version:**

Boris Gribakin, Valentina Litvyak, Mladen Kotur, Régis André, Maria Vladimirova, et al.. Nuclear spin relaxation mediated by donor-bound and free electrons in wide CdTe quantum wells. 2024. hal-04525437

**HAL Id: hal-04525437**

**<https://hal.science/hal-04525437>**

Preprint submitted on 28 Mar 2024

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Nuclear spin relaxation mediated by donor-bound and free electrons in wide CdTe quantum wells

B. F. Gribakin,<sup>1,2,\*</sup> V. M. Litvyak,<sup>2</sup> M. Kotur,<sup>3</sup> R. André,<sup>4</sup> M. Vladimirova,<sup>1</sup> D. R. Yakovlev,<sup>3</sup> and K. V. Kavokin<sup>2</sup>

<sup>1</sup>*Laboratoire Charles Coulomb, UMR 5221 CNRS-Université de Montpellier, F-34095 Montpellier, France*

<sup>2</sup>*Spin Optics Laboratory, St. Petersburg State University, 198504 St. Petersburg, Russia*

<sup>3</sup>*Experimentelle Physik 2, Technische Universität Dortmund, 44227 Dortmund, Germany*

<sup>4</sup>*Université Grenoble Alpes, CNRS, Institut Néel, 38000 Grenoble, France*

(Dated: February 29, 2024)

The nuclear spin systems in CdTe/(Cd,Zn)Te and CdTe/(Cd,Mg)Te quantum wells (QW) are studied using a multistage technique combining optical pumping and Hanle effect-based detection. The samples demonstrate drastically different nuclear spin dynamics in zero and weak magnetic fields. In CdTe/(Cd,Zn)Te, the nuclear spin relaxation time is found to strongly increase with the magnetic field, growing from 3 s in zero field to tens of seconds in a field of 25 G. In CdTe/(Cd,Mg)Te the relaxation is an order of magnitude slower, and it is field-independent up to at least 70 G. The differences are attributed to the nuclear spin relaxation being mediated by different kinds of resident electrons in these QWs. In CdTe/(Cd,Mg)Te, a residual electron gas trapped in the QW largely determines the relaxation dynamics. In CdTe/(Cd,Zn)Te, the fast relaxation in zero field is due to interaction with localized donor-bound electrons. Nuclear spin diffusion barriers form around neutral donors when the external magnetic field exceeds the local nuclear field, which is about  $B_L \approx 0.4$  G in CdTe. This inhibits nuclear spin diffusion towards the donors, slowing down relaxation. These findings are supported by theoretical modeling. In particular, we show that the formation of the diffusion barrier is made possible by several features specific to CdTe: (i) the large donor binding energy (about 10 meV), (ii) the low abundance of magnetic isotopes (only  $\approx 30\%$  of nuclei have nonzero spin), and (iii) the absence of nuclear quadrupole interactions between nuclei. The two latter properties are also favorable to nuclear spin cooling via optical pumping followed by adiabatic demagnetization. Under non-optimized conditions we have reached sub-microkelvin nuclear spin temperatures in both samples, lower than all previous results obtained in GaAs.

## I. INTRODUCTION

The nuclear spin physics of solids has enjoyed a renewed interest from the scientific community in recent years, with modern research being largely stimulated by the possible spintronics and quantum computing applications. Frequently, nuclear spins are seen as an obstacle to reaching long electron coherence times, especially in quantum dots [1, 2]. However, they can also be made useful. For example, the feedback from the nuclei can be used for frequency focusing of electron spin precession in quantum dots [3], and there is a growing body of encouraging research on the topic of hybrid quantum registers employing nuclear spins as long-lived quantum bits [4–8]. As the nuclear spins do not interact directly with light, they are controlled via hyperfine interaction with electrons, which is typically achieved through resonant or nonresonant optical pumping, with protocols of increasing complexity [6, 9–11].

In GaAs, the model semiconductor, every nucleus has spin  $I = 3/2$ , and therefore possesses a nonzero quadrupolar magnetic moment. Once the cubic symmetry is lifted by, e.g., strain or defects, the uncontrollable quadrupolar interactions shorten the nuclear spin lifetime and fundamentally limit nuclear spin temperatures achievable via adiabatic demagnetization. Further-

more, a strong field dependence of nuclear spin relaxation is introduced [12, 13]. Although there is ongoing research on comparatively strain-free GaAs/(Al,Ga)As quantum dots (see, e.g., Ref. [6]), the quadrupolar effects can hardly be eliminated completely and become particularly important in small magnetic fields.

Consequently, materials with  $I = 1/2$  are intriguing, as the nuclei do possess spin, but completely lack quadrupolar moments, and thus the aforementioned properties of their nuclear spin systems are robust with respect to stress, defects and electric fields. CdTe is especially interesting in this regard as the local field describing nuclear spin-spin interactions ( $B_L \approx 0.4$  G [14]) is smaller than in GaAs ( $\approx 1$  G [15]) due to the low abundance of Cd and Te isotopes with nonzero spin (the latter will be referred to as magnetic nuclei hereafter). This is expected to reduce the lowest achievable nuclear spin temperature [16, 17] and to influence nuclear spin diffusion [18]. Additionally, CdTe is very similar to GaAs in electronic properties, the primary difference being the higher exciton/donor binding energy and, consequently, the smaller Bohr radius  $a_B \approx 5$  nm [19, 20].

To use the nuclear spin system in a device, one should find a way of controlling it. A seldom explored possibility consists in using an external magnetic field to manipulate the diffusion barrier [18]. A nuclear spin diffusion barrier arises when the magnetic field gradient becomes larger than the local field; this hinders spin flips between neighboring nuclei, slowing down and eventually inhibiting nu-

\* [boris.gribakin@umontpellier.fr](mailto:boris.gribakin@umontpellier.fr)




FIG. 1. Schematic diagrams of the spin-lattice interactions studied in this work. (a) Donor-bound electrons in a wide insulating CdTe QW with low barriers; nuclear spins interact with the strongly localized individual electron spins. (b) Resident electron gas forming on QW potential fluctuations (shown by barrier color) in a deep CdTe QW with unintentional barrier doping; nuclear spins interact with the weakly localized 2D electron gas. The electron gas puddles constitute a only a small portion of the entire QW area ( $\langle n_{2D} \rangle$  is the electron gas density averaged over the entire QW).

clear spin diffusion. Upon applying a threshold magnetic field the bulk polarized nuclei would become separated from the donor site, preventing rapid diffusion and relaxation on the donor after pumping is stopped [21]. In semiconductors, there is no consensus on the subject of diffusion barriers: although there is some evidence for their formation in GaAs quantum dots at high magnetic fields [22, 23], there is more recent evidence to the contrary [24]. Nevertheless, it is tempting to search for diffusion barrier formation in lightly or even unintentionally  $n$ -doped CdTe, as the relatively strong localization on donors together with the small local field should make the effect quite observable as far as the electrons remain localized. Conversely, one would not expect to see a significant magnetic field response if the electrons are not strongly localized, disappearing completely in the limit of bulk Korringa relaxation [25].

For our study of the CdTe nuclear spin system, we have chosen two illustrative structures. Both samples are studied in similar conditions via optical pumping followed by adiabatic demagnetization, with photoluminescence (PL) polarization measurements serving as a probe of the nuclear spin state. Sample A is a very wide high-quality CdTe quantum well (QW) sandwiched between low (Cd,Zn)Te barriers. The QW contains a small number of donors due to unintentional  $n$ -doping. The nuclear spin dynamics develops around these donors. The inhomogeneous Knight field of the donor-bound electrons creates a diffusion barrier, which results in a magnetic




FIG. 2. Low-temperature PL and PL polarization spectra of the two samples studied: (a) Sample A, (b) Sample B. Black vertical lines show the energies used for nuclear spin polarization measurements.

field dependence of the nuclear spin relaxation. Sample B is a thinner CdTe QW surrounded by very high (Cd,Mg)Te barriers. Here, fluctuations of the QW potential attract electrons, which form rare ( $< 10^{10} \text{ cm}^{-3}$ ) two-dimensional (2D) electron gas puddles, while the rest of the QW remains basically electron-free. This leads to slow temperature-dependent nuclear spin relaxation induced by fluctuations of the electron spin near the Fermi level in the areas covered by 2D electron gas with a large contribution due to nuclear spin diffusion from electron-free areas but with no notable dependence on the applied magnetic field. Phenomenological modeling of nuclear spin relaxation in these two different regimes supports the proposed interpretation.

The paper is organized as follows. Section II describes the studied samples in more detail. It is followed by Section III which describes the experimental data obtained. In Section IV we examine the experimental results and present their theoretical modeling, summarizing our findings in Section V. Finally, Appendices A and B feature extended descriptions of the theoretical models.

## II. SAMPLES & CHARACTERIZATION

The two CdTe QW structures were grown by molecular beam epitaxy. Sample A is a 30-nm-wide CdTe QW sandwiched between  $\text{Cd}_{0.95}\text{Zn}_{0.05}\text{Te}$  barriers, grown on a  $\text{Cd}_{0.96}\text{Zn}_{0.04}\text{Te}$  substrate. The top barrier also functions as the capping layer and is 93 nm thick. The other studied structure contains four 20-nm CdTe QWs surrounded by high  $\text{Cd}_{1-x}\text{Mg}_x\text{Te}$  barriers ( $x \approx 20 - 30\%$ ), which differ in top barrier (=capping layer) thickness. For Sample B we have chosen the QW with the smallest cap layer thickness of just 17.5 nm.

Both samples are nominally undoped, however, the low-temperature PL spectra shown in Fig. 2 indicate some unintentional doping. In Sample A, we interpret the main PL features as the free exciton ground state X (1.5981 eV), the negative trion X<sup>-</sup> (1.5962 eV), and the exciton bound to neutral donor D<sup>0</sup>X (1.5953 eV), as the binding energies are consistent with literature data [26–28]. The structure of the free exciton resonance series is also reproduced by calculations similar to that of Ref. [29], where a sample grown under the same conditions as Sample A was studied.

In Sample B the overall blueshift due to additional quantum confinement energy is partly compensated by the enhanced exciton binding energy [20]. We interpret the spectrum similarly to Sample A. Evidently, there are some donors inside the QW as well as acceptors (the D<sup>0</sup>X, A<sup>0</sup>X peaks at 1.5939 and 1.5903 eV, respectively) [28]. However, the relative intensity of the trion line (1.5962 eV) as compared with the free exciton (1.5988 eV) suggests that a dilute carrier gas is present. Although a structure similar to Sample B was shown to contain a hole gas, with the carrier type changing under above-barrier excitation [30], supplementary pump-probe measurements (data not shown) confirm the presence of an electron gas in Sample B. Additionally, due to the height of the Mg barriers, small variations of Mg content lead to rather large QW potential fluctuations. That is to say, a Mg density variation of just 1% would lead to more than a 10 meV change in total barrier height [31, 32]. These areas trap the electrons drawn to the QW from the barriers, which results in electron gas puddles that live indefinitely. As we will show in Sec. IV, the electron gas density of these puddles is no higher than 10<sup>10</sup> cm<sup>-2</sup>.

### III. EXPERIMENTAL

Nuclear spin polarization experiments were performed following the standard optical orientation technique [33]. Overall, the setups and experimental protocols are quite similar to Refs. [12, 13, 34, 35], and have been extensively used in studies of nuclear spin relaxation in GaAs. During the optical cooling stage, the nuclear spins are dynamically polarized in a longitudinal magnetic field  $B_{\text{pump}}$  under optical pumping with circularly polarized light. Once the pumping is stopped, we proceed with adiabatic demagnetization to zero field. During this process, the nuclear spin system reaches internal equilibrium and its lowest spin temperature  $\theta_N^{(0)}$ . In the next stage, the transverse field  $B_{\text{dark}}$  is applied, and nuclear spin relaxation proceeds for a time  $t_{\text{dark}}$ , after which we conduct the measurement. An illustration of the protocol is shown in Fig. 3.

The measurement procedure yields the effective nuclear field  $B_N$  (the Overhauser field [36] that the nuclei exert on the electrons via hyperfine interaction). The procedure consists in switching on simultaneously the transverse measuring field  $B_m$  and the pumping beam,




FIG. 3. An illustration of the experimental protocol used to measure nuclear spin relaxation as a function of the magnetic field  $B_{\text{dark}}$ . The demagnetization stage (shown by gray area) is very short and takes place between the cooling and relaxation stages. The times  $t_{\text{pump}}$ ,  $t_{\text{dark}}$  are not to scale. The data shown in the lower panel have been measured on Sample A at  $B_{\text{dark}} = 25$  G at  $t_{\text{dark}} = 25$  s.

and then recording the PL depolarization. The PL polarization degree  $\rho(t)$  is then determined by the total field  $B_m + B_N$  experienced by the electrons (the Hanle effect), and can be described with

$$\rho(t) = \frac{\rho_0 B_{1/2}^2}{B_{1/2}^2 + \left[ B_m + b + (B_N(t_{\text{dark}}) - b) \exp\left(-\frac{t-t_{\text{dark}}}{T_1}\right) \right]^2}, \quad (1)$$

where  $\rho_0$  is the polarization degree in zero transverse field,  $B_{1/2}$  is the half-width of the Hanle curve,  $T_1$  is the PL polarization relaxation time, and  $b$  is a small nuclear field brought about by additional nuclear spin cooling in the Knight field of photocreated electrons during measurement [12].

In experiments on Sample A, the nuclear spins were pumped for  $t_{\text{pump}} = 610$  s in an external field of  $B_{\text{pump}} = 150$  G by a laser tuned to  $E = 1.822$  eV (above-barrier excitation), with  $B_m = 1.2$  G.

Sample B was subjected to a shorter pumping time of  $t_{\text{pump}} = 100$  s, and the applied field was also somewhat weaker,  $B_{\text{pump}} = 115$  G. The pumping energy was  $E = 1.631$  eV (below-barrier excitation), and the measuring field was chosen equal to the pumping field,  $B_m = 115$  G. We note that in experiments on both samples the pumping energy was dictated by laser availability, not pumping efficiency.

The rate of spin exchange between, e.g., neutral donors and free electrons is orders of magnitude faster than the nuclear spin dynamics [21]. Therefore, all of the electron states are equally valid sensors of the nuclear spin state. As such, the detection energies were chosen to maximize the PL polarization degree  $\rho(t)$ . The PL intensity and polarization spectra are shown in Fig. 2. Solid black lines




FIG. 4. Nuclear spin dynamics in Sample A. Solid lines: self-consistent theoretical modeling via diffusion equation. The strong dependence on magnetic field is well-described by the onset of a diffusion barrier due to the inhomogeneous Knight field. The curve at  $B_{\text{dark}} = 0$  corresponds to spatially homogeneous diffusion with  $D = 3 \times 10^{-13} \text{ cm}^2\text{s}^{-1}$  with relaxation via bound electrons. The diffusion barrier becomes more significant as  $B_{\text{dark}}$  grows, slowing nuclear spin diffusion and impeding relaxation. For details, see Sec. IV A and Appendix A.

indicate the detection energies, 1.6019 eV and 1.5861 eV for Samples A and B respectively. Additional modeling shows that in Sample A this roughly corresponds to the free exciton state formed by the e1-hh3 quantum-confined states. In Sample B we are likely probing states that are localized on QW potential fluctuations.

The results of measurements on Samples A and B are presented in Figs. 4 and 5, respectively. The two samples exhibit drastically different nuclear spin dynamics.

In Sample A we observe an increase of the nuclear spin lifetime with the transverse magnetic field  $B_{\text{dark}}$ , and it reaches tens of seconds at best.

Sample B demonstrates a much longer nuclear spin lifetime of the order of hundreds of seconds, which is independent of  $B_{\text{dark}}$ , but depends on temperature. Additionally, there is a background – an extremely long-lived component of the nuclear spin polarization that persists for thousands of seconds.

It is instructive to estimate the lowest nuclear spin temperature reached in these experiments on CdTe and compare to the existing measurements in GaAs samples. Since  $B_m > B_L$ , from the Curie law we get [33]

$$\theta_N^{(0)} = \frac{\hbar \langle \gamma \rangle I(I+1)}{3k_B} \frac{B_L b_N}{B_N} \Big|_{t_{\text{dark}}=0}, \quad (2)$$

where  $k_B$  is the Boltzmann constant,  $\langle \gamma \rangle = -6.47 \times 10^7 \text{ rad s}^{-1} \text{ T}^{-1}$  is the average gyromagnetic ratio of magnetic isotopes [37], and

$$b_N = \frac{I \langle A \rangle}{\mu_B g_e} \approx 700 \text{ G} \quad (3)$$




FIG. 5. Nuclear spin dynamics in Sample B at  $T = 5 \text{ K}$  (a) and  $10 \text{ K}$  (b). Points: experimental data, solid lines: modeling via Eq. (7). The dynamics is governed by free electron-induced relaxation and diffusion. It is independent of the magnetic field, as the electron localization is insufficient for the diffusion barrier effect. At  $10 \text{ K}$  the relaxation rate is the same at  $6.8 \text{ G}$  and  $68 \text{ G}$ , only the backgrounds are different. For details, see Sec. IV B and Appendix B.

is the value of the nuclear field at saturation, where  $\langle A \rangle = -13 \mu\text{eV}$  is the average hyperfine constant [38–40],  $g_e = -1.6$  is the electron  $g$ -factor [41], and  $\mu_B$  is the Bohr magneton.

Applying Eq. (2), we find that the nuclear spins of Sample A are cooled down to around  $0.3 \mu\text{K}$ . In Sample B the temperature is even lower, possibly reaching as low as  $0.08 \mu\text{K}$ , although it is difficult to make a precise measurement due to the aforementioned in-plane inhomogeneity of Sample B. Nevertheless, even after subtracting the background completely, we arrive at around the same nuclear spin temperature as for Sample A,  $\theta_N^{(0)} \approx 0.3 \mu\text{K}$ . For comparison, to our knowledge the lowest spin temperatures obtained in GaAs are  $0.5 \mu\text{K}$  ([35], rotating frame) and  $2 \mu\text{K}$  ([17], laboratory frame). Considering that such a low temperature is obtained under pumping conditions which were not optimized for the most efficient nuclear spin cooling, these results suggest that CdTe is a potential candidate for reaching record low temperatures in the semiconductor nuclear spin system.




FIG. 6. Results of modeling the Sample A nuclear spin dynamics with a field-dependent diffusion coefficient  $D(B_{\text{dark}})$ . Sharp changes in diffusion occur in fields close to the local field  $B_L \approx 0.2 - 0.4$  G. Inset: corresponding fits of the data.

## IV. DISCUSSION

### A. Donor-bound electrons (Sample A)

The nuclear spin relaxation in Sample A (see Fig. 4) is rather fast, with nuclear spin lifetimes of the order of seconds. We assume that the relaxation is due to hyperfine interaction with donor-bound electrons, as these are essentially the only resident electrons in the sample. The distinct field-dependent behavior that we observe can be phenomenologically modeled by a radial diffusion equation with a nuclear spin diffusion coefficient  $D$  that depends on  $B_{\text{dark}}$ , see Fig. 6. To account for the experimental results, the diffusion coefficient must experience a sharp change in fields of the order of 0.3 G, close to the value of the local field  $B_L$ . We theoretically estimate the local field due to both magnetic dipole-dipole interaction and indirect interactions to be  $\lesssim 0.4$  G. This is consistent with NMR linewidth measurements in CdTe, which give a value of about 0.2 G for  $^{125}\text{Te}$  [42].

The field dependence of the diffusion coefficient suggests the formation of a nuclear spin diffusion barrier. Below we briefly explain the principles of nuclear spin relaxation affected by the diffusion barrier; further details can be found in Appendix A.

In weak magnetic fields  $B_{\text{dark}} \gtrsim B_L$ , the cold nuclear spins are easily polarized, resulting in an Overhauser field that is much larger than  $B_{\text{dark}}$ . The polarized nuclei interact with electrons. Since the resident electrons are localized on donors and their density is low, the hyperfine relaxation mechanism is dominant over the spin-orbit one. It can be shown that in this regime dynamic electron polarization by nuclei takes place [43], and the average electron spin  $\langle S_z \rangle$  is determined by the mean nuclear spin  $\langle I_z \rangle$ , and is therefore proportional to the Overhauser

field  $B_N$ . In turn, the polarized electrons exert a weak but highly inhomogeneous Knight field back upon the nuclei,  $B_e(\mathbf{r}_j) \propto |\psi(\mathbf{r}_j)|^2 \langle S \rangle$ , where  $\psi(\mathbf{r}_j)$  is the electron wavefunction at the nucleus located at  $\mathbf{r}_j$ . Indeed, the Knight fields experienced by two nearby nuclei situated at a distance  $r$  away from the donor and separated by  $r_{ij} \ll a_B$  differ by:

$$\Delta B_e(r, B_N) = r_{ij} \left| \frac{\partial B_e(r)}{\partial r} \right|. \quad (4)$$

If at any distance  $r$  from the donor  $\Delta B_e(r, B_N) > B_L$ , then the corresponding nuclear spin flips are suppressed due to energy conservation. Eq. (4) allows us to estimate (see Appendix A) that at  $B_{\text{dark}}$  as small as 1 G in the immediate vicinity of the donor site  $\Delta B_e(r, B_N) > B_L$  even for a pair of nearest-neighbor nuclei with nonzero spin separated by  $r_{\text{nn}}$ , so nuclear diffusion is expected to be strongly suppressed.

The rigorous calculation of the spatial and field-dependent behavior of the diffusion coefficient is outside the scope of this work. Instead, we incorporate the effect by linking the diffusion coefficient  $D$  with the Overhauser field  $B_N$  induced by  $B_{\text{dark}}$  through  $\Delta B_e(r_{\text{nn}}, B_N)$  (hereafter referred to as  $\Delta B_e^{\text{nn}}$ ) as defined by Eq. (4). This is ensured by a phenomenological dependence which satisfies

$$D(\Delta B_e^{\text{nn}}) \approx 0, \quad \text{if} \quad \Delta B_e^{\text{nn}} \gg B_L; \quad (5)$$

$$D(\Delta B_e^{\text{nn}}) \approx D_0, \quad \text{if} \quad \Delta B_e^{\text{nn}} \ll B_L. \quad (6)$$

In the above,  $D_0$  is the nuclear spin diffusion coefficient in the absence of Knight-field feedback, i.e., in zero external field. Thus, the diffusion coefficient is spatially inhomogeneous and time-dependent, as  $\Delta B_e^{\text{nn}}$  follows the spatial distribution of the Knight field, which scales with the time-dependent  $B_N$ . In the theoretical curves of Fig. 4, a step-like  $D(\Delta B_e^{\text{nn}})$  was used, accurately describing the data with  $B_L = 0.4$  G as calculated from the spin-spin interaction constants measured by Nolle [15, 42]. Additional details regarding the modeling can be found in Appendix A.

Note that the optical cooling stage, where the strong field  $B_{\text{pump}}$  is applied, is modeled with the diffusion coefficient  $D = 0$ , while the curve at  $B_{\text{dark}} = 0$  corresponds to the maximum diffusion coefficient  $D_0 = 3 \times 10^{-13} \text{ cm}^2\text{s}^{-1}$ , which is around what is typically seen in GaAs [21, 44].

### B. Free electrons (Sample B)

As discussed in the previous Section, the seconds-long nuclear spin relaxation and its magnetic field dependence in Sample A are direct consequences of strong electron localization. Since in Sample B we observe nuclear spin relaxation times of the order of a hundred seconds, the electrons responsible for this relaxation must be much less localized. Indeed, as discussed in Sec. II, the presence

of electron gas puddles in Sample B is quite probable, so we turn our attention to free 2D electrons.

In structures hosting an electron gas, nuclear spin relaxation via interaction with free electrons is known to be relevant [44–47]. In the extreme case of a degenerate electron gas, one expects the Korringa relaxation mechanism to dominate. Its defining feature is the simple relationship  $\gamma_K \propto k_B T$  between the Korringa relaxation rate  $\gamma_K$  and the temperature of the electron gas [25]. This is consistent with our measurements, which yield  $\Gamma^{-1} = (138 \pm 8) \text{ s}$  at  $T = 5 \text{ K}$  and  $\Gamma^{-1} = (75 \pm 9) \text{ s}$  at  $T = 10 \text{ K}$ , as determined from single-exponential fits of the data shown in Fig. 5. Thus, we continue with free electron-mediated relaxation.

To implement this idea theoretically, we employ an approach similar to Ref. [48]. A detailed calculation of the Korringa-like relaxation rate  $\Gamma_K(z)$  in a QW containing a low density 2D electron gas is presented in Appendix B; here we only remark that the result is similar to the usual bulk Korringa relaxation [25] and the results of Ref. [48]. However, we do obtain a low-density correction which becomes significant if the Fermi energy is small compared to  $k_B T$ , i.e., when the gas is nondegenerate. As the Korringa mechanism is reserved for degenerate electron gases, hereafter we will refer to the resulting relaxation as *Korringa-like*.

A prominent feature of nuclear spin relaxation via 2D electrons is the dependence of their relaxation rate  $\Gamma_K$  on the position of the nucleus along the QW growth axis:  $\Gamma_K \propto |\psi_e(z)|^4$ . Performing a calculation of  $\Delta B_e^{\text{nn}}$  similar to that made for Sample A via Eq. (4), we find that during pumping, when the Knight field is at its maximum due to the high electron density and average spin, a soft diffusion barrier may arise along the growth axis. During relaxation, however, confinement-induced electron localization in the QW is certainly insufficient to significantly affect spin diffusion along  $z$ , and the diffusion barrier cannot be formed.

The large long-lived backgrounds seen in Fig. 5 are quite surprising, especially in comparison with Sample A. We believe they can only be explained by the entirety of the QW being polarized during pumping. This is consistent with Ref. [49], where homogeneous polarization occurs under resonant pumping. Although in our case the optical pumping is nonresonant, Sample B is pumped below the barrier, which ensures efficient polarization of the QW nuclei.

After pumping we observe a slow relaxation process (see Fig. 5), which could be caused by two factors. First of all, the unpolarized resident electron gas siphons the nuclear spin polarization via Korringa-like relaxation as discussed above. On the other hand, it is possible that simultaneously a portion of the polarization escapes into the electron-free parts the QW via spin diffusion. However, the resident electrons induce relaxation also during pumping. Therefore, the nuclei situated within electron puddles should not be more polarized than the rest of the QW, and the second mechanism is unlikely to be signif-

icant. Eventually, a quasi-stationary regime is reached, where the flow of nuclear spin into the puddles becomes completely compensated by the slow Korringa-like relaxation, leading to the long-lived signal.

It is not feasible to meaningfully model the experiments on Sample B with a diffusion equation similarly to Sec. IV A, as that requires the knowledge of the in-plane electron localization area in addition to other parameters such as the Fermi energy and the diffusion coefficient. To evade this, we spatially integrate the diffusion equation over the area occupied by the resident electron gas. This yields a rate equation for the Overhauser field, or, equivalently, for the average nuclear spin  $I_z = IB_N/b_N$  with the average Korringa-like relaxation rate  $\Gamma_K^{(\text{avg})} = L^{-1} \int_{\text{QW}} \Gamma_K(z) dz$ . An additional term  $P_D(t)$  describes the diffusion flow into or out of the area:

$$\frac{\partial I_z(t)}{\partial t} = P_D(t) - \Gamma_K^{(\text{avg})} I_z(t). \quad (7)$$

Because one cannot easily calculate  $P_D(t)$ , we use a simplified phenomenological expression:

$$P_D(t) = \Gamma_D [J_z - I_z(z)], \quad (8)$$

where  $J_z$  is the average nuclear spin of nuclei unaffected by Korringa-like relaxation, and  $\Gamma_D$  is the diffusion rate. The diffusion coefficient cannot be extracted with this approach, unfortunately. Furthermore, only the sum  $\Gamma_K^{(\text{avg})} + \Gamma_D$  is determined from experiments, although we would expect  $\Gamma_D \ll \Gamma_K^{(\text{avg})}$ , as discussed above.

Fitting the model defined by Eqs. (7-8) to the data enables us to give the lower limit of the nuclear spin polarization of the entire QW in Sample B, which is around 15% at  $T = 5 \text{ K}$  and 6.5–8% at 10 K. These estimates are obtained under the assumption that the observed relaxation is entirely due to diffusion, so  $\Gamma_D \gg \Gamma_K^{(\text{avg})}$ , which is unlikely. Therefore, we expect that the polarization of the electron-free areas is much higher in reality. On the other hand, if all of the relaxation was due to the resident electron gas, that would require a 2D density of approximately  $5 \times 10^9 \text{ cm}^{-2}$  and  $8 \times 10^9 \text{ cm}^{-2}$  for  $T = 5 \text{ K}$  and 10 K, respectively (see Fig. 8 in the Appendix), which are reasonable carrier densities considering the PL spectrum in Fig. 2(b) [30, 40]. The difference between the two densities is also unsurprising, as it is possible that at higher temperatures more electrons from the barriers are collected into the QW, and more donor-acceptor pairs inside the QW are ionized. The noticeable difference between the backgrounds in  $B_{\text{dark}} = 6.8 \text{ G}$  and  $68 \text{ G}$  data at  $T = 10 \text{ K}$  is not clear as the nature of the background signal is not exactly identified. Additional experiments are required to elucidate this issue.

## V. CONCLUSIONS

The nuclear spin dynamics in CdTe QWs is shown to depend strongly on the nature of the electrons present in

the sample.

In the presence of donor-bound electrons, like in the CdTe/(Cd,Zn)Te QW studied here, the enhanced role of the hyperfine interaction is a direct consequence of features specific to CdTe: the low density of magnetic nuclei and absence of quadrupole nuclear moments lead to very efficient nuclear spin cooling, while the large binding energy of electrons produces a strong hyperfine interaction. Thus, the normally weak effect of dynamic polarization of electron spins by the nuclei is enhanced, and leads to the formation of a nuclear spin diffusion barrier. The nuclear spin relaxation is then easily tunable. In zero field nuclear spin diffusion is efficient and the relaxation time is of the order of seconds. In fields larger than  $B_L$ , diffusion is strongly suppressed, increasing the nuclear spin lifetime by more than an order of magnitude in a field of 25 G. A model that accounts for the spatial inhomogeneity of the Knight field and the resulting field-dependent diffusion barrier allows us to quantitatively describe the experimental results.

On the other hand, if resident electrons form a nondegenerate 2D electron gas, as it is in the CdTe/(Cd,Mg)Te QW studied in this work, nuclear spin relaxation is much slower, and is field-independent at least up to fields of the order of 70 G. At  $T = 10$  K, the relaxation time is of the order of 70 s, and two times slower at  $T = 5$  K, much longer than even the longest times measured in the CdTe/(Cd,Zn)Te QW, where nuclear spin relaxation is driven by donor-bound electrons. Such relaxation times are consistent with our calculations of the nuclear spin relaxation induced by hyperfine interaction with a low-density 2D electron gas.

Notably, not only the nuclei in the areas covered by electron gas puddles, but the nuclear spin system across the entire QW plane is polarized during below-barrier pumping, as during pumping electrons are present everywhere in the QW. This introduces a spin diffusion flow into the areas occupied by the resident electrons. Eventually it compensates the Korringa-like relaxation and a steady state is reached, where we end up with a stable nuclear spin polarization that persists for thousands of seconds, dynamically supported by spin diffusion. Modeling shows that at least a  $\sim 15\%$  polarization of the bulk nuclei is achieved at  $T = 5$  K, although further study is required to completely unveil the nature of the long-lived signal and its temperature dependence.

Our theoretical description of free electron-mediated relaxation includes a low-density correction, which generalizes the Korringa relaxation mechanism for arbitrary QW electron densities. This may become useful if the electron gas is purposely injected, either electrically or by modulation doping, at densities below the Mott transition. Applied to our experiments on the CdTe/(Cd,Mg)Te QW, the theory gives us rough estimates of the electron gas density that is inline with our expectations.

Finally, the sub-microkelvin temperatures that we reach by unoptimized optical pumping indicate that

CdTe is a potential candidate for reaching record low nuclear spin temperatures, presumably due to the low abundance of magnetic isotopes and their zero quadrupole moment.

## VI. ACKNOWLEDGEMENTS

The authors are grateful to Steeve Cronenberger and Denis Scalbert for helpful and valuable discussions. BG and MV acknowledge financial support from French National Research Agency, Grant No. ANR-21-CE30-0049 (CONUS). BG acknowledges support from the French Embassy in Moscow (Vernadskii fellowship for young researchers 2021). Contributions of MK and DY are supported by the Deutsche Forschungsgemeinschaft within the International Collaborative Research Center TRR 160 (project A6). VL and KK acknowledge financial support from Russian Science Foundation, Grant No. 22-42-09020. RA has benefited from the technical and scientific environment of the CEA-CNRS joint team "Nanophysics and Semiconductors".

### Appendix A: Nuclear spin relaxation and diffusion in the vicinity of donor-bound electrons

We describe the nuclear spin system in CdTe by the average nuclear spin  $\langle I_z(\mathbf{r}, t) \rangle$  as experienced by the electrons, so the angled brackets imply a spatial average over an area that is small in comparison to  $a_B$ , but large enough to include thousands of nuclei. To model the behavior of the nuclear spin polarization, following the seminal work of D. Paget [21] and many others, we write a spin diffusion equation with relaxation and pumping terms. In general, this equation has the form

$$\frac{\partial \langle I_z \rangle}{\partial t} = \nabla [D(\mathbf{r}, t|B) \nabla \langle I_z \rangle] - \Gamma(\mathbf{r}, t) \langle I_z \rangle + P(\mathbf{r}, t). \quad (\text{A1})$$

Here  $\Gamma(\mathbf{r}, t)$  and  $P(\mathbf{r}, t)$  are the electron-mediated nuclear spin relaxation and polarization rates, and  $D(\mathbf{r}, t|B)$  is the magnetic field-dependent diffusion coefficient, which generally is inhomogeneous and time-dependent. The experimentally measured Overhauser field acting on the donor-bound electron is recovered by performing the integration

$$B_N(t) = \frac{b_N}{I} \int \langle I_z(\mathbf{r}, t) \rangle |\psi_{e,\text{loc}}(\mathbf{r})|^2 d\mathbf{r}, \quad (\text{A2})$$

where  $\psi_{e,\text{loc}}(r) = (\pi a_B^3)^{-1/2} \exp(-r/a_B)$  is the wavefunction of the donor-bound electrons.

Let us consider a perfect crystal that is weakly doped with donors. That is to say, at low temperatures the only electrons in the system are the electrons localized on donors, which are separated by distances much greater than the Bohr radius ( $a_B \approx 5$  nm in CdTe). Since all electrons contribute to the signal independently, it is sufficient to describe what happens under one donor orbit.






FIG. 7. (a) Magnitude of the Knight field produced by a donor-bound electron vs. distance from donor  $r$ , measured in units of  $a_B = 5$  nm; (b) difference of Knight fields experienced by two nuclei separated by the most probable nearest-neighbor distance  $r_{nn} = 0.41$  nm. Colors denote values of electron polarization:  $\langle S_z \rangle = 0.5$  (maximum value [33]) and  $\langle S_z \rangle = 0.015$  (estimated from experimental nuclear polarization right after pumping,  $B = 1$  G). Gray area in (b): approximate value of local field  $B_L$ .

The spherical symmetry of the problem reduces Eq. (A1) to its radial part.

Because of the above-barrier pumping and the strong localization of a donor-bound electron, we assume that both the pumping and the relaxation occur via the donor-bound electrons. It is possible to directly calculate the nuclear spin pumping and relaxation rates due to spin-flips with a donor-bound electron described by the wavefunction  $\psi_{e,loc}(r)$ . However, here we limit ourselves to a simpler approach. The nature of the contact hyperfine interaction requires the rates to be proportional to  $|\psi_{e,loc}(r)|^4$ . We may therefore simply write

$$\Gamma(r, t) = \Gamma_0 \exp(-4r/a_B), \quad (\text{A3})$$

$$P(r, t) = P_0 \exp(-4r/a_B), \quad (\text{A4})$$

with  $\Gamma_0$  and  $P_0$  being the relaxation and pumping rates at the center of the donor. In the steady-state, these rates are related through [50, 51]

$$P(r, t) = \frac{I+1}{S+1} \Gamma(r, t) p_e, \quad (\text{A5})$$

where  $S = 1/2$  is the electron spin,  $I = 1/2$  is the spin of magnetic isotopes in CdTe, and  $p_e = \langle S_z \rangle / S$  is the electron spin polarization. The fitted curves in Fig. 4 correspond to  $P_0 = 0.54$  s $^{-1}$  and  $\Gamma_0 = 13.2$  s $^{-1}$  during pumping ( $p_e = 0.04$ ), and  $\Gamma_0 = 0.08$  s $^{-1}$  during relaxation.

As stated in the main text, the field dependent behavior of nuclear spin relaxation observed in Sample A can be understood in terms of a diffusion barrier that builds up due to the inhomogeneity of the Knight field. As the cold nuclear spins are polarized by a magnetic field  $B > B_L$ , the electrons are polarized via mutual spin-flips with nuclei [43], creating a strongly inhomogeneous Knight field  $B_e(r, t) \sim \exp(-2r/a_B)$ . If  $B_e$  is so strong




FIG. 8. Average Korringa-like relaxation rate  $\langle \Gamma_K \rangle$  as a function of 2D electron gas density at various temperatures in a 20-nm CdTe QW, calculated according to Eqs. (B10-B11). The relaxation time of a degenerate electron gas  $\tau_K^d$  is marked for  $T = 5$  K and 25 K, highlighting the distinct  $\tau_K^d T = \text{const}$  behavior.

that the Zeeman splitting of neighboring nuclear spins in  $B_e$  is greater than in the local field  $B_L$ , then mutual spin-flips are forbidden by energy conservation, and diffusion is hindered.

The distance  $r_{nn}$  between two nearest-neighbor magnetic nuclei may be estimated assuming a continuous Poisson distribution with an average density of magnetic isotopes per unit volume  $\sigma$ :

$$r_{nn} = \int_0^\infty r e^{-\frac{4}{3}\pi\sigma r^3} 4\pi r^2 dr \approx 0.55 \sigma^{-1/3}. \quad (\text{A6})$$

Taking into account the isotopic abundances from Table I along with the CdTe lattice constant  $a_0 = 0.648$  nm, we obtain  $r_{nn} = 0.41$  nm. The Knight field experienced by an average magnetic nucleus may be written as:

$$B_e(\mathbf{r}) = -\nu_0 \frac{\sum_\alpha x_\alpha A_\alpha / \gamma_\alpha |\psi_{e,loc}(r)|^2 \langle S_z \rangle}{\sum_\alpha x_\alpha}, \quad (\text{A7})$$

where  $A_\alpha$ ,  $\gamma_\alpha$  and  $x_\alpha$  are the hyperfine constants, gyromagnetic ratios and abundances of magnetic isotopes in CdTe (see Table I), and  $\nu_0 = a_0^3/4$  is the elementary cell volume. The average electron spin is tied to the Overhauser field via

$$\langle I_z \rangle = \langle S_z \rangle \frac{I(I+1)}{S(S+1)}, \quad (\text{A8})$$

which is another form of Eq. (A5). The difference of Knight fields experienced by two nuclei is given by Eq. (4). A simple calculation of  $\Delta B_e^{nn}$  is displayed in Fig. 7, showing that a diffusion barrier should indeed arise at distances of the order of  $a_B$ , depending on the electron spin polarization.

We now suggest a phenomenological expression to model  $D(\mathbf{r}, t|B)$ . The asymptotic conditions of Eqs. (5-6) can be fulfilled most easily by a step function

$$D(\mathbf{r}, t|B) = D_0 H(B_L^{(fit)} - \Delta B_e^{nn}), \quad (\text{A9})$$

where  $H(x)$  is the Heaviside function, and  $B_L^{(\text{fit})}$  is a fitting parameter close to the value of  $B_L$ . Of course, the choice of fitting function is not unique. We have also tested Lorentzian, Gaussian and Fermi functions, as well as a smoothed Heaviside function with similar results, so Eq. (A9) was chosen for simplicity.

A problem that is inherent in this approach has to do with the Knight field following the evolution of the nuclear spin polarization. Because of this, when solving the equation (A1), in principle one must recalculate  $B_N \sim \int \langle I_z(r, t) \rangle |\psi_{e, \text{loc}}(r)|^2 r^2 dr$  at every time-step of the calculation. We evade this by first modeling the experimental data with Eq. (A1) using a set of constant diffusion coefficients  $D(B_{\text{dark}})$ , as shown in Fig. 6. The resulting theoretical curves are used as estimates of the Overhauser field for the purposes of calculating the diffusion coefficient according to Eq. (A9). Injecting these into Eq. (A1), we obtain the theoretical curves in Fig. 4, which display a quantitative agreement with the experimental observations.

TABLE I. Isotope parameters used throughout the work.  $x_\alpha$  are the natural abundances,  $A_\alpha$  are the hyperfine constants, and  $\gamma_\alpha$  are the nuclear gyromagnetic ratios. Throughout this work, we neglect the  $^{123}\text{Te}$  isotope, as its natural abundance is less than 1%. Data are taken from Refs. [38, 40].

Isotope	$x_\alpha$	$A_\alpha$ ( $\mu\text{eV}$ )	$\gamma_\alpha$ ( $10^7 \text{ rad s}^{-1} \text{ T}^{-1}$ )
$^{111}\text{Cd}$	0.13	-37.4	-5.698
$^{113}\text{Cd}$	0.12	-39.1	-5.960
$^{125}\text{Te}$	0.07	-45	-7.059

### Appendix B: Nuclear spin relaxation induced by hyperfine relaxation with 2D electron gas

In this Section, we describe the calculation of the Korringa-like nuclear spin relaxation rate  $\Gamma_K$  introduced in Sec. IV B. Let us consider a perfect infinite QW of width  $L$  with an area  $S$  hosting a 2D electron gas described by Fermi statistics. Applying the same approach as in Ref. [48], we calculate the matrix elements of the electron-nucleus spin-flip transitions due to hyperfine interaction.

Let  $S_z$  be the electron spin projection on the QW growth axis, and let  $I_{z,j}$  be that for the  $j$ -th nucleus. The free electron's wavefunction in the QW  $\psi_{e, \text{free}}(\mathbf{r})$  is given by:

$$\psi_{e, \text{free}}(\mathbf{r}) = \sqrt{\frac{2}{LS}} \cos\left(\frac{\pi}{L}z\right). \quad (\text{B1})$$

Denoting the hyperfine interaction operator as  $\hat{V}_j(\mathbf{r}) = A_j \nu_0 \hat{\mathbf{I}}_j \cdot \hat{\mathbf{S}} \delta(\mathbf{r} - \mathbf{r}_j)$ , where  $\hat{\mathbf{S}}$  and  $\hat{\mathbf{I}}_j$  are the spin operators for electron and  $j$ -th nucleus, respectively, we may write the matrix elements for the mutual spin-flips of the

electron and a nucleus as

$$M_{\pm, j} = \langle S_z \mp 1, I_{z, j} \pm 1, \psi_{e, \text{free}} | \hat{V}_j | S_z, I_{z, j} \psi_{e, \text{free}} \rangle. \quad (\text{B2})$$

A straightforward calculation gives

$$|M_{\pm, j}|^2 = \frac{1}{4} (A_j \nu_0)^2 |\psi_{e, \text{free}}(z_j)|^4 \times [I(I+1) - I_{z, j}^2 \mp I_{z, j}]. \quad (\text{B3})$$

To deal with the average nuclear spin  $\langle I_z(\mathbf{r}, t) \rangle$  interacting with the electron at a given position, we average the matrix elements as

$$|M_\pm(z)|^2 = \frac{1}{4} \langle A^2 \rangle \nu_0^2 |\psi_{e, \text{free}}(z)|^4 \times [I(I+1) - \langle I_z^2 \rangle \mp \langle I_z \rangle]. \quad (\text{B4})$$

The average square of the hyperfine constant  $\langle A^2 \rangle$  is given by

$$\langle A^2 \rangle = \frac{\sum_\alpha A_\alpha^2 x_\alpha}{\sum_\alpha x_\alpha}, \quad (\text{B5})$$

where the sum goes over all magnetic isotopes in CdTe, see Table I.

To obtain the nuclear spin flip rate we average the matrix elements over the statistics of the electron gas, i.e., the Fermi-Dirac distribution  $f(E, E_F) = (1 + \exp[(E - E_F)/k_B T])^{-1}$ . According to the Fermi's golden rule

$$W_\pm = \frac{2\pi}{\hbar} |M_\pm|^2 g_{2D}^2 \int_0^\infty f(E, E_{F, \pm}) [1 - f(E, E_{F, \mp})] dE, \quad (\text{B6})$$

where  $g_{2D} = m_e S / \pi \hbar^2$  is the 2D density of states,  $E_{F, \pm} = E_F \pm \Delta/2$  is the quasi-Fermi level of the  $S_z = \pm 1/2$  electrons,  $\Delta$  is the splitting of the quasi-Fermi levels, and  $E = 0$  corresponds to the bottom of the conduction band.

Neglecting nuclear spin diffusion, we write the rate of change of the nuclear spin as

$$\frac{d\langle I_z \rangle}{dt} = W_+ - W_-. \quad (\text{B7})$$

Performing the integration in Eq. (B6) we find

$$W_+ - W_- = \frac{\pi}{\hbar} k_B T \langle A^2 \rangle \nu_0^2 g_{2D}^2 |\psi_{e, \text{free}}(z)|^4 \times \left[ \tanh \frac{\Delta}{2k_B T} [I(I+1) - \langle I_z^2 \rangle] - \langle I_z \rangle \right] \times f(\Delta, E_F, T), \quad (\text{B8})$$

where

$$f(\Delta, E_F, T) = \frac{1}{2} \ln \left| \frac{e^{-E_F/k_B T} + e^{\Delta/2k_B T}}{e^{-E_F/k_B T} + e^{-\Delta/2k_B T}} \right| \times \coth \frac{\Delta}{2k_B T} \quad (\text{B9})$$

is a dimensionless factor that depends on the 2D electron gas density and temperature. For a degenerate unpolarized gas  $f(\Delta, E_F, T) = 1$ , and we recover the classic Korringa relaxation [25].

In Eq. (B8), the term proportional to  $[I(I+1) - \langle I_z^2 \rangle]$  can be identified as the pumping term, while the coefficient before  $\langle I_z \rangle$  is the relaxation rate. When the pumping beam is turned off after the optical cooling stage, the few resident electrons in Sample B rapidly lose the light-induced polarization, and  $P \rightarrow 0$  as  $\Delta \rightarrow 0$ . We are then left with the Korringa-like nuclear spin relaxation rate

$$\Gamma_K(z) = \frac{\pi}{\hbar} \frac{k_B T}{1 + e^{-E_F/k_B T}} \langle A^2 \rangle \nu_0^2 g_{2D}^2 |\psi_{e,\text{free}}(z)|^4, \quad (\text{B10})$$

which recovers the Korringa behavior  $\Gamma_K(z) \propto k_B T$  at high electron densities, where  $E_F \gg k_B T$ , but is spatially inhomogeneous due to the  $|\psi_{e,\text{free}}(z)|^4$  factor.

As explained in the main text, due to practical diffi-

culties, we do not apply the full Eq. (A1) to describe the Sample B data. Instead, we use Eqs. (7-8), which can be thought of as a spatial average of Eq. (A1). There, we use the spatially averaged  $\Gamma_K^{(\text{avg})} = \frac{1}{L} \int_{\text{QW}} \Gamma_K(z) dz$  as an estimate of the observed nuclear spin relaxation rate. Considering that the Fermi energy and the electron density are linked by

$$n_{2D} = \int_0^\infty g_{2D} f(E, E_F) dE, \quad (\text{B11})$$

we may directly plot  $\Gamma_K^{(\text{avg})}$  as a function of electron density using the parameters from Table I, see Fig. 8. The data presented in this Figure allow us to estimate the density of the electron gas puddles in Sample B by varying the the diffusion contribution  $\Gamma_D$  to the total observed relaxation rate  $\Gamma$ , as described in the main text.

- 
- [1] I. A. Merkulov, A. L. Efros, and M. Rosen, Electron spin relaxation by nuclei in semiconductor quantum dots, *Phys. Rev. B* **65**, 205309 (2002).
- [2] A. V. Khaetskii, D. Loss, and L. Glazman, Electron spin decoherence in quantum dots due to interaction with nuclei, *Phys. Rev. Lett.* **88**, 186802 (2002).
- [3] A. Greilich, A. Shabaev, D. R. Yakovlev, A. L. Efros, I. A. Yugova, D. Reuter, A. D. Wieck, and M. Bayer, Nuclei-induced frequency focusing of electron spin coherence, *Science* **317**, 1896 (2007).
- [4] G. Waldherr, Y. Wang, S. Zaiser, M. Jamali, T. Schulte-Herbrüggen, H. Abe, T. Ohshima, J. Isoya, J. F. Du, P. Neumann, and J. Wrachtrup, Quantum error correction in a solid-state hybrid spin register, *Nature* **506**, 204 (2014).
- [5] T. H. Taminiau, J. Cramer, T. van der Sar, V. V. Dobrovitski, and R. Hanson, Universal control and error correction in multi-qubit spin registers in diamond, *Nature Nanotechnology* **9**, 171 (2014).
- [6] E. A. Chekhovich, S. F. C. da Silva, and A. Rastelli, Nuclear spin quantum register in an optically active semiconductor quantum dot, *Nature Nanotechnology* **15**, 999 (2020).
- [7] E. V. Denning, D. A. Gangloff, M. Atatüre, J. Mørk, and C. Le Gall, Collective quantum memory activated by a driven central spin, *Phys. Rev. Lett.* **123**, 140502 (2019).
- [8] D. A. Gangloff, G. Éthier Majcher, C. Lang, E. V. Denning, J. H. Bodey, D. M. Jackson, E. Clarke, M. Hugues, C. Le Gall, and M. Atatüre, Quantum interface of an electron and a nuclear ensemble, *Science* **364**, 62 (2019).
- [9] M. V. G. Dutt, L. Childress, L. Jiang, E. Togan, J. Maze, F. Jelezko, A. S. Zibrov, P. R. Hemmer, and M. D. Lukin, Quantum register based on individual electronic and nuclear spin qubits in diamond, *Science* **316**, 1312 (2007).
- [10] J. Reiner, Y. Chung, S. H. Misha, C. Lehner, C. Moehle, D. Poulos, S. Monir, K. J. Charde, P. Macha, L. Kranz, I. Thorvaldson, B. Thorggrimsson, D. Keith, Y. L. Hsueh, R. Rahman, S. K. Gorman, J. G. Keizer, and M. Y. Simmons, High-fidelity initialization and control of electron and nuclear spins in a four-qubit register, *Nature Nanotechnology* (2024).
- [11] C. E. Bradley, J. Randall, M. H. Abobeih, R. C. Berrevoets, M. J. Degen, M. A. Bakker, M. Markham, D. J. Twitchen, and T. H. Taminiau, A ten-qubit solid-state spin register with quantum memory up to one minute, *Phys. Rev. X* **9**, 031045 (2019).
- [12] V. M. Litvyak, R. V. Cherbunin, V. K. Kalevich, A. I. Lihachev, A. V. Nashchekin, M. Vladimirova, and K. V. Kavokin, Warm-up spectroscopy of quadrupole-split nuclear spins in *n*-GaAs epitaxial layers, *Phys. Rev. B* **104**, 235201 (2021).
- [13] M. Vladimirova, S. Cronenberger, A. Colombier, D. Scalbert, V. M. Litvyak, K. V. Kavokin, and A. Lemaître, Simultaneous measurements of nuclear-spin heat capacity, temperature, and relaxation in GaAs microstructures, *Phys. Rev. B* **105**, 155305 (2022).
- [14] As determined from the data in Ref. [42] following Refs. [15, 50].
- [15] V. M. Litvyak, R. V. Cherbunin, V. K. Kalevich, and K. V. Kavokin, Local field of spin-spin interactions in the nuclear spin system of *n*-GaAs, *Phys. Rev. B* **108**, 235204 (2023).
- [16] A. Abragam and W. G. Proctor, Spin temperature, *Phys. Rev.* **109**, 1441 (1958).
- [17] M. Vladimirova, S. Cronenberger, D. Scalbert, I. I. Ryzhov, V. S. Zapasskii, G. G. Kozlov, A. Lemaître, and K. V. Kavokin, Spin temperature concept verified by optical magnetometry of nuclear spins, *Phys. Rev. B* **97**, 041301 (2018).
- [18] G. R. Khutsishvili, Spin diffusion, *Soviet Physics Uspekhi* **8**, 743 (1966).
- [19] K. Kheng, R. T. Cox, M. Mamor, K. Saminadayar, and S. Tatarenko, Negatively charged exciton X and donor bound exciton D0X in planar doped CdTe/Cd1-xZnxTe quantum well heterostructures, *Le Journal de Physique IV* **03**, C5 (1993), publisher: EDP Sciences.
- [20] G. Garcia-Arellano, F. Bernardot, G. Karczewski, C. Testelin, and M. Chamarro, Spin relaxation time of

- donor-bound electrons in a CdTe quantum well, *Phys. Rev. B* **99**, 235301 (2019).
- [21] D. Paget, Optical detection of NMR in high-purity GaAs: Direct study of the relaxation of nuclei close to shallow donors, *Phys. Rev. B* **25**, 4444 (1982).
- [22] J. Lu, M. J. R. Hoch, P. L. Kuhns, W. G. Moulton, Z. Gan, and A. P. Reyes, Nuclear spin-lattice relaxation in  $n$ -type insulating and metallic GaAs single crystals, *Phys. Rev. B* **74**, 125208 (2006).
- [23] Z.-X. Gong, Z.-q. Yin, and L.-M. Duan, Dynamics of the overhauser field under nuclear spin diffusion in a quantum dot, *New Journal of Physics* **13**, 033036 (2011).
- [24] P. Millington-Hotze, S. Manna, S. F. Covre da Silva, A. Rastelli, and E. A. Chekhovich, Nuclear spin diffusion in the central spin system of a GaAs/AlGaAs quantum dot, *Nature Communications* **14**, 2677 (2023).
- [25] J. Korringa, Nuclear magnetic relaxation and resonance line shift in metals, *Physica* **16**, 601 (1950).
- [26] G. V. Astakhov, M. M. Glazov, D. R. Yakovlev, E. A. Zhukov, W. Ossau, L. W. Molenkamp, and M. Bayer, Time-resolved and continuous-wave optical spin pumping of semiconductor quantum wells, *Semiconductor Science and Technology* **23**, 114001 (2008).
- [27] J. M. Francou, K. Saminadayar, and J. L. Pautrat, Shallow donors in CdTe, *Phys. Rev. B* **41**, 12035 (1990).
- [28] T. Schmidt, K. Lischka, and W. Zulehner, Excitation-power dependence of the near-band-edge photoluminescence of semiconductors, *Phys. Rev. B* **45**, 8989 (1992).
- [29] A. V. Mikhailov, A. S. Kurdyubov, E. S. Khramtsov, I. V. Ignatiev, B. F. Gribakin, S. Cronenberger, D. Scalbert, M. R. Vladimirova, and R. André, Exciton dynamics in CdTe/CdZnTe quantum well (2023), [arXiv:2304.07135](https://arxiv.org/abs/2304.07135).
- [30] G. Bartsch, M. Gerbracht, D. R. Yakovlev, J. H. Blokland, P. C. M. Christianen, E. A. Zhukov, A. B. Dzyubenko, G. Karczewski, T. Wojtowicz, J. Kossut, J. C. Maan, and M. Bayer, Positively versus negatively charged excitons: A high magnetic field study of CdTe/Cd<sub>1-x</sub>Mg<sub>x</sub>Te quantum wells, *Phys. Rev. B* **83**, 235317 (2011).
- [31] E. G. LeBlanc, M. Edirisooriya, O. S. Ogedengbe, O. C. Noriega, P. A. R. D. Jayathilaka, S. Rab, C. H. Swartz, D. R. Diercks, G. L. Burton, B. P. Gorman, A. Wang, T. M. Barnes, and T. H. Myers, Determining and controlling the magnesium composition in CdTe/CdMgTe heterostructures, *Journal of Electronic Materials* **46**, 5379 (2017).
- [32] S. Adachi, Energy-band structure: Energy-band gaps, in *Properties of Group-IV, III-V and II-VI Semiconductors* (John Wiley & Sons, Ltd, 2005) Chap. 6, pp. 103–145.
- [33] F. Meier and B. P. Zakharchenya, *Optical Orientation* (North-Holland, Amsterdam, 1984).
- [34] M. Kotur, R. I. Dzhioev, M. Vladimirova, B. Jouault, V. L. Korenev, and K. V. Kavokin, Nuclear spin warm up in bulk  $n$ -gaas, *Phys. Rev. B* **94**, 081201 (2016).
- [35] M. Kotur, D. O. Tolmachev, V. M. Litvyak, K. V. Kavokin, D. Suter, D. R. Yakovlev, and M. Bayer, Ultra-deep optical cooling of coupled nuclear spin-spin and quadrupole reservoirs in a gaas/(al,ga)as quantum well, *Communications Physics* **4**, 193 (2021).
- [36] A. W. Overhauser, Polarization of nuclei in metals, *Phys. Rev.* **92**, 411 (1953).
- [37] R. K. Harris, E. D. Becker, S. M. Cabral De Menezes, R. Goodfellow, and P. Granger, NMR nomenclature: Nuclear spin properties and conventions for chemical shifts (IUPAC recommendations 2001), *Concepts in Magnetic Resonance* **14**, 326 (2002).
- [38] M. Syperek, D. R. Yakovlev, I. A. Yugova, J. Misiewicz, I. V. Sedova, S. V. Sorokin, A. A. Toropov, S. V. Ivanov, and M. Bayer, Long-lived electron spin coherence in CdSe/Zn(S,Se) self-assembled quantum dots, *Physical Review B* **84**, 085304 (2011), publisher: American Physical Society.
- [39] C. Testelin, F. Bernardot, B. Eble, and M. Chamarro, Hole-spin dephasing time associated with hyperfine interaction in quantum dots, *Phys. Rev. B* **79**, 195440 (2009).
- [40] E. A. Zhukov, A. Greulich, D. R. Yakovlev, K. V. Kavokin, I. A. Yugova, O. A. Yugov, D. Suter, G. Karczewski, T. Wojtowicz, J. Kossut, V. V. Petrov, Y. K. Dolgikh, A. Pawlis, and M. Bayer, All-optical nmr in semiconductors provided by resonant cooling of nuclear spins interacting with electrons in the resonant spin amplification regime, *Phys. Rev. B* **90**, 085311 (2014).
- [41] D. Sprinzl, P. Horodyská, N. Tesařová, E. Rozkotová, E. Belas, R. Grill, P. Malý, and P. Němec, Influence of  $n$ -type doping on electron spin dephasing in cdte, *Phys. Rev. B* **82**, 153201 (2010).
- [42] A. Nolle, Direct and indirect dipole-dipole coupling between <sup>111</sup>Cd, <sup>113</sup>Cd and <sup>125</sup>Te in solid CdTe, *Zeitschrift für Physik B Condensed Matter* **34**, 175 (1979).
- [43] M. Vladimirova, D. Scalbert, M. S. Kuznetsova, and K. V. Kavokin, Electron-induced nuclear magnetic ordering in  $n$ -type semiconductors, *Phys. Rev. B* **103**, 205207 (2021).
- [44] M. Vladimirova, S. Cronenberger, D. Scalbert, M. Kotur, R. I. Dzhioev, I. I. Ryzhov, G. G. Kozlov, V. S. Zapasskii, A. Lemaitre, and K. V. Kavokin, Nuclear spin relaxation in  $n$ -GaAs: From insulating to metallic regime, *Phys. Rev. B* **95**, 125312 (2017).
- [45] M. Kotur, R. Dzhioev, K. Kavokin, V. L. Korenev, B. Namozov, P. Pak, and Y. G. Kusrayev, Nuclear spin relaxation mediated by Fermi-edge electrons in  $n$ -type GaAs, *JETP letters* **99**, 37 (2014).
- [46] L. Tracy, I. Spielman, J. Eisenstein, L. Pfeiffer, and K. West, Korringa-like nuclear spin-lattice relaxation in a 2DES at  $\nu=1/2$ , *Physica E: Low-dimensional Systems and Nanostructures* **34**, 220 (2006).
- [47] E. Evers, T. Kazimierzczuk, F. Mertens, D. R. Yakovlev, G. Karczewski, T. Wojtowicz, J. Kossut, M. Bayer, and A. Greulich, Nuclear spin dynamics influenced and detected by electron spin polarization in CdTe/(Cd,Mg)Te quantum wells, *Phys. Rev. B* **99**, 045303 (2019).
- [48] A. Berg, M. Dobers, R. R. Gerhardtts, and K. v. Klitzing, Magnetoquantum oscillations of the nuclear-spin-lattice relaxation near a two-dimensional electron gas, *Phys. Rev. Lett.* **64**, 2563 (1990).
- [49] I. J. H. Leung and C. A. Michal, Optical enhancement of NMR signals in CdTe, *Phys. Rev. B* **70**, 035213 (2004).
- [50] D. Paget, G. Lampel, B. Sapoval, and V. I. Safarov, Low field electron-nuclear spin coupling in gallium arsenide under optical pumping conditions, *Phys. Rev. B* **15**, 5780 (1977).
- [51] A. Abragam, *The Principles of Nuclear Magnetism* (Oxford University Press, Oxford, UK, 1961).