



# Électrode à oxygène de type $\text{La}_2\text{NiO}_4+\delta$ pour électrolyseur de la vapeur d'eau à haute température (EHT)

Fabrice Mauvy, Jean-Claude Grenier, Julien Vulliet, Jean-Marc. Bassat, Aline Rougier

## ► To cite this version:

Fabrice Mauvy, Jean-Claude Grenier, Julien Vulliet, Jean-Marc. Bassat, Aline Rougier. Électrode à oxygène de type  $\text{La}_2\text{NiO}_4+\delta$  pour électrolyseur de la vapeur d'eau à haute température (EHT). 2ème Réunion Plénières de la Fédération FRH2, Fédération FRH2, May 2022, Aussois, France. hal-04590136

HAL Id: hal-04590136

<https://hal.science/hal-04590136v1>

Submitted on 28 May 2024

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# **Electrode à oxygène de type $\text{La}_2\text{NiO}_{4+\delta}$ pour électrolyseur de la vapeur d'eau à haute température (EHT)**

**Fabrice Mauvy<sup>1</sup>, Jean-Claude Grenier<sup>1</sup>, Julien Vulliet<sup>2</sup> Jean-Marc Bassat<sup>1</sup>, Aline Rougier<sup>1</sup>**

<sup>1</sup>*CNRS, Université de Bordeaux, Bx INP, ICMCB-UMR 5026, F-33600 Pessac, France.*

<sup>2</sup>*CEA, DAM, Le Ripault, F-37260 MONTS, France*

The present study focuses on an alternative structured oxygen electrode for solid oxide electrolysis cell (SOEC).  $\text{La}_2\text{NiO}_{4+\delta}$  nickelate, LNO, was selected with respect to its mixed electronic and ionic conductivity and its good chemical stability. Complete single cells were built using screen printing of LNO and  $\text{LaNi}_{0.6}\text{Fe}_{0.4}\text{O}_3$  (LNF) layers on a standard hydrogen electrode supported half cell consisting of a porous NiO-YSZ layer, a dense 8YSZ electrolyte layer and a thin interlayer of GDC. The polarization curves of LNO cells under various anodic flows of  $\text{H}_2\text{O}/\text{H}_2$  (90/10) show excellent performances compared to the commercial LSCF ( $\text{La}_{0.6}\text{Sr}_{0.4}\text{Co}_{0.2}\text{Fe}_{0.8}\text{O}_{3-\delta}$ ) based cells. The steam conversion ratio SC increases from around 40 % to 80 % when the gas flow decreases from 36 to 12 NmL/min/cm<sup>2</sup>. With a degradation rate of 1.5 %/1000 h after 500 h operating time ( $i = -0.5 \text{ A/cm}^2$ ), at 800 °C, using a medium gas flow of  $\text{H}_2\text{O}/\text{H}_2$  (90/10) of 24 NmL/min/cm<sup>2</sup>, LNO oxygen electrode shows higher durability than the state of the art LSCF oxygen electrode (4 %/1000 hrs). Energy efficiency analysis confirms the dependency of the total efficiency with the current density and gas flow allowing us to suggest optimized conditions for reaching targets of commercial H<sub>2</sub> production.

[1] «  $\text{La}_2\text{NiO}_{4+\delta}$  as efficient oxygen electrode for Solid Oxide Electrolysis Cell », F.Mauvy, J-C Grenier, J.Vulliet, J-M Bassat, A. Rougier, Fuel Cell, 22 (2022) 48-56 <https://doi.org/10.1002/fuce.202200013>