

Femtosecond inscription of type-a volume Bragg Gratings in silver-containing phosphate glasses

Joelle Harb, Lauris Talbot, Yannick Petit, Martin Bernier, Lionel Canioni

▶ To cite this version:

Joelle Harb, Lauris Talbot, Yannick Petit, Martin Bernier, Lionel Canioni. Femtosecond inscription of type-a volume Bragg Gratings in silver-containing phosphate glasses. 2023 Conference on Lasers and Electro-Optics Europe & European Quantum Electronics Conference (CLEO/Europe-EQEC), European Physical Society; Optica - Advancing Optics and Photonics Worldwide; IEEE Photonics Society, Jun 2023, Munich, Germany. pp.1-1, 10.1109/CLEO/Europe-EQEC57999.2023.10232355. hal-04596643

HAL Id: hal-04596643 https://hal.science/hal-04596643v1

Submitted on 9 Oct 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers. L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

Femtosecond inscription of *Type-A* Volume Bragg Gratings in silvercontaining phosphate glasses

Joelle Harb¹, Lauris Talbot², Yannick Petit^{1,3}, Martin Bernier², Lionel Canioni¹

¹University of Bordeaux, CNRS, CEA, CELIA, UMR 5107, 351 Cours de la Libération, 33405 Talence, Cedex, France.
²Centre d'Optique, Photonique et Laser (COPL), Université Laval, Québec City, Québec G1V0A6, Canada
³University of Bordeaux, CNRS, ICMCB, UMR 5026, 87 avenue du Dr. A. Schweitzer, 33608 Pessac, Cedex, France.

Volume Bragg gratings (VBGs) have gained growing interest over the last decades for diverse applications. Typically, they are produced in photo-thermo-refractive glasses using UV light [1]. Later, femtosecond (fs) laser pulses were used to produce refractive-index modifications (Δ n), mainly type-1, in various other materials [2]. To obtain more freedom in designing optical systems, it is desirable to inscribe VBGs in glasses exhibiting a much higher Δ n, such as silver-containing phosphate glasses. Indeed, a novel type of Δ n has been demonstrated in such glasses, denominated *Type-A* (*A* from *Argentum*), which is related to the spatial distribution of the photo-induced silver clusters around the interaction voxel and exhibits two positive Δ n peaks at each laser pass [3], reaching a value of up to 2×10^{-2} [4]. Recently, we demonstrated the first *Type-A* VBGs inscribed in silver-containing phosphate glasses with a Gaussian-Bessel beam. The most efficient grating was recorded in ~1 hour at a velocity of 20 µm/s for a transverse area of 400×400 µm². Indeed, there is a growing interest in writing high throughput VBGs suitable for industrial manufacturing.

For this reason, we report here the inscription of VBGs using a laser light-sheet to accelerate the recording time. The sample is a commercial silver-containing zinc-phosphate glass (AG01®, Argolight). A 1030-nm laser emitting pulses of 507 fs and a maximum output power of 100 W was used in burst mode, i.e., 10 pulses spaced 30 ns apart at a repetition rate of 200 kHz. The beam is focused into the glass sample by a cylindrical lens (f = 5*cm*) in one direction, generating a light-sheet of 900x4.3x449.7 μ m³. When propagating from air to glass, refraction extended the beam to a length of 1.43 mm in the glass material. Thus, we inscribe a VBG with only a single layer, with a periodicity of 7.5 µm corresponding to a writing process achieved within 33 mins for 500 µm of transverse length. Fig. 1(a) shows the fluorescence image of the inscribed VBG using the light sheet, where the periodic modification is composed of silver clusters. In addition to the recording time, a second method was used to overcome the period stability constraints that may affect the inscription process in general [5]. This convenient and widely used method is based on the use of a phase mask approach, generating an interference pattern with half of its periodicity. For this method, we apply ultrashort laser pulses (30 fs) and a low repetition rate (1 kHz). An 800 nm beam is focused by a cylindrical mirror (f = 40 cm) through the phase mask (period = 14 µm) into the glass sample. An 800x0.25 mm² grating was inscribed at 130 mW after the cylindrical lens and for a velocity of 4.1 µm/s, corresponding to a one-minute inscription process. Fig. 1(b) reports a fluorescent image of the VBG showing the periodic modification corresponding to the half-periodicity of the phase mask. Indeed, using this low repetition rate laser, we generated mostly non-stable species (namely hole traps silver species) in addition to a small amount of stable silver clusters. The diffraction efficiency in transmission at 632.8 nm wavelength was measured for both VBGs at the Bragg condition, indicating a promising result.



Fig. 1: Microscopy fluorescence image (excitation at 365nm) of (a) VBG inscribed using the light-sheet (DLW parameters: laser power = 96 W); (b) VBG induced with the phase mask technique (DLW parameters: laser power = 130 mW, velocity = 4.1μ m/s).

In summary, we demonstrated the possibility to access experimental high-throughput inscription of *Type-A* based periodic structures in silver-containing phosphate glasses using the phase mask technique. A higher repetition rate laser is needed to promote a more efficient creation of silver clusters to obtain hereby higher diffraction efficiencies. Further optimizations are required to demonstrate higher efficiencies with *Type-A* refractive index modifications using the light-sheet method.

References

[1] L. Siiman, et al., Non-collinear generation of third harmonic of IR ultrashort laser pulses by PTR glass volume Bragg gratings Opt. Lett, **34**,17 (2009).

[2] K.Yamada, et al., Volume Grating induced by a self-trapped long filament of femtosecond laser pulses in silica glass, Jpn. J. Appl. Phys. 42 6916 (2003)

[3] A. Abou Khalil et al., Direct laser writing of a new type of waveguides in silver containing glasses, Scientific reports, 7, 1 (2017)

[4] L. Loi, et al, High refractive index change in Type A laser modification using a multi-scan approach, Opt. Mater. Express, 12, 6 (2022)

[5] L. Talbot, et al., Femtosecond-written volume Bragg gratings in fluoride glasses, Opt Lett, 45, 13 (2020)