



Impact of initial surface passivation on wetting properties analysis during III-V/Si epitaxy

Sreejith Pallikkara Chandrasekharan, Divishth Gutpa, C. Cornet, Laurent Pedesseau

► To cite this version:

Sreejith Pallikkara Chandrasekharan, Divishth Gutpa, C. Cornet, Laurent Pedesseau. Impact of initial surface passivation on wetting properties analysis during III-V/Si epitaxy. E-MRS 2024 Spring meeting, May 2024, Strasbourg, France. hal-04597986

HAL Id: hal-04597986

<https://hal.science/hal-04597986>

Submitted on 3 Jun 2024

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.


Impact of initial surface passivation on wetting properties analysis during III-V/Si epitaxy

S. Pallikkara Chandrasekharan^{1,*}, D. Gupta¹, C. Cornet¹, L. Pedesseau¹


(1) Univ Rennes, INSA Rennes, CNRS, Institut FOTON-UMR 6082, F-35000, Rennes, France.

Introduction


Molecular beam epitaxy



Experimental observations



Objectives



- Highly reactive Si surface (high surface energy)
- Passivation of Si (intentional or not) stabilizes the surface and promotes 3D growth

Lucci et al., Phys. Rev. Materials 2, 060401(R) (2018). FOTON Inst.


Initial coverage of Si by group-V, -III, H or other atoms
A. Dupré, Théorie Mécanique de la Chaleur (Gauthier-Villars, Paris, 1869)

Spreading parameter (solid wetting theory)...


$$\Omega = \gamma^S_{(Si:X)} - \gamma^S_{(III-V)} - \gamma^i_{(III-V/Si)}$$

$\Omega > 0$, complete wetting
 $\Omega < 0$, partial wetting


Absolute surface energies




Surface and interface energies vs chemical potentials for GaP/Si



Absolute interface energies




Wetting properties



Young-Dupré spreading parameter Ω

- Passivation promotes partial wetting conditions.

*Pallikkara Chandrasekharan, et al. Physical Review B 109.4 (2024): 045304. FOTON Inst.




"Illustration summarizing the energies involved in the 3D island formation of GaP on the Si substrate with a range of possible energy values"

- Stable surface and interface energies support the growth of 3D islands.


*Pallikkara Chandrasekharan, et al. Physical Review B 109.4 (2024): 045304. FOTON Inst.

Initial surface passivation



*Lucci et al., Phys. Rev. Materials 2, 060401(R) (2018). FOTON Inst.

Proposed III-V/Si growth steps



Conclusions

- ↳ Inevitable passivation of Si prior to GaP/Si heteroepitaxy leads to a large decrease of the substrate surface energy.
- ↳ This decrease leads to a significant reduction in the spreading parameter.
- ↳ Destabilizing a passivated Si surface by at least 15 meV/Å² or stabilizing the III-V (001) surface makes a complete wetting situation possible.
- ↳ Si passivation is a driving force for the formation of 3D stable islands, which leads to the emergence of structural defects due to their coalescence.

Acknowledgements

This research was supported by the French National Research NUAGES Project (Grant no. ANR-21-CE24-0006). DFT calculations were performed at FOTON Institute, and the work was granted access to the HPC resources of TGCC/CINES under the allocation A0120911434, A0140911434, and A0160911434 made by GENCI.