



**HAL**  
open science

## **Nouvelle génération de réflecteurs à neutrons lents utilisant des nanodiamants purifiés**

K Henry, M Emo, T Gaudisson, V Pischedda, S Le Floch, V Nesvizhevsky, K Zhernenkov, A Bosak, B Vigolo, M Dubois

### ► To cite this version:

K Henry, M Emo, T Gaudisson, V Pischedda, S Le Floch, et al.. Nouvelle génération de réflecteurs à neutrons lents utilisant des nanodiamants purifiés. Séminaire de l'Ecole Doctorale C2MP, Jun 2022, Nancy, France. <hal-04649421>

**HAL Id: hal-04649421**

**<https://hal.science/hal-04649421v1>**

Submitted on 16 Jul 2024

**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.



HAL Authorization

# Nouvelle génération de réflecteurs à neutrons lents utilisant des nanodiamants purifiés

K. HENRY<sup>1</sup>, M. EMO<sup>1</sup>, T. GAUDISSION<sup>2</sup>, V. PISCHEDDA<sup>2</sup>, S. LE FLOCH<sup>2</sup>,  
V. NESVIZHEVSKY<sup>3</sup>, K.ZHERNENKOV<sup>4,5</sup>, A. BOSAK<sup>6</sup>, B. VIGOLO<sup>1</sup>, M. DUBOIS<sup>7</sup>

**1** Université de Lorraine, Institut Jean Lamour, UMR 7198, allée André Guinier 545000 Nancy, France

**2** Université Claude Bernard - Lyon 1, Institut Lumière matière, UMR5306 10 rue Ada Byron 69622 Villeurbanne, France

**3** Institut Max von Laue – Paul Langevin, 71 av. des Martyrs, F-38042 Grenoble, France

**4** Joint Institute for Nuclear Research, 6 Joliot Curie, Ru-141980 Dubna, Russia

**5** JCNS at Heinz Maier-Leibnitz Zentrum (MLZ), Forschungszentrum Julich GmbH, 1 Lichtenbergstrasse, Garching G-85748, Germany

**6** European Synchrotron Radiation Facility, 71 av. des Martyrs, F-38042 Grenoble, France

**7** Université Clermont Auvergne, CNRS, ICCF UMR 6296, 24 av. Blaise Pascal, F-63178 Aubière, France

Advances in neutronics are of great importance in fundamental science in many fields, from biology to physics. Slow neutrons (SN) are highly interesting to probe material since they are the only neutron type allowing the diffraction phenomenon. However, today most efficient SN reflectors are limited in the range of useful neutrons. This is mainly due to the nature of neutron reflectors, as they are composed of atoms generally spaced of  $\sim 1$  Å, as soon as the neutron wavelength reaches this value the neutrons are almost no longer diffracted. The key to increasing the efficiency of the SN flux therefore lies in the development of efficient reflectors.

Our strategy is to mimic standard reflectors and replace the atoms by nanoparticles of highly scattering materials with low absorption: detonation nanodiamonds (DNDs) and fluorine graphite intercalation compounds (F-GIC). This new class of reflectors will provide a virtually continuous reflectivity curve, with a high albedo minimizing the so-called neutron reflectivity gap.

DNDs are available in an industrial scale and extremely stable under neutron fluxes. However, they contain some impurities that are unfavourable for neutron applications because of their high neutron absorption (e.g. hydrogen,  $sp^2$  C, surface functional groups or metallic impurities). Thus, ultrapure DNDs are highly required for this application.

Our approach to selectively purify DNDs is based on a combination of gas phase purification treatments: chlorination and fluorination. They will respectively remove the metallic impurities and eliminate the surface functional groups and  $sp^2$  C shell. Fluorination will allow the increase of the interplanar distance between graphite layers.

In addition, the design of a unique neutron experimental set-up at the PF1B line at the ILL aims to record simultaneously reflectivity and diffraction of neutrons with a wide range of wavelengths, including slow and very slow neutrons. Data on various powdered DNDs and F-GICs were recorded as well on the precursors before fluorination.