




Production, storage and conversion of hydrogen into electricity: technological achievements and remaining challenges

Annie LE GAL LA SALLE, Clément NICOLLET, Eric QUAREZ, Olivier JOUBERT



Institut des Matériaux de Nantes
Jean Rouxel - France
Electrochemical Storage and
Conversion of Energy group:
Fuel cells & Electrolyzers team



Outline

Challenges...

Introduction:
Fuel cells and electrolyzers

Conversion


Storage

Production


Recycling

Conclusion


Outline




What is a fuel cell? An electrolyser?





What is a fuel cell? An electrolyser?



What about the cell?




Different types...



... depending on electrolyte:
- Ion transported...
- Temperature allowing conductivity...

Hydrogen... associated to renewable energies




Stationary applications



Applications
in « heavy »
mobility:
ships, trains,
trucks...

Heavy mobility...



ALSTOM CORADIA iLINT
(Germany)

Reaching carbon-free autonomy of isolated territories

Pass « Le Palet » : Refuge powered by solar electricity...



- wasted during a part of the year for lack of means to store it
- completed by a diesel or gasoline generator during other parts of the year (numerous visitors)

*In 2015, electrolyzers,
 H_2 storage, FCs (+ batteries)*

Total autonomy of the building,
with better comfort for visitors
(charge of electronic devices!)

(1-30 MWh/y, -30→30°C)




- Financial support from FEDER,
- 5 companies: Gest'Hydrogène, Gest'Performance, MaHyTec, Powidian, WaechterÉnergies.

Carbon-free autonomy of isolated territories




La Nouvelle at La Réunion:
(excluded from the electrical grid and
the road network: foot path or
helicopter!)



In 2016, micro-grid with batteries,
electrolysers, H₂ storage, FCs*

→ Total autonomy of some buildings
(school, health center, ONF, ...)



*European Regional Development Fund (ERDF)
... EDF and SIDELEC for local distribution




Carbon-free autonomy of isolated territories



Coupling with wind farms...

Mainz Energie Park (Germany)



Domestic
cogeneration
heat/electricity



To develop hydrogen uses... simultaneously...




**Hydrogen
production**
(electrolyzers)



**Hydrogen
storage**



**Hydrogen
conversion**
(FC)



Hydrogen issues adressed all around the world...

→ in France, one program:



The French Research
network on Hydrogen energy




Organization: 30 laboratories, 300 permanent CNRS researchers and lecturers (70%), 4000 publications (2014-2019) 4 start-ups from CNRS



Aim: synergy between complementary skills:
Materials, Processes, Components, Systems...




Outline




1. Hydrogen production...

Today, 95% of hydrogen
is issued from fossil
sources (grey H₂)...
... and green H₂ expensive



Need for **clean**
production of (green) H₂
at **low cost**




1. Green hydrogen production (electrolysis)

Currently:


- low temperature technologies are mature
 - ... but costly catalysts (platinum ou PGM)
- Technologies without PGM, but low yields
- **High Temperature Electrolysis*** :
- higher yields... without PGM

*Technological
improvements
at the cell scale*



*L. Ye et al., High-temperature electrocatalysis and key materials in solid oxide electrolysis cells, *J. Energy Chem.*, 2021

1. HTE cells





Ageing of the cell:
redox reactions
→ segregation (porosity),
diffusion, delamination,...

Today, electrode-supported cells

- **High performance $\geq 1\text{A}/\text{cm}^2$ à 1,3V**
- Weak durability: loss of 2 to 5%/1000h
at 1.3V and 0.5 à 0,6 A/cm^2



1. In order to increase the durability of the HTE cells...



PC CELCER-HT, *F. Lefebvre-Joud et coll.*



1. Improvement of current materials

Morphology (nanomaterials), barrier layers, shaping...

2024 :

Cells degradation rate :

- 1%/1000h at 1.3V and 0.85 A/cm^2
- on cells of 200 cm^2

Cells robustness :

- Low temperature starting time = 8h
- High temperature starting time = 300s

2. New materials

Composition (modelling, calculations...)

2026-2027 :


Cells degradation rate :

0,7%/1000h at 1,3V and 1 A/cm^2

1. IMN's involvement in CELCER project ...


New materials for H₂ electrode: 1. New Ce & Ni-based materials: Ni exsolution
(homogeneous distribution)

- Previous studies: Ni-introduction limited to 15%: Ce_{0.85}Ni_{0.15}O_{2-δ}*
- Ce_{0.95}Ni_{0.05}O_{2-δ} prepared at IMN**:



→ No crystallized secondary phase
→ Ni exsolution

1. IMN's involvement in CELCER project



New materials for H₂ electrode: 2. Use of Metal–organic frameworks (MOFs):

Porous Zirconium Terephthalate UiO-66

- ❖ MOFs : porous and tunable materials composed by organic structures and inorganic nodes¹.
- ❖ High porosity after burning the organics ².
- ❖ Easy synthesis of Zr-based MOFs ³.
- ❖ Possible doping of Zr-based MOF with Yttrium ⁴.
- ❖ Possible infiltration (due to their high porosity) ⁵.




Next step: Addition of NiO?

1. F. Ragon et al. Inorg. Chem. 53 (2014), 2491 – 2500.
2. R. Quin et al. Adv. Funct. Mater. 29 (2019), 1903264.
3. M.J. Katz et al. Chem Commun., 49 (2013), 9449.
4. Z. Yue et al. RSC Adv. 5 (2015), 10619.
5. R. Lippi et al. J. Mater. Chem. A 5 (2017), 12990.

1. Versatile High temperature electrolyzers: fuel electrode


Adaptation of classical fuel electrode material for CO₂/H₂O electrolysis:





... and also seawater electrolysis...

1. Another route to improve HTE...

Anionic conductor based cells



Protonic conductor based cells




→ Production of non diluted hydrogen


→ Protonic conduction efficient at lower temperature (lifetime)

1. Versatility of the PC-HTE


@ 600°C



H₂O Electrolysis




CO₂ Electrolysis




NH₃ Synthesis

1. How to improve PC-HTE



1. How to improve CP-HTE: electrolyte synthesis at IMN






Electro-catalytic activity,,
chemical stability,
architecture optimisation



Chemical stability, optimized conductivity

1. $\text{BaCe}_{0.8}\text{Zr}_{0.1}\text{Y}_{0.1}\text{O}_{3-\delta}$ by Cold Sintering*

*Z. Zhao , J. Gao, Y. Meng, K. Brinkman, J. Tong, *Ceramics Int.* 2021




Cold sintering

Conventional sintering

1. How to improve CP-HTE: electrolyte synthesis at IMN*

2. Another compound: $\text{BaCe}_{0.2}\text{Zr}_{0.7}\text{Y}_{0.1}\text{O}_{3-\delta}$ ** (CO₂/H₂O electrolysis)




Cold-sintering process at
180°C before sintering

CSP with the addition of
sintering aid

* P. Castellani thesis

** S. M. Babiniec et al., *Int. J. Hydrogen Energy*, 2015

(↑ stability, ↓sinterability)



Grain density values calculated by ImageJ from SEM images cross section:

Sintering protocol	Conventional	CSP	ZnO-Li	CSP + ZnO-Li
Grain count (grain)	50	86	6	74
Count Area (μm^2)	4.5	26.1	26.7	26.5
Grain Density (grain. μm^{-2})	11	3.3	0.2	2.8


1. How to improve CP-HTE: synthesis of air electrode

Air electrode suited to electrolyte

$\text{Ba}_{0.5}\text{Sr}_{0.5}\text{Co}_{0.8}\text{Fe}_{0.2}\text{O}_{3-\delta}$
• Commercial powder (Mariontech)

$\text{BaZr}_{0.7}\text{Ce}_{0.2}\text{Y}_{0.1}\text{O}_{3-\delta}$

- Preparation of two Inks for screen printing:
(powder + 95 wt% alpha terpineol (solvent) + 5 wt% ethyl-cellulose (binder))
- Single phase ink synthesis: $\text{Ba}_{0.5}\text{Sr}_{0.5}\text{Co}_{0.8}\text{Fe}_{0.2}\text{O}_{3-\delta}$
- Composite ink synthesis : $\text{Ba}_{0.5}\text{Sr}_{0.5}\text{Co}_{0.8}\text{Fe}_{0.2}\text{O}_{3-\delta}$ +
 $\text{BaZr}_{0.7}\text{Ce}_{0.2}\text{Y}_{0.1}\text{O}_{3-\delta}$
- Screen printing on a $\text{BaZr}_{0.7}\text{Ce}_{0.2}\text{Y}_{0.1}\text{O}_{3-\delta}$ dense electrolyte
- 4 layers (3 Composite + BSCF) + drying at 120°C+ treatment of the cell at 750°C for 6h




SEM images of the cathode

a) Porous structure of the air electrode
b) Homogeneous morphology of the electrode layer

Complete cells...

1. How to improve CP-HTE: new designs



Electro-catalytic activity,
chemical stability,
architecture optimisation



Chemical stability, optimized conductivity

3. New cells designs: metal supported cells:




French-German ANR project "ARCADE" (2020-2023)

1 PhD (2020-23) – P. Castellani


Metal-supported SOEC cell based on $\text{BaCe}_x\text{Zr}_{1-x-y}\text{Y}_y\text{O}_{3-\delta}$ (BCZY)

Mechanical strength
assumed by the metallic
interconnect

Reduction of the amount of
active materials



Outline



2. Another challenge: H₂ storage!



2g/mol

Light... BUT






0.09 kg/m³

Voluminous!



<http://www.imageproduction.nl>


2. H₂ storage: existing solutions ...



2. Solid storage:

- compact, energy-efficient
- contributes to hydrogen social acceptability: safe, without pressure

2. Solid storage: current research ...



PC SOLHYD, *F. Cuevas et coll.*



...highly efficient...

Materials

Metal hydrides
(Mg_2FeH_6 , 150 kg H₂/m³)

Regenerable hydrides
intermetallic: AB₅ (LaNi₅...), AB₂
(ZrV₂), A₂B (Mg₂Ni)...

Complex Hydrides are adsorption
materials (LiBH₄ (18%), but
200000 atm!)

*...costly, energy
consuming...*

Slow desorption
→ Improvement
of regeneration
processes

Development of
new compositions,
new materials

Improvement of synthesis
and regeneration
processes




Nantes
Université

IMN
INSTITUT DES MÉTÉRIAUX
DE NANTES JEAN ROUXEL

2. Hyperbaric storage : remaining challenges

- ✓ Increasing its level of safety and confidence → better societal acceptability
- ✓ Reducing the carbon footprint of tanks (with life cycle analysis)

2. Hyperbaric storage : remaining challenges



PC HYPERSTOCK, *D. Chapelle et coll.*




MAIN STUDIES:

- embrittlement of the different materials (metallic and non-metallic) with H_2 ,
- responses to mechanical stresses

Security,
Trust,
Acceptability



Carbon footprint

Outline




3. Low temperature fuel cells: remaining objectives

2. Decrease of the amount of catalyst (nanomaterials)



1. System: temperature (H_2O) management




3. New materials, to increase activity, stability, robustness (impurities, stop and start,...) *

* (> 25000h)


H. Su et al., A review of low temperature proton exchange membrane fuel cell degradation caused by repeated freezing start, *Int. J. Hydrogen Energy*, 2022

P.H. Affonso Nobrega et al., A review of physics-based low-temperature proton-exchange membrane fuel cell models for system-level water and thermal management studies, *J. Power Sources*, 2023

3. Low temperature fuel cells: remaining objectives



3. High temperature fuel cells




With these devices,

- High yields without costly catalysts
- Possible to use other fuels, such as various gaseous or liquid mixtures issued from biomass...
(≠ LTFC)

... Same materials as HTE, but:

- Increase their robustness towards pollutants present in different fuels

3. High temperature fuel cells



With these devices,

- High yields without costly catalysts
- Possible to use other fuels, such as various gaseous or liquid mixtures issued from biomass...

(≠ LTFC)

... Same materials as HTE, but:


- Increase their robustness towards pollutants present in different fuels

To further increase their versatility:

- Use wet, marine, polluted air
- Decrease T

3. Versatile high temperature fuel cells

Development of
convenient
materials



Precise objectives on fuel side:


- ✓ Carbon formation $< 0,5 \text{ mg}_{\text{carbone}} \text{ g}_{\text{cat}}^{-1} \text{ h}^{-1}$ à 600°C
- ✓ H_2S tolerance between 3 and 5 ppm

PC FLEXISOC, A. Le Gal La Salle et coll.



3. Versatile high temperature fuel cells

Development of
convenient
materials



After:

Materials and
cells shaping:



Tests and
optimisation,
modélisations

- ✓ Power density (without reforming)
of 1 W/cm² at 600°C

Precise objectives on fuel side:


- ✓ Carbon formation < 0,5 mg_{carbone} g_{cat}⁻¹ h⁻¹ à 600°C
- ✓ H₂S tolerance between 3 and 5 ppm

PC FLEXISOC, A. Le Gal La Salle et coll.





3. Versatile high temperature fuel cells

Development of
convenient
materials



Materials and
cells shaping:

In situ exsolution of Ni particles from $Pr_{0.65}Ba_{0.35}Mn_{0.975}Ni_{0.025}O_3$




M. Bahout et al. J. Mater. Chem. A, 2020, 8, 3590–7

Precise objectives for fuel electrodes:


- ✓ Carbon formation < 0,5 mg_{carbone} g_{cat}⁻¹ h⁻¹ à 600°C
- ✓ H₂S tolerance between 3 and 5 ppm
- ✓ Power density (without reforming) of 1 W/cm² at 600°C

3. Versatile high temperature fuel cells

Dévelopment of
convenient
materials



Materials and
cells shaping:




F. Ricoul et al. J. Solid St. Electrohem. 2018, 22, 2789–800

Precise objectives for fuel side electrodes :

- ✓ Carbon formation < 0,5 mg_{carbone} g_{cat}⁻¹ h⁻¹ à 600°C
- ✓ H₂S tolerance between 3 and 5 ppm
- ✓ Power density (without reforming) of 1 W/cm² at 600°C

3. Versatile high temperature fuel cells

Dévelopment of
convenient
materials



Materials and
cells shaping:

Tests and
optimisation,
modélisations


Precise objectives on the fuel side

... But also on the air side:

- ✓ Carbon formation < 0,5 mg_{carbone} g_{cat}⁻¹ h⁻¹ à 600°C
- ✓ H₂S tolerance between 3 and 5 ppm
- ✓ Power density (without reforming) of 1 W/cm² at 600°C


Increase of tolerance towards
air impurities (NO_x)

Outline



Recycling... Why?

Aim:
Recycling and re-use of oxides entering the composition of commercial cells



Ni- $Zr_{1-x}Y_xO_{2-x/2}$ (Ni-YSZ)

$Zr_{1-x}Y_xO_{2-x/2}$ (YSZ)


$La_xSr_{1-x}CoO_3$

Interest: 1MW electrolysis*:

1136 kg
Ni


411 kg
 $Y_xZr_{1-x}O_{2-\delta}$

PhD, 80IPRIME CNRS program : 1st route



PhD, 80|PRIME CNRS program : 2nd route

Broken cells???
→ Grinding of the entire cell





More complex route
→ One additional step

European project NOUVEAU (2022-2025)




NOVEL ELECTRODE COATINGS AND INTERCONNECT FOR SUSTAINABLE AND REUSABLE SOLID OXIDE ELECTROLYSIS CELLS


EU Grants: Application form (HE RIA/IA): V1.2 – 25.05.2021




European project NOUVEAU (2022-2025)



European project NOUVEAU (2022-2025)



Outline



Conclusion

Hydrogen sector to be developed (with other storage technologies) in order to limit CO₂ emissions and global warming

- Technical limitations to overcome for fuel cells/electrolysers :
 - ↗ Durability : Targets: 40 000 h to 60 000h (stationary, HT systems)
5 000h (transport)
+ robustness (temperature, ...)
 - ↗ Versatility : Increase tolerance to pollutants to use industrial H₂ or coming from biomass
 - ↘ Costs : use of rare and expensive materials (Pt)
- Technical limitations *for the whole sector (FC/Electrolysers/Storage)*
 - ↘ Environmental impact of the synthesis and use, Life Cycle Analysis

To conclude... evolution of our research topics...

New materials:
electrolyte, electrodes
Synthesis → Recycling

Cell Shaping: New
and/or optimized
methods

Diagnosis by EIS: Application to materials
and complete cells

... non-toxic and cheap
reagents, and involving less
energy consuming reactions

... Recyclable
materials

Enlarging cell operating conditions, other fuels,
and other conditions of electrolysis
(seawater electrolysis, marine atmosphere,...)



...recyclable cells

Outlooks

Besides technical objectives:

- Enlarge H₂ infrastructures deployment
- Create and harmonize hydrogen regulations between countries

... depends on political wills...



- Chile : 2028?
- Germany: 2032?
- US (some states) 2034?


And finally...

A lot of technical exciting challenges

But none technical solution will prevent our earth to be limited...



We need a real
energy saving policy
all around the world!







Acknowledgments



ARCADE



OPHARM



MODTESTER

NOUVEAU



ARCADE



FLEXISOC



CELCER-HT

PROTEC




Acknowledgments



Olivier JOUBERT (Prof Polytech),
Clément NICOLLET, Eric QUAREZ,
Annie LE GAL LA SALLE
(CNRS Researchers)

PhD students:

Alexandre MERIEAU
Pablo CASTELLANI
Valentin BRARD
Simon GUILLONEAU
Lozane HAMSE



Post-Doc:

Insaf ABDOULI
Stefan HENFLING
Gudaysew T. YENESEW
Victor ZAPATA RAMIREZ

Thanks for your attention!
annie.legal@cnrs-imn.fr