



HAL
open science

The role of sputtered atom and ion energy distribution in films deposited by Physical Vapor Deposition: A molecular dynamics approach

Soumya Atmane, Alexandre Maroussiak, Amaël Caillard, Anne-Lise Thomann, Movaffaq Kateb, Jón Tómas Gudmundsson, Pascal Brault

► To cite this version:

Soumya Atmane, Alexandre Maroussiak, Amaël Caillard, Anne-Lise Thomann, Movaffaq Kateb, et al.. The role of sputtered atom and ion energy distribution in films deposited by Physical Vapor Deposition: A molecular dynamics approach. *Journal of Vacuum Science & Technology A*, 2024, 42 (6), pp.060401. 10.1116/6.0004134 . hal-04683463v2

HAL Id: hal-04683463

<https://hal.science/hal-04683463v2>

Submitted on 13 Nov 2024 (v2), last revised 18 Nov 2024 (v3)

HAL is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

The role of sputtered atom and ion energy distribution in films deposited by Physical Vapor Deposition: A molecular dynamics approach

Soumya Atmane,¹ Alexandre Maroussiak,¹ Amaël Caillard,¹ Anne-Lise Thomann,¹ Movaffaq Kateb,² Jon Tomas Gudmundsson,^{3,4} and Pascal Brault^{1,5}

¹*GREMI, UMR7344 CNRS Université d'Orléans, Orléans, France*

²*Condensed Matter and Materials Theory,*

Department of Physics, Chalmers University, Sweden

³*Science Institute, University of Iceland,*

Dunhaga 3, IS-107 Reykjavik, Iceland

⁴*Division of Space and Plasma Physics,*

School of Electrical Engineering and Computer Science,

KTH Royal Institute of Technology, SE-10044 Stockholm, Sweden

⁵*MS4ALL, Lab'O Village by CA, Orléans, France**

(Dated: November 7, 2024)

Abstract

We present a comparative molecular dynamics simulation study of copper film growth between various physical vapor deposition (PVD) techniques: a constant energy neutral beam, thermal evaporation, dc magnetron sputtering, high-power impulse magnetron sputtering (HiPIMS), and bipolar HiPIMS. Experimentally determined energy distribution functions were utilized to model the deposition processes. Our results indicate significant differences in the film quality, growth rate, and substrate erosion. Bipolar HiPIMS shows the potential for improved film structure under certain conditions, albeit with increased substrate erosion. Bipolar +180 V HiPIMS with 10% Cu⁺ ions exhibited the best film properties in terms of crystallinity and atomic stress among the PVD processes investigated.

*Electronic address: corresponding author: pascal.brault@univ-orleans.fr; pascal.brault@ms4all.eu

I. INTRODUCTION

Molecular dynamics (MD) simulation is a simulation technique well suited for describing thin film or nanoparticle growth phenomena [1–4]. Here, MD simulations are applied to compare the growth of thin copper (Cu) films using various physical vapor deposition (PVD) techniques [5]. The deposition systems assumed in the present work, include a constant energy neutral beam, thermal evaporation, dc magnetron sputtering (dcMS), high power impulse magnetron sputtering (HiPIMS), and bipolar HiPIMS [5, 6]. In neutral beam, thermal evaporation, and dcMS depositions the film forming species are neutral atoms. In HiPIMS operation the magnetron sputtering discharge is driven by high power pulses at low frequency and short duty cycle [6, 7] and the ionized flux fraction of the sputtered species can be high [8], and furthermore the ion energy can be significantly higher than in dcMS operation [9]. In bipolar HiPIMS operation a positive voltage is applied to the target following the negative sputter pulse, which increases the plasma potential and shifts the ion energy distribution (IED) to higher energies [10–13]. Some successful attempts have been made to include the specific characteristics of different magnetron sputtering (MS) deposition techniques into MD simulations, the role of the ionized flux fraction [14], the ion potential energy [15], and the IED shift due to substrate bias [16], which show varying film properties depending on the deposition method. Usually, in MD simulations, this is achieved by setting a mean kinetic energy or sampling from a uniform energy distribution. The earlier studies were based on a uniform IED, while in practice the IED is meant to demonstrate that the probability of certain energies can vary, depending on the deposition method. Here, we further improve the description of the physically released film forming species by using selected initial velocity conditions from experimental data (energy-resolved mass spectrometry) and SRIM simulations [17] for the IED and the atom energy distribution (AED). This choice was motivated by approximating the experimental conditions as closely as possible. Further improvement of the initial conditions is expected to give a step forward for a more realistic MD simulation and, thus a more accurate prediction of sputtered film properties, such as morphology, composition, structure, and tribology.

II. EXPERIMENTAL SETUP AND RESULTS

The reactor used to determine the IED for the magnetron sputtering processes is made up of a central chamber, which is a cylindrical stainless steel enclosure with a diameter of 200 mm. It contained six crossed flanges with an external diameter of 240 mm (ISO-K200). The first flange was connected to a pumping system that ensured a vacuum of approximately 5×10^{-5} Pa using a primary pump (Pfeiffer vacuum, ACP15, 15 m³/h) and a turbo-molecular pump (Pfeiffer vacuum, 500 l/s). The lamination valve placed between the chamber and the turbo-molecular pump made it possible to adjust the working gas pressure inside the enclosure, and the two gauges (a combined pirani/cold cathode gauge and baratron gauge) made it possible to measure this pressure. The magnetron assembly (Angstrom Sciences (ONYX-2)) where the sputtering target (copper) is placed, had a diameter of 2 inches. It was placed facing the EQP1000 300 amu Hiden Analytical mass spectrometer at a distance of 10 cm. A pulsed power module (Starfire Industries), that contains a solid-state switching device, was fed by a Kurt J. Lesker PDX 500 DC generator. This system can be used to power the magnetron sputtering discharge with unipolar pulses (HiPIMS) or bipolar pulses (bipolar-HiPIMS) with a voltage limit of 1000 V. The current-voltage characteristics were observed using a Tektronix oscilloscope. Argon was used as the working gas, set at 0.7 Pa, and the flow rate was regulated at 40 sccm using a Bronkhorst mass flow meter (F-200CV). In the present work, the HiPIMS sputter pulse was 50 μ s long and the negative bias -650 V. In bipolar HiPIMS configuration, the negative pulse was followed by a longer pulse (250 μ s) with a positive bias varying from +20 to +180 V. Figure 1 shows the corresponding experimentally recorded IEDs for Cu⁺ ions measured 10 cm from the Cu target center.

III. MOLECULAR DYNAMICS SIMULATION SETUP

Molecular dynamics simulations allow the calculation of the trajectories of a set of species by solving Newton's equations of motion:

$$m_i \frac{d^2 \vec{r}_i(t)}{dt^2} = \vec{F}_i = -\vec{\nabla} V(\vec{r}_1(t), \vec{r}_2(t), \dots, \vec{r}_N(t)) \quad (1)$$

where $\vec{r}_i(t)$ is the position of atom i at time t with mass m_i , and V is the interaction potential between all N involved species. These equations only require knowledge of two initial




FIG. 1: Experimentally determined copper ion Cu^+ ion energy distributions (IEDs) (semilog scale) in HiPIMS mode (0V) and bipolar HiPIMS for various positive voltages recorded 10 cm away from the target surface.

conditions, positions and velocities for all species at the initial time $t = 0$, and of the interactions between all species at all times. The initial positions refer to the geometry/topology of the particles at the beginning of the simulation, while velocities are (randomly) selected from a velocity distribution that is consistent with the deposition method under study. To examine the effect of the AEDs and IEDs on the deposited films, we considered AISI 3016L stainless-steel substrate (bcc $\text{Fe}_{67}\text{Cr}_{17}\text{Mo}_2\text{Ni}_{14}$, $72 \times 72 \times 46 \text{ \AA}^3$ slab composed of 20000 atoms). The stainless steel substrate is composed of fixed layers, Langevin thermostated layers, and layers free to move as seen in Figure 2, showing the initial simulation box. For a constant energy neutral beam, thermal evaporation, and dcMS 10000 neutral Cu atoms are periodically released towards the surface. In the case of HiPIMS and bipolar HiPIMS, 10000 species composed of 90% Cu + 10% Cu^+ or 50% Cu + 50% Cu^+ were released at a periodic rate from random positions above the surface. Such neutral and ion compositions are chosen for mimicking low and high ion flux towards the substrate. Sets of 10 Cu (or $x\text{Cu} + y\text{Cu}^+$) atoms, randomly located above the surface and sufficiently far from each other, were released every 40 ps. Thus, the total simulation time was 40 ns.

The initial velocities are randomly selected from the corresponding AEDs and IEDs. For thermal evaporation, a Maxwell-Boltzmann distribution at melting temperature is considered; for dcMS, SRIM AED modified by transport through the MS reactor is used [1]. For HiPIMS and bipolar HiPIMS, the kinetic energy of the sputtered ions was selected from




FIG. 2: Simulation box with the stainless steel substrate and the first set of 10 atoms/ions before release towards the surface. Langevin thermostat is used for the thermostated layers. Color code: cyan Cu, yellow Cr, silver Fe, red Mo, and blue Ni.




FIG. 3: Sputtered Cu atom and ion energy distributions (linear scale). — Blue: Thermal Evaporation at 1358 K, - - - black: dcMS SRIM propagated along 10 cm target to substrate path, at 0.7 Pa, - • - purple: HIPIMS Cu^+ , Exp QMS at 10 cm, 0.7 Pa, - • • - red: bipolar HiPIMS (+180 V).

the experimental energy-resolved mass spectra (Figure 3), while that of sputtered neutral Cu was assumed similar to dcMS, and were selected in the corresponding AED. The constant kinetic beam-like Cu energy was chosen as the mean kinetic energy of the SRIM AED propagated through 10 cm at 0.7 Pa. Figure 3 shows the different AEDs and IEDs used in this study. The Embedded Atom Method was chosen to describe Cu, Fe, Cr, Ni, and Mo interactions [18, 19]. Cross interactions use the Johnson mixing rule [20].

IV. SIMULATION RESULTS

Figure 4 shows the resulting deposited films with different initial conditions, mimicking the different deposition processes, while Table I summarizes the properties of the simulated




FIG. 4: Snapshots of the simulated films after 40 ns. (a) Cu beam like at $\mathcal{E}_n = 1.45$ eV, (b) thermal evaporation, (c) dcMS, (d) HIPIMS 90% Cu-10% Cu⁺, (e) bipolar HIPIMS +180 V 90% Cu-10% Cu⁺, (f) HIPIMS 50% Cu-50% Cu⁺, and (g) bipolar HIPIMS +180 V 50% Cu-50% Cu⁺. The location indicated as $z = 0$ is the initial substrate surface. Color code: cyan Cu, yellow Cr, silver Fe, red Mo, blue Ni.

films. The more aggressive deposition condition, bipolar HiPIMS, results in high interface mixing and a low Cu content, suggesting Cu⁺ sputtering of the depositing film, since the acceleration voltage was 180 V. This was not visible in the 10% Cu⁺ conditions owing to the low Cu⁺ ion flux. The atomic structures of the films were calculated using the Polyhedral Template Matching method [21] available in the OVITO software [22]. The highest structural film quality (60% fcc) was achieved by the monoenergetic neutral beam with a kinetic energy corresponding to the dcMS mean kinetic energy (1.45 eV) 10 cm away from the target at 0.7 Pa. However, this condition is challenging to reproduce experimentally. The next highest crystallinity was obtained for bipolar HiPIMS with 10% Cu⁺, also providing a non-negligible mixing interface that is expected to improve film adhesion (Figure 4 (e)). Regular HiPIMS without a secondary positive pulse showed a similar film quality, but the interface mixing was reduced (Figure 4 (d)). Both have high sticking coefficients. Thermally evaporated and dcMS-deposited films exhibited similar film quality (50% fcc), but thermal evaporation showed a sticking coefficient that was 13% lower. The high ion rate in bipolar HiPIMS allows

TABLE I: The Cu film properties derived from the simulated films.

	Cu Sticking coefficient	Substrate erosion rate (%)	Interface height (nm)	Film structure (% fcc)	RMS roughness ^a (nm)
Monoenergetic Cu atom beam	0.98	< 0.01	0	60	1.45
Thermal evaporation	0.76	0	0	50	0.56
dcMS	0.86	0.3	0.5	48	0.57
HiPIMS 10% Cu ⁺	0.91	0.01	0.3	54	0.59
Bipolar +180 V HiPIMS 10% Cu ⁺	0.79	0.5	1.5	57	0.56
HiPIMS 50% Cu ⁺	0.94	0	0.5	42	0.53
Bipolar +180 V HiPIMS 50% Cu ⁺	0.42	1	5	8	0.23

^a Root mean square (RMS) roughness $R = \frac{1}{N} \sqrt{\sum (|z^2 - \langle z \rangle|^2)}$

for large layer mixing, but at the expense of low Cu sticking owing to film self-sputtering [23]. Additionally, it exhibited the largest substrate erosion rate (1%), whereas it was marginal for all the other processes. The rms roughness, reported in Table I, is highest for constant energy beam deposition, while regular HiPIMS with 50% Cu-50% Cu⁺ and bipolar HiPIMS with 180 V positive pulse and 10% Cu⁺, the lowest roughness. Regular HiPIMS with 90% Cu-10% Cu⁺ exhibit only slightly higher roughness than thermal evaporation and dcMS deposition. The most aggressive (+180 V bipolar HiPIMS with 50% Cu⁺) leads to a very low roughness but with almost no film growth due to self-sputtering. So it seems that bipolar HiPIMS with low ion content reduces roughness. So for regular HiPIMS, to reduce roughness, it is preferable to have higher ion flux, while with bipolar HiPIMS low ion flux and high positive bias is preferred. Note that the simulated films are around 3 nm thick. Experimental rms surface roughness values for HiPIMS deposited copper films, determined by atomic force microscope (AFM), are in the range 3.6 – 6.4 nm [24] and 1.3 – 3.9 nm [25], depending on surface bias, and 1.8 – 5.8 nm, depending on pulse width [26]. For dc magnetron sputter deposition values of 11 nm have been reported [26]. All the experimentally deposited films have thickness above 120 nm. The difference in the rms roughness values between experiments and MD simulations is due to thickness difference.

Atomic stress is an important property for comparing films deposited by the different processes [27, 28]. The calculated atomic virial stress [29] is expressed as:

$$\sigma_i = -m_i \frac{d}{dt} \vec{u}_i \times \frac{d}{dt} \vec{u}_i + \frac{1}{2} \sum_{j \neq i} \vec{r}_{ij} \times \vec{f}_{ij} \quad (2)$$

where, i and j are atom indices and \vec{f}_{ij} is the interatomic force between atoms j and i . The summation is over all neighboring atoms within the force cutoff, m_i is the mass of atom i , \vec{u}_i is the displacement vector of atom i relative to a reference position, $\vec{r}_{ij} = \vec{r}_j - \vec{r}_i$, and \times is the tensor product of the two vectors.




FIG. 5: Atomic virial stress in the films deposited via the various PVD processes. (a) Cu beam like at $\mathcal{E}_n = 1.45$ eV, (b) thermal evaporation, (c) dcMS, (d) HIPIMS 90% Cu-10% Cu^+ , (e) bipolar HIPIMS +180 V 90% Cu-10% Cu^+ , (f) HIPIMS 50% Cu-50% Cu^+ , and (g) bipolar HIPIMS +180 V 50% Cu-50% Cu^+ . The substrate atoms have been removed for clarity.

In Figure 5 the stress magnitude of each atom (represented by a sphere) is demonstrated by the colour map for the films drawn in Figure 4. The substrate has been removed for clarity. The dcMS deposited film (Figure 5 (c)) exhibits the lowest stress while the highest stress is obtained for the +180 V bipolar HiPIMS deposited film with 50% Cu^+ (Figure 5 (g)).

The beam-like deposition (Figure 5 (a)) did not display a high stress, but the roughness was the highest. The thermal evaporation film exhibits low stress (Figure 5 (b)). The three HiPIMS deposited films shown in Figure 5 (d), (e) and (f), provide reasonably low stress

compared to the dcMS deposited film. It should be noted that more stressed atoms are present at the interface with the substrate. The bipolar +180 V 50% Cu⁺ film (Figure 5 (e)) shows less stress in the inner film than the other HiPIMS deposited films. This means that bipolar HiPIMS can provide a relaxed film. This has to be linked to the highest degree of crystal ordering, as shown in Table 1, where the fcc fraction reached 57%.

V. SUMMARY

In summary, molecular dynamics simulations of various PVD processes can be handled and differentiated using the corresponding AEDs and IEDs of sputtered atoms and ions. It is possible to use the experimental IEDs obtained by energy-resolved mass spectrometry. This allows for a better account of the process characteristics. In the present case of Cu deposition, bipolar +180 V HiPIMS with 10% Cu⁺ ions exhibited the best film properties in terms of crystallinity and atomic stress among the PVD processes investigated.

Acknowledgments

Data Availability Statement Research data supporting this publication are available from the author on reasonable request.

Conflict of interest The authors declare that they have no affiliations with or involvement in any organization or entity with any financial interest in the subject matter or materials discussed in this manuscript.

-
- [1] L. Xie, P. Brault, J.-M. Bauchire, A.-L. Thomann, and L. Bedra, *J. Phys. D: Appl. Phys.* **47**, 224004 (2014).
 - [2] E. C. Neyts and P. Brault, *Plasma Process. Polym.* **14**, 1600145 (2017).
 - [3] P. Brault, A.-L. Thomann, and M. Cavarroc, *Eur. Phys. J. D* **77**, 19 (2023).
 - [4] P. Brault, *Reviews of Modern Plasma Physics* **8**, 1 (2024).
 - [5] J. T. Gudmundsson, A. Anders, and A. von Keudell, *Plasma Sources Sci. Technol.* **31**, 083001 (2022).
 - [6] J. T. Gudmundsson, *Plasma Sources Sci. Technol.* **29**, 113001 (2020).

- [7] J. T. Gudmundsson, N. Brenning, D. Lundin, and U. Helmersson, *J. Vac. Sci. Technol. A* **30**, 030801 (2012).
- [8] J. Fischer, M. Renner, J. T. Gudmundsson, M. Rudolph, H. Hajihoseini, N. Brenning, and D. Lundin, *Plasma Sources Sci. Technol.* **32**, 125006 (2023).
- [9] J. Bohlmark, M. Lattemann, J. T. Gudmundsson, A. P. Ehiasarian, Y. A. Gonzalvo, N. Brenning, and U. Helmersson, *Thin Solid Films* **515**, 1522 (2006).
- [10] J. Keraudy, R. P. B. Viloan, M. A. Raadu, N. Brenning, D. Lundin, and U. Helmersson, *Surf. Coat. Technol.* **359**, 433 (2019).
- [11] M. Michiels, A. Hemberg, T. Godfroid, O. Douheret, J. L. Colaux, P. Moskovkin, S. Lucas, A. Caillard, A. L. Thomann, P. Laha, H. Terry, M. Voué, A. Panepinto, R. Snyders, and S. Konstantinidis, *J. Phys. D: Appl. Phys.* **54**, 415202 (2021).
- [12] F. Walk, R. Valizadeh, and J. W. Bradley, *Plasma Sources Science and Technology* **31**, 065002 (2022).
- [13] M. Zanaška, D. Lundin, N. Brenning, H. Du, P. Dvořák, P. Vašina, and U. Helmersson, *Plasma Sources Science and Technology* **31**, 025007 (2022).
- [14] M. Kateb, H. Hajihoseini, J. T. Gudmundsson, and S. Ingvarsson, *J. Vac. Sci. Technol. A* **37**, 031306 (2019).
- [15] M. Kateb, J. T. Gudmundsson, P. Brault, A. Manolescu, and S. Ingvarsson, *Surf. Coat. Technol.* **426**, 127726 (2021).
- [16] M. Kateb, J. T. Gudmundsson, and S. Ingvarsson, *J. Vac. Sci. Technol. A* **38**, 043006 (2020).
- [17] J. P. Biersack and W. Eckstein, *Appl. Phys. A* **34**, 73 (1984).
- [18] M. S. Daw and M. I. Baskes, *Phys. Rev. B* **29**, 6443 (1984).
- [19] M. S. Daw, S. M. Foiles, and M. I. Baskes, *Materials Science Reports* **9**, 251 (1993).
- [20] R. A. Johnson, *Phys. Rev. B* **39**, 12554 (1989).
- [21] P. M. Larsen, S. Schmidt, and J. Schiøtz, *Model. Simul. Mater. Sci. Eng.* **24**, 055007 (2016).
- [22] A. Stukowski, *Model. Simul. Mater. Sci. Eng.* **18**, 015012 (2010).
- [23] Z.-H. Hong, S.-F. Hwang, and T.-H. Fang, *Computational Materials Science* **41**, 70 (2007).
- [24] B. H. Wu, J. Wu, F. Jiang, D. L. Ma, C. Z. Chen, H. Sun, Y. X. Leng, and N. Huang, *Vacuum* **135**, 93 (2017).
- [25] F. Cemin, G. Abadias, T. Minea, C. Furgeaud, F. Brisset, D. Solas, and D. Lundin, *Acta Materialia* **141**, 120 (2017).

- [26] X. Liu, H. Bai, Y. Ren, J. Li, and X. Liu, [Materials](#) **17**, 2342 (2024).
- [27] Z.-H. Hong, S.-F. Hwang, and T.-H. Fang, [Computational Materials Science](#) **48**, 520 (2010).
- [28] H. Windischmann, [Critical Reviews in Solid State and Materials Sciences](#) **17**, 547 (1992).
- [29] S. Shen and S. N. Atluri, [Computer Modeling in Engineering & Sciences](#) **6**, 91 (2004).