



## Polar textures in multiferroic BiFeO<sub>3</sub>-based superlattices

Razvan Burcea, Oana Condurache, Mouna Khiari, Maxime Vallet, Stéphane Roux, Pascale Ruello, Brahim Dkhil, Houssny Bouyanfif

### ► To cite this version:

Razvan Burcea, Oana Condurache, Mouna Khiari, Maxime Vallet, Stéphane Roux, et al.. Polar textures in multiferroic BiFeO<sub>3</sub>-based superlattices. EMC 2024, Aug 2024, Copenhague, Denmark. hal-04684955

HAL Id: hal-04684955

<https://hal.science/hal-04684955v1>

Submitted on 3 Sep 2024


**HAL** is a multi-disciplinary open access archive for the deposit and dissemination of scientific research documents, whether they are published or not. The documents may come from teaching and research institutions in France or abroad, or from public or private research centers.

L'archive ouverte pluridisciplinaire **HAL**, est destinée au dépôt et à la diffusion de documents scientifiques de niveau recherche, publiés ou non, émanant des établissements d'enseignement et de recherche français ou étrangers, des laboratoires publics ou privés.

# Polar textures in multiferroic $\text{BiFeO}_3$ -based superlattices

Razvan Burcea<sup>1</sup>, Oana Condurache<sup>1</sup>, Mouna Khiari<sup>2</sup>, Maxime Vallet<sup>1,3</sup>, Stéphane Roux<sup>3</sup>, Pascale Ruello<sup>4</sup>, Brahim Dkhil<sup>1</sup>, Houssny Bouyanif<sup>2</sup>


<sup>1</sup> Université Paris-Saclay, CentraleSupélec, SPMS, Gif-sur-Yvette, France    <sup>3</sup> Université de Paris-Saclay, ENS Paris-Saclay, LMPS, Gif-sur-Yvette, France  
<sup>2</sup> LPMC EA2081, Université de Picardie Jules Verne, Amiens, France    <sup>4</sup> IMMN, Le Mans Université, Le Mans, France



CentraleSupélec


## Context and motivation

- Recently, ferroelectric-based superlattices (SLs) have emerged and led to the discovery of exotic polar textures such as **skyrmionic states** or **vortices** in  $\text{PbTiO}_3/\text{SrTiO}_3$  SLs [1,2]. Thus, SLs offer a unique and promising new platform to study these novel polar states which result mainly from the effects of strain, confinement, and competing interactions between the degrees of freedom (polar displacements, oxygen tilts) of these perovskite layers.


Vortices polar states observed in  $\text{PbTiO}_3/\text{SrTiO}_3$  SLs [2].

- Previous work on  $\text{BiFeO}_3/\text{LaFeO}_3$  SLs [3]: coexistence of  $\text{PbZrO}_3$ -like (red squares) and  $\text{Pnma}$ -like (blue circles) polar states depending on the BFO thickness in the period of SLs.

- Objective:** control the polar states of the BFO by adjusting various parameters: **thickness** of the bilayer ( $\Lambda$ ), type of **substrate**, type of **intermediate layer**, etc.

SAED of BFO/LFO SL obtained for  $\Lambda = 150 \text{ \AA}$  [3].

## SL system and growth method




- SLs grown by PLD on (001)  $\text{SrTiO}_3$  and  $\text{DyScO}_3$  single crystals.
- $\text{LaFeO}_3$  and  $\text{NdFeO}_3$  used as intermediate layers.
- Various periods  $\Lambda$  (3, 6, 12 and 20 nm) and same BFO/LFO (NFO) thickness ratio.
- Deposition characteristics: 0.5 mbar of  $\text{pO}_2$  at 740°C, 6 Hz repetition rate using a KrF laser (248 nm).

## Characterization methods

- Cross-section TEM samples prepared on an FEI Thermofisher Helios Nanolab 660.
- ABF and HAADF STEM images acquired on FEI Titan 3 G2 80-300 microscope (Cs probe corrector).
- Analysis of atomic displacements by Atomap [4,5] and a “render-and-compare” (RAC) method based on Principle Component Analysis (PCA).




## Influence of $\Lambda$




- Depending on  $\Lambda$ , the BFO polar states can be switched to antiferro-like (step-like).

## Substrate influence




- Antiferro-like polar states are still visible using anisotropic  $\text{DyScO}_3$  as a substrate.
- The BFO appears to be more ordered, with a single variant of polar step-like states.

## LFO vs NFO



- Antiferro-like polar states are observed regardless of the intermediate layer used.

## RAC vs ATOMAP



- In this example, RAC shows a more complex polar distribution (4 different displacements).

## Conclusion

- BFO exhibits antiferro-like polar states regardless of the substrate or intermediate layer used, provided that  $\Lambda$  is sufficiently high (> 3 nm).
- The use of  $\text{DyScO}_3$  as a substrate seems more appropriate for controlling the polar states of the BFO.

- RAC can be considered as a complementary analysis tool for understanding the complexity of polar states.

- Understand the crystalline orientation relationships between the BFO and the intermediate layers (observation of O sites).
- Continue to develop and optimize the Matlab code for the RAC method (analysis of oxygen sites, etc).

## References

- [1] Das, S. et al. *Nature* 568, 368–372 (2019).  
[2] Yadav, A. et al. *Nature* 530, 198–201 (2016).  
[3] B. Carcan, H. Bouyanif, et al. *J. Appl. Phys.* 124(4), 044105 (2018).  
[4] Nord, M. et al. *Adv Struct Chem Imag* 3, 9 (2017).  
[5] E. O'Connell, M. Hennessy, and E. Moynihan, “PinkShnack/TEMUL: Version 0.1.3,” (2021) 10.5281/zenodo.4543963.

Contact: razvan.burcea@centralesupelec.fr

